Chemical Science

EDGE ARTICLE



Cite this: Chem. Sci., 2017, 8, 165

Received 18th June 2016 Accepted 4th August 2016

DOI: 10.1039/c6sc02668k

www.rsc.org/chemicalscience

Copper-catalyzed dehydrogenative borylation of terminal alkynes with pinacolborane[†]

Erik A. Romero, Rodolphe Jazzar and Guy Bertrand*

LCuOTf complexes [L = cyclic (alkyl)(amino)carbenes (CAACs) or N-heterocyclic carbenes (NHCs)] selectively promote the dehydrogenative borylation of C(sp)–H bonds at room temperature. It is shown that σ,π -bis(copper) acetylide and copper hydride complexes are the key catalytic species.

H-H

LCuOTf + Cu

С

Popularized by the Suzuki–Miyaura reaction, organoboronic esters and acids are now regarded as key building blocks for compounds with applications ranging from material to life sciences. Consequently, numerous methodologies have been developed to access these valuable substrates.¹ Following ground-breaking reports by Hartwig *et al.*,² and Smith *et al.*,³ the catalytic dehydrogenative borylation of $C(sp^3)$ –H bonds and $C(sp^2)$ –H bonds are now well documented.⁴ In contrast, for C(sp)–H bonds there are only a few reports by Ozerov *et al.*⁵ using iridium and palladium complexes supported by pincer ligands, and one by Tsuchimoto *et al.*⁶ with zinc triflate, which is only effective with 1,8-naphthalenediaminatoborane as the boron partner. One of the difficulties of the dehydrogenative borylation of terminal alkynes is the competing hydroboration of the triple bond, which affords alkenyl boronic esters.⁷

We recently reported⁸ on the role of the X ligand in the mechanism of the LCuX catalyzed azide-alkyne cycloaddition (CuAAC reaction) [L = cyclic (alkyl)(amino)carbene].^{9,10} Herein we show that these results allow for the rational design of copper catalysts that selectively promote the dehydrogenative borylation of terminal alkynes with pinacolborane.

In the above mentioned study, we found that in the presence of triethylamine, LCuOTf reacts with terminal alkynes to give the catalytically active σ,π -bis(copper) acetylides \mathbf{A} ,^{8,11} along with ammonium triflate (Scheme 1). We hypothesized that in dinuclear complexes \mathbf{A} , the triple bond is protected which should prevent the classical hydroboration reaction leading to alkenyl boronic esters. Instead, the highly polarized coppercarbon bond could undergo a σ -bond metathesis with pinacolborane (**TS**) to afford the desired alkynyl boronic ester \mathbf{B} , as well as the copper hydride \mathbf{C} . The latter should react with triethylammonium triflate to regenerate LCuOTf and triethylamine with the elimination of dihydrogen.

Scheme 1 Hypothetical mechanism for the LCuOTf induced dehydrogenative borylation of terminal alkynes.

Et₃N

L Cu

OTf

Et₃NH.OTf

We first checked that in the absence of catalyst no reaction occurred between *p*-tolylacetylene **1a** and pinacolborane in C_6D_6 at room temperature for 2 hours (Table 1, entry 1). In the presence of 1 mol% of **L**₁CuOTf, no significant reaction occurred either because of the difficulty of the triflate to deprotonate the alkyne⁸ (entry 2). In order to promote the deprotonation of the alkyne, 1 mol% of Et₃N was added which resulted in immediate hydrogen evolution (as characterized by a singlet at 4.47 ppm in ¹H NMR). The major product was the alkynyl boronic ester **B**₁ (48%), but the alkenyl boronic ester **D**₁ (11%), and the styrene derivative **E**₁ (7%) were also formed (entry 3).

Note that no reaction occurred under ligand-free conditions (entry 4). Encouraged by these preliminary results, we further optimized the dehydrogenative borylation leading to B_1 . We found that a two-fold excess of Et_3N with respect to (CAAC) CuOTf was beneficial (entry 5). By screening solvents






L-Cu

TfO

UCSD-CNRS Joint Research Chemistry Laboratory (UMI 3555), Department of Chemistry and Biochemistry, University of California San Diego, La Jolla, CA 92093-0358, USA. E-mail: guybertrand@ucsd.edu

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/c6sc02668k

Table 1 Optimization of the dehydrogenative borylation reaction^a



Entry	Cat. (mol%)	Base (mol%)	Solvent	Conc. (M)	$\mathbf{1a}^{b}\left(\% ight)$	$\mathbf{B_{1}}^{b}(\%)$	$\mathbf{D_1}^b$ (%)	$\mathbf{E_{1}}^{b}(\%)$
1	_	_	C_6D_6	1.4	100	0	0	0
2	L_1 CuOTf (1)	—	C_6D_6	1.4	86	0	6	6
3	L_1 CuOTf (1)	$Et_3N(1)$	C_6D_6	1.4	14	48	11	7
4	CuOTf	$Et_3N(1)$	C_6D_6	1.4	100	0	0	0
5	L_1 CuOTf (1)	$Et_3N(2)$	C_6D_6	1.4	1	70	14	12
6	$L_1CuOTf(1)$	$Et_3N(2)$	CD_2Cl_2	1.4	12	42	6	26
7	L_1 CuOTf (1)	$Et_3N(2)$	THF-d ₈	1.4	5	64	12	17
8	$L_1CuOTf(1)$	$Et_3N(2)$	CD_3CN	1.4	18	38	0	6
9	L_1 CuOTf (1)	i PrNH ₂ (2)	C_6D_6	1.4	67	5	12	10
10	L_1 CuOTf (1)	$^{i}Pr_{2}NH(2)$	C_6D_6	1.4	47	11	13	7
11	$L_1CuOTf(1)$	$^{i}Pr_{2}NEt$ (2)	C_6D_6	1.4	10	28	45	3
12	L_1 CuOTf (1)	$BnNEt_2(2)$	C_6D_6	1.4	14	53	8	7
13	$L_1CuOTf(1)$	DABCO (2)	C_6D_6	1.4	18	60	1	7
14	L_1 CuOTf (0.25)	$Et_{3}N(0.5)$	C_6D_6	1.4	37	36	15	6
15	$L_1CuOTf(0.5)$	$Et_3N(1)$	C_6D_6	1.4	20	54	15	9
16	L_1 CuOTf (2.5)	$Et_3N(5)$	C_6D_6	1.4	4	83	4	7
17	L_1 CuOTf (2.5)	$Et_3N(5)$	C_6D_6	0.1	1	98	0	1
18	$L_2CuOTf(2.5)$	$Et_3N(5)$	C_6D_6	0.1	0	96	0	4
19	L_3 CuOTf (2.5)	$Et_3N(5)$	C_6D_6	0.1	0	92	0	8


^{*a*} Reactions were carried out in a test tube for 2 h at RT under an argon atmosphere using a 1 : 1 mixture (0.69 mmol) of *p*-tolylacetylene and pinacolborane. ^{*b*} Measured by NMR using 1,4-dioxane as an internal standard.

(Entries 5–8) and base additives (Entries 9–13), we identified benzene and Et_3N as being most appropriate for the reaction. When we increased the catalyst loading to 2.5 mol% (Entries 14–16), and decreased the concentration of the solution from 1.4 to 0.1 mol L⁻¹ (entry 17) there was quantitative formation of the desired alkynyl boronic ester **B**₁ with excellent selectivity within two hours at room temperature. Notably, substitution of ligand L₁ for the more bulky menthyl CAAC L₂ or even IPr-NHC¹² L₃ gave comparable results.

The scope of the dehydrogenative borylation reaction was then studied at room temperature in a benzene solution (0.1 M) using a stoichiometric mixture of alkyne and borane (1.82 mmol), 5 mol% of Et₃N and 2.5 mol% of L₁CuOTf (Scheme 2). This methodology is readily applicable to a broad range of terminal alkynes bearing functionalities such as OMe, CN, F, Cl, TMS and CO₂Me. It is worth noting that electron-rich terminal alkynes require longer reaction times (12 h instead of 2 h) (B₁₁₋₁₅). Alkynyl boronic esters B₁₋₁₅ were isolated in good to excellent yields *via* filtration through a short plug of dry neutral alumina using pentane as the eluent. This straightforward protocol allows for gram-scale synthesis, as shown for B₃.

With these results in hand, we performed a set of experiments in order to verify our mechanistic hypothesis. When the 2.5 mol% mononuclear complex **F** was used, with or without Et_3N , no traces of the dehydrogenative borylation product B_1 were observed, instead the hydroboration product D_1 was quantitatively formed (Fig. 1 and Scheme 3) (see also the kinetic profile in the ESI†). In marked contrast, when 2.5 mol% $Et_3NH \cdot OTf$ was added as a proton source, we observed the rapid formation of B_1 , and the kinetic profile was comparable with those obtained using our standard catalytic conditions (LCuOTf/Et₃N) or the bis(copper) acetylide **A**. Since we already proved that LCuOTf/ Et_3N reacts with terminal alkynes to afford the dinuclear species A,⁸ we verified that similarly complex **F** reacts with $Et_3NH \cdot OTf$ to give **A**. These experiments as a whole strongly suggest that the dinuclear complex **A** is pivotal in the dehydrogenative process.

The other important species in our postulated mechanism is the copper hydride **C**, a type of complex that has been proposed to play a major role in a number of catalytic transformations.¹³ While there is still no report of a monomeric mono-ligated Cu hydride,¹⁴ a range of dimeric species have been described by us and others.¹⁵ An indication of **L**₁CuH formation in this process is the observation of a small amount of styrene derivatives **E** in our experiments (Table 1). Indeed, copper hydrides are known to undergo 1,2-addition across alkynes to generate copper vinyl complexes, which by protonolysis give alkenes.¹⁵ Consistent with this hypothesis,



Scheme 2 Scope of the dehydrogenative borylation of terminal alkynes. [a] Reaction time 2 h. [b] Reaction time 12 h.







Fig. 1 Kinetic profiles of the formation of B_1 using various catalytic systems. [a] Reactions were carried out in a J-Young NMR tube at RT under an argon atmosphere using a 1 : 1 mixture (0.45 mmol) of *p*-tolylacetylene and pinacolborane in 1 mL of C_6D_6 . [b] 2.5 mol% of F and 5 mol% Et₃N; no trace of B_1 was observed, instead D_1 was obtained quantitatively. [c] 2.5 mol% of F, Et₃N and Et₃NH·OTf. [d] 2.5 mol% of A, 3.75 mol% Et₃N and 1.25 mol% Et₃NH·OTf. [e] 2.5 mol% of L₁CuOTf and 5 mol% of Et₃N.

a catalytic experiment using deuterium labelled phenyl acetylene under our optimized conditions, but in CD_2Cl_2 instead of C_6D_6 (Table 1, entry 6), afforded B_3 and Styrene-D (75% D-incorporation) (Scheme 4).









Conclusions

In summary, we have disclosed the first example of a highly selective dehydrogenative borylation of terminal alkynes with pinacolborane, using an inexpensive metal center supported by readily accessible ligands.¹⁶ Preliminary mechanistic studies suggest the pivotal role of a σ , π -bis(copper) acetylide **A** and a copper hydride **C**.

Acknowledgements

The authors gratefully acknowledge financial support from the DOE (DE-FG02-13ER16370).

Notes and references

- 1 J. F. Hartwig, *Acc. Chem. Res.*, 2012, **45**, 864; A. J. Lennox and G. C. Lloyd-Jones, *Chem. Soc. Rev.*, 2014, **43**, 412.
- 2 H. Chen, S. Schlecht, T. C. Semple and J. F. Hartwig, *Science*, 2000, **287**, 1995.
- 3 J. Y. Cho, M. K. Tse, D. Holmes, R. E. Maleczka Jr. and M. R. Smith III, *Science*, 2002, **295**, 305.
- 4 J. F. Hartwig, *Chem. Soc. Rev.*, 2011, 40, 1992; I. A. Mkhalid,
 J. H. Barnard, T. B. Marder, J. M. Murphy and
 J. F. Hartwig, *Chem. Rev.*, 2010, 110, 890.
- 5 C. I. Lee, J. Zhou and O. V. Ozerov, J. Am. Chem. Soc., 2013, 135, 3560; C. I. Lee, N. A. Hirscher, J. Zhou, N. Bhuvanesh and O. V. Ozerov, Organometallics, 2015, 34, 3099; C. I. Lee, W. C. Shih, J. Zhou, J. H. Reibenspies and O. V. Ozerov,

Angew. Chem., Int. Ed., 2015, 54, 14003; C. I. Lee, J. C. DeMott, C. J. Pell, A. Christopher, J. Zhou, N. Bhuvanesh and O. V. Ozerov, Chem. Sci., 2015, 6, 6572; C. J. Pell and O. V. Ozerov, Inorg. Chem. Front., 2015, 2, 720.

- 6 T. Tsuchimoto, H. Utsugi, T. Sugiura and S. Horio, Adv. Synth. Catal., 2015, 357, 77.
- 7 R. Barbeyron, E. Benedetti, J. Cossy, J. J. Vasseur, S. Arseniyadis and M. Smietana, *Tetrahedron*, 2014, **70**, 8431.
- 8 L. Jin, D. R. Tolentino, M. Melaimi and G. Bertrand, *Sci. Adv.*, 2015, 1, e1500304; L. Jin, E. A. Romero, M. Melaimi and G. Bertrand, *J. Am. Chem. Soc.*, 2015, 137, 15696.
- 9 For reviews on CAACs, see: M. Melaimi, M. Soleilhavoup and G. Bertrand, *Angew. Chem., Int. Ed.*, 2010, 49, 8810; D. Martin, M. Melaimi, M. Soleilhavoup and G. Bertrand, *Organometallics*, 2011, 30, 5304; M. Soleilhavoup and G. Bertrand, *Acc. Chem. Res.*, 2015, 48, 256.
- 10 For the synthesis of CAACs, see: V. Lavallo, Y. Canac, C. Präsang, B. Donnadieu and G. Bertrand, Angew. Chem., Int. Ed., 2005, 44, 5705; R. Jazzar, R. D. Dewhurst, J. B. Bourg, B. Donnadieu, Y. Canac and G. Bertrand, Angew. Chem., Int. Ed., 2007, 46, 2899; R. Jazzar, J. B. Bourg, R. D. Dewhurst, B. Donnadieu and G. Bertrand, J. Org. Chem., 2007, 72, 3492.
- 11 For other mechanistic studies, involving the transient formation of σ,π -bis(copper) acetylides, see: V. O. Rodionov, V. V. Fokin and M. G. Finn, *Angew. Chem., Int. Ed.*, 2005, 44, 2210; F. Himo, T. Lovell, R. Hilgraf, V. V. Rostovtsev, L. Noodleman, K. B. Sharpless and V. V. Fokin, *J. Am. Chem. Soc.*, 2005, **127**, 210; M. Ahlquist and V. V. Fokin, *Organometallics*, 2007, **26**, 4389; B. F. Straub, *Chem. Commun.*, 2007, 3868; C. Nolte,

P. Mayer and B. F. Straub, *Angew. Chem., Int. Ed.*, 2007, 46, 2101;
A. Makarem, R. Berg, F. Rominger and B. F. Straub, *Angew. Chem., Int. Ed.*, 2015, 54, 7431;
B. T. Worrell, J. A. Malik and V. V. Fokin, *Science*, 2013, 340, 457.

- 12 A. J. Arduengo, R. Krafczyk and R. Schmutzler, *Tetrahedron*, 1999, 55, 14523.
- 13 For reviews, see: J. D. Egbert, C. S. J. Cazin and S. P. Nolan, *Catal. Sci. Technol.*, 2013, 3, 912; C. Deutsch, N. Krause and B. H. Lipshutz, *Chem. Rev.*, 2008, 108, 2916; B. H. Lipshutz, *Synlett*, 2009, 509.
- 14 For an example of diligated copper hydride, see: B. H. Lipshutz and B. A. Frieman, *Angew. Chem., Int. Ed.*, 2005, **44**, 6345.
- 15 G. D. Frey, B. Donnadieu, M. Soleilhavoup and G. Bertrand, Chem.-Asian J., 2011, 6, 402; N. Cox, H. Dang, A. M. Whittaker and G. Lalic, Tetrahedron, 2014, 70, 4219; M. R. Uehling, R. P. Rucker and G. Lalic, J. Am. Chem. Soc., 2014, 136, 8799; A. M. Suess, M. R. Uehling, W. Kaminsky and G. Lalic, J. Am. Chem. Soc., 2015, 137, 7747; N. P. Mankad, D. S. Laitar and J. P. Sadighi, Organometallics, 2004, 23, 3369; K. Semba, T. Fujihara, T. H. Xu, J. Terao and Y. Tsuji, Adv. Synth. Catal., 2012, 354, 1542; A. J. Jordan, C. M. Wyss, J. Bacsa and J. P. Sadighi, Organometallics, 2016, 35, 613; A. M. Suess and G. Lalic, Synlett, 2016, 27, 1165; L. R. Collins, I. M. Riddlestone, M. F. Mahon and M. K. Whittlesey, Chem.-Eur. J., 2015, 21, 14075; C. M. Wyss, B. K. Tate, J. Bacsa, T. G. Gray and J. P. Sadighi, Angew. Chem., Int. Ed., 2013, 52, 12920.
- 16 CAAC and NHC precursors are commercially available.