


Cite this: *RSC Adv.*, 2024, 14, 2264

Promotion of SO₂ resistance of Ce–La/TiO₂ denitrification catalysts by V doping

Yang Liu,^a Na Wang,^{ID}*^b Huidong Xie,^c Yepeng Sun,^a Kaiyue Yang,^a Liang Zhang,^a Chang Yang^c and Chengmin Ge^d

Conventional cerium-based denitrification catalysts show good catalytic activity at moderate and high temperatures, but their denitrification performance may be decreased due to poisoning by SO₂ in the flue gas. In this paper, V was introduced into Ce–La/TiO₂ catalysts by a ball-milling method, and the effects of the V content on catalyst denitrification performance and SO₂ resistance were investigated. Fourier-transform diffuse reflectance *in situ* infrared spectroscopy was used to examine the denitrification mechanism and evaluate the catalysts for surface acidity, redox characteristics, and SO₂ adsorption. After introducing V, Brønsted acids played the dominant role in the catalytic reaction by increasing the number of acidic sites on the catalyst surface, adsorbing NH₃ to participate in the reaction, and improving the sulfur resistance by inhibiting SO₂ poisoning. The Ce³⁺ and O ratio on the catalyst surface were also enhanced by V doping, which reduced interactions between SO₂ and the primary metal oxide active ingredients. The modified catalyst inhibited the formation of sulfate species on the catalyst surface and prevented the generation of additional nitrate species on the surface, which protected the main active sites. After V doping, the NH₃–SCR reaction on the catalyst surface followed the Langmuir–Hinshelwood mechanism.

Received 19th October 2023
Accepted 10th December 2023

DOI: 10.1039/d3ra07073e

rsc.li/rsc-advances

1 Introduction

NO_x is a major atmospheric pollutant whose emissions cause acid rain, photochemical smog, and ozone layer depletion.¹ Selective catalytic reduction (SCR) has a wide range of denitrification efficiencies, does not produce secondary contamination due to NH₃ escape, and is widely used in various plants and municipal waste facilities.² Cerium-based catalysts are one of the commonly used catalysts in SCR, which is due to the fact that Ce atoms contain a special arrangement of electrons outside the nucleus and have excellent oxidizing properties and oxygen storage capacity. CeO₂ can be converted from Ce⁴⁺ to Ce³⁺ when cerium ions generate oxygen vacancies,³ giving the catalyst excellent redox properties and thermal stability. Cerium promotes the conversion of nitrate species and ammonia species, which facilitates the conversion of NH₃ and NO to reactive intermediates on the catalyst surface, thus promoting the NH₃–SCR reaction.

Usually, the flue gas in coal-fired boilers contains SO₂, which inevitably poisons the catalyst and reduces its denitrification performance. The reasons for SO₂ poisoning can be classified

into three categories: (1) the competitive adsorption of SO₂ with reactants inhibits the formation of reactive intermediates; (2) the reaction of SO₂ with NH₃ to generate (NH₄)₂SO₄ and NH₄HSO₄, which covers active sites on the catalyst surface and reduces the specific surface area of the catalyst; (3) metal active sites are sulfated by SO₂ to create metal sulfates, which results in the loss of the active components and results in irreversible deactivation. For Ce-based catalysts, SO₂ can be adsorbed and oxidized to SO₃ by CeO₂ to generate Ce(SO₄)₂ or Ce₂(SO₄)₃ or react with NH₃ to form stable (NH₄)₂SO₄ or NH₄HSO₄, the NO conversion of CeO₂/TiO₂ catalysts was close to 100% above 300 °C and remained stable for 12 h. However, the value decreased significantly after 12 h, which was below 40% after 48 h.⁴ For Mn-based catalysts, the NO conversion of fresh samples of MnO₂-based catalysts was 100% at 130–150 °C. After SO₂ poisoning, the NO conversion decreased sharply from 100% to 53% at 130 °C and did not increase when the reaction temperature was increased to 150 °C.⁵ Ma *et al.*⁶ prepared Cu_{0.02}Fe_{0.2}W_{0.02}TiO_x by doping W to Cu_{0.02}Fe_{0.2}TiO_x catalysts, the NO conversion of which maintained at 100% after passing water and sulfur at 240 °C for 10 h. Jiang *et al.*⁷ prepared Mn–Fe(0.4)–Ce(0.4)/ACN catalysts, which showed a NO_x conversions higher than 95% at 100–250 °C, and remained around 91% at 175 °C for 32 h under 100 ppm SO₂ and 10 vol% H₂O.

Early studies on SO₂ poisoning catalysts mostly concentrated on vanadium-based catalysts. In the temperature range of 180 to 400 °C, Li *et al.*'s⁸ investigation of the distribution of SO₂

^aXi'an University of Science and Technology, Xi'an, 710054, Shaanxi, China

^bShaanxi University of Science and Technology, Xi'an, 710016, Shaanxi, China. E-mail: wangna811221@sust.edu.cn; Fax: +86-29-82202335; Tel: +86-29-82203378

^cXi'an University of Architecture and Technology, Xi'an, 710055, Shaanxi, China

^dShandong Dongyuan New Material Technology Co., 257300, Shandong, China



oxidation products during the NH_3 -SCR process over $\text{V}_2\text{O}_5/\text{TiO}_2$ catalysts discovered that the amount of gaseous SO_3 products increased with temperature in this range. The presence of O_2 in flue gas promoted the oxidation of SO_2 and the formation of gaseous SO_3 on the $\text{V}_2\text{O}_5/\text{TiO}_2$ catalysts. On the catalyst surface, the major pathway for SO_2 oxidation comprises oxidizing SO_2 to generate adsorbed SO_3 , which either desorbs to form gaseous SO_3 or interacts with NH_3 to form sulfate. Sulfite is created when a tiny amount of SO_2 interacts with NH_3 ; this product was then quickly oxidized to $(\text{NH}_4)_2\text{SO}_4$. At 180 °C, the amount of deposition products peaked, while below 230 °C, more NH_4^+ emerged. Additives that also strengthened the water and sulfur resistance of the rare-earth-based catalysts helped them conduct denitrification even better. Many researchers have prepared binary-loaded metal oxide catalysts using transition metals and doping with rare earth elements such as CoO ,⁹ Cr_2O_3 ,¹⁰ and Sm_2O_3 .¹¹ This method boosted the denitrification activity of the original Ce-based catalysts as well as their resistance to water and sulfur.

In this paper, we prepared a Ce-La-V/TiO₂ catalyst *via* a previously reported ball milling method.¹² The effect of the V introduction on the denitrification performance of the catalyst as well as on the water and sulfur resistance was tested. It was found that the NO conversion still maintained 85% after 52 h of water and sulfur feeding. After stopping the water and sulfur,

1.4 and 2.3). In addition, the catalyst was poisoned by passing 300 ppm SO_2 and 5% H_2O on top of a mixture of 500 ppm NO, 500 ppm NH_3 , 5% H_2O and N_2 , which was allowed to stabilize and then reacted continuously for 4 h to obtain a poisoned sample, which was labeled as 10Ce-2La- $x\text{V}/\text{Ti-S}$.

2.2 Catalysts activity test

First, the prepared catalysts were ball-milled and attached to porous cordierite cylinders (commercial grade, ϕ 20 × L 50). After drying in an oven, the catalyst-loaded cordierite cylinders were placed in a quartz tube furnace to test the catalytic activity of the catalyst. The catalyst was loaded with a weight of 1 g. The gas mixture consisted of 500 ppm NO, 500 ppm NH_3 , 300 ppm SO_2 , 5% H_2O , and 3% O_2 , with N_2 as the equilibrium gas. The total gas flow rate was 2500 mL min^{−1} and the corresponding GHSV was 150 000 mL g^{−1} h^{−1}. The flow of all the gases was controlled by a mass flowmeter. NO and NO₂ concentrations at the outlet were monitored in real time using an ECOM flue gas analyzer (Germany). NO conversion, N₂ selectivity and SO₂ conversion were calculated from eqn (1)–(3):

$$\text{NO conversion (\%)} = \frac{[\text{NO}]_{\text{in}} - [\text{NO}]_{\text{out}}}{[\text{NO}]_{\text{in}}} \times 100\% \quad (1)$$

$$\text{N}_2 \text{ selectivity (\%)} = \frac{[\text{NO}]_{\text{in}} + [\text{NH}_3]_{\text{in}} - [\text{NO}_2]_{\text{out}} - 2[\text{N}_2\text{O}]_{\text{out}} - [\text{NO}]_{\text{out}} - [\text{NH}_3]_{\text{out}}}{[\text{NO}]_{\text{in}} + [\text{NH}_3]_{\text{in}} - [\text{NO}]_{\text{out}} - [\text{NH}_3]_{\text{out}}} \times 100\% \quad (2)$$

the NO conversion recovered to 99%. In addition, the mechanism of the resistance to SO_2 toxicity at high temperatures was elucidated using various physicochemical characterization techniques and reaction kinetics analysis.

2 Experimental

2.1 Catalysts preparation

According to the chemical formula of $\text{Ce}_{10}\text{La}_2\text{V}_x\text{Ti}_{88-x}$ (where x is the mass ratio of V_2O_5 per 100 parts of catalyst), cerium carbonate, lanthanum carbonate, ammonium metavanadate and titanium dioxide were added and put in the nylon ball milling jar, appropriate amount of deionized water and zirconia balls were added. The volume of the ball milling jar was 530 mL, the inner diameter was 94.5 mm, the height was 93.5 mm, the weight of zirconia balls was 95 g, and the volume of water was 100 mL. Then the slurry was ball milled in KQM-Z/B planetary ball mill, the rotational speed and time were set (usually 500 rpm, 1 h), and the direction of rotation was changed once per 20 min, separation of the slurry from the zirconia balls at the end of the process, and the slurry was dried in an oven at 105 °C for 12 h. After drying, the slurry was calcined at 500 °C for 4 h to obtain the desired catalysts, and the corresponding catalysts were notated as 10Ce-2La- $x\text{V}/\text{Ti}$ ($x = 0.1, 0.3, 0.6, 0.9$,

$$\text{SO}_2 \text{ conversion (\%)} = \frac{[\text{SO}_2]_{\text{in}} - [\text{SO}_2]_{\text{out}}}{[\text{SO}_2]_{\text{in}}} \times 100\% \quad (3)$$

where the subscript 'in' and 'out' represent the inlet and outlet concentrations of each gas at steady state, respectively.

In order to visualize the differences in the catalytic activity of the samples more intuitively, the tests were conducted at a higher GHSV (150 000 mL g^{−1} h^{−1}), keeping the NO conversion rate lower than 30%, and the surface activation energies of the different catalysts were calculated. Assuming that the NH_3 -SCR catalytic reaction is not controlled by diffusion, the SCR reaction rate normalized by the specific surface area of the catalyst can be calculated according to eqn (4)^{13,14}

$$\text{Rate (mol m}^{-2} \text{ s}^{-1}) = \frac{X_{\text{NO}} \times Q \times C_f}{V_m \times W \times S_{\text{BET}}} \quad (4)$$

where X_{NO} is the NO conversion (%) at different temperatures, Q is the volumetric flow (2500 mL min^{−1}), V_m is the molar volume of gas under standard conditions (22.4 L mol^{−1}), C_f is the fed NO concentration (500 ppm), W is the weight of the catalyst (g), and S_{BET} is the specific surface area of the catalyst (m² g^{−1}).

Turn over frequency (TOF) can be calculated to compare the catalytic rate of different catalysts. Keeping the NO conversion below 30% (to ensure that all catalytically active sites are



operational), the TOF value of NO on the active center Ce is calculated from eqn (5):^{15,16}

$$\text{TOF} = \frac{P_V/RT\alpha}{m_{\text{cat}}\beta_{\text{Ce}}/M_{\text{Ce}}} \quad (5)$$

where P is the standard atmospheric pressure (1.01×10^5 Pa), v is the flow of NO, R is the molar gas constant ($8.314 \text{ J mol}^{-1} \text{ K}^{-1}$), T is the test temperature (K), α is the NO conversion (%), m_{cat} is the weight of the catalyst (g), β_{Ce} is the loading ratio of Ce (%) calculated using XPS data, and M_{Ce} is the molecular weight of cerium (140.1 g mol^{-1}).

2.3 Characterization of catalysts

The physical composition of the samples was examined using a Thermo ARL SCINTAG X'TRA X-ray diffraction analyzer. Cu K- α rays (wavelength 0.154056 nm) were used as its X-ray source, with a tube voltage of 40 kV and a tube current of 40 mA. Sample surface area, pore volume and pore size were measured by N_2 adsorption and desorption using a Biaoode SSA-7300 automatic pore size and surface area analyzer. X-ray photoelectron spectroscopy (XPS) was carried out using a Thermo Scientific K-Alpha electron spectrometer equipped with an Al K α ($h\nu = 1486.6 \text{ eV}$) radiation at an operating voltage of 12 kV and a reference pressure of 3×10^{-7} mbar. Temperature programmed desorption/reduction (TPD/TPR) experiments were carried out on a chemisorption apparatus (Micromeritics, AutoChem II 2920). TG and DSC quantities were measured using a simultaneous thermal analyzer (PerkinElmer STA-8000). N_2 was used as the carrier gas, and the samples were heated up to 100°C at a heating rate of $10^\circ\text{C min}^{-1}$ to pretreat moisture and other impurities on their surface, and then heated up to 800°C at a heating rate of $10^\circ\text{C min}^{-1}$. The *in situ* IR tests were performed on an *in situ* FTIR spectrometer (Tensor 27). The tests were consisted by four parts: NH_3 adsorption, $\text{NO} + \text{O}_2$ adsorption, $\text{NO} + \text{O}_2$ reaction with pre-adsorbed NH_3 and NH_3 reaction with pre-adsorbed $\text{NO} + \text{O}_2$.

3 Results and discussion

3.1 Characterization of catalysts physical properties

3.1.1 XRD. The physical phases present in the catalysts were analyzed by X-ray diffraction. As shown in Fig. 1, all samples contained peaks near 25.2° , 37.7° , 48.0° , 53.9° , and 54.9° , which belonged to anatase TiO_2 (JCPDS no. 21-1272). In addition, weak diffraction peaks of CeO_2 (JCPDS no. 43-1002) were detected near 28.6° , 33.0° , which indicated that some CeO_2 was present on the catalyst surface. La_2O_3 and V_2O_5 diffraction peaks were not observed for all samples, indicating that they are poorly crystallized and highly dispersed on the surface of the catalysts, which allows the active components to interact more fully and thus enhance the catalytic activity.¹⁷ The absence of neither crystallographic changes nor the appearance of new diffraction peaks in the poisoned samples compared with the fresh samples may be due to the low content of sulfate species generated on the catalyst surface or that they were amorphous.

Fig. 2 shows the N_2 adsorption-desorption isotherms and BJH pore size distribution. As shown in Fig. 2(a), all samples




Fig. 1 XRD spectra of 10Ce-2La-xV/Ti series catalysts before and after poisoning.

showed typical H3 hysteresis loops at higher relative pressures in the latter half ($P/P_0 = 0.7-1.0$), which is usually associated with capillary coalescence in the catalyst.¹⁸ The curves were a type IV isotherm according to the IUPAC classification, indicating that the catalysts had mesoporous structures. From Fig. 2(b), it is clear that all samples showed a wide range of pore sizes, further confirming that the catalysts are mesoporous and are made up of a variety of irregularly shaped particles stacked together. In addition, the specific surface area, total pore volume, and average pore size obtained from N_2 adsorption-desorption isotherms were calculated (Table 1). These values were slightly reduced after adding V because it favored sintering. After poisoning, the catalyst's surface area, average pore volume, and total pore volume were drastically decreased, demonstrating that sulfate species had coated the catalyst's surface.¹⁹

3.1.2 TEM. Fig. 3 shows the TEM images, HR-TEM images and elemental distributions of Ce, La, Ti and V for 10Ce-2La/Ti and 10Ce-2La-1.4V/Ti. From Fig. 3(a) and (c), it can be seen that the catalysts are porous structures formed by the stacking of nanoparticles with uneven sizes, which can exhibit good catalytic activity. In the HR-TEM images in Fig. 3(b) and (d), the crystal spacing of 0.35 nm corresponds to the (101) facets of anatase TiO_2 , 0.19 nm corresponds to the (220) crystalline facets of CeO_2 , and 0.17 nm can be indexed to the (202) crystalline facets of TiO_2 . Lattice fringes of lanthanum oxide and vanadium oxides were not found in any of the catalysts, confirming that they existed in an amorphous structure. It can also be observed that the elemental distribution of Fig. 3(e-h) and (i-k) shows that the elements Ce, La, Ti, and V are all uniformly distributed in the catalyst.²⁰

3.2 Catalyst surface acidity

NH_3 -TPD was used to investigate the acidic properties of the catalyst surface (Fig. 4). While the peaks of medium and strong






Fig. 2 (a) N₂ adsorption-desorption isotherms and (b) BJH pore size distributions of 10Ce-2La-xV/Ti series catalysts before and after poisoning.

Table 1 Structural information of 10Ce-2La-xV/Ti series catalysts

Samples	Surface area (m ² g ⁻¹)	Pore volume (cm ³ g ⁻¹)	Diameter of hole (nm)
10Ce-2La/Ti	74.13	0.062	21.96
10Ce-2La-1.4V/Ti	71.81	0.056	16.55
10Ce-2La/Ti-S	57.51	0.037	15.73
10Ce-2La-1.4V/Ti-S	54.30	0.035	15.65

acidic sites in the temperature range of 200–500 °C were associated with the desorption of NH₄⁺ from Brønsted acidic sites, the peaks of weak acidic sites below 200 °C corresponded to physisorbed NH₃ on the catalyst. The peaks of strong acidic sites >500 °C were attributed to the desorption of liganded NH₃ on Lewis acidic sites.²¹ By comparison, we found that the weak acidic site peaks did not change much after the introduction of V. However, the peak intensities and peak areas of the strong acidic sites in the catalysts increased significantly and the




Fig. 3 (a and b) TEM and HR-TEM image of 10Ce-2La/Ti; (c and d) TEM and HR-TEM image of 10Ce-2La-1.4V/Ti; (e-h) elemental distribution of Ce, La, Ti, V of 10Ce-2La-1.4V/Ti; (i-k) elemental distribution of Ce, La, and Ti of 10Ce-2La/Ti.




Fig. 4 NH_3 -TPD spectra of 10Ce-2La- x V/Ti series catalysts before and after poisoning.

detachment peaks moved toward higher temperatures, which may be due to the interaction of the different active components, which in turn led to an increase in the length of the metal-oxygen coordination bonds and the surface acidity.²² Meanwhile the decrease in the peak area of the strong acidic sites indicates that the medium-strong and weak acidic sites play a greater role in the catalytic activity of the catalyst during the catalytic reaction. In addition, it was observed that the peak intensity of the weak acidic sites of the 10Ce-2La/Ti catalyst became smaller after poisoning, which may be due to the reaction of SO_2 on the surface of the catalyst to generate sulfate to reduce the number of acidic sites, which led to the weakening of the catalyst's ability to adsorb NH_3 . In contrast, the peak position of catalyst 10Ce-2La-1.4V/Ti-S not only shifted toward high temperature, but also the peak intensity and peak area of the medium-strong acidic sites increased instead, indicating that the sulfation of the catalyst increased the NH_3 uptake by the medium, which is one of the reasons that the catalyst exhibits good water and sulfur.²³

3.3 Catalyst redox properties

XPS was used to investigate the chemical environment of the catalyst surface elements. The XPS spectra of catalyst Ce 3d are shown in Fig. 5(a), in which ten peaks were fitted to the spectra of all the samples. These were identified with "U" and "V" for the $3d_{5/2}$ and $3d_{3/2}$ spin-orbit components of Ce, respectively, which were located at 879 eV (V_0), 885 eV (V_2), 900 eV (U_0), and 905 eV (U_2). These belong to the $3d^{10}4f^1$ initial electronic state of Ce^{3+} , and the remaining peaks were related to the $3d^{10}4f^0$ state of Ce^{4+} . The existence of the double peaks of V_0/U_0 and V_2/U_2 suggests the presence of partially-reduced oxygen vacancies in the catalyst.²⁴ The fitted integrated peak area ratio of Ce^{3+} and total Ce was used to determine the relative content of Ce^{3+} on the catalyst surface, as shown in Table 2 by the formula $\text{Ce}^{3+} (\%) = (S_{V_0} + S_{V_2} + S_{U_0} + S_{U_2}) / (S_U + S_V) \times 100\%$.²⁵ After

introducing V, Ce and La concentrations on the catalyst surface considerably rose, proving that V interacted with the active ingredients and had an impact on how many atoms were present there. The higher proportion of Ce^{3+} , was attributed to an increase in the Ce concentration and also to the movement of free carriers on the catalyst surface towards the CeO_2 surface, which had a higher binding energy (eV).²⁶ A large fraction of Ce^{3+} on the catalyst surface enhanced the formation of oxygen vacancies, unsaturated chemical bonds, and charge imbalance, all of which boost the NO oxidation reaction.^{27,28} Fig. 5(b) depicts the catalyst's La 3d XPS spectra, in which La $3d_{5/2}$ and La $3d_{3/2}$ peaks emerged in all spectra at 834 eV and 37 eV, as well as at 852 eV and 855 eV, respectively.²⁹

Fig. 5(c) shows the O 1s XPS spectrum of the catalyst, in which peaks belonging to lattice oxygen and surface unsaturated oxygen (labeled O_β and O_α), can be observed at positions 528.7–529 eV and 530.1–530.7 eV. Because surface unsaturated oxygen O_α has a higher migration rate than lattice oxygen O_β , O_α increased the number of surface oxygen vacancies, which were more favorable to the SCR reaction.³⁰ The relative atomic percentages of these oxygen species on the catalyst surface were estimated from the areas of the fitted peaks, as listed in Table 2. The $O_\alpha / (O_\alpha + O_\beta)$ ratio on the catalyst surface significantly increased after adding V, which is consistent with the Ce 3d XPS analysis and is one of the reasons for the good activity of the catalyst. Fig. 5(d) showed the V 2p XPS spectra before and after catalyst poisoning, in which the V^{4+} peak was located at 515.2 eV, and the V^{5+} peaks were located at 516.4 eV and 523.1 eV. This indicates that V on the catalyst surface mainly existed as V^{5+} .³¹ The ratio of $V^{4+} / (V^{4+} + V^{5+})$ on the catalyst surface increased significantly after poisoning. Ce^{3+} also increased significantly, but the concentrations of Ce and V, the main active components on the surface of the catalyst, decreased. This was because SO_2 reacted with the active components to produce sulfate in the presence of O_2 .⁷ Similarly, the significant increase in the $O_\alpha / (O_\alpha + O_\beta)$ ratio on the surface after catalyst poisoning was because the higher Ce^{3+} ratio promoted the creation of more surface oxygen vacancies. This was because oxygen from sulfate species was formed on the sample surface after sulfation, as well as chemisorbed oxygen.³² Fig. 5(e) shows the S 2p XPS spectra of the catalyst before and after poisoning, in which peaks belonging to the spin-orbit components of $S^{6+} 2p_{3/2}$ and $S^{6+} 2p_{1/2}$ can be observed at 167.7–168 eV and 168.8–169 eV after fitting. This implies that S in +6 valence state was mostly present on the catalyst surface as SO_4^{2-} .^{33,34} After poisoning, the XPS peaks of all elements on the catalyst changed to higher binding energies, showing that the electron cloud density around each element was lowered to varying degrees. All were involved in the sulfation reaction. Peaks of Ce, La, O, Ti, V, S and C were observed in the full spectrum of the catalyst in Fig. 5(f).

As shown in Fig. 6, the redox properties of catalysts before and after 10Ce-2La/Ti and 10Ce-2La-1.4V/Ti poisoning were tested using H_2 -TPR. Measurements were performed using CuO as the standard, and the hydrogen consumption for the reduction peaks between 400 °C and 700 °C was quantitatively calculated (Table 3). 10Ce-2La/Ti displayed a large H_2 reduction






Fig. 5 XPS spectra of 10Ce-2La/Ti and 10Ce-2La-1.4V/Ti catalysts and before and after poisoning. (a) Ce 3d; (b) La 3d; (c) O 1s; (d) V 2p; (e) S 2p; (f) full spectrum.

peak, which was attributed to the reduction of surface-ligated unsaturated Ce^{4+} , which played an important role in the oxidation reaction.³⁵ After introducing V, the catalyst reduction

peaks shifted toward lower temperatures, and the H_2 consumption increased significantly ($1.37 \rightarrow 1.51 \text{ mmol g}^{-1}$). This indicates strong interactions between V oxides and Ce

Table 2 Surface element concentrations and Ce^{3+} , O_α , and V^{4+} ratios of catalysts

Samples	Surface atomic concentration (at%)						Ce^{3+}/Ce	O_α/O	V^{4+}/V
	O	Ce	La	V	S	Ti			
10Ce-2La/Ti	71.94	2.74	0.28	—	—	25.04	42.14%	14.34%	—
10Ce-2La-1.4V/Ti	70.58	3.42	0.40	1.21	—	24.92	45.60%	21.40%	9.98%
10Ce-2La/Ti-S	70.53	2.39	0.25	—	3.75	23.08	53.49%	27.51%	—
10Ce-2La-1.4V/Ti-S	69.84	2.92	0.40	0.72	4.63	21.50	57.30%	34.07%	18.83%






Fig. 6 H_2 -TPR spectra of 10Ce-2La-xV/Ti series catalysts.

Table 3 Catalyst H_2 -TPR peak positions and corresponding H_2 consumption

Samples	Peak position (°C)	H_2 consumption (mmol g^{-1})
10Ce-2La/Ti	536	1.37
10Ce-2La-1.4V/Ti	486	1.51
10Ce-2La/Ti-S	603	2.05
10Ce-2La-1.4V/Ti-S	537	2.54

oxides on the catalyst, which enhanced the reducing properties of the catalyst, which promoted catalytic cycling during SCR reaction.³⁶ A strong peak was observed at 603 °C in the poisoned 10Ce-2La/Ti-S sample, which was shifted to a higher temperature relative to the fresh sample. This shift was primarily due to the reduction of S^{6+} to S^{4+} in sulfate, along with the reduction of certain metal oxides.³⁷ To study the degree of metal oxide reduction in the catalyst 10Ce-2La-1.4V/Ti-S, the peaks were divided into α - and β -peaks by fitting, and the fitted area ratio was used to calculate the amount of hydrogen consumed for each peak. The α peak was associated with the reduction of metal oxides on the catalyst surface, while the β peak was related to the reduction process of sulfate species.³⁶ The position of the metal oxide reduction peak in 10Ce-2La-1.4V/Ti-S was essentially unchanged, and the hydrogen consumption of α_1 was larger than that of α_2 ($1.54 > 0.89 \text{ mmol g}^{-1}$). That of β_1 was less than that of β_2 ($1.00 < 1.157 \text{ mmol g}^{-1}$), indicating that co-doping V with 10Ce-2La/Ti limited the interactions between SO_2 and active metal oxide.

3.4 SO_2 desorption and reaction

SO_2 -TPD was used to investigate the adsorption capacity of the catalyst toward SO_2 . As shown in Fig. 7(a), the catalyst contained two main desorption peaks in the temperature ranges of 400–460 °C and 600–670 °C. The low-temperature peaks were related to the desorption of SO_2 from the catalyst surface,³⁸ while the high-temperature peaks were related to the desorption of SO_2




Fig. 7 SO_2 -TPD curves of fresh catalysts and TG/DTG curves of poisoned catalysts. (a) SO_2 -TPD curves; (b) 10Ce-2La/Ti; (c) 10Ce-2La-1.4V/Ti.



generated by the decomposition of sulfate species. The peak of 10Ce-2La/Ti at 665 °C represented the decomposition of cerium sulfate.³⁹ In comparison, the desorption peak of 10Ce-2La/Ti at low temperature has a larger peak area, implying that more SO₂ molecules are adsorbed on the surface than 10Ce-2La-1.4V/Ti, the addition of V reduced the amount of SO₂ molecules adsorbed on the surface of the catalyst in order to alleviate competition between SO₂ and NO adsorption, and to prevent the occupation of more active sites. The addition of V enhanced the strength of the catalyst's high-temperature peak, indicating that SO₂ molecules were adsorbed onto V₂O₅ species, shielding the catalyst's major active sites.⁴⁰

To study the substances generated on the surface of the samples during the catalytic reaction, the poisoned samples were analyzed using thermogravimetric analysis, and the results are shown in Fig. 7(b) and (c). The two samples' weight reduction procedure was separated into three steps: step I (40–200 °C) was mostly ascribed to the desorption of water from the samples; step II (200–600 °C) was attributed to the breakdown of ammonium sulfate and ammonia bisulfate on the catalyst surface; and step III (600–800 °C) to the decomposition of

sulfates in the samples.^{36,41} 10Ce-2La-1.4V/Ti-S showed an absorption peak related to the decomposition of sulfate (511 °C) and an exothermic peak related to the phase transition of the composite metal oxide (719 °C) above 500 °C. The 10Ce-2La/Ti-S catalyst had a higher decomposition temperature (540 °C), which was attributed to the low decomposition temperature of VOSO₄ generated by SO₂ with V. The 10Ce-2La/1.4V/Ti-S catalyst had the highest decomposition temperature (540 °C). In addition, the weight loss of ammonium sulfate or ammonia bisulfate on the surface of the 10Ce-2La-1.4V/Ti-S catalyst was larger (0.609%) than that of 10Ce-2La/Ti-S (0.485%). It is shown that the introduction of V protects the main active component of the catalyst from reacting with SO₂ and inhibits the formation of sulfate species on the catalyst surface, thus enhancing the water and sulfur resistance of the catalyst.

3.5 *In situ* infrared spectroscopy of catalysts

Fig. 8(a) and (b) show the *in situ* DRIFTS spectra of catalysts 10Ce-2La/Ti and 10Ce-2La-1.4V/Ti after adsorbing NH₃ (500 ppm) for 30 min. The peaks near 954 (960) cm⁻¹ for both samples were related to weakly-adsorbed gas-phase NH₃.^{42,43}




Fig. 8 *In situ* DRIFTS spectra of NH₃ or NO + O₂ adsorption on catalysts. (a) NH₃ adsorption on 10Ce-2La/Ti, (b) NH₃ adsorption on 10Ce-2La-1.4V/Ti, (c) NO + O₂ adsorption on 10Ce-2La/Ti, and (d) NO + O₂ adsorption on 10Ce-2La-1.4V/Ti.

Absorption peaks near 1312–1343 (1350) cm^{-1} and 1414 (1413) cm^{-1} belonged to NH_4^+ at Brønsted acid sites.^{44,45} The asymmetric bending vibration of NH_3 coupled to Lewis acid sites was responsible for the lower absorption peak at 1601 (1607) cm^{-1} .⁴⁴ The peak at 3253–3385 cm^{-1} was attributed to the stretching vibration of NH_3 at the Lewis acid sites.⁴⁶ 10Ce–2La–1.4V/Ti shows a weak adsorption band near 1550 cm^{-1} , which is due to the oxidation of NH_3 on the catalyst surface by surface-active oxygen to generate an important intermediate product, $-\text{NH}_2$, in the catalytic reaction $-\text{NH}_2$ facilitates the conversion of NO, and promotes the smooth progress of the SCR reaction.⁴⁷ In comparison, the intensity of the peaks related to the Brønsted acidic sites increased after the introduction of V, and NH_3 was more easily activated. This indicates that Brønsted acids dominated the reaction, and the addition of V increased the proportion of Brønsted acids.

The DRIFTS spectra of the catalysts 10Ce–2La/Ti and 10Ce–2La–1.4V/Ti after 30 minutes of NO (500 ppm) + O_2 adsorption are shown in Fig. 8(c) and (d). Nitrate bridged ions and free nitrate ions, respectively, were responsible for the bands at 1355 (1352) cm^{-1} and 1600 (1602) cm^{-1} .⁴⁸ The absorption peak

belonging to the nitrite species $\text{trans-N}_2\text{O}_2^{2-}$ was located at 1415 cm^{-1} . Weakly adsorbed gas-phase NO_2 was thought to be active in the band at 1625–1627 cm^{-1} because it may react quickly with gaseous NH_3 .⁴⁵

Fig. 9(a) and (b) show the DRIFTS profiles of the catalysts 10Ce–2La/Ti and 10Ce–2La–1.4V/Ti after 30 min of pre-adsorption of NH_3 (500 ppm) followed by NO (500 ppm) + O_2 (3%) adsorption for 30 min. In the NH_3 adsorption curve, the peaks near 1317 and 1415 (1417) cm^{-1} belonged to NH_4^+ on the Brønsted acid sites, and the intensity of the peak at 1415 (1417) cm^{-1} did not change greatly with the passage of NO + O_2 . This was attributed to the coincidence of the peak at 1600 (1604) cm^{-1} for the NH_3 and Lewis acid sites with the stronger peaks of rapidly-generated nitrate at 1604 and 1625 cm^{-1} after flowing NO + O_2 . This indicates that pre-adsorbed NH_3 did not directly react with gas-phase NO and that the NH_3 -SCR did not involve gas-phase NO. With the passage of NO + O_2 , the intensity of the 1415 (1417) cm^{-1} peak did not change significantly, because, at this time, the 1600 (1604) cm^{-1} peaks of NH_3 and Lewis acid sites overlapped with those of the stronger nitrate peaks at 1604 and 1625 cm^{-1} . This suggests that pre-adsorbed




Fig. 9 *In situ* DRIFTS spectra of $\text{NH}_3(\text{NO} + \text{O}_2)$ reaction with pre-adsorbed $\text{NO} + \text{O}_2(\text{NH}_3)$ on the catalyst. (a) Reaction of $\text{NO} + \text{O}_2$ on 10Ce–2La/Ti with pre-adsorbed NH_3 ; (b) reaction of $\text{NO} + \text{O}_2$ on 10Ce–2La–1.4V/Ti with pre-adsorbed NH_3 ; (c) reaction of NH_3 on 10Ce–2La/Ti with pre-adsorbed $\text{NO} + \text{O}_2$; (d) reaction of NH_3 on 10Ce–2La–1.4V/Ti with pre-adsorbed $\text{NO} + \text{O}_2$ reaction.






Fig. 10 Catalytic performance *versus* temperature curves of 10Ce-2La-xV/Ti series catalysts. (a) NO removal efficiency *versus* temperature transformation curves at different weight ratios V; (b) N₂ selectivity at different temperatures; (c) effect of temperature on the concentration of NO₂ and N₂O production; (d) stability test of the catalysts for water and sulfur resistance; (e) N₂ selectivity at different time; (f) TOF values (200–225 °C). (g) Arrhenius plots.

NH₃ did not react directly with gas-phase NO and that the NH₃-SCR reaction did not proceed *via* the Eley-Rideal mechanism.

Fig. 9(c) and (d) show the DRIFTS spectra of the catalysts 10Ce-2La/Ti and 10Ce-2La-1.4V/Ti pre-adsorbed with NO (500 ppm) + O₂ (3%) for 30 min and then allowed to adsorb NH₃ (500 ppm) for 30 min. Prior to the passage of NH₃, peaks attributed

to nitrates were observed at 1349 (1351) cm⁻¹, 1624 (1625) cm⁻¹, 1415 (1418) cm⁻¹, and 1600 (1604) cm⁻¹, similar to those in Fig. 8(a) and (b).⁴⁹ The nitrate peaks at 1602 and 1625 cm⁻¹ disappeared rapidly upon the passage of NH₃, it indicates that adsorbed NO can react with NH₃ in the adsorbed state, so the reaction mechanism is Langmuir-Hinshelwood mechanism. In



an L-H reaction mechanism, the reaction orders of both NO and NH_3 are zero.⁵⁰

3.6 Catalyst denitrification performance testing

Fig. 10(a) shows the NO conversion *versus* temperature curves of the catalysts after adding different ratios of V. The overall activity of the catalyst was improved after adding V, and the starting temperatures were all lower. As the weight percent of V increases, the catalyst denitrification efficiency improved and then became worse, and the temperature window gradually became wider. The optimal catalytic efficiency was obtained when the weight ratio of V_2O_5 was 1.4, and the denitrification efficiency remained above 80% in the temperature range of 270–490 °C. The NO conversion reached a maximum of 99% at 330 °C, and the catalytic activity was greatly improved compared with the original rare-earth-based catalyst. In addition to catalytic activity, N_2 selectivity is another important index for evaluating a catalyst's performance. As the temperature of the reaction increased, N_2O and NO_2 were produced, causing the N_2 selectivity to slowly decrease, as shown in Fig. 10(b) and (c). In the reaction temperature interval, the N_2 selectivity and N_2O concentration of catalyst was slightly improved by the addition of V. The lower N_2O generation resulted in better overall N_2 selectivity than the original catalyst.

The stability of the catalyst was tested by passing 300 ppm SO_2 under constant test conditions and the results were shown in Fig. 10(d). After 2.5 h of the water and sulfur feeding, the NO conversion of 10Ce–2La/Ti decreased from the initial 97% to 44%, which maintained almost unchanged for 52 h. If the feeding of water and sulfur was cut off, the NO conversion recovered to 78%. Compared with 10Ce–2La/ TiO_2 , the V-doped catalyst had a higher NO conversion in the presence of water and sulfur, which remained above 85% and recovered to 99% after shutting down water and sulfur. Fig. 10(e) shows the N_2 selectivity comparison in the water and sulfur resistance stabilization experiments. Both the two catalysts showed a high N_2 selectivity over than 99% and the N_2 selectivity was not influenced by water and sulfur. It can also seen that the N_2 selectivity was slightly improved by the addition of V. The turnover frequency (TOF) value calculated from eqn (5) is shown in Fig. 10(f). The 10Ce–2La–1.4V/Ti catalyst displayed better TOF values at each temperature, demonstrating that single Ce atoms on the catalytic surface were the primary active sites and displayed the best intrinsic activity under identical circumstances. Additionally, the reaction rate of NO on each square meter of a catalyst within the investigated temperature range was calculated according to eqn (4). It was plotted as $\ln(\text{rate})$ against $1000/T$, and the Arrhenius activation energy of the reaction was determined by fitting. As shown in Fig. 10(g), the surface activation energy of 10Ce–2La/Ti was 24.6 kJ mol^{-1} , which was higher than that of 10Ce–2La–1.4V/Ti (13.5 kJ mol^{-1}). The lower activation energy suggests an improved denitrification efficiency.

4. Conclusion

V-doped 10Ce–2La– x V/Ti catalysts were prepared by a ball milling method, and it was found that the rare earth Ce exerted

a synergistic effect with V. The composite carrier-type oxides exhibited a good activity window and denitrification performance, as well as excellent water and sulfur resistance when the weight ratio of V_2O_5 was 1.4. The prepared catalysts showed mesoporous structures, and the ball milling method enhanced the interactions between different active components, resulting in good dispersion of the active components. V doping improved the surface acidity of the catalysts, and Brønsted acids on the surface of the catalysts played the dominant role. The greater number of acid sites adsorbed more NH_3 that participated in the reaction and also prevented SO_2 poisoning. The Ce^{3+} and O ratios on the catalyst surface were also enhanced by the addition of V, which was significant for the SCR- NH_3 reaction. V limited the interactions between SO_2 and the main active component (metal oxides), reduced the amount of SO_2 adsorbed on the catalyst surface, and inhibited the formation of sulfate species on the catalyst surface. These all improved the sulfur resistance of the catalyst. The NH_3 -SCR on the catalyst surface proceeded *via* the Langmuir–Hinshelwood mechanism, with Brønsted acid sites playing the dominant role. The better denitrification activity and sulfur resistance of 10Ce–2La– x V/Ti catalysts make them promising for various applications.

Author contributions

Yang Liu: writing – original draft, data curation, formal analysis, investigation, methodology. Na Wang: conceptualization, data curation, formal analysis, funding acquisition, investigation, methodology, project administration, supervision, validation, writing – review & editing. Huidong Xie: investigation, methodology, project administration, supervision. Yepeng Sun: data curation, formal analysis. Liang Zhang: investigation, methodology. Kaiyue Yang: investigation, methodology. Chang Yang: data curation, formal analysis. Chengmin Ge: conceptualization, funding acquisition, supervision, validation.

Conflicts of interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

The work was supported by the National Natural Science Foundation of China under grant No. 51708447 and Major Scientific and Technological Innovation Projects of Shandong Province under grant No. 2019JZZY010343. The project is also supported by the Science and Technology Planning Project of Yulin City, Shaanxi Province under grant CXY-2021-135. We would like to thank Mogo Edit (<https://www.mogoedit.com>) for its English editing during the preparation of this manuscript.

References

- 1 D. Singh, A. Kumar, K. Kumar, B. Singh, U. Mina, B. B. Singh and V. K. Jain, Statistical modeling of O_3 , NO_x , CO, $\text{PM}_{2.5}$,



- VOCs and noise levels in commercial complex and associated health risk assessment in an academic institution, *Sci. Total Environ.*, 2016, **572**, 586–594.
- 2 Y. Liu, K. Liu, P. Wang, Z. Jin and P. Li, Electrocatalytic upcycling of nitrogenous wastes into green ammonia: advances and perspectives on materials innovation, *Carbon Neutrality*, 2023, **2**, 14.
 - 3 L. Long, S. Tian, Y. Zhao, X. Zhang, W. Luo and X. Yao, Promotional effects of Nb⁵⁺ and Fe³⁺ co-doping on catalytic performance and SO₂ resistance of MnO–CeO₂ low-temperature denitration catalyst, *J. Colloid Interface Sci.*, 2023, **648**, 876–888.
 - 4 J. Xu, Y. Zhang, X. Zou, T. Tang, Q. Zhang, F. Guo and H. Liu, Recent advances and perspectives in the resistance of SO₂ and H₂O of cerium-based catalysts for NO_x selective catalytic reduction with ammonia, *New J. Chem.*, 2022, **46**, 2053–2067.
 - 5 X. Fang, Y. Liu, Y. Cheng and W. Cen, Mechanism of Ce-Modified Birnessite-MnO₂ in Promoting SO₂ Poisoning Resistance for Low-Temperature NH₃-SCR, *ACS Catal.*, 2021, **11**, 4125–4135.
 - 6 S. Ma, X. Zhao, Y. Li, T. Zhang, F. Yuan, X. Niu and Y. Zhu, Effect of W on the acidity and redox performance of the Cu_{0.02}Fe_{0.2}W_aTiO_x (*a* = 0.01, 0.02, 0.03) catalysts for NH₃-SCR of NO, *Appl. Catal., B*, 2019, **248**, 226–238.
 - 7 L. Jiang, Y. Liang, W. Liu, H. Wu, T. Aldahri, D. S. Carrero and Q. Liu, Synergistic effect and mechanism of FeO and CeO co-doping on the superior catalytic performance and SO₂ tolerance of Mn-Fe-Ce/ACN catalyst in low-temperature NH₃-SCR of NO, *J. Environ. Chem. Eng.*, 2021, **9**, 106360.
 - 8 Y. Li, J. Xiong, Y. Lin, J. Guo and T. Zhu, Distribution of SO₂ oxidation products in the SCR of NO over V₂O₅/TiO₂ catalysts at different temperatures, *Ind. Eng. Chem. Res.*, 2020, **59**, 5177–5185.
 - 9 H. Li, J. Zhang, Y. Cao, F. Li and Y. Wang, Enhanced activity and SO₂ resistance of Co-modified CeO₂-TiO₂ catalyst prepared by facile co-precipitation for elemental mercury removal in flue gas, *Appl. Organomet. Chem.*, 2020, **34**, e5463.
 - 10 L. Yu, W. Liu, Z. Gao, X. Zhao, J. Gao and R. Yang, Promotion effect of chromium on the activity and SO₂ resistance of CeO₂-TiO₂ catalysts for the NH₃-SCR reaction, *Ind. Eng. Chem. Res.*, 2021, **60**, 11676–11688.
 - 11 H. Liu, Z. Fan, C. Sun, S. Yu, S. Feng, W. Chen, D. Chen, C. Tang, F. Gao and L. Dong, Improved activity and significant SO₂ tolerance of samarium modified CeO₂-TiO₂ catalyst for NO selective catalytic reduction with NH₃, *Appl. Catal., B*, 2019, **244**, 671–683.
 - 12 N. Wang, L. Wang, H. Xie, Y. Liu, Y. Sun, C. Yang and C. Ge, Preparation of high temperature NH₃-SCR catalysts with carbonate as precursors by ball milling method, *RSC Adv.*, 2022, **12**, 35094–35102.
 - 13 B. Shen, Y. Wang, F. Wang and T. Liu, The effect of Ce–Zr on NH₃ -SCR activity over MnO_x (0.6)/Ce_{0.5}Zr_{0.5}O₂ at low temperature, *Chem. Eng. J.*, 2014, **236**, 171–180.
 - 14 Y. Liu, J. Xu, H. Li, S. Cai, H. Hu, C. Fang, L. Shi and D. Zhang, Rational design and *in situ* fabrication of MnO₂@NiCo₂O₄ nanowire arrays on Ni foam as high-performance monolith de-NO_x catalysts, *J. Mater. Chem. A*, 2015, **3**, 11543–11553.
 - 15 R. Q. Long and R. T. Yang, Fe-ZSM-5 for selective catalytic reduction of NO with NH₃: a comparative study of different preparation techniques, *Catal. Lett.*, 2001, **74**, 201–205.
 - 16 S. Brandenberger, O. Kröcher, A. Tissler and R. Althoff, The determination of the activities of different iron species in Fe-ZSM-5 for SCR of NO by NH₃, *Appl. Catal., B*, 2010, **95**, 348–357.
 - 17 Z. Fan, J. W. Shi, C. Gao, G. Gao, B. Wang, Y. Wang, C. He and C. Niu, Gd-modified MnO_x for the selective catalytic reduction of NO by NH₃: The promoting effect of Gd on the catalytic performance and sulfur resistance, *Chem. Eng. J.*, 2018, **348**, 820–830.
 - 18 S. W. K. Sing, Reporting physisorption data for gas/solid systems with special reference to the determination of surface area and porosity (Recommendations 1984), *Pure Appl. Chem.*, 1985, **57**, 603–619.
 - 19 Z. Liu, J. Zhu, S. Zhang, L. Ma and S. I. Woo, Selective catalytic reduction of NO_x by NH₃ over MoO₃-promoted CeO₂/TiO₂ catalyst, *Catal. Commun.*, 2014, **46**, 90–93.
 - 20 L. Meng, J. Wang, Z. Sun, J. Zhu, H. Li, J. Wang and M. Shen, Active manganese oxide on MnO_x–CeO₂ catalysts for low-temperature NO oxidation: Characterization and kinetics study, *J. Rare Earths*, 2018, **36**, 142–147.
 - 21 C. Fang, D. Zhang, S. Cai, L. Zhang, L. Huang, H. Li, P. Maitarad, L. Shi, R. Gao and J. Zhang, Low-temperature selective catalytic reduction of NO with NH₃ over nanoflaky MnO_x on carbon nanotubes *in situ* prepared *via* a chemical bath deposition route, *Nanoscale*, 2013, **5**, 9199–9207.
 - 22 D. Chen, J. Feng, J. Sun, C. Cen and Y. Xiong, Molybdenum modified montmorillonite clay as an efficient catalyst for low temperature NH₃-SCR, *Chem. Eng. Technol.*, 2020, **95**, 1441–1452.
 - 23 X. S. Du, X. Gao, L. W. Cui, Y. C. Fu, Z. Y. Luo and K. F. Cen, Investigation of the effect of Cu addition on the SO₂-resistance of a CeTi oxide catalyst for selective catalytic reduction of NO with NH₃, *Fuel*, 2012, **92**, 49–55.
 - 24 R. Q. Long and R. T. Yang, Structural characterization of CeO₂-TiO₂ and V₂O₅/CeO₂-TiO₂ catalysts by Raman and XPS techniques, *J. Phys. Chem. B*, 2003, **107**, 5162–5167.
 - 25 S. Liu, P. Yao, Q. Lin, S. Xu, M. Pei, J. Wang, H. Xu and Y. Chen, Optimizing acid promoters of Ce-based NH₃-SCR catalysts for reducing NO_x emissions, *Catal. Today*, 2021, **382**, 34–41.
 - 26 W. Cha, S. H. Ehrman and J. Jurng, Surface phenomenon of CeO₂-added V₂O₅/TiO₂ catalyst based chemical vapor condensation (CVC) for enhanced selective catalytic reduction at low temperatures, *Chem. Eng. J.*, 2016, **304**, 72–78.
 - 27 T. Zhang, R. Qu, W. Su and J. Li, A novel Ce–Ta mixed oxide catalyst for the selective catalytic reduction of NO_x with NH₃, *Appl. Catal., B*, 2015, **176**, 338–346.
 - 28 W. Liu, Y. Long, S. Liu, Y. Zhou, X. Tong, Y. Yin, X. Li, K. Hu and J. Hu, Promotional effect of Ce in NH₃-SCO and NH₃-SCR reactions over Cu-Ce/SCR catalysts, *J. Ind. Eng. Chem.*, 2022, **107**, 197–206.



- 29 I. A. A. Vesga, XPS fitting model proposed to the study of Ni and La in deactivated FCC catalysts, *J. Electron Spectrosc.*, 2019, **233**, 5–15.
- 30 W. Zheng, X. Zhang, Y. Zheng and Y. Yue, “Oxynitride trap” over N/S co-doped graphene-supported catalysts promoting low temperature NH₃-SCR performance: insight into the structure and mechanisms, *J. Hazard. Mater.*, 2022, **423**, 127187.
- 31 F. Wang, G. Li, B. Shen, Y. Wang and C. He, Mercury removal over the vanadia-titania catalyst in CO₂-enriched conditions, *Chem. Eng. J.*, 2015, **263**, 356–363.
- 32 A. Tan, J. Wang, L. Li, A. Liu, G. Song, K. Guo, Y. Luo, F. Liu, F. Gao and L. Dong, Gas phase sulfation of ceria-zirconia solid solutions for generating highly efficient and SO₂ resistant NH₃-SCR catalysts for NO removal, *J. Hazard. Mater.*, 2020, **388**, 121729.
- 33 A. Fan, Y. Jing, J. Guo, X. Shi, S. Yuan and J. Li, Investigation of Mn doped perovskite La-Mn oxides for NH₃-SCR activity and SO₂/H₂O resistance, *Fuel*, 2022, **310**, 122237.
- 34 X. Yao, K. Kang, J. Cao, L. Chen, W. Luo, W. Zhao, J. Rong and Y. Chen, Enhancing the denitration performance and anti-K poisoning ability of CeO₂-TiO₂/P25 catalyst by H₂SO₄ pretreatment: Structure-activity relationship and mechanism study, *Appl. Catal., B*, 2020, **269**, 118808.
- 35 C. Fang, D. Zhang, L. Shi, R. Gao, H. Li, L. Ye and J. Zhang, Highly dispersed CeO₂ on carbon nanotubes for selective catalytic reduction of NO with NH₃, *Catal. Sci. Technol.*, 2013, **3**, 803–811.
- 36 L. Jiang, Q. Liu, G. Ran, M. Kong, S. Ren, J. Yang and J. Li, V₂O₅-modified Mn-Ce/AC catalyst with high SO₂ tolerance for low-temperature NH₃-SCR of NO, *Chem. Eng. J.*, 2019, **370**, 810–821.
- 37 X. Fang, Y. Liu, Y. Cheng and W. Cen, Mechanism of Ce-modified birnessite-MnO₂ in promoting SO₂ poisoning resistance for low-temperature NH₃-SCR, *ACS Catal.*, 2021, **11**, 4125–4135.
- 38 L. Weiman, L. Haidi and C. Yunfa, Mesoporous MnO_x-CeO₂ composites for NH₃-SCR: the effect of preparation methods and a third dopant, *RSC Adv.*, 2019, **9**, 11912–11921.
- 39 X. Huang, S. Li, W. Qiu, Y. Chen, J. Cheng, Y. Sun, G. Bai, L. Song, G. Zhang and H. He, Effect of Organic Assistant on the Performance of Ceria-Based Catalysts for the Selective Catalytic Reduction of NO with Ammonia, *Catalysts*, 2019, **9**, 357.
- 40 S. Jia, G. Pu, W. Xiong, P. Wang, J. Gao and C. Yuan, Investigation on simultaneous removal of SO₂ and NO over a Cu-Fe/TiO₂ catalyst using vaporized H₂O₂: An analysis on SO₂ effect, *Ind. Eng. Chem. Res.*, 2021, **60**, 13474–13484.
- 41 C. Sun, H. Liu, W. Chen, D. Chen, S. Yu, A. Liu, L. Dong and S. Feng, Insights into the Sm/Zr co-doping effects on N₂ selectivity and SO₂ resistance of a MnO_x-TiO₂ catalyst for the NH₃-SCR reaction, *Chem. Eng. J.*, 2018, **347**, 27–40.
- 42 N. Wang, C. Ye, H. Xie, L. Wang, B. Zheng, Y. He, C. Yang, J. Zhou and C. Ge, High-temperature vanadium-free catalyst for selective catalytic reduction of NO with NH₃ and theoretical study of La₂O₃ over CeO₂/TiO₂, *Catal. Sci. Technol.*, 2021, **11**, 6112–6125.
- 43 Z. Liu, S. Zhang, J. Li and L. Ma, Promoting effect of MoO₃ on the NO_x reduction by NH₃ over CeO₂/TiO₂ catalyst studied with *in situ* DRIFTS, *Appl. Catal., B*, 2014, **144**, 90–95.
- 44 P. Gong, J. Xie, D. Fang, F. He, F. Li and K. Qi, Enhancement of the NH₃-SCR property of Ce-Zr-Ti by surface and structure modification with P, *Appl. Surf. Sci.*, 2020, **505**, 144641.
- 45 Z. Yan, J. Yang, X. Ge, J. Yu, L. Wei, T. Yang, B. He, X. Wang and L. Liu, Manganese oxide catalysts supported on zinc oxide nanorod arrays: A new composite for selective catalytic reduction of NO_x with NH₃ at low temperature, *Appl. Surf. Sci.*, 2019, **491**, 579–589.
- 46 N. Li, S. Tan, T. Wang, L. Hou, K. Jiao and W. Wu, Study on Performance and mechanism of low-temperature NH₃-SCR denitrification over Mn/(Ce, La)PO₄ catalysts, *Mol. Catal.*, 2023, **551**, 113648.
- 47 Y. Zhang, X. Yue, T. Huang, K. Shen and B. Lu, In situ DRIFTS studies of NH₃-SCR mechanism over V₂O₅-CeO₂/TiO₂-ZrO₂ catalysts for selective catalytic reduction of NO_x, *Materials*, 2018, **11**, 1307.
- 48 Y. Pan, B. Shen, L. Liu, Y. Yao, H. Gao, C. Liang and H. Xu, Develop high efficient of NH₃-SCR catalysts with wide temperature range by ball-milled method, *Fuel*, 2020, **282**, 118834.
- 49 N. Li, C. Ren, L. Hou, K. Jiao and W. Wu, Study on NH₃-SCR performance and mechanism of Mn supported SO₄²⁻-CeCO₃F-CePO₄ catalysts, *Mol. Catal.*, 2022, **533**, 112763.
- 50 S. Yang, J. Li, C. Wang, J. Chen, L. Ma, H. Chang, L. Chen, Y. peng and N. Yan, Fe-Ti spinel for the selective catalytic reduction of NO with NH₃: Mechanism and structure-activity relationship, *Appl. Catal., B*, 2012, **117**, 73–80.

