

# Chemical Science

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

*Accepted Manuscripts* are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

**EDGE ARTICLE**

# Electrocatalytic CO<sub>2</sub> Reduction by M(bpy-R)(CO)<sub>4</sub> (M = Mo, W; R = H, *t*Bu) Complexes. Electrochemical, Spectroscopic, and Computational Studies and Comparison with Group 7 Catalysts.

Melissa L. Clark,<sup>a</sup> Kyle A. Grice,<sup>‡a</sup> Curtis E. Moore, Arnold L. Rheingold, and Clifford P. Kubiak\*<sup>5</sup> Received (in XXX, XXX) XthXXXXXXXXXX 20XX, Accepted Xth XXXXXXXXXXXX 20XX

DOI: 10.1039/b000000x

The tetracarbonyl molybdenum and tungsten complexes of 2,2'-bipyridine and 4,4'-di-*tert*-butyl-2,2'-bipyridine (M(bpy-R)(CO)<sub>4</sub>; R = H, M = Mo (1), W (2); R = *t*Bu, M = Mo (3), W (4)) are found to be active electrocatalysts for the reduction of CO<sub>2</sub>. The crystal structures of M(bpy-*t*Bu)(CO)<sub>4</sub> (M = Mo (3), W (4)), the singly reduced complex [W(bpy)(CO)<sub>4</sub>][K(18-crown-6)] (5) and the doubly reduced complex [W(bpy-*t*Bu)(CO)<sub>3</sub>][K(18-crown-6)]<sub>2</sub> (6) are reported. DFT calculations have been used to characterize the reduced species from the reduction of W(bpy-*t*Bu)(CO)<sub>4</sub> (4). These compounds represent rare examples of group 6 electrocatalysts for CO<sub>2</sub> reduction, and comparisons are made with the related group 7 complexes that have been studied extensively for CO<sub>2</sub> reduction.


## Introduction

15 The electrocatalytic reduction of CO<sub>2</sub> to value-added products and fuels is an area that has seen significant progress over the last several decades.<sup>1-5</sup> In particular, the use of homogeneous electrocatalysts is an attractive approach because they can be studied with a variety of techniques and modified via synthesis to  
20 affect reactivity. Previous work from our group focused on the study of complexes of the type M(bpy-R)(CO)<sub>3</sub>X (M = Re, Mn; R = H, *t*Bu, etc.), based on the 2,2'-bipyridine system originally reported by Lehn<sup>6</sup>. Our more recent studies have shown that the 4,4'-di-*tert*-butyl-2,2'-bipyridine (bpy-*t*Bu) ligand is effective in  
25 increasing the activity of rhenium-based CO<sub>2</sub> reduction catalysts compared to the complexes of their 2,2'-bipyridine counterparts.<sup>7-9</sup>

Many homogeneous electrocatalysts for CO<sub>2</sub> reduction are based on expensive and rare metals such as Ru and Re. The cost  
30 of these metals makes it difficult to envision their use in large-scale deployment of systems for the synthesis of renewable chemicals and fuels from CO<sub>2</sub>. Significant progress has been made towards developing electrocatalysts based on more abundant metals (for example: Mn,<sup>10, 11</sup> Ni,<sup>12</sup> Fe,<sup>13, 14</sup> and Cu<sup>15</sup>).  
35 Notably, there are very few reports of electrocatalytic CO<sub>2</sub> reduction catalysts based on complexes of group 6 metals (Cr, Mo, W),<sup>16, 17</sup> even though this group contains the metals commonly found in the active sites of formate dehydrogenase (FDH) enzymes, which interconvert CO<sub>2</sub> and formate.<sup>18</sup> Aerobic  
40 bacteria also utilize molybdenum in the active site of carbon monoxide dehydrogenase (CODH) enzymes that are capable of oxidizing CO to CO<sub>2</sub>.<sup>19</sup>

Stoichiometric reactions of dianionic Cr, Mo and W pentacarbonyl complexes with CO<sub>2</sub> lead to the formation of  
45 coordinated CO (Scheme 1),<sup>20</sup> and there are other examples of stoichiometric CO<sub>2</sub> reduction at homogeneous group 6 metal complexes.<sup>21,22,23</sup> The coupling of CO<sub>2</sub> with olefins,<sup>24</sup> as well as

hydrogenation of CO<sub>2</sub> to formic acid<sup>25</sup> or alkyl formates<sup>26</sup> have been observed at group 6 complexes. Given the precedent for  
50 CO<sub>2</sub> reactivity with group 6 complexes, we were curious to see if 2,2'-bipyridine complexes of these group 6 metals could be used as *electrocatalysts* for the reduction of CO<sub>2</sub> to produce value-added products such as CO.



55 **Scheme 1.** Reactions of group 6 dianions with CO<sub>2</sub> (M = Cr, Mo, W).<sup>20</sup>

The spectroscopic, photochemical, and electrochemical properties of group 6 complexes of the type M(L)(CO)<sub>4</sub> (M = Cr, Mo, W, L = diimine ligand) are well known.<sup>27</sup> It has been proposed that the reduction of these metal complexes by two electrons leads to the loss of a CO ligand and generation of a five-coordinate [M(L)(CO)<sub>3</sub>]<sup>2-</sup> species,<sup>27,28</sup> although spectroscopic characterization of such species has not been  
65 reported. We note the parallel between this postulated [M(L)(CO)<sub>3</sub>]<sup>2-</sup> species and the dianionic [M(CO)<sub>5</sub>]<sup>2-</sup> complexes reported by Cooper and co-workers to react with CO<sub>2</sub> to form M(CO)<sub>6</sub>,<sup>20</sup> thus reducing CO<sub>2</sub> to CO. The group 6 dianionic [M(bpy-R)(CO)<sub>3</sub>]<sup>2-</sup> complexes are also formally isoelectronic to  
70 the five-coordinate [Re(bpy-*t*Bu)(CO)<sub>3</sub>]<sup>-</sup> and [Mn(bpy-*t*Bu)(CO)<sub>3</sub>]<sup>-</sup> anions, the critical intermediates that react with CO<sub>2</sub> in electrocatalytic reduction of CO<sub>2</sub> by Re(bpy-*t*Bu)(CO)<sub>3</sub>X and


Mn(bpy-*t*Bu)(CO)<sub>3</sub>X.<sup>11</sup>

Herein we report electrochemical studies of the group 6 complexes M(bpy-R)(CO)<sub>4</sub> (R = H, M = Mo (**1**), W (**2**); R = *t*Bu, M = Mo (**3**), W(**4**)). We find that these complexes are electrocatalysts for the reduction of CO<sub>2</sub>. Particular focus is placed on complex **4**, as it is isoelectronic with previously published highly active rhenium and manganese systems. NMR spectroscopy, X-ray crystallography, and Density Functional Theory (DFT) studies are also used to examine the species relevant to catalytic CO<sub>2</sub> reduction. The comparisons between the group 6 and group 7 complexes contribute to a clearer understanding of the specific characteristics that lead to more active CO<sub>2</sub> reduction catalysts.

## Results and Discussion

### Synthesis and Characterization

The known complexes M(bpy-R)(CO)<sub>4</sub> (M = W, Mo; R = H, *t*Bu, **1–4**, Figure 1), were synthesized similar to literature procedures.<sup>29</sup> These complexes were isolated as bright orange-red (M = Mo) or dark red (M = W) air-stable solids. Although complex **4** has been mentioned in the literature,<sup>30–32</sup> its <sup>1</sup>H and <sup>13</sup>C NMR spectra had not been previously reported, and this data is included in the ESI. The FT-IR spectra of these complexes display the standard four-signal pattern (2A<sub>1</sub>, B<sub>1</sub>, and B<sub>2</sub>) in the ν(CO) region (1700–2100 cm<sup>-1</sup>, Fig. S1 in the ESI) for tetracarbonyl complexes of this type with values that are in agreement with the literature (Table S1 in the ESI).<sup>33, 34</sup> The addition of the *t*Bu groups increases the solubility of **3** and **4** in organic solvents compared to **1** and **2**.




**Figure 1.** Tetracarbonyl complexes of molybdenum and tungsten examined in this work.

In order to compare with the reported X-ray structures of M(bpy)(CO)<sub>4</sub> (M = Mo (**1**)<sup>35</sup>, W (**2**)<sup>36, 37</sup>), X-ray quality crystals were grown of the *tert*-butyl derivatives M(bpy-*t*Bu)(CO)<sub>4</sub> (M = Mo (**3**), W (**4**); see Figure 2) by vapor diffusion of pentane into concentrated toluene solutions of the complexes. The molecular geometries of **3** and **4** are similar to the corresponding complexes with the parent bipyridine ligand (**1** and **2**), with slightly shorter M–N bonds (Table S2), indicating slightly stronger donation from the *tert*-butyl ligand and slightly stronger back donation to the M–CO groups. This is also observed in the FT-IR data for complexes **1–4**, in which the ν(CO) frequencies are shifted to lower wavenumbers on the *t*Bu-substituted complexes compared to the parent complexes. The C–C bond lengths between the two pyridyl rings (C9–C10) for all of the complexes are consistent with a neutral bipyridine ligand.<sup>38</sup>

A search of the Cambridge Crystallographic Database did not yield any other tetracarbonyl tungsten or molybdenum complexes with 4,4'-disubstituted bipyridine ligands.<sup>39</sup> However, a comparison of the structures of **1–4** with previously reported

isoelectronic [Re(bpy-R)(CO)<sub>4</sub>](OTf) complexes reveals interesting similarities and differences. The bending of the axial CO ligands away from the bipyridine ligands in complexes **1–4** (as seen in the M–C1–O1 and M–C4–O4 angles of ca. 171–172°) is a common feature of group 6 tetracarbonyl complexes, and has been explained in terms of back donation from a π\* orbital on the bidentate diimine ligand.<sup>40</sup> This structural deviation of the metal carbonyls from linearity is also apparent in the structure of the d<sup>6</sup> [Re(bpy-R)(CO)<sub>4</sub>](OTf) complexes (R = H, *t*Bu).<sup>41, 42</sup> Notably, complex **4** has significantly longer C–O bond lengths compared to [Re(bpy-*t*Bu)(CO)<sub>4</sub>](OTf), which is evidence of stronger back donation from the tungsten metal center. This is also reflected in the FT-IR spectra of **4** and the corresponding rhenium complex. They have similar patterns for the ν(CO) stretches in their FTIR spectra, but the stretches for the tungsten complex **4** are 116–138 cm<sup>-1</sup> lower in energy than the rhenium complex in acetonitrile.



**Figure 2.** Molecular structures of **3** (top) and **4** (bottom), with ellipsoids shown at 50% probability and hydrogen atoms excluded for clarity. Selected bond lengths and angles are listed in Table S2 in the ESI.

### Electrochemical Studies

The cyclic voltammograms of complexes **1–4** in acetonitrile are very similar, displaying one reversible reduction at ca. –1.6 V vs. SCE followed by an irreversible reduction at ca. –2.1 V vs. SCE (voltammogram for **1** shown in Figure 3, reduction potentials for **1–4** are listed in Table 1 and voltammograms of **2–4** Fig. S2). This data is similar to previously reported electrochemistry for **1** and **2** that was obtained in THF,<sup>43, 44</sup> acetonitrile (1<sup>st</sup> reduction only),<sup>45</sup> and dimethoxyethane.<sup>46, 47</sup> The first reduction of **3** has also been reported in multiple solvents.<sup>48</sup> The first reduction of these complexes is primarily localized on

the bipyridyl ligand, forming stable 19-electron  $[M(\text{bpy-R})(\text{CO})_4]^-$  species that have been previously characterized for the parent bipyridine complexes **1** and **2** by FT-IR,<sup>46</sup> UV-Vis,<sup>28</sup> and EPR spectroscopies.<sup>28, 49</sup>

5


**Table 1.** Reduction potentials vs. SCE for complexes **1–4**. All complexes were studied under the same conditions as stated for **1**.

Complex	$E_{1/2}$ (V)	$2^{\text{nd}}$ (V) <sup>a</sup>
<b>1</b>	−1.58	−2.14
<b>2</b>	−1.49	−2.08
<b>3</b>	−1.66	−2.20
<b>4</b>	−1.58	−2.15

<sup>a</sup>Irreversible, reported as the location of the peak of the irreversible wave vs. SCE during the reductive sweep in the cyclic voltammogram at 100 mV/s.

When acetonitrile solutions containing complexes **1–4** are exposed to a  $\text{CO}_2$  atmosphere, the first reduction in the cyclic voltammograms is similar to the reduction under inert atmosphere. However, at the second reduction potential, a current increase is observed ( $i_{\text{cat}}/i_{\text{p}} = 2.3, 3.4, 3.1,$  and  $3.9$  for **1, 2, 3,** and **4**, respectively, Figure 3), which is attributed to catalytic reduction of  $\text{CO}_2$ . These current enhancements occur at potentials that are similar to the peak potential of  $\text{CO}_2$  reduction by  $\text{Re}(\text{bpy-}t\text{Bu})(\text{CO})_3\text{Cl}$  (−2.1 V vs SCE).<sup>7</sup> The  $i_{\text{cat}}/i_{\text{p}}$  and the corresponding turnover frequency (TOF, Table 2) show that the tungsten complexes are more active than the molybdenum complexes, and the *tert*-butyl groups enhance the activity for both metals. Complex **4** was selected for further study as it was the most active catalyst based on cyclic voltammetry ( $i_{\text{cat}}/i_{\text{p}}$  of 3.9), but more importantly because it is isoelectronic with the well-studied fac- $\text{Re}(\text{bpy-}t\text{Bu})(\text{CO})_3\text{X}$  species so that the most appropriate comparison can be made.

Scan-rate dependence studies for complex **4** (Fig. S3 in the ESI) show that the second reduction remains irreversible even at high scan rates (ca.  $10 \text{ V s}^{-1}$ ). The irreversibility of the second reduction indicates that a chemical reaction occurs following this reduction. This can be postulated as a loss of one CO ligand, although there is only brief mention of this in the literature, and full characterization for the dianions has not been previously reported.<sup>28, 27</sup> The small oxidation wave observed at ca. −700 mV only appears after the second reduction is reached.



**Figure 3.** Representative cyclic voltammogram of **1** at a scan rate of 100


$\text{mV}\cdot\text{s}^{-1}$  under  $\text{N}_2$  (black line) and  $\text{CO}_2$  (red). Conditions: 1 mm diameter glassy carbon working electrode, platinum wire counter electrode, Ag/AgCl reference, decamethylferrocene ( $\text{FeCp}_2^*$ ) internal reference, 1 mM **1**, 0.1 M tetrabutylammonium hexafluorophosphate ( $\text{TBAPF}_6$ ), room temperature. Complexes **2, 3,** and **4** exhibit similar behavior (see ESI).

#### Controlled Potential Electrolysis

In order to study the catalytic reduction of  $\text{CO}_2$ , controlled potential electrolysis experiments were carried out with complex **4**. Care was taken to separate the counter electrode from the solution with a glass tube packed with a plug of glass wool during bulk electrolysis, because it has been shown that electrochemical oxidation of group 6  $\text{M}(\text{L})(\text{CO})_4$  complexes leads to the liberation of  $\text{CO}$ .<sup>34</sup> Bulk electrochemical reduction at −2.3 V under a  $\text{CO}_2$  atmosphere led to formation of  $\text{CO}$  with a  $109 \pm 7\%$  faradaic efficiency, as detected by gas chromatography (Fig. S4). Carbon monoxide was also observed by gas chromatography when the same experiment was performed under inert atmosphere, due to the loss of a carbonyl ligand that occurs after the second reduction. The current density under  $\text{CO}_2$  initially decreased after the start of the bulk electrolysis but stabilized at  $0.66 \text{ mA/cm}^2$ , whereas under  $\text{N}_2$  it stabilized at  $0.44 \text{ mA/cm}^2$  (Fig. S5). This verifies the catalytic activity observed in the cyclic voltammograms, and also indicates that the catalyst is highly selective for  $\text{CO}$  formation. There was no evidence of carbonate, formate, or other  $\text{CO}_2$ -derived products by NMR or FT-IR measurements of complex **4**, and therefore the reaction is likely of the form  $\text{CO}_2 + 2e^- + 2\text{H}^+ \rightarrow \text{CO} + \text{H}_2\text{O}$ , similar to the group 7 catalysts. The catalytic activity was observed to be stable over the course of several hours (Fig. S6), indicating that the compound remains active over time. Hydrogen was observed only in small quantities (less than 3% faradaic efficiency).


#### Chemical Reduction and Characterization of the Reduced Species

Crystallographic characterization of the mono or di-reduced forms of  $\text{M}(\text{bpy-R})(\text{CO})_4$  have not been reported, nor have the di-reduced species been characterized by spectroscopy. While the oxygen and proton sensitivity of these highly reduced forms makes isolation challenging, the anions and dianions of **2** and **4** were produced in yields of 40%–70% and characterized by FT-IR and NMR (ESI). After many attempts, crystal structures of the anion  $[\text{W}(\text{bpy})(\text{CO})_4]^-$  (**5**) and dianion  $[\text{W}(\text{bpy-}t\text{Bu})(\text{CO})_3]^{2-}$  (**6**) were obtained. Addition of 1 equivalent of  $\text{KC}_8$  to a solution of **2** and 18-crown-6 in THF led to the formation of a dark orange solution of the new species **5**. Vapor diffusion of pentane into a solution of **5** in THF led to black-orange crystals suitable for X-ray diffraction. Consistent with analogous anionic complexes,<sup>7, 8, 11</sup> the anionic tungsten complex crystallizes with the potassium cation enclosed in the crown ether, seen in Figure 4. The potassium is both associated with an axial carbonyl (K–O bond length of  $2.813(3) \text{ \AA}$ ) and a THF solvent molecule. The bond length alteration in the 2,2'-bipyridine ring of **5** is suggestive of substantial electron density on the ligand, supporting the assignment of the first electrochemical reduction as being ligand based.<sup>50</sup>



**Figure 4.** Molecular structure of  $[W(bpy)(CO)_4][K(18\text{-crown-6})\cdot THF]$  (**5**). Ellipsoids are shown at 50% probability. Hydrogen atoms are omitted for clarity.

Dianionic species **6** was formed by the addition of 2.2 equivalents of  $KC_8$  to a THF solution of **4** in the presence of 18-crown-6. The  $^1H$  NMR spectrum of the black-purple solution of complex **6** in  $THF-d_8$  (Fig. S9) showed signals for a diamagnetic compound, with bipyridine ligands that were significantly shifted upfield from the starting material (4.80, 6.60, and 8.47 ppm for **6** vs. 7.58, 8.40, and 9.10 ppm for **4**). This upfield shift in the C–H protons on the bipyridine ligand has also been observed in the  $[Al(bpy-H)_2]^-$  anion, which has been assigned as possessing two  $(bpy-H)^{2-}$  ligands.<sup>51</sup>



**Figure 5.** FTIR spectra of the chemically reduced species of  $W(bpy\text{-}tBu)(CO)_4$  (**4**) in THF under  $N_2$ . The neutral species **4** (black) has  $\nu(CO)$  stretches of  $2004\text{ cm}^{-1}$ ,  $1886\text{ cm}^{-1}$ , and  $1837\text{ cm}^{-1}$ . The chemically reduced anion (red)  $\nu(CO)$  stretches are  $1982\text{ cm}^{-1}$ ,  $1854\text{ cm}^{-1}$ ,  $1835\text{ cm}^{-1}$ , and  $1798\text{ cm}^{-1}$ ; the doubly reduced species **6** (blue)  $\nu(CO)$  stretches are  $1837\text{ cm}^{-1}$  and  $1713\text{ cm}^{-1}$ .


A diffracting crystal of **6** was obtained after multiple crystallization attempts. Although several issues exist with the structure, it was found to be the  $[W(bpy\text{-}tBu)(CO)_3][K(18\text{-crown-}$

$6)]_2$  species. The dianion crystallizes between two layers of the 18-crown-6 ligands, which display significant disorder (Fig. S7 in the ESI). The C9–C10 distance in **6** is significantly shorter than the corresponding bond in **4** ( $1.483\text{ \AA}$ ). The C–O distances in the carbonyl ligands of **6** are also significantly longer than those in **4**.

The lengthening of the metal-carbonyl bonds in **5** and **6** due to the increased back bonding from the metal is consistent with the FT-IR spectra of these complexes. The carbonyl stretching frequencies of complex **4** shift to a lower frequency by roughly  $30\text{ cm}^{-1}$  upon the first chemical reduction, and the subsequent reduction leads to the dianion **6**, which exhibits a band at  $1837\text{ cm}^{-1}$  and a broad band at  $1713\text{ cm}^{-1}$  as shown in Figure 5 (the IR spectra of **5** and of the dianion  $[W(bpy)(CO)_3]^{2-}$  are shown in Fig. S8 in the ESI). These  $\nu(CO)$  bands are observed at much lower frequencies than  $[Re(bpy\text{-}tBu)(CO)_3]^-$  ( $1940\text{ cm}^{-1}$  and  $1835\text{ cm}^{-1}$ ) and  $Mn(bpy\text{-}tBu)(CO)_3]^-$  ( $1911\text{ cm}^{-1}$  and  $1813\text{ cm}^{-1}$ ) anions that are isoelectronic with **6**. This indicates that the anion **6** has much stronger back donation to the antibonding  $\pi^*$  orbitals of the CO ligands than the corresponding Re or Mn monoanions with the same ligand sets.


### DFT Calculations of Catalytically Relevant Complexes

In order to obtain a deeper insight into the species formed upon electrochemical reduction of **4**, the DFT-optimized structures of the reduced species obtained from **4** were calculated. Geometry optimized structures were obtained by using the X-ray coordinates of **4** and **6** as the initial inputs to obtain the structures of the neutral form (**A**) and the five-coordinate dianion (**D**). The geometry of the mono-reduced species  $[W(bpy\text{-}tBu)(CO)_4]^-$  (**B**) and the doubly-reduced species structure  $[W(bpy\text{-}tBu)(CO)_4]^{2-}$  (**C**) were then optimized from **A** (Scheme 2). Frequency calculations were used to establish that the optimized structures were not intermediates. The crystal structure for **6** and the DFT-optimized structure of **D** are intermediate between a square pyramid and a trigonal bipyramid ( $\tau_5 = 0.44$  and  $0.46$ , respectively)<sup>52</sup> (Figure 5). Pertinent bond distances for the calculated structures and coordinates for the optimized structures are included in the ESI. The calculated  $\nu(CO)$  stretching frequencies for species **D** ( $1822$ ,  $1734$ , and  $1724\text{ cm}^{-1}$ ) agree well with the  $\nu(CO)$  band energies observed in IR for the reduced species **6** in THF ( $1837\text{ cm}^{-1}$  and a broad band at  $1713\text{ cm}^{-1}$ ). A comparison of the calculated and experimental  $\nu(CO)$  stretching frequencies for species **A–D** is included in the ESI (Table S5). The central C–C bonds in the bipyridine ligands in the dianions **C** and **D** are significantly shortened compared to **A** and **B**, with C–C bond lengths of  $1.390$  and  $1.398\text{ \AA}$  for the central C–C bond in the bipyridine ligand in the octahedral (**C**) and five-coordinate (**D**) complexes. The bond lengths for **C** and **D** are shorter than the bond lengths in the neutral complex ( $1.463$  and  $1.481\text{ \AA}$  for geometry optimization (**A**) and X-ray structure of **4**), and the monoanion (**B**) ( $1.423\text{ \AA}$ ). These results are consistent with our understanding of the system from the electrochemical and structural studies, indicating that the bipyridine accepts a significant amount of the electron density from both  $1e^-$  reductions observed in the electrochemistry of **1–4**.



**Scheme 2.** Complexes based on complex **4** that were studied using DFT calculations.

Examination of the calculated highest occupied molecular orbitals (HOMOs) and lowest unoccupied molecular orbitals (LUMOs) of complexes **A–D** provides further insights about these complexes. The calculated HOMO of the dianion **D** is delocalized over the bipyridine and somewhat over the tungsten center (Figure 6). In comparison, the LUMO, singly occupied molecular orbital (SOMO) and HOMO of **A**, **B**, and **C** are primarily localized on the bipyridine with some electron density on the CO ligands (see ESI). The calculated HOMO for species **D** is qualitatively similar to the calculated HOMO for the  $[\text{Re}(\text{bpy}-t\text{Bu})(\text{CO})_3]^{-1}$  anion, which is the reactive species in catalysis with  $\text{Re}(\text{bpy}-t\text{Bu})(\text{CO})_3\text{X}$  catalysts.<sup>8</sup> Calculations on a related species,  $[\text{Mn}(\text{bpy}-\text{H})(\text{CO})_3]^{-1}$  also showed that the HOMO of this species is delocalized over the bipyridine ligand as well as the metal center.<sup>53</sup>



**Figure 6.** Ball and stick representation of the geometry optimized structure (top) and the DFT-calculated HOMO (bottom left: top view; right: side view) of the five-coordinate dianionic species **D**.

### Comparison with Group 7 Catalysts

A comparison of the catalytic activities of **1–4** with analogous group 7 complexes is shown in Table 2. The group 6 species are similar in activity to  $[\text{Re}(\text{bpy}-t\text{Bu})(\text{CO})_3(\text{CH}_3\text{CN})](\text{OTf})$  and

more active than the corresponding Mn species under the same conditions (Mn complexes do not exhibit catalysis without added protons). Upon the addition of a proton source, the group 7 catalysts greatly outperform the W and Mo species. The effect of adding a Brønsted acid could not be quantified for the group 6 species due to the negative potentials of the second reductions being too close to the direct reduction of the acids at the electrodes in the cyclic voltammetry experiments.

While the Mo and W complexes reported herein are not exceptional electrocatalysts for  $\text{CO}_2$  reduction, their study is very valuable because it provides a framework in which to understand similar electrocatalysts, such as the group 7 species. Through comparisons of the structurally similar and isoelectronic group 6  $\text{M}(\text{bpy}-\text{R})(\text{CO})_4$  species and the group 7  $\text{M}(\text{bpy}-\text{R})(\text{CO})_3\text{X}$  species, we can understand what characteristics lead to efficient and active catalysts.

The first electrochemical reduction of both the group 6 (**1–4**) and group 7  $\text{M}(\text{bpy}-\text{R})(\text{CO})_3\text{X}$  ( $\text{M} = \text{Re}, \text{Mn}$ ) electrocatalysts proceeds through reduction of the bipyridine ligand. In the rhenium system, ligand loss (dissociation of the chloride or other X ligand) subsequently occurs from  $[\text{Re}(\text{bpy}-\text{R})(\text{CO})_3\text{X}]^{-1}$  leading to a species that can be assigned as a  $\text{Re}(0)$  center and a neutral bipyridine ligand. Ultimately, a  $\text{Re}(0)\text{--Re}(0)$  dimer is formed, and characterization of the dimer gives clear indication that the reduction has occurred at the metal center.<sup>54</sup> For manganese, reduction of a  $\text{Mn}(\text{bpy}-\text{R})(\text{CO})_3\text{X}$  species leads to extremely rapid dimerization such that monomeric  $[\text{Mn}(\text{bpy}-\text{R})(\text{CO})_3\text{X}]^{-1}$  species have not been observed spectroscopically. In stark comparison, the group 6 complexes do not lose a ligand or dimerize upon reduction, but rather the axial carbonyl becomes somewhat more susceptible to substitution.<sup>43</sup> However, the electron density remains primarily over the bipyridine ligand, and the carbonyl ligand remains strongly coordinated enough that we were able to crystallize the  $[\text{W}(\text{bpy})(\text{CO})_4]^{-1}$  anion (complex **5**), wherein the bipyridine ligand is clearly reduced. Notably, reduction of a  $[\text{Re}(\text{bpy}-\text{R})(\text{CO})_4]^+$  cation does not lead to an observable  $\text{Re}(\text{bpy}-\text{R})(\text{CO})_4$  species,<sup>42</sup> indicating that the group 6 complexes bind CO more strongly than the group 7 complexes.

A second reduction in both the group 6 and the group 7 systems leads to a diamagnetic complex with five-coordinate geometry and a similar HOMO delocalized over the metal and the bipyridine. For the rhenium complexes, XANES data suggests that these species are best described as  $\text{M}^0(\text{bpy}^{-1})$ . The second reduction in the  $\text{Re}(\text{bpy}-\text{R})(\text{CO})_3\text{Cl}$  systems is 300–400 mV more negative than the first, however the second reduction potentials of **1–4** are 540–590 mV more negative than their first reduction. This is similar to the separation observed between the 2,2'-bipyridine monoanion and dianion.<sup>55</sup> Thus it seems reasonable that they are described as  $\text{M}^0(\text{bpy}^{-2})$  species, rather than  $\text{M}^{-1}(\text{bpy}^{-1})$  or  $\text{M}^{-2}(\text{bpy}^0)$  complexes. Further studies are needed to unambiguously assign these ground states.

**Table 2.** Comparison of the catalytic activity of complexes **1-4** to relevant group 7 complexes.<sup>11</sup>

Complex	$i_{cat}/i_p$	TOF (s <sup>-1</sup> ) <sup>a</sup>
Mo(bpy)(CO) <sub>4</sub> ( <b>1</b> )	2.3	1.0
W(bpy)(CO) <sub>4</sub> ( <b>2</b> )	3.4	2.2
Mo(bpy- <i>t</i> Bu)(CO) <sub>4</sub> ( <b>3</b> )	3.1	1.9
W(bpy- <i>t</i> Bu)(CO) <sub>4</sub> ( <b>4</b> )	3.9	2.9
[Re(bpy- <i>t</i> Bu)(CO) <sub>3</sub> (CH <sub>3</sub> CN)](OTf) <sup>b</sup>	3.3	2.1
Mn(bpy- <i>t</i> Bu)(CO) <sub>3</sub> Br <sup>b</sup>	1.0	0.0
[Re(bpy- <i>t</i> Bu)(CO) <sub>3</sub> (CH <sub>3</sub> CN)](OTf) <sup>c</sup>	54	570
Mn(bpy- <i>t</i> Bu)(CO) <sub>3</sub> Br <sup>d</sup>	42	340

<sup>a</sup>TOF for **1-4** obtained using method described by Smieja et al.<sup>11</sup> <sup>b</sup>Activity under similar conditions to those used for **1-4**. <sup>c</sup>1.4 M 2,2,2-trifluoroethanol (TFE) added. <sup>d</sup>1.6 M TFE added.

These comparisons lead to two important conclusions about electrocatalysts for CO<sub>2</sub> reduction. The first is that having catalytically relevant electrons stored in both the bipyridine ligand and the metal center leads to a lower overpotential compared to having two electrons stored on the bipyridine ligand. The second conclusion about these electrocatalysts is that having a complex that strongly back-donates to CO is undesirable because it will hinder release of the product and slow overall catalysis, *i.e.* CO poisoning of the catalyst.

## Conclusions

Electrochemical experiments on groups 6 complexes **1-4** M(bpy-R)(CO)<sub>4</sub> (R = H, M = Mo (**1**), W (**2**); R = *t*Bu, M = Mo (**3**), W (**4**)) have shown that these complexes are competent catalysts for CO<sub>2</sub> reduction through a two-electron reduction process to generate a diamagnetic dianionic complex. The reduced species have been studied using X-ray crystallography, IR spectroscopy and DFT calculations. These catalysts display stronger back donation to CO than group 7 catalysts, which may explain why they operate at slower rates. Future studies will include studying the stoichiometric reactions of the reduced species with CO<sub>2</sub> and H<sup>+</sup> sources, as well as attempting to elucidate the full catalytic cycle. The catalytic cycle of CO<sub>2</sub> reduction by Re(bpy)(CO)<sub>3</sub>Cl has recently been elucidated by computational methods, and similar study of group 6 catalysts would be very informative.<sup>56</sup> Complexes **1-4** are rare examples of group 6 electrocatalysts for CO<sub>2</sub> reduction and future work will focus on developing more efficient and selective catalysts based on these relatively abundant metals.

## Acknowledgements

This material is based upon work supported by the Air Force Office of Scientific Research through the MURI program under AFOSR Award No. FA9550-10-1-0572. Dr. Jonathan M. Smieja, Dr. Eric E. Benson, Jesse Froehlich, and Matthew Sampson are acknowledged for valuable discussions and assistance with electrochemistry, chemical reductions, and crystallography. Professor Joshua Figueroa, Professor John A. Keith, Steve George, and Alissa Sasayama are acknowledged for assistance with DFT calculations.

## Notes and references

Department of Chemistry and Biochemistry, University of California, San Diego, 9500 Gilman Drive MC 0358, La Jolla, California 92093, USA. E-mail: ckubiak@ucsd.edu; Fax: 01 858 534 5383; Tel: 01 858 822 2665

50

<sup>a</sup>These authors had equal contribution.

† Electronic Supplementary Information (ESI) available: Synthesis and experimental details, additional electrochemistry results, additional FT-IR data, crystallographic data tables, and DFT Geometry optimized coordinates. The CIF files for complexes **2**, **4**, **5**, and **6** have been deposited at the CCDC, with deposition numbers of 967672, 967673, 967674, and 967675, respectively. See DOI: 10.1039/b000000x/

<sup>‡</sup> Current address: Department of Chemistry, DePaul University, 1110 W. Belden Ave, Chicago, IL, 60614.

1. E. E. Benson, C. P. Kubiak, A. J. Sathrum and J. M. Smieja, *Chem. Soc. Rev.*, 2009, **38**, 89-99.
2. J.-M. Savéant, *Chemical reviews*, 2008, **108**, 2348-2378.
3. C. D. Windle and R. N. Perutz, *Coordination Chemistry Reviews*, 2012, **256**, 2562-2570.
4. C. Costentin, M. Robert and J.-M. Saveant, *Chemical Society reviews*, 2013, **42**, 2423-2436.
5. A. M. Appel, J. E. Bercaw, A. B. Bocarsly, H. Dobbek, D. L. DuBois, M. Dupuis, J. G. Ferry, E. Fujita, R. Hille, P. J. A. Kenis, C. A. Kerfeld, R. H. Morris, C. H. F. Peden, A. R. Portis, S. W. Ragsdale, T. B. Rauchfuss, J. N. H. Reek, L. C. Seefeldt, R. K. Thauer and G. L. Waldrop, *Chemical reviews*, 2013, **113**, 6621-6658.
6. J. Hawecker, J. M. Lehn and R. Ziessel, *J. Chem. Soc., Chem. Commun.*, 1984, 328-330.
7. J. M. Smieja and C. P. Kubiak, *Inorg. Chem.*, 2010, **49**, 9283-9289.
8. J. M. Smieja, E. E. Benson, B. Kumar, K. A. Grice, C. S. Seu, A. J. Miller, J. M. Mayer and C. P. Kubiak, *Proceedings of the National Academy of Sciences of the United States of America*, 2012, **109**, 15646-15650.
9. K. A. Grice and C. P. Kubiak, in *Advances in Inorganic Chemistry*, eds. A. Michele and E. Rudi van, Academic Press, 2014, vol. Volume 66, pp. 163-188.
10. M. Bourrez, F. Molton, S. Chardon-Noblat and A. Deronzier, *Angewandte Chemie, International Edition*, 2011, **50**, 9903-9906.
11. J. M. Smieja, M. D. Sampson, K. A. Grice, E. E. Benson, J. D. Froehlich and C. P. Kubiak, *Inorganic Chemistry*, 2013, **52**, 2484-2491.
12. J. D. Froehlich and C. P. Kubiak, *Inorg. Chem.*, 2012, **51**, 3932-3934.
13. I. Bhugun, D. Lexa and J.-M. Savéant, *The Journal of Physical Chemistry*, 1996, **100**, 19981-19985.
14. C. Costentin, S. Drouet, M. Robert and J.-M. Savéant, *Science*, 2012, **338**, 90-94.
15. A. M. Lilio, K. A. Grice and C. P. Kubiak, *European Journal of Inorganic Chemistry*, 2013, **2013**, 4016-4023.
16. J. A. Ramos Sende, C. R. Arana, L. Hernandez, K. T. Potts, M. Keshevarz-K and H. D. Abruna, *Inorganic Chemistry*, 1995, **34**, 3339-3348.
17. C. J. Pickett and D. Pletcher, *J Chem Soc Dalton*, 1976, 749-752.
18. T. Reda, C. M. Plugge, N. J. Abram and J. Hirst, *Proceedings of the National Academy of Sciences*, 2008, **105**, 10654-10658.
19. H. Dobbek, L. Gremer, R. Kiefersauer, R. Huber and O. Meyer, *Proceedings of the National Academy of Sciences*, 2002, **99**, 15971-15976.
20. G. R. Lee, J. M. Maher and N. J. Cooper, *Journal of the American Chemical Society*, 1987, **109**, 2956-2962.
21. U. Jayarathne, P. Chandrasekaran, H. Jacobsen, J. T. Mague and J. P. Donahue, *Dalton Transactions*, 2010, **39**, 9662-9671.
22. L. Contreras, M. Paneque, M. Sellin, E. Carmona, P. J. Perez, E. Gutierrez-Puebla, A. Monge and C. Ruiz, *New Journal of Chemistry*, 2005, **29**, 109-115.

23. B. L. Yonke, J. P. Reeds, P. Y. Zavalij and L. R. Sita, *Angewandte Chemie International Edition*, 2011, **50**, 12342-12346.
24. W. H. Bernskoetter and B. T. Tyler, *Organometallics*, 2011, **30**, 520-527.
25. C.-C. Tai, T. Chang, B. Roller and P. G. Jessop, *Inorganic Chemistry*, 2003, **42**, 7340-7341.
26. D. J. Darensbourg and C. Ovalles, *Journal of the American Chemical Society*, 1984, **106**, 3750-3754.
27. A. n. Vlček Jr, *Coordination Chemistry Reviews*, 2002, **230**, 225-242.
28. Y. Kaizu and H. Kobayashi, *Bulletin of the Chemical Society of Japan*, 1972, **45**, 470-477.
29. T. S. A. Hor and S.-M. Chee, *Journal of Organometallic Chemistry*, 1987, **331**, 23-28.
30. E. Tolun, C. J. Proctor, J. F. J. Todd, J. M. A. Walshe and J. A. Connor, *Organic Mass Spectrometry*, 1984, **19**, 294-294.
31. M. J. Schadt and A. J. Lees, *Inorganic Chemistry*, 1986, **25**, 672-677.
32. S. Cao, K. Bal Reddy, E. M. Eyring and R. van Eldik, *Organometallics*, 1994, **13**, 91-93.
33. J. A. Connor and C. Overton, *Journal of Organometallic Chemistry*, 1983, **249**, 165-174.
34. R. Johnson, H. Madhani and J. P. Bullock, *Inorganica Chimica Acta*, 2007, **360**, 3414-3423.
35. S. S. Braga, A. C. Coelho, I. S. Goncalves and F. A. Almeida Paz, *Acta Crystallographica Section E*, 2007, **63**, m780-m782.
36. Q. Ye, Q. Wu, H. Zhao, Y.-M. Song, X. Xue, R.-G. Xiong, S.-M. Pang and G.-H. Lee, *Journal of Organometallic Chemistry*, 2005, **690**, 286-290.
37. J. Chapman, G. Kolawole, N. Long, A. J. P. White, D. J. Williams and P. O'Brien, *S. Afr. J. Sci.*, 2005, **101**, 454-456.
38. C. C. Scarborough and K. Wieghardt, *Inorganic Chemistry*, 2011, **50**, 9773-9793.
39. F. Allen, *Acta Crystallographica Section B*, 2002, **58**, 380-388.
40. C. Makedonas and C. A. Mitsopoulou, *European Journal of Inorganic Chemistry*, 2007, **2007**, 110-119.
41. T. Scheiring, W. Kaim and J. Fiedler, *Journal of Organometallic Chemistry*, 2000, **598**, 136-141.
42. K. A. Grice, N. X. Gu, M. D. Sampson and C. P. Kubiak, *Dalton Transactions*, 2013, **42**, 8498-8503.
43. D. Miholová and A. A. Vlček, *Journal of Organometallic Chemistry*, 1985, **279**, 317-326.
44. D. Miholová, B. Gaš, S. Záliš, J. Klíma and A. A. Vlček, *Journal of Organometallic Chemistry*, 1987, **330**, 75-84.
45. R. J. Crutchley and A. B. P. Lever, *Inorganic Chemistry*, 1982, **21**, 2276-2282.
46. R. E. Dessy and L. Wiczorek, *Journal of the American Chemical Society*, 1969, **91**, 4963-4974.
47. R. E. Dessy, F. E. Stary, R. B. King and M. Waldrop, *Journal of the American Chemical Society*, 1966, **88**, 471-476.
48. J. A. Connor, C. Overton and N. El Murr, *Journal of Organometallic Chemistry*, 1984, **277**, 277-284.
49. J. A. Vlček, F. Baumann, W. Kaim, F.-W. Grevels and F. Hartl, *Journal of the Chemical Society, Dalton Transactions*, 1998, 215-220.
50. E. Gore-Randall, M. Irwin, M. S. Denning and J. M. Goicoechea, *Inorg. Chem.*, 2009, **48**, 8304.
51. G. B. Nikiforov, H. W. Roesky, M. Noltemeyer and H. G. Schmidt, *Polyhedron*, 2004, **23**, 561.
52. A. W. Addison, T. N. Rao, J. Reedijk, J. van Rijn and G. C. Verschoor, *Journal of the Chemical Society, Dalton Transactions*, 1984, 1349-1356.
53. F. Hartl, P. Rosa, L. Ricard, P. Le Floch and S. Záliš, *Coordination Chemistry Reviews*, 2007, **251**, 557-576.
54. E. E. Benson and C. P. Kubiak, *Chemical communications*, 2012, **48**, 7374-7376.
55. M. Krejčík and A. A. Vlček, *Journal of Electroanalytical Chemistry and Interfacial Electrochemistry*, 1991, **313**, 243-257.
56. J. A. Keith, K. A. Grice, C. P. Kubiak and E. A. Carter, *Journal of the American Chemical Society*, 2013, **135**, 15823-15829.