

Energy & Environmental Science

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

Broader Context:

Plastic based dye solar cells present several attractive features regarding their potential use as energy source for portable rechargeable devices or in building integrated photovoltaics. One of them is beyond any doubt their low weight, which arise as a result of replacing partially or totally the thick glass slides that support the transparent conducting coatings usually employed. However, the efficiencies that can be achieved with these plastic based devices have traditionally been limited by the poor charge diffusion properties of the absorbing materials involved, which result from the low temperature processing of the absorbing materials, required to preserve the integrity of the plastic components. In this work we demonstrate a method to maximize the performance of plastic based dye solar cells based on an optimization procedure in which theoretical and experimental analysis are combined to reach the largest photocurrent achieved up to date from these devices. This serves both to better rationalize the effect of each relevant parameter on their final efficiency and to pave the way to even further future increase of their performance.



Energy & Environmental Science

ARTICLE

Maximized performance of dye solar cells on plastic: a combined theoretical and experimental optimization approach

Yuelong Li,^{a,b,†} Sol Carretero-Palacios,^{a,†} Kicheon Yoo,^{b,c,†} Jong Hak Kim,^c Alberto Jiménez-Solano,^a Chul-Ho Lee,^d Hernán Míguez^a and Min Jae Ko^{b,d,e}

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

We demonstrate that a combined optimization approach based on the sequential alternation of theoretical analysis and experimental realization gives rise to plastic supported dye solar cells for which both light harvesting efficiency and electron collection are maximized. Rationalized configurations with optimized light trapping and charge extraction are realized to achieve photoanodes on plastic prepared at low temperature that reach a power conversion efficiency of 8.55% and a 16.11 mA/cm² short circuit photocurrent, unprecedented for plastic based dye solar cell devices. Furthermore, the corresponding fully flexible designs present stable mechanical properties after several bending cycles, displaying 7.79% power conversion efficiency, average broadband internal quantum efficiency above 90%, and a short circuit photocurrent of 15.94 mA/cm², which is the largest reported value for bendable cells of this sort up to date.

Introduction

Flexible photovoltaic devices offer an alternative, versatile, adaptable and scalable energy source for ample surface areas for both indoor and outdoor applications.^{1, 2} They may replace the traditional installation approach by one based on the integration of the solar-to-electric energy conversion functionality into already existing structures, from windows to roofs, without adding load to the structures. New generation flexible solar cells can also present a wide color hue, which make them practical as elements of housing design. In this context, most photovoltaic technologies present today a branch devoted to the development of flexible energy conversion devices.³⁻⁹ The field of dye sensitized solar cells (DSCs) is not an exemption.¹⁰ Several works have reported on the development of bendable cells deposited on conducting metallic and plastic substrates.^{11, 12} While record certified power conversion efficiency (PCE) of 7.6% has been reached,¹³ average value in the field may be considered to be around 5.5%.¹⁴ These values, which are significantly lower than the record and average values attained

for rigid DSC,¹⁵ are due to the poor charge transport properties that nanocrystalline titania electrodes processed at low temperatures present. With the aim of improving its photoconductivity, relevant advances have been made by the introduction of compression techniques,¹³ novel synthetic approaches that yield enhanced inter-particle connectivity,¹⁶ or original transfer methods for fabrication of completely transparent conducting oxide-free flexible cells of high efficiency.¹⁷ Another key aspect to be considered when optimizing the performance of a solar cell is that of light harvesting. In this regards, DSCs based on plastic substrates also have their particularities. A photoanode, in which the electron diffusion length is expected to be relatively short when compared to the electrode thickness, would benefit more, as it has recently been demonstrated theoretically,¹⁸ from a specific light trapping scheme based on multiple scattering caused by high refractive index inclusions rather than by the presence of a diffuse back scattering layer, like the one typically employed in optimized DSCs on transparent conducting oxide (TCO) glass.¹⁹ The reason is that, in the former case, the electron generation function, which follows the optical absorption profile along the electrode,²⁰ is increased in regions closer to the metal contact, thus enhancing electron collection efficiency. So far, no integral approach in which both a rigorous theoretical design and experimental realization are combined together in order to maximize light absorption and charge collection to achieve a high efficiency solar cell on a plastic substrate has been reported.

Herein, we propose and demonstrate a gradual optimization strategy of DSCs deposited on plastic substrates based on the sequential modeling and experimental evaluation of the optical and electrical properties of low temperature processed nanocrystalline titania electrodes. The result is that we are able to attain DSCs that

^a Multifunctional Optical Materials Group, Instituto de Ciencia de Materiales de Sevilla, Consejo Superior de Investigaciones Científicas–Universidad de Sevilla (US-CSIC), Américo Vespucio 49, 41092 Sevilla, Spain.

^b Photo-Electronic Hybrids Research Center, Korea Institute of Science and Technology, Seoul 02792, Republic of Korea.

^c Department of Chemical and Biomolecular Engineering, Yonsei University, 03722, Republic of Korea.

^d KU-KIST Graduate School of Converging Science and Technology, Korea University, Seoul 02841, Republic of Korea.

^e Green School, Korea University, 145, Anam-ro, Seongbuk-gu, Seoul 02841, Republic of Korea.

† These authors contributed equally to this work. Correspondence and requests for materials should be addressed to H.M. and M.J.K (email: h.miguez@csic.es and mjko@kist.re.kr).

Electronic Supplementary Information (ESI) available: See DOI: 10.1039/x0xx00000x

Energy & Environmental Science

ARTICLE

display power conversion efficiencies (PCE) of 8.55%, when TCO glass is used as the counter-electrode, and a short circuit photocurrent (J_{sc}) of 16.11 mA/cm² under 1 sun illumination, which is, to the best of our knowledge, the highest achieved on plastic substrates up to date. Furthermore, in the case of fully flexible devices, when both substrates are made of plastic, a PCE of 7.79 % and a J_{sc} of 15.94 mA/cm², also under 1 sun illumination, are achieved, establishing a new J_{sc} record for this sort of bendable devices. The mechanical stability of the optimized flexible device is also analyzed, the same photovoltaic performance being retrieved after 150 bending cycles with curvature radius of 15 mm. Unlike previous approaches, we use a systematic and gradual evaluation of the theoretical designs proposed at each optimization step by means of their experimental realization and characterization. This yields designs of increasingly better performance and provides at the same time a thorough physical insight into the optical and electrical properties of such devices. Maximum light absorbance is achieved by an optical scattering configuration in which TiO₂ light scatterers of adequate size are randomly distributed at the right concentration within a photoelectrode. Simultaneously, electron collection is optimized by the incorporation of an intermediate layer with the same composition as the rest of the photoanode but without scatterers, whose role is enhancing the electrical contact between the electrode and the metal contacts without affecting the optimum optical absorption already achieved. A full description of the productive and parasitic absorption that occur in different parts of the cell allows us to provide a reliable estimation of the internal quantum efficiency of the devices, which turns out to be around 90% over a wide spectral range.

Methods

Fabrication of dye-sensitized solar cells. For the fabrication of dye-sensitized solar cells, the autoclaved TiO₂ (coined "autoTiO₂") nanoparticles are synthesized by slowly adding a mixture of titanium (IV) tetra-isopropoxide/2-propanol into distilled water in the presence of acetic acid, followed by gelation in oil bath and hydrothermal processes in a titanium autoclave.²¹ Then, the synthesized autoTiO₂ nanoparticles are collected by centrifuging and washed by EtOH for three times, which are finally re-dispersed in a mixture of EtOH/tert-butanol (v/v = 50:50) for use. The resulting autoTiO₂ nanoparticles, which present a pure anatase phase and an average radius of about 10 nm, possess better electron transport and N719 dye adsorption properties than commercial Degussa P25 TiO₂ nanoparticles. An inorganic binding agent, or nanoglue, was synthesized by the same sol-gel process as autoTiO₂ but without hydrothermal process in an autoclave,¹⁶ and following the same optimization method for its combination with commercial anatase particles within a hot compression procedure

as recently demonstrated in Ref [22]. Nanoglue containing anatase TiO₂ particles of 2.5 nm radius were added into the organic binder-free paste to induce good interparticle connection at low temperature. Large TiO₂ particles (T030, radius of 160 nm, K. K. Titan, Japan) were employed to give rise to multiple scattering within the electrode and hence enhance light harvesting at long wavelengths. The viscous organic binder-free paste made out of a combination of the three type of particles herein employed was formulated according to the typical procedure as follows: Dispersed autoTiO₂ particles, smaller particles of nanoglue, and T030 particles were mixed and further well-dispersed by tip sonication (Q500 Sonicator, Qsonica) and vigorous shaking by vortex mixer for at least 10 min each step. The weight ratio of particles from autoTiO₂, T030 and small particles of nanoglue is optimized at 55:30:15. The content of particles mixture in final pastes was fixed at 15 wt%. A similar paste without adding T030 scattering particle was also prepared following same procedure above for coating a thin adhesion layer which had thickness of approximately (2.65 ± 0.15) microns and was employed to improve the electrical contact between the photoelectrode and the indium tin oxide (ITO) contact, differentiating itself from the well-known recombination blocking layer in the field of DSCs.

The TiO₂ films were coated using doctor blade with 3M tape as spacer onto a transparent conducting plastic substrate (ITO/PEN, 200 μm thick, 15Ω/sq, transmittance of 80% at 550 nm, Peccell Tech. Inc.). TiO₂ films were dried at ambient temperature and then simply hot compressed at 130 °C for 5 min with a lamination apparatus (Creative & Innovation System, Korea). To avoid contamination and film peeling off during compression, a thin Teflon film was inserted between the TiO₂ film and the piston. Compressed films were then immersed into 0.5 mM N719 (cis-bis (isothiocyanato) bis (2, 2'-bipyridyl-4, 4'-dicarboxylato)-ruthenium (II) bis-tetrabutylammonium, Everlight) anhydrous ethanol solution for dye loading at 40 °C for 3 h with continuous shaking. For plastic cells, Pt counter-electrodes were prepared by spreading a drop of 7 mM of H₂PtCl₆•6H₂O in 2-propanol on a glass substrate (FTO/glass, 8Ω/sq, 2.3 mm thick, Pilkington TEC8), and annealed at 400 °C for 20 min after being dried at ambient temperature. For fully flexible cells, a flexible counter-electrode consisting of Pt-Ti alloy on an ITO/PEN substrate (5Ω/square, 188 μm thickness), was purchased from Peccell Technologies Inc. The two electrodes were assembled using 60 μm-thick hot melt Surlyn (Dupont 1702). The standard electrolyte solution was introduced through the drilled holes on the counter-electrode, which was composed of 0.4 M tetrabutylammonium iodide (TBAI), 0.1 M LiI, 0.02 M I₂, 0.5 M 4-tert-butylpyridine (tBP) in acetonitrile. Unless otherwise indicated, the active area of dye-adsorbed TiO₂ films was about 0.40 cm², which was measured by an image analysis program equipped with a digital microscope camera (Moticam 1000). The thickness of TiO₂

films was measured by an Alpha-step IQ surface profiler (KLA Tencor).

Photovoltaic characterization of dye-sensitized solar cells. The optical characterization of each component of the solar cell was carried out using an integrating sphere (Labsphere RTC-060-SF), a halogen lamp (Ocean Optics HL-2000) as light source, and a spectrometer (Ocean Optics USB 2000) as detector. Photocurrent-voltage measurements were performed using a Keithley 2400 source measure unit. A solar simulator (Yamashida Denso) equipped with a 1000 W Xenon lamp was used as a light source. Light intensity was adjusted employing an NREL-calibrated Si solar cell. A black mask with a proper aperture was placed on top of the cells to prevent the effect of diffuse light during measurement. The external quantum efficiency was measured using a system specifically designed for DSCs (PV measurements, Inc.).

For investigating the mechanical stability of the optimized flexible DSCs, the photovoltaic properties were recorded before and after various bending cycles (up to 180) using a cylindrical rod of radius 15 mm for the bending test.²³

Optical modelling. For calculations, the same approach applied in Ref [24] was considered. It consists on a Monte-Carlo approach in which, for each wavelength, the trajectories of 10^7 photons impinging on the cell are considered. This number guarantees convergence for all computed output variables. The system involves a general multilayer structure in which each layer of a given thickness may comprise several materials (m), each one described by the corresponding complex spectral refractive index $\tilde{n}_m(\lambda) = n_m(\lambda) + ik_m(\lambda)$, with λ the incident wavelength. In particular, from reflectance ($R(\lambda)$) and transmittance ($T(\lambda)$) measurements of simplified experimental samples of known thickness, the spectral $\tilde{n}_m(\lambda)$ values of all materials here employed, including the dye and the electrolyte extinction coefficients, are extracted after applying the formalisms described in Refs.²⁵⁻²⁷ Specifically, the optical properties of the infiltrated mesoporous dye-sensitized TiO₂ layer are defined in terms of a volumetric effective refractive index accounting for a 50% porous dye-sensitized TiO₂ film infiltrated with electrolyte, $\tilde{n}_{dye-TiO_2}^{porous}(\lambda) = 0.5(\tilde{n}_{dye-TiO_2}(\lambda) + \tilde{n}_{electrolyte}(\lambda))$. $\tilde{n}_m(\lambda)$ spectra of all materials considered in the calculations are available in the ESI Fig. S1. The trajectory of each individual photon is described by Fresnel coefficients at the interface of two layers, and by scattering Mie theory when photons interact with light scatterers. In this regard, the main novelty we introduced is the consideration of the influence of the external absorbing media on the diffuse dispersion of light described by Mie theory,²⁸ something that was neglected in previously developed approaches in the field.^{15, 29-32} To determine the trajectory of a photon, we calculate the distance l it travels before suffering either an absorption or a scattering event, through:

$$l = -\ln(r)/\alpha_{ext}$$

with r a random number fulfilling $0 < r \leq 1$, and α_{ext} the extinction coefficient accounting for both absorption (α_A^m) and scattering (α_{SC}^m) coefficients of all materials comprised in each layer:

$$\alpha_{ext} = \sum_m \alpha_A^m + \alpha_{SC}^m$$

For light scatterers, we define $\alpha_A^{scatterer} = \rho\sigma_A^{scatterer}$ and $\alpha_{SC}^{scatterer} = \rho\sigma_{SC}^{scatterer}$ with $\rho = ff_s(\%)/V_{scatterer}$ the number density of the scatterers that depends upon the volume filling

fraction ($ff_s(\%)$) and the scatterer volume ($V_{scatterer}$), and $\sigma_A^{scatterers}$ and $\sigma_{SC}^{scatterers}$ the corresponding single particle absorption or scattering cross sections calculated through Mie theory.²⁸ For the rest of cell materials, $\alpha_A^m = 4\pi k_m/\lambda$, and $\alpha_{SC}^m = 0$. If the distance l travelled by the photon is larger than the possible distance it can cover in straight light before reaching the interface between two layers, the photon reaches the layer interface and it is transmitted or reflected back according to Fresnel coefficients. Those photons concluding their trajectory at the incoming or outgoing media contribute to reflectance and transmittance, and we can distinguish between diffuse and specular reflectance ($R_d(\lambda)$ and $R_s(\lambda)$, respectively) as well as diffuse and ballistic transmittance ($T_d(\lambda)$ and $T_b(\lambda)$, respectively) through their exit angle. If the distance l travelled by the photon is shorter, either an absorption or scattering event occurs, and a new random number r' is generated. If $r' \leq \alpha_{SC}^m/\alpha_{ext}$, the photon is scattered, and a new direction (θ, ϕ) is raffled according to the angular scattering distribution defined by Mie theory. Otherwise, the photon is absorbed by one of the absorbing materials contained in that layer, and the trajectory of the photon finishes. To determine the absorbing material, another random number is generated r'' and it is compared to each of the absorption coefficients of all materials comprised in the layer, i.e., if $r'' \leq \alpha_A^m/\alpha_{ext}$, the photon is absorbed by material m . This allows us to specifically evaluate light absorbed by dye molecules within the electrode and therefore, evaluate the light harvesting of the cell $\eta_{LH}(\lambda)$, separating it from electrolyte and scatterers absorptance. Moreover, parasitic absorption in the cell can be also evaluated. In addition, calculation of the trajectory of each photon provides spatial and spectral information of absorption events. This allows us to also evaluate the optical path or distance covered by photons before absorption, as well as the electron generation function, or spectral absorption profile, $g(\lambda, x)$ as spatial location of all photons inside the cell is registered while the photon is travelling. The variable x is defined as the distance along the incident light propagation direction, with $x = 0$ set at the interface between the ITO and the nanocrystalline photoanode. Indeed, integration of $g(\lambda, x)$ in x provides $\eta_{LH}(\lambda)$, in which just absorption of dye molecules is considered.

Therefore, as input parameters it is necessary to know the thickness of each layer in the structure, the filling fraction of the materials comprising each layer, the corresponding refractive indexes of all materials in each layer, and the particle radius if light scatterers are included. Importantly, with this model all optical magnitudes are evaluated without any fitting parameters.

Electrical modelling. Regarding the electrical part of the model, we assume an electron diffusion model like that originally proposed by Södergren et al. in ref. 20, and whose validity has been confirmed in numerous occasions afterwards. We assume, in a first approximation, that the electron recombination is linear, and take as the only fitting parameter the 'effective' electron diffusion length, L_e , that accounts for the average distance covered by the electron before recombination.¹⁸ This is the simplest electrical model to be employed in which all microscopic (intra-grain) and mesoscopic (inter-grain) electron transportation processes are gathered together in L_e (without the chance of discriminating processes). The $\eta_{EQE}(\lambda)$, is affected by four partial efficiencies,

Energy & Environmental Science

ARTICLE




Figure 1. Schematic illustration of the final fabrication process of a plastic dye solar cell on flexible ITO/PEN substrate containing the necessary optimization steps. (a) A thin adhesion layer was coated by doctor blade method with 3M tape as a spacer from an organic binder free paste which was prepared by dispersing 2.5 nm radius nanoglue nanoparticles (NPs) with 10 nm radius TiO_2 NPs into the mixture solvent of EtOH and tert-butanol. (b) Main TiO_2 layer was coated with same method but with a 160 nm radius scattering NPs added paste. (c) Hot pressing, that is, physically pressing at 100 MPa simultaneously with heating at 130 °C to synergistically enhance the interconnection of TiO_2 NPs. (d) Dye soaking of TiO_2 film. (e) Electrolyte infiltration, and assembling dye sensitized TiO_2 film with a thermoplastic surlyn and a counter electrode composing of catalytic Pt layer on ITO/PEN substrate. (f) Hot sealing of electrodes by thermoplastic surlyn for a plastic dye solar cell.

namely, light harvesting efficiency (or absorbance) $\eta_{\text{LH}}(\lambda)$, electron collection efficiency $\eta_{\text{col}}(\lambda)$, electron injection efficiency $\eta_{\text{inj}}(\lambda)$, and dye regeneration efficiency $\eta_{\text{reg}}(\lambda)$:

$$\eta_{\text{EQE}}(\lambda) = \eta_{\text{LH}}(\lambda)\eta_{\text{col}}(\lambda)\eta_{\text{inj}}(\lambda)\eta_{\text{reg}}(\lambda) \quad (1)$$

Collection efficiency is determined by spatial integration of the electron generation function weighted by the fitting parameter L_e :

$$\eta_{\text{col}}(\lambda) = \frac{\int_0^d g(\lambda, x) \frac{\cosh(\frac{d-x}{L_e})}{\cosh(\frac{d}{L_e})} dx}{\int_0^d g(\lambda, x) dx} \quad (2)$$

being d the total electrode thickness. Electron collection is thus herein considered as the result of electron diffusion through the nanocrystalline network and the transfer to the ITO and, from there, to the metal contact. In addition, our full optical and electrical model allows evaluating the internal quantum efficiency

$\eta_{\text{IQE}}(\lambda)$ defined as:

$$\eta_{\text{IQE}}(\lambda) = \eta_{\text{EQE}}(\lambda)/\eta_{\text{LH}}(\lambda) = \eta_{\text{col}}(\lambda)\eta_{\text{inj}}(\lambda)\eta_{\text{reg}}(\lambda) \quad (3)$$

Moreover, since the inclusion of light scatterers within the photoelectrode affects both $\eta_{\text{LH}}(\lambda)$ and $\eta_{\text{col}}(\lambda)$, while it can be assumed that it has a negligible effect on the injection and regeneration efficiencies, we can take $\eta_{\text{inj}}(\lambda) = \eta_{\text{reg}}(\lambda) = 1$ rendering the internal quantum efficiency and charge collection efficiency equivalent:

$$\eta_{\text{IQE}}(\lambda) = \eta_{\text{EQE}}(\lambda)/\eta_{\text{LH}}(\lambda) = \eta_{\text{col}}(\lambda) \quad (4)$$

All predictions and fittings herein presented have been carried out using this model.




Figure 2. (a) Experimental J-V curves of plastic cells. Square black symbols correspond to an (8.60 ± 0.05) microns electrode without scatterers, and circular red ones to an electrode of the same thickness with 30% of titania particles of radius 160 nm. (b) Experimental (symbols) and theoretical (solid lines) $\eta_{EQE}(\lambda)$ spectra for the same systems as in panel (a). The “effective” electron diffusion length is taken to be $L_e = 8$ microns. (c) Corresponding calculated $\eta_{IQE}(\lambda)$ (or equivalently $\eta_{col}(\lambda)$) curves and (d) $\eta_{LH}(\lambda)$ (or absorptance) spectra. (e) and (f) electron generation functions, or spectral absorption profiles $g(\lambda, x)$ of each photoelectrode as a function of x and λ for a (e) reference cell without scatterers and (f) a DSC with 30% of light scatterers ($r = 160$ nm).

Results and discussion

In what follows we will describe the optimization procedure followed to obtain a highly efficient flexible solar cell, maximizing light harvesting and electron collection by introducing gradual changes in the electrode structure. Our optimization approach is based on the sequential maximization of optical absorption and charge transport in four steps: first a reference DSC on a plastic substrate with a rigid counter-electrode is devised; second, TiO_2 scatterers of optimal size and concentration are randomly distributed within the electrode to enhance light absorption; third, electron collection is enlarged by including an intermediate adhesion layer between the contact and the electrode of the previous DSC already optimized optically; and finally, the rigid counter-electrode is replaced with a plastic film to realize the fully flexible version. Partial results of each of the optimization steps just mentioned will be shown along this work. As a result of this study, we reach a final experimental procedure to attain the optimum design of a highly efficient mechanically stable flexible DSC, which constitutes one the main contributions of our work and is

schematized in Fig. 1. First, a thin layer (< 3 microns) made of low sintering temperature nanocrystalline titania is deposited on an ITO coated plastic substrate (Fig. 1a) in order to maximize the electrical contact between the photoanode and the transparent conductor; on top of this, a titania film containing a multimodal distribution of crystals with sizes comprised in three well defined ranges, so they can serve to build a chemically glued mesostructure containing light scatterers, is casted (Fig. 1b); hot compression (Fig. 1c) and dye soaking of the film (Fig. 1d) follows; finally, a platinumized conducting plastic substrate is added as counter-electrode (Fig. 1e), and the electrodes are hot sealed with a thermoplastic (Fig. 1f).

Each modification in the electrode structure was realized following the guidelines extracted from a detailed electrical and optical theoretical model of the cell, whose full description can be found in the Methods section. In brief, it consists on a Monte Carlo approach in which the trajectory of individual photons defined by Fresnel coefficients at the interface of two material layers, and scattering Mie theory when light scatterers are considered, is fully accounted for. By collecting all photons concluding their trajectory at the incoming or outgoing media, we can evaluate reflectance and transmittance and distinguish diffuse light through their exit angle. Those photons finishing their trajectory inside the DSC contribute to the absorption of the cell, our model being capable of discriminating between productive (photons absorbed by dye molecules) and parasitic (photons absorbed by any other material comprising the cell) absorption. With our model we can evaluate all optical magnitudes not only spectrally but also spatially (inside each component of the cell) thus yielding the electron generation function (or spectral absorption profile) $g(\lambda, x)$ and, most importantly, without employing any fitting parameters. Concerning the electrical magnitudes, the only fitting parameter enters the model via the electrical part, when the external quantum efficiency $\eta_{EQE}(\lambda)$ is calculated through an ‘effective’ electron diffusion length, L_e , that accounts for the average distance covered by the electron before recombination. This theoretical model was first employed to evaluate the reference cell, i.e., that without any kind of electrode structuring and/or light scatterers. Such DSCs were prepared on standard conducting plastic substrates, namely ITO coated Polyethylene naphthalate (ITO-PEN), following a combination of chemical and physical sintering.²² This method relies on the use of a bimodal distribution of particles in the precursor paste, the smaller ones being of the order of a few nanometers and the larger with an average size of around a few tens of nanometers. The former ones serve as a sort of nanoglu capable of enhancing the connectivity, and hence the electrical and mechanical properties, of the photoanode.¹⁶ The compression at low temperature of this paste results in the formation of a mesoporous film with improved charge transport properties. In our case, and in order to maximize the efficiency with photoanodes built by this method, we use autoclaved nanocrystalline titania particles (auto TiO_2), following a procedure, as described in the Methods section, which provides films with better dye adsorption and charge transport properties than commercial particles.³³ Besides, a highly transparent electrolyte is prepared to minimize parasitic absorption losses in the cell. The results of the photovoltaic characterization of solar cells containing these compressed nanoglued

Energy & Environmental Science

ARTICLE

photoanodes of approximately (8.60 ± 0.05) microns are presented in Fig. 2. Analysis of the current density-voltage (J-V) curve of the reference cell prepared using this combined chemical and physical sintering method, displayed as a black squares curve in Fig. 2a, yields an overall PCE of 5.94%. Although it is a relatively high value for a transparent cell, the analysis of these first cells unconcealed the need of improving both light harvesting and electron collection in order to enhance the performance of the plastic substrate based device. Indeed, a first look at the $\eta_{EQE}(\lambda)$ plotted as black squares in Fig. 2b, reveals that light absorption of the dye is meaningful, but it is still inefficient in the wavelength range above 600 nm. With our model, we evaluate $\eta_{EQE}(\lambda)$, $\eta_{IQE}(\lambda)$ and $\eta_{LH}(\lambda)$ for the same reference cell. All magnitudes are displayed in Fig. 2b, 2c and 2d as solid, dashed and dash-dotted lines, respectively. From the fitting of $\eta_{EQE}(\lambda)$ and the calculation of $\eta_{LH}(\lambda)$, we notice that, while light absorption by the dye is close to saturation for blue and green photons, it drops significantly for red ones. Also, the estimated $\eta_{IQE}(\lambda)$ (or equivalently $\eta_{col}(\lambda)$) is around 85% for the former and only 70% for the latter, revealing that charge collection is not optimal and that it presents significant wavelength dependence. This is characteristic of electrodes in which the electron average diffusion length is shorter than the one required to effectively collecting all photocarriers, hence being charge collection very sensitive to the precise profile of the electron generation function, of $g(\lambda, x)$, which is plotted in Fig. 2e. In this contour plot it can be readily seen that red photons are absorbed at longer distances from the metal contact as a result of the smaller absorption coefficient of the dye at those wavelengths, their absorption being therefore more affected by a short L_e . In fact, the best fit of $\eta_{EQE}(\lambda)$ for the reference cell is found for $L_e = 8$ microns. Although this is a respectable value for a non-thermally sintered electrode, our model allows us to identify it as the main responsible, along with the observed insufficient long wavelength absorption, for the limited performance of the device of reference.

In order to tackle the low red photon absorption observed, we employed an optimization procedure based on the evaluation of numerous optical configurations. Both back diffuse scattering layers and intra-electrode multiple scattering configurations were theoretically analyzed (Fig. S2 in ESI). In this latter case, a wide range of spherical titania particle radius and concentrations were considered, and different electrode thicknesses covering the experimental error were compared. The response of systems differing 50 nm in thickness was the same. Best results were attained for those configurations in which light harvesting is augmented as a result of light trapping caused by multiple scattering due to inclusions in the nanocrystalline photoanode. Calculations also showed that this approach presents a high degree of tolerance, as a wide range of particle sizes (between 100 nm and 200 nm radius) and concentrations (filling fractions ff_s between 10% and 30%) gave rise to similar absorption enhancements (Fig. S3

and S4 in ESI). Upper limits of particle concentration are not absolute, as the model is not applicable for concentrations above 30%. Moreover, our theoretical analysis shows that the use of structured electrodes with a multilayer architecture,¹² in which the concentration of light scatterers is gradually increased as the incident light enters the electrode, yields slightly less efficient cells than those made of electrodes containing just a single concentration of scatterers (Fig. S4 in ESI). This is more clearly seen through the analysis of the solar spectrum weighted integrated absorption (η_{SSWIA}), defined as the fraction of light absorbed by dye molecules weighted across the solar spectrum (AM1.5), between 400 and 800 nm

$$\eta_{SSWIA} = \frac{\int_{400}^{800} \eta_{LH}(\lambda) \cdot AM1.5 d\lambda}{\int_{400}^{800} AM1.5 d\lambda} \quad (5)$$

With this definition, the SSWIA would be directly proportional to the estimated short circuit photocurrent if a charge collection efficiency of 100% is assumed. In Fig. S4b in ESI it can be seen that the SSWIA in electrodes composed of several layers, each one containing particles of similar size at different concentrations, remains practically the same as in simple electrodes containing just a single particle concentration (above concentrations of 10%). These effects evidence the high tolerance of the system to changes in particle concentration and size as long as they are kept within certain boundaries.²⁹ The experimental realization of one of these optimized designs, containing scattering centers with a radius of 160 nm, gave rise to a plastic substrate based solar cell that showed an abrupt increase of PCE up to 7.1%, as extracted from its J-V characteristics (red circles in Fig. 2a). Results for $\eta_{EQE}(\lambda)$, $\eta_{IQE}(\lambda)$ (or equivalently $\eta_{col}(\lambda)$), and $\eta_{LH}(\lambda)$ are shown in red in Fig. 2b, 2c and 2d, respectively. This enhancement is undoubtedly due to the enhanced light harvesting at long wavelengths caused by multiple scattering, as revealed by the measured $\eta_{EQE}(\lambda)$ (red circles in Fig. 2b), which is in good agreement with the calculated $\eta_{LH}(\lambda)$ of the electrode with embedded scatterers (red line in Fig. 2d). In addition, the inclusion of light scatterers is responsible for the lower $\eta_{LH}(\lambda)$ at short wavelengths as they absorb light mainly in the blue range. Furthermore, our results also show that the predicted $\eta_{IQE}(\lambda)$ (red line in Fig. 2c) is slightly improved for shorter wavelengths. While our analysis demonstrate that the electron diffusion length (estimated to be $L_e = 8$ microns) is not influenced by the presence of scatterers, the electron generation function or spatial distribution of absorption, $g(\lambda, x)$, on the contrary, is strongly affected by multiple scattering events occurring within the electrode, as it can be seen in Fig. 2f, in which the absorption profile of a cell containing light scatterers is displayed. Comparison between these two absorption maps shows explicitly that multiple scattering not only provides larger overall light harvesting, but also that absorption takes place closer to the ITO contacts for shorter wavelengths, which improves the amount of collected photocarriers and therefore, also enhances $\eta_{IQE}(\lambda)$ at short wavelengths. Please notice that this sort of insight can only be provided because our model permits discriminating between productive and parasitic absorption in each part of the cell. Details of the spectral absorption

Energy & Environmental Science

ARTICLE




Figure 3. (a) Theoretical results of reflectance (left panel), absorbance (intermediate panels) and transmittance (right panel) for the same systems as those considered in Figure 2. Lines correspond to a reference cell without scatterers, and symbols with lines to a cell with 30% scatterers ($r = 160$ nm). The cell is illuminated from the PEN substrate. Dashed grey line accounts for 0 reflectance, absorbance or transmittance. Diffuse and specular reflectance are labeled by $R_d(\lambda)$ and $R_s(\lambda)$, respectively, and diffuse and ballistic transmittance by $T_d(\lambda)$ and $T_b(\lambda)$, respectively. Each absorbance panel correspond to each element comprising the cell: [a+b] PEN and ITO substrate, [c] electrode (distinguishing each component, i.e., dye molecules, electrolyte and TiO_2 scatterers in the case of the electrode containing light scatterers), [d] electrolyte, and [e+f+g] counter electrode (platinized FTO and glass). (b) Schematic of the multilayer DSC containing light scatterers, displaying corresponding slab thicknesses.

dependence of each material within each medium, as well as of the other relevant optical parameters (diffuse, R_d , and specular, R_s , reflectance; diffuse, T_d , and ballistic, T_b , transmittance), are presented in Fig. 3, where symbol and solid line graphs correspond to cells with and without scatterers, respectively. Interestingly, improvement of productive absorption when TiO_2 scattering particles are included also gives rise to a slight increase of parasitic absorption, as diffuse scattering within the cell also increases the optical path length along the electrolyte and the ITO coating. Besides, the inclusion of light scatterers yields larger diffuse reflectance and transmittance, which renders the device translucent. To analyze the effect of multiple scattering on the effective optical path travelled by photons in the photoanode, in Fig. S5 of ESI section we plot the histograms corresponding to the number of absorbed photons *versus* distance travelled by those photons before absorption. Data are shown for photons of $\lambda = 650$ nm and for two cells, one containing light scatterers and another without them. In cells deprived of light scatterers, photons are only absorbed as they cross along the electrode thickness (8.5 microns) or, although to a much less extent, after being back reflected at the counter-electrode. In contrast, in cells containing light scatterers, as

the photon incoming direction is successively changed after several scattering events, the optical path is increased up to values as large as ~ 40 microns, which may be considered as the effective electrode thickness.

Analysis of these first samples show that light harvesting absorption within the cell is close to optimum after introducing scattering centers in the electrode, while charge collection is still insufficient. This was confirmed by building a much thicker photoanode with an approximate 11.3 micron thick mesoporous titania film, with and without scatterers (Fig. S6 in ESI). The cell with scatterers yielded only 7.23% PCE (Table 1), which implies a weak improvement with respect to the cell made with an approximate 8.5 micron thick electrode with the same internal structure (7.1% PCE), in spite of being around a 50% thicker. In order to further raise electron collection, we opted for improving the electrical contact between the scatterer embedded nanocrystalline electrode and the ITO. To this aim, a structured electrode consisting of a thinner 2.65 ± 0.15 micron intermediate layer, which we will refer to as “adhesion layer” from here onwards, made with the basic nanoglued titania but without scatterers, was deposited onto the ITO before coating it with a highly diffusive 9.15 ± 0.65 microns

Energy & Environmental Science

ARTICLE

Table 1. Photovoltaic characterization of cells with various anode and cell structures. “rigid” indicates the counter electrode is made of a rigid Pt/FTO/Glass arrangement while the counter electrode for “flexible” is Pt/ITO/PEN. “SL” stands for single layer, without an adhesion layer, and “BL” for bilayer in which the anode structure employs an adhesion layer which contains no scattering particles. The substrate for the anode is the flexible ITO/PEN for all cases. The active area of dye-adsorbed TiO₂ films was about 0.4 cm².

sample	J_{sc} (mA/cm ²)	V_{oc} (V)	FF	PCE (%)	d (μm)	Area (cm ²)
SL-without scatterers-rigid	12.25	0.681	0.712	5.94	8.60±0.05	0.387
SL-with scatterers-rigid	13.61	0.704	0.741	7.10	8.60±0.05	0.409
SL-with scatterers-rigid	14.06	0.697	0.737	7.23	11.80±0.50	0.432
BL-with scatterers-rigid	16.11	0.729	0.728	8.55	11.80±0.50	0.390
BL-with scatterers-flexible	15.94	0.719	0.679	7.79	11.80±0.50	0.350




Figure 4. (a) Experimental J-V curve for a plastic cell with a total structured electrode thickness of (11.80 ± 0.50) microns consisting of a first (2.65 ± 0.15) micron adhesion layer without scatterers, and a second layer on top with 30% of nanoparticles of radius 160 nm. The schematics in the inset represent the considered electrode. (b) Experimental (symbols) and theoretical (solid lines) $\eta_{EQE}(\lambda)$ spectra for the same system as that in panel (a). The effective electron diffusion length estimated from the fitting is $L_e = 16$ microns. Corresponding calculated $\eta_{IQE}(\lambda)$ curves are displayed with dashed lines.

thick electrode containing light scatterers (filling fraction of 30%, and $r = 160$ nm). This approach was suggested by the observation that the electrodes containing light scatterers presented a slightly higher probability of delamination than scatterer free pastes, indicating that the former might not be properly adhered to the substrate and hence having potentially a poorer electrical contact. In Fig. 4a and 4b, the experimental J-V curves and $\eta_{EQE}(\lambda)$, attained for the adhesion improved electrodes, are displayed with red circles, respectively. In this case, the PCE is 8.55%, which, as far as we know, is the highest reported for a cell containing a photoanode deposited on a plastic substrate. Interestingly, the estimated $\eta_{LH}(\lambda)$ is basically the same as it was before including the intermediate adhesion layer, while the estimated effective electron diffusion length is doubled ($L_e = 16$ microns) and the $\eta_{IQE}(\lambda)$ is significantly higher, being now a few points above 90% for $\lambda < 600$ nm and above 85% for longer wavelengths. Direct comparison of $\eta_{LH}(\lambda)$ between cells containing electrodes of ~ 8 micron and ~ 11 micron total electrode thickness, with and without scatterers and with and without adhesion layer are shown in Fig. S6 in ESI. Also in that figure, the optical absorption profiles of cells with scatterers, with and without the adhesion layer, are displayed, presenting identical light absorbance between pairs of comparable systems. Thus, the PCE enhancement observed should be attributed to the improved electron collection derived from the presence of the adhesion layer.

Once both light harvesting and electron collection were optimized for a cell containing a plastic substrate based photoanode, a fully flexible version of the cell was built by substituting the FTO coated glass, employed as counter-electrode during the optimization process, by a platinized ITO coated PEN substrate. Comparison of the theoretical parasitic and productive absorbance of the optimized cell employing either a flexible or rigid counter electrode is shown in Fig. S7 and Fig. S8 in ESI, respectively. Results of the photovoltaic characterization of one of these cells are shown in Fig. 5, together with a scheme of the cell and a photograph of the bendable device. In Table 1, the relevant photovoltaic parameters are listed for all the different cells built during the optimization process. The optimum flexible cell

Energy & Environmental Science

ARTICLE




Figure 5. (a) Experimental J-V curve for a flexible cell with a total structured electrode thickness of (11.80 ± 0.50) microns consisting on a first (2.65 ± 0.15) microns layer without scatterers, and a second layer on top with 30% of light scatterers ($r = 160$ nm). (b) Experimental (symbols) and theoretical (solid lines) $\eta_{EQE}(\lambda)$ spectra for the same system as that considered in panel (a). The effective electron diffusion length estimated from the fitting is $L_e = 16$ microns. Corresponding calculated $\eta_{IQE}(\lambda)$ curves are displayed with dashed lines. (c) Image of the fabricated flexible dye solar cell.




Figure 6. Normalized photonic characterization (J_{sc} in panel (a), V_{oc} in panel (b), FF in panel (c) and PCE in panel (d)) of the optimized flexible cell in Figure 5 as a function of bending cycles with radius 15 mm.

displayed a PCE of 7.79% and, importantly, a short circuit photocurrent of $J_{sc} = 15.94$ mA/cm², which is, to the best of our knowledge, the highest reported so far for a flexible DSC, being even above that attained for flexible cells of record efficiency (15.2 mA/cm²).¹² Further enhancement of the PCE could be achieved by increasing the fill factor which, as it can be seen in Table 1, drops by an 8% with respect to the optimized cell built using FTO-glass for the counter electrode. This is likely caused by the poorer catalytic activity of the plastic based counter-electrode, as it has been demonstrated elsewhere.³⁴ Most importantly, the $\eta_{EQE}(\lambda)$ of the flexible device remains almost unaltered with respect to that of the optimized rigid device. Overall, these cells consistently show PCE values above 7.5%. For better comparison, Fig. S9 in ESI displays $\eta_{IQE}(\lambda)$ for all cells herein considered. Starting from the reference cell, the first improvement of the internal quantum efficiency observed at short wavelengths when light scatterers are considered is linked to light absorption occurring closer to the contact, as demonstrated by electron generation functions in Fig. 2e and 2f. The abrupt enhancement of average 10% retrieved when the adhesion layer is incorporated in the structured electrode accounts for an improvement of the electron collection, as confirmed by the enlargement of the electron diffusion length while light harvesting remains almost unaltered.

The mechanical stability of the optimized flexible DSC was also investigated by a repeated bending test using a cylindrical rod of

Energy & Environmental Science

ARTICLE

radius 15 mm. The photovoltaic properties were recorded before and after various bending cycles. Figure 6 shows the normalized photovoltaic characterization (J_{SC} , V_{OC} , FF, and PCE) of the designed flexible DSC analysed in Figure 5. These results demonstrate that this device presents an excellent tolerance to bending tests, reserving all photovoltaic properties after 150 bending cycles, after which the cell performance becomes slightly worse, its J_{SC} decreasing by 10% and its PCE by 15%. The origin of this lowering of J_{SC} and V_{OC} may be attributed to the presence of microcracks generated within the inorganic titania electrode as a consequence of the repeated bendings. As FF mainly accounts for the electrical conductivity of the thin ITO layer, which shows a better mechanical stability than the thick TiO_2 layer, its value remains constant after several bending cycles.²³

Conclusion

In summary, we have presented a combined theoretical and experimental optimization procedure to build highly efficient dye solar cells on plastic substrates with maximized light harvesting and charge collection efficiencies, which are attained following the guidelines of a rigorous and complete optical and electrical model of the cell. The optimized design includes a dispersion of scatterers to reinforce light absorption over the whole spectral range at which the dye absorbs (leading to saturation absorption), and structuring of the electrode incorporating an adhesion layer to enhance charge collection. A synthetic route to prepare these electrodes at low temperature based on a combination of chemical and physical sintering is employed. An analysis of the effect of introducing gradual changes in the electrode structure have allowed us rationalizing the importance of each variable and quantifying its relevance. We have demonstrated that by using this approach it is possible to build DSCs on plastic electrodes with record PCE as high as 8.55%, and fully flexible DSCs with efficiencies as high as 7.79%. In this latter case, the photocurrent reaches a value of 15.94 mA/cm², above the highest value previously reported for a flexible DSC device (15.2 mA/cm²).¹² Moreover, bending tests prove that the optimized design of flexible DSCs is mechanically stable, photovoltaic performance being preserved after 150 bending cycles. We foresee our work may have an impact in the fields of building integrating photovoltaics and in that of rechargeable portable devices, for which light weight and adaptability of energy suppliers are key aspects.

Acknowledgements

Financial support of the European Research Council under the European Union's Seventh Framework Programme (FP7/2007–2013)/ERC grant agreement n° 307081 (POLIGHT) and

the Spanish Ministry of Economy and Competitiveness under grant MAT2014-54852-R is gratefully acknowledged. YL acknowledges the financial support from the People Programme (Marie Curie Actions) of the European Union's Seventh Framework Programme FP7/2007–2013/ under REA grant agreement n° 622533. AJS thanks Spanish Ministry of Economy and Competitiveness for funding through an FPI program under the project MAT2011–23593. MJK acknowledges funding support from the Global Frontier R&D Program on Center for Multiscale Energy System (2012M3A6A7054856), the Technology Development Program to Solve Climate Changes (2015M1A2A2056824) and 2015 University-Institute cooperation program funded by the National Research Foundation under the Ministry of Science, ICT & Future Planning, Korea; This work was also supported by the KIST institutional programs.

Notes and references

- 1 M. Pagliaro, G. Palmisano and R. Ciriminna, *Flexible Solar Cells*, WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim, 2008.
- 2 J. Jean, P. R. Brown, R. L. Jaffe, T. Buonnassisi and V. Bulovic, *Energy Environ. Sci.*, 2015, **8**, 1200-1219.
- 3 F. C. Krebs, S. A. Gevorgyan and J. Alstrup, *J. Mater. Chem.*, 2009, **19**, 5442-5451.
- 4 Z. Fan, H. Razavi, J.-w. Do, A. Moriwaki, O. Ergen, Y.-L. Chueh, P. W. Leu, J. C. Ho, T. Takahashi, L. A. Reichertz, S. Neale, K. Yu, M. Wu, J. W. Ager and A. Javey, *Nat. Mater.*, 2009, **8**, 648-653.
- 5 B. Kippelen and J.-L. Brédas, *Energy Environ. Sci.*, 2009, **2**, 251-261.
- 6 I. J. Kramer, G. Moreno-Bautista¹, J. C. Minor, D. Kopilovic and E. H. Sargent, *Appl. Phys. Lett.*, 2014, **105**, 163902.
- 7 B. J. Kim, D. H. Kim, Y.-Y. Lee, H.-W. Shin, G. S. Han, J. S. Hong, K. Mahmood, T. K. Ahn, Y.-C. Joo, K. S. Hong, N.-G. Park, S. Lee and H. S. Jung, *Energy Environ. Sci.*, 2015, **8**, 916-921.
- 8 A. Chirilă, S. Buecheler, F. Pianezzi, P. Bloesch, C. Gretener, A. R. Uhl, C. Fella, L. Kranz, J. Perrenoud, S. Seyrling, R. Verma, S. Nishiwaki, Y. E. Romanyuk, G. Bilger and A. N. Tiwari, *Nat. Mater.*, 2011, **10**, 857-861.
- 9 S.-M. Lee, R. Biswas, W. Li, D. Kang, L. Chan and J. Yoon, *ACS Nano*, 2014, **8**, 10507-10516.
- 10 W. Guo, X. Zhang, R. Yu, M. Que, Z. Zhang, Z. Wang, Q. Hua, C. Wang, Z. L. Wang and C. P. Pan, *Adv. Energy Mater.*, 2015, **5**, DOI: 10.1002/aenm.201500141.
- 11 S. Ito, N.-L. C. Ha, G. Rothenberger, P. Liska, P. Comte, S. M. Zakeeruddin, P. Pechy, M. K. Nazeeruddin and M. Grätzel, *Chem Commun.*, 2006, 4004-4006.
- 12 H. Arakawa, T. Yamaguchi, T. Sutou, Y. Koishi, N. Tobe, D. Matsumoto and T. Nagai, *Curr. Appl. Phys.*, 2010, **10**, S157-S160.
- 13 T. Yamaguchi, N. Tobe, D. Matsumoto, T. Nagai and H. Arakawa, *Sol. Energ. Mat. Sol. Cells*, 2010, **94**, 812-816.
- 14 K. Miettunen, J. Halme and P. Lund, *WIREs Energy Environ.*, 2013, **2**, 104-120.

- 15 A. Yella, H. W. Lee, H. N. Tsao, C. Y. Yi and A. K. Chandiran, M. K. Nazeeruddin, E. W-G. Diao, C.-Y. Yeh, S. M. Zakeeruddin, M. Grätzel, *Science*, 2011, **334**, 1203-1203.
- 16 Y. Li, W. Lee, D. K. Lee, K. Kim, N. G. Park and M. J. Ko, *Appl. Phys. Lett.*, 2011, **98**, 103301.
- 17 K. Yoo, J.-Y. Kim, J. A. Lee, J. S. Kim, D.-K. Lee, K. Kim, J. Y. Kim, B. Kim, H. Kim, W. M. Kim, J. H. Kim and M. J. Ko, *ACS Nano*, 2015, **9**, 3760-3771.
- 18 F. E. Gálvez, E. Kemppainen, H. Míguez and J. Halme, *J. Phys. Chem. C*, 2012, **116**, 11426-11433.
- 19 S. Ito, S. M. Zakeeruddin, R. Humphry-Baker, P. Liska, R. Charvet, P. Comte, M. K. Nazeeruddin, P. Pechy, M. Takata, H. Miura, S. Uchida and M. Grätzel, *Adv. Mater.*, 2006, **18**, 1202.
- 20 S. Södergren, A. Hagfeldt, J. Olsson and S. E. Lindquist, *J. Phys. Chem.*, 1994, **98**, 5552-5556.
- 21 A. Zaban, S. Ferrere, J. Sprague and B. A. Gregg, *J. Phys. Chem. B*, 1997, **101**, 55-57.
- 22 Y. Li, K. Yoo, D.-K. Lee, J. Y. Kim, H. J. Son, J. H. Kim, C.-H. Lee, H. Míguez and M. J. Ko, *RSC Adv.*, 2015, **5**, 76795-76803.
- 23 Y. Li, D.-K. Lee, J. Y. Kim, B. Kim, N.-G. Park, K. Kim, J.-H. Shin, I.-S. Choi and M. J. Ko, *Energy Environ. Sci.*, 2012, **5**, 8950-8957.
- 24 J. M. Miranda-muñoz, S. Carretero-Palacios, A. Jiménez-Solano, Y. Li, G. Lozano and H. Míguez, *J. Mater. Chem. A*, 2016, **4**, 1953-1961.
- 25 E. Nichelatti, *J. Opt. A: Pure Appl. Opt.*, 2002, **4**, 400-403.
- 26 R. Santbergen, H. Tan, M. Zeman and A. H. M. Smets, *Opt. Express*, 2014, **22**, A1023-A1028.
- 27 M. Anaya, G. Lozano, M. E. Calvo, W. Zhang, M. B. Johnston, H. J. Snaith and H. Míguez, *J. Phys. Chem. Lett.*, 2015, **6**, 48-53.
- 28 I. W. Sudiarta and P. Chylek, *J. Opt. Soc. Am. A*, 2001, **18**, 1275-1278.
- 29 F. E. Gálvez, P. R. F. Barnes, J. Halme and H. Míguez, *Energy Environ. Sci.*, 2014, **7**, 689-697.
- 30 J. Ferber and J. Luther, *Sol. Energy Mater. Sol. Cells*, 1998, **54**, 265-275.
- 31 A. Usami, *Sol. Energy Mater. Sol. Cells*, 2000, **64**, 73-83.
- 32 G. Rothenberger, P. Comte and M. Grätzel, *Sol. Energy Mater. Sol. Cells*, 1999, **58**, 321-336.
- 33 Y. Li, K. Yoo, D.-K. Lee, J. Y. Kim, H. Kim, B. Kim and M. J. Ko, *Nanoscale*, 2013, **5**, 4711-4719.
- 34 D. Kuang, J. Brilliet, P. Chen, M. Takata, S. Uchida, H. Miura, K. Sumioka, S. M. Zakeeruddin and M. Grätzel, *ACS Nano*, 2008, **2**, 1113-1116.

Table of Content:

Maximizing performance of dye solar cells on plastic with a combined theoretical and experimental optimization approach

