

EES Batteries

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: X. Dong, H. Chen, B. V. R. Chowdari, X. Wu and Z. Wen, *EES Batteries*, 2025, DOI: 10.1039/D5EB00117J.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

Solid polymer electrolytes (SPEs) based sodium metal batteries (SMBs) are promising materials for next-generation lightweight energy storage, combining excellent processability with cost-effectiveness. Transitioning from gel-state to all-solid-state sodium metal batteries (ASSMBs) is a necessary step to enhance both safety and energy density. However, the removal of solvents or unpolymerized monomers in SPEs often results in intrinsically low ionic conductivity (below 10^{-5} S cm⁻¹ at room temperature), low Na⁺ transference numbers ($t_{\text{Na}^+} < 0.3$), and poor interfacial compatibility with electrodes. Herein, a host-guest recognition strategy was designed for polymer electrolytes by incorporating bimetallic metal-organic frameworks (MOFs) with abundant Lewis acid sites into the polymer matrix. Tailoring the electronic configuration of the bimetallic MOFs enables them to effectively capture TFSI⁻ anions and accelerate the dissociation-desorption of Na⁺ along the PEO chains. The unique system achieves an ionic conductivity of 1.37×10^{-4} S cm⁻¹ at 30 °C, which ranks among the highest reported for all-solid-state polymer systems to date, and a t_{Na^+} of 0.63, along with a wide electrochemical oxidation window. Specifically, the NVP//Na ASSMB demonstrates a highly reversible capacity of 100.6 mA h g⁻¹ and a good cycling stability with 97.2% capacity retention after 600 cycles at 1C. Furthermore, the all-solid-state sodium metal pouch cells achieve an impressive initial discharge specific capacity of 113.4 mAh g⁻¹ and remained stable for 56 cycles at 0.1C. This work proposes a promising host-guest recognition strategy for SPEs to enhance Na⁺ transport, providing valuable insights for the design of next-generation all-solid-state electrolyte systems with high energy density.



ARTICLE

Electronic Structure Modulation of MOF-Based Host–Guest Recognition Polymer Electrolytes for High-Performance All-Solid-State Sodium Metal Batteries

Xiaorong Dong ^{a,b}, Huan Chen ^{a,b}, B.V.R. Chowdari ^c, Xiangwei Wu, ^{*a,b} Zhaoyin Wen, ^{*a,b}Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Transitioning from gel to all-solid-state sodium metal batteries (ASSMBs) is essential for upgrading the energy density and safety of flexible energy storage devices. Herein, a novel host-guest recognition strategy for all-solid-state composite polymer electrolytes (CPEs) is proposed by introducing Fe-Ni bimetallic Metal-organic frameworks (MOFs) into the PEO matrix. Fe-Ni MOF with various synergetic sites serves as a ‘host’ platform for CPEs to weaken the Coulombic interaction between Na⁺ and bis(trifluoromethylsulfonyl)imide (TFSI), thereby promoting the dissociation of sodium salt. They reduce the Na⁺ migration barrier and improve high-voltage stability. The optimized CPE achieves an ionic conductivity of 1.37×10^{-4} S cm⁻¹ at 30 °C, and the Na⁺ transference number increased threefold (from 0.23 to 0.63). The corresponding Na//Na symmetric cells operate stably for 1150 h at 25 °C, and the Na// Na₃V₂(PO₄)₃ (NVP) cells demonstrate 97.2% capacity retention after 600 cycles at 1C. Thanks to the high oxidation limit of the CPE (4.5 V), the Na₃V₂(PO₄)₂F₃ (NVPF)-based ASSMBs demonstrate stable cycling over 500 cycles within the voltage range of 2.5–4.3 V. Furthermore, the all-solid-state Na metal pouch cell exhibits an high initial discharge specific capacity of 113.4 mAh/g and remains stable for 56 cycles at 0.1C. This innovative host-guest recognition polymer electrolyte offers valuable insights for enhancing rapid ion transport and contributing to the better understanding of the underlying Na⁺ kinetics mechanisms.

Introduction

Sodium metal has high theoretical specific capacity (1165 mAh/g) and a low redox potential (-2.714 V vs standard hydrogen electrode),¹ making sodium metal batteries (SMBs) an important form of high-energy-density energy storage systems.^{2, 3} Traditional SMBs use organic liquid electrolytes, where the organic solvents are highly flammable, prone to leakage, and susceptible to severe side reactions with the chemically reactive Na metal.⁴ Therefore, the large-scale application of SMBs still faces significant challenges. Consequently, substituting traditional liquid electrolytes with solid-state electrolytes (SSEs) has been proven to be a viable strategy.⁵ Among various SSEs, solid polymer electrolytes (SPEs) have significant advantages in improving battery safety, enhancing mechanical properties, preventing uncontrolled dendrite formation, and exhibiting high electrochemical stability.⁶ Polyethylene oxide (PEO)-based SPEs have been extensively studied owing to their excellent salt solubility.⁷ The ether oxygen groups on PEO exhibit strong coordination interactions with Na⁺, which is beneficial to the

dissolution of sodium salts. However, these strong interactions hinder the migration of Na⁺, resulting in low Na⁺ transference number (t^+) leading to severe concentration polarization and thus uneven sodium deposition and ultimately dendrite formation.^{8, 9} Therefore, achieving a balance between high ionic conductivity and t^+ while maintaining stable electrochemical performance is a key challenge for all-solid-state sodium metal batteries (ASSMBs) based on SPEs.

In recent years, development of single sodium ion conductive SPEs by bonding anions to the main chain of polymers to suppress anion migration has significantly improved the Na⁺ transference number.¹⁰ However, the ionic conductivity remains relatively low, making battery operation difficult. Incorporating fillers into the polymer matrix has been shown to be a promising approach to enhance the ionic conductivity of SPEs.¹¹ Metal-organic frameworks (MOFs) have advantages including large pore volume, high surface area, adjustable pore size, and diverse topological structures. They provide a new method for the design of composite polymer electrolytes (CPEs).¹² The excellent specific surface area of MOFs provides closely packed cation hopping sites reducing the activation energy required for ion transfer and increasing ionic conductivity.¹³ The ordered porosity of MOFs can also regulate the uniform deposition of Na⁺ on the anode and suppress the dendrite formation.¹⁴ Additionally, the strong coordination interaction between the unsaturated metal sites exposed in MOFs after removing solvent molecules and the anions in sodium salts can balance the charge and maximize the Na⁺ transference number.¹⁵ Meanwhile, incorporating MOFs into polymer electrolytes can effectively reduce polymer crystallinity, increase the amorphous

^a The State Key Lab High Performance Ceram & Superfine Microstructure Shanghai Institute of Ceramics Chinese Academy of Sciences Shanghai 200050, P. R. China.

^b Center of Materials Science and Optoelectronics Engineering University of Chinese Academy of Sciences Beijing 100049, P. R. China.

^c School of Materials Science and Engineering, Nanyang Technological University, 639798, Singapore

[†] Electronic Supplementary Information (ESI) available: See DOI: 10.1039/x0xx00000x



fraction, and promote Na⁺ transport through anion capture and continuous migration channels.¹⁶⁻¹⁹ The utilization of MOFs as fillers in SPEs has significantly influenced the development of CPEs, leading to improved electrochemical performance.²⁰ However, the critical role of MOFs in CPEs and their Na⁺ migration mechanisms are not fully understood.²¹ Therefore, further research is necessary to improve our understanding of the critical role of MOFs in SMBs.²²

In this work, we propose a novel host-guest recognition MOFs-CPE strategy for SMBs. A bimetallic Fe-Ni MOF with anion-trapping effects was introduced into the PEO-based electrolyte for developing a composite polymer electrolyte with the addition of 10% (CPE-10) to selectively enhance Na⁺ migration capabilities and achieving ultra-stable ASSMBs. In CPE-10, the abundant Lewis-acid sites exposed on the bimetallic Fe-Ni MOF can inhibit the migration of TFSI⁻ through strong anion-trapping effects. This unique structure, combined with the synergistic effect of highly promoted sodium salt dissociation provides a long-range, efficient, and continuous pathway for selectively rapid Na⁺ transport. This significantly enhances the ionic conductivity (1.37×10^{-4} S cm⁻¹, 30 °C) and the Na⁺ transference number (0.63) of the CPE. Molecular dynamics (MD) simulations elucidate that the Fe-Ni MOF has strong anion-trapping effects, endowing CPE-10 with robust Na⁺ transport capabilities and coordination environments. The Na/Na cell demonstrates stable cycling for 1150 h at 25 °C. Further, the Na₃V₂(PO₄)₃ (NVP)/CPE-10/Na cell exhibits excellent cycling stability and rate performance at 25 °C and 60 °C. Moreover, the pouch cell delivers an initial discharge specific capacity close to its theoretical capacity and maintains stable cycling at a high loading of nearly 4 mg cm⁻². This work lays the foundation for long lifespan and large-scale ASSMBs.

Results and discussion

Design rationale of Fe-Ni MOF structure

In conventional PEO-based solid polymer electrolytes, strong O-Na⁺ coordination significantly impedes Na⁺ migration, resulting in a low *t*⁺. To address this issue, the Fe-Ni bimetallic MOF is introduced as functional fillers to weaken O-Na⁺ coordination, thereby significantly accelerating the dissociation of Na salts. Following dissociation, it is essential to inhibit the complexation of Na⁺ with TFSI⁻ to increase the availability of active Na⁺ (Figure 1a). To fulfill the requirements for efficient "host" functionality, theoretical calculations were employed to screen nine representative metal MOF materials for their adsorption energy of TFSI⁻ in sodium salts. This analysis covers the adsorption energies of five monometallic MOFs and four bimetallic MOFs, with ligands of trimesic acid. As depicted in Figure 1b, the Fe-Ni bimetallic MOF exhibits the highest adsorption energy for TFSI⁻, while the monometallic Fe MOF and Ni MOF show the lowest adsorption energies. In the Fe-Ni MOF structure, the projected density of states (PDOS) reveals that the d states of the Fe center are closer to the Fermi level (*E*) than the Ni center (Figure 1c). This indicates that the d-orbitals of Fe are the main active orbitals, determining the adsorption strength of Na and the catalytic activity of Fe-Ni MOF. It also demonstrates that the introduction of Fe into the monometallic MOF(Ni) results in more electronic states within a specific energy range, enhancing the opportunities for electron exchange with reactants. Therefore, Fe-Ni bimetallic MOF was

ultimately chosen as the filler for the PEO matrix for the following reasons: (1) In Fe-Ni bimetallic MOF, the d-band center of the Fe sites is closer to the Fermi level compared to single-metal MOFs, which significantly enhances the adsorption ability for F/O in TFSI⁻. Besides, the d-band center of the Ni sites shifts upward, avoiding the issue of difficult anion desorption seen in single Ni-MOF due to a deeper d-band center. This synergistic electronic structure allows for "moderate anion adsorption," meeting the ion adsorption-desorption balance required for electrolyte fillers.²³ (2) The unique Fe-O-Ni-O-Fe bonding pathway creates an efficient electron transfer channel. The Ni sites act as electron donors, continuously supplying electrons to the Fe sites through the d- π conjugation effect.²⁴ This charge distribution mechanism is not achievable in single-metal MOFs. It enhances the Fe sites' adsorption capacity and prevents the Ni sites from excessive electron localization, which could lead to strong adsorption and poisoning of active sites. (3) The electron delocalization effect in Fe-Ni bimetallic MOF effectively disperses the negative charge of TFSI⁻, reducing steric hindrance, while maintaining high ionic conductivity and ensuring strong adsorption.²⁵ To sum up, the synergistic effect of Fe and Ni sites in Fe-Ni bimetallic MOF addresses the issues of anion adsorption-desorption balance found in single-metal MOFs, making it the optimal choice.

The introduction of Fe-Ni MOF into the PEO-based electrolyte creates a homogeneous structure, providing a continuous linear path for rapid ion transport, thus reducing the activation energy required for Na⁺ migration, referred as CPE-10 (Figure 1d). Additionally, the increase in amorphous regions within the PEO matrix in CPE-10, induced by the interaction between the numerous metal sites in the MOF and the ether oxygen bonds in PEO, leads to the opening of polymer chains. This improves ionic conductivity and synergistically facilitated rapid Na⁺ transport within the system. On the other hand, the numerous metal sites in the Fe-Ni MOF act as Lewis-acid sites which can constrain TFSI⁻ to accelerate sodium salt dissociation and balance charges while increasing the free state of Na⁺ that can participate in complexation. This results into the increase of Na⁺ transference number, and reducing concentration polarization and ohmic polarization within CPE-10 due to uneven ion distribution.²⁶ Consequently, CPE-10 is expected to achieve both high ionic conductivity and high Na⁺ transference number, therefore enabling ultralong cycle life in ASSMBs (Figure 1e).

Design and characterization of host-guest recognition electrolyte

Scanning electron microscopy (SEM) and the transmission electron microscopy (TEM) were used to observe the morphology of Fe-Ni MOF. As shown in Figures 2a (SEM) and 2b (TEM), the Fe-Ni MOF is composed of uniformly stacked three-dimensional cauliflower shaped structure arranged in a lamellar stack. This uniform and well-ordered nanostructure facilitates sufficient contact between the electrolyte and the MOF, thereby providing more effective migration pathways for Na⁺ and enhancing ionic conductivity. Energy dispersive X-ray spectroscopy (EDS) results confirmed the uniform distribution of Fe, Ni, C, and O elements on the surface of the Fe-Ni MOF (Figure S1). The uniform distribution of elements ensures that the Lewis acid sites are evenly distributed across the MOF surface, which helps uniformly capture TFSI⁻ anions and optimize Na⁺ migration pathways and transference number. The Fe-Ni MOF is featured by its high






Figure 1. (a) Detailed depiction of the dissociation and adsorption mechanisms of NaTFSI. (b) Theoretical calculations that screen the adsorption energy of TFSI⁻ on reported and representative single-metal and bimetallic MOFs. (c) DFT-calculated the DOS of MOF(Fe-Ni). (d) Schematic diagram of CPEs synthesis. (e) Schematic illustration of Fe-Ni MOF enhanced structure of CPEs with selective and rapid Na⁺ transport.

Lewis acidity, which makes it a promising solid catalyst.²⁷ Therefore, these Fe-Ni MOF nanocrystals enable the exposure of more active sites, leading to a more sufficient interaction with C–O–C segments, which are considered as Lewis-base centers in PEO chains.²⁸ Brunauer-Emmett-Teller (BET) results indicated that the Fe-Ni MOF has a large specific surface area (284.0 m² g⁻¹) (Figure S2a).²⁹ The micropore structure of the Fe-Ni MOF can selectively restrict the passage of TFSI⁻, thus enhancing the Na⁺ transference number (Figure S2b).³⁰ The larger specific surface area provides more accessible active surfaces and microporous spaces, offering additional migration pathways for Na⁺ and thereby enhancing the ionic conductivity of the electrolyte. To highlight the advantages of Fe-Ni bimetallic MOF, we synthesized Fe-MOF and Ni-MOF using the same experimental methods and tested their specific surface areas and porosity (Figure S3). The results showed that the specific surface area of the Fe-Ni bimetallic MOF is more than three times that of Fe-MOF and 28 times that of Ni-MOF. This indicates that the design of the bimetallic MOF optimizes its structure, significantly increasing the specific surface area and the number of exposed Lewis-acid sites. This enhancement is beneficial for optimizing the host functions of the bimetallic MOF and strengthening its effective recognition of guest molecules. While all metal MOFs can ensure the presence of Na⁺ within their microporous structures, the bimetallic MOF system

releases more dissociated Na⁺, effectively facilitating the rapid migration and diffusion of Na⁺. Furthermore, the X-ray diffraction (XRD) spectrum of the Fe-Ni MOF exhibited peaks at positions consistent with the standard Fe-Ni MOF XRD pattern, with characteristic diffraction peaks at 7.7° and 10.6° (Figure 2c). However, both peaks exhibited a slight low-angle shift, possibly due to the nanoscaling and defect doping of Fe-Ni MOF.²⁷ The crystallinity of Fe-Ni MOF was also enhanced, attributed to the loss of organic components during the hydrothermal process. This results in slight growth of the three-dimensional cauliflower shaped structure of Fe-Ni MOF and exposing more effective Lewis-acid sites on the surface of the nanosheets material, thus facilitating better interaction with the PEO-based electrolyte components.³¹ X-ray photoelectron spectroscopy (XPS) was used to determine the surface composition and chemical states of elements in the Fe-Ni MOF. The C 1s spectrum was fitted with three peaks centered at 284.8 eV, 286.3 eV and 288.4 eV, corresponding to C–C, C–O, and C=O bonds, respectively.³² The O 1s spectrum revealed the presence of –OH peaks at 531.7 eV and C=O bonds at 532.8 eV. Furthermore, the Fe 2p XPS curve showed two chemically distinct substances, including metallic iron and oxidized iron states.³³ The Ni 2p spectrum identified peaks at 855.5 eV and 873.2 eV belonging to the oxidized state of Ni (Figure S4).³⁴ The transition metals are successfully anchored onto the organic






Figure 2. (a) SEM image and (b) TEM image of as-prepared Fe-Ni MOF powder. (c) XRD patterns of Fe-Ni MOF and simulation Fe-Ni MOF. (d) SEM images of PEO and CPE-10. (e) Surface morphologies of PEO and CPE-10 obtained by AFM. High-resolution XPS spectra of (f) C 1s, (g) F 1s and (h) S 2p for PEO and CPE-10 membranes. (g) Optical photographs of the states of PEO and CPE-10 membranes at 25, 60, 90, 120 and 150 °C.

framework. The optical photograph of the CPE-10 prepared by the solution casting method is shown in **Figure S5**. The resulting brown film exhibits excellent flexibility, undergoing significant inelastic deformation when manually stretched. The stress-strain curve indicates that CPE-10 also possesses good mechanical strength and tensile performance (**Figure S6**), with a Young's modulus as high as 35.0 MPa at room temperature, which helps to suppress the penetration of sodium dendrites. SEM analysis results show that the surface of CPE-10 is smoother and denser than that of PEO, which is beneficial for improving the interfacial contact between the electrolyte and the electrode (**Figure 2d**). Such improved interface uniformity facilitates more efficient Na^+ transport across the electrode-electrolyte interface, and thus enhances the overall ionic conductivity and electrochemical performance of the cell. Atomic force microscopy (AFM) tests also revealed that the surface roughness did not change significantly after the introduction of

inorganic fillers, indicating good dispersion and compatibility of the Fe-Ni MOF in the PEO matrix (**Figure 2e**). This uniform dispersion helps Na^+ migrate efficiently, improving ionic conductivity and electrochemical performance.

Figure 2f presents the C 1s, F 1s, and S 2p XPS spectra of PEO and CPE-10 for comparative analysis. In the C 1s spectra of both electrolytes, four peaks were observed corresponding to C-C, C-O-C, C=O and $-\text{CF}_3$. The changes in peak area ratios indicate the interaction between PEO and Fe-Ni MOF, leading to the disentanglement of polymer electrolyte chains in the PEO-based system. Furthermore, in the S 2p spectrum of CPE-10, the intensity of the $-\text{SO}_x$ peak decreased, suggesting the suppression of TFSI decomposition into $-\text{SO}_x$, which further demonstrates the high stability of the CPE-10 electrolyte. Additionally, in CPE-10, the Na-F peak area ratio decreased from 36.87% to 18.95%. With the incorporation of Fe-Ni MOF, compared to PEO, more ion pairs






Figure 3. (a) TGA curves and (b) XRD patterns of PEO and CPE-10. (c) Ionic conductivity of CPE with different mass fractions of Fe-Ni MOF at room temperature. (d) Ionic conductivity of CPE with varying content. (e) Arrhenius plots of the ionic conductivity of CPEs. (f) LSV curves of PEO and CPE-10. (g, h) AC polarization curves of Na//Na cells using CPE-10 and PEO, with EIS (inset) before and after polarization. (i) Tafel plot comparison of Na//Na cells based on CPE-10 and PEO after 30 h of cycling.

formed after NaTFSI dissociation (Na⁺-TFSI⁻) are formed in the system. This is likely due to the strong electrostatic interaction between the Fe-Ni metallic MOF and TFSI⁻, which facilitates the dissociation of NaTFSI and enhances the mobility of Na⁺. CPE-10 maintains a stable shape with better mechanical properties even at high temperatures over 150 °C, highly improving the safety application potential of PEO even if the temperature is over 90 °C (Figure 2g).

Figure 3a shows the thermogravimetric analysis (TGA) of CPE-10 and PEO. The addition of the Fe-Ni MOF increased the decomposition temperature of the electrolyte, effectively raising it from 200 °C to 304 °C. Due to the high thermal stability of the Fe-Ni MOF, the residual mass of the composite electrolyte remains as high as nearly 10% even at temperatures close to 600 °C. This residual proportion is consistent with Fe-Ni MOF content. XRD analysis results

show that the Fe-Ni MOF did not alter the crystal structure of PEO (Figure 3b). The peaks at 19° and 23° correspond to the crystalline regions of PEO, and their reduced intensity in CPE-10 indicates a decrease in crystallinity. The Fe-Ni MOF disrupts the regular packing of PEO chains through steric hindrance, weakening interchain van der Waals interactions and increasing the amorphous region, which provides more accessible Na⁺ migration pathways. Additionally, the MOF's porous structure and Lewis acid sites interact with NaTFSI, capturing and dispersing anions and locally enriching Na⁺, while also helping form continuous migration channels that lower the Na⁺ migration energy barrier. Together, these effects synergistically enhance the overall ionic conductivity of CPE-10.³⁵ Figure S7 shows the DSC thermal curves of CPE-10 and PEO electrolytes in the temperature range of -60-100 °C, with the corresponding glass transition temperature (T_g), melting temperature (T_m), melting



enthalpy (ΔH_m), and crystallinity (χ_c) listed in **Table S1** (the method for calculating crystallinity can also be found in the Supporting Information). For CPE-10, the synchronous decrease of T_g , T_m , and ΔH_m (**Table S1**) indicates an expansion of the amorphous region. The XRD and DSC results demonstrate that the introduction of Fe-Ni MOF with abundant unsaturated metal sites can disrupt the crystalline regions of the polymer, promote segmental chain motion, and thus inhibit the crystallization of the PEO matrix. To evaluate the effectiveness of Fe-Ni MOF developed in CPEs on Na^+ migration, the ionic conductivities at room temperature of various CPEs were measured (**Figure 3c and Figure S8**). It is found that CPE-10 exhibited the highest ionic conductivity, reaching $5.75 \times 10^{-5} \text{ S cm}^{-1}$, almost an order magnitude higher than that of PEO, Fe-MOF CPE and Ni-MOF CPE. **Figure 3d** shows the ionic conductivity of different Fe-Ni MOF content's (0-15 wt%) CPE-X ($X=0, 3, 5, 7, 10, 15$) at different temperatures. With an increase in Fe-Ni MOF content, the ionic conductivity of CPEs initially increased and then decreased, reaching a maximum at 10 wt%. Specifically, the ionic conductivity of the CPE-10 achieves $1.37 \times 10^{-4} \text{ S cm}^{-1}$ at 30°C and $7.96 \times 10^{-4} \text{ S cm}^{-1}$ at 60°C , which is much higher than that of PEO, Fe-MOF CPE and Ni-MOF CPE (**Table S2**). The Arrhenius plots of CPEs with different Fe-Ni MOF content and the single metal MOF's CPEs are shown in **Figure 3e**. When the content of Fe-Ni MOF was insufficient or excessive in CPE-X ($X=0, 3, 5, 7, 15$), Fe-MOF CPE and Ni-MOF CPE, the Arrhenius plots show a turning point around 50°C . This indicates higher activation energy below the turning point (greater than 1.0 eV) and lower Na^+ conductivity within the temperature range of $30\text{--}50^\circ\text{C}$. When the temperature exceeded the polymer melting point (48°C), the activation energy became very small (approximately 0.3-0.4 eV), activating the diffusion behavior of Na^+ . The Arrhenius plot of the optimized CPE-10 showed a nearly linear relationship across the entire temperature range with an activation energy of 0.50 eV. Therefore, the high ionic conductivity behavior can be extended to lower temperature regions. The increase in ionic conductivity is attributed to the transfer of Na^+ between the amorphous PEO domain and the Fe-Ni MOF interface ensuring uninterrupted high-speed migration of Na^+ . Furthermore, linear sweep voltammetry (LSV) was adopted to evaluate the electrochemical stability of CPE-10 and PEO electrolytes (**Figure 3f**). The results indicate that CPE-10 exhibits higher electrochemical stability within the voltage range of 1-4.5 V with no detectable decomposition current below 4.5 V (vs Na^+/Na), indicating excellent antioxidative properties,³⁶ while PEO electrolyte showed a decomposition current at 3.75 V, indicating poorer antioxidative properties.³⁷ Besides, the migration of anions during cycling can lead to severe concentration polarization, causing sodium dendrite growth and interface side reactions, hindering the normal operation of the cell at high current densities. Therefore, electrolytes with high Na^+ transference number are ideal for reducing concentration polarization and suppressing side reactions, thereby contributing to excellent energy storage performance. The Na^+ transference number of CPE-10 is 0.63, nearly three times that of PEO (0.23) (**Figures 3g and 3h**),³⁸ which is significantly higher than that of the single metal Fe-MOF ($t^+=0.47$) and Ni-MOF ($t^+=0.48$) (**Figure S9, S10 and Table S3**). It highlights the recognition function of the bimetallic MOF as the host molecule for the guest molecule TFSI^- . The bimetallic MOF can effectively recognize and confine the anions, thereby increasing the mobility of the cations. **Figure 3i**

presents a comparison of Tafel plots, showing enhanced Na^+ transport kinetics at the Na/polymer interface in CPE-10 after 30 h of cycling, as evidenced by a significant increase in the exchange current density ($6.45 \times 10^{-2} \text{ mA cm}^{-2}$). In contrast, the exchange current density of PEO is $3.80 \times 10^{-2} \text{ mA cm}^{-2}$, nearly double that of CPE-10. However, at 0 h of cycling, the initial exchange current density of PEO is an order of magnitude higher than that of CPE-10, and the exchange current density of CPE-10 remains almost unchanged before and after cycling, indicating a more stable interface (**Figure S11**). This demonstrates that symmetric cells using CPE-10 exhibit faster mass transfer kinetics at the Na/polymer interface.

In situ Raman characterization of host-guest interaction and ionic transport mechanisms in CPE-10

In-situ Raman spectra reveal that the peak intensity of TFSI^- (739 cm^{-1}) in PEO initially increases and then decreases during the charging process, with only a very small amount of sodium salt dissociating in the initial charging phase, indicating a higher degree of anion mobility within the system. In contrast, the peak intensity remains relatively stable in CPE-10 (**Figures 4a and 4b**). This stability suggests that the bimetallic MOF in CPE-10 acts as a host to recognize the salts within the system, thereby restraining the anions. Besides, ex-situ Raman spectra measurements were performed on CPE-10 and PEO (**Figure S12**). There are two main states of TFSI^- anions in PEO-based electrolytes, namely dissociated (uncoordinated) TFSI^- and ion clusters (two TFSI^- coordinated with Na^+).³⁹ The percentage of free TFSI^- in PEO is 66.8%, whereas in CPE-10, it reaches 87.7%. This proves that Fe-Ni MOF as a Lewis-acid induces better decomposition of $\text{Na}^+[\text{TFSI}]_n$ ion clusters. Fourier transform infrared (FTIR) spectra of Fe-Ni MOF, PEO, and CPE-10 are shown in **Figure 4c**. The introduction of the Fe-Ni MOF filler also affects the vibration of CH_2 , resulting in weakening of peaks corresponding to symmetric stretching and bending vibrations of CH_2 at 2881 cm^{-1} and 1463 cm^{-1} , respectively.⁴⁰ The vibration at 1340 cm^{-1} of CH_2 weakens due to the strong vibration of the C-O-C group and its chain effect.⁴¹ The abnormal decrease in vibration intensity at 1096 cm^{-1} (related to symmetric stretching of C-O-C) is likely due to the strong interference from the Lewis-acid centers of Fe-Ni MOF.⁴² The peak at 842 cm^{-1} corresponds to the stretching vibration of $\text{CH}_2\text{CH}_2\text{O}$. FTIR results indicate that the strong interactions between Fe-Ni MOF and PEO chains promote the vibration of C-O-C groups, facilitating the establishment of highly conductive interfaces between polymer chains and fillers.⁴³ FTIR results indicate that the strong interactions between Fe-Ni MOF and PEO chains promote the vibration of C-O-C groups, facilitating the establishment of highly conductive interfaces between polymer chains and fillers. This enhanced interaction improves Na^+ transport across the polymer-filler interface, contributing to higher ionic conductivity and better electrochemical performance of the electrolyte. Furthermore, molecular dynamics simulations (MDs) were used to assess the diffusion dynamics of Na^+ in the two electrolytes, as shown in **Figures 4d and S13**. In the PEO electrolyte, the simulation results indicate that the polymer chains are randomly dispersed, and the transport of Na^+ follows a hopping mechanism within these chains. Na^+ moves from one coordination site to another, facilitated by the motion of polymer chain segments, leading to a random and anisotropic migration process for Na^+ in PEO, posing challenges for achieving rapid Na^+ migration. In contrast,






Figure 4. (a, b) In-situ Raman spectra under full cell operation. (c) FTIR spectra of Fe-Ni MOF, PEO and CPE-10. (d) Snapshot of CPE-10/NaTFSI obtained by MDs. (e) Calculated radial distribution functions ($g(r)$, solid lines) and coordination numbers ($n(r)$, dashed lines) for Na—O_{TFSI} in different environments. (f) MSD of Na⁺ in the PEO and CPE-10 calculated from MDs. Here, the slope values are the linear fitting results for MSD. (g) The binding ability comparison of Fe-Ni MOF-TFSI⁻, Fe-Ni-MOF-TFSI⁻-Na⁺ and Na⁺-TFSI⁻ in the CPE-10. (h) Migration energy barriers of Na⁺ diffusion pathways in PEO and CPE-10 electrolytes. Inset: (Left) Na⁺ migration pathway within PEO chains in the PEO system; (Right) Na⁺ migration pathway within PEO chains in the CPE-10 system.

in the CPE-10 electrolyte, the MD results show that the introduction of Fe-Ni MOF promotes the directional and orderly migration of Na⁺.⁴⁴ From the coordination number ($n(r)$, dashed line) and radial distribution function ($g(r)$, solid line) shown in **Figure 4e**, for the PEO system, the interaction probability of O_{TFSI}...Na at 2.3 Å and 4.5 Å indicates higher interactions between Na⁺ and TFSI⁻ suggesting a lower concentration of free Na⁺ in the system. However, in CPE-10, the coordination effect of O_{TFSI}...Na is weaker compared to that of PEO, so that the addition of Fe-Ni MOF promotes the dissociation of NaTFSI, consistent with the Raman spectroscopy results. Additionally, the mean square displacement (MSD) analysis qualitatively assesses the diffusion rate of Na⁺ in solid electrolyte systems. **Figure 4f** shows the MSD curves for CPE-10 and PEO. The

results indicate that CPE-10 significantly enhances the diffusion rate of Na⁺, reaching up to $2.12 \times 10^{-6} \text{ cm}^2 \text{ s}^{-1}$, an order of magnitude higher than that of PEO ($4.9 \times 10^{-7} \text{ cm}^2 \text{ s}^{-1}$), demonstrating the outstanding ability of CPE-10 to facilitate rapid Na⁺ transport. To substantiate the host role of the Fe-Ni bimetallic MOF, we conducted theoretical calculations to explore the microscopic interactions between NaTFSI and the Fe-Ni MOF (**Figure 4g**). The Fe-Ni MOF leads to lower binding energy between Na⁺ and TFSI⁻, indicating a higher dissociation degree of NaTFSI and enhanced Na⁺ mobility. Moreover, the Fe-Ni MOF exhibits a higher adsorption energy for TFSI⁻, enabling effective recognition of TFSI⁻. Meanwhile, the binding energy between TFSI⁻ and Fe-MOF is -0.27 eV, and the binding energy between TFSI⁻ and Ni-MOF is -0.55 eV (**Figure S14**), both of which are



significantly weaker than that of the Fe-Ni bimetallic MOF, aligning with its lower Na^+ transference number. Additionally, electrostatic potential results indicate that introducing the Fe-Ni bimetallic MOF into the PEO system weakens the binding energy between EO bonds and Na^+ , while enhancing the binding energy between TFSI⁻ and the Fe-Ni bimetallic MOF, achieving a unique "killing two birds with one stone" effect (Figure S15). The mechanism of fast sodium ion transport was revealed by calculating the migration energy barriers (Figure 4h). In PEO, the energy barrier for Na^+ migration from the initial Na site to the final Na site is relatively high, at 5.10 eV. Conversely, in CPE-10, the migration energy barrier from the asymmetric initial Na site to the intermediate Na site is 0.73 eV, while the barrier from the intermediate Na site to the final Na site is only 2.29 eV. This indicates that in the Fe-Ni MOF-modified electrolyte, Na^+ is more likely to undergo rapid migration along the disentangled PEO chain segments.

Na metal compatibility and Interfacial analysis of Na metal

To examine the electrochemical stability of CPE-10 with the sodium anode, galvanostatic charge-discharge cycling test was conducted on Na/Na symmetrical cells. Figure 5a demonstrates the periodic charge-discharge curves at 0.05 mA cm⁻² and 25 °C, where the symmetrical cells assembled with CPE-10 exhibited relatively flat polarization curve and were able to cycle stably for over 1150 h. In contrast, the cell assembled with PEO short-circuited in less than 5 h, revealing superior interfacial stability of CPE-10 with Na anode. Meanwhile, the symmetric cells assembled with CPE-10 can also cycle stably for 1200 h at 60 °C and a current density of 0.1 mA cm⁻² (Figure S16). Furthermore, rate cycling at different current densities also showed that CPE-10 has a better ability to resist dendrite formation compared to PEO (Figure S17). Figure 5b and 5c exhibits the SEM images of Na/CPE-10/Na and Na/PEO/Na symmetrical cells after 50 h of cycling. The sodium surface of the PEO-based cell exhibited dendrites, an uneven surface, and signs of instability. On the other hand, the sodium surface of Na/CPE-10/Na cell remained smooth and flat at both large and small scales, confirming uniform sodium deposition and thus greater stability for the sodium anode. To analyze the composition of the sodium surface after cycling, ex-situ XPS measurements were performed on the sodium anode, as shown in Figure 5d and 5e. The C 1s spectrum of the PEO system consists of a C-C/C-H peak at 284.8 eV, C-O peak at 286.7 eV, C=O peak at 288.2 eV, and Na₂CO₃ peak at 289.3 eV, as the etching time increased from 60 s to 120 s, the Na₂CO₃ peak gradually intensified.⁴⁵ However, in the CPE-10 system, the Na₂CO₃ peak did not appear, and the C-O peak increased. With the introduction of Fe-Ni MOF as Na⁺ modulator, the Na₂CO₃ signal was absent in the O 1s spectrum, while the Na₂O peak at 531.4 eV gradually intensified with etching time.⁴⁶ The F 1s spectrum also showed that in the CPE-10 system, the NaF peak at 684.0 eV gradually intensified, and the TFSI⁻ peak at 688.8 eV gradually attenuated, almost completely disappearing after etching for 120 s.⁴⁷ Conversely, in the PEO system, the NaF peak was relatively weak, and there was a significant presence of TFSI⁻. The S 2p spectra showed similar results, with the Na₂S peak at 159.9 eV in the PEO system gradually decreasing as the etching depth increased.⁴⁸ The results indicate that the residual Na₂CO₃, captured TFSI⁻, and its decomposition products passivated the interface of the PEO system, resulting in poor cycling performance (Figure 5f).

However, the Fe-Ni MOF as Na⁺ modulator could better adsorb TFSI⁻, allowing it to diffuse to the sodium anode. Therefore, the O atoms at the end of the PEO segment near the sodium metal tend to become sodiated, forming Na₂O and retaining the C-O groups. The capture and degradation of TFSI⁻ on the sodium anode were mitigated and no additional carbon source was provided for the conversion of Na₂O to Na₂CO₃. Meanwhile, it has been found that Na₂O and NaF exhibit excellent affinity for sodium ions. Their abundant presence in the SEI layer promotes the formation of smooth, non-dendritic sodium deposition, whereas a deficiency or insufficient content leads to rough, moss-like accumulation on the sodium surface, facilitating dendrite growth. Moreover, NaF is more effective than Na₂O in suppressing vertical dendrite formation, and its high interfacial energy promotes lateral migration of sodium along the interface, enhancing the SEI's dendrite-suppressing capability. Sodium ions also migrate more easily in Na₂O and NaF, while migration in Na₂CO₃ is hindered and electronically insulating; excessive Na₂CO₃ can cause SEI instability and increased cell impedance.^{6, 46, 49} Taken together, constructing an organic-inorganic gradient SEI rich in Na₂O, NaF, and Na₂S with a small amount of Na₂CO₃ can simultaneously facilitate sodium ion transport and improve long-term cycling stability. (Figure 5g).

Electrochemical performance and compatibility of CPE-10 with various cathodes

The full-cells were assembled using Na₃V₂(PO₄)₃ (NVP) as the cathode and sodium as the anode to further evaluate the cell performance. As shown in Figure 6a, the all-solid-state NVP/CPE-10/Na cell exhibits an initial discharge capacity of 91.37 mAh/g at 0.2C and 25 °C. After 350 cycles, the capacity retention rate is as high as 95.06%, with minimal polarization observed in the later cycles (Figure 6b). In contrast, the full battery based on PEO cannot cycle normally at room temperature due to its low ionic conductivity. Figure 6c compares the rate performance of NVP/CPE-10/Na and NVP/PEO/Na cells. Compared to the NVP/PEO/Na cell, the NVP/CPE-10/Na cell exhibits superior rate performance. At 60 °C, the discharge capacities at current densities of 0.3C, 0.5C, 1C, 1.5C, and 2C are 90.4 mAh/g, 90.3 mAh/g, 88.2 mAh/g, 87.4 mAh/g, and 85.6 mAh/g, respectively (Figure S18). Notably, the capacity can recover to its initial value when the current density returns to 0.3C, indicating high electrochemical reversibility of the NVP/CPE-10/Na cell. During cycling at 0.2C and 60 °C (Figure S19), the initial discharge specific capacity of NVP/CPE-10/Na cell is 80.6 mAh/g, with a lower capacity at the early stage. However, as cycling progresses, the discharge specific capacity gradually increases and reaches a stable value of 112.8 mAh/g due to interface activation and stabilization. After 210 cycles, the discharge specific capacity is still 111.4 mAh/g, with a capacity retention rate of 98.8%. This performance is significantly better than that of the NVP/PEO/Na cell, which exhibits lower discharge specific capacity at 0.2C and experiences overcharging after 123 cycles, resulting in battery failure (Figure S20). The rate performance of the full-cells based on CPE-10 at 0.2C surpasses any relevant electrolyte level reported to date (Figure 6e and Table S4). When the current density is increased to 1C (Figure 6d), the initial discharge specific capacity is 100.6 mAh/g for the NVP/CPE-10/Na cell, and after 600 cycles, the capacity retention rate is still as high as 97.2%. SMBs assembled with Fe-MOF CPE and Ni-MOF CPE as






Figure 5. (a) Comparison of cycling performance of Na/Na symmetric cells with the CPE-10 and PEO electrolytes plating/stripping at 0.05 mA cm⁻² for 30 min. The inset shows the enlarged view of cycle stages at 25 °C. The SEM images of Na anode after cycling for 50 h for (b) Na/CPE-10/Na and (c) Na/PEO/Na cells. Ex-situ XPS measurements of sodium metal anode surface, etched for 60 s and 120 s after cycling for 50 h for (d) PEO and (e) CPE-10 systems, with the signals of C 1s, O 1s, F 1s and S 2p. Schematic illustration of components at the surface of cycled sodium metal anode based on (f) PEO and (g) CPE-10.

electrolytes can both cycle normally at 1C, but their discharge specific capacities are relatively low, and they exhibit significant

polarization during cycling (**Figure S21**). The NVP/Fe-MOF CPE/Na cell shows overcharging after 107 cycles, while the NVP/Ni-MOF CPE/Na cell can cycle normally for 300 cycles, but its interface is






Figure 6. (a, b) Cycling performance of the NVP/CPE-10/Na cell at 25 °C with a current density of 0.2C. (c) Rate performances (0.3–2C) of the NVP/PEO/Na and NVP/CPE-10/Na cells. (d) Cycling performance of the NVP/CPE-10/Na cells at 60 °C and 1C. (e) Comparison of CPE-based cells with the previously reported ASSMBs in rate capability and long-term cycling performance. (f) Cycling performance of the NVPF/CPE-10/Na cells at 60 °C with a current density of 0.5C. (g) The corresponding voltage profile of the all-solid-state NVPF/CPE-10/Na at 0.5C in different cycles.

highly unstable, with fluctuating curves, and the capacity after 300 cycles is only 15.9 mAh/g. Therefore, SMBs assembled with CPEs based on single-metal MOFs exhibit poor performance, mainly because single metals are less stable during cycling compared to bimetals, and their lower ion transport capacity leads to severe concentration polarization, resulting in unstable interfaces. The cycling impedance test at 1C revealed that the interface impedance stabilized after 50 cycles (**Figure S22**). When the current is increased to 2C, the cell can still operate stably for 3000 cycles, with an initial discharge specific capacity of 83.6 mAh/g (**Figure S23**). After interface activation, its highest discharge specific capacity can reach 91.8 mAh/g with no significant polarization during cycling (**Figure S24**). Additionally, the NVP/CPE-10/Na cell also exhibits good cycling performance at 45 °C (**Figure S25**). These findings indicate that the prepared CPE-10 electrolyte is expected to be used at room to high temperatures, enabling ASSMBs to be used over a wider temperature range. Given its electrochemical window reaching up to

4.5 V, a high-voltage sodium cell was assembled using $\text{Na}_3\text{V}_2(\text{PO}_4)_2\text{F}_3$ (NVPF) as the cathode and CPE-10 as the electrolyte. The long-cycle performance at a rate of 0.5C was tested (**Figure 6f and 6g**). The initial discharge specific capacity was 95.8 mAh/g, with the highest discharge specific capacity reaching 119.9 mAh/g. After 300 cycles, the capacity retention rate was still 77.8%. No short-circuit or overcharging occurred during the cell cycling process. The all-solid-state NVPF-based sodium cell assembled with CPE-10 as the electrolyte exhibited excellent electrochemical performance, laying a foundation for subsequent high-voltage sodium batteries.

Considering potential practical applications, solid-state sodium metal pouch cells were assembled using CPE-10 as the electrolyte and tested under various mechanical abuses (**Figure 7d**). Their overall superior performance enabled the fabrication of a foldable all-solid-state pouch cell. The cell could continuously light a bulb when folded and even when the entire battery was repeatedly folded. Besides, the all-solid-state pouch cell with a cathode loading






Figure 7. (a) Cycling performance of pouch-type all-solid-state NVP/CPE-10/Na cell at 0.1C with a cathode loading of 2.1 mg cm⁻². (b) Corresponding charge-discharge curves of pouch-type NVP/CPE-10/Na cell at different cycling stages. (c) Cycling performance of pouch-type all-solid-state NVP/CPE-10/Na cell at 0.1C with a cathode loading of 4.0 mg cm⁻². (d) Lighting test of the NVP/CPE-10/Na pouch cell under repeated bending and folding.

of 2.1 mg cm⁻² could stably cycle for 56 cycles at 0.1C (**Figure 7a**), with an initial discharge specific capacity of 113.4 mAh/g. The charge-discharge curves of the first three cycles exhibit a high degree of overlap (**Figure 7b**). Even the pouch cell assembled with a higher cathode loading of 4.0 mg cm⁻² could steadily cycle for 30 cycles at 0.1C, with a capacity retention of up to 97.8% (**Figure 7c**).

In conclusion, the proposed CPE-10 in ASSMBs exhibits high safety and excellent electrochemical performance, demonstrating promising application potential in future high-energy-density storage systems.

Conclusions

In summary, we demonstrated ultra-stable ASSMBs using a composite polymer electrolyte enhanced by a bimetallic MOF structure that selectively promotes rapid Na⁺ transport. Our results confirm that the bimetallic MOF reduces the Na⁺ diffusion energy barrier by decreasing the polymer crystallinity and providing continuous Na⁺ transport pathways. In-situ Raman spectroscopy and molecular dynamics simulations further confirm the strong Lewis acid-base interactions between the bimetallic MOF and TFSI⁻, thereby enhancing the Na⁺ migration capability. Consequently, the Na⁺ transference number significantly increases (from 0.23 to 0.63), enabling the symmetric cell to operate stably for 1150 h. Based on the bimetallic MOF-enhanced PEO-based polymer electrolyte, the ASSMBs combined with an NVP cathode exhibit significantly enhanced cycle stability, excellent rate capability, and outstanding wide-temperature performance. The pouch cell remains functional and continues to power a bulb under mechanical abuse, and its

capacity stays stable over long cycles even with a high cathode loading of 4.0 mg cm⁻², demonstrating the potential of CPE-10 for practical applications. This work promises to provide meaningful insights into the design of high-performance polymer electrolytes for practically feasible all-solid-state sodium metal batteries.

Conflicts of interest

The authors declare no conflict of interest.

Acknowledgements

This work was financially supported by the National Natural Science Foundation of China (No. 52394173, No. 52102328), the Shanghai Engineering Research Center of Inorganic Energy Materials and Electric Power Sources (Grant No. 18DZ2280800), the Science and Technology Commission of Shanghai Municipality (Grant No. 24DZ3001302).



references

1. X. E. Wang, C. Zhang, M. Sawczyk, Q. H. Yuan, F. F. Chen, T. C. Mendes, P. C. Howlett, C. K. Fu, P. Kral, C. J. Hawker, A. Whittaker, M. Forsyth, J. Sun, Y. Q. Wang, X. Tan and D. J. Searles, *Nat. Mater.*, 2022, **21**, 1057-1065.
2. Z. P. Li, K. J. Zhu, P. Liu and L. F. Jiao, *Adv. Energy Mater.*, 2022, **12**, 100359.
3. J. H. Guo, F. Feng, S. Q. Zhao, Z. H. Shi, R. Wang, M. Yang, F. F. Chen, S. L. Chen, Z. F. Ma and T. X. Liu, *Carbon Energy*, 2023, **5**, e314.
4. P. Jaumaux, J. R. Wu, D. Shanmukaraj, Y. Z. Wang, D. Zhou, B. Sun, F. Y. Kang, B. H. Li, M. Armand and G. X. Wang, *Adv. Funct. Mater.*, 2021, **31**, 2008644.
5. P. Lennartz, B. A. Paren, A. Herzog-Arbeitman, X. C. Chen, J. A. Johnson, M. Winter, Y. Shao-Horn and G. Brunklaus, *Joule*, 2023, **7**, 1471-1495.
6. X. R. Dong, Y. Zhang, Z. C. You, Y. M. Chen, X. W. Wu and Z. Y. Wen, *Adv. Funct. Mater.*, 2024, **34**, 2405931.
7. Y. Li, F. Wu, Y. Li, M. Q. Liu, X. Feng, Y. Bai and C. Wu, *Chem. Soc. Rev.*, 2022, **51**, 4484-4536.
8. J. P. Hoffknecht, A. Wettstein, J. Atik, C. Krause, J. Thienenkamp, G. Brunklaus, M. Winter, D. Diddens, A. Heuer and E. Paillard, *Adv. Energy Mater.*, 2023, **13**, 202789.
9. N. Meng, Y. N. Ye, Z. X. Yang, H. Li and F. Lian, *Adv. Funct. Mater.*, 2023, **33**, 2305072.
10. H. Li, Y. F. Du, Q. Zhang, Y. Zhao and F. Lian, *Adv. Energy Mater.*, 2022, **12**, 2103530.
11. Y. Wei, H. J. Zhou, H. Deng, W. J. Ji, K. Tian, Z. Y. Ma, K. Y. Zhang and Q. Fu, *Nano-Micro Lett.*, 2022, **14**, 35.
12. S. Li, S. Q. Zhang, L. Shen, Q. Liu, J. B. Ma, W. Lv, Y. B. He and Q. H. Yang, *Adv. Sci.*, 2020, **7**, 1903088.
13. Z. B. Liang, C. Qu, W. H. Guo, R. Q. Zou and Q. Xu, *Adv. Mater.*, 2018, **30**, 1702891.
14. Z. W. Cao, R. Momen, S. S. Tao, D. Y. Xiong, Z. R. Song, X. H. Xiao, W. T. Deng, H. S. Hou, S. Yasar, S. Altin, F. Bulut, G. Q. Zou and X. B. Ji, *Nano-Micro Lett.*, 2022, **14**, 181.
15. L. Q. Xu, X. H. Xiao, H. Y. Tu, F. J. Zhu, J. Wang, H. X. Liu, W. Y. Huang, W. T. Deng, H. Hou, T. C. Liu, X. B. Ji, K. Amine and G. Q. Zou, *Adv. Mater.*, 2023, **35**, 2303193.
16. T. Kim, S. Hyeok Ahn, Y. Y. Song, B. Jin Park, C. Lee, A. Choi, M. H. Kim, D. H. Seo, S. K. Jung and H. W. Lee, *Angew. Chem. Int. Ed.*, 2023, **62**, e202309852.
17. T. W. Kim, K. H. Park, Y. E. Choi, J. Y. Lee and Y. S. Jung, *Journal of Materials Chemistry A*, 2018, **6**, 840-844.
18. J. Park, D. Han, J. P. Son, H. Kwak, W. Ko, C. Park, C. Lee, H.-W. Lee, J. Kim, K.-W. Nam and Y. S. Jung, *ACS Energy Letters*, 2024, **9**, 2222-2230.
19. T.-U. Wi, S. O. Park, S. J. Yeom, M.-H. Kim, I. Kristanto, H. Wang, S. K. Kwak and H.-W. Lee, *ACS Energy Letters*, 2023, **8**, 2193-2200.
20. A. M. Mohamed, M. Ramadan and N. K. Allam, *J. Energy Storage*, 2021, **34**, 102195.
21. Z. W. Lei, J. L. Shen, W. D. Zhang, Q. R. Wang, J. Wang, Y. H. Deng and C. Y. Wang, *Nano Research*, 2020, **13**, 2259-2267.
22. J. F. Zhang, Y. Y. Wang, Q. B. Xia, X. F. Li, B. Liu, T. P. Hu, M. Tebyetekerwa, S. L. Hu, R. Knibbe and S. L. Chou, *Angew. Chem. Int. Ed.*, 2024, **63**, e202318822.
23. L. Zhao, J. Yan, H. Huang, X. Du, H. Chen, X. He, W. Li, W. Fang, D. Wang, X. Zeng, J. Dong and Y. Liu, *Adv. Funct. Mater.*, 2023, **34**, 2310902.
24. X. Liu, R. Liu, J. Qiu, X. Cheng and G. Li, *Angew. Chem. Int. Ed.*, 2020, **59**, 13962-13967. DOI: 10.1039/D5EB00117J
25. L. Xu, X. Xiao, H. Tu, F. Zhu, J. Wang, H. Liu, W. Huang, W. Deng, H. Hou, T. Liu, X. Ji, K. Amine and G. Zou, *Adv. Mater.*, 2023, **35**, 2303193.
26. J. H. Guo, F. Feng, X. Y. Jiang, R. Wang, D. K. Chu, Y. F. Ren, F. F. Chen, P. He, Z. F. Ma, S. L. Chen and T. X. Liu, *Adv. Funct. Mater.*, 2024, **34**, 2313496.
27. Y. F. Li, W. J. Ma, H. H. Yang, Q. Y. Tian, Q. Xu and B. X. Han, *Chem. Commun.*, 2022, **58**, 6833-6836.
28. J. L. Hu, C. Z. Lai, K. Y. Chen, Q. P. Wu, Y. P. Gu, C. L. Wu and C. L. Li, *Nat. Commun.*, 2022, **13**, 7914.
29. F. F. Zheng, C. W. Li, Z. C. Li, X. Cao, H. B. Luo, J. Liang, X. D. Zhao and J. Kong, *Small*, 2023, **19**, 2206355.
30. X. W. Yu, Y. J. Liu, J. B. Goodenough and A. Manthiram, *ACS Appl. Mater. Interfaces*, 2021, **13**, 30703-30711.
31. G. Xi, M. Xiao, S. J. Wang, D. M. Han, Y. N. Li and Y. Z. Meng, *Adv. Funct. Mater.*, 2021, **31**, 2007598.
32. Y. Q. Liao, L. X. Yuan, Y. Han, C. F. Liang, Z. Z. Li, Z. Li, W. Luo, D. H. Wang and Y. H. Huang, *Adv. Mater.*, 2024, **36**, 2312287.
33. X. Q. Huang, Z. P. Zhao, L. Cao, Y. Chen, E. B. Zhu, Z. Y. Lin, M. F. Li, A. M. Yan, A. Zettl, Y. M. Wang, X. F. Duan, T. Mueller and Y. Huang, *Science*, 2015, **348**, 1230-1234.
34. Y. Yang, Z. Y. Lin, S. Q. Gao, J. W. Su, Z. Y. Lun, G. L. Xia, J. T. Chen, R. R. Zhang and Q. W. Chen, *ACS Catal.*, 2017, **7**, 469-479.
35. G. Liu, M. Reinhout, B. Mainguy and G. L. Baker, *Macromolecules*, 2006, **39**, 4726-4734.
36. J. Y. Zhang, Y. L. Yan, X. Wang, Y. Y. Cui, Z. F. Zhang, S. Wang, Z. K. Xie, P. F. Yan and W. H. Chen, *Nat. Commun.*, 2023, **14**, 3701.
37. S. D. Huo, L. Sheng, W. D. Xue, L. Wang, H. Xu, H. Zhang and X. M. He, *Infomat*, 2023, **5**, e12394.
38. H. Zhang, C. M. Li, M. Piszcz, E. Coya, T. Rojo, L. M. Rodriguez-Martinez, M. Armand and Z. B. Zhou, *Chem. Soc. Rev.*, 2017, **46**, 797-815.
39. N. Chen, Y. J. Dai, Y. Xing, L. L. Wang, C. Guo, R. J. Chen, S. J. Guo and F. Wu, *Energy Environ. Sci.*, 2017, **10**, 1660-1667.
40. R. Kumar, S. Sharma, D. Pathak, N. Dhiman and N. Arora, *Solid State Ionics*, 2017, **305**, 57-62.
41. X. Zhou, B. Zhang, F. Huang, F. Li, Z. Ma and J. Liu, *Nano Energy*, 2023, **108**, 108221.
42. T. Krah, A. Vimont, G. Eltanany, M. Daturi and E. Kemnitz, *J. Phys. Chem. C*, 2007, **111**, 18317-18325.
43. S. J. Wen, T. J. Richardson, D. I. Ghantous, K. A. Striebel, P. N. Ross and E. J. Cairns, *J. Electroanal. Chem.*, 1996, **408**, 113-118.
44. J. Q. Sun, C. H. He, Y. G. Li, Q. H. Zhang, C. Y. Hou, M. De Volder, K. R. Li and H. Z. Wang, *Energy Storage Mater.*, 2023, **54**, 40-50.
45. S. Zhong, Y. S. Yu, Y. Yang, Y. Yao, L. F. Wang, S. N. He, Y. X. Yang, L. Liu, W. P. Sun, Y. Z. Feng, H. G. Pan, X. H. Rui and Y. Yu, *Angew. Chem. Int. Ed.*, 2023, **62**, e202301169.
46. M. Y. Xu, Y. Li, M. Ihsan-Ul-Haq, N. Mubarak, Z. J. Liu, J. X. Wu, Z. T. Luo and J. K. Kim, *Energy Storage Mater.*, 2022, **44**, 477-486.
47. J. Luo, M. R. Yang, D. H. Wang, J. Y. Zhang, K. M. Song, G. C. Tang, Z. K. Xie, X. N. Guo, Y. Shi and W. H. Chen, *Angew. Chem. Int. Ed.*, 2024, **62**, e202315076.
48. J. F. Liu, Z. Y. Wu, F. J. Stadler and Y. F. Huang, *Angew. Chem. Int. Ed.*, 2023, **62**, e202300243.
49. B. Qiu, N. Sun, X. Li, R. A. Soomro, Y. Guan, H. Mi and B. Xu, *Adv. Funct. Mater.*, 2025, e12543.



All data generated or analyzed during this study are included in this manuscript and its supplementary information files.

[View Article Online](#)

[DOI: 10.1039/D5EB00117J](#)

