Soft Matter

Accepted Manuscript



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/softmatter

Journal Name

ARTICLE TYPE

Cite this: DOI: 10.1039/xxxxxxxxx

Revealing the signature of dipolar interactions in dynamic spectra of polydisperse magnetic nanoparticles[†]

Alexey O. Ivanov,*^a Vladimir S. Zverev,^a and Sofia S. Kantorovich^{a,b}

Received Date Accepted Date

DOI: 10.1039/xxxxxxxxx

www.rsc.org/journalname

We investigate, via modified mean field approach, the dynamic magnetic response of a polydisperse dipolar suspension to a weak, linear polarised, AC field. We introduce an additional term into the Fokker-Planck equation, which takes into account dipole-dipole interaction in the form of the first order perturbation, and allows for particle polydispersity. The analytical expressions, obtained for the real and imaginary dynamic susceptibilities, predict three measurable effects: the increase of the real part low-frequency plateaux; the enhanced growth of the imaginary part in the low-frequency range; and the shift of the imaginary part maximum. Our theoretical predictions find an experimental confirmation and explain the changes in the spectrum.

1 Introduction

AC susceptometry is a widely used technique to analyse and characterise the dynamic dielectric and magnetic response in molecular and supramolecular liquids, solutions and suspensions $^{1-4}$. On the molecular level, this method can provide important information about the structure and distributions of both dipoles and charges depending on the details of the system $^{1,5-8}$. In the case of supramolecular liquids or solutions, depending on the frequency range, dielectric spectroscopy is an efficient tool to investigate polarisation effects, charge transport and collective dipolar fluctuations^{1,4}. Increasing the size of building blocks, AC susceptometry turns out to be very useful to elucidate the properties of nanoparticle suspensions, such as correlations in polyelectrolytes^{4,9} or magnetic relaxation in the case of magnetic soft materials^{10–13}. In magnetic soft matter, dynamic response is used to characterise the systems $^{14-16}$. The broad range of applications and the fundamental importance of molecular liquids can hardly be overestimated ^{3,4,17}, but the impact of magnetic nanoparticles has also grown significantly in the last decade. The latter is related to the increasing interest in biological and medical applications of magnetic soft materials for diagnostics, therapy and in*vitro* analysis $^{18-21}$. One of the examples, based on the dynamic magnetic relaxation of magnetic particles, is so-called hyperther mia^{22-25} . In this method it is absolutely essential to predict the frequencies and the characteristic relaxation scales of the systems depending on the particle anisotropy, granulometric composition and magnetic phase concentration²⁶⁻²⁸. Traditional methods to do this are based on the Debye-like approach, in which magnetic nanoparticles are considered to form an ideal superparamagnetic "gas"^{2,27}. Despite being very simple and clear, this method ignores the inherent and sometimes crucial interparticle correlations, providing as such the incorrect low-frequency behaviour. The latter is known to differ significantly from the so-called Langevin law, even for the systems where the dipolar interactions have the same order as thermal fluctuations²⁹. Stronger interparticle or intermolecular interactions can lead to a broad range of structuring^{30,31} and self-assembly^{11,32-35} in soft matter, which cannot but affect the dynamics of these systems. Several attempts to incorporate the dipole-dipole interaction into the theoretical description of dynamic spectra are known^{36–39}. The main conclusion of these works is that the dipolar correlations slow down the dynamics and result in larger relaxation time-scales^{36–38}. The role of magnetic dipolar interactions on the the specific absorption rate was actively studied both theoretically and experimentally 40-42. In these works it was shown that the interparticle correlations might lead to the decrease and as well as the increase in the hypothermia efficiency depending on the magnetic particle size, thus underlining the crucial part of polydispersity and interactions on the dynamic magnetic response. Unfortunately, these approaches cannot be directly applied to predict or analyse the dynamic spectra of magnetic dipolar nanoparticle systems, as they lack an intrinsic feature of the latter, namely, particle polydispersity.

In this manuscript, we present a new theoretical approach based on the solution of Fokker-Planck equation with an additional term in the form of the modified mean field. This term is



^a Ural Federal University, Lenin av. 51, 620000, Ekaterinburg, Russia

^b University of Vienna, Sensengasse 8, 1090, Vienna, Austria; sofia.kantorovich@univie.ac.at

[†] Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/b000000x/

the first order perturbation that allows for the magnetic dipoledipole interaction in the system. In this framework, the particle polydispersity enters the equation in a very natural and straightforward way. The resulting expressions for the initial dynamic susceptibility, i.e. dynamic response of the system to a weak, linear polarised, harmonic, external field, have a closed analytical form and represent the first-order density corrections to the Debye spectrum. We apply our formalism to describe three measurable effects stemming from the interparticle correlations: the low-frequency regime of the real part of the dynamic susceptibility; its imaginary part maximum shift; and the low-frequency growth of the imaginary part. Analysing the effect of the dilution on the experimentally obtained spectra, we not only find a very good agreement of our theoretical results and the experimental data, but also conclude that the measured spectra do not reflect the superposition of the individual particle relaxations, but are the consequences of the complex interplay between this individual particles' dynamics, their polydispersity, and the interparticle interactions, both steric and magnetic.

Although, here, we will focus on the simplest case of magnetic dipoles and magnetic fields, the approach put forward in this manuscript is rather generic and can be applied to the dipoles of different nature. Here, it is worth saying that for electric dipoles the approach has to be extended as both higher order corrections to the dipolar interactions and the currents might become relevant, see, for example⁷ and references therein.

2 Theoretical Approach

Let us consider a system of single-domain magnetic nanoparticles with number density n, suspended in a liquid magnetopassive carrier, in a long cylindrical tube, whose long axis coincides with O_z of the coordinate system. A weak linearly polarised ac magnetic field $\mathbf{H} = (0, 0, h \exp(i\omega t))$ is applied along *Oz*-axis (*h* is the amplitude; ω stands for the angular frequency; *t* denotes time). At a given temperature T, each magnetic particle (magnetic core diameter x) has a magnetic dipole $(\mu, |\mu| \equiv \mu(x) = \pi M_0 x^3/6)$. Here, M_0 is the saturation magnetisation of the magnetic material. The orientation of each dipole is characterised by the angle $\theta = \angle (\mu, \mathbf{H})$, and can be described by the probability density $W(t, \theta)$. This probability in reality is determined by three factors: thermal fluctuations, dipole-field coupling and interparticle interactions. In the classical approach, for a randomly chosen dipolar particle (1) this density $(W(t, \theta_1) \equiv W(1))$ is the solution of the Fokker-Planck equation:

$$2\tau_{1}\frac{\partial W(1)}{\partial t} = \frac{1}{\sin\theta_{1}}\frac{\partial}{\partial\theta_{1}}\left\{\sin\theta_{1}\left[\frac{\partial W(1)}{\partial\theta_{1}} - W(1)\frac{\partial U_{H}(1)}{\partial\theta_{1}}\right]\right\}; \quad (1)$$
$$U_{H}(1) = (\mu_{1} \cdot \mathbf{H})/kT = \alpha_{1}e^{i\omega t}\cos\theta_{1}.$$

Here, τ_1 is the characteristic relaxation time of the particle (1). The function $U_{\rm H}(1)$ describes the interaction of the first particle with an applied external field and has the form of Zeeman energy related to kT; $\alpha_1 = \mu_1 h/kT$ is the first particle Langevin parameter. Equation (1) is usually used to describe the fluctuations of the single-domain magnetic particle magnetisation, assuming that the problem is polar-rotation independent^{43,44}. Be-

sides that, equation (1) holds true only for a system of noninteracting dipoles. The solution of Eq. (1) should satisfy the probability normalisation condition, and also defines the magnetisation as a function of time:

$$M(t) = \frac{n}{2} \int_{0}^{\pi} sin(\theta) d\theta \int_{0}^{\infty} W(t,\theta) \cos \theta \mu(x) p(x).$$
(2)

One can notice that Eq. (1) is a one-particle equation, and as such it depends on the properties of the given particle. In this way, it turns out to be very easy to allow for the inherent polydispersity of particles in dipolar soft matter. Thus, the expression for M(t) contains the averaging, not only over all orientations, but also over the granulometric composition p(x) (each particle has a dipole moment $\mu(x)$). Assuming that the field amplitude h is small, the solution of Eq. (1) can be easily found within the linear response approach:

$$W_0(1) = 1 + \frac{\alpha_1 \cos \theta_1}{1 + i\omega \tau_1} e^{i\omega t}.$$
(3)

In other words, for a system of polydisperse dipolar particles, we obtain familiar Debye linear response expressions for the dynamic initial (zero field) susceptibility $\chi_{\rm D}(\omega) = \chi'_{\rm D}(\omega) - i\chi''_{\rm D}(\omega)$:

$$\chi_{\rm D}'(\omega) = \frac{n}{3kT} \int_{0}^{\infty} \frac{\mu^2(x)}{1 + \omega^2 \tau^2(x)} p(x) dx,$$

$$\chi_{\rm D}''(\omega) = \frac{n}{3kT} \int_{0}^{\infty} \frac{\mu^2(x)\omega\tau(x)}{1 + \omega^2 \tau^2(x)} p(x) dx.$$
(4)

For many decades these classical formulas have been widely used for processing the dynamic spectra of both magnetic and electric responses. However, in reality they are valid for very diluted systems only, since in the zero-frequency limit the real part (4) predicts the Langevin value $\chi_L = n \langle \mu^2 \rangle / 3kT$ for the static susceptibility, which is linearly dependent on particle number density and contains averaged over all particles sizes dipole moment $\langle \mu^2 \rangle$. It holds true only for vanishing n; even for low and moderate concentrations, a large number of experimental measurements and computer simulations^{29,45,46} prove the susceptibility to obey the parabolic *n*-dependence (19). Density dependence is also inherent to the position of the imaginary part maximum and is not reflected by the Debye model (see, below Fig. 1). All this clearly underlines the necessity to include interdipolar correlations in the description of the dynamic spectra. At the same time, in the static case, the modified mean-field approach⁴⁷ prove to be a very accurate model to describe equilibrium magnetic properties of moderately interacting dipolar systems. Thus, modifying Eq. (1), we know the static limit of the perturbed solution. In equilibrium conditions (static uniform magnetic field H, $\omega = 0$) $\partial W(1)/\partial t = 0$, *i.e.* the expression in square brackets in Eq. (1) becomes zero

$$\frac{\partial \tilde{W}(1)}{\partial \theta_1} - \tilde{W}(1) \frac{\partial U_{\rm H}(1)}{\partial \theta_1} = 0.$$
(5)

Soft Matter

=

Here, we indicate the equilibrium orientation probability density with tilde. The solution of Eq. (5) has the Boltzmann form

$$\tilde{W}_0(1) = (\alpha_1 / \sinh \alpha_1) \exp(\alpha_1 \cos \theta_1),$$

and leads to the Langevin law for magnetisation:

$$M(H) = n \int_{0}^{\infty} \left[\coth \frac{\mu(x)H}{kT} - \frac{kT}{\mu(x)H} \right] \mu(x)p(x)dx, \tag{6}$$

valid only for an ideal paramagnetic gas. On the other hand, the equilibrium probability density should satisfy the equation, connecting the one-particle probability density with the pair distribution function $g_2(1,2)^{47}$:

$$\frac{\partial \tilde{W}(1)}{\partial \theta_1} - \tilde{W}(1) \frac{\partial U_{\rm H}(1)}{\partial \theta_1} = n \left\langle g_2(1,2) \frac{\partial U_{\rm dd}(1,2)}{\partial \theta_1} \right\rangle_2, \tag{7}$$
$$\langle \dots \rangle_k = \int_0^\infty \left(\int d\Omega_k \int d\mathbf{r}_k \dots \right) p(x_k) dx_k,$$
$$d\Omega_k = (4\pi)^{-1} \sin \theta_k d\theta_k d\zeta_k, \quad d\mathbf{r}_k = r_k^2 dr_k \sin \psi_k d\psi_k d\phi_k.$$

Here, the azimuthal and the polar angles (θ_k and ζ_k) define the orientation of the *k*-th magnetic moment in spherical coordinate system, and the vector \mathbf{r}_k denotes the radius-vector of the *k*-th particle. The integration in angular brackets means the averaging over all degrees of freedom and over all possible sizes of the *k*-th particle. Expanding the pair distribution function $g_2(1,2)$ in series over the particle concentration *n*, and considering the presence of *n* in the Eq. (7), the pair distribution function might be expressed in the following form, that corresponds to the lowest order of the thermodynamic perturbation method:

$$g_2(1,2) = \tilde{W}(1)\tilde{W}_0(2)\Theta(1,2),$$
(8)

where $\Theta(1,2)$ is the Heaviside step-function, describing the impenetrability of two dipolar particles, and the function $\tilde{W}_0(2)$ is the probability density of the ideal paramagnetic gas. Substituting it in the right-hand part of Eq. (7) and using the fact that $\tilde{W}(1)$, $\tilde{W}_0(2)$ and $\Theta(1,2)$ do not depend on θ_1 and that $\tilde{W}(1)$ does not need to be averaged over the second dipole orientations, we obtain:

$$\left\langle g_{2}(1,2)\frac{\partial U_{dd}(1,2)}{\partial \theta_{1}}\right\rangle_{2} = \left\langle \tilde{W}(1)\tilde{W}_{0}(2)\Theta(1,2)\frac{\partial U_{dd}(1,2)}{\partial \theta_{1}}\right\rangle_{2} = \tilde{W}(1)\frac{\partial}{\partial \theta_{1}}\left\langle \tilde{W}_{0}(2)U_{dd}(1,2)\Theta(1,2)\right\rangle_{2}.$$
(9)

So, the equilibrium Fokker-Planck equation (5) can be written as

$$\frac{\partial \tilde{W}(1)}{\partial \theta_1} - \tilde{W}(1) \frac{\partial \tilde{U}_e(1)}{\partial \theta_1} = 0, \tag{10}$$

$$\tilde{U}_{\rm e}(1) = U_{\rm H}(1) + n \left\langle \tilde{W}_0(2) U_{\rm dd}(1,2) \Theta(1,2) \right\rangle_2;$$

where

$$U_{\rm dd}(1,2) = \frac{1}{kT} \left[3 \frac{(\mu_1 \cdot \mathbf{r}) (\mu_2 \cdot \mathbf{r})}{r^5} - \frac{(\mu_1 \cdot \mu_2)}{r^3} \right].$$
 (11)

The second term in $\tilde{U}_{e}(1)$ is the dipole-dipole interaction $(U_{dd}(1,2))$ between particles (1) and (2), separated by the centreto-centre distance $|\mathbf{r}| = r$, and it is weight-averaged over all possible orientations, positions and sizes of the randomly chosen particle (2).

Returning to a non-equilibrium case, Eq. $(1)^2$ transforms into Eq.(12)

$$2\tau_{1}\frac{\partial W(1)}{\partial t} = \frac{1}{\sin\theta_{1}} \times$$

$$<\frac{\partial}{\partial\theta_{1}} \left\{ \sin\theta_{1} \left[\frac{\partial W(1)}{\partial\theta_{1}} - W(1) \frac{\partial U_{e}(1)}{\partial\theta_{1}} \right] \right\}.$$
(12)

where instead of an equilibrium function \tilde{W} , its non-equilibrium analogue W is used. In this case, $\tilde{U}_e(1)$ should be also replaced by $U_e(1)$. In general, function U_e , described by Eq. (13), denotes the dimensionless effective field (normalised by thermal energy kT), with which a randomly chosen dipole moment interacts in the system. It consists of the external field and the effective field created by all other dipoles. This term provides a key difference between our approach and standard Weiss-like mean-field models.

$$U_{\rm e}(1) = U_{\rm H}(1) + n \langle W_0(2) U_{\rm dd}(1,2) \Theta(1,2) \rangle_2.$$
 (13)

Let us find the solution of Eq. (12). The ideal gas probability density W_0 is its solution if the *n*-dependent term, allowing for interparticle interactions, is neglected. Using the expression in Eq. (3) for the particle 2, we may calculate the effective field produced by all dipoles:

$$\langle W_0(2)U_{dd}(1,2)\Theta(1,2)\rangle_2 =$$

$$= e^{i\omega t} \int_0^\infty \frac{\alpha(x_2)}{1+i\omega\tau(x_2)} \int d\mathbf{r}_2 \Theta(1,2) \int d\Omega_2 U_{dd}(1,2) \cos\theta_2 p(x_2) dx_2 =$$

$$= \frac{e^{i\omega t}}{kT} \int_0^\infty \frac{\alpha(x_2)}{1+i\omega\tau(x_2)} \int d\Omega_2 (\mu_2 \cdot \hat{\mathbf{z}})^2 p(x_2) dx_2 \times$$

$$\times \int d\mathbf{r}_2 \Theta(1,2) \left[3 \frac{(\mu_1 \cdot \mathbf{r})(\mathbf{r} \cdot \hat{\mathbf{z}})}{r^5} - \frac{(\mu_1 \cdot \hat{\mathbf{z}})}{r^3} \right] = (14)$$

$$= \frac{e^{i\omega t}}{kT} \int_0^\infty \frac{\alpha(x_2)}{1+i\omega\tau(x_2)} \frac{\mu(x_2)}{3} p(x_2) dx_2 \frac{4\pi\mu_1 \cos\theta_1}{3} =$$

$$= \frac{4\pi\alpha_1 \cos\theta_1 e^{i\omega t}}{9kT} \int_0^\infty \frac{1-i\omega\tau(x)}{1+\omega^2\tau^2(x)} \mu^2(x) p(x) dx,$$

where we introduce the unit vector $\hat{\mathbf{z}}$ of O_z -axis. Note that the integral $d\mathbf{r}$ over translational degrees of freedom is dependent on the shape of the container; here, the usage of the long cylindric tube allows to avoid the demagnetisation effects. The technical details of the integration can be found in ⁴⁷. Hence, the effective field term is

$$U_{e}(1) = \alpha_{1} \cos \theta_{1} e^{i\omega t} \left[1 + \frac{4\pi n}{9kT} \int_{0}^{\infty} \frac{1 - i\omega\tau(x)}{1 + \omega^{2}\tau^{2}(x)} \mu^{2}(x)p(x)dx \right] \equiv$$

$$\equiv \alpha_{1} \cos \theta_{1} e^{i\omega t} \left[1 + \frac{4\pi}{3} \left(\chi_{D}'(\omega) - i\chi_{D}''(\omega) \right) \right].$$
(15)

The integration here does not depend on the index of a chosen particle. As a result, the effective field $U_e(1)$ turns out to be expressed in terms of Debye susceptibilities. We can present the solution of Eq. (12) in the form of the sum of the zeroth and the first harmonic

$$W(1) = 1 + \alpha_1 A_1(\omega) \cos \theta_1 e^{i\omega t}, \qquad (16)$$

where the zeroth harmonics is simply equal to unity. The first harmonics amplitude $A_1(\omega) = A'_1(\omega) - iA''_1(\omega)$ is complex, and its real and imaginary parts satisfy the linear set of equations:

$$\begin{cases} A_1'(\boldsymbol{\omega}) + \boldsymbol{\omega}\tau_1 A_1''(\boldsymbol{\omega}) = 1 + 4\pi \chi_D'(\boldsymbol{\omega})/3, \\ \boldsymbol{\omega}\tau_1 A_1'(\boldsymbol{\omega}) - A_1''(\boldsymbol{\omega}) = -4\pi \chi_D''(\boldsymbol{\omega})/3. \end{cases}$$
(17)

The dynamic susceptibility $\chi(\omega)$ is also defined by A_1 , and we obtain the expressions for the real and imaginary parts of the spectrum in the interacting dipolar system:

$$\chi(\omega) \equiv \chi'(\omega) - i\chi''(\omega) = \frac{n}{3kT} \left\langle \mu_1^2 \left[A_1'(\omega) - iA_1''(\omega) \right] \right\rangle_1, \quad (18)$$
$$\chi'(\omega) = \chi_D'(\omega) + \frac{4\pi}{3} \left[\chi_D'^2(\omega) - \chi_D''^2(\omega) \right],$$
$$\chi''(\omega) = \chi_D''(\omega) \left[1 + \frac{8\pi}{3} \chi_D'(\omega) \right].$$

The novelty of the described above approach is to introduce the second term for the effective field produced by all dipole moments $(n \langle W_0(2)U_{dd}(1,2)\Theta(1,2)\rangle_2)$ into the expression for $U_e(1)$ to construct Eq. (12).

This term has a meaning of the effective field acting on each particle due to the presence of all others. In the case of the static applied field ($\omega \rightarrow 0$), the perturbation theory of the first order in *n* correctly leads to a well-tested modified mean field approach⁴⁷ expression for the initial susceptibility:

$$\chi(0) = \chi_L (1 + 4\pi \chi_L/3).$$
 (19)

In the latter, the effective field is expressed in terms of Langevin susceptibility χ_L . Importantly, the expressions in Eq. (18) are the exact results of the first order perturbation theory and, being expressed in terms of Debye dynamic susceptibilities, have the quadratic precision in *n*. Besides that, in zero-frequency limit, the real part $\chi'(\omega \to 0) = \chi(0)$ (see, Eq. (19)). In contrast to the aforementioned attempts to allow for interparticle interactions^{36–39}, this approach extends the concept of modified mean field, does not contain any Weiss-type singularities, and takes accurately into account the part of polydispersity. The latter is of crucial importance when applying the model to describe real experimental systems.

Below, as one of the measurable characteristics of the spectrum, we analyse the dependence of the frequency ω^* , at which the maximum of the imaginary part is reached, which, as mentioned above, does not depend on *n* in the framework of standard Eq. (1). We can define the value of ω^* in our formalism by solving

1-7

$$\frac{\partial \chi''(\omega)}{\partial \omega}\bigg|_{\omega=\omega^*} = 0.$$
 (20)

For the polydisperse case, the solution can be only found implicitly:

$$\left[1 + \frac{8\pi}{3}\chi_{\rm D}'(\omega_*)\right] \int_0^\infty \frac{1 - \omega_*^2 \tau^2(x)}{\left[1 + \omega_*^2 \tau^2(x)\right]^2} \tau(x) x^6 p(x) dx =$$
$$= \frac{16\pi}{3}\chi_{\rm D}''(\omega_*) \int_0^\infty \frac{\omega_* \tau^2(x) x^6}{\left[1 + \omega_*^2 \tau^2(x)\right]^2} p(x) dx.$$
(21)

In the monodisperse case, one can replace p(x) by δ -function corresponding to a chosen particle size. This substitution, after some algebra, leads to the equation for ω^* :

$$\begin{bmatrix} \left(\frac{\omega_*(0)}{\omega_*(\varphi_m)}\right)^2 + 1 + \frac{8\pi\chi_L(\varphi_m)}{3} \left(\frac{\omega_*(0)}{\omega_*(\varphi_m)}\right)^2 \end{bmatrix} \begin{bmatrix} \left(\frac{\omega_*(0)}{\omega_*(\varphi_m)}\right)^2 - 1 \end{bmatrix} = \frac{16\pi\chi_L(\varphi_m)}{3} \left(\frac{\omega_*(0)}{\omega_*(\varphi_m)}\right)^2.$$
(22)

The ratio in the brackets $(\omega_*(0)/\omega_*(\varphi_m))^{-1}$ shows the shift of the maximum position with respect to its zero-concentration value $(\omega_*(0))$. The solution of the latter bi-quadratic equation always exists, however, our approach is the low-order perturbation in particle concentration *n*, *i.e.* in the magnetic phase fraction φ_m . So, it is only meaningful to find the solution in the linear order in $\chi_L \propto \varphi_m$:

$$\frac{\boldsymbol{\omega}_*(0)}{\boldsymbol{\omega}_*(\boldsymbol{\varphi}_m)} = 1 + \frac{4\pi\chi_L(\boldsymbol{\varphi}_m)}{3}.$$
 (23)

In the following we will test Expressions from Eq. (18) by comparing the latter to the experimental results for moderately interacting magnetic fluids.

3 Results and Discussions

One of the known mechanisms for a dipole moment to relax in a carrier liquid is a so-called Brownian rotation. Its characteristic time $\tau_{\rm B} = 3\eta v/kT$ is determined by the particle hydrodynamic volume $v = \pi x_h^3/6$ (x_h being a hydrodynamic particle diameter), and the carrier viscosity η . In the case of magnetic nanoparticles, their dipole can also relax via Neél mechanism, which does not involve the rotation of the particle as a whole. Rather, it is due to the fluctuation of the dipole moment within the crystalline lattice of the nanoparticle⁴⁸. The latter mechanism has a characteristic time $\tau_{\rm N} = \tau_0 \exp(K v_m / kT)$, which depends on the particle characteristic relaxation time scale $\tau_0 \sim 10^{-9}$ sec, anisotropy constant *K*, and its magnetic core volume $v_m = \pi x^3/6$. For each dipole in the system, its most probable relaxation is the shortest of $\tau_{\rm N}$ and $\tau_{\rm B}$, which is why it is common to use the following expression for the relaxation time as a function of the particle size: $\tau(x) = \tau_{\rm N} \tau_{\rm B} / (\tau_{\rm N} + \tau_{\rm B}).$

In order to illustrate the model proposed above for the dynamic response, we use two ferrofluids with well-defined particlesize distributions that can be accurately described using gammadistribution:

$$p(x) = \frac{1}{x_0} \left(\frac{x}{x_0}\right)^a \frac{\exp\left(-x/x_0\right)}{\Gamma(a+1)}.$$
 (24)

The first ferrofluid, F1 (magnetite nanoparticles in kerosene, stabilised with oleic acid, $x_0 = 1.23$ nm; a = 4.95, $x_h = x+6$ nm),

was extensively studied by a combination of experiment, theory and computer simulations in Ref.²⁹, where the static magnetic properties were analysed. In this work, the basic sample was diluted to obtain another 6 samples with the same granulometric composition, but different magnetic material content. In the static case, we showed that the modified mean field approach is a suitable model to describe the initial susceptibility and the magnetisation curves for each sample. Here, we use this system to



Fig. 1 Dynamic Susceptibility $4\pi\chi(\omega)$ of F1: comparison of the Debye ideal gas model to the expressions in Eq. (18). Frequency range is given in log-scale. Here, $\varphi_m = 0.06$; T = 293 K; K = 20 kJ/m³; effective viscosity $\eta = 2 \times 10^3$ Pa sec; $M_0 = 480$ kA/m.

analyse the dynamic response, because we know that the static limit Eq. (19) of the proposed model Eq. (18) is correct. The commonly used Debye ideal gas model (4) does not provide this kind of $\omega \rightarrow 0$ asymptote, and as such is expected to provide a quantitatively different susceptibility spectrum. This is fully confirmed by Fig. 1, where we plot the dynamic susceptibility for the F1 with magnetic phase concentration ($\varphi_m = 0.06$) calculated using both aforementioned formalisms. In addition to the difference in the values of χ' , one also sees that for χ'' , both the height of the maximum and its position are not the same if the interparticle correlations are properly taken into account. Note that the maximum of χ'' is of particular importance, as it determines the characteristic frequency of the corresponding dipolar fluid. In order to analyse the influence of particle concentration on the dynamic spectrum, in Fig. 2, we plot $\chi(\omega)/\chi(0)$ for three different values of φ_m . The spectrum visibly changes on dilution: the maximum of χ' shifts to higher ω when φ_m decreases. In the inset, the frequency ($\omega^*(\varphi_m)$), at which the maximum of the imaginary part of the spectrum is reached, is plotted normalised by $\omega^*(0)$. In the same inset of Fig. 2, we plot the theoretical prediction for reduced ω^* for a monodisperse system with the same value of χ_L , i.e. with the same value of the mean-squared magnetic moment Eq. (23). It can be seen that the relative shift of ω^* is stronger in the monodisperse system. It is the consequence of the following: in a polydisperse system, the value of ω^* is determined by a relatively small number of Brownian particles that



Fig. 2 Reduced Dynamic Susceptibility $\chi(\omega)/\chi(0)$ of F1: the effect of dilution. Three spectrums are plotted for $\varphi_m = 0.12; 0.06; 0.01$ in blue, orange and bordeaux respectively. Frequency range is given in log-scale. Inset: the dependence $\omega^*(\varphi_m)/\omega^*(0)$. Solid line is the solution of Eq. (21); the dotted line is a corresponding monodisperse sample Eq. (23).

slowly grows with φ_m , whereas in a corresponding monodisperse system all particles contribute to the same relaxation. However, even for a polydisperse ferrofluid, this effect is large enough to be measured; the experiment, however, should be performed accurately without changing the granulometric composition on dilution. To the best of our knowledge, only one experimental work is available¹¹, that satisfies the aforementioned condition. In the plot below (Fig. 3), we compare our theoretical prediction to the results measured for system C from¹¹, which we address as F2 (ferrum-cobalt particles in Decalin, stabilised by polyisobuten). Following the experimental strategy, we analyse the spectra of F2 and F2 diluted by 10 times. After fitting gamma-distribution Eq. (24) to that of Ref. ¹¹ we obtained $x_0 = 0.38$ nm; a = 17, $x_h = x + 17$ nm. Even for a low concentrated reference sample, the value of ω^* shifts by 10 per cent on 10 times dilution. As it is stated in Ref.¹¹, in sample F2 no aggregates were observed; this is why the changes in the dynamic spectrum are to be attributed to the dipolar interparticle correlations only, and the prediction of Eq. (18) is fully capable of describing them.

The other measurable effect can be observed when analysing the initial slope κ of χ'' :

$$\kappa \equiv \lim_{\omega \to 0} \frac{4\pi \chi''(\omega)}{\omega} = 4\pi \chi_L \left(1 + \frac{8\pi \chi_L}{3} \right) \tau_{\text{char}}, \quad (25)$$
$$\tau_{\text{char}} = \left(\int_0^\infty x^6 p(x) dx \right)^{-1} \int_0^\infty x^6 \tau(x) p(x) dx,$$

which depends parabolically on the particle concentration through χ_L and contains a very important characteristic of the system, namely τ_{char} . The latter has the meaning of the relaxation time averaged over the system granulometric composition with the weight of mean-squared particle dipole moment. From



Fig. 3 Dynamic Susceptibility $4\pi\chi(\omega)$ of F2: comparison of the experimental data to the expressions in Eq. (18). Frequency range is given in log-scale. Here, mass fraction of iron for the basic sample is 0.061; T = 293 K; K = 100 kJ/m³; effective viscosity $\eta = 5 \times 10^3$ Pa sec; $M_0 = 1490$ kA/m. Reference sample: orange, filled symbols; 10 times diluted sample: blue, empty symbols (rescaled to be visible).

Eq. (4), the analogous slope κ_D is linear in concentration, but contains the same characteristic time scale as a prefactor. In Fig.



Fig. 4 Initial slope (κ) as a function of φ_m : comparison of the Debye ideal gas model to the expressions in Eq. (25). The results for F1 (black) are associated with the left ordinate axis; the results for F2 (orange) with the right one. Inset: particle size distributions versus magnetic core diameter (x).

4 we plot $\kappa(\varphi_m)$ for F1 and F2 as predicted by Debye ideal gas model Eq. (4) and by the modified mean field approach Eq. (18). The results of the two models differ substantially. The absolute value of these deviations are different for F1 and F2. In the case of F1, the quadratic correction from χ_L is not very large, because the particles in F1 are rather magnetically weak. On the other hand, particles in F2 are predominantly magnetically hard (very high crystallographic magnetic anisotropy), and in this case, the quadratic term in χ_L is much larger. The actual values of the slope are determined by the value of τ_{char} . Even though p(x) is broader in the case of F1, the value of τ_{char} for F2 is approximately an

1 - 7

order of magnitude larger, due to the dominance of the Brownian slower relaxations in it. Notice that, had we used the Debye model to extract τ_{char} from the experimental measurements, at a finite magnetic phase concentration of approximately 5 percent, the error due to the neglected interparticle correlations would have been as high as the factor of two.

4 Conclusions

Our study demonstrates the impact of the dipolar interparticle correlations on the dynamic susceptibility. By introducing the interparticle interactions and the inherent polydispersity into the theoretical model, we show that the dynamic spectra are not a simple reflection of the individual dipole relaxations in the system, but are rather defined by a complex weave of granulometric composition, individual particle properties, their interaction strengths, and particle concentration. There are three spectra characteristics that are especially sensitive to the nonideality of the system: the low-frequency behaviour of the real part; the low-frequency growth of the imaginary part; and the maximum of the imaginary part. Interactions lead to an overall decrease of the characteristic time-scales for a given polydisperse dipolar system on dilution. This result is especially important for medical applications of dipolar systems, where the correct prediction of the working frequency range defines the efficiency of the treatment^{19,40–42}. As we show in the present manuscript, the analysis of the spectra based on the Debye ideal gas approximation can lead to highly pronounced inconsistency in the determination of characteristic relaxations. We are confident that the presented theoretical predictions will serve as a motivation for further and more detailed AC susceptometry experiments.

Acknowledgements

The research is supported by Russian Science Foundation Grant No. 15-12-10003. S.S.K. is grateful to the FWF START-Projekt Y 627-N27 and EU-Project 642774 ETN-Colldense. We also thank Michaela McCaffrey for language suggestions.

References

- 1 F. Kremer and A. Schönhals, Broadband Dielectric Spectroscopy, 2003.
- 2 Y. L. Raikher and V. I. Stepanov, in *Nonlinear Dynamic Susceptibilities and Field-Induced Birefringence in Magnetic Particle Assemblies*, John Wiley and Sons Inc., 2004, pp. 419–588.
- 3 M. Michl, T. Bauer, P. Lunkenheimer and A. Loidl, *Phys. Rev. Lett.*, 2015, **114**, 067601.
- 4 V. Raicu and Y. Feldman, *Dielectric Relaxation in Biological Systems: Physical Principles, Methods, and Applications,* 2015.
- 5 L. P. Singh and R. Richert, Phys. Rev. Lett., 2012, 109, 167802.
- 6 Z. Wojnarowska, Y. Wang, J. Pionteck, K. Grzybowska, A. P. Sokolov and M. Paluch, *Phys. Rev. Lett.*, 2013, **111**, 225703.
- 7 M. Sega, S. S. Kantorovich, A. Arnold and C. Holm, *Recent Advances in Broadband Dielectric Spectroscopy*, Springer Netherlands, 2013, pp. 103–122.
- 8 M. Sega, S. S. Kantorovich, C. Holm and A. Arnold, *The Jour*nal of Chemical Physics, 2014, **140**, 211101.

Soft Matter

- 9 A. Kahouli, J. Valle-Orero, J.-L. Garden and M. Peyrard, *The European Physical Journal E*, 2014, **37**, 82.
- 10 A. Pshenichnikov and A. Lebedev, Journal of Experimental and Theoretical Physics, 1989, 68, 498–502.
- 11 B. H. Erné, K. Butter, B. W. M. Kuipers and G. J. Vroege, *Lang-muir*, 2003, **19**, 8218–8225.
- 12 S. H. Chung, A. Hoffmann, S. D. Bader, C. Liu, B. Kay, L. Makowski and L. Chen, *Applied Physics Letters*, 2004, 85, 2971–2973.
- 13 R. Ferguson, A. Khandhar, C. Jonasson, J. Blomgren, C. Johansson and K. Krishnan, *Magnetics, IEEE Transactions on*, 2013, **49**, 3441–3444.
- 14 C. Barrera, V. Florian-Algarin, A. Acevedo and C. Rinaldi, Soft Matter, 2010, 6, 3662–3668.
- 15 V. L. Calero-DdelC, D. I. Santiago-Quinonez and C. Rinaldi, Soft Matter, 2011, 7, 4497–4503.
- 16 R. S. M. Rikken, R. J. M. Nolte, J. C. Maan, J. C. M. van Hest, D. A. Wilson and P. C. M. Christianen, *Soft Matter*, 2014, **10**, 1295–1308.
- 17 S. Pawlus, S. Klotz and M. Paluch, *Phys. Rev. Lett.*, 2013, **110**, 173004.
- 18 J. Durán, J. Arias, V. Gallardo and A. Delgado, Journal of Pharmaceutical Sciences, 2008, 97, 2948–2983.
- 19 Q. A. Pankhurst, N. T. K. Thanh, S. K. Jones and J. Dobson, Journal of Physics D: Applied Physics, 2009, 42, 224001.
- 20 K. M. Krishnan, Magnetics, IEEE Transactions on, 2010, 46, 2523–2558.
- 21 M. M. van Oene, L. E. Dickinson, F. Pedaci, M. Köber, D. Dulin, J. Lipfert and N. H. Dekker, *Phys. Rev. Lett.*, 2015, **114**, 218301.
- 22 R. Hergt, R. Hiergeist, I. Hilger, W. Kaiser, Y. Lapatnikov, S. Margel and U. Richter, *Journal of Magnetism and Magnetic Materials*, 2004, **270**, 345 – 357.
- 23 F. Sonvico, S. Mornet, S. Vasseur, C. Dubernet, D. Jaillard, J. Degrouard, J. Hoebeke, E. Duguet, P. Colombo and P. Couvreur, *Bioconjugate Chemistry*, 2005, 16, 1181–1188.
- 24 J.-P. Fortin, C. Wilhelm, J. Servais, C. Ménager, J.-C. Bacri and F. Gazeau, *Journal of the American Chemical Society*, 2007, 129, 2628–2635.
- 25 Y. L. Raikher, V. V. Rusakov and R. Perzynski, Soft Matter, 2013, 9, 10857–10865.
- 26 R. Müller, R. Hergt, M. Zeisberger and W. Gawalek, *Journal* of Magnetism and Magnetic Materials, 2005, **289**, 13 16.
- 27 Y. L. Raikher and V. Stepanov, Journal of Magnetism and Magnetic Materials, 2014, 368, 421 – 427.
- 28 M. Boskovic, G. F. Goya, S. Vranjes-Djuric, N. Jovic, B. Jancar and B. Antic, *Journal of Applied Physics*, 2015, 117, –.
- 29 A. Ivanov, S. Kantorovich, E. Reznikov, C. Holm, A. Pshenichnikov, A. Lebedev, A. Chremos and P. Camp, *Phys. Rev. E*, 2007, **75**, 061405.
- 30 J. Köfinger and C. Dellago, *Phys. Rev. Lett.*, 2009, **103**, 080601.
- 31 D. Heinrich, A. R. Goñi, A. Smessaert, S. H. L. Klapp, L. M. C. Cerioni, T. M. Osán, D. J. Pusiol and C. Thomsen, *Phys. Rev.*

Lett., 2011, 106, 208301.

- 32 M. Klokkenburg, R. Dullens, W. Kegel, B. Erné and A. Philipse, *Phys. Rev. Lett*, 2006, **96**, 037203.
- 33 V. Domenici, C. A. Veracini and B. Zalar, *Soft Matter*, 2005, 1, 408–411.
- 34 S. Kantorovich, A. O. Ivanov, L. Rovigatti, J. M. Tavares and F. Sciortino, *Phys. Rev. Lett.*, 2013, **110**, 148306.
- 35 C. E. Alvarez and S. H. L. Klapp, Soft Matter, 2013, 9, 8761– 8770.
- 36 A. Y. Zubarev and A. V. Yushkov, Journal of Experimental and Theoretical Physics, 1998, 87, 484.
- 37 B. U. Felderhof and R. B. Jones, *Journal of Physics: Condensed Matter*, 2003, **15**, 4011.
- 38 P. Ilg and S. Hess, Zeitschrift f§r Naturforschung A, 2003, 58, 589–600.
- 39 P. M. Déjardin and F. Ladieu, *The Journal of Chemical Physics*, 2014, **140**, 034506.
- 40 E. L. Verde, G. T. Landi, J. A. Gomes, M. H. Sousa and A. F. Bakuzis, *Journal of Applied Physics*, 2012, **111**,.
- 41 M. A. Martens, R. J. Deissler, Y. Wu, L. Bauer, Z. Yao, R. Brown and M. Griswold, *Medical Physics*, 2013, **40**,.
- 42 G. T. Landi, Phys. Rev. B, 2014, 89, 014403.
- 43 W. F. Brown, Journal of Applied Physics, 1963, 34, 1319–1320.
- 44 J. Brown, W., Magnetics, IEEE Transactions on, 1979, 15, 1196–1208.
- 45 A. F. Pshenichnikov and A. V. Lebedev, J. Chem. Phys., 2004, 121, 5455–5467.
- 46 D. S. Wood and P. J. Camp, Phys. Rev. E, 2011, 83, 011402.
- 47 A. O. Ivanov and O. B. Kuznetsova, *Phys. Rev. E*, 2001, **64**, 041405–1.
- 48 A. Balan, P. M. Derlet, A. F. Rodríguez, J. Bansmann, R. Yanes, U. Nowak, A. Kleibert and F. Nolting, *Phys. Rev. Lett.*, 2014, 112, 107201.