

Cite this: *Chem. Sci.*, 2014, 5, 32

Evaluating metal-organic frameworks for natural gas storage†

Jarad A. Mason,^a Mike Veenstra^b and Jeffrey R. Long^{*a}

Metal-organic frameworks have received significant attention as a new class of adsorbents for natural gas storage; however, inconsistencies in reporting high-pressure adsorption data and a lack of comparative studies have made it challenging to evaluate both new and existing materials. Here, we briefly discuss high-pressure adsorption measurements and review efforts to develop metal-organic frameworks with high methane storage capacities. To illustrate the most important properties for evaluating adsorbents for natural gas storage and for designing a next generation of improved materials, six metal-organic frameworks and an activated carbon, with a range of surface areas, pore structures, and surface chemistries representative of the most promising adsorbents for methane storage, are evaluated in detail. High-pressure methane adsorption isotherms are used to compare gravimetric and volumetric capacities, isosteric heats of adsorption, and usable storage capacities. Additionally, the relative importance of increasing volumetric capacity, rather than gravimetric capacity, for extending the driving range of natural gas vehicles is highlighted. Other important systems-level factors, such as thermal management, mechanical properties, and the effects of impurities, are also considered, and potential materials synthesis contributions to improving performance in a complete adsorbed natural gas system are discussed.

Received 19th September 2013
Accepted 22nd October 2013

DOI: 10.1039/c3sc52633j

www.rsc.org/chemicalscience

Natural gas storage

Natural gas has the potential to replace petroleum as the world's primary fuel for transportation. Consisting mainly of methane (CH_4), natural gas has the highest H to C ratio of any fossil fuel, resulting in less CO and CO_2 released per unit of energy generated.¹ Lower sulfur and nitrogen contents also lead to lower SO_x and NO_x emissions, making natural gas a significantly cleaner burning fuel than gasoline.² Indeed, initial field tests found up to 86% less CO, 26% less CO_2 , and 77% less NO_x emissions after converting gasoline cars to run on natural gas.³ In addition, recent engineering advances in horizontal drilling and hydraulic fracturing have led to a rapid increase in global natural gas reserves, driving the price of natural gas below that of gasoline in many countries.⁴

^aDepartment of Chemistry, University of California, Berkeley, CA 94720, USA. E-mail: jrlong@berkeley.edu

^bFord Motor Company, Research and Advanced Engineering, Dearborn, MI 48121, USA

† Electronic supplementary information (ESI) available: Details of metal-organic framework synthesis and characterization, powder X-ray diffraction patterns, 77 K N_2 adsorption isotherms, density calculations, high-pressure adsorption experimental details, background high-pressure CH_4 adsorption isotherms, excess and total CH_4 adsorption isotherms, description of isotherm fitting, table of fitted parameters, description of isosteric heat of adsorption calculations, correlations between surface area and uptake, usable capacity plots for different adsorption/desorption conditions, description of optimal binding enthalpy calculations, raw experimental data, and an electronic version of Table 2. See DOI: 10.1039/c3sc52633j

In spite of this, several challenges have prevented the widespread use of natural gas in vehicles. Most importantly, the volumetric energy density of natural gas at ambient temperature and pressure is only 0.04 MJ L⁻¹, compared to 32.4 MJ L⁻¹ for gasoline.⁵ The volumetric energy density can be increased by compression or liquefaction, but both of these solutions are costly and poorly suited for light-duty passenger vehicles. For instance, compressed natural gas (CNG) requires expensive multi-stage compressors that consume energy, as well as heavy, bulky fuel tanks that reduce passenger and cargo space. Even with compression to 250 bar, the energy density of CNG (near 9 MJ L⁻¹) is only 26% that of gasoline,^{2a} leading to a significant reduction in the driving range of a vehicle. Moreover, CNG refueling stations are not yet common enough for convenient refueling and are costly to build.⁶

As a result of the low critical temperature of CH_4 (190.6 K, Table 1), natural gas cannot be liquefied by compression alone,

Table 1 Relevant physical properties of pure CH_4

Critical temperature ^{8a}	190.6 K
Boiling point ^{8a}	111.7 K
Kinetic diameter ⁹	3.80 Å
Polarizability ⁹	2.6 Å ³
Volumetric density (1 bar, 25 °C) ⁸	0.9 v/v
Volumetric density (250 bar, 25 °C) ⁸	263 v/v
Volumetric density (1 bar, -162 °C) ⁸	591 v/v

and cryogenic cooling is necessary to store liquefied natural gas (LNG). While the volumetric energy density of LNG can reach 20.8 MJ L^{-1} (64% of gasoline),⁵ the overall system energy density is reduced due to the insulation required to maintain a low temperature and prevent boil-off. Additionally, the high cost of cooling systems and complications of handling a cryogenic fuel make LNG unlikely to find much application in the transportation sector beyond commercial trucking and public transportation.⁷

As an alternative to CNG and LNG, using adsorbents to store natural gas at higher densities at ambient temperature and moderate pressures has been an active area of research since the early 1970s.^{10a} Significantly, adsorbents that operate at relatively low pressures should allow the use of inexpensive on-board fuel tanks and single-stage compressors. Lower storage pressures also facilitate at-home refueling,⁷ which would reduce the large investment needed to build a new refueling infrastructure since natural gas distribution networks are already connected to many homes throughout the world.⁶ Additionally, adsorbed natural gas (ANG) systems would permit the use of lightweight, conformable fuel tanks that can be more optimally integrated into the limited space available within a small car.¹¹ Note that in addition to natural gas powered cars, which are the focus of this work, ANG systems have also been evaluated for use in mobile natural gas tankers and for large-scale, stationary storage on natural gas distribution pipelines.¹² Although it is important to evaluate and optimize a similar set of adsorbent properties for each of these applications, the relevant storage conditions can differ significantly.

While early efforts in ANG storage focused primarily on zeolites, their relatively low surface areas of less than $1000 \text{ m}^2 \text{ g}^{-1}$ resulted in insufficient CH_4 capacities.^{7,10} With considerably higher surface areas, activated carbons have been the most studied class of materials for ANG over the last several decades.¹³ A large portion of research has involved investigating the effects of surface area, pore size, and pore shape on the CH_4 adsorption properties of different carbons. Indeed, it was demonstrated that slit-shaped pores with a diameter of 7.6 \AA , which can accommodate two layers of CH_4 , are ideal for maximizing the volumetric density of CH_4 stored at 35 bar and 25°C .^{14,15} Note that 35 bar has been widely used as a standard pressure for evaluating adsorbents for ANG storage, as this has represented the maximum pressure achievable by most inexpensive single-stage compressors.¹⁶ Additionally, strategies for compacting and shaping activated carbons to optimize packing inside a storage tank have been explored in depth,¹ and prototype activated carbon ANG systems have been demonstrated and tested.¹⁷

In 2012, the US Department of Energy set new CH_4 storage targets for adsorbents at $350 \text{ cm}_{\text{STP}}^3 \text{ cm}_{\text{adsorbent}}^{-3} (\text{v/v})^{18}$ and $0.5 \text{ g}_{\text{CH}_4} \text{ g}_{\text{adsorbent}}^{-1} (699 \text{ cm}_{\text{STP}}^3 \text{ g}^{-1})^{19}$. Assuming a 25% loss in volumetric capacity due to packing an adsorbent inside a fuel tank, the target of 350 v/v is required for an ANG system to have a volumetric energy density of 263 v/v, equivalent to that of CNG at 250 bar and 25°C . The highest reported volumetric CH_4 capacities for activated carbons are in the range of 100–170 v/v,²⁰ well below the energy density of CNG, and computational

studies have predicted a theoretical maximum volumetric capacity for carbons of 198 v/v at 34 bar and 25°C .¹⁴ Accordingly, a next generation of adsorbents is required to meet these storage targets without moving to higher adsorption pressures or lower temperatures, both of which would add significant complexity and cost to an ANG vehicle.

Owing to their high porosity and tunable pore surfaces, metal-organic frameworks have received significant attention as a new class of adsorbents.²¹ While early research on these materials for gas storage applications was mostly related to H_2 ,²² a growing number of frameworks have been evaluated for CH_4 storage.^{23,24} Significantly, several metal-organic frameworks have reported CH_4 capacities comparable to or exceeding those of the best activated carbons; however, inconsistencies in reporting adsorption results and a lack of comparative studies have made it challenging to compare the performance of different materials. Here, we discuss the most important material properties for evaluating both new and existing metal-organic frameworks for natural gas storage and briefly review recent work. In this context, six metal-organic frameworks and an activated carbon, with a range of surface chemistries, pore structures, and surface areas representative of the most promising adsorbents for CH_4 storage, are evaluated in detail.

High-pressure adsorption

All evaluations of adsorbents for natural gas storage rely on the measurement of accurate high-pressure adsorption isotherms. However, high-pressure experiments introduce several complexities, both in terms of collecting isotherm data and interpreting the results, that are not as significant at lower pressures. For instance, there is often inconsistent usage of the terms excess, total, and absolute when describing high-pressure adsorption capacities, which can lead to needless uncertainty when comparing the uptakes of different materials.

Excess, total, and absolute adsorption

At a fundamental level, a gas is considered to be adsorbed when attractive forces from a surface result in a greater density of gas molecules than would normally be present at the same temperature, T , and pressure, P . For adsorption on a two-dimensional surface, the strength of the interaction between the gas and surface will decrease with increasing distance until the attractive forces of the surface become negligible and only bulk or free gas molecules are present. At this distance, an imaginary line, known as the Gibbs dividing surface, can be drawn to divide the total free volume into *adsorbed* and *bulk* regions (Fig. 1a).²⁵ The *absolute* amount adsorbed, n_{abs} , is defined simply as the total number of molecules that are in the adsorbed region. Unfortunately, absolute adsorption cannot be directly measured since it is not possible to determine the location of the Gibbs dividing surface or the size of the adsorbed region experimentally.²⁶ As a result, all adsorption measurements give *excess* adsorption, n_{ex} , which is the difference between the absolute adsorption amount and the amount






Fig. 1 (a) For adsorption on a two-dimensional surface (rectangle), the Gibbs dividing surface (red) divides the free volume into two regions where gas molecules are either in an adsorbed (green) or bulk (blue) state.²⁵ *Absolute* adsorption, which includes all gas molecules in the adsorbed state, is the sum of the experimentally measured excess adsorption and the bulk gas molecules that would have been present in the adsorbed region in the absence of a surface. (b) For porous materials, the *total* adsorption includes all gas molecules inside the total pore volume, which corresponds to the sum of the excess adsorption and the bulk gas that would have been present in the pore volume in the absence of adsorption.²⁸ Note that for microporous materials, the *total* adsorption is often used as an approximation for *absolute* adsorption,²⁹ since it is not possible to determine the location of the Gibbs dividing surface experimentally.²⁶

of bulk gas that would have been present in the adsorbed region, V_a , in the absence of a surface (eqn (1)).²⁶

$$n_{\text{ex}} = n_{\text{abs}} - V_a \rho_{\text{bulk}}(P, T) \quad (1)$$

Since it is not possible to determine V_a experimentally, there is no straightforward method for calculating absolute adsorption from the measured excess adsorption. Instead, the *total* adsorption,^{27,28} n_{tot} , which includes all gas molecules within the pores of an adsorbent, is often used as an approximation for absolute adsorption (Fig. 1b).^{29,30} Total adsorption can be calculated from the excess adsorption using eqn (2) and the experimentally measured total pore volume, V_p . Note that the total pore volume is typically determined from an N_2 adsorption isotherm at 77 K by assuming all pores have been completely filled with condensed N_2 at a sufficiently high P/P_0 , where P_0 is the N_2 saturation pressure.³¹ Based on the Gurvich rule,^{32,33} the total pore volume can be calculated by assuming that the molar volume of liquid N_2 is the same regardless of the size or surface chemistry of the pore it is condensed within. For microporous materials with negligible external surface areas, which have a well-defined plateau in the N_2 adsorption isotherm at 77 K, the exact P/P_0 used is not particularly important. However, a P/P_0 of 0.9–0.95 is typical and will include any pores less than 200–400 Å in the total volume calculation.³⁴ Other adsorbates, such as CH_4 , can be used similarly to determine the total pore volume, but results generally do not vary significantly as long as all pores are equally accessible to the different probe molecules.³⁵ In most cases, small errors in the total pore volume do not have a significant impact on the calculated total adsorption.³⁶

$$n_{\text{tot}} = n_{\text{ex}} + V_p \rho_{\text{bulk}}(P, T) \quad (2)$$

For gas storage applications, the *total* adsorption is most relevant for comparing the capacities of different adsorbents, as it is an intrinsic property of a material that represents the total amount of gas that can be stored inside a material's pores.²⁸ Since the density of gas in the bulk phase, ρ_{bulk} , is significant at high pressures, there is usually a large difference between the excess and total amount adsorbed at conditions relevant to natural gas storage. As a result, inconsistent usage of the terms *excess*, *absolute*, and *total* makes comparing CH_4 capacities of different materials challenging, and it is always important to specify clearly the type of adsorption capacity that is being reported.

High-pressure adsorption measurements

Due primarily to the large pressure range that is covered and the increasing nonideal behavior of gases above ambient pressure, adsorption experiments are inherently more difficult to perform accurately at high pressures than at low pressures. This can lead to large errors that make it challenging to compare the properties of different materials. Most commercial high-pressure adsorption instruments operate using either a gravimetric or volumetric measurement technique. At a basic level, gravimetric instruments measure the amount of CH_4 adsorbed by using a balance to record the change in weight of a sample at different equilibrium pressures of CH_4 , while volumetric instruments record the change in pressure when dosing CH_4 from a calibrated volume to a volume containing the sample. In both cases, it is important to be aware of the most common issues that can affect the quality of the experimental data.



For both gravimetric and volumetric adsorption measurements, He is used to determine the precise volume occupied by the adsorbent inside the sample holder, which is needed for buoyancy corrections and free space calculations in gravimetric and volumetric experiments, respectively. Techniques for performing these corrections have been discussed in detail elsewhere,^{28,37} but it is worth emphasizing that errors in buoyancy and free space calculations can significantly affect the accuracy of adsorption data (Fig. S17†). Note that for both corrections, He adsorption by the sample is assumed to be negligible, and as such, it is best to perform He measurements at the low pressures and high temperatures where this is most likely to be true.^{26,38}

Regardless of the exact method used to perform buoyancy or freespace corrections, there will always be many other potential sources of error in high-pressure experiments, such as volume calibrations, thermocouple readings, pressure transducer readings, sample mass measurements, nonideality corrections and temperature gradients.^{37c} Therefore, it is essential to measure background CH₄ adsorption isotherms with empty sample holders, or with a nonadsorbing material similar in volume to a typical sample, at all potential analysis temperatures and pressures.²⁸ Ensuring that background adsorption is negligible under the exact same conditions as in an actual experiment confirms that all calibrations, corrections, measurements, and calculations are valid, which is critical for verifying the accuracy of the resulting adsorption data. Note that this is equally important for volumetric, gravimetric, commercial, and custom-built high-pressure instruments.

Additionally, for gravimetric adsorption measurements, it is particularly important to ensure that no impurities are present in the CH₄ used, as even small quantities of more strongly adsorbing impurities, such as heavier hydrocarbons or water, can lead to large errors in the measured uptake. Similarly, large errors in volumetric measurements can often result from the fact that high-pressure sample holders, which are typically constructed from stainless steel, are very heavy compared to a typical sample. As a result, it is usually not practical to weigh an activated adsorbent in a fully assembled sample holder, as is common for low-pressure experiments. Thus, it can be difficult to obtain an accurate sample mass, which can lead to significant errors in measured capacities that have a 1 : 1 dependence on the amount of sample present. One potential solution is to measure the surface area of a sample directly prior to a high-pressure measurement in a fully assembled high-pressure sample holder. By confirming that the surface area is as expected, uncertainties associated with sample mass can be mostly eliminated.

Evaluating metal–organic frameworks

Although high-pressure CH₄ adsorption isotherms have been measured for almost one hundred metal–organic frameworks, their CH₄ uptakes have been reported in a variety of different units and at a range of pressures and temperatures, which makes evaluating the relative performance of a particular compound difficult. To facilitate comparisons between existing materials for which ambient temperature, high-pressure CH₄

adsorption isotherms have been published, Table 2 lists the total CH₄ uptake of all metal–organic frameworks at conditions as close to 35 bar and 25 °C as possible. To make comparisons between materials more meaningful, all isotherm data that was originally reported in terms of excess adsorption has been converted to total adsorption using each framework's measured pore volume and the bulk gas density from the NIST Refprop database at the appropriate temperature and pressure (eqn (2)).⁸ Note, however, that in a number of instances there was no indication of whether reported data were given in terms of excess, total, or absolute adsorption, adding significant uncertainty to comparisons of these uptakes to those of other materials.

In almost all standard adsorption measurements, the amount adsorbed is determined per unit mass, not volume, of adsorbent. However, the amount of CH₄ adsorbed per volume, which ultimately determines the amount of natural gas that can be stored in a given fuel tank, has to be calculated using the density of a material. For metal–organic frameworks, the ideal crystallographic density has commonly been used to convert gravimetric adsorption capacities to a volumetric capacity that represents the maximum possible volumetric uptake in the absence of any loss in density from packing actual particles together inside a fuel tank. This method of calculating volumetric capacities certainly over-estimates what is realistically achievable, but it is still useful for initial comparisons between adsorbents, provided the crystallographic densities used are appropriate. Here, a substantial effort was made to ensure that all crystallographic densities were as representative as possible of the framework during CH₄ adsorption, which mainly involved confirming that both metal-bound and free solvent molecules from solvated crystal structures were not included in density calculations. Based upon these and other observations made while surveying published CH₄ adsorption data for metal–organic frameworks, we make the following recommendations for future evaluations of new frameworks for ANG storage:

(1) Report background high-pressure CH₄ adsorption isotherms for an empty sample holder (or sample holder with a nonadsorbing solid) at all measured temperatures and pressures as supplementary information.^{28,39}

(2) Specify whether all isotherms are reported in terms of excess, total, or absolute adsorption. Methods used to convert experimental excess adsorption data to total or absolute adsorption should be detailed, including any assumptions made about the size of the adsorbed volume.²⁸ If a pore volume was used to calculate total adsorption, it should be reported along with the isotherm used to calculate it.

(3) When volumetric uptakes are reported, the density used should be given and the type of density (e.g. crystallographic, bulk, tap, pellet) specified.⁴⁰ When crystallographic densities are used, details of their calculation should be provided, including at a minimum: unit cell volume, unit cell content, and any potential differences between the state of the framework when the unit cell was determined and when adsorption isotherms were measured, which may involve desolvation, removal of excess ligand, framework flexibility, and/or different measurement temperatures.



(4) If the unit $\text{cm}^3 \text{STP}$ is used to report adsorption data, the standard temperature and pressure should be defined.

(5) When isosteric heats of adsorption are reported, the method used to calculate them should be specified. Note that stating that the Clausius–Clapeyron relation was used is not sufficient, as this does not give any indication about how interpolations between measured data points were made.

(6) When mathematical models are used to fit experimental adsorption isotherms, all fitted parameters should be given, and the quality of the isotherm fits should be illustrated.

CH₄ adsorption isotherms

In examining Table 2, there are many cases, particularly for the highest capacity frameworks, where CH₄ adsorption isotherms have been reported for the same material in multiple publications with inconsistent results. This makes it challenging to compare different frameworks and to understand the effects of different characteristics of the materials on CH₄ uptake. For example, HKUST-1 has been reported to have total CH₄ uptakes at 35 bar ranging between 184 and 220 v/v. By synthesizing and activating a selection of the most promising compounds in the same laboratory and measuring high-pressure isotherms on the same instrument, evaluating and comparing their CH₄ adsorption properties becomes more straightforward. To this end, the six metal–organic frameworks depicted in Fig. 2, along with an activated carbon for comparison, were chosen for a detailed evaluation. The seven materials have features that are common to many of the adsorbents that have shown the highest gravimetric and volumetric CH₄ uptakes at 35 bar, including strong adsorption sites, pores shaped by Cu₂-paddlewheel units, and high surface areas.

With modest gravimetric surface areas of 1500–2000 $\text{m}^2 \text{ g}^{-1}$, the M₂(dobdc) (M = Ni, Co, Mg; dobdc⁴⁻ = 2,5-dioxido-1,4-

benzenedicarboxylate; M-MOF-74, CPO-27-M) compounds have one-dimensional hexagonal channels featuring square pyramidal metal cations that have been shown to act as strong adsorption sites for many small gas molecules.^{41,42} The compounds Cu₃(btc)₂ (btc³⁻ = 1,3,5-benzenetricarboxylate; HKUST-1)^{43,44} and Cu₂(adip) (adip⁴⁻ = 5,5'-(9,10-anthracenediyi)di-isophthalate; PCN-14)^{44,45} are built from Cu₂-paddlewheels that also contain exposed metal cations upon desolvation; however, their pore structures are significantly more complicated than M₂(dobdc), with several differently sized pores and pore windows. Significantly, PCN-14 has been widely cited as one of the best existing metal–organic frameworks for CH₄ storage, based upon its reported total volumetric uptake of 230 v/v at 17 °C and 35 bar.^{45a} The compound Zn₄O(bdc)₃ (bdc²⁻ = 1,4-benzene-dicarboxylate; MOF-5, IRMOF-1) has a high Langmuir surface area of 3995 $\text{m}^2 \text{ g}^{-1}$, but does not contain any inherently strong adsorption sites for CH₄.^{21a,24a,46} Indeed, its pore surface is more similar to that of an activated carbon. For comparison, the activated carbon AX-21, which has an exceptionally high Langmuir surface area of 4880 $\text{m}^2 \text{ g}^{-1}$ and is one of many activated carbons that have been studied in detail for ANG storage, was also evaluated.⁴⁷

After synthesis, surface areas and pore volumes were measured for all seven materials to ensure samples were fully activated and of high quality (Fig. S7–S15†). High-pressure CH₄ adsorption isotherms from 0 to 100 bar were then measured for each material at –25, 25, 38, and 50 °C. Experimentally measured excess adsorption isotherms were converted to total adsorption using total pore volumes, as determined from N₂ isotherms at 77 K ($P/P_0 = 0.9$), and the bulk gas density at each temperature and pressure from the NIST Refprop database (eqn (2)).⁸ Volumetric adsorption was calculated using the crystallographic densities of desolvated structures at as near ambient temperature as possible (Table S2†).




Fig. 2 Crystal structures and organic bridging ligands for the six metal–organic frameworks evaluated in this work: M₂(dobdc) (M = Ni, Co, Mg; dobdc⁴⁻ = 2,5-dioxido-1,4-benzenedicarboxylate; M-MOF-74, CPO-27-M), Zn₄O(bdc)₃ (bdc²⁻ = 1,4-benzene-dicarboxylate; MOF-5, IRMOF-1), Cu₃(btc)₂ (btc³⁻ = 1,3,5-benzenetricarboxylate; HKUST-1), and Cu₂(adip) (adip⁴⁻ = 5,5'-(9,10-anthracenediyi)di-isophthalate; PCN-14). Green, gray, and red spheres represent Cu, C, and O atoms, respectively; H atoms have been omitted for clarity. Black spheres represent Ni, Co, or Mg atoms, and blue tetrahedra represent Zn atoms.



Table 2 Crystallographic density, pore volume, surface area and total CH_4 adsorption near 35 bar and ambient temperature for metal-organic frameworks (sorted by decreasing volumetric intake)

Chemical formula ^a	Common name	ρ_{cryst} (g cm ⁻³)	V_p (cm ³ g ⁻¹)	Surface area (m ² g ⁻¹)			Total CH ₄ adsorption ^b		T (°C)	Ref.
				BET	Langmuir	cm ³ STP cm ⁻³	cm ³ STP g ⁻¹	P (bar)		
Ni ₂ (dobdc)	Ni-MOF-74, CPO-27-Ni	1.195	0.56	1593	230	193	35	25	This work	
Zn ₃ (btc) ₂	HKUST-1	0.881	0.47 0.44 0.77	1218 1027 2203	214 206 225	179 172 255	35 35 35	25 25 25	41h 42	
Zn ₂ O ₂ (dobdc)	HKUST-1 tablet (3 × 3 mm) Co-MOF-74, CPO-27-Co	1.173	0.51	1663 1850 1502 1555 0.75 0.67 0.76 0.71 0.72	220 217 2216 198 194 184 94 ^d	250 246 225 221 209 162 ^d	35 35 35 35 35 35	22 30 30 30 30 30	43e 43g 43b 43d 44b 43c	
Zn ₂ (adip)	PCN-14	0.829	0.48 0.83	1056 1984	194 2360	165 202	35 35	25 25	This work	
Mg ₂ (dobdc)	Mg-MOF-74, CPO-27-Mg	0.909	0.87 0.69	1753 1957	2176 1957	235 200	283 220	17 25	42 45a	
Zn ₂ (bdcpp)	NJU-Bai10 NOTT-109	0.668 0.790	0.63 1.11 0.85	1542 1332 2883 2110	188 168 3108 197	207 184 296 250	35 35 35 35	25 25 17 27	41h 42	
Zn ₂ (1,4-nddi)	UTSA-20 NOTT-101	0.893 0.91	0.65 0.63	1794 1156	2015 197	197 ^d 217	221 ^d 35	25 27	80 82	
Zn ₃ (bdb)	PCN-11 NOTT-100, MOF-505	0.684 0.91	1.08 0.749	2805 1931	2442 194	286 259	35 35	27 25	61 61	
Zn ₂ (tpic)	NOTT-103	0.927	0.677	1661	194	209	35	27	83 61	
Zn ₂ (sbtc)	Zn ₂ (bptc)	1.157 0.643	2958 2718	2718 3120	194 194	301 283	35 35	27 25	61 84	
Zn ₂ (2,6-nddi)	Zn ₃ (OH)] ₄ (tbcppm)-H ₂ tbcppm) ₂	0.685	1.14	2273 1770	192 191	265 252	35 35	27 25	85 24h	
Zn ₂ (ebdc)	PCN-16 NOTT-107	0.724 0.756	1.06 0.767	2800 1770	192 191	280 190	35 35	27 25	87 88	
Zn ₂ (C ₂₆ H ₂₀ O ₈)	ZJU-5 Zn-MOF-74 MTU-53 (A) 0.978	0.679 1.231 0.54	1.074 885 1235	2823 885 1607	2823 885 1607	280 153 190	35 35 35	27 25 20	87 42 88	



Table 2 (Contd.)

Chemical formula ^a	Common name	ρ_{cryst} (g cm ⁻³)	V_p (cm ³ g ⁻¹)	Surface area (m ² g ⁻¹)		Total CH ₄ adsorption ^b		T (°C)	Ref.
				BET	Langmuir	cm ³ STP cm ⁻³	cm ³ STP g ⁻¹		
Cu ₃ (tdpat)		0.54	1140	1590	155	159	35	31	89
Cu ₂ (qpic)	NOTT-102	0.56	1140	1590	121	124	35	30	91
Cu ₂ (fddi)	ZJU-25	0.93	1938	2608	182	232	35	25	50
Cu ₃ [(C ₆ H ₅) ₂ C ₆ N ₃ H] ₃ ⁻	NU-125	1.268	3342	181	308	35	27	61	
[C ₆ H ₅) ₃ (COO) ₆] ⁻	IRMOF-6	1.18	2125	3304	180	289	35	27	92
Zn ₄ O(C ₂ H ₄ -bdc) ₃	Mn-MOF-74	1.29	3120	179	310	35	25	93	
Mn ₂ (dbbdc)									
Zn ₂ (bdc) ₂ (dabco)									
Cu ₃ (OH-stpdc)	SDU-6	0.65	0.92	2630	177	272	36.5	25	94
Cu ₃ (btei)	PCN-61	1.084	0.5	1102	176	163	35	25	42
Cu ₂ (bdi)	PCN-46	0.622	0.75	1448	2104	164	35	30	43b
Zn ₄ O(bdc) ₃	IRMOF-1, MOF-5	0.587	0.68	1450	159	194	35	23	95
Cu ₃ (OH-stpdc)	SDU-6	0.611	1.17	2826	172	281	35	25	96
Cu ₃ (btei)	PCN-61	0.56	1.36	3000	171	306	35	25	97
Cu ₂ (bdi)	PCN-46	0.619	1.012	2500	171	277	35	25	98
Zn ₄ O(NH ₂ -bdc) ₃	IRMOF-1, MOF-5	0.621	1.4 ^c	3995	168	271	36.5	25	23a
			1.4	3995	150	241	35	25	This work
Zr ₆ O ₄ (OH) ₄ (NH ₂ -bdc) ₆	UiO-66-NH ₂	1.2	1.55	3800	4400	143	230	36	27
Cr(OH)(bdc)	MIL-53 (Cr)	1.36	0.4	1080	138	223	35	25	46d
Co ₂ (bdc) ₂ (dabco)		1.04	0.5	1500	167	123	35	30	43g
Cu ₃ (Me-stpdc)	SDU-7	0.815	0.82	1600	165	159	35	31	89
Cu ₃ (tipb)	UTSA-34	0.805	1.1	2713	1600	197	35	30	99
Cu ₂ (dceni)	UTSA-40	0.84	0.542	991	159	263	35	25	96
Cu ₂ (ndc) ₂ (dabco)	DUT-8 (Cu)	0.827	0.65	1630	1661	152	35	17	100
Cu ₂ (bttcd)	PCN-80	0.681	1.04	2535	148	184	35	27	101
Zn ₂ (bttcd)	SNU-77	0.575	1.47	3850	4150	217	35	25	102
Zn ₄ O(tcbpda) ₂	SDU-8	0.586	1.52	3670	4180	147	250	35	103
Cu ₃ (btei)	UiO-66	0.613	1.02	2516	146	146	238	35	105
Zr ₆ O ₄ (OH) ₄ (bdc) ₆	IRMOF-3	1.32	0.36	970	110	146	30	35	43g
Zn ₄ O(NH ₂ -bdc) ₃		0.63	1.07	144	144	228	36.5	25	23a
Ti ₈ O ₈ (OH) ₄ (bdc) ₆	ML-125	0.81	0.67	1820	141	174	35	30	43g
Yb ₃ O[(C ₆ H ₅) ₄ (C ₆ H ₄) ₆](COO) ₆ [NO ₃] ⁻	UTSA-62	0.59	0.91	2190	139	236	35	25	107
Cu ₃ (tcepbb)	NU-111	0.409	2.09	4930	136	333	35	25	49
Cu ₃ (ntei)	PCN-66	0.44	1.63	4000	134	304	35	25	108
Co ₂ (bipy) ₃ (bttb) ₄	DUT-23 (Co)	0.401	2.03	4850	133	331	35	25	109
Zn(MeIM) ₂	ZIF-8	1.141	0.49	1445	115	115	36	27	39
			0.59	1445	124	109	35	30	110
Zn ₄ O(ceb) ₃	SNU-71	0.835	0.709	1770	1923	130	155	35	111
Ni(ndc)(ted) _{0.5}	PCN-68	0.789	0.84	2307	2647	128 ^d	35	25	81
Cu ₃ (ptei)		0.38	2.13	5109	6033	126	332	35	25



Table 2 (Contd.)

Chemical formula ^a	Common name	ρ_{cryst} (g cm ⁻³)	V_p (cm ³ g ⁻¹)	Surface area (m ² g ⁻¹)		Total CH ₄ adsorption ^b		T (°C)	Ref.
				BET	Langmuir	cm ³ STP cm ⁻³	cm ³ STP g ⁻¹		
Zn ₄ O(btbt) ₂	MOF-177	0.427	1.89	4500	5340	126	293	35	25
Cu(SiF ₆)(4,4'-bpy) ₂		0.86	1.55		1337	106	249	35	25
Zn ₃ O(2,7-ndc) ₂		1.04	0.56	1337	125	146	36.5	25	112
Cu(GeF ₆)(4,4'-bpy) ₂		0.925	0.458	901	1281	124	144	35	113
Cu ₂ (bdcppi)		0.65	1.08	2300	2450	123	120	35	114
Al(OH)(ndc)	DUT-4	0.773	0.68	1308	1906	122	158	35	115
Zn ₄ O(ndc) ₃	UTSA-38	0.962	0.61	1090	1690	120 ^d	124 ^d	35	113
Cr ₃ O(btco) ₂ F	MIL-100 (Cr)	0.7	1.1	1900	1900	120	171	35	116
Zn ₄ O(btbt) _{4/3} (ndc)	MOF-205	0.38	2.16	4460	6170	119	314	35	116
Zn ₄ O(ndc) ₃	IRMOF-8	0.448	1.827	4326	4326	114	254	35	117
Zn ₄ O(btbt) _{4/3} (ndc)	DUT-6	0.39	2.02	6005	6005	106	271	35	118
Fe ₃ O ₄ (bdc) ₂ F	MIL-100 (Fe)	0.7	0.99	2410	2410	117	167	35	119
Al(OH)(bpdc)	DUT-5	0.634	0.81	1613	2335	113	179	35	120
Cu ₂ (bbcdc)	DUT-49	0.311	2.91	5476	5476	113	363	35	121
Zn ₄ O(cvb) ₃	SNU-70	0.408	2.17	5290	6100	111	273	35	121
Zn ₆ (btbt) ₄ (4,4'-bpy) ₃	FJ-1	0.405	1.43	4043	4624	111	273	35	123
Zn ₄ (Im) _{1.5} (cbIM) _{0.5}	ZIF-76	0.869	0.57	1340	1340	110	126	35	124
NOTT-119		0.361	2.35	4118	4118	106	294	35	125
Cu ₃ (C ₆ H ₃ O ₁₂) ₂		1.21	0.35	346	346	104	86	35	126
Cd(bpypdb)	DUT-9	0.358	2.18	6120	6120	101	283	35	127
Ni ₅ O ₂ (btb) ₂		0.44	2.15	4230	4230	101	230	35	119
Cr ₃ O(btco) ₃ F	MIL-101 (Cr)		1.57	3870	3870	87	197	35	117
			1.38	2674	2674	82	186	35	48
			1.38	1.303	1.303	79	178	35	122
			1.38	2693	4492	96	250	35	123
Zn ₄ O(BenzTB) _{3/2}	DUT-13	0.385	1.98	5570	5570	83	331	35	124
Zn ₄ O(btbe) _{4/3} (bpdc)	MOF-210	0.25	3.6	6240	10 400	83	331	35	125
Co ₂ (4,4'-bpy) ₃ (NO ₃) ₄		1.36			73	73	54	35	23
Zn ₄ O(bbbc) ₂	MOF-200	0.22	3.59	4530	10 400	67	304	35	46d
Cd ₂ (azpy) ₃ (NO ₃) ₄		1.54			66	66	43	36.5	129
Co ₂ (ndc) ₂ (dabco)	DUT-8 (Co)	0.67	0.62	1400	1400	52	78	35	102
Zn ₂ (ndc) ₂ (dabco)	DUT-8 (Zn)	0.68	0.3	710	710	40	59	35	102
Cu ₂ (PF ₆) ₂ (NO ₃) ₄ (4,4'-bpy) ₄		1.057		559	559	33	31	36.5	113
1,4PF ₆ ·0.6NO ₃								25	113
Zn ₂ (tcpbda)	SNU-30	0.381	0.28	704	770	27	71	35	130
Co(azpy) ₂ (NCS) ₂		1.31			19	15	35.5	25	129
Co ₂ (azpy) ₃ (NO ₃) ₄		1.32			17	13	36.5	25	129
Zn ₂ (tcpbda)(bpta)	SNU-31	0.459	0.14		308	17	37	35	130
Cu(C ₁₀ H ₆ O ₃)(ted) _{0.5}		1.08			3129			25	131
Cu(bpdc)(ted) _{0.5}		1.27			3265		214 ^f	35	131b
Cu(bdc)(ted) _{0.5}		0.71			1891		185 ^f	35	132
VO(btco)	ML-47 (V)	0.5			1030		137 ^f	35	132
Cu(C ₄ H ₂ O ₄)(ted) _{0.5}		0.24			606		103 ^f	35	131b

Table 2 (Contd.)




Fig. 3 Total gravimetric (top) and volumetric (bottom) CH_4 adsorption isotherms at 25 °C. Note that crystallographic densities were used to calculate volumetric adsorption. The solid line corresponds to the volumetric density of pure CH_4 at 25 °C.

In Fig. 3, the 25 °C high-pressure CH_4 isotherms of all materials measured in this work are compared in terms of total gravimetric and volumetric adsorption. Of the materials

measured, AX-21 has the highest gravimetric uptake at all pressures. For the metal–organic frameworks, HKUST-1 has the highest gravimetric uptake ($255 \text{ cm}^3_{\text{STP}} \text{ g}^{-1} = 0.183 \text{ g}_{\text{CH}_4} \text{ g}^{-1}$) at 35 bar, but the capacity of MOF-5 is highest at pressures greater than 40 bar. At high pressures, the gravimetric capacity is reasonably well correlated with the gravimetric surface area (Fig. S38†), which is consistent with previous observations for both metal–organic frameworks and activated carbons.^{7,13,24f,h,61} Indeed, the metal–organic frameworks in Table 2 with the three highest reported gravimetric uptakes at 25 °C and 35 bar all have exceptionally high specific surface areas: DUT-49 with an uptake of $0.26 \text{ g}_{\text{CH}_4} \text{ g}^{-1}$ and a surface area of $5476 \text{ m}^2 \text{ g}^{-1}$, NU-111 with an uptake of $0.24 \text{ g}_{\text{CH}_4} \text{ g}^{-1}$ and a surface area of $4930 \text{ m}^2 \text{ g}^{-1}$, and PCN-68 with an uptake of $0.24 \text{ g}_{\text{CH}_4} \text{ g}^{-1}$ and a surface area of $5109 \text{ m}^2 \text{ g}^{-1}$.^{48,50}

In addition to the different CH_4 capacities of the frameworks studied here, there are important differences in the shapes of their adsorption isotherms. Specifically, AX-21 and MOF-5 have shallower isotherms at low pressures and do not begin to approach saturation until much higher pressures than $\text{M}_2(\text{dobdc})$, HKUST-1, and PCN-14. This is expected based on the lack of strong adsorption sites in AX-21 and MOF-5, and has important consequences for the amount of CH_4 that can actually be delivered by each material.

Importantly, as will be discussed in detail below, achieving a high volumetric adsorption capacity is much more critical than a high gravimetric capacity for extending the driving range of a vehicle. While the overall shapes of the volumetric isotherms are similar to the gravimetric ones, the trends in capacity differ significantly. For instance, $\text{Ni}_2(\text{dobdc})$ and $\text{Co}_2(\text{dobdc})$ have the highest uptakes at lower pressures, and $\text{Ni}_2(\text{dobdc})$ and HKUST-1 have the highest total volumetric uptakes at 35 bar: 230 and 225 v/v, respectively. Note that the total volumetric uptake of $\text{Ni}_2(\text{dobdc})$ is the highest value yet reported for any metal–organic framework at 25 °C and 35 bar. Although PCN-14 has been widely cited as the best existing metal–organic framework




Fig. 4 (a) Crystal structure of HKUST-1 highlighting the three different types of pores in the structure that have diameters of roughly 5 Å (dark yellow), 11 Å (orange), and 13.5 Å (blue). Note that the open coordination site of the exposed Cu^{2+} cations is only directed into the 13.5 Å (blue) pores. Atomic coordinates are taken from a desolvated crystal structure at 100 K.⁵¹ (b) Location of adsorbed CD_4 molecules at the four windows sites of an octahedral cage. The atomic coordinates are taken from a powder neutron diffraction structure with a loading of 1.1 CD_4 per Cu^{2+} at 4 K.^{44c} Green, gray, red, and light blue spheres represent Cu, C, O, and D atoms, respectively; H atoms have been omitted for clarity.



for volumetric CH_4 storage, $\text{Ni}_2(\text{dobdc})$ and HKUST-1 have significantly higher volumetric capacities at 35 bar and 25 °C.

It is worth noting that in contrast to gravimetric adsorption, the volumetric uptake at 35, 65, or 100 bar, does not correlate with volumetric surface area (Fig. S39†). Indeed, MOF-5 has a volumetric surface area 30% greater than $\text{Ni}_2(\text{dobdc})$, but a volumetric uptake that is lower at all pressures measured here of less than 100 bar. This highlights the importance of the density and strength of specific CH_4 adsorption sites, rather than just surface area and pore volume, for achieving high volumetric capacities.

Methane adsorption sites in $\text{Ni}_2(\text{dobdc})$ and HKUST-1

While $\text{Ni}_2(\text{dobdc})$ and HKUST-1 have the highest volumetric uptakes of all metal–organic frameworks reported to date (Table 2), they are still well short of the 350 v/v target that is expected to achieve a volumetric energy density similar to that of CNG. In designing a next generation of improved framework materials to meet this target, it is useful to consider the fundamental mechanisms responsible for the high volumetric uptakes of $\text{Ni}_2(\text{dobdc})$ and HKUST-1. Detailed powder X-ray and neutron diffraction experiments have previously been used in several studies to identify the strongest CH_4 adsorption sites in both structures.^{42,44} Note that the only structural study of CH_4 in $\text{M}_2(\text{dobdc})$ was for the Mg analogue,⁴² but based on the similar adsorption isotherms and previous structural studies with H_2 and CO_2 ,^{41d–f,i,j,l,m} it is reasonable to expect similar CH_4 binding sites within $\text{Ni}_2(\text{dobdc})$.

In both HKUST-1 and $\text{Ni}_2(\text{dobdc})$, the exposed Cu^{2+} and Ni^{2+} cations act as strong binding sites that can contribute a maximum of 98 v/v and 172 v/v, respectively, to the total volumetric capacity when one CH_4 is bound to each metal. These are the only strong binding sites expected in $\text{Ni}_2(\text{dobdc})$, and just weaker secondary adsorption sites should be available for CH_4 after the Ni^{2+} sites are fully occupied.⁴² In contrast, HKUST-1 has additional strong adsorption sites, located in the four windows of each octahedral cage, which are populated at the same time as the Cu^{2+} sites,⁴⁴ suggesting both adsorption sites have similar CH_4 binding energies (Fig. 4). These window sites bind CH_4 strongly due to several close interactions, in the range 2.7–3.2 Å, between framework O atoms and an adsorbed CH_4 molecule (Fig. S47†).

Significantly, the window sites can contribute an additional 65 v/v to the volumetric capacity of HKUST-1, bringing the total contribution of strong adsorption sites to 163 v/v, just below that of $\text{Ni}_2(\text{dobdc})$ (172 v/v). On the other hand, there is a more pronounced difference in the contribution of strong adsorption sites to the total gravimetric capacity of each material at 144 $\text{cm}^3_{\text{STP}} \text{g}^{-1}$ and 185 $\text{cm}^3_{\text{STP}} \text{g}^{-1}$ for $\text{Ni}_2(\text{dobdc})$ and HKUST-1, respectively. Further, while both materials have similar volumetric surface areas (Table S1†), HKUST-1 has a significantly greater gravimetric surface area that can be expected to lead to a higher gravimetric density of weak CH_4 adsorption sites. Taken together, the similar volumetric and different gravimetric capacities of strong and weak adsorption sites can help explain the experimental CH_4 isotherms, wherein both materials have

similar volumetric uptakes at 35 bar, but HKUST-1 has a much higher gravimetric uptake. In order to explain why $\text{Ni}_2(\text{dobdc})$ has a steeper isotherm at lower pressures, it is necessary to also consider differences in the binding energies of the strong adsorption sites of each material.

Isosteric heats of adsorption

To gain further insight into differences between the seven materials, isosteric heats of adsorption (Q_{st}), which represent the average binding energy of an adsorbing molecule at a specific surface coverage, were determined as a function of the amount of CH_4 adsorbed, n , by using the Clausius–Clapeyron relation (eqn (3)).⁵²

$$-Q_{\text{st}} = RT^2 \left(\frac{\partial \ln P}{\partial T} \right)_n \quad (3)$$

In order to employ this relation, it is first necessary to fit the high-pressure isotherm data with a mathematical model, such that it is possible to interpolate between measured data points to determine the exact pressures that correspond to the same amount adsorbed at different temperatures. Regardless of the mathematical model used, it is important to remember that the Clausius–Clapeyron equation is fundamentally a thermodynamic relation that describes a phase transition of a gas from a bulk to adsorbed state, and as such, it is based on the absolute amount adsorbed, which includes all gas molecules that experience an attractive potential from the adsorbent surface.^{26d} For microporous materials, the total adsorption is often used as an approximation for absolute in heat of adsorption calculations, as most gas molecules inside micropores will have some degree of interaction with the pore surface.^{22a,29} In contrast to low-pressure experiments, there is a significant difference between excess and total adsorption at high pressures, and *it is critical that the total adsorption is used for all thermodynamic calculations*,³⁶ unless the relevant thermodynamic relations have been specifically altered for excess quantities.^{26d}

Virial-type equations have been routinely used to fit high-pressure adsorption data for metal–organic frameworks,⁵³ despite the fact that most virial parameters lack any physical meaning.⁵⁴ In contrast, equations that are based on physical models of adsorption, such as the Dubinin–Astakhov (DA)⁵⁵ and multi-site Langmuir equations,⁵⁶ have been more widely used in analyzing CH_4 isotherms of activated carbons.⁵⁷ One major advantage of fitting isotherm data with physically relevant parameters is that it makes extrapolation to temperatures and pressures that were not experimentally measured more meaningful, which is important not only for calculating heats of adsorption but also for process modeling and systems design. Additionally, errors in high-pressure isotherm data can be significant, especially when compared to low-pressure experiments, and leveraging at least some physical constraints on the fitting parameters can help ensure that the resulting isosteric heats are reasonable. Here, single- and dual-site Langmuir models were used to fit the adsorption data of each material at all measured temperatures with one set of parameters (see ESI† for details). Several recent studies have demonstrated the ability



of Langmuir-type equations to successfully model adsorption in metal–organic frameworks, especially those that have well-defined adsorption sites on the pore surface.^{36,41n–r,58}

The importance of the method used for calculating Q_{st} can be illustrated by examining the heats of adsorption originally reported for PCN-14, wherein the low-coverage binding enthalpy of -30 kJ mol^{-1} is nearly double the value of -18 kJ mol^{-1} determined in this work (Fig. S37†).^{45a} It was suggested that this record high heat of adsorption was largely responsible for the high volumetric uptake of PCN-14, but no details of the Q_{st} calculations were reported. While PCN-14 certainly does exhibit high volumetric uptake, the reported values of Q_{st} , which influenced several follow-up computational studies,^{24h,44c,45b} can hinder efforts to understand the underlying adsorption mechanisms that are responsible and to design improved materials.

For all seven materials evaluated in this work, the isosteric heats of adsorption as a function of the total CH_4 loading are plotted in Fig. 5. As expected based upon its steep isotherm and high volumetric uptake, $\text{Ni}_2(\text{dobdc})$ has the highest Q_{st} at low coverage, followed by $\text{Co}_2(\text{dobdc}) > \text{Mg}_2(\text{dobdc}) > \text{PCN-14} \sim \text{HKUST-1} > \text{AX-21} > \text{MOF-5}$. It is interesting to note differences in the shape of Q_{st} curves as the CH_4 loading is increased. For example, the $\text{M}_2(\text{dobdc})$ compounds have relatively constant binding energies at low loadings that begin to decrease as the exposed metal cation sites become populated. On the other hand, PCN-14 and HKUST-1 have heats of adsorption near -17 kJ mol^{-1} regardless of the amount of CH_4 adsorbed, confirming that the exposed Cu^{2+} cations and window adsorption sites in both materials have similar CH_4 binding strengths. Likewise, MOF-5 exhibits a constant, but much weaker, binding energy of -12.3 kJ mol^{-1} . These differences are consistent with the shapes of the adsorption isotherms, for which the $\text{M}_2(\text{dobdc})$ compounds have the steepest rises at low pressures, while MOF-5 is the most shallow. Note that the gradual decline in the isosteric heat of adsorption of AX-21 from 15.5 to 12.4 kJ mol^{-1} is likely due to the wide distribution of pore sizes present

in the activated carbon, whereby smaller pores will tend to have stronger interactions with CH_4 than larger pores.

It is important to emphasize that while the single- and dual-site Langmuir models used here describe the experimental adsorption data very well over a wide temperature and pressure range, there may be other models that result in equally good, or in some cases perhaps even better, fits to the data. Some of these models may involve an increase in the isosteric heat of adsorption at high CH_4 loadings due to the contribution of $\text{CH}_4 \cdots \text{CH}_4$ interactions at high pressures, as has been reported for several frameworks.⁵⁹ Unfortunately, the experimental high-pressure adsorption data is typically not accurate enough to determine reliably whether such an increase actually exists in any of the materials studied here. However, it is worth noting that several studies have clearly shown that using excess adsorption isotherms to calculate Q_{st} can lead to large increases in Q_{st} at higher loadings that do not occur when using absolute or total adsorption.^{28,36} Moreover, the contribution of $\text{CH}_4 \cdots \text{CH}_4$ interactions to the overall heat of adsorption has been estimated to be less than 2 kJ mol^{-1} , which would be difficult to detect accurately at the high pressures where it would be most influential and the adsorption data is least accurate.⁶⁰ Regardless, the differences in isosteric heats of adsorption at pressures most relevant to ANG storage are clear, and these have important consequences for the amount of CH_4 that can actually be delivered by each material inside a vehicle.

Usable CH_4 capacity

Comparing the 35 bar CH_4 capacities of different adsorbents is useful for initial evaluations, but not all of this capacity will be accessible when delivering natural gas to an engine that requires a minimum inlet pressure to operate. As such, the usable CH_4 capacity is defined as the amount of CH_4 that can be delivered when decreasing from the filling or adsorption pressure to a specific desorption pressure (Fig. 6a).²⁸ For ANG storage, the adsorption pressure is usually assumed to be 35 bar, since this is a typical benchmark for the maximum achievable pressure of inexpensive single-stage compressors.¹⁶ While 5 bar is commonly cited as a minimum desorption pressure,^{49,61} engines that can operate at inlet pressures as low as 3 bar are available and would allow for a greater usable CH_4 capacity and increased vehicle driving range. Currently, most natural gas vehicles contain gasoline engines that have been retrofitted to run on natural gas and require inlet pressures of 5 to 10 bar. If the demand for natural gas vehicles increases dramatically, the minimum operating pressure may decrease as engines are built and optimized specifically to burn natural gas. It is important to note that the amount of CH_4 retained by the adsorbent during desorption can also be reduced by heating, ideally taking advantage of waste heat from the engine.⁶²

The volumetric usable CH_4 capacities of all materials evaluated here are plotted in Fig. 6b for adsorption at 35 bar and 25 °C and desorption at 5 bar and temperatures from 25 to 145 °C. Despite the fact that $\text{Ni}_2(\text{dobdc})$ has a higher total volumetric uptake at 35 bar, HKUST-1 has the highest usable CH_4 capacity for all calculated desorption temperatures. This is




Fig. 5 Isosteric heats of adsorption, $-Q_{st}$, at 25 °C as a function of the total amount of CH_4 adsorbed.






Fig. 6 (a) The usable capacity represents the amount of CH_4 that can be delivered when discharging from a specific adsorption temperature, T_{ads} , and pressure, P_{ads} , to a desorption temperature, T_{des} , and pressure, P_{des} . (b) The volumetric usable CH_4 capacity as a function of desorption temperature for adsorption at 25 °C and 35 bar and desorption at 5 bar.

a direct result of the weaker interaction of CH_4 with HKUST-1 than with $\text{Ni}_2(\text{dobdc})$, which results in significantly less CH_4 retained by HKUST-1 at 5 bar. Indeed, the usable CH_4 capacity of $\text{Ni}_2(\text{dobdc})$ is only 115 v/v for desorption at 25 °C, which is just 50% of its 35 bar capacity. In contrast, the usable capacity of HKUST-1 under the same conditions is 149 v/v, which is 66% of its 35 bar capacity.

The gravimetric usable CH_4 capacity is plotted in Fig. S40† for the same adsorption–desorption conditions. In this case, AX-21 has the highest usable capacity at all desorption temperatures, while MOF-5 is the best metal–organic framework for desorption temperatures below 60 °C. Although HKUST-1 exhibits a higher total gravimetric uptake at 35 bar, its usable capacity is below that of MOF-5 unless the desorption temperature is increased. This is due to the weak interaction of MOF-5 with CH_4 (−12 kJ mol^{-1}), which results in only a small amount of CH_4 adsorbed at 5 bar. Usable capacity plots as a function of desorption pressure are also given in the ESI† and show similar trends between materials, as is expected since decreasing the desorption pressure has a similar effect to increasing the desorption temperature (Fig. S41–S42†).

Adsorption at lower temperatures or higher pressures can also be considered as a strategy for increasing the usable

capacity (Fig. S43–S46†). Indeed, by decreasing the adsorption temperature to −25 °C, the usable capacity of HKUST-1 reaches 222 v/v for desorption at 5 bar and 25 °C, which is 67% greater than for adsorption at 25 °C. However, a full systems-level analysis is necessary to determine whether the higher costs associated with cooling the fuel and the thermal management of the tank, or with compressing natural gas to higher pressures, would be worth the increase in usable capacity and driving range.

Of all the metal–organic frameworks previously evaluated by others and those studied here, HKUST-1 appears to be the most promising current framework for natural gas storage, as it features one of the highest usable volumetric capacities for CH_4 . A similar conclusion was also reached by others while this manuscript was in preparation,⁶³ and it is perhaps not surprising that HKUST-1 was chosen by BASF for use in a prototype ANG van in 2007.⁶⁴

Optimal binding enthalpy

The differences in the usable CH_4 capacities between the materials studied illustrate the importance of both increasing capacity and optimizing binding enthalpy when designing improved adsorbents. If the binding enthalpy is too high, then too much CH_4 will be retained at low pressures, decreasing the usable capacity. On the other hand, if the binding enthalpy is too low, then too little CH_4 will be adsorbed at higher pressures. Using a single-site Langmuir model, it can be shown that the optimal binding enthalpy for CH_4 adsorption at 35 bar and 25 °C and desorption at 5 bar is −17 kJ mol^{-1} ,⁶⁵ exactly equal to that determined for HKUST-1 over the entire pressure range of 5 to 35 bar.

Note that the optimal binding enthalpy is dependant on the exact desorption conditions used. Indeed, Fig. 7 shows the percentage of the saturation capacity that is usable at different binding energies and desorption temperatures. As the desorption




Fig. 7 Assuming a single-site Langmuir isotherm, the percentage of the saturation capacity that is usable is plotted for isosteric heats of adsorption, Q_{st} , ranging from −10 to −25 kJ mol^{-1} and desorption temperatures from 25 to 145 °C, with adsorption at 35 bar, desorption at 5 bar, and a molar entropy of adsorption of −9.5 R. As the desorption temperature increases, the optimal Q_{st} and usable capacity also increase.⁶⁵

temperature is increased, or desorption pressure decreased, the optimal binding enthalpy increases (see ESI† for details). Note that the simple analysis presented here ignores correlations between the adsorption enthalpy and entropy, but these correlations would be expected to lead to even larger increases in the optimal Q_{st} as the desorption temperature is increased.⁶⁶ Regardless, Fig. 7 illustrates the importance of optimizing binding enthalpy and the benefits of using higher desorption temperatures to maximize usable capacity. Nevertheless, employing a material with optimal binding enthalpy is useless if the density of adsorption sites having that enthalpy is small, resulting in a low optimized capacity. Since dramatic improvements in both gravimetric and volumetric capacities are needed to meet the Department of Energy targets at 35 bar and ambient temperature, increasing capacity must be the primary focus of materials development efforts, but these efforts will be most beneficial if the binding enthalpy is near optimal.

Relative importance of gravimetric and volumetric capacity

It is important to recognize that the acceptability and viability of natural gas vehicles are directly linked to their utility and value to the customer. As indicated, the lower volumetric energy density of compressed natural gas significantly reduces the driving range in comparison to conventional gasoline vehicles and therefore reduces the utility of the vehicle. In designing a next generation of adsorbents for natural gas storage, it is essential to consider the relative importance of improvements in gravimetric *versus* volumetric usable capacity toward increasing the maximum achievable driving range of an ANG vehicle.

In order to make the comparison more informative, the effects of changes in gravimetric and volumetric usable capacity on driving range are considered independently using a few simple assumptions (Fig. 8). In the gravimetric case, a 10 GGE (gallons gasoline equivalent) vehicle is assumed to have an adsorbent

capable of delivering $0.12 \text{ g}_{\text{CH}_4} \text{ g}^{-1}$, which is equal to the usable capacity of HKUST-1 for 35 bar adsorption and 5 bar desorption at 25°C . In order to isolate the effects of changing the usable gravimetric capacity, this analysis assumes a fixed volumetric capacity and changes in gravimetric capacity thus lead to an increase or decrease in the weight of adsorbent required to achieve a 10 GGE energy density (2.567 kg CH_4).⁶⁷ As a general rule, the fuel economy on conventional light-duty vehicles can be improved or reduced by up to 2% per 100 lbs (45 kg) of weight subtracted or added.⁶⁸ Since the total amount of natural gas is fixed, changes in the fuel economy are directly proportional to changes in the driving range for this scenario. For example, a 10% improvement in the usable gravimetric capacity of HKUST-1 results in a 19 kg reduction in weight and a 0.8% improvement in fuel economy and driving range.

To isolate the effects of changing usable volumetric capacity, it is assumed that a light-duty vehicle will have a fixed amount of space available for a fuel tank. As a result, there is a roughly 1 : 1 correlation between the usable volumetric capacity of an adsorbent and the expected driving range of a vehicle.

As shown in Fig. 8, improvements in gravimetric capacity have considerably less impact than improvements in volumetric capacity. While increases in gravimetric capacity are still important, similar improvement percentages do not have as significant an impact as volumetric on increasing driving range since the increased weight of the adsorbent material has a minor effect on the fuel economy of the vehicle. Therefore, increasing the usable volumetric CH_4 capacity is significantly more important than increasing the usable gravimetric capacity for natural gas storage in light-duty vehicles.

These relationships, along with knowledge of the importance of certain vehicle attributes to consumers, such as driving range and cost, are critical for directing adsorbent material improvements and tradeoffs toward the optimal solution for a viable ANG system.

Adsorbed natural gas system requirements

While working to synthesize a next generation of metal–organic frameworks with improved volumetric and gravimetric capacities, it is also important to consider the complete ANG storage system, as there are several factors that can dramatically affect the ultimate performance of a material when delivering natural gas to an engine. It is worth noting that many of these systems-level issues are not just engineering problems and are fundamentally related to materials properties that can potentially be tuned through synthetic chemistry to improve performance.

Thermal properties

In an actual ANG system, the heats of adsorption (exothermic) and desorption (endothermic) will likely lead to large temperature changes that both have a negative impact on the usable CH_4 capacity.⁶⁹ Specifically, an adsorbent bed will release heat during refueling and cool during discharge, resulting in less CH_4 stored during adsorption and more retained during desorption. Faster




Fig. 8 Effects of changes in gravimetric and volumetric CH_4 usable capacity on vehicle driving range. To isolate each effect, the gravimetric case assumes a 10 GGE vehicle with a constant volumetric capacity, while the volumetric case assumes a fixed amount of space available for a fuel tank and a constant gravimetric capacity.

refueling and discharge rates, which are often desirable, lead to even greater temperature changes. Indeed, a prototype activated carbon storage tank cooled by as much as 37 °C at a discharge rate typical for a normal driving speed, resulting in a 20% loss in CH₄ capacity compared to isothermal desorption.⁶⁹ Various thermal management strategies have been proposed to minimize the impacts of heat flowing in and out of the adsorbent bed, including incorporating a heat exchanger inside the storage tank, changing how natural gas flows inside the tank, and altering the material and geometry of the tank.^{13,69,70} While some form of thermal management will ultimately be necessary, all of these engineering solutions involve a significant tradeoff between cost, weight, and available space.

More importantly, all efforts to manage heat flow are highly dependent on the heat capacity and thermal conductivity of the adsorbent. High heat capacities decrease the magnitude of temperature changes resulting from the energy released or consumed during adsorption and desorption, while high thermal conductivities allow heat to dissipate more quickly and permit the use of simpler external or internal temperature control systems. With this in mind, it is worth noting that overcoming thermal management challenges is not just an engineering problem, and there can be a significant contribution from a more fundamental materials synthesis perspective.

While heat capacities have been reported for several metal-organic frameworks,^{41a,71} to the best of our knowledge, there have been just two thermal conductivity measurements, both of which were for MOF-5.⁷² As is typical of many porous materials, the MOF-5 thermal conductivities were very low at less than 0.32 W m⁻¹ K⁻¹ for both a single crystal and packed powder. It is possible to improve the thermal conductivity by incorporating an additive such as graphite, but this will lead to a decrease in both the gravimetric and volumetric CH₄ capacities.^{72b} To better understand these tradeoffs, there is a clear need for thermal conductivity and heat capacity measurements on a much wider range of metal-organic frameworks, especially with experiments designed to identify structural and chemical features that are likely to lead to frameworks with higher intrinsic thermal conductivities and heat capacities.

Mechanical properties

As has been emphasized, the volumetric CH₄ capacity of an adsorbent has a critical impact on the ultimate driving range of an ANG vehicle. Notably, almost all reported volumetric uptakes for metal-organic frameworks, including those in this study, are calculated using the density of a perfect single crystal and represent the maximum possible volumetric capacity. In reality, metal-organic frameworks synthesized on a large enough scale to fill a fuel tank will likely be powders that contain a significant amount of empty space between particles. This interparticle void space results in a much lower density, and consequently a lower volumetric CH₄ capacity, for a bulk powder than that calculated for a single crystal. Indeed, the bulk powder density of MOF-5 was measured at just 0.13 g cm⁻³, 79% less than the single crystal density of 0.621 g cm⁻³.^{73d} Note that in addition to decreasing volumetric capacity, low packing densities also lead to lower thermal conductivities.

In order to minimize the losses in capacity and thermal conductivity that result from packing adsorbent particles inside a tank, it will be essential to compact the material in some fashion. Compaction reduces the interparticle void space and increases the bulk density of the powder, but it can also cause partial or complete collapse of framework pores. As a result, materials with higher mechanical stability are desirable, as they are more likely to survive compaction to higher densities without significant losses in porosity. While there have been initial studies on the intrinsic mechanical properties of different metal-organic frameworks, the majority of work has been limited to frameworks that can be synthesized as large single crystals.⁷⁴

Additional research efforts have examined changes in surface area, pore volume, and gas uptake when compacting different metal-organic framework powders, including MOF-5, HKUST-1, and Ni₂(dobdc), at increasing mechanical pressures.^{43c,73} For instance, tablets of HKUST-1 compacted to 66% of its crystallographic density adsorbed just 94 v/v of CH₄ at 35 bar and 30 °C,^{43c} highlighting the importance of packing losses on the actual volumetric capacity of an adsorbent. Similarly, a pellet of Ni₂(dobdc) compacted with 0.1 GPa of pressure adsorbed just 100 v/v of CH₄ at 34 bar and 30 °C,^{73c} significantly less than the 230 v/v measured here. These types of compaction studies are certainly useful, but it is difficult to compare the intrinsic mechanical properties of each material based on such measurements, since compaction is affected by particle size and shape in addition to mechanical stability. More importantly, comparisons of the volumetric usable capacity of different materials will be highly dependent on the mechanical stability of the framework and the maximum compaction density that can be achieved. Based on current work, the extent of varying degrees of mechanical stability between different metal-organic frameworks is poorly understood.

With this in mind, efforts to understand fundamental relationships between framework structure and mechanical properties will be extremely valuable in directing synthesis efforts toward robust materials that can be compacted to sufficiently high densities without structural changes that might affect CH₄ adsorption capacities.⁷⁵ Equally important will be research toward obtaining finer control over the size and morphology of metal-organic framework particles. In particular, studies on compacting activated carbons have demonstrated that significantly higher packing densities can be achieved when particles of two or more different sizes are mixed and compacted at the same time.^{7,76} To our knowledge, there have not yet been any studies evaluating the effects of the particle size distribution and shape on the achievable packing density for metal-organic frameworks. Note that in addition to evaluating changes in porosity upon compaction, it is also important to consider potential affects on the adsorption and desorption kinetics, as fast kinetics are important for achieving practical refueling and discharge rates in a vehicle.⁷⁷

Natural gas impurities

Although CH₄ is the largest component, pipeline-quality natural gas contains many other impurities that can affect the long-term stability and capacity of an adsorbent (Table 3).⁷⁸ In an ANG vehicle, a guard bed will likely be placed before the storage



Table 3 Example composition of pipeline natural gas (Union Gas)⁷⁹

Component	Mol.%
CH ₄	87–96
C ₂ H ₆	1.5–5.1
C ₃ or greater hydrocarbons	0.1–2.3
C ₆ or greater hydrocarbons	<0.1
N ₂	0.7–5.6
CO ₂	0.1–1.0
O ₂	<0.1
H ₂	<0.02
H ₂ O	<80 mg m ⁻³
Sulfur (including odorants)	5.5 mg m ⁻³

tank during refueling to minimize exposure to impurities.²⁰ Still, the adsorbent will inevitably be exposed to at least some level of each impurity throughout its lifetime. Additionally, most guard beds are unlikely to remove a significant amount of the C₂ and C₃ hydrocarbons that are present in natural gas, and it is unclear how this might affect the usable CH₄ capacity of an adsorbent. Smaller levels of other impurities, especially sulfur-containing compounds, H₂O, O₂, and C₄ and greater hydrocarbons, may slowly poison CH₄ adsorption sites or degrade the framework over an extended time period. Performing cycling studies in the presence of all expected natural gas impurities will be critical to designing metal–organic frameworks with the long lifetimes necessary for use in a natural gas powered vehicle.

Conclusions

With some of the highest volumetric and gravimetric CH₄ capacities ever reported, metal–organic frameworks have shown significant potential as adsorbents for natural gas storage. There are still, however, some formidable challenges to overcome before they are likely to find widespread use in natural gas vehicles. Most importantly, substantial increases in the usable volumetric capacity are needed for improving the driving range to levels closer to that of gasoline vehicles. To go beyond just incremental improvements in capacity, completely new design strategies will likely be necessary. For instance, new types of strong binding sites that occupy a small volume but can each polarize multiple CH₄ molecules should dramatically increase the volumetric density of stored CH₄. Above all, any efforts to minimize the amount of wasted volume inside frameworks that does not contribute to optimally attracting CH₄ molecules, without significantly decreasing porosity, should be beneficial. This includes extra empty space inside large pores, as well as adsorption sites on the pore surface that are too weak or too strong for maximizing the usable capacity.

It is important to emphasize that efforts to design a next generation of high-capacity metal–organic frameworks for natural gas storage must address systems-level factors that will heavily influence the actual performance of a material, including compaction, heat capacity, thermal conductivity, and tolerance to impurities. Studies that address these areas are not only important for determining the practically achievable

usable capacity and lifetime of different materials, but improving our fundamental understanding of the relationship of framework structure and chemical composition with thermal properties, mechanical properties, and long-term stability will also help guide synthetic efforts toward the most useful materials. Ultimately, the cost of the material will also be an important factor in determining the competitiveness of an ANG vehicle. While it is difficult to predict the large-scale cost of organic ligands for which there are currently little demand, basic economic analyses of the best current metal–organic frameworks would be useful for identifying strategies to target materials with the greatest potential for scale-up to the levels required to have an impact in natural gas vehicles.

Acknowledgements

This research was funded by the Advanced Research Projects Agency – Energy (ARPA-E), U.S. Department of Energy. We thank Dr Bruce Hardy, Dr Donald Anton, Michael SantaMaria, Dr Bill Dolan, Dr Lena Arnold, Dr Stefan Marx, and Dr Dane Boysen for helpful discussions. We also thank NSF for providing graduate fellowship support for J.A.M.

Notes and references

- 1 A. Celzard and V. Fierro, *Energy Fuels*, 2005, **19**, 573.
- 2 (a) O. Talu, *Proc. IVth Int. Conf. on Fundamentals of Adsorption*, Kyoto, 1992, p. 655; (b) D. Lozano-Castelló, J. Alcañiz-Monge, M. A. de la Casa-Lillo, D. Cazorla-Amorós and A. Linares-Solano, *Fuel*, 2002, **81**, 1777.
- 3 C. F. Blazek, J. Grimes, P. Freeman, B. K. Bailey and C. Colucci, *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, 1994, **39**, 476.
- 4 International Energy Agency, *World Energy Outlook 2011: Are We Entering a Golden Age of Gas*, <http://www.worldenergyoutlook.org>.
- 5 Alternative Fuels Data Center – Fuel Properties Comparison, 2013, http://www.afdc.energy.gov/fuels/fuel_comparison_chart.pdf.
- 6 (a) S. Yeh, *Energy Policy*, 2007, **35**, 5865; (b) G. A. Whyatt, *Issues Affecting Adoption of Natural Gas in Light- and Heavy-Duty Vehicles*, 2010, PNNL-19745.
- 7 V. C. Menon and S. Komarneni, *J. Porous Mater.*, 1998, **5**, 43.
- 8 (a) E. W. Lemmon, M. L. Huber and M. O. McLinden, *NIST Standard Reference Database 23: Reference Fluid Thermodynamic and Transport Properties-REFPROP*, Version 8.0, National Institute of Standards and Technology, Standard Reference Data Program, Gaithersburg, 2007; (b) U. Setzmann and W. Wagner, *J. Phys. Chem. Ref. Data*, 1991, **20**, 1061.
- 9 D. W. Breck, *Zeolite Molecular Sieves*, J. Wiley & Sons, New York, 1974.
- 10 (a) R. A. Munson and R. A. Clifton, Jr., *Natural Gas Storage with Zeolites*, U.S. Dept. of the Interior, 1971; (b) R. F. Cracknell, P. Gordon and K. E. Gubbins, *J. Phys. Chem.*, 1993, **97**, 494.
- 11 J. Wegrzyn and M. Gurevich, *Appl. Energy*, 1996, **55**, 71.





12 (a) R. W. Judd, D. T. M. Gladding, R. C. Hodrien, D. R. Bates, J. P. Ingram and M. Allen, *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, 1998, **43**, 575; (b) K. Dvorak and R. C. Hodrien, *Development of Adsorbed Natural Gas Technology for Large Scale Diurnal Storage Applications*, *Int. Gas Research Conference*, Amsterdam, 2001; (c) L. Y. Lau and R. Judd, *New Approach to Natural Gas Storage – Advances in Adsorbed Natural Gas (ANG) Technology*, *Int. Gas Research Conference*, Paris, 2008.

13 N. D. Parkyns and D. F. Quinn, in *Porosity in Carbons*, ed. J. W. Patrick, Edward Arnold, London, 1995, ch. 11.

14 K. R. Matranga, A. L. Myers and E. D. Glandt, *Chem. Eng. Sci.*, 1992, **47**, 569.

15 Note that 11.4 Å pores, which can accommodate 3 layers of CH₄, are optimal for maximizing the amount of usable CH₄ for adsorption near 35 bar and desorption near 1 bar.

16 D. F. Quinn, J. A. MacDonald and K. Sosin, *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, 1994, **39**, 451.

17 P. Pfeifer, *et al.*, *Chaos*, 2007, **17**, 041108.

18 The unit cm³_{STP} is defined as the volume occupied by an ideal gas at a standard temperature and pressure (STP). Here, STP is defined as 273.15 K and 1 atm, resulting in a volume of 22.414 mL for 1 mmol of ideal gas at STP.

19 Methane Opportunities for Vehicular Energy, Advanced Research Project Agency – Energy, U.S. Dept. of Energy, Funding Opportunity no. DE-FOA-0000672, 2012.

20 T. L. Cook, C. Komodromos, D. F. Quinn and S. Ragan, *Carbon Materials for Advanced Technologies*, ed. T. D. Burchell, Elsevier, Amsterdam, 1999, ch. 9.

21 (a) H. Li, M. Eddaoudi, M. O'Keeffe and O. M. Yaghi, *J. Am. Chem. Soc.*, 1999, **402**, 276; (b) S. Kitagawa, R. Kitaura and S.-I. Noro, *Angew. Chem., Int. Ed.*, 2004, **43**, 2334; (c) R. Matsuda, R. Kitaura, S. Kitagawa, Y. Kubota, R. V. Belosludov, T. C. Kobayashi, H. Sakamoto, T. Chiba, M. Takata, Y. Kawazoe and Y. Mita, *Nature*, 2005, **436**, 238; (d) A. R. Millward and O. M. Yaghi, *J. Am. Chem. Soc.*, 2005, **127**, 17998; (e) G. Férey, *Chem. Soc. Rev.*, 2008, **37**, 191; (f) R. E. Morris and P. S. Wheatley, *Angew. Chem., Int. Ed.*, 2008, **47**, 4966; (g) A. U. Czaja, N. Trukhan and U. Müller, *Chem. Soc. Rev.*, 2009, **38**, 1284; (h) B. Chen, S. Xiang and G. Qian, *Acc. Chem. Res.*, 2010, **1115**; (i) H.-C. Zhou, J. R. Long and O. M. Yaghi, *Chem. Rev.*, 2012, **112**, 673; (j) K. Sumida, D. L. Rogow, J. A. Mason, T. M. McDonald, E. D. Bloch, Z. R. Herm, T.-H. Bae and J. R. Long, *Chem. Rev.*, 2012, **112**, 724; (k) J.-R. Li, J. Sculley and H.-C. Zhou, *Chem. Rev.*, 2012, **112**, 869.

22 (a) H. Furukawa, M. A. Miller and O. M. Yaghi, *J. Mater. Chem.*, 2007, **17**, 3197; (b) M. Dincă and J. R. Long, *Angew. Chem., Int. Ed.*, 2008, **47**, 6766; (c) L. J. Murray, M. Dincă and J. R. Long, *Chem. Soc. Rev.*, 2009, **38**, 1294; (d) M. P. Suh, H. J. Park, T. K. Prasad and D.-W. Lim, *Chem. Rev.*, 2012, **112**, 782.

23 M. Kondo, T. Yoshitomi, K. Seki, H. Matsuzaka and S. Kitagawa, *Angew. Chem., Int. Ed. Engl.*, 1997, **36**, 1725.

24 (a) M. Eddaoudi, J. Kim, N. Rosi, D. Vodak, J. Wachter, M. O'Keeffe and O. M. Yaghi, *Science*, 2002, **295**, 469; (b) T. Düren, L. Sarkisov, O. M. Yaghi and R. Q. Snurr, *Langmuir*, 2004, **20**, 2683; (c) W. Zhou, *Chem. Rec.*, 2010, **10**, 200; (d) R. B. Getman, Y.-S. Bae, C. E. Wilmer and R. Q. Snurr, *Chem. Rev.*, 2012, **112**, 703; (e) K. Konstas, T. Osl, Y. Yang, M. Batten, N. Burke, A. J. Hill and M. R. Hill, *J. Mater. Chem.*, 2012, **22**, 16698; (f) T. A. Makal, J.-R. Li, W. Lu and H.-C. Zhou, *Chem. Soc. Rev.*, 2012, **41**, 7761; (g) Y. He, W. Zhou, R. Krishna and B. Chen, *Chem. Commun.*, 2012, **48**, 11813; (h) C. E. Wilmer, M. Leaf, C. Yeon Lee, O. K. Farha, B. G. Hauser, J. T. Hupp and R. Q. Snurr, *Nat. Chem.*, 2012, **4**, 83.

25 J. W. Gibbs, *The Collected Works of J. W. Gibbs*, Longmans and Green, New York, 1928.

26 (a) S. Sircar, *Ind. Eng. Chem. Res.*, 1999, **38**, 3670; (b) S. Sircar, *AIChE J.*, 2001, **47**, 1169; (c) K. Murata, M. El-Merraoui and K. Kaneko, *J. Chem. Phys.*, 2001, **114**, 4196; (d) A. L. Myers and P. A. Monson, *Langmuir*, 2002, **18**, 10261; (e) D. D. Do and H. D. Do, *Carbon*, 2003, **41**, 1777; (f) S. Gumma and O. Talu, *Langmuir*, 2010, **26**, 17013.

27 While the total *material* adsorption is defined as the total number of gas molecules inside the pores of an adsorbent, the total *system* adsorption is defined as the total number of gas molecules inside the entire system, which includes interparticle voids and other empty spaces inside the adsorption vessel. Even though the total system adsorption is most important for application in a vehicle, total material adsorption is more meaningful for comparing properties of different adsorbents. In this work, the terms “total material adsorption” and “total adsorption” are used interchangeably.

28 K. J. Gross, K. R. Carrington, S. Barcelo, A. Karkamkar, J. Purewal, S. Ma, H.-C. Zhou, P. Dantzer, K. Ott, T. Burrell, T. Semeslberger, Y. Pivak, B. Dam and D. Chandra, *Recommended Best Practices for the Characterization of Storage Properties of Hydrogen Storage Materials*, 2011, pp. V3–V5, U.S. D.O.E. Hydrogen Program document, http://www1.eere.energy.gov/hydrogenandfuelcells/pdfs/best_practices_hydrogen_storage.pdf.

29 (a) M. Dincă, A. Dailly, Y. Liu, C. M. Brown, D. A. Neumann and J. R. Long, *J. Am. Chem. Soc.*, 2006, **128**, 16876; (b) E. Poirier and A. Dailly, *J. Phys. Chem. C*, 2008, **112**, 13047.

30 For microporous materials, this is a particularly good approximation since most gas molecules inside a micropore should have some degree of interaction with the pore surface. As pores get larger, this may not always be a valid assumption, which can affect the accuracy of using isotherm data to calculate thermodynamic properties.

31 K. S. W. Sing, D. H. Everett, R. A. W. Haul, L. Moscou, R. A. Pierotti, J. Rouquerol and T. Siemieniewska, *Pure Appl. Chem.*, 1985, **57**, 603.

32 L. Gurvich, *J. Phys. Chem. Soc. Russ.*, 1915, **47**, 805.

33 More advanced techniques, such as t-Plots, the Horvath–Kawozoe (H–K) equation, and Density Functional Theory (DFT), can be used to extract detailed pore size

distributions, but whether the calculated total pore volume from these methods will differ significantly from the simple single-point calculation using the Gurvich rule is not well studied.

34 S. Lowell, J. Shields, M. A. Thomas and M. Thommes, *Characterization of Porous Solids and Powders: Surface Area, Pore Size and Density*, Springer, The Netherlands, 2004, pp. 111–112.

35 J. Moellmer, E. B. Celer, R. Luebke, A. J. Cairns, R. Staudt, M. Eddaoudi and M. Thommes, *Microporous Mesoporous Mater.*, 2010, **129**, 345.

36 R. Krishna, *Microporous Mesoporous Mater.*, 2012, **156**, 217.

37 (a) J. U. Keller, E. Robens and C. du Fresne von Hohenesche, *Proc. COPS-VI*, 2002, **144**, 387; (b) Y. Belmabkhout, M. Frère and G. De Weireld, *Meas. Sci. Technol.*, 2004, **15**, 848; (c) D. P. Broom, *Int. J. Hydrogen Energy*, 2007, **32**, 4871.

38 P. Malbrunot, D. Vidal, J. Vermesse, R. Chahine and T. K. Bose, *Langmuir*, 1997, **13**, 539.

39 W. Zhou, H. Wu, M. R. Hartman and T. Yildirim, *J. Phys. Chem. C*, 2007, **111**, 16131.

40 M. Kunowsky, F. Suárez-García and Á. Linares-Solano, *Microporous Mesoporous Mater.*, 2013, **173**, 47.

41 (a) N. L. Rosi, J. Kim, M. Eddaoudi, B. Chen, M. O'Keeffe and O. M. Yaghi, *J. Am. Chem. Soc.*, 2005, **127**, 1504; (b) S. R. Caskey, A. G. Wong-Foy and A. J. Matzger, *J. Am. Chem. Soc.*, 2008, **130**, 10870; (c) P. D. C. Dietzel, R. Blom and H. Fjellvag, *Eur. J. Inorg. Chem.*, 2008, 3624; (d) Y. Liu, H. Kabbour, C. M. Brown, A. D. Neumann and C. C. Ahn, *Langmuir*, 2008, **24**, 4772; (e) P. D. C. Dietzel, R. E. Johnsen, H. Fjellvag, S. Bordiga, E. Gropo, S. Chavan and R. Blom, *Chem. Commun.*, 2008, 5125; (f) W. Zhou, H. Wu and T. Yildirim, *J. Am. Chem. Soc.*, 2008, **130**, 15268; (g) D. Britt, H. Furukawa, B. Wang, T. G. Glover and O. M. Yaghi, *Proc. Natl. Acad. Sci. U. S. A.*, 2009, **106**, 20637; (h) P. D. C. Dietzel, V. Besikiotis and R. Blom, *J. Mater. Chem.*, 2009, **19**, 7362; (i) H. Wu, J. M. Simmons, G. Srinivas, W. Zhou and T. Yildirim, *J. Phys. Chem. Lett.*, 2010, **1**, 1946; (j) L. Valenzano, B. Civalleri, S. Chavan, G. T. Palomino, C. O. Areán and S. Bordiga, *J. Phys. Chem. C*, 2010, **114**, 11185; (k) Z. Bao, L. Yu, Q. Ren, X. Lu and S. Deng, *J. Colloid Interface Sci.*, 2011, **353**, 549; (l) K. Sumida, C. M. Brown, Z. R. Herm, S. Chavan, S. Bordiga and J. R. Long, *Chem. Commun.*, 2011, **47**, 1157; (m) W. L. Queen, C. M. Brown, D. K. Britt, M. R. Hudson and O. M. Yaghi, *J. Phys. Chem. C*, 2011, **115**, 24915; (n) Z. R. Herm, J. A. Swisher, B. Smit, R. Krishna and J. R. Long, *J. Am. Chem. Soc.*, 2011, **133**, 5664; (o) J. A. Mason, K. Sumida, Z. R. Herm, R. Krishna and J. R. Long, *Energy Environ. Sci.*, 2011, **4**, 3030; (p) W. L. Queen, E. D. Bloch, C. M. Brown, M. R. Hudson, J. A. Mason, L. J. Murray, A. J. Ramirez-Cuesta, V. K. Peterson and J. R. Long, *Dalton Trans.*, 2012, **41**, 4180; (q) E. D. Bloch, W. L. Queen, R. Krishna, J. M. Zadrozny, C. M. Brown and J. R. Long, *Science*, 2012, **335**, 1606; (r) S. J. Geier, J. A. Mason, E. D. Bloch, W. L. Queen, M. R. Hudson, C. M. Brown and J. R. Long, *Chem. Sci.*, 2013, **4**, 2054.

42 H. Wu, W. Zhou and T. Yildirim, *J. Am. Chem. Soc.*, 2009, **131**, 4995.

43 (a) S. S. Y. Chui, S. M. F. Lo, J. P. H. Charmant, A. G. Orpen and I. D. Williams, *Science*, 1999, **283**, 1148; (b) I. Senkovska and S. Kaskel, *Microporous Mesoporous Mater.*, 2008, **112**, 108; (c) S. Cavenati, C. A. Grande, A. E. Rodrigues, C. Kiener and U. Müller, *Ind. Eng. Chem. Res.*, 2008, **47**, 6333; (d) J. Moellmer, A. Moeller, F. Dreisbach, R. Glaeser and R. Staudt, *Microporous Mesoporous Mater.*, 2011, **138**, 140; (e) P. Chowdhury, S. Mekala, F. Dreisbach and S. Gumma, *Microporous Mesoporous Mater.*, 2012, **152**, 246; (f) N. C. Jeong, B. Samanta, C. Y. Lee, O. K. Farha and J. T. Hupp, *J. Am. Chem. Soc.*, 2012, **134**, 51; (g) A. D. Wiersum, J.-S. Chang, C. Serre and P. L. Llewellyn, *Langmuir*, 2013, **29**, 3301.

44 (a) E. García-Pérez, J. Gascón, V. Morales-Flórez, J. M. Castillo, F. Kapteijn and S. Calero, *Langmuir*, 2009, **25**, 1725; (b) J. Getzschmann, I. Senkovska, D. Wallacher, M. Tovar, D. Fairén-Jimenez, T. Düren, J. M. van Baten, R. Krishna and S. Kaskel, *Microporous Mesoporous Mater.*, 2010, **136**, 50; (c) H. Wu, J. M. Simmons, Y. Liu, C. M. Brown, X.-S. Wang, S. Ma, V. K. Peterson, P. D. Southon, C. J. Kepert, H.-C. Zhou, T. Yildirim and W. Zhou, *Chem.-Eur. J.*, 2010, **16**, 5205.

45 (a) S. Ma, D. Sun, J. M. Simmons, C. D. Collier, D. Yuan and H.-C. Zhou, *J. Am. Chem. Soc.*, 2008, **130**, 1012; (b) S. M. P. Lucean, P. G. M. Mileo, P. F. G. Silvino and C. L. Cavalcante, Jr, *J. Am. Chem. Soc.*, 2011, **133**, 19282.

46 (a) J. L. C. Roswell, A. R. Millward, K. S. Park and O. M. Yaghi, *J. Am. Chem. Soc.*, 2004, **126**, 5666; (b) A. G. Wong-Foy, A. J. Matzger and O. M. Yaghi, *J. Am. Chem. Soc.*, 2006, **128**, 3494; (c) S. S. Kaye, A. Dailly, O. M. Yaghi and J. R. Long, *J. Am. Chem. Soc.*, 2007, **129**, 14176; (d) H. Furukawa, N. Ko, Y. B. Go, N. Aratani, S. B. Choi, E. Choi, A. Ö. Yazaydin, R. Q. Snurr, M. O'Keeffe, J. Kim and O. M. Yaghi, *Science*, 2010, **329**, 424.

47 (a) D. F. Quinn and J. A. MacDonald, *Carbon*, 1992, **30**, 1097; (b) J. A. F. MacDonald and D. F. Quinn, *Fuel*, 1998, **77**, 61; (c) L. Zhou, Y. Zhou, M. Li, P. Chen and Y. Wang, *Langmuir*, 2000, **16**, 5955.

48 U. Stoeck, S. Krause, V. Bon, I. Senkovska and S. Kaskel, *Chem. Commun.*, 2012, **48**, 10841.

49 Y. Peng, G. Srinivas, C. E. Wilmer, C. E. Wilmer, I. Eryazici, R. Q. Snurr, J. T. Hupp, T. Yildirim and O. K. Farha, *Chem. Commun.*, 2013, **49**, 2992.

50 B. Li, Z. Zhang, Y. Li, K. Yao, Y. Zhu, Z. Deng, F. Yang, X. Zhou, G. Li, H. Wu, N. Nijem, Y. J. Chabal, Z. Lai, Y. Han, Z. Shi, S. Feng and J. Li, *Angew. Chem., Int. Ed.*, 2012, **51**, 1412.

51 Y. Wu, A. Kobayashi, G. J. Halder, V. K. Peterson, K. W. Chapman, N. Lock, P. D. Southon and C. J. Kepert, *Angew. Chem., Int. Ed.*, 2008, **47**, 8929.

52 S. Sircar, *Ind. Eng. Chem. Res.*, 1992, **31**, 1813.

53 See for example: ref 82, 87, 95, 104 and 116.





54 L. Czepirski and J. Jagiełło, *Chem. Eng. Sci.*, 1989, **44**, 797.

55 K. A. G. Amankwah and J. A. Schwarz, *Carbon*, 1995, **33**, 1313.

56 I. Langmuir, *J. Am. Chem. Soc.*, 1918, **40**, 1361.

57 See for example: (a) C. R. Clarkson, R. M. Bustin and J. H. Levy, *Carbon*, 1997, **35**, 1689; (b) J. H. Levy, S. J. Day and J. S. Killingley, *Fuel*, 1997, **76**, 813; (c) M.-A. Richard, P. Bénard and R. Chahine, *Adsorption*, 2009, **15**, 43.

58 R. Krishna and J. R. Long, *J. Phys. Chem. C*, 2011, **115**, 12941.

59 See for example: ref 45a, 46c, 83, 87 and 92.

60 K. Sillar and J. Sauer, *J. Am. Chem. Soc.*, 2012, **134**, 18354.

61 Y. He, W. Zhou, T. Yildirim and B. Chen, *Energy Environ. Sci.*, 2013, **6**, 2735.

62 R. Saidur, M. Rezaei, W. K. Muzammil, M. H. Hassan, S. Paria and M. Hasanuzzaman, *Renewable Sustainable Energy Rev.*, 2012, **16**, 5649.

63 Y. Peng, V. Krungleviciute, I. Eryazici, J. T. Hupp, O. K. Farha and T. Yildirim, *J. Am. Chem. Soc.*, 2013, **135**, 11887.

64 B. Yilmaz, N. Trukhan and U. Müller, *Chin. J. Catal.*, 2012, **33**, 3.

65 S. K. Bhatia and A. L. Myers, *Langmuir*, 2006, **22**, 1688.

66 E. Garrone, B. Bonelli and C. Otero Areán, *Chem. Phys. Lett.*, 2008, **456**, 68.

67 NIST Handbook 44 – 2012 Edition, “Specifications, Tolerances, and Other Technical Requirements for Weighing and Measuring Devices”, 2012, D-13.

68 U.S. Dept. of Energy, 2013, <http://www.fueleconomy.gov/feg/drivehabits.shtml>.

69 K. J. Chang and O. Talu, *Appl. Therm. Eng.*, 1996, **16**, 359.

70 L. L. Vasiliev, L. E. Kanonchik, D. A. Mishkinis and M. I. Rabetsky, *Int. J. Therm. Sci.*, 2000, **39**, 1047.

71 B. Mu and K. S. Walton, *J. Phys. Chem. C*, 2011, **115**, 22748.

72 (a) B. L. Huang, Z. Ni, A. Millward, A. J. H. McGaughey, C. Uher, M. Kaviani and O. M. Yaghi, *Int. J. Heat Mass Transfer*, 2007, **50**, 405; (b) D. Liu, J. J. Purewal, J. Yang, A. Sudik, S. Maurer, U. Müller, J. Ni and D. J. Siegel, *Int. J. Hydrogen Energy*, 2012, **37**, 6109.

73 (a) J. Aclaniz-Monge, C. Trautwein, M. Pérez-Cadenas and M. C. Román-Martínez, *Microporous Mesoporous Mater.*, 2006, **126**, 291; (b) R. Zacharia, D. Cossement, L. Lafi and R. Chahine, *J. Mater. Chem.*, 2010, **20**, 2145; (c) M. Tagliabue, C. Rizzo, R. Millini, P. D. C. Dietzel, R. Blom and S. Zanardi, *J. Porous Mater.*, 2011, **18**, 289; (d) J. J. Purewal, D. Liu, J. Yang, A. Sudik, D. J. Siegel, S. Maurer and U. Müller, *Int. J. Hydrogen Energy*, 2012, **37**, 2723; (e) G. W. Peterson, J. B. DeCoste, T. G. Glover, Y. Huang, H. Jasuja and K. S. Walton, *Microporous Mesoporous Mater.*, 2013, **179**, 48.

74 J. C. Tan and A. K. Cheetham, *Chem. Soc. Rev.*, 2011, **40**, 1059.

75 (a) W. Zhou and T. Yildirim, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2006, **74**, 180301; (b) H. Wu, T. Yildirim and W. Zhou, *Phys. Chem. Lett.*, 2013, **4**, 925.

76 (a) M. Greenbank, *U.S. Pat.*, 4,972,658, 1990; (b) C. H. Chang, *U.S. Pat.*, 5,308,821, 1994.

77 L. Arnold, G. Averlant, S. Marx, M. Weickert, U. Müller, J. Mertel, C. Horch, M. Peksa and F. Stallmach, *Chem. Ing. Tech.*, 2013, **85**, 1.

78 (a) J. P. B. Mota, *AIChE J.*, 1999, **45**, 986; (b) O. Pupier, V. Goetz and R. Fiscal, *Chem. Eng. Process.*, 2005, **44**, 71.

79 <http://www.uniongas.com/about-us/about-natural-gas/Chemical-Composition-of-Natural-Gas>.

80 Z. Lu, L. Du, K. Tang and J. Bai, *Cryst. Growth Des.*, 2013, **13**, 2252.

81 J. Y. Lee, L. Pan, X. Huang, T. J. Emge and J. Li, *Adv. Funct. Mater.*, 2011, **21**, 993.

82 Z. Guo, H. Wu, G. Srinivas, Y. Zhou, S. Xiang, Z. Chen, Y. Yang, W. Zhou, M. O’Keeffe and B. Chen, *Angew. Chem., Int. Ed.*, 2011, **50**, 3178.

83 X.-S. Wang, S. Ma, K. Rauch, J. M. Simmons, D. Yuan, X. Wang, T. Yildirim, W. C. Cole, J. J. López, A. de Meijere and H.-C. Zhou, *Chem. Mater.*, 2008, **20**, 3145.

84 D. Liu, H. Wu, S. Wang, Z. Xie, J. Li and W. Lin, *Chem. Sci.*, 2012, **3**, 3032.

85 D. Sun, S. Ma, J. M. Simmons, J.-R. Li, D. Yuan and H.-C. Zhou, *Chem. Commun.*, 2010, **46**, 1329.

86 X. Lin, I. Telepeni, A. J. Blake, A. Dailly, C. M. Brown, J. M. Simmons, M. Zoppi, G. S. Walker, K. M. Thomas, T. J. Mays, P. Hubberstey, N. R. Champness and M. Schröder, *J. Am. Chem. Soc.*, 2009, **131**, 2159.

87 X. Rao, J. Cai, J. Yu, Y. He, C. Wu, W. Zhou, T. Yildirim, B. Chen and G. Qian, *Chem. Commun.*, 2013, **49**, 6719.

88 P. Rallapalli, D. Patil, K. P. Prasanth, R. S. Soman, R. V. Jasra and H. C. Bajaj, *J. Porous Mater.*, 2010, **17**, 523.

89 S. Bourrelly, P. L. Llewellyn, C. Serre, F. Millange, T. Loiseau and G. Férey, *J. Am. Chem. Soc.*, 2005, **127**, 13519.

90 T. Loiseau, C. Serre, C. Huguenard, G. Fink, F. Taulelle, M. Henry, T. Bataille and G. Férey, *Chem.-Eur. J.*, 2004, **10**, 1373.

91 A. Lyubchyk, I. A. A. C. Esteves, F. J. A. L. Cruz and J. P. B. Mota, *J. Phys. Chem. C*, 2011, **115**, 20628.

92 X. Duan, J. Yu, J. Cai, Y. He, C. Wu, W. Zhou, T. Yildirim, Z. Zhang, S. Xiang, M. O’Leiffe, B. Chen and G. Qian, *Chem. Commun.*, 2013, **49**, 2043.

93 C. E. Wilmer, O. K. Farha, T. Yildirim, I. Eryazici, V. Krungleviciute, A. A. Sarjeant, R. Q. Snurr and J. T. Hupp, *Energy Environ. Sci.*, 2013, **6**, 1158.

94 M. Eddaoudi, J. Kim, N. Rosi, D. Vodak, J. Wachter, M. O’Keeffe and O. M. Yaghi, *Science*, 2002, **296**, 469.

95 H. Kim, D. G. Samsonenko, S. Das, G.-H. Kim, H.-S. Lee, D. N. Dybtsev, E. A. Berdonosova and K. Kim, *Chem.-Asian J.*, 2009, **4**, 886.

96 X. L. Zhao, D. Sun, S. Yuan, S. Feng, R. Cao, D. Yuan, S. Wang, J. Dou and D. Sun, *Inorg. Chem.*, 2012, **51**, 10350.

97 D. Yuan, D. Zhao, D. Sun and H.-C. Zhou, *Angew. Chem., Int. Ed.*, 2010, **49**, 5357.

98 D. Zhao, D. Yuan, A. Yakovenko and H.-C. Zhou, *Chem. Commun.*, 2010, **46**, 4196.

99 H. Wang, J. Getzschmann, I. Senkovska and S. Kaskel, *Microporous Mesoporous Mater.*, 2008, **116**, 653.

100 Y. He, Z. Zhang, S. Xiang, H. Wu, F. R. Fronczek, W. Zhou, R. Krishna, M. O'Keeffe and B. Chen, *Chem.-Eur. J.*, 2012, **18**, 1901.

101 Y. He, S. Xiang, Z. Zhang, S. Xiong, C. Wu, W. Zhou, T. Yildirim, R. Krishna and B. Chen, *J. Mater. Chem. A*, 2013, **1**, 2543.

102 N. Klein, H. C. Hoffmann, A. Cadiou, J. Getzschmann, M. R. Lohe, S. Paasch, T. Heydenreich, K. Adil, I. Senkovska, E. Brunner and S. Kaskel, *J. Mater. Chem.*, 2012, **22**, 10303.

103 W. Lu, D. Yuan, T. A. Makal, J.-R. Li and H.-C. Zhou, *Angew. Chem., Int. Ed.*, 2012, **51**, 1580.

104 H. J. Park, D.-W. Lim, W. S. Yang, T.-R. Oh and M. P. Suh, *Chem.-Eur. J.*, 2011, **17**, 7251.

105 X. L. Zhao, D. Sun, S. Yuan, S. Feng, R. Cao, D. Yuan, S. Wang, J. Dou and D. Sun, *Inorg. Chem.*, 2012, **51**, 10350.

106 J. L. C. Rowsell and O. M. Yaghi, *J. Am. Chem. Soc.*, 2006, **128**, 1304.

107 Y. He, H. Furukawa, C. Wu, M. O'Keeffe, R. Krishna and B. Chen, *Chem. Commun.*, 2013, **49**, 6773.

108 D. Yuan, D. Zhao, D. Sun and H.-C. Zhou, *Angew. Chem., Int. Ed.*, 2010, **49**, 5357.

109 N. Klein, I. Senkovska, I. A. Baburin, R. Grünker, U. Stoeck, M. Schlichtenmayer, B. Streppel, U. Mueller, S. Leoni, M. Hirscher and S. Kaskel, *Chem.-Eur. J.*, 2011, **17**, 13007.

110 J. Pérez-Pellitero, H. Amrouche, F. R. Siperstein, G. Pirngruber, C. Nieto-Draghi, G. Chaplais, A. Simon-Masseron, D. Bazer-Bachi, D. Peralta and N. Bats, *Chem.-Eur. J.*, 2010, **16**, 1560.

111 T. K. Prasad and M. P. Suh, *Chem.-Eur. J.*, 2012, **18**, 8673.

112 J. L. Mendoza-Cortés, S. S. Han, H. Furukawa, O. M. Yaghi and W. A. Goddard III, *J. Phys. Chem. A*, 2010, **114**, 10824.

113 S. Noro, R. Kitaura, M. Kondo, S. Kitagawa, T. Ishii, H. Matsuzaka and M. Yamashita, *J. Am. Chem. Soc.*, 2002, **124**, 2568.

114 S. Noro, S. Kitagawa, M. Kondo and K. Seki, *Angew. Chem., Int. Ed.*, 2000, **39**, 2082.

115 M. Park, D. Moon, J. W. Yoon, J.-S. Chang and M. S. Lah, *Chem. Commun.*, 2009, 2026.

116 T. K. Prasad, D. H. Hong and M. P. Suh, *Chem.-Eur. J.*, 2010, **16**, 14043.

117 I. Senkovska, F. Hoffmann, M. Fröba, J. Getzschmann, W. Böhlmann and S. Kaskel, *Microporous Mesoporous Mater.*, 2009, **122**, 93.

118 M. C. Das, H. Xu, Z. Wang, G. Srinivas, W. Zhou, Y.-F. Yue, V. N. Nesterov, G. Qian and B. Chen, *Chem. Commun.*, 2011, **47**, 11715.

119 P. L. Llewellyn, S. Bourrelly, C. Serre, A. Vimont, M. Daturi, L. Hamon, G. D. Weireld, J.-S. Chang, D.-Y. Hong, Y. K. Hwang, S. H. Jhung and G. Férey, *Langmuir*, 2008, **24**, 7245.

120 J. I. Feldblyum, D. Dutta, A. G. Wong-Foy, A. Dailly, J. Imirzian, D. W. Gidley and A. J. Matzger, *Langmuir*, 2013, **29**, 8146.

121 N. Klein, I. Senkovska, K. Gedrich, U. Stoeck, A. Henschel, U. Mueller and S. Kaskel, *Angew. Chem., Int. Ed.*, 2009, **48**, 9954.

122 T. K. Prasad and M. P. Suh, *Chem.-Eur. J.*, 2012, **18**, 8673.

123 D. Han, F.-L. Jian, M.-Y. Wu, L. Chen, Q.-H. Chen and M.-C. Hong, *Chem. Commun.*, 2011, **47**, 9861.

124 J. Pérez-Pellitero, H. Amrouche, F. R. Siperstein, G. Pirngruber, C. Nieto-Draghi, G. Chaplais, A. Simon-Masseron, D. Bazer-Bachi, D. Peralta and N. Bats, *Chem.-Eur. J.*, 2010, **16**, 1560.

125 Y. Yan, S. Yang, A. J. Blake, W. Lewis, E. Poirier, S. A. Barnett, N. R. Champness and M. Schröder, *Chem. Commun.*, 2011, **47**, 9995.

126 M. K. Sharma, I. Senkovska, S. Kaskel and P. K. Bharadwaj, *Inorg. Chem.*, 2011, **50**, 539.

127 K. Gedrich, I. Senkovska, N. Klein, U. Stoeck, A. Henschel, M. R. Lohe, I. A. Baburin, U. Mueller and S. Kaskel, *Angew. Chem., Int. Ed.*, 2010, **49**, 8489.

128 R. Grünker, I. Senkovska, R. Biedermann, N. Klein, M. R. Lohe, P. Müller and S. Kaskel, *Chem. Commun.*, 2011, **47**, 490.

129 M. Konda, M. Shimamure, S. Noro, S. Minakoshi, A. Asami, K. Seki and S. Kitagawa, *Chem. Mater.*, 2000, **12**, 1288.

130 H. J. Park, Y. E. Cheon and M. P. Suh, *Chem.-Eur. J.*, 2010, **16**, 11662.

131 (a) K. Seki, *Chem. Commun.*, 2001, 1496; (b) K. Seki and W. Mori, *J. Phys. Chem. B*, 2002, **106**, 1380.

132 P. L. Llewellyn, S. Bourrelly, C. Vagner, N. Heymans, H. Leclerc, A. Ghoufi, P. Bazin, A. Vimont, M. Daturi, T. Devic, C. Serre, G. D. Weireld and G. Maurin, *J. Phys. Chem. C*, 2013, **117**, 962.

133 R. Kitaura, K. Seki, G. Akiyama and S. Kitagawa, *Angew. Chem., Int. Ed.*, 2003, **42**, 428.

134 H. Furukawa and O. M. Yaghi, *J. Am. Chem. Soc.*, 2009, **131**, 8875.

135 D. Yuan, W. Lu, D. Zhao and H.-C. Zhou, *Adv. Funct. Mater.*, 2011, **21**, 3723.

136 (a) P. D. Rolniak and R. Kobayashi, *AIChE J.*, 1980, **26**, 616; (b) Q. H. Dirar and K. F. Loughlin, *Adsorption*, 2013, DOI: 10.1007/s10450-013-9543-2.

