

Cite this: *Chem. Sci.*, 2025, 16, 4788

All publication charges for this article have been paid for by the Royal Society of Chemistry

## Pd single atoms on g-C<sub>3</sub>N<sub>4</sub> photocatalysts: minimum loading for maximum activity†

Velu Jeyalakshmi,<sup>‡ab</sup> Siming Wu,<sup>‡a</sup> Shanshan Qin,<sup>Ⓜa</sup> Xin Zhou,<sup>a</sup> Bidyut Bikash Sarma,<sup>Ⓜc</sup> Dmitry E. Doronkin,<sup>Ⓜd</sup> Jan Kolařík,<sup>e</sup> Miroslav Šooš<sup>b</sup> and Patrik Schmuki<sup>Ⓜ\*ae</sup>

Noble metal single atoms (SAs) on semiconductors are increasingly explored as co-catalysts to enhance the efficiency of photocatalytic hydrogen production. In this study, we introduce a “spontaneous deposition” approach to anchor Pd SAs onto graphitic carbon nitride (g-C<sub>3</sub>N<sub>4</sub>) using a highly dilute tetraaminepalladium(II) chloride precursor. Maximized photocatalytic activity and significantly reduced charge transfer resistance can be achieved with a remarkably low Pd loading of 0.05 wt% using this approach. The resulting Pd SA-modified g-C<sub>3</sub>N<sub>4</sub> demonstrates a remarkable hydrogen production efficiency of 0.24 mmol h<sup>-1</sup> mg<sup>-1</sup> Pd, which is >50 times larger than that of Pd nanoparticles deposited on g-C<sub>3</sub>N<sub>4</sub> via conventional photodeposition. This significant enhancement in catalytic performance is attributed to improved electron transfer facilitated by the optimal coordination of Pd SAs within the g-C<sub>3</sub>N<sub>4</sub> structure.

Received 19th December 2024

Accepted 4th February 2025

DOI: 10.1039/d4sc08589b

rsc.li/chemical-science

### Introduction

In recent years, the demand for hydrogen as a clean renewable energy carrier has grown rapidly, driven by the need to replace traditional fossil fuels. Photocatalytic water splitting is a promising and most elegant way to directly convert solar energy into clean, renewable hydrogen (H<sub>2</sub>).<sup>1,2</sup> Since the pioneering work of Fujishima *et al.*, titanium dioxide (TiO<sub>2</sub>) has become the most extensively studied material for this purpose.<sup>3–5</sup> More recently, graphitic carbon nitride (C<sub>3</sub>N<sub>4</sub>) is being increasingly explored as it shares many advantageous features with TiO<sub>2</sub>, such as high stability, abundance, and a suitable band structure for water splitting but provides the key advantage of strong visible light absorption, resulting in significantly enhanced solar light utilization.<sup>6–9</sup>

Nevertheless, due to strong kinetic hindrance for the photocatalytic hydrogen evolution reaction (HER) on the C<sub>3</sub>N<sub>4</sub>

surface, an enhanced efficiency highly depends on the development of highly active co-catalysts – typically noble metals such as Pt, Pd, and Rh need to be deposited on the semiconductor surface to obtain a reasonable H<sub>2</sub> production rate. Despite efforts made using non-precious metal HER electrocatalysts,<sup>10</sup> noble metal-based materials remain nearly irreplaceable due to their superior activity and chemical stability. However, the scarcity and high cost of these metals pose significant challenges to the large-scale application of these noble metal-based co-catalysts. This has prompted considerable efforts to minimize noble metal usage while retaining high catalytic performance. In this context, single-atom catalysts have garnered wide attention due to their maximized atom utilization efficiency.<sup>11–13</sup>

As for many other semiconductors and also for C<sub>3</sub>N<sub>4</sub> substrates, a wide range of noble metal SAs have been successfully deposited as nanoparticles, clusters or SA, and accordingly improvement in photocatalytic H<sub>2</sub> production has been reported.<sup>14–21</sup> In search of the most active SA species, Akinaga *et al.* conducted a remarkable study on ten transition metal elements, including Cu, Ni, Pd, Pt, Rh, Ru, Ag and Au, as SAs anchored on g-C<sub>3</sub>N<sub>4</sub>. Among the metals tested, Pd demonstrated significantly higher hydrogen evolution activity compared to other precious metals such as Pt, Rh as well as other transition metals.<sup>14</sup> The authors ascribed the superior activity of Pd on C<sub>3</sub>N<sub>4</sub> to the suitable electronic structure of this metal on C<sub>3</sub>N<sub>4</sub>. In their work, Akinaga *et al.* used a photodeposition approach to achieve a relatively high SA loading (>0.5 wt%).

However, for many semiconductors, the activity of SAs in photocatalysis is extremely dependent on the deposition

<sup>a</sup>Department of Materials Science WW4-LKO, Friedrich-Alexander-University of Erlangen-Nuremberg, Martensstrasse 7, 91058 Erlangen, Germany. E-mail: schmuki@www.uni-erlangen.de

<sup>b</sup>Department of Chemical Engineering, University of Chemistry and Technology, Technická 3, Prague 160 00, Czech Republic

<sup>c</sup>Laboratoire de Chimie de Coordination (LCC), CNRS, Université de Toulouse, INPT, UPR 8241, 205 Route de Narbonne, 31077 Toulouse Cedex 4, France

<sup>d</sup>Institute of Catalysis Research and Technology, KIT, Hermann-von-Helmholtz-Platz 1, 76344 Eggenstein-Leopoldshafen, Germany

<sup>e</sup>Regional Centre of Advanced Technologies and Materials, Štechtitelů 27, 78371 Olomouc, Czech Republic

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d4sc08589b>

‡ These authors contributed equally to this work.



approach.<sup>13,21–23</sup> Namely, for Pt SAs on TiO<sub>2</sub>, it was reported that “reactive” deposition leads to highly active SA configurations that can provide maximized H<sub>2</sub> production, *i.e.*, a very high catalytic efficiency can be reached at very low noble-metal loading. This approach relies on the surface reaction of highly dilute solutions of suitable noble-metal precursors.<sup>24–27</sup>

In the present work, we first explore various Pd precursors for the feasibility of a reactive SA attachment on C<sub>3</sub>N<sub>4</sub>. We find that tetraaminopalladium(II) chloride – Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> as a Pd precursor solution with C<sub>3</sub>N<sub>4</sub> allows for an adjustable Pd SA loading with a wide range of deposition concentrations from 0.04 wt% to 0.75 wt%. Our results show that by the reaction of a minimal amount of a 0.05 mM precursor, maximum photocatalytic efficiency can be obtained. The photocatalytic hydrogen production activity of such Pd SA-decorated C<sub>3</sub>N<sub>4</sub> achieves a normalized H<sub>2</sub> production activity of 0.24 mmol h<sup>-1</sup> mg<sup>-1</sup> Pd, which is 55 times higher than that observed with Pd nanoparticle-decorated C<sub>3</sub>N<sub>4</sub> at an effective loading that is more than 10 times lower than that typically reported in the literature for Pd on C<sub>3</sub>N<sub>4</sub>. The superior activity of Pd SAs/C<sub>3</sub>N<sub>4</sub> is attributed to the strong coordination of Pd SAs within the C<sub>3</sub>N<sub>4</sub> structure, forming a highly stable and catalytically effective configuration that drastically reduces the charge transfer resistance for the HER. These results illustrate how a refined anchoring of SAs on substrates can enable more cost- and production-effective use of precious metals in photocatalysis.

## Results and discussion

Nanosheets of g-C<sub>3</sub>N<sub>4</sub> were synthesized using a thermal polycondensation method starting from an equimolar mixture of melamine and dicyandiamide, followed by thermal exfoliation, as described in the literature.<sup>28–30</sup> In order to explore the feasibility of direct deposition of a (reactive) SA such as Pd on C<sub>3</sub>N<sub>4</sub>,

we examined different precursor species, namely tetraaminopalladium(II) chloride (Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub>), palladium(II) chloride (PdCl<sub>2</sub>) and ammonium hexachloropalladate(IV) ((NH<sub>4</sub>)<sub>2</sub>[PdCl<sub>6</sub>]). To investigate the reactive deposition behavior, we used three different Pd precursors at a concentration of 2 mM to decorate Pd on C<sub>3</sub>N<sub>4</sub>. We then evaluated the general deposition behavior with electron microscopy and XPS and also evaluated the photocatalytic H<sub>2</sub> production performance. Among the samples, XPS results reveal that both PdCl<sub>2</sub> and (NH<sub>4</sub>)<sub>2</sub>[PdCl<sub>6</sub>] lead to relatively high Pd loadings (>1 at%) (Fig. S1a and b<sup>†</sup>); however, the strong Cl 2p signals in the XPS spectra (Fig. S1c<sup>†</sup>) indicate that most of the Pd precursor did not react with C<sub>3</sub>N<sub>4</sub>, *i.e.*, the precursor is just physically adsorbed on the C<sub>3</sub>N<sub>4</sub> surface. In the SEM images of these two samples (Fig. S2<sup>†</sup>), obvious Pd nanoparticles can be seen, due to the agglomeration caused by high loading. In contrast, the Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> sample shows no visible metal nanoparticle formation in SEM (Fig. 1a), non-metallic Pd position in XPS (Fig. S1a<sup>†</sup>) and no detectable Cl 2p signal (Fig. S1b<sup>†</sup>), indicating a complete reaction of this particular precursor with the C<sub>3</sub>N<sub>4</sub> surface.

Fig. 1a shows the SEM image of Pd-deposited g-C<sub>3</sub>N<sub>4</sub> (Pd SAs/C<sub>3</sub>N<sub>4</sub>) using Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> at a concentration of 0.002 mM, and Fig. S3<sup>†</sup> shows the SEM image of neat g-C<sub>3</sub>N<sub>4</sub>. The introduction of Pd SAs does not affect the morphology of C<sub>3</sub>N<sub>4</sub> – both samples show a sheet-like structure with a thin layer thickness of approximately 16 nm. The high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) image of Pd SAs/g-C<sub>3</sub>N<sub>4</sub> is shown in Fig. 1b and c, which confirms the presence of individual Pd atoms (highlighted in Fig. 1c with red dots and yellow circles). Also, in the HAADF-STEM image (Fig. 1d), there are no observable Pd agglomeration on the g-C<sub>3</sub>N<sub>4</sub> surface. Energy-dispersive X-ray spectroscopy (EDX) mapping (Fig. 1e–g) further proves the uniform dispersion of Pd SAs throughout the g-C<sub>3</sub>N<sub>4</sub> structure. The density of




Fig. 1 (a) SEM image, (b) original HAADF-STEM image, (c) the HAADF-STEM image with individual Pd SAs highlighted by red dots and yellow circles, (d) HAADF-STEM image and the corresponding EDS mapping (e) C, (f) N, and (g) Pd of Pd SAs/C<sub>3</sub>N<sub>4</sub>.






Fig. 2 (a) X-ray diffraction pattern, (b–d) XPS spectra of (b) C 1s, (c) N 1s and (d) Pd 3d for  $C_3N_4$  and Pd SAs/ $C_3N_4$ , (e) XANES spectra of Pd/ $C_3N_4$  at Pd K-edge, and (f) Fourier transform extended X-ray absorption fine structure (FT-EXAFS) spectra of Pd SAs/ $C_3N_4$ .

Pd SAs was calculated as  $1.6 \times 10^6 \mu\text{m}^{-2}$  from HAADF-STEM images shown in Fig. S4.†

X-ray diffraction (XRD) patterns of  $g\text{-}C_3N_4$  and Pd SAs/ $g\text{-}C_3N_4$  are presented in Fig. 2a. Both samples display two distinct diffraction peaks at  $13^\circ$  and  $27.6^\circ$ , corresponding to the (100) and (002) crystal planes of  $g\text{-}C_3N_4$ , respectively.<sup>31</sup> Notably, no diffraction peaks related to metallic Pd are observed in the Pd SAs/ $g\text{-}C_3N_4$  sample (as is expected for the SA-decorated sample).<sup>14</sup>

X-ray photoelectron spectroscopy (XPS) was utilized to investigate the chemical state of  $g\text{-}C_3N_4$  and Pd SAs on  $C_3N_4$  (Fig. 2b–d and Table S1†). The high-resolution C 1s XPS spectrum (Fig. 2b) of both samples can be fitted by three peaks at

284.7 eV, 286.2 eV, and 288.1 eV corresponding to C–C, C–N and N–C=N of the heptazine ring carbon structure, respectively.<sup>16</sup> The fitted N 1s spectra (Fig. 2c) exhibit peaks at 398.7 eV (N1), 400 eV (N2), and 401.4 eV (N3), representing the  $sp^2$  hybridized aromatic two-coordinated (N2c) nitrogen of the triazine unit (C=N–C, *i.e.*, pyridinic N) and three coordinated (N3c) bridging N atoms connected to carbon as N–(C)<sub>3</sub> groups and amino functional (C–NH/NH<sub>x</sub>) groups respectively.<sup>16,32,33</sup> The Pd 3d spectrum of Pd SAs/ $C_3N_4$  shows two peaks (Fig. 2d), doublets at 337.6 and 342.9 eV corresponding to  $\text{Pd}^{\delta+} 3d_{5/2}$  and  $\text{Pd}^{\delta+} 3d_{3/2}$  ( $0 < \delta < 2$ ), respectively.<sup>16</sup> For comparison, Pd nanoparticles were deposited on  $g\text{-}C_3N_4$  (Pd NPs/ $C_3N_4$ ) using an established photodeposition method described in the literature.<sup>34,35</sup> SEM



images of Pd NPs/C<sub>3</sub>N<sub>4</sub> (Fig. S5†) clearly show distinct Pd nanoparticles on the C<sub>3</sub>N<sub>4</sub> surface with their typical diameter in the range of 7–15 nm. For this sample, the Pd 3d XPS spectra (Fig. S6†) of Pd NPs/C<sub>3</sub>N<sub>4</sub> exhibit doublets at 335 eV and 340 eV, which are typically attributed to metallic Pd<sup>0</sup>.<sup>33</sup>

The nature of Pd species was further investigated by X-ray absorption spectroscopy (XAS) and diffuse reflectance infrared Fourier transform spectroscopy (DRIFTS) measurements. Fig. 2e and f show the absorption near-edge structure (XANES) and extended X-ray absorption fine structure (EXAFS) spectra of Pd SAs/C<sub>3</sub>N<sub>4</sub>. The X-ray absorption spectrum of Pd SAs/C<sub>3</sub>N<sub>4</sub> measured at the Pd K-edge (24 350 eV) indicates the presence of Pd atoms that are non-metallic and carry a positive charge.<sup>15,16,20</sup> The EXAFS analysis and the corresponding Fourier transformed (FT) radial distribution function of Pd SAs/C<sub>3</sub>N<sub>4</sub> show a peak at approximately 1.5 Å (without phase correction), attributed to the Pd–N bond, and no obvious scattering is observed for the metallic Pd–Pd bonding.<sup>16,20</sup> CO-DRIFT spectra of Pd SAs/C<sub>3</sub>N<sub>4</sub> (Fig. S7†) show a CO vibrational peak at 2125 cm<sup>-1</sup>, which is characteristic of linearly bonded CO on a Pd single site (usually Pd<sup>2+</sup>).<sup>36,37</sup> These results are well in line with the XPS results, *i.e.*, Pd SAs are N-coordinated in C<sub>3</sub>N<sub>4</sub> with an oxidation state ≈ 2.

We then used the above deposition approach to place Pd SAs from Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> solutions in the concentration range of

0.0005 mM to 10 mM on C<sub>3</sub>N<sub>4</sub>. Fig. 3a shows the Pd 3d XPS spectra for these Pd SAs loaded on C<sub>3</sub>N<sub>4</sub> samples. Notably, neither metallic Pd peaks nor Cl 2p peaks (Fig. S8†) are observed under any of the deposition conditions. Instead, the incorporation of Pd SAs is evident across all samples, as indicated by the Pd 3d doublet peaks at 337.6 and 342.9 eV. The XPS data align with the SEM images shown in Fig. S9,† where no Pd nanoparticles are observed in any of the samples, even at the highest precursor concentration of 10 mM.

The bulk loading of the samples prepared using different concentrations of Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> solutions was further quantified by atomic absorption spectroscopy (AAS) – the results are shown in Table S1.† As the concentration of the Pd precursor increases, the loading of Pd SAs increases (Fig. S10†), which is consistent with the XPS data (Table S2†). For the highest precursor concentration of 10 mM, the Pd SA loading reaches 0.75 wt%.

We then examined for all samples the photocatalytic H<sub>2</sub> evolution using a 365 nm LED light source with an intensity of 65 mW cm<sup>-2</sup> and an aqueous solution of 10% triethanolamine (TEOA) as a hole scavenger.<sup>19,38,39</sup> From the results shown in Fig. 3b, it is evident that the decoration of either Pd NPs or Pd SAs significantly enhances the H<sub>2</sub> production activity compared to bare C<sub>3</sub>N<sub>4</sub>. In the concentration range of 0.0005 mM to 0.05 mM, corresponding to Pd SA loadings from 0.04 wt% to




Fig. 3 (a) Pd 3d XPS spectra of Pd SAs/C<sub>3</sub>N<sub>4</sub> at different concentrations of tetraaminepalladium chloride, (b) photocatalytic H<sub>2</sub> evolution, (c) evolved H<sub>2</sub> at different Pd SA loadings, and (d) normalized H<sub>2</sub> evolution rates for different concentrations Pd SAs using tetraaminepalladium chloride.



0.26 wt% (Fig. S10<sup>†</sup>), the photocatalytic H<sub>2</sub> production activity increases with loading (Fig. 3c). It is worth mentioning that Pd SAs deposited through our method, utilizing the Pd(NH<sub>3</sub>)Cl<sub>2</sub>-precursor, lead to the notable finding that even a minimal loading of 0.05 wt% outperforms Pd NPs synthesized *via* photodeposition, the latter having a much higher loading of 1.5 wt% (Table S2<sup>†</sup>). As a side note, this loading is also much more efficient than using PdCl<sub>2</sub> and (NH<sub>4</sub>)<sub>2</sub>PdCl<sub>6</sub> precursors (see Fig. S11<sup>†</sup>). Also, in this comparison, the photocatalytic H<sub>2</sub> production results show that an SA deposition approach using Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> leads to much higher activity, despite the significantly lower Pd loading compared with PdCl<sub>2</sub> and (NH<sub>4</sub>)<sub>2</sub>PdCl<sub>6</sub>.

In general, the data clearly show that the H<sub>2</sub> production amount increases with Pd precursor concentration loading until reaching a maximum at 0.05 mM (with a Pd SA loading of 0.26 wt%). Beyond this point, a further increase in Pd loading does not increase the activity any further but even leads to a slight drop in the activity and in the 10 mM case a very obvious decrease (Fig. 3c). This is likely due to the decrease in the density of Pd SAs and the formation of Pd agglomerates, which may increase charge recombination.<sup>40</sup>

To further assess and compare the effectiveness of Pd as a co-catalyst in both single-atom and nanoparticle forms, we normalized the data from Fig. 3b relative to Pd loading (Table S1<sup>†</sup>); the results are shown in Fig. 3d. The analysis reveals that the highest mass-specific photocatalytic efficiency, resulting in an H<sub>2</sub> production rate of 0.24 mmol h<sup>-1</sup> mg<sup>-1</sup> Pd, is achieved with 0.002 mM Pd precursor (0.05 wt%). This efficiency is 55 times higher than that obtained through conventional photodeposition of Pd nanoparticles on g-C<sub>3</sub>N<sub>4</sub>, highlighting the superiority of our reactive deposition method for optimizing photocatalytic H<sub>2</sub> production. The exceptional performance of low Pd SA loading on g-C<sub>3</sub>N<sub>4</sub>, prepared using our direct deposition method, is evident when compared to other Pd SA-loaded g-C<sub>3</sub>N<sub>4</sub> structures reported in the literature for photocatalytic H<sub>2</sub> generation. As shown in Table S3,<sup>†</sup> our work demonstrates the highest photocatalytic hydrogen evolution per Pd atom. Notably, even when compared to studies with similar or higher Pd SA loadings, the Pd SAs obtained through our reactive

deposition method using Pd(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub> exhibit the highest efficiency.

To better examine the origin of high activity of our SAs on C<sub>3</sub>N<sub>4</sub>, we evaluated the charge transfer properties of the Pd-decorated C<sub>3</sub>N<sub>4</sub> photocatalysts by electrochemical impedance spectroscopy (EIS). The measurements were performed in the 0.1 M Na<sub>2</sub>SO<sub>4</sub> electrolyte at -0.5 V *vs.* Ag/AgCl, *i.e.*, close to flat band conditions (details are outlined in the ESI-Experimental section<sup>†</sup>). Fig. 4a presents the Nyquist plots for bare g-C<sub>3</sub>N<sub>4</sub>, and g-C<sub>3</sub>N<sub>4</sub> decorated with varying amounts of Pd SAs, and g-C<sub>3</sub>N<sub>4</sub> decorated with Pd NPs (see the zoomed-in spectra shown in Fig. S12<sup>†</sup>). The Nyquist plots were fitted using the classic Randle's equivalent circuit model (inset of Fig. 4a).<sup>41,42</sup> The significantly smaller radius of the fitted curve for Pd SAs/C<sub>3</sub>N<sub>4</sub>, compared to bare C<sub>3</sub>N<sub>4</sub>, indicates a substantial reduction in charge transfer resistance (*R*<sub>ct</sub>) upon Pd SA loading. Quantitative fitting data in Table S4<sup>†</sup> show a 98-fold decrease in *R*<sub>ct</sub> due to Pd SA incorporation (already at a concentration of 0.05 mM). Fig. 4b shows the *R*<sub>ct</sub> values plotted against Pd SA loading, showing that even a minimal amount of Pd SAs (0.03 wt%) can dramatically enhance the charge transfer of C<sub>3</sub>N<sub>4</sub> to the electrolyte. This aligns with the low loading required to achieve peak efficiency in photocatalytic H<sub>2</sub> production. Conversely, Pd NPs on C<sub>3</sub>N<sub>4</sub> also reduce *R*<sub>ct</sub> compared to bare C<sub>3</sub>N<sub>4</sub> (Fig. 4b) but require a much higher loading (1.5 wt%) to achieve a similar reduction in charge transfer resistance, as compared to the Pd SA-loaded sample, which achieves this with just 0.03 wt%. PEIS measurements for all the samples were measured using a 365 nm LED (as described in the ESI Experimental section<sup>†</sup>). As shown in Fig. S13,<sup>†</sup> the results indicated a similar trend to the EIS data collected in the dark (Fig. 4 and Table S4<sup>†</sup>), although *R*<sub>ct</sub> values were different. Under illumination, *R*<sub>ct</sub> values decreased due to enhanced charge transfer dynamics in the presence of light (Fig. S13 and Table S5<sup>†</sup>). Notably, Pd SAs demonstrated lower *R*<sub>ct</sub> values compared to Pd nanoparticles, indicating the superior performance of Pd SAs. These results underscore the effectiveness of small Pd SA quantities in significantly improving the charge transfer characteristics of C<sub>3</sub>N<sub>4</sub>.




Fig. 4 (a) EIS plots of C<sub>3</sub>N<sub>4</sub>, Pd SAs/C<sub>3</sub>N<sub>4</sub> and Pd NPs/C<sub>3</sub>N<sub>4</sub> at the voltage of -0.5 V *vs.* Ag/AgCl in 0.1 M Na<sub>2</sub>SO<sub>4</sub> aqueous electrolyte. The equivalent circuit model used for fitting is depicted in the inset of (a). (b) *R*<sub>ct</sub> vs. Pd loading plot of Pd SAs/C<sub>3</sub>N<sub>4</sub> samples.



Incident photon-to-current conversion efficiency (IPCE) measurements were also conducted to assess the photoelectrochemical characteristics of  $C_3N_4$  and Pd SAs/ $C_3N_4$ . Fig. S14† shows photocurrent spectra for both samples with a photocurrent onset in the visible range. The bandgap (determined from a replot of the photocurrent data according to an indirect transition, Fig. S14-inset†) was 2.7 eV, consistent with the typical bandgap of  $g-C_3N_4$ .<sup>14,43</sup> Additionally, the photocurrent (Fig. S15†) increases after the decoration of Pd SAs on  $g-C_3N_4$  (under near flat band conditions), which confirms the beneficial effect of Pd SAs in promoting charge transfer under illumination conditions.

The enhanced performance of Pd-SAs deposited by our decoration technique, compared with the literature, must be attributed to the used precursor  $Pd(NH_3)_4^{2+}$  that leads to the direct formation of active Pd–N configurations (as confirmed by EXAFS, Fig. 2e and f) – in the literature, such sites are regarded as premier active sites in  $C_3N_4$ .<sup>16,20,44,45</sup>

The presence of  $NH_3$  groups in  $Pd(NH_3)_4^{2+}$  ions may promote the formation of such a Pd–N coordination structure compared to the chloride-coordinated Pd precursors due to suitable ligand exchange energetics.<sup>46,47</sup> Furthermore, the  $Pd^{2+}$  in  $Pd(NH_3)_4Cl_2$  enables stronger interactions with nitrogen atoms in  $C_3N_4$  than the  $Pd^{4+}$  in  $(NH_4)_2PdCl_6$  or  $Pd^{2+}$  in  $PdCl_2$ .<sup>48,49</sup> Evidently, chloro-coordinated Pd precursors in the  $Pd^{2+}$  or  $Pd^{4+}$  state are either adsorbed onto the  $C_3N_4$  surface at less specific sites, as shown by the XPS Pd 3d spectra (Fig. S1a†) and the significant presence of Cl detected in the XPS Cl 2p spectra (Fig. S1b†), or reduced and form metallic Pd agglomerates, as clearly observed in the SEM images (Fig. S2†). The tetraammonium complex, on the other hand, leads without any evident change in the reduction state to active  $Pd^{\delta+}$  ( $\delta \approx 2$ ) N-coordinated SAs, accompanied by the complete loss of Cl coordination during the reaction (Fig. S8†). Therefore,  $Pd(NH_3)_4Cl_2$  is identified as the most suitable precursor for direct reactive deposition of Pd SAs on  $C_3N_4$ .

Considering that many literature studies, particularly those involving DFT calculations, suggest that Pd in an  $N_4$ -coordination on  $C_3N_4$  exhibits the highest degree of stability and activity, one may conclude that  $Pd^{2+}$  undergoes a ligand exchange process to form this active Pd– $N_4$  configuration. This means that the process is of self-homing nature (as described for the reactive deposition of Pt)<sup>23–25,35</sup> *i.e.*, the Pd precursor reacts and deposits Pd SAs at most active surface sites on  $g-C_3N_4$ , these sites then provide a maximized electron transfer and thus are highly catalytically active. This explains why such a low loading of Pd SAs is sufficient in our work to achieve maximised photocatalytic  $H_2$  production efficiency compared to the higher Pd loadings required, as reported in most literature studies (Table S3†).<sup>14,45,49,50</sup>

The remarkable activity becomes particularly clear if the present data are compared to the work of Akinaga *et al.*,<sup>14</sup> where a 0.5 wt% Pd SA loading was required to maximize the photocatalytic  $H_2$  production activity, *i.e.*, our very low Pd SA loading of 0.05 wt% demonstrates a tenfold increase in efficiency. This superior performance highlights the importance of the attachment chemistry and process of Pd SAs within  $C_3N_4$ , *i.e.*,

processes that lead to Pd SAs located at the most active sites can lead to maximized efficiency with minimal Pd usage, avoiding the waste of Pd associated with random Pd SA or NP deposition.

## Conclusion

In this work, we successfully integrated Pd SAs onto/into exfoliated  $g-C_3N_4$  *via* a reactive deposition method, achieving a controllable uniform loading of highly active Pd SAs in a Pd–N configuration on  $g-C_3N_4$ . Notably, using reactive deposition from a  $Pd(NH_3)_4Cl_2$  precursor a low loading of 0.05 wt% Pd SAs on  $C_3N_4$  with a density of  $1.6 \times 10^6 \mu m^{-2}$  can achieve a maximum  $H_2$  production rate of  $0.24 \text{ mmol h}^{-1} \text{ mg}^{-1} \text{ Pd}$ , significantly higher than that of Pd nanoparticles decorated on  $g-C_3N_4$  and also ten times higher than that of Pd SAs decorated on  $g-C_3N_4$  using other reported approaches. Other tested precursors may also deliver SA attachment but lack the high co-catalytic activity. These results underline the importance of the attachment mechanism in creating a SA/substrate coupling with minimized charge transfer resistance and thus maximized co-catalytic activity – in a most effective way, the process is self-homing, *i.e.*, activation takes place where it is most effective.

## Data availability

The data that support the findings of this study are available within the article and ESI.†

## Author contributions

Velu Jeyalakshmi conducted the majority of the experimental work, including synthesis, characterization, data analysis, and drafting of the manuscript. Siming Wu contributed significantly to data analysis and revision of the original draft. Shanshan Qin participated in data analysis, while Xin Zhou performed HAADF-STEM analysis. Bidyut Bikash Sarma and Dimitry E. Doronkin conducted XAS and EXAFS analyses and Jan Kolařík carried out AAS analysis. Miroslav Šoos supervised the experiments and managed funding acquisition. Patrik Schmuki conceived the idea, supervised the experiments, analyzed the data, revised the manuscript, and secured funding. All authors contributed to the preparation of the manuscript and approved the final manuscript.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research was supported by the Johannes Amos Comenius Programme, European Structural and Investment Funds, project 'CHEMFELLS VI (No. CZ.02.01.01/00/22\_010/0008122). The authors would like to acknowledge DFG and the Operational Program Research, Development and Education (European Regional Development Fund Project No. CZ.02.1.01/0.0/0.0/15\_003/0000416 of the Ministry of Education, Youth and



Sports of the Czech Republic). P. S. particularly thanks the GA CR-EXPRO Project (Grant No. 23-08019X) from the Czech Science Foundation for financial support. We acknowledge DESY (Hamburg, Germany), a member of the Helmholtz Association HGF, for the provision of experimental facilities. Parts of this research were carried out at the light source PETRA III at DESY, a member of the Helmholtz Association (HGF). We would like to thank Dr Edmund Welter for his assistance in using the beamline P65. Beam time was allocated for the proposal II-20230692. The authors would also like to acknowledge the support of the Center for Nanoanalysis and Electron Microscopy (CENEM, Friedrich-Alexander-Universität Erlangen-Nürnberg).

## References

- 1 Y. Li and S. C. E. Tsang, Recent progress and strategies for enhancing photocatalytic water splitting, *Mater. Today Sustain.*, 2020, **9**, 100032.
- 2 S. Nishioka, F. E. Osterloh, X. Wang, T. E. Mallouk and K. Maeda, Photocatalytic water splitting, *Nat. Rev. Methods Primers*, 2023, **3**, 42.
- 3 K. Nakata and A. Fujishima, TiO<sub>2</sub> photocatalysis: design and applications, *J. Photochem. Photobiol., C*, 2012, **13**, 169–189.
- 4 P. Roy, S. Berger and P. Schmuki, TiO<sub>2</sub> nanotubes: synthesis and applications, *Angew. Chem., Int. Ed.*, 2011, **50**, 2904–2939.
- 5 S. Peiris, H. B. de Silva, K. N. Ranasinghe, S. V. Bandara and I. R. Perera, Recent development and future prospects of TiO<sub>2</sub> photocatalysis, *J. Chin. Chem. Soc.*, 2021, **68**, 738–769.
- 6 M. D. Hernández-Alonso, F. Fresno, S. Suárez and J. M. Coronado, Development of alternative photocatalysts to TiO<sub>2</sub>: challenges and opportunities, *Energy Environ. Sci.*, 2009, **2**, 1231–1257.
- 7 D. Bhandari, P. Lakhani and C. K. Modi, Graphitic carbon nitride (g-C<sub>3</sub>N<sub>4</sub>) as an emerging photocatalyst for sustainable environmental applications: a comprehensive review, *RSC sustain.*, 2024, **2**, 265–287.
- 8 Q. Wang, Y. Li, F. Huang, S. Song, G. Ai, X. Xin, B. Zhao, Y. Zheng and Z. Zhang, Recent advances in g-C<sub>3</sub>N<sub>4</sub>-based materials and their application in energy and environmental sustainability, *Molecules*, 2023, **28**, 432.
- 9 J. Pei, H. Li, S. Zhuang, D. Zhang and D. Yu, Recent Advances in g-C<sub>3</sub>N<sub>4</sub> Photocatalysts: A Review of Reaction Parameters, Structure Design and Exfoliation Methods, *Catalysts*, 2023, **13**, 1402.
- 10 Y. Zheng, Y. Jiao, M. Jaroniec and S. Z. Qiao, Advancing the electrochemistry of the hydrogen-evolution reaction through combining experiment and theory, *Angew. Chem., Int. Ed.*, 2015, **54**, 52–65.
- 11 C. Gao, J. Low, R. Long, T. Kong, J. Zhu and Y. Xiong, Heterogeneous single-atom photocatalysts: fundamentals and applications, *Chem. Rev.*, 2020, **120**, 12175–12216.
- 12 Y. Xia, M. Sayed, L. Zhang, B. Cheng and J. Yu, Single-atom heterogeneous photocatalysts, *Chem Catal.*, 2021, **1**, 1173–1214.
- 13 U. Kerketta, A. B. Tesler and P. Schmuki, Single-atom Cocatalysts employed in titanium dioxide photocatalysis, *Catalysts*, 2022, **12**, 1223.
- 14 Y. Akinaga, T. Kawawaki, H. Kameko, Y. Yamazaki, K. Yamazaki, Y. Nakayasu, K. Kato, Y. Tanaka, A. T. Hanindriyo and M. Takagi, Metal Single-Atom Cocatalyst on Carbon Nitride for the Photocatalytic Hydrogen Evolution Reaction: Effects of Metal Species, *Adv. Funct. Mater.*, 2023, **33**, 2303321.
- 15 X. Jia, J. Zhao, W. Zhang, X. Fu, J. Long, Q. Gu and Z. Gao, Single-Atomic Pd Embedded 2D g-C<sub>3</sub>N<sub>4</sub> Homogeneous Catalyst Analogues for Efficient LMCT Induced Full-Visible-Light Photocatalytic Suzuki Coupling, *ChemistrySelect*, 2022, **7**, e202202973.
- 16 F. Hu, L. Leng, M. Zhang, W. Chen, Y. Yu, J. Wang, J. H. Horton and Z. Li, Direct synthesis of atomically dispersed palladium atoms supported on graphitic carbon nitride for efficient selective hydrogenation reactions, *ACS Appl. Mater. Interfaces*, 2020, **12**, 54146–54154.
- 17 Z. Chen, S. Mitchell, E. Vorobyeva, R. K. Leary, R. Hauert, T. Furnival, Q. M. Ramasse, J. M. Thomas, P. A. Midgley and D. Dontsova, Stabilization of single metal atoms on graphitic carbon nitride, *Adv. Funct. Mater.*, 2017, **27**, 1605785.
- 18 R. Xu, B. Xu, X. You, D. Shao, G. Gao, F. Li, X.-L. Wang and Y.-F. Yao, Preparation of single-atom palladium catalysts with high photocatalytic hydrogen production performance by means of photochemical reactions conducted with frozen precursor solutions, *J. Mater. Chem. A*, 2023, **11**, 11202–11209.
- 19 M. Ren, X. Zhang, Y. Liu, G. Yang, L. Qin, J. Meng, Y. Guo and Y. Yang, Interlayer palladium-single-atom-coordinated cyano-group-rich graphitic carbon nitride for enhanced photocatalytic hydrogen production performance, *ACS Catal.*, 2022, **12**, 5077–5093.
- 20 S. Cao, H. Li, T. Tong, H. C. Chen, A. Yu, J. Yu and H. M. Chen, Single-atom engineering of directional charge transfer channels and active sites for photocatalytic hydrogen evolution, *Adv. Funct. Mater.*, 2018, **28**, 1802169.
- 21 P. Suja, J. John, T. Rajan, G. M. Anilkumar, T. Yamaguchi, S. C. Pillai and U. Hareesh, Graphitic carbon nitride (gC<sub>3</sub>N<sub>4</sub>) based heterogeneous single atom catalysts: synthesis, characterisation and catalytic applications, *J. Mater. Chem. A*, 2023, **11**, 8599–8646.
- 22 S. Li, Z. Kan, H. Wang, J. Bai, Y. Liu, S. Liu and Y. Wu, Single-atom photo-catalysts: synthesis, characterization, and applications, *Nano Mater. Sci.*, 2023, 284–304.
- 23 S. M. Wu and P. Schmuki, Single Atom Cocatalysts in Photocatalysis, *Adv. Mater.*, 2024, 2414889.
- 24 Y. Wang, S. Qin, N. Denisov, H. Kim, Z. Bad'ura, B. B. Sarma and P. Schmuki, Reactive Deposition Versus Strong Electrostatic Adsorption (SEA): A Key to Highly Active Single Atom Co-Catalysts in Photocatalytic H<sub>2</sub> Generation, *Adv. Mater.*, 2023, **35**, 2211814.
- 25 S. Qin, J. Will, H. Kim, N. Denisov, S. Carl, E. Spiecker and P. Schmuki, Single atoms in photocatalysis: low loading is good enough, *ACS Energy Lett.*, 2023, **8**, 1209–1214.



- 26 G. Cha, A. Mazare, I. Hwang, N. Denisov, J. Will, T. Yokosawa, Z. Badura, G. Zoppellaro, A. B. Tesler and E. Spiecker, A facile “dark”-deposition approach for Pt single-atom trapping on faceted anatase TiO<sub>2</sub> nanoflakes and use in photocatalytic H<sub>2</sub> generation, *Electrochim. Acta*, 2022, **412**, 140129.
- 27 Z. Wu, I. Hwang, G. Cha, S. Qin, O. Tomanec, Z. Badura, S. Kment, R. Zboril and P. Schmuki, Optimized Pt single atom harvesting on TiO<sub>2</sub> nanotubes—Towards a most efficient photocatalyst, *Small*, 2022, **18**, 2104892.
- 28 A. Torres-Pinto, M. J. Sampaio, C. G. Silva, J. L. Faria and A. M. Silva, Metal-free carbon nitride photocatalysis with in situ hydrogen peroxide generation for the degradation of aromatic compounds, *Appl. Catal., B*, 2019, **252**, 128–137.
- 29 C. Marchal, T. Cottineau, M. G. Méndez-Medrano, C. Colbeau-Justin, V. Caps and V. Keller, Au/TiO<sub>2</sub>-gC<sub>3</sub>N<sub>4</sub> nanocomposites for enhanced photocatalytic H<sub>2</sub> production from water under visible light irradiation with very low quantities of sacrificial agents, *Adv. Energy Mater.*, 2018, **8**, 1702142.
- 30 M. Karimi-Nazarabad, H. Ahmadzadeh and E. K. Goharshadi, Porous perovskite-lanthanum cobaltite as an efficient cocatalyst in photoelectrocatalytic water oxidation by bismuth doped g-C<sub>3</sub>N<sub>4</sub>, *Sol. Energy*, 2021, **227**, 426–437.
- 31 F. Fina, S. K. Callear, G. M. Carins and J. T. Irvine, Structural investigation of graphitic carbon nitride via XRD and neutron diffraction, *Chem. Mater.*, 2015, **27**, 2612–2618.
- 32 N. Wang, J. Wang, J. Hu, X. Lu, J. Sun, F. Shi, Z.-H. Liu, Z. Lei and R. Jiang, Design of palladium-doped g-C<sub>3</sub>N<sub>4</sub> for enhanced photocatalytic activity toward hydrogen evolution reaction, *ACS Appl. Energy Mater.*, 2018, **1**, 2866–2873.
- 33 L. Li, X. Dai, M. Lu, C. Guo, S. M. Wabaidur, X.-L. Wu, Z. Lou, Y. Zhong and Y. Hu, Electron-enriched single-Pd-sites on g-C<sub>3</sub>N<sub>4</sub> nanosheets achieved by in-situ anchoring twinned Pd nanoparticles for efficient CO<sub>2</sub> photoreduction, *Adv. Powder Mater.*, 2024, **3**, 100170.
- 34 S. Mondal, L. Sahoo, M. Banoo, Y. Vaishnav, C. Prabhakaran Vinod and U. K. Gautam, Enhancing the Catalytic Activity of Pd Nanocrystals towards Suzuki Cross-Coupling by g-C<sub>3</sub>N<sub>4</sub> Photosensitization, *ChemNanoMat*, 2024, **10**, e202300451.
- 35 S.-M. Wu, L. Wu, N. Denisov, Z. Badura, G. Zoppellaro, X.-Y. Yang and P. Schmuki, Pt Single Atoms on TiO<sub>2</sub> Can Catalyze Water Oxidation in Photoelectrochemical Experiments, *J. Am. Chem. Soc.*, 2024, 16363–16368.
- 36 P. Liu, Z. Huang, X. Gao, X. Hong, J. Zhu, G. Wang, Y. Wu, J. Zeng and X. Zheng, Synergy between palladium single atoms and nanoparticles via hydrogen spillover for enhancing CO<sub>2</sub> photoreduction to CH<sub>4</sub>, *Adv. Mater.*, 2022, **34**, 2200057.
- 37 P. H. Ho, J.-W. Woo, R. F. Ilmasani, J. Han and L. Olsson, The role of Pd–Pt interactions in the oxidation and sulfur resistance of bimetallic Pd–Pt/γ-Al<sub>2</sub>O<sub>3</sub> diesel oxidation catalysts, *Ind. Eng. Chem. Res.*, 2021, **60**, 6596–6612.
- 38 M. Wang, S. Shen, L. Li, Z. Tang and J. Yang, Effects of sacrificial reagents on photocatalytic hydrogen evolution over different photocatalysts, *J. Mater. Sci.*, 2017, **52**, 5155–5164.
- 39 V. Kumaravel, M. D. Imam, A. Badreldin, R. K. Chava, J. Y. Do, M. Kang and A. Abdel-Wahab, Photocatalytic hydrogen production: role of sacrificial reagents on the activity of oxide, carbon, and sulfide catalysts, *Catalysts*, 2019, **9**, 276.
- 40 N. Denisov, S. Qin, J. Will, B. N. Vasiljevic, N. V. Skorodumova, I. A. Pašti, B. B. Sarma, B. Osuagwu, T. Yokosawa and J. Voss, Light-Induced Agglomeration of Single-Atom Platinum in Photocatalysis, *Adv. Mater.*, 2023, **35**, 2206569.
- 41 J. E. B. Randles, Kinetics of rapid electrode reactions, *Discuss. Faraday Soc.*, 1947, **1**, 11–19.
- 42 Z. Wang, A. Murphy, A. O’Riordan and I. O’Connell, Equivalent impedance models for electrochemical nanosensor-based integrated system design, *Sensors*, 2021, **21**, 3259.
- 43 X. Wang, K. Maeda, A. Thomas, K. Takanabe, G. Xin, J. M. Carlsson, K. Domen and M. Antonietti, A metal-free polymeric photocatalyst for hydrogen production from water under visible light, *Nat. Mater.*, 2009, **8**, 76–80.
- 44 G. Vilé, D. Albani, M. Nachtegaal, Z. Chen, D. Dontsova, M. Antonietti, N. López and J. Pérez-Ramírez, Ein stabiler “Single-site”-Palladiumkatalysator für Hydrierungen, *Angew. Chem.*, 2015, **127**, 11417–11422.
- 45 L. Liu, X. Wu, L. Wang, X. Xu, L. Gan, Z. Si, J. Li, Q. Zhang, Y. Liu, Y. Zhao and R. Ran, Atomic palladium on graphitic carbon nitride as a hydrogen evolution catalyst under visible light irradiation, *Commun. Chem.*, 2019, **2**(1), 18, DOI: [10.1038/s42004-019-0117-4](https://doi.org/10.1038/s42004-019-0117-4).
- 46 A. Ryabov, G. Kazankov, A. Yatsimirskii, L. Kuz'mina, O. Y. Burtseva, N. Dvortsova and V. Polyakov, Synthesis by ligand exchange, structural characterization, and aqueous chemistry of ortho-palladated oximes, *Inorg. Chem.*, 1992, **31**, 3083–3090.
- 47 P. Maitlis, *Metal Complexes: The Organic Chemistry of Palladium*, Elsevier, 2012, pp. 1–103.
- 48 L. Pazderski, <sup>15</sup>N NMR coordination shifts in Pd (II), Pt (II), Au (III), Co (III), Rh (III), Ir (III), Pd (IV), and Pt (IV) complexes with pyridine, 2, 2'-bipyridine, 1, 10-phenanthroline, quinoline, isoquinoline, 2, 2'-biquinoline, 2, 2': 6', 2'-terpyridine and their alkyl or aryl derivatives, *Magn. Reson. Chem.*, 2008, **46**, S3–S15.
- 49 N. Wang, J. Wang, J. Hu, X. Lu, J. Sun, F. Shi, Z.-H. Liu, Z. Lei and R. Jiang, Design of Palladium-Doped g-C<sub>3</sub>N<sub>4</sub> for Enhanced Photocatalytic Activity toward Hydrogen Evolution Reaction, *ACS Appl. Energy Mater.*, 2018, **1**(6), 2866–2873, DOI: [10.1021/acsaeam.8b00526](https://doi.org/10.1021/acsaeam.8b00526).
- 50 R. Xu, B. Xu, X. You, D. Shao, G. Gao, F. Li, X.-L. Wang and Y.-F. Yao, Preparation of single-atom palladium catalysts with high photocatalytic hydrogen production performance by means of photochemical reactions conducted with frozen precursor solutions, *J. Mater. Chem. A*, 2023, **11**(21), 11202–11209.

