

## RESEARCH ARTICLE

View Article Online  
View Journal | View IssueCite this: *Mater. Chem. Front.*,  
2023, 7, 1617Forming a composite electron blocking layer  
to enhance the performance of carbon-based  
CsPbI<sub>3</sub> perovskite solar cells†Yongfa Song,<sup>a</sup> Weiping Li,<sup>id</sup>\*<sup>a</sup> Hailiang Wang,<sup>a</sup> Huicong Liu,<sup>id</sup><sup>a</sup> Yue Deng,<sup>a</sup>  
Qixian Zhang,<sup>a</sup> Han Rao,<sup>a</sup> Xiaoyu Jiang\*<sup>b</sup> and Haining Chen<sup>id</sup>\*<sup>a</sup>

Carbon-based CsPbI<sub>3</sub> perovskite solar cells (C-PSCs) have attracted much interest due to their high chemical stability. However, their efficiency still largely lags behind those achieved by conventional CsPbI<sub>3</sub> PSCs because of the electron back transfer from the perovskite to the carbon electrode. Herein, we address the above issue by forming a composite electron blocking layer at the CsPbI<sub>3</sub>/carbon interface. The CsPbCl<sub>3</sub> quantum dots (QDs) layer is first deposited on the CsPbI<sub>3</sub> film by spin coating a QDs solution, while the Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> nanosheets are then generated on the surface by the post treatment of a CsCl solution. The composite blocking layer not only well suppresses electron back transfer but also passivates crystal defects. As a result, the efficiency of CsPbI<sub>3</sub> C-PSCs is boosted from 12.51% to 16.10%.

Received 1st November 2022,  
Accepted 3rd February 2023

DOI: 10.1039/d2qm01124g

rsc.li/frontiers-materials

## Introduction

Perovskite solar cells (PSCs) have attracted intense attention in the past few years due to their high power conversion efficiency (PCE) based on solution-based processes.<sup>1–6</sup> However, their low stability has greatly inhibited the commercial application of PSCs.<sup>7–10</sup> Generally, their low stability mainly originates from the use of organic-inorganic hybrid perovskites, made from organic hole transport materials (HTMs) and metal electrodes.<sup>11–13</sup> After replacing the HTM and metal electrode with a carbon electrode, carbon-based PSCs (C-PSCs) are made, and the device stability could be well improved because carbon materials are stable, inert to ion migration and inherently H<sub>2</sub>O-resistant.<sup>14–19</sup>

Although C-PSCs have shown obvious enhancement in device stability, the organic components in organic-inorganic hybrid perovskites can be easily removed from the crystal structure, which still limits the device stability. In order to address the issue, researchers have introduced inorganic perovskites to replace the organic-inorganic hybrid perovskites as light absorbers in C-PSCs.<sup>20–25</sup> Among various inorganic perovskites, CsPbI<sub>3</sub> has shown great prospects due to the suitable bandgap of 1.73 eV.<sup>26–32</sup> So far, great progress has been made on CsPbI<sub>3</sub> C-PSCs and over 16% PCE has been achieved.<sup>33</sup>

However, the above PCE still largely lags behind those achieved by the conventional CsPbI<sub>3</sub> PSCs (about 21%).<sup>34</sup> The low hole selectivity of the carbon electrode is the main cause because the photogenerated electrons tend to transfer to the carbon electrode for inducing serious recombination loss.<sup>11,35</sup> To suppress the electron back transport, forming an electron blocking layer at the CsPbI<sub>3</sub>/carbon interface has been employed.<sup>36–38</sup> For example, phenylethylamine iodide (PEAI)<sup>39</sup> or CsCl<sup>40</sup> have been used to treat the CsPbI<sub>3</sub> layer to grow a 2D perovskite layer *in situ* acting as an electron blocking layer. However, the performance improvement is still limited for a single electron blocking layer and a new strategy is needed.

Herein, both CsPbCl<sub>3</sub> QDs and 2D Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> were deposited on the CsPbI<sub>3</sub> perovskite layer to form a composite electron blocking layer. Firstly, CsPbCl<sub>3</sub> QDs were spin coated on the CsPbI<sub>3</sub> perovskite layer by using a CsPbCl<sub>3</sub> QDs cyclohexane solution. Then, a CsCl ethanol solution was also spin coated on the QDs-coated CsPbI<sub>3</sub> perovskite layer to form 2D Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub>. Such architecture forms a favorable energy level alignment for electron blocking. In addition, crystal defects were also effectively passivated. As a result, the PCE of CsPbI<sub>3</sub> C-PSCs was promoted from 12.51% to 16.10%.

## Results and discussion

The CsPbCl<sub>3</sub> QDs were synthesized using the thermal injection method described in the Experimental section.<sup>41,42</sup> The TEM image in Fig. S1a (ESI†) shows that the CsPbCl<sub>3</sub> QDs have a regular square structure with a size of about 12 nm. The X-ray

<sup>a</sup> No. 37 Xueyuan Road, Haidian District, Beijing 100191, People's Republic of China. E-mail: liweiping@buaa.edu.cn, chenaining@buaa.edu.cn

<sup>b</sup> Beijing 100072, People's Republic of China. E-mail: jiangxiaoyu2007@gmail.com

† Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d2qm01124g>

diffraction (XRD) pattern in Fig. S1b (ESI<sup>†</sup>) indicates that all diffraction peaks match well with the tetragonal structure of the CsPbCl<sub>3</sub> perovskite (JCPDS 18-0366).<sup>19</sup> Therefore, CsPbCl<sub>3</sub> QDs have been successfully prepared.

For preparing the CsPbI<sub>3</sub> perovskite films, a precursor solution containing CsI, PbI<sub>2</sub> and DMAI was spin coated on the TiO<sub>2</sub> substrate, followed by annealing at 220 °C for 5 min. After the deposition of the CsPbI<sub>3</sub> perovskite films, three kinds of samples were obtained by the processes illustrated in Fig. 1. For the CsPbI<sub>3</sub>-CsCl film, the as-deposited CsPbI<sub>3</sub> perovskite films were treated with a CsCl ethanol solution (1 mg ml<sup>-1</sup>) by spin coating. For the CsPbI<sub>3</sub>-QDs film, a CsPbCl<sub>3</sub> QDs cyclohexane solution was spin-coated on the as-deposited CsPbI<sub>3</sub> perovskite film. For the CsPbI<sub>3</sub>-QDs/CsCl film, the as-deposited CsPbI<sub>3</sub> perovskite films were successively treated with a CsPbCl<sub>3</sub> QDs solution and CsCl solution.

Scanning electron microscopy (SEM) was employed to evaluate the film morphology (Fig. 2 and Fig. S2, ESI<sup>†</sup>). The control CsPbI<sub>3</sub> film exhibits uniform morphology (Fig. 2a). 2D nanosheets estimated to be around 200–350 nm in width appear on the surface of the CsPbI<sub>3</sub>-CsCl film (Fig. 2b and f). They are uniformly distributed on the surface and are perpendicular to the surface of the perovskite film. The CsPbCl<sub>3</sub> QDs are uniformly distributed on the surface of the QDs film after spin-coating the CsPbCl<sub>3</sub> QDs solution (Fig. 2c and g). After depositing the CsPbCl<sub>3</sub> QDs, the CsPbI<sub>3</sub>-QDs film show a denser and more uniform surface morphology. For the CsPbI<sub>3</sub>-QDs/CsCl film, the CsPbCl<sub>3</sub> QDs are uniformly dispersed and 2D nanosheets are also generated on the surface, forming a 2D/0D electron blocking layer. Atomic force microscopy (AFM) was further used to reveal the morphology change. The roughness of the QDs film is reduced from 41.8 to 28.6 nm compared with control CsPbI<sub>3</sub> film, while the roughness of the CsPbI<sub>3</sub>-QDs/CsCl film is reduced from 72.5 to 48.1 nm compared with the control CsCl film, indicating that the CsPbCl<sub>3</sub> QDs are more easily deposited at the grain boundary and reduce the surface

roughness, which is conducive to the contact between CsPbI<sub>3</sub> and the carbon electrode.

The X-ray diffraction (XRD) patterns in Fig. 3a reveal that the control CsPbI<sub>3</sub> film exhibits two intense peaks at 14.3° and 28.8°, which are assignable to the (110) and (220) peaks of the CsPbI<sub>3</sub> perovskite, respectively. After post treatment with CsCl solution, an additional peak is observed at 9.5°. As reported in our previous work, this peak corresponds to the (002) plane of 2D Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub>, resulting from the reaction between CsCl and CsPbI<sub>3</sub>.<sup>40,43</sup> For the CsPbI<sub>3</sub>-QDs film, the peak corresponding to CsPbCl<sub>3</sub> appear. As expected, both Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> and CsPbCl<sub>3</sub> peaks are found for the CsPbI<sub>3</sub>-QDs/CsCl films. For more detailed observations in Fig. S3 (ESI<sup>†</sup>), the characteristic peaks of CsPbI<sub>3</sub> perovskite shift to a larger angle after QDs or CsCl treatment, implying the partial replacement of I<sup>-</sup> ions with Cl<sup>-</sup> ions.<sup>44,45</sup>

X-ray photoelectron spectroscopy (XPS) measurements were further carried out to evaluate the composition of different CsPbI<sub>3</sub> films. As shown in Fig. S4 (ESI<sup>†</sup>), compared with the control CsPbI<sub>3</sub> film, the characteristic peaks of Cl 2p appeared in the CsPbI<sub>3</sub>-CsCl, -QDs and -QDs/CsCl films,<sup>45,46</sup> indicating that Cl has been incorporated after post treatment. Due to the difference in the chemical environment of the Cl element, compared with the CsPbI<sub>3</sub>-CsCl film, the Cl 2p peak shifts to a lower binding energy for the CsPbI<sub>3</sub>-QDs film. As expected, the Cl 2p in the CsPbI<sub>3</sub>-QDs/CsCl films can be deconvoluted into two sets of Cl 2p peaks, corresponding to the presence of CsPbCl<sub>3</sub> QDs and Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> nanosheets. Similarly, the Pb 4f peaks can also be deconvoluted into two sets of Pb 4f peaks. (Fig. 2d).

Ultraviolet-visible (UV-Vis) absorption spectra were subsequently measured for different films. As shown in Fig. 4a, the pristine CsPbI<sub>3</sub> film shows the absorption onset at around 741 nm. Due to the partial replacement of I with Cl, the absorption onset of the CsPbI<sub>3</sub>-CsCl film blue shifts to about 737 nm. Similarly, a blue shift is also observed for the absorption onset of the CsPbI<sub>3</sub>-QDs film (about 735 nm). More




Fig. 1 Schematic illustrating the deposition processes of the CsPbI<sub>3</sub>-CsCl, CsPbI<sub>3</sub>-QDs and CsPbI<sub>3</sub>-QDs/CsCl films.




Fig. 2 SEM images of the (e and a) control, (b and f)  $\text{CsPbI}_3\text{-CsCl}$ , (c and g)  $\text{CsPbI}_3\text{-QDs}$ , and (d and h)  $\text{CsPbI}_3\text{-QDs/CsCl}$  films; AFM images of different perovskite films: (i)  $\text{CsPbI}_3$ , (j)  $\text{CsPbI}_3\text{-CsCl}$ , (k)  $\text{CsPbI}_3\text{-QDs}$ , and (l)  $\text{CsPbI}_3\text{-QDs/CsCl}$  films.




Fig. 3 (a) XRD patterns and (b) magnified XRD patterns (in the  $2\theta$  ranges of  $8\text{--}10^\circ$ ) of different  $\text{CsPbI}_3$  films. XPS spectra of (c) Cl 2p and (d) Pb 4f for different  $\text{CsPbI}_3$  films.

obviously, the absorption onset of the  $\text{CsPbI}_3\text{-QDs/CsCl}$  film (ESI<sup>†</sup>),  $E_g$  for the pristine  $\text{CsPbI}_3$ ,  $\text{CsPbI}_3\text{-CsCl}$ ,  $\text{CsPbI}_3\text{-QDs}$  and  $\text{CsPbI}_3\text{-QDs/CsCl}$  films are calculated to be 1.671, 1.683, 1.686




Fig. 4 (a) UV-Vis, (b) TRPL spectra, (c) architecture of the electro-only device for SCLC, and (d) SCLC results for different CsPbI<sub>3</sub> films.

and 1.688 eV, respectively. The confocal PL mappings in Fig. S6 (ESI<sup>†</sup>) further confirm the above phenomenon.

Time-resolved photoluminescence decay (TRPL) spectra were also taken for different films (Fig. 4b). By fitting the TRPL spectra with a double exponential decay model, the average lifetime ( $\tau_{\text{ave}}$ ) of the different films could be calculated. As shown in Table S1 (ESI<sup>†</sup>), the  $\tau_{\text{ave}}$  of the control CsPbI<sub>3</sub> film is 8.87 ns, while the  $\tau_{\text{ave}}$  of the CsPbI<sub>3</sub>-CsCl, -QDs and -QDs/CsCl films are obviously increased to 40.60 ns, 38.94 ns and 60.24 ns, respectively. Therefore, post treatment has well prolonged the carrier lifetime due to the reduced defect density, especially for the CsPbI<sub>3</sub>-QDs/CsCl film.<sup>47</sup>

Space charge limited current (SCLC) measurements were performed by constructing an electron-only device of FTO/TiO<sub>2</sub>/CsPbI<sub>3</sub>/PCBM/C (Fig. 4c). According to the dark  $J$ - $V$  curve (Fig. 4d), the trap density ( $n_t$ ) can be calculated by the trap-filled limit voltage ( $V_{\text{TFL}}$ ).

$$n_t = 2\varepsilon_0\varepsilon V_{\text{TFL}}/ed^2 \quad (1)$$

where  $\varepsilon_0$  is the vacuum dielectric constant,  $\varepsilon$  is the relative dielectric constant of perovskite,  $d$  is the film thickness,  $e$  is the basic charge, and  $n_t$  is the density of trapped states.<sup>48</sup> The trap density values were calculated to be  $1.807 \times 10^{15}$ ,  $1.361 \times 10^{15}$ ,  $1.564 \times 10^{15}$  and  $1.266 \times 10^{15} \text{ cm}^{-3}$  for the pristine CsPbI<sub>3</sub>, CsPbI<sub>3</sub>-CsCl, CsPbI<sub>3</sub>-QDs and CsPbI<sub>3</sub>-QDs/CsCl films, respectively. Therefore, the SCLC results further confirm that the post treatment processes have well reduced the trap density, especially for the CsPbI<sub>3</sub>-QDs/CsCl film.

CsPbI<sub>3</sub> C-PSCs were fabricated by directly painting commercial carbon paste on the perovskite films, followed by annealing 120 °C (Fig. 5a). All processes were carried out in dry air. Fig. 5b show the architecture of the CsPbI<sub>3</sub> C-PSCs: FTO/c-TiO<sub>2</sub>/m-TiO<sub>2</sub>/CsPbI<sub>3</sub>/carbon and the cross-sectional SEM image in Fig. 5c indicates the close contact at the CsPbI<sub>3</sub>/carbon interface. The current density-voltage ( $J$ - $V$ ) curves in Fig. 5d and Table S2 (ESI<sup>†</sup>) indicate that the control device achieves a PCE of 12.51% with a  $V_{\text{oc}}$  of 1.081 V,  $J_{\text{sc}}$  of 16.46 mA cm<sup>-2</sup> and FF of 0.703. After treatment with CsCl, the CsPbI<sub>3</sub>-CsCl PSCs device displays a PCE of 13.65% with a  $V_{\text{oc}}$  of 1.099,  $J_{\text{sc}}$  of 17.67 mA cm<sup>-2</sup> and FF of 0.703. The CsPbI<sub>3</sub>-QDs device displays a PCE of 14.18% with a  $V_{\text{oc}}$  of 1.105,  $J_{\text{sc}}$  of 18.14 mA cm<sup>-2</sup> and FF of 0.708. Interestingly, the PCE of the CsPbI<sub>3</sub>-QDs/CsCl device is significantly improved to 16.10% with a  $V_{\text{oc}}$  of 1.137 V,  $J_{\text{sc}}$  of 18.74 mA cm<sup>-2</sup> and FF of 0.755, respectively. As noted, the large improvement in the PCE for the CsPbI<sub>3</sub>-QDs/CsCl device is mainly attributed to the increase in  $V_{\text{oc}}$  and FF, which should originate from the improvement in energy level alignment and the reduction in the surface roughness. The  $J$ - $V$  curves obtained from forward and reverse scans (Fig. S7, ESI<sup>†</sup>) and the steady-state power output for the CsPbI<sub>3</sub>-QDs/CsCl device demonstrate the small hysteresis and stable power output (Fig. S7, ESI<sup>†</sup>). The device stability was tested at 85 °C in N<sub>2</sub> conditions (Fig. S8, ESI<sup>†</sup>). The QDs/CsCl device maintains over 95% of its initial PCE after 140 h, while the PCE of the pristine device declines to about 84%.

Mott-Schottky (M-S) plots (Fig. 5e) were taken for different devices to obtain the built-in potential ( $V_{\text{bi}}$ ). The  $V_{\text{bi}}$  for the




Fig. 5 Schematic diagram of (a) the fabrication process of carbon electrode and (b) device structure; (c) cross-section SEM image of CsPbI<sub>3</sub> C-PSCs; (d)  $J-V$  curves, (e) Mott-Schottky plots obtained at 10 kHz, (f) TPV, (g) dependence of  $V_{oc}$  on  $I$ , and (h) dependence of  $J_{sc}$  on  $I$  for different devices; (i) Energy level diagrams of the CsPbI<sub>3</sub>-QDs/CsCl C-PSCs.

pristine CsPbI<sub>3</sub> device is calculated to be about 1.06 V. After post treatment, all devices show increased  $V_{bi}$  and the highest  $V_{bi}$  of 1.26 V is achieved for the CsPbI<sub>3</sub>-QDs/CsCl device. The higher  $V_{bi}$  provides a larger driving force for carrier separation and collection, which is favorable for achieving higher  $V_{oc}$  and FF. The transient photo-voltage decay (TPV) results in Fig. 5f indicate that the CsPbI<sub>3</sub>-QDs/CsCl device shows the slowest decay, further proving the most effective charge separation and the least charge recombination. The dark  $J-V$  curves of the pristine and QDs/CsCl devices are shown in Fig. S9 (ESI<sup>†</sup>). The QDs/CsCl device exhibits a much lower dark current density compared with the pristine device under a positive bias voltage, indicating that in the QDs/CsCl device the composite electron blocking layer well suppressed the back transfer of electrons from the perovskite to the carbon electrode.

The light intensity dependence of  $J_{sc}$  and  $V_{oc}$  are shown in Fig. 5g and h, respectively. The recombination mechanism can be understood according to eqn (2) and (3).

$$J_{sc} \propto I^{\alpha} \quad (\alpha \leq 1) \quad (2)$$

$$V_{oc} = \varepsilon(K_B T/e) \ln(I) + \text{constant} \quad (3)$$

where  $I$  is the light intensity,  $\alpha$  is the exponential factor,  $\varepsilon$  is the ideality factor,  $K_B$  is the Boltzmann constant,  $T$  is the absolute temperature and the  $e$  is elementary charge. The  $\alpha$  values are fitted and calculated to be 0.97, 0.96, 0.96 and 0.96 for the CsPbI<sub>3</sub>, CsPbI<sub>3</sub>-CsCl, CsPbI<sub>3</sub>-QDs and CsPbI<sub>3</sub>-QDs/CsCl devices, respectively. The  $\alpha$  values closer to 1, indicate more effective charge separation and lower nonradiative recombination. The  $\varepsilon$  for the control CsPbI<sub>3</sub>, CsPbI<sub>3</sub>-CsCl, -QDs and -QDs/CsCl devices are calculated to be 1.79, 1.40, 1.53 and 1.28, respectively, which demonstrates that trap-assisted recombination has been well suppressed in the CsPbI<sub>3</sub>-QDs/CsCl device.

## Conclusion

We have formed a composite electron blocking layer (CsPbCl<sub>3</sub> QDs/Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub>) on the CsPbI<sub>3</sub> film structure by successively treating the film with CsPbCl<sub>3</sub> QDs and CsCl solutions. Such architecture forms a favorable energy level alignment for electron blocking. Furthermore, the crystal defects of the CsPbI<sub>3</sub> film were also effectively passivated. As a result, the PCE of CsPbI<sub>3</sub> C-PSCs was promoted from 12.51% to 16.10%.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was supported by the National Natural Science Foundation of China (51971012).

## References

- C. Liu, J. He, M. Wu, Y. Wu, P. Du, L. Fan, Q. Zhang, D. Wang and T. Zhang, All-Inorganic CsPbI<sub>2</sub>Br Perovskite Solar Cell with Open-Circuit Voltage over 1.3 V by Balancing Electron and Hole Transport, *Sol. RRL*, 2020, **4**, 2000016.
- Q. Tai, K.-C. Tang and F. Yan, Recent progress of inorganic perovskite solar cells, *Energy Environ. Sci.*, 2019, **12**, 2375–2405.
- M. Chen, M.-G. Ju, H. F. Garces, A. D. Carl, L. K. Ono, Z. Hawash, Y. Zhang, T. Shen, Y. Qi, R. L. Grimm, D. Pacifici, X. C. Zeng, Y. Zhou and N. P. Padture, Highly stable and efficient all-inorganic lead-free perovskite solar cells with native-oxide passivation, *Nat. Commun.*, 2019, **10**, 16.
- A. Ho-Baillie, M. Zhang, C. F. J. Lau, F.-J. Ma and S. Huang, Untapped Potentials of Inorganic Metal Halide Perovskite Solar Cells, *Joule*, 2019, **3**, 938–955.
- Z. Chen, Q. Dong, Y. Liu, C. Bao, Y. Fang, Y. Lin, S. Tang, Q. Wang, X. Xiao, Y. Bai, Y. Deng and J. Huang, Thin single crystal perovskite solar cells to harvest below-bandgap light absorption, *Nat. Commun.*, 2017, **8**, 1890.
- L. Qiu, S. He, L. K. Ono, S. Liu and Y. Qi, Scalable Fabrication of Metal Halide Perovskite Solar Cells and Modules, *ACS Energy Lett.*, 2019, **4**, 2147–2167.
- G. Tong, L. K. Ono and Y. Qi, Recent Progress of All-Bromide Inorganic Perovskite Solar Cells, *Energy Technol.*, 2020, **8**, 1900961.
- J. Y. Kim, J.-W. Lee, H. S. Jung, H. Shin and N.-G. Park, High-Efficiency Perovskite Solar Cells, *Chem. Rev.*, 2020, **120**, 7867–7918.
- H. Wang, Z. Dong, H. Liu, W. Li, L. Zhu and H. Chen, Roles of Organic Molecules in Inorganic CsPbX<sub>3</sub> Perovskite Solar Cells, *Adv. Energy Mater.*, 2021, **11**, 2002940.
- Y. Li, H. Xie, E. L. Lim, A. Hagfeldt and D. Bi, Recent Progress of Critical Interface Engineering for Highly Efficient and Stable Perovskite Solar Cells, *Adv. Energy Mater.*, 2022, **12**, 2102730.
- H. Chen and S. Yang, Methods and strategies for achieving high-performance carbon-based perovskite solar cells without hole transport materials, *J. Mater. Chem. A*, 2019, **7**, 15476–15490.
- D. Bogachuk, S. Zouhair, K. Wojciechowski, B. Yang, V. Babu, L. Wagner, B. Xu, J. Lim, S. Mastroianni, H. Pettersson, A. Hagfeldt and A. Hinsch, Low-temperature carbon-based electrodes in perovskite solar cells, *Energy Environ. Sci.*, 2020, **13**, 3880–3916.
- H. Chen and S. Yang, Carbon-Based Perovskite Solar Cells without Hole Transport Materials: The Front Runner to the Market?, *Adv. Mater.*, 2017, **29**, 1603994.
- X. Zhang, Z. Yu, D. Zhang, Q. Tai and X.-Z. Zhao, Recent Progress of Carbon-Based Inorganic Perovskite Solar Cells: From Efficiency to Stability, *Adv. Energy Mater.*, 2022, 2201320.
- B. Conings, J. Drijkoningen, N. Gauquelin, A. Babayigit, J. D'Haen, L. D'Olieslaeger, A. Ethirajan, J. Verbeeck, J. Manca, E. Mosconi, F. D. Angelis and H.-G. Boyen, Intrinsic Thermal Instability of Methylammonium Lead Trihalide Perovskite, *Adv. Energy Mater.*, 2015, **5**, 1500477.
- J. K. Nam, S. U. Chai, W. Cha, Y. J. Choi, W. Kim, M. S. Jung, J. Kwon, D. Kim and J. H. Park, Potassium Incorporation for Enhanced Performance and Stability of Fully Inorganic Cesium Lead Halide Perovskite Solar Cells, *Nano Lett.*, 2017, **17**, 2028–2033.
- P. Yu, W. Zhang, F. Ren, J. Wang, H. Wang, R. Chen, S. Zhang, Y. Zhang, Z. Liu and W. Chen, Strategies for highly efficient and stable cesium lead iodide perovskite photovoltaics: mechanisms and processes, *J. Mater. Chem. C*, 2022, **10**, 4999–5023.
- Y. Zhao, J. Duan, Y. Wang, X. Yang and Q. Tang, Precise stress control of inorganic perovskite films for carbon-based solar cells with an ultrahigh voltage of 1.622 V, *Nano Energy*, 2020, **67**, 104286.
- X. Chang, W. Li, L. Zhu, H. Liu, H. Geng, S. Xiang, J. Liu and H. Chen, Carbon-Based CsPbBr<sub>3</sub> Perovskite Solar Cells: All-Ambient Processes and High Thermal Stability, *ACS Appl. Mater. Interfaces*, 2016, **8**, 33649–33655.
- Z. Yao, W. Zhao and S. Liu, Stability of the CsPbI<sub>3</sub> perovskite: from fundamentals to improvements, *J. Mater. Chem. A*, 2021, **9**, 11124–11144.
- Z. Dong, W. Li, H. Wang, X. Jiang, H. Liu, L. Zhu and H. Chen, High-Temperature Perovskite Solar Cells, *Sol. RRL*, 2021, **5**, 2100370.
- W. Zhu, J. Ma, W. Chai, T. Han, D. Chen, X. Xie, G. Liu, P. Dong, H. Xi, D. Chen, J. Zhang, C. Zhang and Y. Hao, Intermediate Phase-Assisted Sequential Deposition Toward 15.24%-Efficiency Carbon-Electrode CsPbI<sub>2</sub>Br Perovskite Solar Cells, *Sol. RRL*, 2022, **6**, 2200020.
- H. Wang, S. Xiang, W. Li, H. Liu, L. Zhu, S. Xiao, S. Yang and H. Chen, Skillfully deflecting the question: a small amount of piperazine-1,4-dium iodide radically enhances the thermal stability of CsPbI<sub>3</sub> perovskite, *J. Mater. Chem. C*, 2019, **7**, 11757–11763.
- C. Dong, B. Xu, D. Liu, E. G. Moloney, F. Tan, G. Yue, R. Liu, D. Zhang, W. Zhang and M. I. Saidaminov, Carbon-based all-inorganic perovskite solar cells: Progress, challenges and strategies toward 20% efficiency, *Mater. Today*, 2021, **50**, 239–258.
- S. Xiang, W. Li, Y. Wei, J. Liu, H. Liu, L. Zhu and H. Chen, The synergistic effect of non-stoichiometry and Sb-doping on air-stable  $\alpha$ -CsPbI<sub>3</sub> for efficient carbon-based perovskite solar cells, *Nanoscale*, 2018, **10**, 9996–10004.
- R. J. Sutton, G. E. Eperon, L. Miranda, E. S. Parrott, B. A. Kamino, J. B. Patel, M. T. Hörlantner, M. B. Johnston,

- A. A. Haghighirad, D. T. Moore and H. J. Snaith, Bandgap-Tunable Cesium Lead Halide Perovskites with High Thermal Stability for Efficient Solar Cells, *Adv. Energy Mater.*, 2016, **6**, 1502458.
- 27 A. Miyata, A. Mitioglu, P. Plochocka, O. Portugall, J. T.-W. Wang, S. D. Stranks, H. J. Snaith and R. J. Nicholas, Direct measurement of the exciton binding energy and effective masses for charge carriers in organic-inorganic tri-halide perovskites, *Nat. Phys.*, 2015, **11**, 582–587.
- 28 Z. Shao, H. Meng, X. Du, X. Sun, P. Lv, C. Gao, Y. Rao, C. Chen, Z. Li, X. Wang, G. Cui and S. Pang, Cs<sub>4</sub>PbI<sub>6</sub>-Mediated Synthesis of Thermodynamically Stable FA<sub>0.15</sub>Cs<sub>0.85</sub>PbI<sub>3</sub> Perovskite Solar Cells, *Adv. Mater.*, 2020, **32**, 2001054.
- 29 J. Liu, L. Zhu, S. Xiang, H. Wang, H. Liu, W. Li and H. Chen, Cs-Doped TiO<sub>2</sub> Nanorod Array Enhances Electron Injection and Transport in Carbon-Based CsPbI<sub>3</sub> Perovskite Solar Cells, *ACS Sustainable Chem. Eng.*, 2019, **7**, 16927–16932.
- 30 X. Fu, K. Zhou, X. Zhou, H. Ji, Y. Min and Y. Qian, Surface passivation for enhancing photovoltaic performance of carbon-based CsPbI<sub>3</sub> perovskite solar cells, *J. Solid State Chem.*, 2022, **308**, 122891.
- 31 R. Yin, K.-X. Wang, X.-N. Huo, Y.-S. Sun, W.-W. Sun, Y.-K. Gao, T.-T. You and P.-G. Yin, A One-Step Ionic Liquid Interface-to-Bulk Modification for Stable Carbon-Based CsPbI<sub>3</sub> Perovskite Solar Cells with Efficiency Over 15%, *Adv. Mater. Interfaces*, 2022, **9**, 2201488.
- 32 S. Xiang, W. Li, Y. Wei, J. Liu, H. Liu, L. Zhu, S. Yang and H. Chen, Sodium Doping Pushes the Efficiency of Carbon-Based CsPbI<sub>3</sub> Perovskite Solar Cells to 10.7%, *iScience*, 2019, **15**, 156–164.
- 33 H. Wang, H. Liu, Z. Dong, X. Wei, W. Li, L. Zhu, C. Zhu, Y. Bai and H. Chen, Moisture is not always bad: H<sub>2</sub>O accelerates the conversion of DMAPbI<sub>3</sub> intermediate to CsPbI<sub>3</sub> for boosting the efficiency of carbon-based perovskite solar cells to over 16%, *Fundam. Res.*, 2022, DOI: [10.1016/j.fmre.2022.07.005](https://doi.org/10.1016/j.fmre.2022.07.005).
- 34 Y. Cui, J. Shi, F. Meng, B. Yu, S. Tan, S. He, C. Tan, Y. Li, H. Wu, Y. Luo, D. Li and Q. Meng, A Versatile Molten-Salt Induction Strategy to Achieve Efficient CsPbI<sub>3</sub> Perovskite Solar Cells with a High Open-Circuit Voltage >1.2 V, *Adv. Mater.*, 2022, 2205028.
- 35 Z. Dong, W. Li, H. Wang, X. Jiang, H. Liu, L. Zhu and H. Chen, Carbon nanotubes in perovskite-based optoelectronic devices, *Matter*, 2022, **5**, 448–481.
- 36 S. Zouhair, S.-M. Yoo, D. Bogachuk, J. P. Herterich, J. Lim, H. Kanda, B. Son, H. J. Yun, U. Würfel, A. Chahboun, M. K. Nazeeruddin, A. Hinsch, L. Wagner and H. Kim, Employing 2D-Perovskite as an Electron Blocking Layer in Highly Efficient (18.5%) Perovskite Solar Cells with Printable Low Temperature Carbon Electrode, *Adv. Energy Mater.*, 2022, **12**, 2200837.
- 37 X.-N. Huo, K.-X. Wang, R. Yin, W.-W. Sun, Y.-S. Sun, Y.-K. Gao, T.-T. You and P.-G. Yin, High-performance carbon-based all-inorganic CsPbI<sub>2</sub>Br perovskite solar cells via ethylammonium iodide and phenethylammonium iodide synergistic passivation, *Sol. Energy Mater. Sol. Cells*, 2022, **247**, 111963.
- 38 J. Zhou, Z. Ye, J. Hou, J. Wu, Y.-Z. Zheng and X. Tao, Efficient ambient-air-stable HTM-free carbon-based perovskite solar cells with hybrid 2D–3D lead halide photoabsorbers, *J. Mater. Chem. A*, 2018, **6**, 22626–22635.
- 39 K. Wang, Z. Li, F. Zhou, H. Wang, H. Bian, H. Zhang, Q. Wang, Z. Jin, L. Ding and S. Liu, Ruddlesden–Popper 2D Component to Stabilize  $\gamma$ -CsPbI<sub>3</sub> Perovskite Phase for Stable and Efficient Photovoltaics, *Adv. Electron. Mater.*, 2019, **9**, 1902529.
- 40 H. Wang, H. Liu, Z. Dong, W. Li, L. Zhu and H. Chen, Composition manipulation boosts the efficiency of carbon-based CsPbI<sub>3</sub> perovskite solar cells to beyond 14%, *Nano Energy*, 2021, **84**, 105881.
- 41 A. De, N. Mondal and A. Samanta, Luminescence tuning and exciton dynamics of Mn-doped CsPbCl<sub>3</sub> nanocrystals, *Nanoscale*, 2017, **9**, 16722–16727.
- 42 Y. Su, X. Chen, W. Ji, Q. Zeng, Z. Ren, Z. Su and L. Liu, Highly Controllable and Efficient Synthesis of Mixed-Halide CsPbX<sub>3</sub> (X = Cl, Br, I) Perovskite QDs toward the Tunability of Entire Visible Light, *ACS Appl. Mater. Interfaces*, 2017, **9**, 33020–33028.
- 43 X. Zhao, T. Liu, Q. C. Burlingame, T. Liu, R. Holley, G. Cheng, N. Yao, F. Gao and Y.-L. Loo, Accelerated aging of all-inorganic, interface-stabilized perovskite solar cells, *Science*, 2022, **377**, 307–310.
- 44 S. Yang, W. Liu, Y. Han, Z. Liu, W. Zhao, C. Duan, Y. Che, H. Gu, Y. Li and S. Liu, 2D Cs<sub>2</sub>PbI<sub>2</sub>Cl<sub>2</sub> Nanosheets for Holistic Passivation of Inorganic CsPbI<sub>2</sub>Br Perovskite Solar Cells for Improved Efficiency and Stability, *Adv. Energy Mater.*, 2020, **10**, 2002882.
- 45 T. V. Vu, A. A. Lavrentyev, B. V. Gabrelian, K. D. Pham, O. V. Parasyuk, N. M. Denysyuk and O. Y. Khyzhun, Electronic structure and optical constants of CsPbCl<sub>3</sub>: The effect of approaches within ab initio calculations in relation to X-ray spectroscopy experiments, *Mater. Chem. Phys.*, 2021, **261**, 124216.
- 46 Z. Zhao, W. Xu, G. Pan, Y. Liu, M. Yang, S. Hua, X. Chen, H. Peng and H. Song, Enhancing the exciton emission of CsPbCl<sub>3</sub> perovskite quantum dots by incorporation of Rb<sup>+</sup> ions, *Mater. Res. Bull.*, 2019, **112**, 142–146.
- 47 Y. Zhang, Z. Li, H. Chen, Y. Xu, Y. Lei, G. Peng, X. Zhou, Q. Wang and Z. Jin, Double-Layer Quantum Dots as Interfacial Layer to Enhance the Performance of CsPbI<sub>3</sub> Solar Cells, *Adv. Mater. Interfaces*, 2022, 2200813.
- 48 V. M. Le Corre, E. A. Duijnste, O. El Tambouli, J. M. Ball, H. J. Snaith, J. Lim and L. J. A. Koster, Revealing Charge Carrier Mobility and Defect Densities in Metal Halide Perovskites via Space-Charge-Limited Current Measurements, *ACS Energy Lett.*, 2021, **6**, 1087–1094.