RSC Advances



View Article Online **REVIEW**



Cite this: RSC Adv., 2025, 15, 9055

Advancements in binary and ternary transition metal-based composites for high-performance supercapacitors: a comprehensive review

Jannatun Zia ** and M. S. S. R. Tejaswini ** b

As the demand for efficient and high-performance energy storage devices continues to rise, supercapacitors have emerged as a promising technology due to their rapid charge-discharge capabilities and long cycle life. Among the various strategies to enhance supercapacitor performance, binary and ternary transition metal-based composites have garnered significant attention. These composites offer a unique approach by combining multiple transition metals, which synergistically enhance electrochemical performance through both physical and chemical charge storage mechanisms. This review provides an in-depth analysis of the latest research on binary and ternary transition metal composites, discussing their electrochemical properties, synthesis methods, and performance metrics in

Received 22nd January 2025 Accepted 17th March 2025

DOI: 10.1039/d5ra00528k

rsc.li/rsc-advances

^aDepartment of Chemistry, School of Engineering, Siddhartha Academy of Higher Education Deemed to be University, Vijayawada, A. P., India. E-mail: jannat22oct@gmail.com

^bDepartment of Chemistry, School of Applied Sciences and Humanities, Vignan's Foundation for Science, Technology and Research, Vadlamudi, Guntur, A. P., India



Jannatun Zia

Dr Jannatun Zia is currently serving as an Assistant Professor in the Department of Chemistry, School of Engineering, at Siddhartha Academy of Higher Education, Deemed to be University, Vijayawada, Andhra Pradesh, India. Prior to this, she held the position of Senior Research Fellow in the Department of Chemistry at Jamia Millia Islamia University, New Delhi, and was awarded a prestigious postdoctoral fellowship

at the School of Sciences, Harbin Institute of Technology (HIT), China. Dr Zia completed her PhD in Chemistry from Jamia Millia Islamia University, New Delhi, where she was honored with the CSIR-SRF (Direct) Fellowship for research funding. Her primary research interests lie in materials chemistry, focusing on energy and environmental applications. Additionally, she has conducted extensive research in the area of drug delivery systems. With over 25 peer-reviewed publications in high-impact journals, including both original research articles and reviews, Dr Zia has garnered more than 550 citations. Her current H-index is 14, with an i10index of 14 (Google Scholar). Her expertise spans a wide range of topics, including metal oxides, spinel ferrites, conducting polymers, and their functionalization for applications in catalysis, energy storage, and drug delivery.



M. S. S. R. Tejaswini

Dr M. S. S. R. Tejaswini is currently working as an Assistant Professor in the Department of Chemistry, School of Applied sciences & Humanities at Vignan's Foundation for Science, Technology & Research, Guntur, Andhra Pradesh, India. She has obtained her PhD from Department of Environmental Science and Engineering, SRM University AP, India. Her research domain includes valorisation of resources from solid waste,

circular economy, life cycle assessment and sustainable conversion of waste plastics into fuel. Her research area is also aligned with plastic degradation through photocatalysis and its conversion into resourceful materials. She is focused on acquiring secondary resources from waste materials to build a sustainable future. She has contributed significantly to environmental sustainability research through numerous international publications and book chapters. This review article is a comprehensive synthesis of previously published literature and does not include original experimental data. All data and information discussed in the manuscript are sourced from publicly available publications, which are appropriately cited throughout the text. As such, no primary data generated or analyzed for the purpose of this review article are available.

supercapacitor applications. The combination of different transition metals in composite materials as energy storage electrodes allows for a broader voltage window, increased energy density, enhanced power density, and improved cycling stability. Additionally, we discuss the structural and morphological features of these composite materials, such as porosity, surface area, and conductivity, which play critical roles in determining overall performance. Furthermore, the review highlights the challenges faced in optimizing these composites, including material scalability, cost-effectiveness, and long-term stability. The paper also outlines future research directions, emphasizing the potential of binary and ternary transition metal-based composites in supercapacitor applications, providing insights into potential avenues for the next generation of high-performance energy storage systems. This review thus provides valuable insights into both the current state and future potential of these composite materials in high-performance supercapacitors.

1. Introduction

The global energy consumption from fossil fuels reached 13.731 billion tons of oil equivalents (BTOE) in 2012, with projections rising to 18.30 BTOE by 2035. This growth, coupled with diminishing fossil fuel reserves, has led to economic challenges, such as volatile prices and supply chain disruptions. Moreover, the widespread burning of fossil fuels has significantly increased carbon dioxide emissions, contributing to global warming and environmental changes. Consequently, there is an urgent need for sustainable energy solutions, such as renewable energy sources and energy storage technologies. 1.2

Lithium-ion batteries (LIBs), widely used in portable electronics and electric vehicles, offer high energy density but suffer from limited cycle life, suboptimal performance, and safety risks. Recent literature studies have reported that supercapacitors (SCs) can be a potential substitute for existing LIBs. Supercapacitors are among the most promising energy storage devices due to their exceptional power density, long cycle life, and fast charge-discharge capabilities. With growing global demands for efficient energy storage systems, supercapacitors have gained significant attention for applications in portable electronics, electric vehicles, renewable energy storage, and more. These devices offer significantly higher power density $(P_{\rm d})$, about 10 times that of LIBs, and can sustain tens of thousands to millions of charge and discharge cycles with minimal degradation, making them a safer option.^{2,3} The rapid development of SCs technology is further evidenced by their application in Airbus A380 aircraft.4 SCs are categorized based on their charge storage mechanisms and tailored for specific applications. Academic researchers and industries are focusing on various types of SCs to fulfil different energy storage requirements, each offering distinct advantages and uses.5 However, to further enhance their energy storage performance, there is a continuous need for innovative materials that can provide higher energy density, stability, and efficiency.

As the demand for enhanced SCs grows, researchers are investigating advanced electrochemical and nanotechnology approaches. The electrode material is a critical determinant, as it significantly affects the device's energy storage performance. Accordingly, it necessitates the utilization and exploration of novel materials with superior electrochemical properties. By developing innovative materials, sophisticated electrode designs, and cutting-edge manufacturing methods, researchers


are pushing the boundaries of SCs technology, aiming for higher energy densities, faster charging times, and overall enhanced performance.^{1,6}

To overcome this challenge, researchers have focused on improving the performance of supercapacitors through the development of advanced electrode materials. Transition metalbased composites (TMCs) have emerged as promising candidates due to their excellent electrochemical properties, including high electrical conductivity, large surface area, and favourable charge storage mechanisms. These composites, which often combine transition metals with other materials such as metal oxides, hydroxides, chalcogenides, phosphides, phosphates, carbon, and conducting polymers, can provide significant improvements in the energy storage capabilities of supercapacitors.⁷

There are two main types of transition metal-based composites: binary and ternary. Binary transition metal-based composites consist of two different electrode materials and have demonstrated significant progress in enhancing electrochemical performance by optimizing the synergistic effects between different metal ions. These binary systems can achieve better conductivity, electrochemical stability, and higher specific capacitance, which are critical for improving overall energy storage performance. On the other hand, ternary composites incorporate three different electrode materials into a single electrode and have the potential to offer even greater improvements in supercapacitor performance. By combining transition metals with carbon materials or conducting polymers, ternary composites can enhance conductivity, structural stability, and charge storage capacity, making them ideal for high-performance supercapacitor applications. This strategic combination enhances the efficacy and potency of energy storage systems, making composite electrodes a key focus in current research and development.8

This review highlights recent advancements in binary and ternary transition metal-based composites (TMCs), including metal oxides, hydroxides, chalcogenides, phosphides, and phosphates, combined with carbon or conducting polymers to form binary composites. It examines their design, synthesis, structural properties, and electrochemical performance in supercapacitor applications. The review also explores ternary composites that incorporate both metals and conducting polymers with carbon (Scheme 1). A key focus is on the electrochemical performance of these composites, with

Review **RSC Advances**



Scheme 1 Schematic representation of possible combinations for the fabrication of transition metal composites for electrodes of SCs.

a comprehensive analysis of various material combinations and their impact on energy storage efficiency. We aim to provide a comprehensive understanding of their potential for developing next-generation high-performance supercapacitors.

Binary transition metal composites for SCs

Binary transition metal composites, comprised of two distinct materials, encompass combinations such as metal oxides, hydroxides, chalcogenides, phosphides, and phosphates in conjunction with carbon or conducting polymers.

In systems for energy conversion and storage, carbon materials are reported to be extremely valuable. Their superior electrical conductivity, high surface-to-volume ratio, and robust cycling stability make them efficient for effective charge and discharge procedures. Their versatility is evident in their various allotropes such as graphene, fullerene, and graphite, and their wide range of structural forms, from powders and sheets to aerogels, fibers, and composites. 9,10 Additionally, they are chemically stable, easy to process, non-toxic, lightweight, and possess adjustable porosity for enhanced performance. These materials encounter issues like low energy density (E_d) and specific capacitance (C_s) . On the other hand, the highpower densities of electrodes made from transition metal compounds are often limited by their inherently poor conductivity and slow redox reaction kinetics. Integrating carbon materials with transition metal compounds has demonstrated enhanced electrochemical properties.11 This improvement is attributed to synergistic effects that create efficient pathways for electron and ion transfer, while also maintaining the structural stability of the entire electrode. The advantages are as follows:11-13

(1) The incorporation of carbon materials within transition metal compounds-based systems capitalizes on their exceptional conductivity, thereby circumventing the intrinsic constraints of transition metal compounds and promoting

faster charge transport, culminating in enhanced electrochemical performance.

- (2) Carbon functions as a structural framework, mitigating the agglomeration of transition metal compounds. This is pivotal, as agglomeration can result in an uneven distribution and a diminished active surface area, adversely affecting the electrochemical performance.
- (3) The integration of transition metal compounds within a carbon matrix bolsters their thermal and chemical stability. Carbon materials, inherently inert and resistant to degradation, safeguard the transition metal compounds from environmental influences that could compromise their long-term performance.
- (4) The inherent flexibility and lightweight characteristics of carbon accommodate the expansion and contraction that occur during charge and discharge cycles without compromising structural integrity. This adaptability reduces mechanical stress on the transition metal compounds, leading to longer life cycles and improved efficiency.
- (5) Carbon materials' immense and broader surface area makes it easier for charge storage to occur through the creation of double layers, leading to elevated Pd and superior rate performance, in conjunction with the intrinsic pseudocapacitive contribution from transition metal compounds.

2.1 Carbon-based binary TMC

Transition metal oxides and hydroxides show significant potential for high-level energy storage, particularly as SCs electrode materials. As pseudo-capacitance and battery-type electrode materials, transition metal oxides offer higher E_d compared to carbon materials. Their redox properties ensure greater E_d and enhance electrochemical stability. These unique characteristics arise from their ability to exhibit various oxidation states, which facilitate rapid faradaic reactions. Moreover, they are capable of transiting between several oxidation states during charging and discharging owing to this functionality, thereby enabling quick movement of electrolyte ions into and out of the oxide lattice. Additionally, they are cost-effective, environmentally friendly, and possess high theoretical capacitance.14-16 Transition metal hydroxides are also extensively studied as SCs electrode materials due to their layered structure and high theoretical C_s , with common examples being cobalt hydroxides, nickel hydroxides, and layered double hydroxides. However, their electrical conductivity and stability need further improvement, which can be accomplished by constructing various composite electrode material structures.14

In our interesting work on activated carbon nanofibers/ cobalt ferrite (CNF/CoFe₂O₄) composites fabricated using electrospinning and hydrothermal methods (Fig. 1), the binary transition metal oxide-based carbon nanofibers composites are reported.17 It is concluded there that the hydrothermally prepared CNF/CoFe₂O₄ composite had a more extensive area in the cyclic voltammetry (CV) curve compared to the electro spun composite, indicating better electrochemical performance. Specifically, the hydrothermally synthesized composite successfully attained a C_s of 188.36 F g⁻¹ computed from galvanostatic charge-discharge (GCD), whereas the electro spun




Fig. 1 (a) Schematic representation of CNF/CoFe₂O₄ utilizing hydrothermal and electrospinning process, (b) variation of C_s with I_d and (c) cycling stability of CNF/CoFe₂O₄ utilizing hydrothermal and electrospinning process (reproduce from ref. 17 with permission from Springer® 2021).

composite had a lower C_s of 106.59 F g $^{-1}$ at a current density (I_d) of 0.5 A g $^{-1}$. Additionally, the hydrothermal method resulted in 80% C_s retention, which was higher than the 60% retention observed with the electrospinning method. This superior performance stems from the higher carbon concentration in the hydrothermally synthesized composite and the fact that the ${\rm CoFe_2O_4}$ nanoparticles were anchored to the CNF surface, rather than embedded within it as in the electro spun composite. This surface decoration in the hydrothermal method allowed for greater surface area exposure of both ${\rm CoFe_2O_4}$ and CNF, facilitating better electrolyte penetration and overall superior electrochemical behavior. Consequently, the ${\rm CNF/CoFe_2O_4}$ composite prepared via hydrothermal synthesis demonstrated more favourable characteristics which could be efficiently utilized as electrodes in SCs.

The past literature studies Zhao $et~al.^{18}$ reported the synthesis of ultra-fine RuO $_2$ quantum dots on a reduced graphene oxide (rGO) surface with the help of microwave-assisted hydrothermal method. They investigated the impact of different RuO $_2$ loadings on the electrode performance of the RuO $_2$ /rGO nanocomposite. The composite RG-2 (38 wt% RuO $_2$ loading) demonstrated a $C_{\rm s}$ of 1120 F g $^{-1}$ at a $I_{\rm d}$ of 1 A g $^{-1}$. Additionally, it exhibited an excellent capacity retention rate of 84% as the $I_{\rm d}$ boosted from 1 A g $^{-1}$ to 10 A g $^{-1}$, along with outstanding cycling stability, retaining 89% of its capacity after 10 000 cycles. Chong Sun $et~al.^{19}$ synthesized a Ni–Co bimetallic hydroxide/multi-walled carbon nanotube (La–NiCo LDH/MWCNT) composite doped with varying concentrations of La $^{3+}$ ions using a hydrothermal technique. At $I_{\rm d}$ of 1 A g $^{-1}$, the

sample with a 5% La³⁺ ion concentration exhibited a maximum $C_{\rm s}$ of 4396 F g⁻¹. The $C_{\rm s}$ retention of this sample was 70.31% after 3000 cycles.

Metal chalcogenides, represented as M_xC_v where M stands for transition metals from group 3 to 12 (including Ni, Co, Fe, Cu, Zn, Sc, Ti, V, Cr, W, Mo, etc.) and C represents chalcogens like sulfur (S), selenium (Se), and tellurium (Te), have been the subject of much scholarly inquiry. This interest is due to their versatile electronic structures, robust structural stability, anisotropic properties, adjustable kinetics, and remarkable electrochemical characteristics.20 These materials, which are composed of transition metal cations (M) and chalcogen anions, have structural variety that makes it possible to create adaptive surface and interfacial functions that improve ion intercalation in semiconductor conversion as well as storage of energy devices.21 These compounds consist of transition metal cations (M) and chalcogen anions (C). While interlayer bonding is governed by van der Waals forces, the bonds between metals and chalcogens are covalent. The metal atoms typically engage in bonding states with four electrons, resulting in an oxidation state of +4 for the metal and -2 for the chalcogen. The arrangement of C-M-C layers and the metal coordination can vary depending on the specific metals and chalcogens involved, leading to different polymorphic structures. Notably, the most common polymorphs are designated as 1T, 2H, and 3R, where the number denotes the layers within the crystalline unit cell and the letter indicates the symmetry of the structure-tetragonal (T), hexagonal (H), or rhombohedral (R).21,22 Due to their low toxicity and abundance, metal chalcogenides are

economically viable materials for use as electrodes in SCs. They also find a wide range of applications in consumer electronics, backup power systems, hybrid electric vehicles, and more. However, the inherent properties of single-component metal chalcogenides, such as chemical and thermal stability and electrical conductivity, may not always meet the stringent requirements of emerging energy systems. To address these challenges, combining metal chalcogenides with other materials has been found to enhance their properties. The development of composite metal chalcogenides has demonstrated synergistic capabilities, maximizing their potential efficiency and performance.23,24

Lokhande et al.25 synthesized a sulfide-based carbon composite electrode material, specifically CuFeS₂/carbon nanotubes (CFS/CNT), through a hydrothermal method. The electrochemical studies as shown in Fig. 2 demonstrated that the composite electrode exhibited pseudocapacitive behavior, with enhanced electrical and charge transport properties. The CFS/CNT composite electrode achieved a high C_s of 667 F g⁻¹ at a I_d of 15 A g^{-1} in a 1 M Na₂SO₄ electrolyte. Additionally, the electrode showed a high coulombic efficiency (η) of 95% and maintained 100% cyclic stability over 3000 cycles. To assess its practical application potential, a solid-state symmetric device (CFS/CNT//CFS/CNT) was created using a polymer gel electrolyte




Fig. 2 (a) The CV of the CFS and CFS/CNT composite electrode at 100 mV s⁻¹ scan rate (v), (b and c) the CV and the corresponding GCD plot of the CFS/CNT composite electrode at varied ν and varied $l_{\rm d}$, respectively, (d and e) the $C_{\rm s}$ and the η plot to the varied $l_{\rm d}$, respectively and (f) the cyclic stability plot for 3000 cycles (inset shows the CV curves at different cycles) of the CFS/CNT composite electrode (reproduced from ref. 25 with permission from Romania inoe@ 2023).

RSC Advances Review

(PVA-Na₂SO₄). This device achieved a maximum $C_{\rm s}$ of 128 F g⁻¹, an $E_{\rm d}$ of 22 W h kg⁻¹, a $P_{\rm d}$ of 2083 W kg⁻¹, and exhibited excellent durability with 94% cyclic stability over 10 000 cycles, making it a strong candidate for future energy storage.

Pandit et al.26 synthesized hexagonal VS2 nanoparticles on multi-walled carbon nanotube (MWCNT) matrix using a combination of dip-and-dry and successive ionic layer adsorption and reaction (SILAR) methods. The resulting VS₂/ MWCNTs electrode demonstrated a high C_s of 830 F g⁻¹ at a ν of 2 mV s⁻¹, along with excellent stability, retaining 95.9% of its initial C_s over 10 000 cycles. The MWCNTs, processed by the dip-and-dry method, provided a structural and conductive framework, serving as the core for the VS₂ nanostructure shell. This modified conductive network facilitated efficient faradaic charge transfer, while the prevention of charge accumulation helped maintain the structural integrity of the VS2 during charge-discharge (CD) cycles. Consequently, the system exhibited swift ion migration and improved CD kinetics at the conductive interface between VS2 and MWCNTs, reducing overall resistance. A flexible solid-state SSC device was fabricated using VS₂/MWCNTs electrodes and a low-cost PVA-LiClO₄ gel electrolyte. The SSC achieved a peak C_s of 182 F g⁻¹ at a ν of $2~{\rm mV~s^{-1}}$, with a specific energy of $42~{\rm W~h~kg^{-1}}$ and remarkable stability, retaining 93.2% of its C_s over 5000 cycles. As a demonstration of its practical application, the SSC successfully powered a panel labeled 'VNIT', consisting of 21 red LEDs.

Kirubasankar *et al.*²⁷ developed a nanocomposite made of nickel selenide (NiSe) nanoparticles on graphene nanosheets (G) using an *in situ* hydrothermal approach. The NiSe

nanoparticles were uniformly distributed throughout the graphene, creating a nanohybrid with improved diffusion and charge transport capabilities, in addition to many electrochemical active sites. As a NiSe–G nanohybrid combined with freestanding electrode, it showed outstanding electrochemical performance with a 98% retention of $C_{\rm s}$ after 2500 cycles and a high $C_{\rm s}$ of 1280 F g⁻¹ at $I_{\rm d}$ of 1 A g⁻¹. Additionally, an ASC device was put together using an electrospun PVdF membrane bathed in 6 M KOH as the electrolyte and separator, the NiSe–G nanohybrid as the PE, and AC as the NE. High $E_{\rm d}$ of 50.1 W h kg⁻¹ and $P_{\rm d}$ of 816 W kg⁻¹ were attained by this device at an extended operating voltage of 1.6 V.

Kshetri et al.28 developed a metal-organic framework (MOF)derived cobalt telluride-carbon composite on nickel foam (CoTe@C-NiF) as an electrode for SCs. Fig. 3 depicts the schematic representation and structural characterizations of CoTe@C-NiF electrode. The CoTe@C-NiF hybrid material exhibits a unique feature as a bifunctional electrode, functioning in different potential windows. In a three-electrode system, it can serve as a working electrode with potential ranges of -0.8 to 0.0 V for NE and 0.0 to 0.5 V for PE. The electrochemical characterization of CoTe@C-NiF electrode is given in Fig. 4. In the negative potential region, the CoTe@C-NiF electrode demonstrates a maximum areal capacitance (C_a) of 307.5 mF cm⁻² at a I_d of 1 mA cm⁻², retaining 162.0 mF cm⁻² at 20 mA cm⁻², which indicates a rate capability of 52.03%. Conversely, in the positive potential region, the electrode achieves C_a of 1038 mF cm⁻² and 920 mF cm⁻² at the same I_d , respectively, resulting in an 88.63% rate capability.




Fig. 3 (a) Schematic representation of the synthesis of CoTe@C-NiF hybrid electrode; (b and c) SEM images; (d) N_2 adsorption-desorption isotherms with pore size distribution curve in the inset; (e) EDS; and (f) XRD of CoTe@C-NiF hybrid electrode (reproduced from ref. 28 with permission from Elsevier© 2021).

Review




Fig. 4 (a and b) CV curve; (c and d) GCD; and (e and f) current contribution curve of CoTe@C-NiF in the negative and positive potential window, respectively (reproduced from ref. 28 with permission from Elsevier© 2021)

Additionally, the CoTe@C-NiF material demonstrates excellent long-term electrochemical stability during CD cycling in both potential windows. In the negative window, the material retains 86.78% of its initial $C_{\rm a}$ and 98.57% η after 10 000 cycles. In the positive window, it retains 87.50% of its C_a and 98.97% η under the same conditions. For practical application, two identical CoTe@C-NiF hybrid electrodes were utilized as both NE and PE in a SC device with 2 M KOH electrolyte and cellulose filter paper as a separator. The device (Fig. 5) exhibited C_a of 296.27 mF cm⁻² at 2 mA cm⁻² and 156.4 mF cm⁻² at 20 mA cm⁻², demonstrating a rate capability of 52.78%. The device also showed remarkable electrochemical stability, with 83.33% retention of $C_{\rm s}$ and 97.15% η after 10 000 cycles. The maximum

 $E_{\rm d}$ achieved was 43.84 W h ${\rm kg}^{-1}$ at a $P_{\rm d}$ of 738.88 W ${\rm kg}^{-1}$, with an $E_{\rm d}$ of 21.95 W h kg⁻¹ even at a high $P_{\rm d}$ of 6173.44 W kg⁻¹.

In coordination chemistry, phosphorus, a multivalent nonmetallic in the nitrogen group, plays an essential role as a donor atom. Phosphoric compounds are found in a variety of forms, that mainly includes metal phosphates and metal phosphides. The potential of these compounds to improve the performance of electrodes used in energy storage applications such as catalysis, SCs, and LIBs makes them interesting. Particularly, transition metal phosphides are regarded as potential SCs electrode materials due to their metalloid properties, strong electrochemical activity, and outstanding electrical conductivity. The advantages of phosphides over oxides




Fig. 5 (a) CV curves of the CoTe@C-NiF hybrid electrode in the negative and positive windows at 25 mV s⁻¹ (b and c) CV and GCD curves at different ν and I_d , respectively (d) C_a vs. I_d curve (e) cyclic stability curve along with the first and last ten GCD cycles (inset) of the CoTe@C-NiF//CoTe@C-NiF symmetric device (reproduced from ref. 28 with permission from Elsevier® 2021).

stem from phosphorus's lower electronegativity (2.19 on the Pauling scale) compared to oxygen (3.44), and its larger atomic radius (0.109 nm for phosphorus *versus* 0.074 nm for oxygen), which contribute to distinct physicochemical properties. ²⁹ In metal phosphides, the phosphorus atoms attract valence electron density due to the ionic nature of these compounds. As the phosphorus content increases, the degree of electron delocalization decreases, leading to a reduction in ionic character. Consequently, metal-rich phosphides, such as M_3P , M_2P , and MP, contain more free electrons, which enhance electrical conductivity. ³⁰

The term "phosphate" encompasses oxyanions of pentavalent phosphorus, ranging from simple PO₄³⁻ ions to complex ring and chain structures, and even extending to infinite networks. This variety in structural arrangements, along with the numerous cations they can coordinate with and the inclusion of additional anions or molecules, results in a wide diversity of metal phosphates.30 Transition metal phosphates or pyrophosphates (TMPs) are particularly advantageous as SCs electrode materials due to their remarkable attributes, including reversible redox chemistry, a robust open framework, mesoporous architecture, exceptional electrochemical and thermal stability, abundant natural resources, and costeffectiveness. The mesoporous morphology of TMPs provides ample interstitial space for facile ion diffusion, thereby enhancing electrochemical performance. The interplay of metal cations and the strong covalent P-O bonds within TMPs impart exceptional chemical resilience and augmented electrical

conductivity. Moreover, the open framework of TMPs facilitates unhindered electrolyte penetration to active sites, fostering expedited ion transport and optimized charge transfer kinetics. The availability of oxygen within TMPs extends their operational potential window, mitigating degradation and consequently elevating energy storage capacity. These collective advantages render TMPs highly promising candidates for advanced energy storage applications. ^{31,32}

An et al. 33 synthesized Ni₂P nanoparticles on reduced graphene oxide (rGO) using a low-temperature solid-state reaction method. They studied these materials as electrochemical pseudocapacitors. The Ni_2P/rGO composite exhibited a C_s of 2354 F g⁻¹ at 1 mA cm⁻², significantly higher than the 1597 F g^{-1} achieved by the Ni₂P nanoparticles alone. The enhanced C_s of the Ni₂P/rGO composite can be attributed to several factors. First, the precise assembly of Ni₂P nanoparticles with graphene oxide nanosheets, followed by in situ reduction, aids in creating hybrid materials with molecular-level dispersion and strong interfacial interactions. Second, the close integration of nickel phosphide nanoparticles with conductive graphene facilitates efficient charge transport, enhancing overall electronic conductivity. Third, incorporating Ni₂P nanoparticles onto the mechanically robust rGO prevents the aggregation of electroactive material, reduces the restacking of graphene sheets, and increases the electrochemically active surface area, thus maximizing the benefits of Ni₂P pseudocapacitance and graphenebased double-layer capacitance.




Fig. 6 (a) Schematic representation of the preparation of NiCoP/C composite (b) CV curves of NCP/C2-700 and AC at a ν of 10 mV s⁻¹ (c) CV curves at different ν (d) GCD curves (e) rate capability curve of NCP/C2-700//AC device (f) cycling life and η of NCP/C2-700//AC at 10 A g⁻¹ and a digital photo of a red LED illuminated by NCP/C2-700//AC device (reproduced from ref. 34 with permission from Elsevier@ 2024).

Zhao et al.34 fabricated nickel cobalt phosphide/carbon nanofibers (NiCoP/C2-700) with an approximate diameter of 200 nm through a process combining electrospinning and calcination. The synthesis process and electrochemical characterization is illustrated in Fig. 6.

The resulting NiCoP/C2-700 material demonstrated a $C_{\rm s}$ of 478 F g⁻¹ at 2 A g⁻¹ in a 3 M KOH electrolyte. Impressively, it retained 99.99% of its initial C_s even after 5000 charge/ discharge cycles at 10 A g⁻¹, highlighting its excellent electrochemical properties. Additionally, an ASC was engineered using NiCoP/C2-700 as the PE and AC as the NE. This device achieved an $E_{\rm d}$ of 16.72 W h kg⁻¹ at a high $P_{\rm d}$ of 7250 W kg⁻¹. Notably, the capacitance loss after 5000 cycles at 10 A g⁻¹ was only 0.04%. This remarkable stability is largely due to the role of carbon nanofibers as a supporting structure, which enhances the stability of the NiCoP nanoparticles. The outstanding electrochemical performance is attributed to the synergistic interaction between the NiCoP nanoparticles and the carbon nanofibers. Agarwal et al.35 developed a composite of Ni₃P₂O₈ nanodots anchored on multiwalled carbon nanotubes (Ni₃P₂O₈/ MWCNT) using a dip-and-dry method followed by chemical bath deposition as illustrated in Fig. 7(a). The corresponding flexible all-solid-state SSC (Fig. 7(b)), utilizing a carboxymethyl cellulose-Na₂SO₄ (CMC-Na₂SO₄) neutral gel electrolyte.

The electrochemical studies of MWCNT, Ni₃P₂O₈, and Ni₃P₂O₈/MWCNT composite electrodes are given in Fig. 8. The high redox activity of Ni₃P₂O₈ combined with the large surface area provided by the robust carbon framework resulted in a significant synergistic effect within the composite. This synergy led to an increased CV enclosed area and greater redox current compared to the individual components, indicating an improved energy storage capability. The MWCNTs in the composite help reduce the resistance of the host material and enhance the charge collection efficiency, facilitating ion transport within the electrode. Consequently, the Ni₃P₂O₈/MWCNT composite exhibits a significantly higher C_s of 793.1 F g^{-1} at 1.9 A g^{-1} and maintains 64.9% (514.6 F g^{-1}) of its rate capability even at 11.2 A g⁻¹. The composite retains more than 95% of its $C_{\rm s}$ after 5000 GCD cycles, demonstrating high cycling stability. Ni₃P₂O₈/MWCNT solid-state SSC device assembly with CMC-Na₂SO₄ electrolyte membrane achieved maximum specific energy of 72.3 W h kg $^{-1}$ and a $P_{\rm d}$ of 6.4 kW kg $^{-1}$ within an extended voltage window of 1.8 V. Additionally, the device exhibits excellent deformation tolerance, retaining 103% of its performance under a mechanical bending angle of 170°.

Research into supercapacitors has generated a lot of interest in MXenes. MXene-carbon-based hybrid materials have attracted significant attention in the field of supercapacitors due to their unique combination of properties.

Wang et al.36 developed MXene/N-CNT composite materials with a hierarchical porous structure that effectively inhibited the self-aggregation of 2D MXene and 1D N-CNT, as




Fig. 7 (a) Schematic showing easy solution chemistry for coupling hierarchically constructed $Ni_3P_2O_8/MWCNT$ on SS substrate (b) schematic representation of $Ni_3P_2O_8/MWCNT$ solid-state SSC device assembly with CMC- Na_2SO_4 electrolyte membrane (reproduced from ref. 35 with permission from Elsevier© 2023).

demonstrated in Fig. 9(a)-(c).36 This structure enhances the interlayer spacing of MXene and increases the specific surface area of the composite, providing more active sites for reactions and ion diffusion channels. As a result, the composite material exhibits a significantly improved specific capacitance (167.2 F g^{-1}) compared to the pure MXene electrode. Furthermore, the asymmetric supercapacitor device based on these composite shows a high capacitance retention rate of 73.2% after 10 000 cycles, a high coulombic efficiency of 97.5%, and a maximum energy density of 12.1 W h kg⁻¹. Similarly, Chen et al.³⁷ fabricated a Ti₃C₂T_x MXene/CNTs composite for supercapacitor applications, demonstrating that the synthesized material achieved a high capacitance of 300 F g⁻¹ at a current density of 1 A g⁻¹ and exhibited excellent rate performance of 199 F g⁻¹ even at a current density of 500 A g⁻¹. Additionally, the material maintained 92% of its capacitance after 10 000 cycles at a high current density of 20 A g⁻¹, highlighting its impressive longterm cycle stability. The incorporation of CNTs into MXene successfully prevented self-restacking, facilitated rapid ion diffusion, and ensured excellent high-rate performance.

Zhao et al.38 developed a multifunctional Ti₃C₂T_x MXene/ carbon nanotube (MXene/CNT) hybrid fiber using a wet spinning method, as shown in Fig. 9(d)-(f).38 With approximately 1 wt% CNT content, the hybrid fiber achieved a high tensile strength of 61 \pm 7 MPa, a conductivity of 1142.08 \pm 40.04 S cm⁻¹, and an impressive specific capacitance of around 295 F g⁻¹. When the CNT content was increased to 9 wt%, the fiber exhibited a maximum strain of 161 \pm 19 MPa and further enhanced conductivity (1715 \pm 22 S cm⁻¹). These MXene/CNT fibers possess excellent mechanical properties, making them suitable for weaving into energy storage textiles, with a maximum energy density of approximately 6.08 mW h cm⁻³. Similarly, Sun et al.39 developed a novel MXene/N-doped carbon foam (MXene/NCF) compressible composite with a 3D hollow interconnected structure shown in Fig. 10. The NCF provides additional pseudocapacitance through nitrogen atom doping, while supporting MXene nanosheets to form stable 3D interconnected frameworks that offer efficient ion diffusion and electron transport pathways. The MXene enhances the composite's conductivity and hydrophilicity. Due to the




Fig. 8 (a) CV curves and (b) corresponding C_s plot for MWCNT, Ni₃P₂O₈, and Ni₃P₂O₈/MWCNT at 100 mV s⁻¹ (c) CV analysis of the prepared $Ni_{\tau}P_{2}O_{8}/MWCNT$ composite electrode: at different ν between 5 and 10 mV s⁻¹ (d) GCD curves and (e) corresponding C_{τ} plot for MWCNT, $Ni_3P_2O_8$, and $Ni_3P_2O_8$ /MWCNT at 1.9 A g⁻¹ (f) GCD measurement of $Ni_3P_2O_8$ /MWCNT composite at different I_d (g) corresponding C_s values, (h) cyclic retention plot (inset shows GCD curves for the first and last cycle) and (i) Nyquist plot of Ni₃P₂O₈/MWCNT before and after stability (reproduced from ref. 35 with permission from Elsevier@ 2023).

synergistic effects between MXene and NCF, the composite material exhibited outstanding capacitance performance of 332 $F g^{-1}$ (3162 mF cm⁻³), 64% rate performance (0.5–100 A g⁻¹), and excellent capacity retention of 99.2% after 10 000 cycles. Moreover, the material maintains stable electrochemical properties and morphology even under repeated 60% strain (Table 1).

Conducting polymer-based binary TMC

Conducting polymers (CPs), poly(3,4such ethylenedioxythiophene) (PEDOT), polypyrrole (PPy), polythiophene (PTH), polyacetylene (PA), and polyaniline (PANI), have garnered significant interest since their discovery in the 1960s for applications in sensors, electrochromic devices, and energy storage. These materials are noted for their high electrical conductivity and excellent capacitive properties. Their simple chemical composition—consisting mainly of carbon,

hydrogen, nitrogen, or sulphur also suggests a cost-effective production.41 Devices based on conducting polymers exhibit higher C_s compared to EDLCs and demonstrate faster kinetics than most inorganic batteries, offering a promising solution to bridge the gap between these two technologies in energy storage applications. However, the reduction-oxidation processes in conducting polymers lead to mechanical stress, limiting their stability over numerous CD cycles. This repeated swelling and shrinking during cycling compromises their long-term stability and performance. Consequently, using conducting polymers alone as SC electrodes is not ideal. To address these challenges, hybrids that combine conducting polymers with transition metal compounds or carbon materials are popular. These hybrids take advantage of the complementary properties of each component, leading to higher C_s and improved stability.^{7,41,42}

Yang et al.43 synthesized Co3O4@PPy core/shell nanosheet arrays using a combination of solvothermal synthesis and




Fig. 9 One-dimensional carbon/MXene composites: (a) schematic diagram, (b) SEM, and (c) capacitance value of MXene/N-CNT (d) schematic diagram and (e) TEM of MXene/CNT fiber, (f) CV curves (reproduced from ref. 36 with permission from American Chemical Society© 2023).




Fig. 10 MXene/N-doped carbon foam (NCF) composite with threedimensional (3D) hollow interconnected neuron-like architecture (reproduced from ref. 39 with permission from American Chemical Society© 2020).

electrodeposition techniques. They grew a thin layer of polypyrrole (PPy) on the surface of mesoporous ${\rm Co_3O_4}$ nanosheet arrays through electrodeposition. The process of fabrication of ${\rm Co_3O_4}$ @PPy hybrid along with its SEM images is given in Fig. 11. The electrochemical study was performed in 1 M KOH as displayed in Fig. 12. The hybrid ${\rm Co_3O_4}$ @PPy electrode, after an 8 minute electrodeposition process, exhibited the highest $C_{\rm a}$ of 2.11 F cm⁻² at a $I_{\rm d}$ of 2 mA cm⁻², which is significantly higher than the 0.54 F cm⁻² achieved by the pristine ${\rm Co_3O_4}$ electrode. Even when the $I_{\rm d}$ was increased to 20 mA cm⁻², the ${\rm Co_3O_4}$ @PPy electrode maintained an $C_{\rm a}$ of 1.37 F cm⁻², indicating excellent rate capability (65%). In contrast, the pristine ${\rm Co_3O_4}$ electrode only retained 50% of its $C_{\rm a}$ at the same $I_{\rm d}$. Notably, after coating with a PPy layer, the CV curve of the ${\rm Co_3O_4}$ @PPy electrode expanded significantly, demonstrating a substantial increase in

 $C_{\rm a}$ due to the synergistic effects of Co₃O₄ and PPy. The PPy layer enhances electrical conductivity, improving electron transport through the nanosheets. Additionally, PPy contributes to extra pseudocapacitance through ion doping/dedoping in an alkaline solution. The Co₃O₄@PPy hybrid electrode retained 85.5% of its initial $C_{\rm a}$ after 5000 cycles, indicating superior cycling stability. In comparison, the pristine Co₃O₄ electrode retained 97.7% of its $C_{\rm a}$, showing a 12% decrease in the hybrid electrode's retention. This decline is attributed to the inherent poor cycling stability of PPy, which undergoes significant volumetric changes during ion doping/dedoping. The Nyquist plots at high frequencies revealed that the equivalent series resistance (ESR) of the Co₃O₄@PPy hybrid electrode (0.238 Ω) was lower than that of the pristine Co₃O₄ electrode (0.319 Ω), indicating improved electrical conductivity due to the PPy coating.

Kong et al.⁴⁴ developed NiCo₂O₄ nanowire arrays coated with polypyrrole, referred to as NiCo₂O₄@PPy NWAs. These hybrid electrodes achieved a C_s of 2244.5 F g⁻¹ at a I_d of 1 A g⁻¹, significantly surpassing the 1189.4 F g⁻¹ of the pure NiCo₂O₄ NWAs electrode. Even at an increased I_d of 30 A g⁻¹, the NiCo₂O₄@PPy NWAs maintained a C_s of 1358 F g⁻¹, showcasing a notable rate capability of approximately 60.5%. In comparison, the pure NiCo₂O₄ NWAs only retained about 52.6% of their C_s at the same I_d . The hybrid NiCo₂O₄@PPy NWAs also demonstrated strong cycling stability, retaining 89.5% of their initial C_s after 5000 cycles and 82.9% after 10 000 cycles. Throughout extended cycling, the η remained mostly above 97%, indicating efficient electron transfer for charge storage and release. However, the pure NiCo₂O₄ NWAs exhibited

Table 1 Comparative table of carbon-based binary TMC and their performance

S. no.	Composite material	Binary TMC	Conductivity	Current density	Cyclic stability	References
1	Activated carbon nanofibers/	${\rm CNF/CoFe_2O_4}$	188.36 F g ⁻¹	$0.5~{\rm A~g^{-1}}$	80% after 10 000 cycles	17
2	Ultra-fine ruthenium quantum dots on a reduced graphene oxide	RuO ₂ /rGO	$1120~{\rm F~g^{-1}}$	$1~{\rm A~g}^{-1}$	89% after 10 000 cycles	18
3	Bimetallic hydroxide/multi-walled carbon nanotube	La–NiCo LDH/ MWCNT	4396 F g^{-1}	$1~{\rm A~g^{-1}}$	70.31% after 3000 cycles	19
4	Sulfide-based carbon composite electrode	CFS/CNT	667 F g^{-1}	15 A g^{-1}	100% after 5000 cycles	25
5	Hexagonal VS ₂ nanoparticles on a multi-walled carbon nanotube	MWCNT	830 F g^{-1}	$2~\mathrm{mV~s}^{-1}$	95.9% after 10 000 cycles	26
6	Nickel selenide nanoparticles on graphene nanosheets	NiSe-G	$1280 \; \mathrm{F \; g}^{-1}$	$1~{\rm A~g}^{-1}$	98% after 2500 cycles	27
7	Cobalt telluride-carbon composite on nickel foam	CoTe@C-NiF	$1038 \; \mathrm{F} \; \mathrm{g}^{-1}$	$2~\rm mA~cm^{-2}$	97.15% after 10 000 cycles	28
8	Ni ₂ P nanoparticles on reduced graphene oxide (rGO)	${ m Ni}_2{ m P/rGO}$	$2354 \; \mathrm{F \; g^{-1}}$	$1~\rm mA~cm^{-2}$	94% after 5000 cycles	33
9	Nickel cobalt phosphide/carbon nanofibers	NiCoP/C2-700	$478 \; \mathrm{F} \; \mathrm{g}^{-1}$	$2~\mathrm{A~g}^{-1}$	99.99% after 5000 cycles	34
10	Ni ₃ P ₂ O ₈ nanodots anchored on multiwalled carbon panotubes	$\mathrm{Ni_{3}P_{2}O_{8}/MWCNT}$	793.1 F g^{-1}	$1.9~{ m A~g}^{-1}$	95% after 5000 cycles	35
11	MXene/CNTs composite materials	MXene/N-CNT	$167.2 \; \mathrm{F \; g^{-1}}$	$1~{ m A~g^{-1}}$	73.2% after 10 000 cycles	36
12	MXene/CNTs composite	Ti ₃ C ₂ T _x MXene/ CNTs	300 F g ⁻¹	1 A g ⁻¹	92% after 10 000 cycles	37
13	Multifunctional MXene/carbon hybrid fibers	Ti ₃ C ₂ T _x MXene/ CNTs	295 F g^{-1}	1 A g^{-1}	95% after 5000 cycles	38
14	Novel MXene/N-doped carbon foam	MXene/NCF	332 F g^{-1}	$0.5 100 \text{ A g}^{-1}$	99.2% after 10 000 cycles	39
15	Delaminated Mxene heterostructure film	$\mathrm{Ti}_{3}\mathrm{C}_{2}\mathrm{T}_{x}/\mathrm{g}\text{-}\mathrm{C}_{3}\mathrm{N}_{4}$	$414 \; \mathrm{F \; g}^{-1}$	1 A g ⁻¹	94.93% after 2500 cycles	40




Fig. 11 (a) Schematic diagram for the synthesis of mesoporous Co_3O_4 @PPy hybrid nanosheet arrays (b) and (c) SEM images of Co_3O_4 @PPy hybrid at lower and higher resolution (reproduced from ref. 43 with permission from Springer© 2016).

RSC Advances Review

a greater C_s loss of around 10.9% after 5000 cycles. The primary cause of this decay in NiCo₂O₄ is attributed to its dissolution in the electrolyte, whereas the C_s loss in the conducting polymers is due to structural defects from repeated swelling and shrinking of polymer chains. The improved cycling stability of the NiCo₂O₄@PPy NWAs is due to their coaxial structure, where the NiCo₂O₄ core provides a robust framework that interconnects with the PPy nanospheres, while the PPy layer prevents the dissolution of NiCo₂O₄ in the electrolyte. The charge transfer resistance (Rct) of the hybrid NiCo2O4@PPy NWAs electrode is approximately 8.8 Ω , lower than the 13.7 Ω of the pristine NiCo2O4 NWAs electrode. After 10 000 cycles, the Rct only slightly increased from 8.8 to 11.2 Ω , suggesting that the longterm CD process did not significantly damage the NiCo2O4@-PPv hybrid electrode. Furthermore, a flexible ASC device was successfully constructed using the NiCo2O4@PPy NWAs as one

electrode and AC as the other. This device achieved a high $E_{\rm d}$ of 58.8 W h kg⁻¹ at a $P_{\rm d}$ of 365 W kg⁻¹, outstanding $P_{\rm d}$ of 10.2 kW kg⁻¹ at an $E_{\rm d}$ of 28.4 W h kg⁻¹, and excellent cycling stability with approximately 89.2% $C_{\rm s}$ retention after 5000 cycles. The flexible nature of the device makes it highly suitable for future portable and wearable electronic devices. The innovative three-dimensional coaxial architecture design paves the way for developing high-performance, flexible SCs.

Das *et al.*⁴⁵ developed a hybrid NE by combining solvothermal and potentiostatic electrodeposition techniques to deposit CuS@PEDOT-x (x = 5, 10, 15) onto a carbon cloth (CC) substrate. The electrochemical analysis of these electrodes is given in Fig. 13. This CC/CuS@PEDOT-10 electrode achieved the highest C_s of 2.81 mA h cm⁻² at a I_d of 1 mA cm⁻², outperforming the CC/CuS electrode, which reached around 1.01 mA h cm⁻² under the same conditions.




Fig. 12 (a) CV curves of the Co_3O_4 @ppy and Co_3O_4 electrode at a 50 mV s⁻¹ (b) CV curves of the Co_3O_4 @ppy and Co_3O_4 electrode at different ν . (c) GCD curves of the Co_3O_4 @ppy hybrid electrode and Co_3O_4 electrode at 2 mA cm⁻² (d) C_a of the Co_3O_4 @ppy and Co_3O_4 electrodes at varying I_d (e) cycling stability of the Co_3O_4 @ppy and Co_3O_4 electrodes at a ν of 50 mV s⁻¹ for 5000 cycles (f) EIS curves of the Co_3O_4 @ppy and Co_3O_4 electrodes (reproduced from ref. 43 with permission from Springer© 2016).

Review

The hybrid electrode demonstrated excellent rate capability, maintaining 74% of its capacity when the I_d was boosted from 1 to 10 mA cm⁻². Electrochemical impedance spectroscopy (EIS) revealed that the solution resistance (R_s) and R_{ct} of the CC/ CuS@PEDOT-10 electrode were 0.82 Ω and 0.39 Ω , respectively, lower than the CC/CuS electrode ($R_{\rm s}=1.02~\Omega,\,R_{\rm ct}=0.43$ Ω). This indicates that the PEDOT sheath enhances conductivity and reduces internal resistance, facilitating better interfacial electron transfer. The electrode's durability and stability were confirmed through 10 000 GCD cycles at a moderate I_d of 5 mA cm⁻² in a 2 M KOH electrolyte. The hybrid electrode retained 98.1% of its initial capacity after cycling, demonstrating exceptional long-term cycling performance. The stability and structure of the electrode were attributed to the ultrathin, highly conductive PEDOT sheath, which aids in fast ion/electron transport and protects the underlying CC/CuS nanoplate arrays from degradation. Post-cycling analysis using field

emission scanning electron microscopy (FESEM), X-ray diffraction (XRD), and X-ray photoelectron spectroscopy (XPS) showed that the CuS nanoplates maintained their structural integrity, despite some detachment of the PEDOT sheath. The crystalline structure and XPS spectra remained consistent with those of the uncycled electrode, indicating the robustness of the CC/CuS@PEDOT-10 hybrid structure. Furthermore, a flexible quasi-solid-state asymmetric device as illustrated in Fig. 14 constructed from this electrode delivered a Cs of 0.331 mA h cm⁻² at a I_d of 1 mA cm⁻². This device achieved a maximum E_d of 2.21 mW h cm⁻³ at a P_d of 4.20 mW cm⁻³ and maintained an E_d of 1.89 mW h cm⁻³ even at a high P_d of 41.66 $mW cm^{-3}$.

Liu et al.46 synthesized PPy@Co_{0.85}Se nanocomposites using an electrodeposition method. In this composite, Co_{0.85}Se nanoparticles were decorated onto conductive PPy nanowires. The PPy@Co_{0.85}Se hybrid electrode demonstrated a high




Fig. 13 (a) Comparative CV curves of CC/CuS₀ PEDOT-5, CC/CuS₀ PEDOT-10 and CC/CuS₀ PEDOT-15 at 50 mV s⁻¹, CV curves of (b) CC/CuS nanoplate arrays and (c) CC/CuS@PEDOT-10 hybrid at different v (d) comparative GCD profiles of CC/CuS, CC/CuS@PEDOT-5, CC/ CuS@PEDOT-10 and CC/CuS@PEDOT-15 at 1 mA cm⁻², GCD curves of (e) CC/CuS nanoplate arrays and (f) CC/CuS@PEDOT-10 hybrid at various I_{d_1} (q) plot of C_a values versus the I_d for CC/CuS, CC/CuS@PEDOT-5, CC/CuS@PEDOT-10 and CC/CuS@PEDOT-15, (h) Nyquist plots of CC/CuS nanoplate arrays and CC/CuS@PEDOT-10 hybrid (inset shows the magnified Nyquist plots in the higher frequency region and the equivalent circuit), and (i) cycling performance of the CC/CuS@PEDOT-10 hybrid NE for 10 000 consecutive GCD cycles at 5 mA cm $^{-2}$ (inset represents the Nyquist plots before and after the cycling with the fitted equivalent circuit) (reproduced from ref. 45 with permission from Elsevier© 2022).

RSC Advances Review

capacitive performance, achieving a C_s of 827 C g^{-1} at I_d of 1 A g⁻¹, which significantly outperformed the pure Co_{0.85}Se electrode's C_s of 282 C g^{-1} at the same I_d . The PPy@Co_{0.85}Se electrode retained 67% of its capacity, while the pure Co_{0.85}Se electrode retained only 46%. After undergoing 5000 GCD cycles at 10 A g⁻¹, the PPy@Co_{0.85}Se hybrid electrode retained 93% of its initial capacity, which is significantly higher than the 71% retention observed in the pure Co_{0.85}Se electrode. EIS data revealed that the PPy@Co_{0.85}Se hybrid electrode had a R_s of 0.64 Ω and a $R_{\rm ct}$ of 0.14 Ω , whereas the pure Co_{0.85}Se electrode exhibited higher R_s and R_{ct} values of 2.44 Ω and 1.54 Ω , respectively. The improved performance of the PPy@Co_{0.85}Se electrodes can be attributed to several factors. First, the dispersed Co_{0.85}Se nanoparticles on PPy nanowires offer better exposure of electroactive sites to electrolyte ions and shorten the ion diffusion path, enhancing the rate capacities of the electrodes. Second, the interconnected PPv nanowires form a conductive network on the Ni foam substrate, providing efficient pathways for fast charge transport and accelerating

electrode reactions. Lastly, the PPy nanowires act as a structural backbone, anchoring the $Co_{0.85}Se$ nanoparticles and maintaining structural integrity during repeated CD cycles, leading to high initial capacity retention. Additionally, an asymmetric device composed of PPy@Co_{0.85}Se and nitrogen-doped carbon nanotube (N-CNT) electrodes was fabricated. This device demonstrated specific capacities of 234, 226, 211, 194, and 171 C g⁻¹ at I_d of 1, 2, 3, 5, and 10 A g⁻¹, respectively. The device achieved a maximum E_d of 51.9 W h kg⁻¹ at a P_d of 812 W kg⁻¹ and retained an E_d of 38.1 W h kg⁻¹ at a high P_d of 7953 W kg⁻¹.

Yue *et al.*⁴⁷ developed a nanostructured composite of PPy@CoP-x (x=1,2,3) using the electrochemical deposition technique as shown in Fig. 15. The electrochemical studies of PPy, CoP, PPy@CoP-1, PPy@CoP-2, and PPy@CoP-3 electrodes are depicted in Fig. 16. The composite electrode, PPy@CoP-2, achieved a C_s of 440 C g^{-1} at 1 A g^{-1} , which is significantly higher than the specific capacities of the individual components, CoP and PPy, which were 155 C g^{-1} and 101 C g^{-1} , respectively. The PPy@CoP-2 electrodes maintained 64.6% of their stability when tested at




Fig. 14 (a) Schematic of CC/CVS-1:2//CC/CuS@PEDOT-10 asymmetric device, electrochemical properties of CC/CVS-1:2//CC/CuS@PEDOT-10 asymmetric device (b) CV at various ν (c) GCD at various l_d (d) areal capacity ν (e) Ragone plot (f) capacity retention and η over 10 000 cycles (g) EIS plot before and after cycling with fitted equivalent circuit, and (h) illuminating red, green, and blue LEDs and powering a small electrical motor fan using two serially connected CC/CVS-1:2//CC/CuS@PEDOT-10 asymmetric device (reproduced from ref. 45 with permission from Elsevier® 2022).




Fig. 15 Schematic illustration of preparing the PPy@CoP composite electrode (reproduced from ref. 47 with permission from Elsevier© 2021).




Fig. 16 (a) CV curves at 20 mV s⁻¹ (b) GCD curves at 1 A g⁻¹ for PPy, CoP, PPy@CoP-1, PPy@CoP-2, and PPy@CoP-3 (c) GCD curve of PPy@CoP-1 2 at various I_d (d) C_s vs. I_d (e) stability performance for 5000 cycles, and (f) Nyquist plot for PPy, CoP, PPy@CoP-1, PPy@CoP-2, and PPy@CoP-3 (reproduced from ref. 47 with permission from Elsevier@ 2021).

RSC Advances Review

15 A g⁻¹, outperforming the CoP and PPy electrodes, which retained only 52.5% and 34.9%, respectively.

Furthermore, the PPy@CoP-2 electrodes exhibited a capacity retention of 92% after 5000 GCD cycles at 5 A g⁻¹, while the CoP and PPy electrodes retained 79% and 71% of their initial capacities, respectively. In terms of resistance values, the PPy@CoP-2 electrode demonstrated a series resistance (R_s) of 2.34 Ω and a R_{ct} of 0.12 Ω . These values are lower compared to the CoP electrode (R_s of 2.70 Ω and R_{ct} of 0.27 Ω) and the PPy electrode (R_s of 3.09 Ω and R_{ct} of 0.33 Ω). For practical applications, a device composed of PPy@CoP-2 and nitrogen-doped carbon nanotubes (N-CNTs) achieved a C_s of 183 C g⁻¹ at 1 A g⁻¹. This device demonstrated an E_d of 38.1 W h kg⁻¹ at a P_d of 750 W kg⁻¹, and it maintained an E_d of 27.8 W h kg⁻¹ even at a high $P_{\rm d}$ of 7502 W kg⁻¹. After 5000 cycles at 5 A g⁻¹, the device retained 91% of its capacity and exhibited a η of 78%.

MXene/conducting polymer composites have shown great promise as advanced electrode materials. Wu et al.48 successfully synthesized organ-like amino-Ti₃C₂ (N-Ti₃C₂)/PANI composites using a two-step electrochemical approach. As illustrated in Fig. 17(a), N-Ti₃C₂ is first deposited or coated onto an FTO-glass substrate through an electrochemical reaction. Then, the ordered Ti₃C₂ MXene structure serves as a scaffold, where the PANI chains are electrochemically polymerized onto the FTOglass substrate under constant voltage. The SEM image in Fig. 17(b) and the EDS spectra in Fig. 17(c)-(e) confirm the effective integration of N-Ti₃C₂ and PANI. Fig. 17(f) highlights the

unique bonding mechanism between N-Ti₃C₂ and PANI, distinct from the typical direct interaction between Ti₃C₂ and PANI. The amine nitrogen on the PANI chain and the amino group on N-Ti₃C₂ are tightly bonded through chemical interactions, which enhance the spacing and surface area of the Ti₃C₂ MXenes, effectively preventing restacking of MXene sheets. Moreover, the organ-like N-Ti₃C₂/PANI composites, formed through covalent grafting, provide a fast and precise channel for ion and charge transfer, boosting the charge transfer rate of the composites. The special structure and bonding mechanism contribute to the excellent electrochemical properties of the N-Ti₃C₂/PANI composites. Specifically, in a 0.5 M H₂SO₄ electrolyte solution at 5 mV s⁻¹, the N-Ti₃C₂/PANI composite exhibits outstanding performance, with a maximum surface capacitance of 228 mF g^{-1} , which is 32 times greater than that of the pure Ti_3C_2 film, as shown in Fig. 17(g). Additionally, the N-Ti₃C₂/PANI composite electrode retains 85% of its capacitance after 1000 cycles.

Wang et al. 49 prepared Ti₃C₂T_x/PPy composite material using this method primarily relies on the combination of hydrogen bonds and electrostatic forces between Ti₃C₂T_r nanosheets and PPy chains. Additionally, the intercalation of homogeneous PPy nanoparticles expands the interlayer spacing of Ti₃C₂T_r nanosheets. At the same time, the highly oriented polymer chains provide more channels for charge transfer and electrolyte ion diffusion, thereby enhancing the specific capacitance and reducing charge transfer resistance. Notably, as shown in Fig. 18(c),49 the Ti₃C₂T_x/PPy composite electrode with the




Fig. 17 (a) Schematic diagram for the preparation of N-Ti₃C₂/PANI. (b) SEM image of N-Ti₃C₂/PANI and EDS spectrum (c) Ti, (d) C, and (e) N. (f) Atomic schematic diagram of PANI intercalation N-Ti₃C₂. (g) The specific capacitance of pure N-Ti₃C₂ and N-Ti₃C₂/PANI electrodes from 5-100 mV s⁻¹ (reproduced from ref. 48 with permission from Elsevier© 2019).




Fig. 18 (a) Schematic illustration of preparing $Ti_3C_2T_y/PPy$ composites through low-temperature in situ polymerization of PPy on Ti_3C_2 nanosheets. (b) SEM image of $Ti_3C_2T_x/PPy$ (inset of a partially enlarged view). (c) The specific capacitance of PPy, Ti_3C_2 , and Ti_3C_2/PPy at different scanning rates. (d) Cycle curves of PPy, Ti₃C₂, and Ti₃C₂/PPy at 1 A g⁻¹ (reproduced from ref. 49 with permission from Elsevier© 2019).

optimal ratio exhibits a specific capacitance of 184.36 F g⁻¹ at 2 mV s⁻¹, which is 37% higher than the specific capacitance of the pure $Ti_3C_2T_x$ MXene electrode (133.91 F g⁻¹). At a current density of 1 A g^{-1} , the capacitance of the $Ti_3C_2T_x/PPy$ composite electrode retains 83.33% after 4000 charge-discharge cycles, as seen in Fig. 18(d). The enhanced electrochemical performance and cycle stability of the material are attributed to the synergistic effects between Ti₃C₂T_x nanosheets and PPy nanoparticles, along with their complementary energy storage mechanisms. Most importantly, this method provides a lowcost and convenient approach for preparing Ti₃C₂T_x/PPy composites on a large scale.49

Inal et al.50 synthesized PEDOT:PSS:MXene films using electrochemical polymerization and co-doping techniques. Compared to thin films composed of a single dopant and PEDOT, the incorporation of PSS and MXene as co-dopants with PEDOT enables a better synergy between the properties of MXene and PEDOT, resulting in a polymer composite with higher specific capacitance and energy density. The PEDOT:PSS:MXene film (607 \pm 85.3 F cm⁻³, with a capacity retention rate of 78% after 500 cycles) exhibits a higher capacitance than PEDOT:PSS (195.6 \pm 1 F cm⁻³, 37%) and PEDOT:MXene (358.9 \pm 16.7 F cm⁻³, 58%), demonstrating superior volume capacitance and cycle stability (Table 2).

Ternary transition metal composites for SCs

Ternary composites, composed of three dissimilar materials, often exhibit synergistic properties that exceed those of binary

Table 2 Comparative table of conducting polymer-based binary TMC and their performance

S. no.	Composite material	Formula	Conductivity	Current density	Cyclic stability	References
1	Cobalt-oxide core/shell nanosheet	Co ₃ O ₄ @PPy	2.11 F cm ⁻²	2 mA cm ⁻²	85.5% after 5000 cycles	43
2	Nanowire arrays coated with polypyrrole	NiCo ₂ O ₄ @PPy NWAs		1 A g ⁻¹	89.5% after 10 000 cycles	44
3	Conducting polyethylenedioxythiophene	CC/CuS@PEDOT-10	1358 F g ⁻¹	10 mA cm ⁻²	96.7% after 10 000 cycles	45
4	PPy@CoP composite electrode	PPy@Co _{0.85} Se	827 C g ⁻¹	$1~{ m A~g^{-1}}$	93% after 5000 cycles	46
5	Nanostructured composite of PPy@CoP- x ($x = 1, 2, 3$)	PPy@CoP-2	183 C g ⁻¹	5 A g ⁻¹	92% after 5000 cycles	47
6	Organ-like amino Mxene composites	Ti ₃ C ₂ (N-Ti ₃ C ₂)/PANI	$228~\mathrm{mF~g^{-1}}$	$1~{ m A~g^{-1}}$	85% after 1000 cycles	48
7	MXene were coated with polypyrrole particles	$Ti_3C_2T_x/PPy$	184.36 F g ⁻¹	$1 \mathrm{Ag}^{-1}$	83.33% after 4000	49
8	$PPy/Ti_3C_2T_x$ film	$PPy/Ti_3C_2T_x$	$1000~\mathrm{F}~\mathrm{cm}^{-3}$	$5~\mathrm{mV~s}^{-1}$	92%, 25 000	51

RSC Advances Review

composites. Ternary composites in this category may have different configurations, including transition metals, carbon and conducting polymers. Mostafa S. Gouda et al. 52 synthesized nanocomposites of cobalt oxide-AC and nickel oxide-AC. To enhance electrochemical performance, they prepared these nanocomposites with varying weight percentages (10, 25, 50, and 75 wt%) of nickel oxide and cobalt oxide nanoparticles. The CV curves and GCD curves of AC, 25NiO@Co₃O₄-AC, and 25Co₃O₄@NiO-AC are given in Fig. 19. The CV curve of AC demonstrated the EDLC behavior whereas the CV curve of composite 25NiO@Co₃O₄-AC and 25Co₃O₄@NiO-AC clarifying the synergy between EDLC and redox-active nature of 25NiO@Co₃O₄ and 25Co₃O₄@NiO. The AC electrode showed the lowest C_s of 105 F g^{-1} . In contrast, the nanocomposite electrodes 25NiO@Co3O4-AC and 25Co3O4@NiO-AC achieved the highest C_s , 800.9 and 691.8 F g⁻¹, respectively, at I_d of 1 A g⁻¹ when tested in 3 M KOH. Their corresponding energy densities were 136.6 and 116.2 W h kg⁻¹. A C_s retention of 98.1% after 5000 GCD cycles at 10 A g^{-1} was reported for the 25Co₃O₄@NiO-AC electrode.

Su et al.53 successfully synthesized an orderly arranged beadchain ternary nanocomposite consisting of Cu₂O, Mn₃O₄, and NiO (Cu₂O-Mn₃O₄-NiO) through the electrospinning technique. The electrochemical performance of the resulting material was evaluated in a 6 M KOH electrolyte, yielding a maximum C_s of 1306 F g⁻¹ at a ν of 5 mV s⁻¹. Shahat et al.⁵⁴ synthesized a Mn₃O₄/TiO₂/rGO ternary nanocomposite for use in SCs through the hydrothermal method. The electrochemical performance of the material was evaluated in a 6 M KOH electrolyte, where it demonstrated a C_s of 356 F g⁻¹ and retained 91% of its C_s after 3000 cycles. Additionally, they constructed an ASC, utilizing Mn₃O₄/TiO₂/rGO as the PE and graphene as the NE. This device delivered an E_d of 31.95 W h kg⁻¹ at a P_d of 718 W kg⁻¹ and maintained 87% of its C_s after 1000 cycles, showcasing excellent cycling stability.

Recently, mixed transition metal sulfides have garnered significant attention from researchers. Among them, NiCo₂S₄ has emerged as one of the most widely studied electrode materials, demonstrating exceptional performance. Guo et al.55 synthesized a ternary composite of CoNi-Layered Double Hydroxide (LDH)/NiCo₂S₄/Reduced Graphene Oxide (RGO) using a straightforward one-step hydrothermal deposition method. The study found that NiCo₂S₄ nanoparticles were welldispersed across the RGO surface, while CoNi-LDH was uniformly coated. This distinctive structure facilitates the efficient transfer of charge carriers. The CoNi-LDH/NiCo₂S₄/RGO composite showed a C_s of 1846.66 F g^{-1} at 1 A g^{-1} , with 93.57% retention after 5000 cycles. Additionally, the ASC fabricated from this material achieved an $E_{\rm d}$ of 28.88 W h kg⁻¹. Jia et al.⁵⁶ developed NiCo-layered double hydroxide (LDH)/NiCo2S4 nanotube arrays adorned with black phosphorus quantum dots (BPQD) using a combination of solvothermal synthesis and electrostatic adsorption. The material demonstrated an impressive C_s of 2938.2 F g⁻¹ at a I_d of 1 A g⁻¹. The ASC constructed from this material delivered an $E_{\rm d}$ of 133.7 W h kg⁻¹ at a $P_{\rm d}$ of 800 W kg⁻¹ while retaining 76.5% of its $C_{\rm s}$ after 10 000 CD cycles.

PANI is one of the most commonly used conducting polymers in SC applications. In this section, we will examine ternary composites incorporating PANI. Xiong et al.57 explored a manganese ferrite/graphene/polyaniline composite for SC use. The material was synthesized through a two-step process involving hydrothermal treatment followed by polymerization, as illustrated in Fig. 20. Their results showed a $C_{\rm s}$ of 454.8 F g⁻¹ at a I_d of 0.2 A g^{-1} . Additionally, the material demonstrated strong rate capability, retaining 75.8% of its capacity at 5 A g⁻¹, along with 76.4% C_s retention after 5000 cycles at 2 A g⁻¹. Huang et al.58 developed a MnO2/PANI/MWCNTs ternary nanocomposite for SCs. This composite was evaluated in a 1 M KOH electrolyte, where it achieved a maximum C_s of 395 F g⁻¹. Furthermore, the material retained 72% of its C_s after 1000 CD cycles at I_d of 1 A g⁻¹. Xiong et al.⁵⁹ developed a cobalt ferrite/ graphene/polyaniline ternary nanocomposite through a twostep process involving hydrothermal synthesis followed by in situ polymerization, as illustrated in Fig. 21. The electrochemical analysis revealed a C_s of 1133.3 F g⁻¹ at a ν of 1 mV s⁻¹, and 767.7 F g^{-1} at a I_d of 0.1 A g^{-1} in a three-electrode system. The material also demonstrated excellent cycling stability, retaining 96% of its C_s after 5000 cycles. Wang et al. 60 synthesized a nitrogen-doped graphene/nickel ferrite/polyaniline (NGNP) ternary nanocomposite through a two-step process involving hydrothermal synthesis and polymerization. The composite exhibited a C_s of 645.0 F g⁻¹ at a ν of 1 mV s⁻¹. When tested in a two-electrode symmetric configuration, the device delivered an E_d of 23.2 W h kg⁻¹ at a P_d of 27.7 W kg⁻¹. The material demonstrated excellent cycling stability, with only a 5% drop in C_s after 5000 cycles and a 10% drop after 10 000 cycles, indicating its potential for SC applications. Shafi et al.61 developed a ternary composite consisting of LaMnO3, reduced graphene oxide (RGO), and polyaniline (PANI) using an in situ polymerization method. This composite was utilized to construct two types of SCs: a SSC (LaMnO₃/RGO/PANI//LaMnO₃/ RGO/PANI) and an ASC (LaMnO₃/RGO/PANI//RGO). The ASC demonstrated a C_s of 111 F g^{-1} at I_d of 2.5 A g^{-1} , maintaining over 50% C_s retention at a higher I_d of 20 A g^{-1} . Additionally, this device achieved a maximum $E_{\rm d}$ of 50 W h kg⁻¹ at a $P_{\rm d}$ of 2.25 kW kg⁻¹. Maity et al.⁶² developed a composite material consisting of boron nitride (BN), CNTs, and PANI using a simple synthesis method. This composite exhibited a $C_{\rm s}$ of 387.5 F g⁻¹ at $I_{\rm d}$ of 1 A ${\rm g}^{-1}$ when tested in a 1 M KCl electrolyte solution. The BN/CNT/PANI composite demonstrated an impressive E_d of 34.44 W h kg⁻¹ at a $P_{\rm d}$ of 400 W kg⁻¹. Furthermore, the composite maintained an 87% $C_{\rm s}$ retention after 600 CD cycles, showcasing its excellent cycling stability.

Atram et al.63 synthesized a novel ternary nanocomposite, CNF/NiFe₂S₄/PANI, using a combination of electrospinning and in situ polymerization techniques. The preparation method and electrochemical results for this composite are illustrated in Fig. 22. The CV curve for CNF/NiFe₂S₄/PANI showed a significantly larger enclosed area compared to CNF, PANI, and CNF/NiFe₂S₄ at the same ν of 10 mV s⁻¹, indicating a superior capacitive performance. This enhancement is attributed to the increased number of active sites in the CNF/NiFe $_2$ S $_4$ /PANI structure. The ternary nanocomposite achieved a maximum C_s of 645 F g^{-1} at




Fig. 19 (a), (c), and (e) CV curves at varying ν (b), (d), and (f) GCD curves at different I_d of AC, 25NiO@Co₃O₄-AC and 25Co₃O₄@NiO-AC electrodes, respectively (reproduced from ref. 52 with permission from Elsevier@ 2023).




Fig. 20 Schematic illustration for the formation of ternary manganese ferrite/graphene/polyaniline nanostructure (reproduced from ref. 57 with permission from Elsevier© 2014).




Fig. 21 Schematic illustration for the preparation of ternary cobalt ferrite/graphene/polyaniline nanocomposites (reproduced from ref. 59 with permission from Elsevier© 2014).

a I_d of 1 A g^{-1} , outperforming the CNF/NiFe₂S₄ binary composite, which exhibited a C_s of 460 F g^{-1} at the same I_d . Additionally, it demonstrated excellent cycling stability, retaining 60% of its C_s after 5000 cycles. The composite also delivered

a maximum $E_{\rm d}$ of 22.38 W h kg⁻¹ at a $P_{\rm d}$ of 125 W kg⁻¹. Raza *et al.*⁶⁴ fabricated a composite of NiCo₂S₄, g-C₃N₄, and PANI (NiCo₂S₄/g-C₃N₄/PANI) using a combination of hydrothermal synthesis, thermal condensation, and chemical oxidative




Fig. 22 (a) Schematic representation for the preparation of CNF/NiFe₂S₄/PANI (b) I_d vs. C_s curve (c) cycling stability of CNF, PANI, CNF/NiFe₂S₄, and CNF/NiFe₂S₄/PANI (reproduced from ref. 63 with permission from Elsevier© 2021).

polymerization techniques. The resulting electrode exhibited a C_a of 3.4 F cm⁻² (equivalent to 1799.07 F g⁻¹) and demonstrated impressive stability, retaining 90% of its C_a after 2700 cycles at a I_d of 2 mA cm⁻². The material's rate capability showed a gradual decline, with Ca retention of 87.36% at 5 mA cm⁻², 82.92% at 10 mA cm⁻², and 50.35% at a higher I_d of 20 $mA cm^{-2}$.

Karim et al. 65 developed a novel ternary electrode material for SCs by sonochemically synthesizing CNTs-PANI/CoNi(PO₄)₂ nanocomposites. The incorporation of the phosphate group in this ternary system is a unique approach, as the use of phosphates in SC electrode materials is relatively rare. The resulting nanocomposites exhibited an impressive C_s of 1268 C g⁻¹ (2136 F g^{-1}) and demonstrated excellent diffusive behavior. Furthermore, they fabricated a HSC device using the CNTs-PANI/ CoNi(PO₄)₂ nanocomposites as the PE and AC as the NE. This device showcased an outstanding E_d of 87 W h kg⁻¹ and a high $P_{\rm d}$ of 680 W kg⁻¹. Remarkably, the device maintained an

excellent cyclic performance, retaining nearly 100% of its capacity after 5000 CD cycles. The synergistic effects of the various components in the ternary nanocomposite, namely the CNT, PANI, and CoNi(PO₄)₂, contributed to the enhanced electrochemical performance of the SC.

PPy is another promising material for SC electrodes due to its high energy storage capacity, excellent electrical conductivity through doping and de-doping processes, ease of synthesis, and stability. Wang et al.66 synthesized a graphene/SnO2/PPy (GSP) nanocomposite electrode via a one-pot in situ polymerization method. When tested in a 1 M H₂SO₄ electrolyte, the material demonstrated a high C_s of 616 F g^{-1} at a ν of 1 mV s^{-1} , along with an $E_{\rm d}$ of 19.4 W h kg $^{-1}$ and a $P_{\rm d}$ of 9973.26 W kg $^{-1}$. In another study, Oraon et al.67 developed a nanoclay-based ternary graphene/PPv nanocomposite using both in situ and ex situ polymerization techniques. When tested in 1 M KCl with a potential window of 0 to 0.8 V, the composite produced via in situ polymerization showed a C_s of 347 F g⁻¹ at a ν of 10 mV s⁻¹,

Table 3 Comparative table of ternary transition metal composites for SCs

S. no.	Composite material	Formula	Conductivity	Current density	Cyclic stability	References
1	Nanocomposites of cobalt oxide-AC and nickel oxide- AC	25NiO@Co ₃ O ₄ -AC	691.8 F g ⁻¹	1 A g ⁻¹	98.1% after 5000 cycles	52
2	Bead-chain ternary nanocomposite	$\mathrm{Cu_2O} ext{-Mn}_3\mathrm{O}_4 ext{-NiO}$	$1306 \; \mathrm{F} \; \mathrm{g}^{-1}$	$5~\mathrm{mV~s^{-1}}$	96% after 3000 cycles	53
3	Mn–Ti with rGO ternary nanocomposite	$\mathrm{Mn_3O_4/TiO_2/rGO}$	356 F g^{-1}	1 A g^{-1}	91% after 10 000 cycles	54
4	CoNi-layered double hydroxide	CoNi-LDH/NiCo ₂ S ₄ / RGO	1846.66 F g ⁻¹	1 A g^{-1}	93.57% after 5000 cycles	55
5	NiCo-layered double hydroxide nanotube arrays	NiCo ₂ S ₄	2938.2 F g^{-1}	1 A g^{-1}	76.5% after 10 000 cycles	56
6	Manganese ferrite/ graphene/polyaniline composite	MnFe ₂ O ₄ /PANI/ MWCNTs	454.8 F g ⁻¹	5 A g ⁻¹	76.4% after 5000 cycles	57
7	Manganese oxide/ polyaniline/MW carbon nanotube based ternary nanocomposite	MnO ₂ /PANI/ MWCNTs	395 F g ⁻¹	1 A g ⁻¹	72% after 1000 cycles	58
8	Cobalt ferrite/graphene/ polyaniline ternary nanocomposite	CoFe ₂ O ₄ /G/PANI	1133.3 F g ⁻¹ 767.7 F g ⁻¹	1 mV s ⁻¹ 0.1 A g ⁻¹	96% after 5000 cycles	59
9	Boron nitride (BN), CNTs, and PANI based composite	BN/CNT/PANI	387.5 F g^{-1}	1 A g^{-1}	87% after 600 cycles	62
10	Novel ternary nanocomposite	CNF/NiFe ₂ S ₄ /PANI	$645~\mathrm{F~g}^{-1}$	1 A g^{-1}	60% after 5000 cycles	63
11	Composite of NiCo ₂ S ₄ , g-C ₃ N ₄ , and PANI	NiCo ₂ S ₄ /g-C ₃ N ₄ / PANI	1799.07 F g ⁻¹	1 A g^{-1}	90% after 2700 cycles	64
12	Novel ternary electrode material	CNTs-PANI/ CoNi(PO ₄) ₂	$2136 \; \mathrm{F} \; \mathrm{g}^{-1}$	1 A g^{-1}	100% after 5000 cycles	65
13	Graphene/SnO ₂ /PPy (GSP) nanocomposite	SnO ₂ /G/PPy	616 F g^{-1}	$1~\mathrm{mV~s^{-1}}$	90% after 5000 cycles	66
14	Zinc-ion hybrid capacitors (ZHCs)	Zn ²⁺ /CF ₃ SO ₃ / NHPCs-700	$253~\mathrm{mA~h~g}^{-1}$	$0.2~{ m A~g}^{-1}$	94% after 200 000 cycles	69
15	Co-doped W ₁₈ O ₄₉ on carbon cloth (CC)	Co-doped W ₁₈ O ₄₉ / CC	792 F g^{-1}	$1.0~{\rm A~g}^{-1}$	90% after 10 000 cycles	70
16	Nickle cobalt oxide with ZnO–CuO composite based nano-structures and nickel foam	NiCo ₂ O ₄ /ZnO-CuO/ NF	3614.8 F g ⁻¹	2 A g^{-1}	98% after 40 000 cycles	71

RSC Advances Review

outperforming the *ex situ* composite. This research highlights the role of nanoclay in enhancing C_s , demonstrating the potential of nanocomposites for SCs. Similarly, Ishaq *et al.*⁶⁸ investigated a ternary composite made of graphene, doped metal oxides (iron oxide), and PPy, revealing C_s of 147 F g⁻¹ for an rGO/MnFe₂O₄ binary composite and 232 F g⁻¹ for the rGO/MnFe₂O₄/PPy ternary composite. The improvement in C_s for the ternary material showcases the synergistic effect of the PPy additives (Table 3).

4. Summary and future scope

In this paper, we explored the potential composite materials as energy storage electrode that can be fabricated by combining transition metal oxides/hydroxides, chalcogenides, phosphides/phosphates with carbon and/or conducting polymers to form binary and ternary composites for SC applications. This paper demonstrated that these composite materials as energy storage electrode exhibit superior electrochemical performance compared to their respective individual. This enhancement is attributed to the synergistic effects that not only create efficient pathways for electron and ion transfer but also ensure the structural integrity and stability of the entire electrode. Although binary composite materials have been wellexplored, there is still significant untapped potential in a new class of metal compounds, specifically metal phosphides and phosphates. These materials, when combined with carbon, conducting polymers, or other phosphates/phosphides, remain largely unexplored. Due to the lower electronegativity of phosphorus, these compounds exhibit inherent properties that could contribute to high C_s and E_d in SCs. Researchers are encouraged to investigate the potential of such composites. In the realm of ternary composites, research has predominantly focused on metal oxides, leaving other groups such as metal chalcogenides, metal phosphides, and phosphates relatively unexplored. Considering the synergistic advantages that can arise from combining different electrode materials, there is a compelling opportunity to study ternary composites involving these less-explored compounds for SC applications. The fabrication of composite materials as energy storage electrode typically involves multiple steps (often 2-3), which can reduce costeffectiveness and make the process time-consuming. Researchers are encouraged to explore methods like electrospinning and solvothermal synthesis, which can produce binary composites in a single step. These methods can also streamline the preparation of ternary composites, making the process more sustainable, energy efficient and cost-effective.

5. Conclusion

The transition metal-based composites represent a highly promising class of materials for the development of high-performance supercapacitors. The ability to combine multiple materials within binary and ternary composites allows for the synergistic enhancement of electrochemical properties, resulting in superior energy storage capabilities compared to conventional single-material electrodes. These composites offer

advantages such as improved energy density, extended cycle life, and a broader voltage window, which are critical for meeting the growing demand for efficient and durable energy storage systems. However, challenges remain in optimizing the synthesis, stability, and scalability of these materials for commercial applications. Future research should focus on overcoming these obstacles by exploring novel material combinations, optimizing fabrication methods, and understanding the long-term performance under real-world conditions. With continued advancements, transition metal-based composites have the potential to play a pivotal role in the future of high-performance energy storage systems, contributing to the development of more efficient, reliable, and sustainable technologies.

Data availability

This review article is a comprehensive synthesis of previously published literature and does not include original experimental data. All data and information discussed in the manuscript are sourced from publicly available publications, which are appropriately cited throughout the text. As such, no primary data generated or analyzed for the purpose of this review article are available.

Author contributions

Jannatun Zia – writing original draft, conceptualization, review, and methodology, while M. S. S. R. Tejaswini was responsible for writing comparative tables, reviewing, visualization, and editing the article.

Conflicts of interest

The authors declare no competing interest.

Acknowledgements

Jannatun Zia acknowledges the Department of Chemistry, Sid-dhartha Academy of Higher Education, Deemed University, Vijayawada, A. P., India, for providing a suitable research laboratory to carry out the review work. M. S. S. R. Tejaswini acknowledges the Department of Chemistry, School of Applied sciences & Humanities, Vignan's Foundation for Science, Technology & Research, Guntur, Andhra Pradesh India, for research collaboration.

References

- 1 W. Raza, F. Ali, N. Raza, Y. Luo, K. H. Kim, J. Yang, S. Kumar, A. Mehmood and E. E. Kwon, *Nano Energy*, 2018, 52, 441–473.
- 2 A. Tundwa, H. Kumar, B. J. Binoj, R. Sharma, G. Kumar, R. Kumari, A. Dhayal, A. Yadav, D. Singh and P. Kumar, *RSC Adv.*, 2024, **14**, 9406–9439.
- 3 B. Scrosati and J. Garche, *J. Power Sources*, 2010, **195**, 2419–2430.

- 4 K. Sambath Kumar, N. Choudhary, Y. Jung and J. Thomas, *ACS Energy Lett.*, 2018, 3, 482–495.
- 5 J. Libich, J. Máca, J. Vondrák, O. Čech and M. Sedlaříková, *J. Energy Storage*, 2018, **17**, 224–227.
- 6 F. Wang, X. Wu, X. Yuan, Z. Liu, Y. Zhang, L. Fu, Y. Zhu, Q. Zhou, Y. Wu and W. Huang, *Chem. Soc. Rev.*, 2017, 46, 6816–6854.
- 7 Z. S. Iro, C. Subramani and S. S. Dash, *Int. J. Electrochem. Sci.*, 2016, **11**, 10628–10643.
- 8 P. Xiong, J. Zhu and X. Wang, *J. Power Sources*, 2015, **294**, 31–50.
- 9 L. Li, Y. Huang and Y. Li, EnergyChem, 2020, 2, 100024.
- 10 L. Zhang and X. S. Zhao, Chem. Soc. Rev., 2009, 38, 2520–2531.
- 11 Y. Kim, T. Park, J. Na, J. W. Yi, J. Kim, M. Kim, Y. Bando, Y. Yamauchi and J. Lin, *Nanoscale*, 2020, **12**, 8608–8625.
- 12 Y. Dahiya, M. Hariram, M. Kumar, A. Jain and D. Sarkar, *Coord. Chem. Rev.*, 2022, **45**, 214265.
- 13 K. Ren, Z. Liu, T. Wei and Z. Fan, *Nano-Micro Lett.*, 2021, **13**, 129.
- 14 R. Liu, A. Zhou, X. Zhang, J. Mu, H. Che, Y. Wang, T. T. Wang, Z. Zhang and Z. Kou, J. Chem. Eng., 2021, 412, 128611.
- 15 M. Cui and X. Meng, Nanoscale Adv., 2020, 2, 5516-5528.
- 16 A. Pramitha and Y. Raviprakash, J. Energy Storage, 2022, 49, 104120.
- 17 R. R. Atram, N. V. Mangate, R. G. Atram and S. B. Kondawar, J. Electrochem. Energy Convers. Storage, 2021, 18, 041003.
- 18 J. Zhao, J. Zhang, H. Yin, Y. Zhao, G. Xu, J. Yuan, X. Mo, J. Tang and F. Wang, *Nanomaterials*, 2022, 12, 128–134.
- 19 C. Sun, G. Shang, H. Qiu, Y. Zhang and W. He, *Vacuum*, 2024, 227, 113437.
- 20 A. Choubey and A. Yadav, J. Energy Storage, 2024, 79, 110131.
- 21 D. Khalafallah, F. Qiao, C. Liu, J. Wang, Y. Zhang, J. Wang, Q. Zhang and P. H. L. Notten, *Coord. Chem. Rev.*, 2023, 496, 215405.
- 22 Z. A. Sheikh, P. K. Katkar, H. Kim, S. Rehman, K. Khan, V. D. Chavan, R. Jose, M. F. Khan and D. kee Kim, *J. Energy Storage*, 2023, **71**, 107997.
- 23 K. P. Shwetha, Y. Athreya, L. Suraj, C. Kumar Rastogi, M. K. Sudha Kamath, K. Natarajan, A. Khosla and C. Manjunatha, *Mater. Today: Proc.*, 2023, 73, 274–285.
- 24 N. Thakur, P. Kumar, S. Sharda, P. Sharma and A. Ibrahim, *J. Optoelectron. Adv. Mater.*, 2023, 25, 68–82.
- 25 A. C. Lokhande, S. Teotia, A. R. Shelke, T. Hussain, I. A. Qattan, V. C. Lokhande, S. Patole, J. H. Kim and C. D. Lokhande, J. Chem. Eng., 2020, 399, 125711.
- 26 B. Pandit, S. S. Karade and B. R. Sankapal, ACS Appl. Mater. Interfaces, 2017, 9, 44880–44891.
- 27 B. Kirubasankar, V. Murugadoss, J. Lin, T. Ding, M. Dong, H. Liu, J. Zhang, T. Li, N. Wang, Z. Guo and S. Angaiah, *Nanoscale*, 2018, 10, 20414–20425.
- 28 T. Kshetri, T. I. Singh, Y. S. Lee, D. D. Khumujam, N. H. Kim and J. H. Lee, *Composites, Part B*, 2021, **211**, 2101312.
- 29 Q. Zong, C. Liu, H. Yang, Q. Zhang and G. Cao, *Nano Today*, 2021, **38**, 101201.

- 30 X. Li, A. M. Elshahawy, C. Guan and J. Wang, *Small*, 2017, **13**, 1701530.
- 31 R. Murugavel, A. Choudhury, M. G. Walawalkar, R. Pothiraja and C. N. R. Rao, *Chem. Rev.*, 2008, **108**, 3549–3655.
- 32 A. A. Mirghni, M. J. Madito, T. M. Masikhwa, K. O. Oyedotun, A. Bello and N. Manyala, J. Colloid Interface Sci., 2017, 494, 325–337.
- 33 C. An, Y. Wang, Y. Wang, G. Liu, L. Li, F. Qiu, Y. Xu, L. Jiao and H. Yuan, *RSC Adv.*, 2013, **3**, 4628–4633.
- 34 Z. Zhao, Y. Miao and Q. Lu, *J. Power Sources*, 2024, **606**, 234587.
- 35 A. Agarwal, S. Majumder and B. R. Sankapal, *J. Energy Storage*, 2023, **58**, 106396.
- 36 Q. Wang, H. Yuan, M. Zhang, N. Yang, S. Cong, H. Zhao, X. Wang, S. Xiong, K. Li and A. Zhou, ACS Appl. Electron. Mater., 2023, 5, 2506–2517.
- 37 H. Chen, L. Yu, Z. Lin, Q. Zhu, P. Zhang, N. Qiao and B. Xu, *J. Mater. Sci.*, 2020, **55**, 1148–1156.
- 38 X. Zhao, J. Zhang, K. Lv, N. Kong, Y. Shao and J. Tao, *Carbon*, 2022, **200**, 38–46.
- 39 L. Sun, G. Song, Y. Sun, Q. Fu and C. Pan, ACS Appl. Mater. Interfaces, 2020, 12, 44777–44788.
- 40 S. Zhang, Y. Huang, J. Wang, X. Han, C. Chen and X. Sun, Appl. Surf. Sci., 2022, 599, 154015.
- 41 H. Wang, J. Lin and Z. X. Shen, J. Sci.:Adv. Mater. Devices, 2016, 1, 225-255.
- 42 G. A. Snook, P. Kao and A. S. Best, *J. Power Sources*, 2011, **196**, 1–12.
- 43 X. Yang, K. Xu, R. Zou and J. Hu, *Nano-Micro Lett.*, 2016, 8, 143–150.
- 44 D. Kong, W. Ren, C. Cheng, Y. Wang, Z. Huang and H. Y. Yang, ACS Appl. Mater. Interfaces, 2015, 7, 21334–21346.
- 45 A. K. Das, B. Ramulu, E. G. Shankar and J. Su Yu, *J. Chem. Eng.*, 2022, **11**, 429.
- 46 A. Liu, L. Tang, L. Gong, S. Wu and J. Tang, *J. Electroanal. Chem.*, 2022, **923**, 116734.
- 47 C. Yue, B. Hu, W. Huang, A. Liu, Z. Guo, J. Mu, X. Zhang, X. Liu and H. Yuan, *J. Electroanal. Chem.*, 2021, **899**, 1177–1180
- 48 W. L. Wu, D. J. Niu, J. F. Zhu, Y. Gao, D. Wei, X. H. Liu, F. Wang, L. Wang and L. Q. Yang, *J. Electroanal. Chem.*, 2019, **847**, 113203.
- 49 W. L. Wu, D. Wei, J. F. Zhu, D. J. Niu, F. Wang, L. Wang, L. Q. Yang, P. P. Yang and C. W. Wang, *Ceram. Int.*, 2019, 45, 7328–7337.
- 50 S. Wustoni, A. Saleh, J. K. El-Demellawi, A. Koklu, A. Hama, V. Druet, N. Wehbe, Y. Z. Zhang and S. Inal, *APL Mater.*, 2020, 8, 121105.
- 51 M. Boota, B. Anasori, C. Voigt, M. Q. Zhao, M. W. Barsoum and Y. Gogotsi, *Adv. Mater.*, 2016, **28**, 1517–1522.
- 52 M. S. Gouda, M. Shehab, S. Helmy, M. Soliman and R. S. Salama, *J. Energy Storage*, 2023, **61**, 106806.
- 53 L. Su, C. Zhang, L. Shu, L. Huang, J. Li and H. Qin, *Nano*, 2020, **15**, 6.
- 54 M. El-Shahat, M. Mochtar, M. M. Rashad and M. A. Mousa, *J. Solid State Electrochem.*, 2021, 25, 803–819.

55 Y. Guo, C. Hao, X. Wang, Y. Yang, X. Wang, J. Wu and

RSC Advances

- Y. Shen, Ceram. Int., 2022, 48, 17644-17653.
 H. Jia, M. Wang, M. Feng, G. Li, L. Li and Y. Liu, J. Chem. Eng., 2024, 484, 149649.
- 57 P. Xiong, C. Hu, Y. Fan, W. Zhang, J. Zhu and X. Wang, *J. Power Sources*, 2014, **266**, 384–392.
- 58 Y. Huang, J. Lu, S. Kang, D. Weng, L. Han and Y. Wang, *Int. J.*
- Electrochem. Sci., 2019, 14, 9298–9310. 59 P. Xiong, H. Huang and X. Wang, J. Power Sources, 2014, 245,
- 937–946.
- 60 W. Wang, Q. Hao, W. Lei, X. Xia and X. Wang, *J. Power Sources*, 2014, **269**, 250–259.
- 61 P. M. Shafi, V. Ganesh and A. C. Bose, ACS Appl. Energy Mater., 2018, 1, 2802–2812.
- 62 C. K. Maity, G. Hatui, S. Sahoo, P. Saren and G. C. Nayak, *ChemistrySelect*, 2019, 4, 3672–3680.
- 63 R. R. Atram, V. M. Bhuse, R. G. Atram, C. M. Wu, P. Koinkar and S. B. Kondawar, *Mater. Chem. Phys.*, 2021, **262**, 124523.

- 64 M. A. Raza, M. I. Yousaf, S. Akram, A. Siddique, M. Ashraf and D. J. Fu, Synth. Met., 2024, 301, 117534.
- 65 M. R. Abdul Karim, W. Shehzad, M. Atif, E. ul Haq and Z. Abbas, *Energy Environ.*, 2024, 7, 2057.
- 66 W. Wang, Q. Hao, W. Lei, X. Xia and X. Wang, RSC Adv., 2012, 2, 10268–10274.
- 67 R. Oraon, A. De Adhikari, S. K. Tiwari, T. S. Sahu and G. C. Nayak, *Appl. Clay Sci.*, 2015, 118, 231–238.
- 68 S. Ishaq, M. Moussa, F. Kanwal, M. Ehsan, M. Saleem, T. N. Van and D. Losic, *Sci. Rep.*, 2019, **9**, 1–11.
- 69 X. Yang, C. Hu, Y. Chen, Z. Song, L. Miao, Y. Lv, H. Duan, M. Liu and L. Gan, J. Energy Storage, 2024, 104, 114509.
- 70 M. R. Thalji, G. A. M. Ali, J. J. Shim and K. F. Chong, *Adv. Compos. Hybrid Mater.*, 2025, **8**, 148.
- 71 M. A. Bhatti, S. Kumar, A. Tahira, A. L. Bhatti, Z. A. Ujjan, M. A. Jakhrani, U. Aftab, R. H. Alshammari, A. Nafady, E. Dawi, M. Emo, B. Vigolo, A. I. Molina and Z. H. Ibupoto, J. Chem. Eng., 2023, 473, 145341.