


**Showcasing research from Professor Domen's laboratory, Research Initiative for Supra-Materials, Shinshu University, Nagano, Japan and Office of University Professors, The University of Tokyo, Tokyo, Japan**

Zr-doped BaTaO<sub>2</sub>N photocatalyst modified with Na-Pt cocatalyst for efficient hydrogen evolution and Z-scheme water splitting

Direct decomposition of water into hydrogen and oxygen using particulate photocatalysts is a simple and cost-effective approach towards renewable solar hydrogen production on a large scale. We have realized a Z-scheme water splitting system that can operate under visible light at wavelengths up to 520 nm. The Z-scheme system comprises a modified BaTaO<sub>2</sub>N as a hydrogen evolution photocatalyst, BiVO<sub>4</sub> as an oxygen evolution photocatalyst, and [Fe(CN)<sub>6</sub>]<sup>3-/4-</sup> as a redox mediator. We describe how the performance of BaTaO<sub>2</sub>N and associated Z-scheme system can be upgraded.

**As featured in:**



See Kazunari Domen *et al.*,  
*EES Catal.*, 2023, 1, 26.


 Cite this: *EES Catal.*, 2023,  
 1, 26

## Zr-doped BaTaO<sub>2</sub>N photocatalyst modified with Na–Pt cocatalyst for efficient hydrogen evolution and Z-scheme water splitting†

 Huihui Li,<sup>ab</sup> Junie Jhon M. Vequizo,<sup>b</sup> Takashi Hisatomi,<sup>bc</sup>  
 Mamiko Nakabayashi,<sup>d</sup> Jiadong Xiao,<sup>b</sup> Xiaoping Tao,<sup>b</sup> Zhenhua Pan,<sup>b</sup>  
 Wenpeng Li,<sup>e</sup> Shanshan Chen,<sup>f</sup> Zheng Wang,<sup>g</sup> Naoya Shibata,<sup>d</sup>  
 Akira Yamakata,<sup>h</sup> Tsuyoshi Takata<sup>b</sup> and Kazunari Domen<sup>ib</sup>\*

BaTaO<sub>2</sub>N exhibits hydrogen evolution activity under visible light with wavelengths up to 650 nm and is applicable to Z-scheme overall water splitting (ZOWS). However, the insufficient activity and selectivity of BaTaO<sub>2</sub>N in the presence of redox mediators limit the efficiency of this process. Herein, we report the use of modified BaTaO<sub>2</sub>N as a hydrogen evolution photocatalyst in combination with BiVO<sub>4</sub> and [Fe(CN)<sub>6</sub>]<sup>3-/4-</sup> as the oxygen evolution photocatalyst and redox mediator, respectively. Zr-doped BaTaO<sub>2</sub>N (BaTaO<sub>2</sub>N:Zr) synthesized by flux-assisted thermal nitridation and decorated with Na and Pt (Na–Pt) as cocatalysts was found to provide higher hydrogen evolution activity than undoped BaTaO<sub>2</sub>N. Zr doping extended the lifetime of electrons in the BaTaO<sub>2</sub>N and promoted electron injection into the Na–Pt cocatalysts. Consequently, Na–Pt/BaTaO<sub>2</sub>N:Zr modified with Cr<sub>2</sub>O<sub>3</sub> to suppress reverse reactions evolved hydrogen from an aqueous K<sub>4</sub>[Fe(CN)<sub>6</sub>] solution. Optimizing the BaTaO<sub>2</sub>N photocatalyst and the reaction conditions provided a ZOWS system capable of operating under visible light at wavelengths up to 520 nm. This work indicates that ZOWS systems operable under visible light can be constructed based on detailed investigations of photocatalysts, cocatalysts and redox mediators.

 Received 26th August 2022,  
 Accepted 6th November 2022

DOI: 10.1039/d2ey00031h

[rsc.li/eescatalysis](http://rsc.li/eescatalysis)

### Broader context

Direct decomposition of water into hydrogen and oxygen using particulate photocatalysts is a simple and cost-effective approach towards renewable solar hydrogen production on a large scale. Z-scheme overall water splitting (ZOWS) comprising two-step excitation of a hydrogen evolution photocatalyst (HEP) and an oxygen evolution photocatalyst (OEP) has attracted significant interest, because narrow bandgap photocatalysts can be applied to this process if these materials are active during either the hydrogen or oxygen evolution reactions. However, the past ZOWS systems mostly used wide bandgap semiconductors as either HEPs or OEPs, restricting the use of long-wavelength visible light. This work extends the wavelength range of visible light that can be used for ZOWS by improving the performance of a narrow bandgap oxynitride (BaTaO<sub>2</sub>N) as the HEP and by selecting an appropriate redox couple for electron transfer. This represents an essential advance towards achieving the solar energy conversion efficiency required for practical photocatalytic hydrogen production. The practice of comprehensive refinement of narrow bandgap oxynitride photocatalysts, cocatalysts, and redox mediators effective for ZOWS will guide the research and development of photocatalytic solar hydrogen production.

<sup>a</sup> School of Materials and Energy, Lanzhou University, 222 South Tianshui Road, Lanzhou 730000, China

<sup>b</sup> Research Initiative for Supra-Materials, Interdisciplinary Cluster for Cutting Edge Research, Shinshu University, Nagano-shi, Nagano 380-8553, Japan.  
 E-mail: [domen@shinshu-u.ac.jp](mailto:domen@shinshu-u.ac.jp)
<sup>c</sup> PRESTO, JST, 4-17-1 Wakasato, Nagano-shi, Nagano 380-8553, Japan

<sup>d</sup> Institute of Engineering Innovation, The University of Tokyo, Tokyo 113-8656, Japan

<sup>e</sup> Department of Science and Technology, Graduate School of Medicine, Science and Technology, Shinshu University, 4-17-1 Wakasato, Nagano 380-8553, Japan

<sup>f</sup> School of Materials Science and Engineering & National Institute for Advanced Materials, Nankai University, Tianjin 300-350, China

<sup>g</sup> Research Center for Eco-Environmental Sciences, Chinese Academy of Sciences, Beijing 100085, China

<sup>h</sup> Faculty of Natural Science and Technology, Okayama University, 3-1-1, Tsushima-naka, Kita-ku, Okayama, Japan

<sup>i</sup> Office of University Professors, The University of Tokyo, 2-11-16 Yayoi, Bunkyo-ku, Tokyo 113-8656, Japan

 † Electronic supplementary information (ESI) available: Characterization results including those obtained using ICP-OES and N–O analysis; photocatalytic HER data. See DOI: <https://doi.org/10.1039/D2EY00031H>


## Introduction

Z-scheme overall water splitting (ZOWS) comprising two-step excitation of a H<sub>2</sub>-evolving photocatalyst (HEP) and O<sub>2</sub>-evolving photocatalyst (OEP) has attracted significant interest as a means of harvesting solar energy. Narrow-bandgap materials can be applied to this process if these compounds are active during either the hydrogen or oxygen evolution reactions, and photocatalyst sheets have exhibited efficient scalable ZOWS.<sup>1</sup> The use of p-type semiconductors as HEPs is likely to be essential in the sheet system because the ZOWS mechanism is similar to that for photoelectrochemical cells. Many Cu-based chalcogenides are narrow-bandgap p-type semiconductors, but improving the durability and efficiency of such materials in ZOWS remains challenging.<sup>2,3</sup> In contrast, ZOWS systems based on a suspended HEP and OEP together with ionic electron mediators can operate even when both the HEP and OEP are n-type semiconductors. This is possible because charge transfer between the HEP and OEP can occur *via* photocatalytic reactions of mediator ions instead of at junctions between bulk solid materials.<sup>4–8</sup> Many ZOWS systems have been reported to date. As an example, Qi *et al.* demonstrated a ZrO<sub>2</sub>/TaON–[Fe(CN)<sub>6</sub>]<sup>3–/4–</sup>–BiVO<sub>4</sub> system.<sup>9</sup> The ZrO<sub>2</sub>/TaON and BiVO<sub>4</sub> photocatalysts can utilize visible light up to 500 and 520 nm, respectively. However, achieving the target solar-to-hydrogen energy conversion efficiency (STH) of 5% or greater required for practical photocatalytic hydrogen production will necessitate the utilization of materials capable of using solar radiation at wavelengths above 530 nm for ZOWS.

BaTaO<sub>2</sub>N has an absorption edge wavelength of 650 nm and so is a promising candidate for photocatalytic water splitting under visible light.<sup>10–15</sup> Single-crystalline particulate BaTaO<sub>2</sub>N can be obtained by RbCl flux-assisted nitridation.<sup>16</sup> When loaded with a Pt cocatalyst decorated with Na, this compound exhibits excellent hydrogen evolution activity from aqueous methanol solutions, while unmodified BaTaO<sub>2</sub>N is inactive.<sup>17</sup> The addition of Na ensures wide dispersion of the Pt nanoparticles during the hydrogen reduction treatment and these highly-dispersed nanoparticles effectively catalyze the hydrogen evolution reaction (HER) on the BaTaO<sub>2</sub>N. Domen *et al.* reported ZOWS using BaTaO<sub>2</sub>N as the HEP, WO<sub>3</sub> as the OEP and IO<sub>3</sub><sup>–</sup>/I<sup>–</sup> as the ionic shuttle.<sup>16,17</sup> Despite the ability of BaTaO<sub>2</sub>N to utilize visible light, the use of WO<sub>3</sub>, which has a wide bandgap, restricts the use of wavelengths above 450 nm by this system. Therefore, it would be an important breakthrough to combine BaTaO<sub>2</sub>N with OEPs having narrower bandgaps, such as BiVO<sub>4</sub>.<sup>18</sup> Unfortunately, the low activity of BaTaO<sub>2</sub>N in the presence of reversible redox mediators hampers the realization of such ZOWS systems.

Doping is a simple but effective means of tuning the properties of photocatalysts so as to improve their activity. In the case of BaTaO<sub>2</sub>N, doping with Zr tends to enhance performance by suppressing the formation of Ta<sup>3+</sup> defects during the thermal nitridation process. Abe *et al.* demonstrated a negative shift in the photoanodic current onset potential when using Zr-doped BaTaO<sub>2</sub>N.<sup>19</sup> Our own group also synthesized BaZrO<sub>3</sub>–BaTaO<sub>2</sub>N

solid solutions that exhibited improved photocatalytic hydrogen evolution from water under visible light.<sup>20</sup> Accordingly, it is expected that the hydrogen evolution activity of BaTaO<sub>2</sub>N synthesized using nitridation in conjunction with a RbCl flux could be improved by doping with Zr. Another important consideration related to ZOWS systems is the ionic electron mediator, which can induce backward reactions. It is therefore important to improve not only the photoreduction activity but the selectivity for the HER associated with the reduction of the ionic electron mediator. This can be accomplished by surface modification of the BaTaO<sub>2</sub>N photocatalyst to control the reaction selectivity.


The present work devised an efficient ZOWS system based on Zr-doped BaTaO<sub>2</sub>N (denoted herein as BaTaO<sub>2</sub>N:Zr) as the HEP combined with BiVO<sub>4</sub> modified with Au and CoO<sub>x</sub> (denoted as CoO<sub>x</sub>/Au/BiVO<sub>4</sub>) as the OEP and [Fe(CN)<sub>6</sub>]<sup>3–</sup>/[Fe(CN)<sub>6</sub>]<sup>4–</sup> as the redox mediator.<sup>9</sup> The BaTaO<sub>2</sub>N:Zr photocatalyst was additionally loaded with a Pt cocatalyst together with Na, as well as with Cr<sub>2</sub>O<sub>3</sub>.<sup>21</sup> The resulting ZOWS system (denoted as Cr<sub>2</sub>O<sub>3</sub>/Na–Pt/BaTaO<sub>2</sub>N:Zr–[Fe(CN)<sub>6</sub>]<sup>3–/4–</sup>–CoO<sub>x</sub>/Au/BiVO<sub>4</sub>) exhibited stable H<sub>2</sub> and O<sub>2</sub> evolution at the expected stoichiometric molar ratio during a 30 h trial under simulated sunlight with a STH of 0.022%. The effects of the Zr doping, Na–Pt cocatalyst loading and Cr<sub>2</sub>O<sub>3</sub> coating on the ZOWS activity of this material were evaluated.

## Results and discussion


Cation-doped BaTaO<sub>2</sub>N was prepared *via* the thermal nitridation of a mixture of the corresponding starting materials with an RbCl flux. The effect of doping was investigated by assessing the hydrogen evolution activity of doped BaTaO<sub>2</sub>N in an aqueous methanol solution under visible light after loading the Na–Pt cocatalysts. As shown in Fig. 1a, Zr doping enhanced the hydrogen evolution activity of the BaTaO<sub>2</sub>N in aqueous methanol while the other dopants investigated in this work actually lowered the activity. Zr<sup>4+</sup> has the closest valency to Ta<sup>5+</sup> and the disturbance of the anion compositions by cationic doping would be minimum, which may account for the lower hydrogen evolution reaction activity. On this basis, the optimal Zr doping amount was also investigated. The incorporation of 1% Zr in the BaTaO<sub>2</sub>N enhanced the photocatalytic H<sub>2</sub> evolution activity to the greatest extent while higher doping levels reduced the activity (Fig. 1b).

Fig. 2a presents powder XRD patterns obtained from crystals of BaTaO<sub>2</sub>N:Zr with Zr/Ta = 0, 0.01 and 0.1. The major product in all cases was evidently a perovskite-type material based on a comparison with the standard JCSd pattern for bulk BaTaO<sub>2</sub>N.<sup>17</sup> However, some small peaks ascribed to Ta<sub>3</sub>N<sub>5</sub> were observed even in the pattern for the undoped BaTaO<sub>2</sub>N. The formation of Ta<sub>3</sub>N<sub>5</sub> in the undoped BaTaO<sub>2</sub>N was attributed to a loss of barium through volatilization during the high-temperature nitridation process.<sup>22</sup> Upon adding Zr, a larger amount of Ta<sub>3</sub>N<sub>5</sub> was generated as a by-product because Zr<sup>4+</sup> ions were substituted into the Ta<sup>5+</sup> sites and a corresponding





**Fig. 1** Photocatalytic H<sub>2</sub> evolution rates obtained for (a) Na–Pt/BaTaO<sub>2</sub>N doped with various cations (M) with a M/Ta ratio of 0.01 and (b) Na–Pt/BaTaO<sub>2</sub>N:Zr with different Zr/Ta molar ratios in an aqueous solution containing methanol (15 vol%). Reaction conditions: 0.23 wt% Na 0.3 wt% Pt/BaTaO<sub>2</sub>N photocatalyst, 100 mg; 15 vol% aqueous methanol solution, 150 mL; light source, 300 W Xenon lamp equipped with a cut-off filter (420 nm < λ < 800 nm). Reaction system, Pyrex top-illuminated vessel connected to a closed gas-circulation system with a 10 kPa Ar background pressure.




**Fig. 2** (a) XRD patterns, (b) DRS spectra, and TAS decays probed at (c) 5000 cm<sup>-1</sup> (2000 nm; corresponding to electron dynamics) and (d) 15 400 cm<sup>-1</sup> (649 nm; corresponding to hole dynamics) with excitation at 470 nm for BaTaO<sub>2</sub>N, BaTaO<sub>2</sub>N:Zr0.01 and BaTaO<sub>2</sub>N:Zr0.1.

amount of Ta<sub>2</sub>O<sub>5</sub> was segregated and nitrated into Ta<sub>3</sub>N<sub>5</sub>. The deficiency of barium species with respect to the B-site elements (tantalum and zirconium) was further confirmed by chemical composition analysis (Table S1, ESI†). The Ba/(Ta + Zr) atomic ratio was found to decrease from 1.01 in BaTaO<sub>2</sub>N to 0.95 and 0.88 in BaTaO<sub>2</sub>N:Zr0.01 and BaTaO<sub>2</sub>N:Zr0.1, respectively. The specific surface areas of undoped BaTaO<sub>2</sub>N and BaTaO<sub>2</sub>N:Zr0.01 were 2.3 and 2.9 m<sup>2</sup> g<sup>-1</sup>, respectively, suggesting a decrease in the average particle size of BaTaO<sub>2</sub>N by Zr doping. This may partly account for the enhancement in the photocatalytic H<sub>2</sub> evolution activity at the low doping amount. Notably, the Zr/Ta ratio in the nitrated products was virtually the same as that in the corresponding starting materials. This result indicates that the added Zr species were not lost during the flux-assisted nitridation and subsequent rinsing processes. Despite the substitution of the lower valence element Zr for Ta,

the O/(N + O) molar ratio was unchanged, possibly as a consequence of the formation of Ta<sub>3</sub>N<sub>5</sub> (as was indicated by the XRD data). A broad absorption peak in the range of 700–750 nm, characteristic of Ta<sub>3</sub>N<sub>5</sub>, was not observed in the DRS spectra (Fig. 2b). However, the addition of Zr shifted the light absorption onset to shorter wavelengths with increasing concentration. Doping with lower valence cations results in exchange of nitride ions with oxide ions, decreasing the nitride ion content of the material to maintain the charge neutrality. As a result, the band gap was widened by doping Zr.

The effect of zirconium doping on the dynamics of photo-generated electrons and holes was studied by TAS. Fig. 2c and d provide transient absorption intensity profiles acquired at 5000 cm<sup>-1</sup> (2000 nm) and 15 400 cm<sup>-1</sup> (649 nm), respectively. These data reflect the dynamics of the intraband transitions of free and/or shallowly trapped electrons and photoexcited holes, respectively.<sup>23,24</sup> The addition of 1 mol% Zr evidently increased the lifetime of shallowly trapped electrons, in agreement with earlier work by Hojamberdiev *et al.*,<sup>25</sup> but had no appreciable effect on the dynamics of trapped holes. Doping with lower valence cations may suppress the formation of reduced Ta species acting as recombination centers. However, according to the Ta 4f XPS analysis, the chemical states of Ta species were not appreciably changed by Zr-doping, probably due to the low dopant concentration (Fig. S1, ESI†). In-depth analysis of semiconducting properties and defects of particulate oxynitride materials will be required to clarify the physicochemical origin for the prolonged electron lifetime. In contrast, doping with 10 mol% Zr accelerated the decay of both electrons and holes. It is likely that the formation of Ta<sub>3</sub>N<sub>5</sub> impurities, which typically have short carrier lifetimes, promoted charge recombination in the specimens.<sup>26</sup> This effect would explain why excessive Zr doping lowered the H<sub>2</sub> evolution activity.

Fig. 3 shows a TEM image of a crystal of the cocatalyst-loaded BaTaO<sub>2</sub>N:Zr0.01, which exhibited the best H<sub>2</sub> evolution activity. A nearly cubic particle with 100–300 nm in size with clear facets can be seen. Note that rod-like particles typically formed by Ta<sub>3</sub>N<sub>5</sub> crystals were not observable due to the low



**Fig. 3** TEM, HRTEM (inset) and SAED (inset) images of the cross-section of a Cr<sub>2</sub>O<sub>3</sub>/Na–Pt loaded BaTaO<sub>2</sub>N:Zr0.01 sample.






Fig. 4 ADF-STEM image and corresponding STEM-EDS elemental maps of the cross-section of a  $\text{Cr}_2\text{O}_3/\text{Na-Pt}$  loaded  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  sample.

amount. The well-defined SAED pattern with no additional diffraction spots (inset to Fig. 3) and the clear lattice fringes observed by HRTEM (inset to Fig. 3) indicate that these  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  particles were single crystals. Elemental mapping of the cross section of a  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  sample with STEM-EDS (Fig. 4) confirmed that the Zr dopant was not segregated from the  $\text{BaTaO}_2\text{N}$  particles. Fig. 4 also shows that the other four elements (Ba, Ta, O and N) were uniformly distributed throughout the  $\text{BaTaO}_2\text{N}:\text{Zr}$  crystals. These results indicate the homogeneous composition and single-crystalline nature of the  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  crystals.

TAS was also used to examine the effect of zirconium doping on the interaction of the photocatalyst and the Na-Pt cocatalyst (Fig. 5a and b). The addition of the Na-Pt cocatalyst to the  $\text{BaTaO}_2\text{N}$  was found to accelerate the decay of electrons while inhibiting that of holes, similar to the findings of our previous work.<sup>17</sup> This effect occurred because the Na-Pt cocatalyst captured electrons in the  $\text{BaTaO}_2\text{N}$ . Interestingly, the acceleration of the electron decay following cocatalyst loading was stronger in the case of the  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$ , suggesting that electron injection into the Na-Pt cocatalyst was promoted by Zr doping. However, the decay of holes was not retarded appreciably. Zr doping may induce deep-trapping and quenching of photoexcited holes by modifying the anion composition that, in turn, affects the valence band structure of the  $\text{BaTaO}_2\text{N}$ .




Fig. 5 TAS decays probed at (a)  $5000\text{ cm}^{-1}$  ( $2000\text{ nm}$ ; corresponding to electron dynamics) and (b)  $15400\text{ cm}^{-1}$  ( $649\text{ nm}$ ; corresponding to hole dynamics) with excitation at  $470\text{ nm}$  for  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  and  $\text{BaTaO}_2\text{N}$  before and after the addition of Na-Pt cocatalysts.

Additional in-depth spectroscopic investigations will be required to better explain the TAS observations in the present work.

The hydrogen evolution activity of a HEP in an aqueous solution containing an ionic redox mediator depends on the characteristics of the mediator, such as the redox potential, number of electrons involved in the redox reaction, and adsorption properties.<sup>9</sup> Thus, an appropriate redox mediator for the present ZOWS system was determined by experimental screening. The hydrogen evolution activities of  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  samples loaded with the Na-Pt cocatalyst followed by the photodeposition of  $\text{Cr}_2\text{O}_3$  from aqueous  $\text{K}_4[\text{Fe}(\text{CN})_6]$ , NaI or  $\text{FeCl}_2$  solutions were evaluated. Here,  $\text{Cr}_2\text{O}_3$  was employed to suppress backward reactions (*i.e.*, the reduction of oxidized forms of the redox shuttle).<sup>27</sup> As seen in Fig. 6a, the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  was almost inactive in aqueous solutions containing  $\text{I}^-$  or  $\text{Fe}^{2+}$  shuttle ions, while the same photocatalyst exhibited decent activity when  $[\text{Fe}(\text{CN})_6]^{4-}$  was employed as the electron donor. The  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  redox couple has a more negative redox potential than the  $\text{IO}_3^-/\text{I}^-$  or  $\text{Fe}^{3+}/\text{Fe}^{2+}$  redox mediators.<sup>9</sup> As a result, photogenerated holes could be transferred from the valence band of the  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  to the  $[\text{Fe}(\text{CN})_6]^{4-}$  ions more efficiently. In addition, the  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  redox couple works in less extreme pH environments (pH 6–7) than the  $\text{Fe}^{3+}/\text{Fe}^{2+}$  mediator (pH 2–3, at which  $\text{Cr}_2\text{O}_3$  is unstable). The former couple is also cycled by accepting/donating one electron instead of multiple electrons such as the six electrons required by the  $\text{IO}_3^-/\text{I}^-$  shuttle. These features allowed the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  to evolve hydrogen efficiently and steadily, and so the  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  redox shuttle shows promise as a component of ZOWS systems.

Pt nanoparticles were well used as a cocatalyst for hydrogen evolution.<sup>28,29</sup> Note that it was important to apply a  $\text{Cr}_2\text{O}_3$  layer to the Na-Pt nanoparticles to suppress backward reactions during the HER. As shown in Fig. 6b, without  $\text{Cr}_2\text{O}_3$  deposition, hydrogen evolution ceased after a few hours due to the progression of backward reactions. With the optimal amount of




Fig. 6 (a) Photocatalytic  $\text{H}_2$  evolution activities of  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  ( $100\text{ mg}$ ) in aqueous solutions of NaI,  $\text{FeCl}_2$  and  $\text{K}_4[\text{Fe}(\text{CN})_6]$  ( $150\text{ mL}$ ,  $2\text{ mM}$  each) with pH values of 6–7, 2.3 and 6, respectively. (b) Time courses of  $\text{H}_2$  evolution over  $\text{Cr}_2\text{O}_3/0.23\text{ wt}\%$  Na  $0.3\text{ wt}\%$  Pt/ $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  ( $100\text{ mg}$ ) with varying amounts of Cr in an aqueous  $50\text{ mM}$  sodium phosphate buffer solution at pH 6 ( $150\text{ mL}$ ) containing  $6\text{ mM}$   $\text{K}_4[\text{Fe}(\text{CN})_6]$ . Light source:  $300\text{ W}$  xenon lamp ( $420\text{ nm} < \lambda < 800\text{ nm}$ ).



$\text{Cr}_2\text{O}_3$ , the  $\text{H}_2$  evolution performance of the Na-Pt/BaTaO<sub>2</sub>N:Zr0.01 was promoted because the access of  $[\text{Fe}(\text{CN})_6]^{3-}$  to the Na-Pt cocatalyst was suppressed.<sup>30</sup> The optimum amount of Cr based on photodeposition was found to be 0.9 wt% with respect to the photocatalyst mass. Greater amounts of Cr actually lowered the hydrogen evolution activity because of the excessive photodeposition of  $\text{Cr}_2\text{O}_3$  in the presence of methanol. The action spectrum of a  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N:Zr0.01}$  photocatalyst for the hydrogen evolution reaction from aqueous  $\text{K}_4[\text{Fe}(\text{CN})_6]$  solution is provided in Fig. S2 (ESI<sup>†</sup>). The photocatalyst exhibited the hydrogen evolution activity up to 640 nm, which was consistent with the absorption edge of the material. The AQY at 420 nm was measured to be 0.4%.

Fig. 7 provides ADF-STEM, TEM, and STEM-EDS elemental maps of BaTaO<sub>2</sub>N:Zr0.01 loaded with 0.23 wt% Na 0.3 wt% Pt and  $\text{Cr}_2\text{O}_3$  (0.9 wt% Cr). The loading of Pt nanoparticles along with Na was studied in our recent work.<sup>17</sup> According to our previous work, the Pt nanoparticles in this sample had sizes in the range of 2–8 nm. The addition of Na improved the dispersion and structural stability of the Pt cocatalyst, although some cocatalyst particles are seen to have aggregated to form larger secondary particles on the edges of the BaTaO<sub>2</sub>N crystal. Na species were not observed because of the low loading amount and the poor sensitivity of EDS for this element. The Cr species appeared to be present in the same positions as the Pt, suggesting the formation of a layer of  $\text{Cr}_2\text{O}_3$  covering the Pt nanoparticles as in earlier reports,<sup>21</sup> but were distributed over a somewhat wider area.

The BaTaO<sub>2</sub>N:Zr0.01 photocatalyst loaded with  $\text{Cr}_2\text{O}_3/\text{Na-Pt}$  cocatalysts was found to function as a HEP in a ZOWS system in combination with  $\text{CoO}_x/\text{Au}/\text{BiVO}_4$  as the OEP and  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  as a redox mediator (Fig. 8), whereas the amounts of gaseous products were below the detection limits in the absence of the redox mediator. The same HEP and OEP showed  $\text{H}_2$  and  $\text{O}_2$  evolution activities from aqueous solutions containing the corresponding redox mediators, respectively (Fig. S3, ESI<sup>†</sup>). These observations indicate the occurrence of Z-scheme *via* the electron transfer mediated by the  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  redox couple. The ZOWS performance of this system was examined under simulated sunlight with evacuation of the test apparatus followed by the reintroduction of Ar to 10 kPa at 10 h intervals. Both  $\text{H}_2$  and  $\text{O}_2$  were evolved at a molar ratio close to the 2:1 stoichiometric ratio, and the STH of this redox-mediated ZOWS system was determined to be 0.022% in the initial run. The AQY values at 420 nm and 520 nm under monochromatic light were 1.5% and 0.2% respectively (Fig. S4, ESI<sup>†</sup>). Compared with the previously reported BaTaO<sub>2</sub>N-WO<sub>3</sub> ZOWS system, this system using BiVO<sub>4</sub> instead of WO<sub>3</sub> was able to harvest longer-wavelength visible light up to approximately 520 nm. This performance was enabled by doping with 1 mol% Zr, which promoted  $\text{H}_2$  evolution on the BaTaO<sub>2</sub>N, as well as by the modification of the Na-Pt cocatalyst with  $\text{Cr}_2\text{O}_3$  to inhibit reverse reactions and the use of  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  as a suitable redox mediator.

The  $\text{H}_2$  evolution rate obtained for the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}$  modified BaTaO<sub>2</sub>N:Zr0.01 in an aqueous  $[\text{Fe}(\text{CN})_6]^{4-}$  solution ( $37 \mu\text{mol h}^{-1}$ ; Fig. 6) was slightly lower than the  $\text{O}_2$  evolution rate for  $\text{CoO}_x/\text{Au}/\text{BiVO}_4$  in a  $[\text{Fe}(\text{CN})_6]^{3-}$  solution ( $51 \mu\text{mol h}^{-1}$ ;





Fig. 7 (a) TEM and ADF-STEM (inset) images and (b) ADF-STEM image along with STEM-EDS elemental maps of the cross-section of a 0.9 wt%  $\text{Cr}_2\text{O}_3/0.23 \text{ wt}\% \text{ Na } 0.3 \text{ wt}\% \text{ Pt}/\text{BaTaO}_2\text{N:Zr0.01}$  sample.

Fig. S3, ESI<sup>†</sup>). These data indicate that the rate-determining component of this ZOWS system was the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N:Zr0.01}$  photocatalyst. In fact, the present system using  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N:Zr}$  as the HEP showed inferior AQY and STH values compared with an earlier system using  $\text{RhCrO}_x/\text{ZrO}_2/\text{TaON}$ .<sup>9</sup> Thus, it is still necessary to improve the preparation of the BaTaO<sub>2</sub>N:Zr so that more photoexcited charge carriers become available at the surface and to enhance the injection of electrons into the cocatalysts. The present ZOWS system was also found to lose 27% of its original activity when reused, unlike a previously reported system using  $\text{ZrO}_2/\text{TaON}$  loaded with a  $\text{Rh}_{2-y}\text{Cr}_y\text{O}_3$  cocatalyst as the HEP.<sup>9</sup> The evolution





**Fig. 8** Time courses of gas evolution during the ZOWS reaction using 70 mg of  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  as the HEP under simulated sunlight. Conditions: 0.9 wt%  $\text{Cr}_2\text{O}_3/0.23$  wt% Na 0.3 wt% Pt/ $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  as the photocatalyst; 0.5 wt%  $\text{CoO}_x/0.2$  wt% Au/ $\text{BiVO}_4$ , 100 mg; 150 mL 25 mM sodium phosphate buffer solution (pH 6) containing  $\text{K}_4[\text{Fe}(\text{CN})_6]$  (6 mM) under simulated sunlight (AM 1.5G,  $92 \text{ mW cm}^{-2}$ ,  $5.5 \times 5.5 \text{ cm}$ ). Reaction system: Pyrex top-illuminated vessel connected to a closed gas-circulation system, 10 kPa Ar background atmosphere.

of  $\text{N}_2$  was not detected and thus deterioration of the  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  photocatalyst during the 30 h trial was likely negligible. The XRD pattern of the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  photocatalyst was also not changed appreciably during the hydrogen evolution reaction (Fig. S5A, ESI<sup>†</sup>). Therefore, the activity loss was presumably a result of the degradation of the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}$  cocatalyst. Degradation of the hydrogen evolution activity of  $\text{Na-Pt}/\text{BaTaO}_2\text{N}$  was also observed in our previous work.<sup>17</sup> XPS analysis of the  $\text{Cr}_2\text{O}_3/\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}0.01$  photocatalyst before and after a ZOWS reaction suggests that the  $\text{BaTaO}_2\text{N}:\text{Zr}0.01$  photocatalyst was apparently intact while the Pt cocatalyst was slightly oxidized during the reaction (Fig. S5, ESI<sup>†</sup>). This may be associated with the degradation of the HER and ZOWS activities. Our previous work showed that co-loading of an appropriate water oxidation cocatalyst can improve the durability of the cocatalyst by reducing the probability of hole injection into the hydrogen evolution cocatalyst.<sup>31,32</sup> At present, it is difficult to co-load  $\text{BaTaO}_2\text{N}$  with hydrogen evolution cocatalysts and oxygen evolution cocatalysts without sacrificing photocatalytic activity because of the insufficient reactivity and stability of the materials. The development of new technologies for the preparation and modification of narrow-bandgap particulate oxynitride photocatalysts will be vital to the future design of efficient solar-to-chemical energy conversion processes.

## Experimental

### Synthesis of Zr-doped $\text{BaTaO}_2\text{N}$

$\text{BaTaO}_2\text{N}:\text{Zr}$  samples were synthesized by  $\text{RbCl}$  (95.0%; FUJIFILM Wako Pure Chemical Corporation) flux-assisted nitridation of a mixture of  $\text{ZrO}(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}$  (99.5%; Wako Pure

Chemical Industries, Ltd.),  $\text{BaCO}_3$  (99.9%; Kanto Chemical Co., Inc.) and  $\text{Ta}_2\text{O}_5$  (99.9%; High Purity Chemicals). Note that all chemicals employed in this study were used directly as received. In a typical synthesis, a certain amount of the mixture (in which the Ba/Ta molar ratio was 1.1 regardless of the Zr/Ta molar ratio) and  $\text{RbCl}$  were blended thoroughly so that the solute concentration in  $\text{RbCl}$  flux was 10 mol% and the total mass of solute and  $\text{RbCl}$  flux was 2 g. The mixture was subsequently heated under an ammonia flow ( $200 \text{ mL min}^{-1}$ ) at 1223 K for 8 h, based on a procedure previously reported by our group.<sup>17</sup> The resulting  $\text{BaTaO}_2\text{N}:\text{Zr}$  was washed with water and dried to give the final product. The  $\text{BaTaO}_2\text{N}:\text{Zr}$  specimens having varying Zr doping levels are referred to herein as  $\text{BaTaO}_2\text{N}:\text{Zr}_x$ , where  $x$  represents the Zr/Ta molar ratio and ranges from 0 to 0.1.  $\text{BaTaO}_2\text{N}$  specimens doped with other cations at the cation/Ta molar ratio of 0.01 were also prepared for comparison purposes.

### Synthesis of $\text{BiVO}_4$

$\text{BiVO}_4$  was prepared by a hydrothermal procedure.<sup>9</sup> In this process, 5 mmol of  $\text{NH}_4\text{VO}_3$  (99.0%; FUJIFILM Wako Pure Chemical Corporation) and 5 mmol of  $\text{Bi}(\text{NO}_3)_3 \cdot 5\text{H}_2\text{O}$  (99.5%; FUJIFILM Wako Pure Chemical Corporation) were dissolved in 50 mL of a 2.0 M nitric acid solution (65%; FUJIFILM Wako Pure Chemical Corporation). The pH of this solution was then adjusted to 1.0 with an ammonia solution (28 wt%; FUJIFILM Wako Pure Chemical Corporation) while stirring the mixture, which generated a light-yellow precipitate. The solution was allowed to age for 2 h with stirring, after which the precipitate was removed and transferred to a Teflon-lined stainless-steel autoclave with a capacity of 100 mL and was hydrothermally treated at 453 K for 11 h. The single phase of diffraction structure of as-prepared  $\text{BiVO}_4$  (PDF No. 14-0688) was confirmed as shown in Fig. S6 (ESI<sup>†</sup>).

### Deposition of cocatalysts and characterization

The cocatalysts were deposited on the  $\text{BaTaO}_2\text{N}:\text{Zr}$  by impregnation followed by hydrogen reduction.<sup>17</sup> In a typical process, a 110 mg quantity of  $\text{BaTaO}_2\text{N}:\text{Zr}$  was immersed in an aqueous solution containing  $\text{NaOH}$  ( $0.1 \text{ mol L}^{-1}$ ; FUJIFILM Wako Pure Chemical Corporation) and  $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$  (98.5%; FUJIFILM Wako Pure Chemical Corporation) as the precursors. The amounts of Pt and Na in the solution were 0.3 and 0.23 wt%, respectively, with respect to the photocatalyst mass. The solution was subsequently heated on a boiling water bath, after which the product was completely dried and then heated at 523 K for 30 min in a flow of 10%  $\text{H}_2$  in  $\text{N}_2$ . The resulting  $\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}$  was additionally modified with  $\text{Cr}_2\text{O}_3$  by photo-deposition to suppress backward reactions.<sup>21</sup> This was accomplished by dispersing a quantity of the  $\text{Na-Pt}/\text{BaTaO}_2\text{N}:\text{Zr}$  powder in 100 mL of an aqueous solution of methanol (15 vol%), after which  $\text{K}_2\text{CrO}_4$  (99.0%; FUJIFILM Wako Pure Chemical Corporation) was added as a  $\text{Cr}^{6+}$  precursor without pH adjustment. The amount of  $\text{Cr}_2\text{O}_3$  was equivalent to a loading of 0.9 wt% Cr with respect to the photocatalyst mass. After complete degassing, the suspension was irradiated with



visible light ( $420 \text{ nm} < \lambda < 800 \text{ nm}$ ) for 1 h. The photocatalyst was then removed by filtering, washed with ultrapure water and dried at 313 K under vacuum.

The deposition of Au and  $\text{CoO}_x$  as reduction and oxidation cocatalysts, respectively, on the  $\text{BiVO}_4$  was carried out using a stepwise photodeposition process previously reported in the literature.<sup>9</sup> The prepared  $\text{BiVO}_4$  (150 mg) was dispersed in deionized water to which a specific amount of  $\text{HAuCl}_4 \cdot 4\text{H}_2\text{O}$  (99.0%; FUJIFILM Wako Pure Chemical Corporation) was added, equivalent to 0.2 wt% Au relative to the oxide mass. Thereafter, the suspension was irradiated under visible light ( $420 \text{ nm} < \lambda < 800 \text{ nm}$ ) for 1 h, after which the powder was collected by filtration, washed and dried. The as-obtained powder was subsequently loaded with  $\text{CoO}_x$  (0.5 wt%) by photodeposition. This was accomplished by dispersing the powder in 100 mL of a 50 mM sodium potassium buffer solution ( $\text{KH}_2\text{PO}_4$ , 99.5%; FUJIFILM Wako Pure Chemical Corporation; 44 mM;  $\text{Na}_2\text{HPO}_4$ , 99.0%; FUJIFILM Wako Pure Chemical Corporation; 6 mM) at pH 6.0. A quantity of  $\text{K}_3[\text{Fe}(\text{CN})_6]$  (99.0%; FUJIFILM Wako Pure Chemical Corporation) sufficient to give a concentration of 5 mM was added along with a specific amount of  $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$  (98.0%; FUJIFILM Wako Pure Chemical Corporation), and the mixture was illuminated for 1 h. The resulting  $\text{CoO}_x/\text{Au}/\text{BiVO}_4$  has been shown to work as an excellent OEP in ZOWS systems involving  $[\text{Fe}(\text{CN})_6]^{3-}/[\text{Fe}(\text{CN})_6]^{4-}$  as the redox mediator.<sup>9</sup>

X-Ray diffraction (XRD) patterns were acquired using a Rigaku MiniFlex 300 powder diffractometer with a Cu  $K\alpha$  radiation source ( $\lambda = 1.5418 \text{ \AA}$ ). The data were analyzed after mathematically removing the contribution from the  $K\alpha_2$  line. (Scanning) transmission electron microscopy ((S)TEM) images, energy dispersive X-ray spectroscopy (EDS) mapping images, selected area electron diffraction (SAED) patterns, high-resolution transmission electron microscopy (HRTEM) and annular dark-field (ADF) STEM images were obtained with a JEOL JEM-2800 system equipped with an Oxford Instruments X-MAX 100TLE SDD detector. Diffuse reflectance spectroscopy (DRS) data were acquired with an ultraviolet-visible-near-infrared spectrometer (V-670, JASCO) and converted from reflectance to the Kubelka–Munk function. The Ba, Ta and Zr concentrations in the  $\text{BaTaO}_2\text{N}:\text{Zr}$  were determined by inductively coupled plasma-atomic emission spectroscopy (ICP-AES; ICPS-8100, Shimadzu). The oxygen and nitrogen contents of the  $\text{BaTaO}_2\text{N}$  were obtained using an oxygen–nitrogen combustion analyzer (Horiba, EMGA-620W). X-Ray photoelectron spectroscopy (XPS) was performed using a PHI Quantera II spectrometer with an Al  $K\alpha$  radiation source. All binding energies were referenced to the C 1s peak (284.8 eV) arising from adventitious carbon. The specific surface area of the samples was calculated from nitrogen adsorption isotherms measured at 77 K with a BELSORP Mini II apparatus (MicrotracBEL) using the Brunauer–Emmett–Teller method.

Transient absorption (TA) spectroscopic measurements were carried out using a Nd:YAG laser system (Continuum, Surelite I; pulse duration: 6 ns) equipped with custom-built spectrometers.<sup>33</sup> The probe beams coming from the halogen lamp

(producing visible light) and  $\text{MoSi}_2$  coil (producing IR light) were used in this measurement for monitoring the absorption signals at 649 and 2000 nm, respectively. In the case of 2000 nm probing, the beam was focused on the sample and was transmitted from the sample and then detected by an mercury cadmium telluride detector. For the 649 nm probing, we used reflection mode, of which the incident probe beam was focused on the sample and then the reflected light from the sample was detected by a Si photodetector. The output electric signal was amplified with an AC-coupled amplifier (Stanford Research Systems, SR560, 1 MHz). The time resolution of the spectrometer was limited to 1  $\mu\text{s}$  by the response of the photodetectors. One thousand responses were accumulated to obtain the transient profiles (that is, the decay curves) at 649 and 2000 nm. The various  $\text{BaTaO}_2\text{N}:\text{Zr}$  photocatalysts loaded with Na and/or Pt were photoexcited using 470 nm pump pulses with a fluence of  $3 \text{ mJ pulse}^{-1}$ . Each powder sample was fixed on a circular  $\text{CaF}_2$  substrate by drop-casting at a density of  $1.24 \text{ mg cm}^{-2}$ . These TAS analyses were carried out in a vacuum at room temperature.

### Photocatalytic $\text{H}_2$ evolution reaction and OWS reaction

The HER over each  $\text{BaTaO}_2\text{N}$  photocatalyst was performed at room temperature in a Pyrex top-irradiation reaction vessel connected to a glass closed gas circulation system. In each trial, a quantity of Na–Pt/ $\text{BaTaO}_2\text{N}:\text{Zr}$  (100 mg) was dispersed in an aqueous methanol solution (15 vol%, 150 mL) using a magnetic stirrer. The vessel was subsequently evacuated several times to ensure complete air removal. The activity of a photocatalyst can depend on the pressure in the reaction system.<sup>16</sup> Thus, to minimize the effects of changes in pressure resulting from gas evolution and heating of the reaction solution during irradiation, Ar was introduced into the reaction system prior to the reaction to a pressure of approximately 10 kPa. The reaction was initiated by irradiation with a 300 W Xe lamp fitted with a cutoff filter and a dichroic mirror, emitting at  $420 \text{ nm} < \lambda < 800 \text{ nm}$ . A flow of cooling water was used to keep the suspension at approximately 283 K throughout the trial. The evolved gases were analyzed by gas chromatography (GC; Shimadzu, GC-8A with a thermal conductivity detector, MS-5 A columns and Ar as the carrier gas). The  $\text{H}_2$  evolution rates obtained from aqueous solutions of NaI,  $\text{FeCl}_2$  and  $\text{K}_4[\text{Fe}(\text{CN})_6]$  and the  $\text{O}_2$  evolution rates from an aqueous  $\text{K}_3[\text{Fe}(\text{CN})_6]$  solution were also examined. In each case, an aqueous solution (150 mL) containing the photocatalyst sample (100 mg) was prepared and the pH was adjusted to a specific value for NaI (pH 6–7, 2 mM),  $\text{FeCl}_2$  (pH 2.3, 2 mM),  $\text{K}_4[\text{Fe}(\text{CN})_6]$  (pH 6, 2 mM) and  $\text{K}_3[\text{Fe}(\text{CN})_6]$  (pH 6, 5 mM). An aqueous  $\text{HNO}_3$  solution was used to adjust the pH of the  $\text{FeCl}_2$  solution while the pH values of the  $\text{K}_4[\text{Fe}(\text{CN})_6]$  and  $\text{K}_3[\text{Fe}(\text{CN})_6]$  solutions were maintained at 6 using a 50 mM sodium potassium buffer solution.

ZOWS reactions were carried out using the same reactor and system described above. In each experiment,  $\text{Cr}_2\text{O}_3/\text{Na–Pt}/\text{BaTaO}_2\text{N}:\text{Zr}$  (70 mg) and  $\text{CoO}_x/\text{Au}/\text{BiVO}_4$  (100 mg), acting as the HEP and OEP, respectively, were suspended in 150 mL of an aqueous sodium potassium buffer solution (pH 6.0, 25 mM)





containing  $K_4[Fe(CN)_6] \cdot 3H_2O$  (99.5%; FUJIFILM Wako Pure Chemical Corporation; 6 mM). After complete degassing, Ar gas was introduced to the reaction system to an initial pressure of 10 kPa. Following this, the suspension was irradiated with either a Xe lamp or solar simulator (AM 1.5G, 92 mW cm<sup>-2</sup>, 5.5 × 5.5 cm), and a cooling water system was employed to maintain the solution at 283 K, as described above. The evolved gases were also analyzed by the same GC instrumentation.

### Apparent quantum yield (AQY) and STH

The AQY values for the ZOWS reactions were determined using a procedure similar to that described in our previous paper.<sup>34</sup> The same light source was employed but it was equipped with various band-pass filters. The number of incident photons illuminating the reaction cell was measured using a grating spectroradiometer (LS-100, EKO Instruments). The AQY was then calculated as

$$AQY (\%) = [A \times R]/I \times 100, \quad (1)$$

where  $R$  and  $I$  represent the amounts of evolved H<sub>2</sub> and O<sub>2</sub> and the number of incident photons per unit time, respectively, and  $A$  is the number of electrons and holes consumed to generate one molecule of H<sub>2</sub> and one molecule of O<sub>2</sub>. The values of  $A$  are 4 and 8 for Z-scheme water splitting based on two-step photoexcitation, respectively. The average of the AQY values calculated for H<sub>2</sub> and O<sub>2</sub> values was adopted.

The STH values for ZOWS reactions under simulated solar radiation were calculated as

$$STH (\%) = (R(H_2) \times \Delta G_r)/(P \times S) \times 100, \quad (2)$$

where  $R(H_2)$ ,  $\Delta G_r$ ,  $P$ , and  $S$  denote the rate of hydrogen evolution determined from the rate of water splitting during the ZOWS reaction, the Gibbs energy change for the reaction H<sub>2</sub>O (l) → H<sub>2</sub> (g) + 1/2 O<sub>2</sub> (g), the energy intensity of the AM 1.5G solar irradiation (92 mW cm<sup>-2</sup>) and the irradiated sample area (5.5 × 5.5 cm), respectively. The rate of water splitting was assumed to equal the average of the H<sub>2</sub> evolution rate and twice the O<sub>2</sub> evolution rate based on the reaction stoichiometry. The value of  $\Delta G_r$  used for the calculations was 229 kJ mol<sup>-1</sup> at 283 K.<sup>34</sup>

## Conclusions

This work demonstrated the effective modification of a BaTaO<sub>2</sub>N photocatalyst by Zr doping and by incorporating a Na–Pt cocatalyst together with a Cr<sub>2</sub>O<sub>3</sub> coating to produce a HEP for ZOWS. Doping with 1 mol% Zr extended the lifetime of electrons and promoted electron injection into the Na–Pt cocatalyst, leading to improved H<sub>2</sub> evolution activity for an aqueous methanol solution under visible light. The Cr<sub>2</sub>O<sub>3</sub> coating also allowed the Na–Pt/BaTaO<sub>2</sub>N:Zr0.01 photocatalyst to evolve H<sub>2</sub> from an aqueous [Fe(CN)<sub>6</sub>]<sup>3-/4-</sup> solution.

A ZOWS system based on Cr<sub>2</sub>O<sub>3</sub>/Na–Pt/BaTaO<sub>2</sub>N:Zr0.01 as the HEP, CoO<sub>x</sub>/Au/BiVO<sub>4</sub> as the OEP and [Fe(CN)<sub>6</sub>]<sup>3-/4-</sup> as redox ions evolved H<sub>2</sub> and O<sub>2</sub> under visible light up to 520 nm. The

STH efficiency of this process was 0.022%. This newly developed ZOWS system was able to harvest visible light with longer wavelengths than earlier systems utilizing TaON as the HEP or WO<sub>3</sub> as the OEP. This achievement was made possible by improving the performance of the BaTaO<sub>2</sub>N as the HEP and also by the selection of [Fe(CN)<sub>6</sub>]<sup>3-/4-</sup> as an appropriate redox couple. It is therefore important to optimize the photocatalyst, cocatalysts and reaction conditions to enhance the activity of ZOWS systems operating under long-wavelength visible light.

## Author contributions

The manuscript was written through contributions of all authors. H. L. designed and performed the experiments, wrote and edited the manuscript. J. J. M. V. acquired the TAS spectra and analyzed these data together with A. Y. T. H. edited the manuscript and discussed the scientific results as a supervisor. M. N. characterized the morphology and composition of each specimen using STEM-EDS and HRTEM together with N. S. J. X., Z. P. W. L. and W. Z. discussed the scientific results. X. T. and S. C. discussed the synthesis of BiVO<sub>4</sub>. T. T. provided resources as a supervisor. K. D. edited the manuscript and provided resources as a supervisor. All authors have given approval to the final version of the manuscript.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This research was supported by the National Natural Science Foundation of China (grant no. 51402139), the China Scholarship Council (grant no. 201906185004 and 202008440289), the Artificial Photo-synthesis Project (ARPCHEM) of the New Energy and Industrial Technology Development Organization (NEDO), and by JST, PRESTO, Japan (grant no. JPMJPR20T9). Part of this study was supported by the University of Tokyo Advanced Characterization Nanotechnology Platform as part of the Nanotechnology Platform Project sponsored by the Ministry of Education, Culture, Sports, Science and Technology (MEXT), Japan (grant no. JPMXP09A-21-UT-0046). W. L. thanks 2021 MEXT Scholarship with Embassy Recommendation for financial support. The authors thank Ms Michiko Obata of Shinshu University for her assistance during the XPS analyses. The authors thank Dr Taro Yamada, Ms Keiko Kato and Ms Yasuko Kuromiya of the University of Tokyo for their assistance in the ICP-OES and oxygen–nitrogen combustion analyses.

## Notes and references

- Q. Wang, T. Hisatomi, Q. Jia, H. Tokudome, M. Zhong, C. Wang, Z. Pan, T. Takata, M. Nakabayashi, N. Shibata, Y. Li, I. Sharp, A. Kudo, T. Yamada and K. Domen, Scalable water splitting on particulate photocatalyst sheets with a



- solar-to-hydrogen energy conversion efficiency exceeding 1%, *Nat. Mater.*, 2016, **15**, 611–615.
- 2 K. Iwashina, A. Iwase, Y. Ng, R. Amal and A. Kudo, Z-Schematic Water Splitting into H<sub>2</sub> and O<sub>2</sub> Using Metal Sulfide as a Hydrogen-Evolving Photocatalyst and Reduced Graphene Oxide as a Solid-State Electron Mediator, *J. Am. Chem. Soc.*, 2015, **137**, 604–607.
  - 3 S. Chen, J. Vequizo, Z. Pan, T. Hisatomi, M. Nakabayashi, L. Lin, Z. Wang, K. Kato, A. Yamakata, N. Shibata, T. Takata, T. Yamada and K. Domen, Surface Modifications of (ZnSe)<sub>0.5</sub>(CuGa<sub>2.5</sub>Se<sub>4.25</sub>)<sub>0.5</sub> to Promote Photocatalytic Z-Scheme Overall Water Splitting, *J. Am. Chem. Soc.*, 2021, **143**, 10633–10641.
  - 4 J. Nasir, A. Munir, N. Ahmad, T. Haq, Z. Khan and Z. Rehman, Photocatalytic Z-Scheme Overall Water Splitting: Recent Advances in Theory and Experiments, *Adv. Mater.*, 2021, **33**, 2105195.
  - 5 B. Ng, L. Putri, X. Kong, Y. The, P. Pasbakhsh and S. Chai, Z-Scheme Photocatalytic Systems for Solar Water Splitting, *Adv. Sci.*, 2020, **7**, 1903171.
  - 6 Y. Miseki and K. Sayama, Photocatalytic Water Splitting for Solar Hydrogen Production Using the Carbonate Effect and the Z-Scheme Reaction, *Adv. Energy Mater.*, 2019, **9**, 1801294.
  - 7 K. Maeda, Z-Scheme Water Splitting Using Two Different Semiconductor Photocatalyst, *ACS Catal.*, 2013, **3**, 1486–1503.
  - 8 R. Zhang, L. Zhang, Q. Zheng, P. Gao, J. Zhao and J. Yang, Direct Z-Scheme Water Splitting Photocatalyst Based on Two-Dimensional van der Waals Heterostructures, *J. Phys. Chem. Lett.*, 2018, **9**, 5419–5424.
  - 9 Y. Qi, Y. Zhao, Y. Gao, D. Li, Z. Li, F. Zhang and C. Li, Redox-Based Visible-Light-Driven Z-Scheme Overall Water Splitting with Apparent Quantum Efficiency Exceeding 10%, *Joule*, 2018, **2**, 2393–2402.
  - 10 M. Hojamberdiev, K. Yubuta, J. Vequizo, A. Yamakata, S. Oishi, K. Domen and K. Teshima, NH<sub>3</sub>-Assisted Flux Growth of Cube-like BaTaO<sub>2</sub>N Submicron Crystals in a Completely Ionized Nonaqueous High-Temperature Solution and Their Water Splitting Activity, *Cryst. Growth Des.*, 2015, **15**, 4663–4671.
  - 11 S. Wei, S. Chang, F. Yang, Z. Fu, G. Liu and X. Xu, Stable and efficient solar-driven photoelectrochemical water splitting into H<sub>2</sub> and O<sub>2</sub> based on a BaTaO<sub>2</sub>N photoanode decorated with CoO microflowers, *Chem. Commun.*, 2021, **57**, 4412–4415.
  - 12 H. Zhang, S. Wei and X. Xu, Mg modified BaTaO<sub>2</sub>N as an efficient visible-light-active photocatalyst for water oxidation, *J. Catal.*, 2020, **383**, 135–143.
  - 13 S. Wei, G. Zhang and X. Xu, Activating BaTaO<sub>2</sub>N by Ca modifications and cobalt oxide for visible light photocatalytic water oxidation reactions, *Appl. Catal., B*, 2018, **237**, 373–381.
  - 14 B. Dong, Y. Qi, J. Cui, B. Liu, F. Xiong, X. Jiang, Z. Li, Y. Xiao, F. Zhang and C. Li, Synthesis of BaTaO<sub>2</sub>N oxynitride from Ba-rich oxide precursor for construction of visible-light-driven Z-scheme overall water splitting, *Dalton Trans.*, 2017, **46**, 10707–10713.
  - 15 K. Hibino, M. Yashima, T. Oshima, K. Fujii and K. Maeda, Structures, electron density and characterization of novel photocatalysts, (BaTaO<sub>2</sub>N)<sub>1-x</sub>(SrWO<sub>2</sub>N)<sub>x</sub> solid solutions, *Dalton Trans.*, 2017, **46**, 14947–14956.
  - 16 Z. Wang, Y. Luo, T. Hisatomi, J. Vequizo, S. Suzuki, S. Chem, M. Nakabayashi, L. Lin, Z. Pan, N. Kariya, A. Yamakata, N. Shibata, T. Takata, K. Teshima and K. Domen, Sequential cocatalyst decoration on BaTaO<sub>2</sub>N towards highly-active Z-scheme water splitting, *Nat. Commun.*, 2021, **12**, 1005.
  - 17 H. Li, D. Lu, S. Chem, T. Hisatomi, J. Vequizo, J. Xiao, Z. Wang, L. Lin, Q. Xiao, Y. Sun, Y. Miseki, K. Sayama, A. Yamakata, T. Takata and K. Domen, A Na-containing Pt cocatalyst for efficient visible-light-induced hydrogen evolution on BaTaO<sub>2</sub>N, *J. Mater. Chem. A*, 2021, **9**, 13851–13854.
  - 18 A. Iwase, Y. Udagawa, S. Yoshino, Y. Ng, R. Amal and A. Kudo, Solar Water Splitting under Neutral Conditions Using Z-Scheme Systems with Mo-Doped BiVO<sub>4</sub> as an O<sub>2</sub>-Evolving Photocatalyst, *Energy Technol.*, 2019, **7**, 1900358.
  - 19 M. Higashi, Y. Yamanaka, O. Tomita and R. Abe, Fabrication of cation-doped BaTaO<sub>2</sub>N photoanodes for efficient photoelectrochemical water splitting under visible light irradiation, *APL Mater.*, 2015, **3**, 104418.
  - 20 K. Maeda, D. Lu and K. Domen, Solar-Driven Z-scheme Water Splitting Using Modified BaZrO<sub>3</sub>-BaTaO<sub>2</sub>N Solid Solutions as Photocatalysts, *ACS Catal.*, 2013, **3**, 1026–1033.
  - 21 K. Maeda, K. Teramura, D. Lu, N. Saito, Y. Inoue and K. Domen, Noble-Metal/Cr<sub>2</sub>O<sub>3</sub> Core/Shell Nanoparticles as a Cocatalyst for Photocatalytic Overall Water Splitting, *Angew. Chem.*, 2006, **118**, 7970–7973.
  - 22 Y. Luo, Z. Wang, S. Suzuki, K. Yubuta, N. Kariya, T. Hisatomi, K. Domen and K. Teshima, Fabrication of Single-Crystalline BaTaO<sub>2</sub>N from Chloride Fluxes for Photocatalytic H<sub>2</sub> Evolution under Visible Light, *Cryst. Growth Des.*, 2020, **20**, 255–261.
  - 23 A. Yamakata and J. Vequizo, Curious Behaviors of Photo-generated Electrons and Holes at the Defects on Anatase, Rutile, and Brookite TiO<sub>2</sub> Powders: A Review, *J. Photochem. Photobiol., C*, 2019, **40**, 234–243.
  - 24 A. Yamakata, J. Vequizo, T. Ogawa, K. Kato, S. Tsuboi, N. Furutani, M. Ohtsuka, S. Muto, A. Kuwabara and Y. Sakata, Core-Shell Double Doping of Zn and Ca on β-Ga<sub>2</sub>O<sub>3</sub> photocatalysts for Remarkable Water Splitting, *ACS Catal.*, 2021, **11**, 1911–1919.
  - 25 M. Hojamberdiev, R. Vargas, Z. Kadirova, K. Kato, H. Sena, A. Krasnov, A. Yamakata, K. Teshima and M. Lerch, Unfolding the Role of B Site-Selective Doping of Aliovalent Cations on Enhancing Sacrificial Visible Light-Induced Photocatalytic H<sub>2</sub> and O<sub>2</sub> Evolution over BaTaO<sub>2</sub>N, *ACS Catal.*, 2022, **12**, 1403–1414.
  - 26 J. Vequizo, M. Hojamberdiev, K. Teshima and A. Yamakata, Role of CoO<sub>x</sub> cocatalyst on Ta<sub>3</sub>N<sub>5</sub> photocatalysts studied by transient visible to mid-infrared absorption spectroscopy, *J. Photochem. Photobiol., A*, 2018, **358**, 315–319.
  - 27 M. Yoshida, K. Takanabe, K. Maeda, A. Ishikawa, J. Kubota, Y. Sakata, Y. Ikezawa and K. Domen, Role and Function of Noble-Metal/Cr-Layer Core/Shell Structure Cocatalysts for



- Photocatalytic Overall Water Splitting Studied by Model Electrodes, *J. Phys. Chem. C*, 2009, **113**, 10151–10157.
- 28 L. Lin, Z. Lin, J. Zhang, X. Cai, W. Lin, Z. Yu and X. Wang, Molecular-level insights on the reactive facet of carbon nitride single crystals photocatalysing overall water splitting, *Nat. Catal.*, 2020, **3**, 649–655.
- 29 M. Liu, C. Wei, H. Zhuzhang, J. Zhou, Z. Pan, W. Lin, Z. Yu, G. Zhang and X. Wang, Fully Condensed Poly (Triazine Imide) Crystals: Extended  $\pi$ -Conjugation and Structural Defects for Overall Water Splitting, *Angew. Chem., Int. Ed.*, 2022, **61**, e202113389.
- 30 M. Qureshi, T. Shinagawa, N. Tsiapis and K. Takanabe, Exclusive Hydrogen Generation by Electrocatalysts Coated with an Amorphous Chromium-Based Layer Achieving Efficient Overall Water Splitting, *ACS Sustainable Chem. Eng.*, 2017, **5**, 8079–8088.
- 31 H. Lyu, T. Hisatomi, Y. Goto, M. Yoshida, T. Higashi, M. Katayama, T. Takata, T. Minegishi, H. Nishiyama, T. Yamada, Y. Sakata, K. Asakura and K. Domen, An Al-doped SrTiO<sub>3</sub> Photocatalyst maintaining sunlight-driven overall water splitting activity for over 1000 h of constant illumination, *Chem. Sci.*, 2019, **10**, 3196–3201.
- 32 T. Ohno, L. Bai, T. Hisatomi, K. Maeda and K. Domen, Photocatalytic Water Splitting Using Modified GaN:ZnO Solid Solution under Visible Light: Long-Time Operation and Regeneration of Activity, *J. Am. Chem. Soc.*, 2012, **134**, 8254–8259.
- 33 A. Yamakata, M. Kawaguchi, T. Nishimura, T. Minegishi, J. Kubota and K. Domen, Behavior and Energy States of Photogenerated Charge Carriers on Pt- or CoO<sub>x</sub>-Loaded LaTiO<sub>2</sub>N photocatalysts: Time-Resolved Visible to Mid-Infrared Absorption Study, *J. Phys. Chem. C*, 2014, **118**, 23897–23906.
- 34 Z. Wang, T. Hisatomi, R. Li, K. Sayama, G. Liu, K. Domen, C. Li and L. Wang, Efficiency Accreditation and Testing Protocols for Particulate Photocatalysts toward Solar Fuel Production, *Joule*, 2021, **5**, 344–359.

