

# RSC Sustainability

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: A. Cornelio, A. Zanoletti, M. Scaglia, D. La Corte, G. Biava, E. Galli and E. Bontempi, *RSC Sustain.*, 2024, DOI: 10.1039/D4SU00202D.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

Strategic metals recovery from spent lithium-ion batteries is a critical step toward environmental sustainability and resource conservation. Our research introduces a new promising method to recover lithium from spent batteries. This process not only mitigates the ecological and economic impacts associated with mining and refining virgin materials but also fosters a circular economy. By enabling the reuse of valuable metals, we support the transition to renewable energy systems and contribute to lowering the cost of energy storage solutions. This research contributes directly to several UN Sustainable Development Goals: ensuring sustainable consumption and production patterns (SDG 12), building resilient infrastructure and fostering innovation (SDG 9), and supporting industry efforts to promote sustainable practices (SDG 11). Additionally, it underpins efforts to secure the availability and sustainable management of water and sanitation for all (SDG 6) by reducing the water-intensive processes of metal extraction and processing.



# Thermal approaches based on microwaves to recover lithium from spent lithium-ion batteries.

View Article Online  
DOI: 10.1039/D4SU00202D

A. Cornelio<sup>1</sup>, A. Zanoletti<sup>1</sup>, M. Scaglia<sup>1</sup>, E. Galli<sup>1</sup>, D. La Corte<sup>1</sup>, G. Biava<sup>1</sup>, and E Bontempi<sup>1</sup>

<sup>1</sup> INSTM and Chemistry for Technologies Laboratory, Department of Mechanical and Industrial Engineering, University of Brescia, Via Branze, 38, 25123, Brescia, Italy.

\* Corresponding author: elza.bontempi@unibs.it

## Abstract

During the energy transition, the demand for strategic metals has become a focal point due to their crucial roles in advancing cleaner energy technologies and sustainable practices. As a response to the potential supply vulnerabilities of critical raw materials, recycling has gained attention, despite some methods being more expensive than traditional mining. In this context, new technologies based on microwave radiation have been recently introduced to recover lithium from spent lithium-ion batteries.

This study highlights the innovative results achieved through the application of microwave heating to lithium cobalt oxide (LCO) black mass, showing that mass increase can support the possibility of proposing the technology as a new sustainable approach. The possibility of coupling carbon materials with magnetic materials, available in the black mass (BM) results in a strategic approach to increasing the final temperature of microwave-absorbing materials. The process proves highly efficient in lithium recovery, with a treatment at 600 W for 5 minutes, reaching a value higher than 80%, while also eliminating some labour-intensive pre-treatment steps. The research sheds light on both the advantages and potential challenges associated with this ground-breaking technology.

**Keywords: Microwave, Black mass, lithium-ion battery, circular economy, metals recovery, e-waste**

## 1. Introduction

Literature underscores that the availability of strategic metals, for example lithium, will pose a significant long-term sustainability challenge for the transportation sector unless a combination of measures is implemented to address this issue [1]. Among them, recycling is the most suitable option to avoid precious material loss. The advantages of recycling metals in lithium-ion batteries (LIBs) are not only limited to the mitigation of raw materials dependence and risks of shortage, but also include environmental and health benefits, and promotion of circular economy strategies [1]. Recycling can prevent environmental and health problems associated with the disposal of spent batteries [1] and helps to reduce the extraction of raw materials, such as cobalt, nickel, and lithium, which are limited resources and can be subject to supply chain disruptions [1]. By recycling LIBs, valuable metals can be recovered and reused, reducing the need for new mining and extraction [2]. This not only



43 conserves natural resources but also minimizes the environmental impact of mining  
44 activities [3]. However, because of the delayed impacts associated with material recycling  
45 the recycling process is anticipated to have a substantial influence in addressing the long-  
46 term material cost challenges in Electric Vehicle (EV) development [5]. Recycling is set to  
47 increase the adoption rate of EVs from 59% to 67% by the year 2060 [5].

48 Then, recycling holds promise in tackling prolonged challenges related to critical material  
49 prices, thanks to anticipated technological advancements and economies of scale that will  
50 drive down recycling expenses. While recycling has the advantage of shortening supply  
51 chains and cutting down on logistical expenses, it remains more cost-effective to extract  
52 minerals through mining than to recycle them. Consequently, there is an urgent need to  
53 explore cost-efficient and sustainable methods for reclaiming valuable minerals that can  
54 compete with freshly mined ones [5].

55 Moreover, this is not straightforward, partly owing to the intricacies associated with spent  
56 lithium-ion battery waste. For example, because the spent LIBs waste is made of complex  
57 mixtures of different materials, and the classification and sorting of batteries by cathode  
58 chemistry are extremely onerous, the automatization of the separation processes,  
59 preliminary for the recovery, is quite complex [4]. Even if more than 95% in the efficiency of  
60 lithium extraction and recovery can be found, the proposed processes are generally  
61 addressed to specific cathodes [5]. Additionally, recycled materials often have a lower  
62 market value compared to virgin resources [6]. This discrepancy can be attributed to several  
63 factors, including the increase in mining activities, which are considered crucial for meeting  
64 environmental targets for greenhouse gas (GHG) reduction. Furthermore, there is an  
65 absence of explicit provisions for evaluating the environmental impacts of different mineral  
66 sources, such as extraction from geothermal brines, coal, unconventional sources, the  
67 ocean, spent electronics, and virgin mineral mining. This situation poses a significant threat  
68 to environmental protection [7]. Therefore it is essential to make efforts towards establishing  
69 a sustainable battery recycling system and providing resources for the continuous  
70 development of new and advanced battery recycling technologies.

71 The primary objective of this paper is to introduce a novel approach, utilizing microwave-  
72 based non-conventional heating systems, for the treatment of spent LIBs, highlighting the  
73 potentialities of this technology. The efficacy of the process is demonstrated by the lithium  
74 recovery, which allows making evidence occurring of the carbothermic reactions, induced  
75 by thermal treatments. This is a significant contribution, also because existing literature  
76 suggests separating lithium recovery from the other metals but doing so through traditional  
77 thermal methods may present challenges [8]. This study is particularly dedicated to waste  
78 samples, and there are limited comparable examples available due to the prevailing  
79 tendency in the literature to adhere to ideal samples, obtained by using virgin materials.

## 80 2. Pyrometallurgy recovery technologies

81 The prevailing recycling procedures for spent LIBs can be broken down into three key  
82 stages: pre-treatment, the metallurgical processing of recycling, and the creation of new  
83 materials. In the pre-treatment phase, the initial step involves discharging the spent LIBs to  
84 prevent short circuits. Subsequently, they are roughly disassembled into various



85 components, such as cathodes, anodes, membranes, and metallic shells [4]. However, in  
86 most cases, mechanical pre-treatment involves crushing the anodic and cathodic battery  
87 parts, as it can be challenging to separate these components, making more complicate the  
88 recovery of valuable materials. Thermal treatment is also commonly employed as a  
89 preferred method for removing binders and electrolytes during the pre-treatment process.  
90 Following pre-treatment, more advanced technologies are necessary to refine these mixed  
91 products through chemical or physical techniques. The present metallurgical processing  
92 methods predominantly encompass pyrometallurgical and hydrometallurgical technologies.  
93 Nonetheless, the extensive use of chemicals and high energy consumption, along with the  
94 associated high emissions during the metallurgical processes, can pose challenges in  
95 achieving environmentally friendly and efficient recycling of various metals from spent LIBs  
96 [4].

97 In particular, pyrometallurgical methods involve high-temperature procedures used to  
98 extract and recover valuable materials from battery waste. Essentially, the pyrometallurgical  
99 process entails exposing the battery waste to heat while utilizing a reducing agent, like  
100 carbon. The main objective is to transform metal oxides into either their elemental form or  
101 less complex metal oxides. This method has been proven to be especially efficient in the  
102 recovery of metals such as cobalt, nickel, and copper, even if some problems can be  
103 established with lithium recovery [9] which is usually present in the slag,  
104 with other elements such as Al, Ca, and Si.

105 Carbothermal reduction of the lithium cobalt oxide ( $\text{LiCoO}_2$  - LCO), lithium manganese oxide  
106 ( $\text{LiMn}_2\text{O}_4$  - LMO), and lithium nickel manganese oxide ( $\text{LiNi}_{0.5}\text{Mn}_{1.5}\text{O}_4$  - LNMO) can occur  
107 due to carbon present in the black mass (originating from the anodic part of the battery),  
108 which is available for the reaction, promoted by the heat treatment. Indeed, the anodic part  
109 of the LIBs is generally composed of graphite.

110 At high temperatures and in the presence of oxygen (derived from the cathodic material  
111 decomposition), carbon oxidizes and can form CO and/or  $\text{CO}_2$ . The decomposition of LMO,  
112 LCO, and LNMO can produce nickel, manganese, and cobalt oxides, which may be also  
113 further reduced by C and CO at higher temperatures [10].

114 The thermal analysis following the kinetics of the reactions shows that, generally, until  
115 about 600 °C cathode material seems to be stable (the weight loss of the black mass is quite  
116 limited), and it is more evident beyond 600 °C [11]. Weight losses observed after 850°C are  
117 generally associated with the formation of oxides of Mn and Co [11].

118 Although pyrometallurgical techniques offer the potential for metal reclamation, they have  
119 certain limitations, mainly related to their energy demand [12]. High-temperature processes  
120 require substantial energy input, leading to heightened environmental consequences and  
121 elevated expenses in comparison to other recycling approaches. Furthermore,  
122 pyrometallurgical methods might not be applicable for recovering all materials contained  
123 within lithium-ion batteries, and specific hazardous constituents within the battery waste  
124 could necessitate supplementary treatment and disposal.

125 In this frame, the advantages of microwave (MW) technology over traditional  
126 pyrometallurgical processes are commonly recognized [13].

### 129 3. Microwave treatments and the hybrid-heating mechanism




130 MW technologies have been recently applied in various ways as new methodologies to  
131 recycle metals in lithium-ion batteries (LIBs). One example is the MW-enhanced approach  
132 which uses a biodegradable and recyclable deep eutectic solvent to leach valuable metals  
133 from spent LIBs [14]. The high electric field induced by MW heating increases the dipole  
134 moments on the battery surface, allowing for fast leaching of metals such as lithium and  
135 cobalt. MW was also used for sample leaching, in a closed vessel, to facilitate the dissolution  
136 of the metals [15]. Another example consists of biomass pyrolysis supporting the recovery  
137 of LIB from biomass waste, with the result of reducing the decomposition temperature of the  
138 cathodic materials [16]. Finally, a very recent example concerns the use of the microwave-  
139 assisted reduction roasting method to promote carbothermal reduction reactions [17,18]. In  
140 particular, the use of a hybrid-heating mechanism has shown promising results in the direct  
141 recovery of lithium from spent batteries. In this case, Li was shown to be available as lithium  
142 oxide, then it is soluble in water.

143 Nonetheless, even though certain research findings showcase the potential of MW  
144 technology for recycling metals from LIBs, efforts in this field remain relatively restricted.  
145 Specifically, the impacts of MW heating on the treatment of spent cathode materials are not  
146 yet comprehensively understood and necessitate further exploration. This is also because  
147 the black mass (BM), based on carbon materials with microwave absorption properties,  
148 brings both opportunities and challenges in providing new ways to recover strategic metals.  
149 Then a deep understanding of the MW heating-related phenomena must be realized. In  
150 particular, MW heating, with its distinctive internal heat mechanism, can mitigate the shadow  
151 effect during material heating, alter the heat transfer mode, and significantly reduce reaction  
152 times. Nevertheless, it's essential to emphasize that this heating mechanism differs from the  
153 process that takes place in solutions.

154 Fig. 1 illustrates the difference between the heating mechanisms in a water-based solution  
155 and a solid composed of carbon-based material. In the context of MW heating in a solution,  
156 the primary process involves the rotation of polar solvent molecules. Conversely, for  
157 electron-rich solids devoid of freely rotatable dipoles, such as carbon-based solids, the  
158 literature suggests that heat is generated through electron motion, manifesting as joule  
159 heating within the material's structure. This heat generation arises either due to collisions  
160 triggered by graphite's delocalized pi-electrons moving within a confined region and  
161 interacting with the oscillating field or as heat generated at grain/phase boundaries [19] due  
162 to the interfacial polarization. Furthermore, the comprehensive mechanism behind the MW  
163 heating of solids remains incompletely understood. Therefore, its potential applied to BM  
164 treatments hasn't yet been highlighted in the literature.

165






View Article Online  
DOI: 10.1039/D4SU00202D


Fig. 1: The MW heating mechanism in a water-based solution a) and a solid composed of carbon-based material b). In a solution, the primary process involves the rotation of polar solvent molecules. For electron-rich solids, such as carbon-based solids, the heat is generated through electron motion, manifesting as joule heating within the material's structure.

The main parameters used to model MW heating are permittivity, permeability, and loss tangent. Permittivity ( $\epsilon$ ) refers to a material's ability to engage with the MW electric field. It comprises both a real and an imaginary component. The real part ( $\epsilon'$ ) signifies the extent to which the electric field permeates, often referred to as the dielectric constant or permittivity. The imaginary part ( $\epsilon''$ ) signifies the energy retained within the material and is known as the electric loss factor [20]. It dictates the material's capacity to transform electric energy into heat. Permeability, on the other hand, characterizes the material's aptitude to interact with the magnetic field. The substrate's reaction to converting microwave energy into thermal loss is denoted as the loss tangent ( $\tan \delta$ ) and it is calculated as  $\epsilon''/\epsilon'$  [17]. The MW penetration depth ( $D_p$ ) indicates the distance a wave travels before its energy diminishes to  $1/e$ , and it is proportional to the MW wavelength and inversely proportional to  $(\tan \delta)^{1/2}$ . It can be calculated as reported in equation 1 [21]:

$$D_p = \frac{\lambda_0}{2\pi(2\xi')^{1/2}} \left\{ \left[ 1 + \left( \frac{\xi''}{\xi'} \right)^2 \right] - 1 \right\}^{-1/2} \quad (1)$$

On exposure to MW, the electromagnetic loss in a material is converted into heat. Moreover, with the temperature rise, the material's dielectric properties can change. This can alter the MW loss, with the consequence of changes in the heating characteristics [22]. As an example, alumina results transparent to MW up to 900 °C (resulting in high penetration depth of MW radiation), yet it starts to interact with microwaves at temperatures surpassing 1000 °C [20]. This makes it necessary to investigate suitable materials to be used for MW adsorbing and/or heat insulation applications.

It was already shown that MW can penetrate the spent carbon cathode material (produced in the process of aluminum electrolysis) with a depth higher than 0,01 m [21], also reaching values higher than 0.3 m for cathodic materials and graphite [10] and 0,2 - 1 m for anthracite



[23] and bituminous coal [24]. In particular, as the dielectric properties of the materials depend on the temperature, it results that MW penetration depth also can be variable. It also depends on the material density [24] and packing, making its evaluation extremely complicated for a mixture of different materials, such as waste made of several compounds and some contaminants, with variable chemistry.

In the case of MW heating the use of a solid-state material that can be excited by MW radiation, such as carbon, allows a very efficient heating, because the target material absorbs the MW energy. This is the case of LIBs, where the cathodic and anodic (generally made in graphite) materials are both in black mass. Graphite has  $\pi$ -electrons, which are responsible for heat generation (see Fig. 1). For carbon-based materials combined with magnetic materials, these heating effects can be further enhanced. Magnetic materials can absorb microwaves through magnetic losses, including hysteresis, eddy currents, and relaxation losses [20]. The interplay between the magnetic losses and the Joule heating in carbon can lead to efficient internal heating of the material. Finally, in MW processing of various materials, a susceptor can be also employed to amplify the MW-absorbing capabilities of the sample being treated. A susceptor material absorbs energy from the MW, converting it into heat energy that is then transferred to the processed material. For example, carbon can be used as a susceptor. For applications requiring reaching high temperatures, such as high melting point materials treatments, Si is often used. Conversely, charcoal powder is easily accessible at a significantly lower cost.

A susceptor can be also external to the sample, but in its proximity: the heat will be subsequently conveyed to the sample through conventional modes of heat transfer.

The susceptor assisted microwave heating is generally defined as “hybrid heating” (see Fig. 2). This was recently proposed for BM treatment [25] because graphite is generally used for low-temperature applications [26], then the presence of an external susceptor can be effective in the increasing of system temperature.





Fig. 2: A susceptor external to the sample heats a material from its surface due to the MW excitation (a), while when there is an interaction between the materials and MW, the material is heated from the centre (b).





228 The susceptor-assisted microwave heating, supporting the material heating (b) is generally defined as  
229 “hybrid heating”.

View Article Online  
DOI: 10.1039/D4SU00202D

232 The effective and suitable configuration of a susceptor-assisted MW heating system needs  
233 to couple a material that can be excited by MW with a thermal insulation system, which must  
234 envelop it. Indeed, thermal insulation plays a fundamental role in any technology involving  
235 a thermal process by limiting heat dissipation, especially at high temperatures. A suitable  
236 thermal insulation for MW depends not only on the material thermal stability but also on its  
237 ability to remain transparent to MW radiation across the entire temperature range. Alumina  
238 is a commonly used insulation material due to its outstanding transparency to MW radiation  
239 and its strong resistance to thermal and wear-related challenges over a wide range of  
240 temperatures.

241 Concerning the drawbacks connected with thermal treatments, the main negative aspect is  
242 pollutants gas generation, including electrolyte components, oxygenated hydrocarbons,  
243 hydrocarbons, and others [27]. The formation of different gas species is due to electrolyte  
244 volatilization, electrolyte degradation/decomposition, and pyrolysis of the organic separator  
245 and binder, followed by complex radical reactions among the species formed by the  
246 physicochemical reactions.

#### 248 4. Experimental

249 LCO spent BM was provided by Spirit s.r.l., a company recycling battery located in Chiampo,  
250 Vicenza, Italy.


251 The BM was obtained after conventional mechanical pretreatments to separate the battery  
252 case, the plastic components, and the electrolyte.

253 The sample was digested to evaluate the concentration of Li, as described in [18]. The  
254 composition results in 38.4 g/Kg of Li, 288 g/Kg of Co, 5.2 g/Kg of Mn, 49 g/Kg of Ni, and  
255 4.8 g/Kg of Cu. The amount of graphite in the BM is 19.2% [18].

256 BM was treated at 600 W at 2.4GHz for 5 minutes, increasing the sample mass, in each  
257 experiment, from 0.5 to 4.5 g (see Table 1 for the sample name with the corresponding  
258 mass), in a PYRO Advanced Microwave Muffle Furnace (Milestone s.r.l., Bergamo, Italy),  
259 which was equipped with a susceptor [25]. The tests were repeated three times. The  
260 temperature of the samples, after the thermal treatment was provided by thermal imaging  
261 camera testo 890.

262 The sample resulted in filling the sample holder to about 1 cm.

263 All the samples, after the MW treatments, were analysed by X-ray diffraction (XRD), using  
264 a Panalytical diffractometer using Cu Ka (1.5406 Å) radiation and operating at 40 kV and 40  
265 mA. The patterns were acquired from 10° to 70° (2θ). For the leaching test, BM was mixed  
266 with Milli-Q water in a heating plate at 80 °C for 30 min using a solid/liquid ratio of 40 g/L  
267 [25]. After this time the solution was filtered with a vacuum filtration by using a nylon  
268 membrane with 0.45 µm. Li<sup>+</sup> concentration was evaluated by ion chromatography (IC),  
269 Metrohm 883 Compact IC plus (Metrohm AG, Herisau, Switzerland) and cation exchange  
270 column Metrosep C4-150/4.0 (Metrohm AG, Herisau, Switzerland).  
271  
272



273

274 **5. Results and discussion**View Article Online  
DOI: 10.1039/D4SU00202D

## 275 5.1 A mass and sample heating correlation

276  $\text{LiCoO}_2$ , in the presence of a carbon source, can decompose into  $\text{LiO}_2$  and Co (or  $\text{CoO}$ ), by  
277 increasing the temperature, showing the most favourable condition at about  $700^\circ\text{C}$  [28].  
278 Graphite is converted into CO and  $\text{CO}_2$ . The reactions can be followed by analysing the  
279 sample mass loss, which is because  $\text{CO}_2$  removes solid carbon contained in the BM, to form  
280 a gas.


281 However classical heating systems are more time-consuming in comparison to MW  
282 technologies, and the target temperature needs more time to be reached. To obtain an  
283 efficient heating system, it is fundamental to evaluate the MW penetration depth: if the  
284 penetration depth is not high, the heating efficiency may be low.

285 For an LCO BM, containing about 20% of graphite, the penetration depth of the microwave  
286 can be calculated based on (1) [17]. The results reported in Fig. S1 (see the Supporting)  
287 show that till to about  $400^\circ\text{C}$ , the MW penetration depth decreases with the increase of the  
288 temperature, due to the rise of the MW-absorbing properties of the BM. This means that the  
289 loss factor ( $\epsilon''$ ) and the dielectric constant ( $\epsilon'$ ) increase.

290 Fig. S1 shows that for the range of temperatures reached by these experiments, the  
291 penetration depth of MW radiation ranges from 0.025 to 0.065 m [17]. For a range of  
292 temperatures from  $650^\circ\text{C}$  to  $900^\circ\text{C}$  the penetration depth may also be higher than 0.06 m,  
293 depending on the BM density and dielectric parameters.

294 Concerning the samples investigated in this work, it is possible to conclude that all the  
295 samples were penetrated by MW radiation (see Fig. S1), with the consequence that an  
296 increase in the sample mass subjected to the treatment produces an increase in its  
297 temperature, due to the increase of the material that is excited by MW.

298 The temperature reached by the samples versus the different masses is reported in Fig. 3.



300



Fig. 3: Temperatures reached by the spent LCO battery samples, treated at 600 W for 5 minutes, as a function of the samples' mass. Error bars correspond to the temperature variation inside the samples, evaluated by the thermal imaging camera.

Article Online  
DOI: 10.1039/D4SU00202D

An increase in the mass undergoing treatment leads to a rise in sample temperature during MW excitation because there's more BM to absorb the MW energy. This specific effect hasn't been explored in spent LIBs, although it's documented in other contexts. According to the literature, this may be attributed to the fact that a larger mass in the same container will have a reduced surface area to volume ratio, thus lowering heat dissipation [29–31]. Unlike conventional heating methods, where heat is applied externally, microwave systems generate heat internally. As a result, it can be expected that the temperature of the material will rise. Therefore, the loss of heat from the sample becomes a significant factor that governs the heating process. In the present case, the rate of temperature increase is not linear, probably because of the changes in the permittivity ( $\epsilon'$ ), and the electric loss factor ( $\epsilon''$ ) that after 600 °C start to increase significantly.

The mass loss (%) of samples treated in this work is shown in Fig. 4 and is plotted against the mean detected sample temperatures. The linear correlation observed in the data can be explained by the fact that an increase in temperature, due to a more prolonged treatment, more effectively promotes the oxidation of carbon. With the increase in the treatment time and the temperature rise, the carbon within the samples reacts more readily with oxygen to form carbon dioxide. This gas is released into the atmosphere, resulting in a carbon loss for the sample (weight loss). This process highlights the occurrence of carbothermic reactions, where the elevated temperatures facilitate the transformation of solid carbon into gaseous carbon dioxide. Thus, higher temperatures enhance the efficiency of carbon oxidation, leading to greater mass loss in the samples due to the emission of CO<sub>2</sub> (as described in section 2).




Fig. 4: Mass loss of the LCO BM samples, reported versus the final temperature.




333

334 Fig. 5 shows the XRD patterns of LCO BM before (LCO\_tq) and after MW treatments with  
 335 the mass increased (sample 2 and sample 5, see Figure 3). The results show that LCO  
 336 powder (before MW treatment) is characterized by graphite and lithium cobalt oxide  
 337 ( $\text{LiCoO}_2$ ). Some peaks of Ni were also detected. This is also confirmed by the chemical  
 338 analysis reported in the experimental section, probably due to some other cathode  
 339 contamination. Also, some peaks of  $\text{CoO}$ ,  $\text{Co}_3\text{O}_4$ , and  $\text{Li}_2\text{O}$  are present. The presence of  
 340 unexpected phases may be due to several reasons: first, it is important to highlight that the  
 341 BM used for this study is a real sample, provided by a recycling facility, then it also contains  
 342 Mn and Ni probably due to contamination of other cathodic materials. In addition, the pre-  
 343 treatment (performed at  $800\text{ }^\circ\text{C}$ ) realised in the recycling facility, to remove the binder and  
 344 the electrolyte, can have partially promoted some carbothermal reactions [17].

345

346 After MW treatment, XRD patterns show an evident decrease in graphite peaks and the  
 347 reduction of  $\text{LiCoO}_2$  with the formation of  $\text{CoO}$ . In the case of a sample with a higher mass  
 348 amount (sample 5), it is clear the increase in the  $\text{CoO}$  intensity. This means that the  
 349 carbothermal reactions are promoted by the mass increase, which is related to the higher  
 350 temperature rise (see Fig. 3).

351



352

353

354 Fig.5: XRD patterns of LCO BM before (sample LCO\_tq) and after MW treatment with the increase of black  
 355 mass (sample 2 and sample 5).

356

357 These results suggest that the heating mechanism is completely different in comparison to  
 358 conventional systems, where an increase in the mass needs a corresponding increase in  
 359 the energy that must be transferred for the increase in the sample temperature [32].

360 Carbon materials possess excellent electrical conductivity, which is crucial for microwave  
 361 absorption. When combined with magnetic materials, the interface between these two types



of materials increases [30]. This interface can act as a site for interfacial polarization, where the electric field can cause charges at the interface to oscillate, leading to energy dissipation as heat (see Figure 1). LCO exhibits some magnetic properties, even though it is not typically classified as a magnetic material for applications relying on strong magnetic interactions, such as magnetic storage devices or magnetic structural components. However, cobalt oxides, which are formed by carbothermic reaction (see Figure 3) are magnetic materials [33]. These cobalt oxides can significantly contribute to the magnetic loss mechanisms essential for effective microwave absorption, making them valuable as high-temperature microwave-absorbing materials [20]. When these materials interact with microwave radiation, they absorb the electromagnetic energy and convert it into heat, which typically increases their temperature. Magnetic loss materials dissipate electromagnetic energy through hysteresis loss, natural resonance, eddy current loss, magnetic hysteresis loss, domain-wall resonance, and other forms [20]. This effect was very recently demonstrated for cobalt oxide composite [34]. In this work, this effect is proposed, for the first time, to explain the heating mechanism of the black mass, induced by microwave.

To assess the potential of this technology, the amount of lithium that can be recovered is quantified.

For a simplified recovery of strategic metals from spent LIBs it is suggested to separate Li from transition metals. This is possible due to the high water solubility of  $\text{Li}_2\text{O}$ , which is formed after carbothermic reduction of LCO [35]. Then after the MW treatment, the samples were subjected to water leaching.

Table 1 shows the amount (%) of Li recovered by water leaching. As expected, an increase in the recovered Li corresponds to a higher mass treated in the MW oven. This demonstrates that higher temperatures promote carbothermic reductions and that this treatment can allow to recovery high amount of the lithium found in spent LIBs in a few minutes.

Table 1: Evaluation of the Li recovered by water leaching versus the mass increased. The analyses were realised by Ion Chromatography

Sample name	Sample mass (g)	Li (g/kg)		Li recovery (%)
0	0.5	21.76	± 0.33	56.7 ± 1.2
1	1	24.47	± 0.37	63.7 ± 1.4
2	2	23.80	± 0.36	62.0 ± 1.4
3	3	20.74	± 0.32	54.0 ± 1.2
4	4	20.14	± 0.31	52.4 ± 1.1
5	4.5	34.19	± 2.85	89.0 ± 7.4

## 5.2 Revision of the pyrometallurgy characteristics associated with battery recovery

Literature indicates that hydrometallurgical methods are better suited for recycling specific cathodic materials since they must be optimized for the material to be recovered. On the





398 other hand, pyrometallurgical approaches are suitable for recycling different cathodic  
399 materials, also in a mixture, due to the presence of carbon in the BM, which supports  
400 carbothermic reactions [36].

401 However, traditional pyrometallurgical techniques employed in the recycling of LIBs have  
402 numerous drawbacks, and there is a prevailing idea that these processes might not be  
403 suitable for large-scale industrial implementation. Although they offer relative simplicity in  
404 execution, these methods are not completely investigated. In particular, new technologies  
405 involving the use of MW are still at low TRL.

406 Furthermore, literature also suggests that lithium is generally recycled in low quantities  
407 through pyrometallurgical methods, while these techniques exhibit their highest  
408 effectiveness in recovering particularly valuable metals like cobalt [8]. It is preferred to  
409 extract Li, after the thermal treatment, by hydrometallurgy [37]. As battery technology  
410 advances, the cobalt content in electrode materials is diminishing, while the utilization of  
411 nickel and manganese is on the rise. This shift makes pyrometallurgy less attractive.

412 However, the treatment proposed in this paper, obtained by using MW radiation,  
413 demonstrates that some drawbacks of the traditional pyrometallurgical procedures can be  
414 overcome.

415 The advantages and improvements of the new proposed technologies are reported in the  
416 following.

417 First, the dosage of a carbon source to have a carbothermic reaction is not necessary,  
418 because in the BM the graphite is already present, and it can be used as the reducing agent.  
419 This means that it is not mandatory to use onerous pre-treatment methods to separate the  
420 cathode and anode materials.

421 Second, the reactions can be carried out also in an ambient atmosphere, even if the rapid  
422 increase in the temperature of the samples must be monitored. Then inert atmosphere can  
423 be not necessary for the reactions.

424 In addition, Li can be recovered directly after the thermal process by water leaching and  
425 then precipitated as lithium carbonate ( $\text{Li}_2\text{CO}_3$ ) by the carbonation of the water solution. After  
426 water leaching and Li recover, the other metals (Mn, Co, Ni, etc.) can be precipitated through  
427 hydrometallurgical processes, by using organic acids instead of inorganic ones [25]

428 Concerning the aspect connected with the management of gases generated by the  
429 reactions, it would be possible to equip the treatment apparatus with suitable air treatment  
430 systems, to recover and neutralize pollutant gases. For this aim, the organic gas species  
431 may be recovered as liquids or solids. For example, a dedicated condensation system, with  
432 a controlled temperature may be designed to recover the organic gaseous components via  
433 low-temperature volatilization [38]. There is also the possibility of using an afterburner and/or  
434 an adsorbent [38]. This must also be evaluated considering that it may allow to avoid some  
435 onerous thermal pre-treatments which are generally realized to remove plastics,  
436 electrolytes, and the binder. Finally, the possibility of recovering the carbon dioxide emitted  
437 during the carbothermic reactions, after its partial purification of some pollutants, to be  
438 reused for lithium carbonation seems quite attractive. A second way to face this drawback  
439 would be to improve the pre-treatments: the organic solvents, binders, and separators would  
440 be recovered with dedicated treatments, to improve the quality of the BM addressed to the  
441 treatment.



442 In summary, the proposed technology would also allow a simplification of the entire recovery  
443 process, by reducing some pre-treatment steps. However, this requires more dedicated  
444 studies, involving considerations about all the pre-treatment steps (considering LIBs  
445 collection, separation, sorting, and preliminary thermal processes).  
446  
447

## 448 6. Conclusions and outlook

449 This work outlines both the benefits and hurdles associated with a novel MW heating  
450 approach for lithium recovery from spent lithium-ion batteries. The possibility of coupling  
451 carbon materials with magnetic materials in the BM appears to result in a strategic approach  
452 to increasing the final temperature of microwave-absorbing materials, by coupling dielectric  
453 loss with magnetic loss.

454 The application of MW allows for the rapid elevation of temperature in the BM, facilitating  
455 carbothermic reactions that yield lithium oxide and enable lithium separate recovery through  
456 a water solution. Experimental results obtained from a spent LCO BM sample reveal an  
457 efficiency higher than 80% within just a 5-minute treatment period. These findings support  
458 the proposition of this technology as a promising alternative to the traditional  
459 pyrometallurgical method and offer the opportunity to avoid several onerous BM pre-  
460 treatment steps. However, despite the evident advantages, full comprehension, and  
461 modelling of the mechanism of microwave heating are still in infancy and some open issues  
462 need to be addressed in the future:  
463

464 i) The dielectric loss, and consequently the penetration depth of the BM has great  
465 importance for the energy conversion efficiency, nevertheless, BM is the result of a  
466 combination of the cathodic materials in graphite. Then, dedicated studies to promote the  
467 realization of a library containing the data of the loss capacity due to the different cathodic  
468 species mixed with graphite should be implemented;  
469

470 ii) All the advantages of MW processes involved in LIBs recovery are not completely  
471 considered and investigated. For example, additional thermal effects, defined as the  
472 localized superheating effects are still not investigated for this waste [39];  
473

474 iii) The possibility of recovering carbon dioxide generated during the carbothermic reactions,  
475 to be used as reactants to produce lithium carbonate must be exploited;  
476

477 iv) The design and development of MW reactors operating in continuous mode for large  
478 batches of the process should be considered;  
479

480 v) The introduction of susceptors may allow for the expansion of the applicability of MW  
481 technology to a range of applications, including the treatment of materials that are typically  
482 highly transparent to microwaves, for example, some ceramics, and materials that are highly  
483 reflective to microwaves, such as metals. This opportunity must be better investigated for  
484 BM recovery.  
485



486 In conclusion, given the early stage of LIBs recovery efforts, MW-heating presents a highly  
487 promising method to be explored and developed to propose a sustainable approach for  
488 strategic metals recovery.

489

## 490 **Author contribution**

491 Conceptualization, A.C, A.Z, M.S, and E.B.; methodology, A.C, A.Z, M.S, and E.B.;  
492 validation, A.C, A.Z, M.S, and E.B.; formal analysis, A.C, A.Z, M.S, D.L.C, G.B, and E.B;  
493 investigation, A.C, A.Z, and M.S.; resources, E.B.; data curation, A.C, A.Z, M.S, and E.B;  
494 writing—original draft preparation, A.C, A.Z, M.S, and E.B.; writing—review and editing, A.C,  
495 A.Z, M.S, and E.B visualization, A.C, A.Z, M.S, G.B and E.B supervision E.B.; project  
496 administration, E.B.; funding acquisition, E.B. All authors have read and agreed to the  
497 published version of the manuscript.

## 498 **Conflicts of interest**

499 There are no conflicts to declare

500 **Funding:** This study was realized with the support of Fondazione CARIPO to “Tech4Lib—  
501 Spent Lithium-ion battery recovery” (CUP D73C23000170007) and by InnovFin Equity, with  
502 financial backing of the European Union under Horizon 2020 Financial Instruments and the  
503 European Fund for Strategic Investments (EFSI) set up under the Investment Plan for  
504 Europe. The purpose of EFSI is to help support financing and implementing productive  
505 investments in the European Union and to ensure increased access to financing. Alessandra  
506 Zanoletti acknowledges financial support from the Next-GenerationEU (Italian PNRR – M4  
507 C2, Invest 1.3 – D.D. 1551.11-10-2022, PE00000004) within the MICS (Made in Italy –  
508 Circular and Sustainable) Extended Partnership for her research fellowship. Matteo Scaglia  
509 acknowledges financial support for his grant from CSMT Gestione S.c.a.r.l. This manuscript  
510 reflects only the authors’ views and opinions, neither the European Union nor the European  
511 Commission can be considered responsible for them.


512 **Acknowledgments:** The authors thank Spirit s.r.l. company for the BM supply. Graphical  
513 abstract Created with BioRender.com and IA support. Figures 1 and 2 were realised with  
514 BioRender.com.

## 515 **References**

- 516 [1] N. Vieceli, R. Casasola, G. Lombardo, B. Ebin, M. Petranikova, Hydrometallurgical  
517 recycling of EV lithium-ion batteries: Effects of incineration on the leaching efficiency of  
518 metals using sulfuric acid, *Waste Management* 125 (2021) 192–203.  
519 <https://doi.org/10.1016/j.wasman.2021.02.039>.



- 520 [2] X. Chen, D. Kang, J. Li, T. Zhou, H. Ma, Gradient and facile extraction of valuable metals  
521 from spent lithium ion batteries for new cathode materials re-fabrication, *J Hazard Mater* 389  
522 (2020). <https://doi.org/10.1016/j.jhazmat.2019.121887>. Article Online  
DOI: 10.1039/D4SU00202D
- 523 [3] E. Mossali, N. Picone, L. Gentilini, O. Rodriguez, J.M. Pérez, M. Colledani, Lithium-ion  
524 batteries towards circular economy: A literature review of opportunities and issues of  
525 recycling treatments, *J Environ Manage* 264 (2020).  
526 <https://doi.org/10.1016/j.jenvman.2020.110500>.
- 527 [4] X. Wang, G. Gaustad, C.W. Babbitt, C. Bailey, M.J. Ganter, B.J. Landi, Economic and  
528 environmental characterization of an evolving Li-ion battery waste stream, *J Environ Manage*  
529 135 (2014) 126–134. <https://doi.org/10.1016/j.jenvman.2014.01.021>.
- 530 [5] Q. Cheng, Z. Wang, Y. Wang, J.T. Li, H. Fu, Recent advances in preferentially selective Li  
531 recovery from spent lithium-ion batteries: A review, *J Environ Chem Eng* 12 (2024).  
532 <https://doi.org/10.1016/j.jece.2024.112903>.
- 533 [6] P. Söderholm, T. Ekvall, Metal markets and recycling policies: impacts and challenges,  
534 (n.d.). <https://doi.org/10.1007/s13563-019-00184-5/Published>.
- 535 [7] J.N. Trost, J.B. Dunn, Assessing the feasibility of the Inflation Reduction Act's EV critical  
536 mineral targets, *Nat Sustain* 6 (2023) 639–643. <https://doi.org/10.1038/s41893-023-01079-8>.
- 537 [8] Z.J. Baum, R.E. Bird, X. Yu, J. Ma, Lithium-Ion Battery Recycling—Overview of  
538 Techniques and Trends, *ACS Energy Lett* 7 (2022) 712–719.  
539 <https://doi.org/10.1021/acseenergylett.1c02602>.
- 540 [9] N. Li, J. Guo, Z. Chang, H. Dang, X. Zhao, S. Ali, W. Li, H. Zhou, C. Sun, Aqueous  
541 leaching of lithium from simulated pyrometallurgical slag by sodium sulfate roasting, *RSC*  
542 *Adv* 9 (2019) 23908–23915. <https://doi.org/10.1039/c9ra03754c>.
- 543 [10] S. Pindar, N. Dhawan, Evaluation of in-situ microwave reduction for metal recovery from  
544 spent lithium-ion batteries, *Sustainable Materials and Technologies* 25 (2020).  
545 <https://doi.org/10.1016/j.susmat.2020.e00201>.
- 546 [11] S. Pindar, N. Dhawan, Comparison of Microwave and Conventional Indigenous  
547 Carbothermal Reduction for Recycling of Discarded Lithium-Ion Batteries, *Transactions of*  
548 *the Indian Institute of Metals* 73 (2020) 2041–2051. <https://doi.org/10.1007/s12666-020-01956-2>.
- 549 [12] A. Fahimi, A. Zanoletti, A. Cornelio, E. Mousa, G. Ye, P. Frontera, L.E. Depero, E.  
550 Bontempi, Sustainability Analysis of Processes to Recycle Discharged Lithium-Ion Batteries,  
551 Based on the ESCAPE Approach, *Materials* 15 (2022). <https://doi.org/10.3390/ma15238527>.
- 552 [13] Y. Fu, Y. He, Y. Yang, L. Qu, J. Li, R. Zhou, Microwave reduction enhanced leaching of  
553 valuable metals from spent lithium-ion batteries, *J Alloys Compd* 832 (2020).  
554 <https://doi.org/10.1016/j.jallcom.2020.154920>.
- 555 [14] A. Zhu, X. Bian, W. Han, Y. Wen, K. Ye, G. Wang, J. Yan, D. Cao, K. Zhu, S. Wang,  
556 Microwave-ultra-fast recovery of valuable metals from spent lithium-ion batteries by deep  
557 eutectic solvents, *Waste Management* 156 (2023) 139–147.  
558 <https://doi.org/10.1016/j.wasman.2022.11.035>.
- 559 [15] J. Lie, J.C. Liu, Closed-vessel microwave leaching of valuable metals from spent lithium-ion  
560 batteries (LIBs) using dual-function leaching agent: Ascorbic acid, *Sep Purif Technol* 266  
561 (2021). <https://doi.org/10.1016/j.seppur.2021.118458>.
- 562 [16] Y. Zhao, B. Liu, L. Zhang, S. Guo, Microwave Pyrolysis of Macadamia Shells for Efficiently  
563 Recycling Lithium from Spent Lithium-ion Batteries, *J Hazard Mater* 396 (2020).  
564 <https://doi.org/10.1016/j.jhazmat.2020.122740>.
- 565 [17] Y. Zhao, B. Liu, L. Zhang, S. Guo, Microwave-absorbing properties of cathode material  
566 during reduction roasting for spent lithium-ion battery recycling, *J Hazard Mater* 384 (2020).  
567 <https://doi.org/10.1016/j.jhazmat.2019.121487>.
- 568 [18] M. Scaglia, A. Cornelio, A. Zanoletti, D. La Corte, G. Biava, I. Alessandri, A. Forestan, C.  
569 Alba, L.E. Depero, E. Bontempi, Microwave-Assisted Recovery of Spent LiCoO<sub>2</sub> Battery  
570





- 571 from the Corresponding Black Mass, Batteries 9 (2023) 536.  
 572 <https://doi.org/10.3390/batteries9110536>.
- 573 [19] T. Kim, J. Lee, K.H. Lee, Full graphitization of amorphous carbon by microwave heating,  
 574 RSC Adv 6 (2016) 24667–24674. <https://doi.org/10.1039/c6ra01989g>.
- 575 [20] Q. Xia, Z. Han, Z. Zhang, Z. Huang, X. Wang, J. Chang, Q. Chen, M. Chen, High  
 576 temperature microwave absorbing materials, J. Mater. Chem. C 11 (2023) 4552.  
 577 <https://doi.org/10.1039/d2tc04671g>.
- 578 [21] Z. Zhu, L. Xu, Z. Han, J. Liu, L. Zhang, C. Yang, Z. Xu, P. Liu, Defluorination study of  
 579 spent carbon cathode by microwave high-temperature roasting, J Environ Manage 302  
 580 (2022). <https://doi.org/10.1016/j.jenvman.2021.114028>.
- 581 [22] S. Tamang, S. Aravindan, Joining of dissimilar metals by microwave hybrid heating: 3D  
 582 numerical simulation and experiment, International Journal of Thermal Sciences 172 (2022).  
 583 <https://doi.org/10.1016/j.ijthermalsci.2021.107281>.
- 584 [23] Z. Peng, X. Lin, X. Wu, J.Y. Hwang, B.G. Kim, Y. Zhang, G. Li, T. Jiang, Microwave  
 585 absorption characteristics of anthracite during pyrolysis, Fuel Processing Technology 150  
 586 (2016) 58–63. <https://doi.org/10.1016/j.fuproc.2016.04.036>.
- 587 [24] Z. Peng, J.Y. Hwang, B.G. Kim, J. Mouris, R. Hutcheon, Microwave absorption capability of  
 588 high volatile bituminous coal during pyrolysis, in: Energy and Fuels, 2012: pp. 5146–5151.  
 589 <https://doi.org/10.1021/ef300914f>.
- 590 [25] A. Fahimi, I. Alessandri, A. Cornelio, P. Frontera, A. Malara, E. Mousa, G. Ye, B. Valentim,  
 591 E. Bontempi, A microwave-enhanced method able to substitute traditional pyrometallurgy  
 592 for the future of metals supply from spent lithium-ion batteries, Resour Conserv Recycl 194  
 593 (2023). <https://doi.org/10.1016/j.resconrec.2023.106989>.
- 594 [26] S. Rawat, R. Samyal, R. Bedi, A. kumar Bagha, Comparative performance of various  
 595 susceptor materials and vertical cavity shapes for selective microwave hybrid heating  
 596 (SMHH), Phys Scr 97 (2022). <https://doi.org/10.1088/1402-4896/ac9e7d>.
- 597 [27] X. Hu, E. Mousa, L. Ånnhagen, Z. Musavi, M. Alemrajabi, B. Hall, G. Ye, Complex gas  
 598 formation during combined mechanical and thermal treatments of spent lithium-ion-battery  
 599 cells, J Hazard Mater 431 (2022). <https://doi.org/10.1016/j.jhazmat.2022.128541>.
- 600 [28] G. Lombardo, B. Ebin, M.R.J. St Foreman, B.M. Steenari, M. Petranikova, Chemical  
 601 Transformations in Li-Ion Battery Electrode Materials by Carbothermic Reduction, ACS  
 602 Sustain Chem Eng 7 (2019) 13668–13679. <https://doi.org/10.1021/acssuschemeng.8b06540>.
- 603 [29] M. Omran, T. Fabritius, E.P. Heikkinen, G. Chen, Dielectric properties and carbothermic  
 604 reduction of zinc oxide and zinc ferrite by microwave heating, R Soc Open Sci 4 (2017).  
 605 <https://doi.org/10.1098/rsos.170710>.
- 606 [30] R.K. Amankwah, C.A. Pickles, Microwave roasting of a carbonaceous sulphidic gold  
 607 concentrate, Miner Eng 22 (2009) 1095–1101. <https://doi.org/10.1016/j.mineng.2009.02.012>.
- 608 [31] C.A. Pickles, Microwave heating behaviour of nickeliferous limonitic laterite ores, Miner  
 609 Eng 17 (2004) 775–784. <https://doi.org/10.1016/j.mineng.2004.01.007>.
- 610 [32] R.R. Mishra, A.K. Sharma, Microwave-material interaction phenomena: Heating  
 611 mechanisms, challenges and opportunities in material processing, Compos Part A Appl Sci  
 612 Manuf 81 (2016) 78–97. <https://doi.org/10.1016/j.compositesa.2015.10.035>.
- 613 [33] A. Das, C. Balasubramanian, P. Orpe, G.M. Pugliese, A. Puri, A. Marcelli, N.L. Saini,  
 614 Morphological, electronic, and magnetic properties of multicomponent cobalt oxide  
 615 nanoparticles synthesized by high temperature arc plasma, Nanotechnology 33 (2022).  
 616 <https://doi.org/10.1088/1361-6528/ac30f5>.
- 617 [34] A. Ahlawat, M. Bala, M.K. Nayak, S. Tyagi, Development of cobalt oxide and titanium  
 618 carbide based composite for microwave absorption in X-band, Materials Science and  
 619 Engineering: B 305 (2024). <https://doi.org/10.1016/j.mseb.2024.117447>.

View Article Online  
DOI: 10.1039/D4SU00202D



- 620 [35] Z. Yan, A. Sattar, Z. Li, Priority Lithium recovery from spent Li-ion batteries via  
621 carbothermal reduction with water leaching, *Resour Conserv Recycl* 192 (2023). View Article Online  
DOI: 10.1039/D4SU00202D  
622 <https://doi.org/10.1016/j.resconrec.2023.106937>.
- 623 [36] E. Fan, L. Li, Z. Wang, J. Lin, Y. Huang, Y. Yao, R. Chen, F. Wu, Sustainable Recycling  
624 Technology for Li-Ion Batteries and Beyond: Challenges and Future Prospects, *Chem Rev*  
625 120 (2020) 7020–7063. <https://doi.org/10.1021/acs.chemrev.9b00535>.
- 626 [37] L.F. Zhou, D. Yang, T. Du, H. Gong, W. Bin Luo, The Current Process for the Recycling of  
627 Spent Lithium Ion Batteries, *Front Chem* 8 (2020).  
628 <https://doi.org/10.3389/fchem.2020.578044>.
- 629 [38] X. Zhong, W. Liu, J. Han, F. Jiao, W. Qin, T. Liu, C. Zhao, Pyrolysis and physical separation  
630 for the recovery of spent LiFePO<sub>4</sub> batteries, *Waste Management* 89 (2019) 83–93.  
631 <https://doi.org/10.1016/j.wasman.2019.03.068>.
- 632 [39] Z. Wang, C. Yu, H. Huang, W. Guo, J. Yu, J. Qiu, Carbon-enabled microwave chemistry:  
633 From interaction mechanisms to nanomaterial manufacturing, *Nano Energy* 85 (2021).  
634 <https://doi.org/10.1016/j.nanoen.2021.106027>.
- 635
- 636



The data supporting this article have been included as part of the Supplementary Information

Open Access Article. Published on 15 Gouere 2024. Downloaded on 2024-07-21 00:23:05.  
This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

