ChemComm

COMMUNICATION



View Article Online

Biferrocenium salts with magnetite-like mixed-valence iron: coexistence of Fe^{3+} and $Fe^{2.5+}$ in the crystal[†]

Tomoyuki Mochida,*^{ab} Eri Nagabuchi,^b Masashi Takahashi^b and Hatsumi Mori^c

DOI: 10.1039/c3cc49568j

50. 2481

Cite this: Chem. Commun., 2014,

Received 18th December 2013.

Accepted 13th January 2014

www.rsc.org/chemcomm

The biferrocene-based salt $[Bifc]_2[Ni(mnt)_2]_3$ (Bifc = bis(isopropylthio)biferrocene; mnt = maleonitriledithiolate) contains a biferrocenium monocation and dication within the same crystal. The coexistence of Fe³⁺ and mixed-valence Fe^{2.5+}, which resembles the valence state of magnetite, was confirmed by Mössbauer spectroscopy.

Magnetite (Fe_3O_4) is a basic mixed-valence compound that has attracted significant attention.¹ In the inverse spinel structure of magnetite, the tetrahedral sites (A sites) and octahedral sites (B sites) are occupied by Fe^{3+} ions and $Fe^{2.5+}$ ions, respectively, and the latter ions comprise Fe²⁺ and Fe³⁺ ions that undergo rapid electron exchange, as demonstrated by ⁵⁷Fe Mössbauer spectroscopy and other methods.^{1,2} Mixed valency in molecular compounds and metal complexes has attracted considerable interest.^{3,4} Biferrocenium salts are well-known organometallic mixed-valence compounds.⁵ Biferrocenes exhibit three redox states, *i.e.*, neutral, monocation, and dication (Fig. 1), and produce salts with mixedvalence monocations. We previously reported a biferrocenium salt that undergoes a phase transition from a monocationic to dicationic salt at low temperatures, which demonstrates that the dicationic species can exist when stabilized by electrostatic interactions.⁶ Herein, we report the intriguing valence state of a biferrocenebased salt, *i.e.*, $[Bifc]_2[M(mnt)_2]_3$ (**1**, Bifc = 1', 1'''-bis(isopropylthio)-1,1"-biferrocene, Fig. 2) that exhibits a 2:3 cation/anion ratio and contains both a mixed-valence monocation and dication in the same crystal. \ddagger [Ni(mnt)₂]⁻ is a planar paramagnetic anion, which has produced intriguing ferrocenium-based salts.7



Fig. 1 The three redox states of biferrocene



Fig. 2 Chemical formula of [bis(isopropylthio)biferrocene]₂[Ni(mnt)₂]₃ (1).

The crystal structure of 1 was determined at 173 K (space group $P\bar{1}$).⁸ The packing diagram of **1** viewed along the *a*-axis is shown in Fig. 3. There are two crystallographically independent cations, i.e., A and B, which are both located on the inversion center. The $[Ni(mnt)_2]^{-1}$ anions form centrosymmetric trimers, which are further stacked along the *a*-axis to form a columnar structure (ESI[†]).⁹ The cations are located between the columns of anions. Examination of the intramolecular geometry revealed that cations A and B have different valence states and are dicationic and monocationic, respectively. The average Fe–C(Cp) distance in cation A (2.085 Å) is similar to that of a ferrocenium cation (2.08 Å), whereas that in cation B (2.063 Å) is intermediate of that for a ferrocenium cation and neutral ferrocene (2.04 Å) and thus corresponds to a mixed-valence monocation.¹⁰ The valence state of **1** is hence represented as $[Bifc_A]^{2+}[Bifc_B]^+[{Ni(mnt)_2}_3]^{3-}$. Because the two Fe atoms in each cation are crystallographically equivalent, cations A and B contain Fe³⁺ and averaged-valence Fe^{2.5+}, respectively. The corresponding Pt-containing salt, *i.e.*, [Bifc]₂[Pt(mnt)₂]₃ 2, has a similar structure¹¹ and the same valence state characteristics.

^a Department of Chemistry, Graduate School of Science, Kobe University, Rokkodai, Nada, Hyogo 657-8501, Japan. E-mail: tmochida@platinum.kobe-u.ac.jp;

Fax: +81 78 803 5679; Tel: +81 78 803 5679

^b Department of Chemistry, Faculty of Science, Toho University, Miyama, Funabashi, Chiba 274-8510, Japan

^c Institute for Solid State Physics, The University of Tokyo, Kashiwanoha, Kashiwa, Chiba 277-8581, Japan

[†] Electronic supplementary information (ESI) available: Experimental procedures, molecular structures and crystal structures, temperature dependence of ⁵⁷Fe Mössbauer spectra, and crystallographic data. CCDC 263333 (1) and 263334 (2). For ESI and crystallographic data in CIF or other electronic format see DOI: 10.1039/c3cc49568j



Fig. 3 Packing diagram of 1 viewed along the *a*-axis. Hydrogen atoms are omitted for clarity. Dotted lines indicate the close Fe \cdots NC distances between the cation and the anion.



The valence states of the iron atoms in the cations were unambiguously determined using 57 Fe Mössbauer spectroscopy. Fig. 4 shows the spectrum recorded at 300 K, which features two equal-intensity components. The inner doublet, which has an isomer shift of 0.43 mm s⁻¹ (relative to α -iron) and a quadrupole splitting of 0.49 mm s⁻¹, corresponds to Fe³⁺ in the biferrocenium dication (cation A). The outer doublet, which has an isomer shift of 0.44 mm s⁻¹ and a quadrupole splitting of 1.28 mm s⁻¹, corresponds to Fe^{2.5+} in a mixed-valence biferrocenium monocation that undergoes rapid valence exchange (>10⁸ s⁻¹, cation B).⁵ The spectral features remain unchanged down to 6 K (Fig. S1, ESI†).

This salt, which contains Fe^{3+} and $Fe^{2.5+}$, is isoelectronic to magnetite in terms of the valence state of the iron, while the electron transfer between Fe^{2+} and Fe^{3+} is intramolecular. Although magnetite undergoes a charge-ordering transition at around 119 K,¹ 1 exhibits no valence localization of the $Fe^{2.5+}$ site, at least down to 6 K; thus, it is highly likely that valence tautomerization of 1 occurs *via* electron tunneling.¹² The origin



Fig. 5 Temperature dependence of the magnetic susceptibility (χT value) of **1**.

of the coexistence of a dication and monocation in **1** is reasonably attributed to differences in the local electrostatic interactions. The ferrocenium sites in biferrocenium-[Ni(mnt)₂] salts are stabilized by neighboring cyano groups.⁹ In **1**, the Fe atom in cation A is surrounded by four electronegative cyano groups from the anion (Fe···NC distances: 3.999(4)–4.325(4) Å, indicated by dotted lines in Fig. 3), which strongly stabilizes the cationic state; in contrast, cation B has no such interactions.

This salt exhibits paramagnetic behavior. The temperature dependence of the γT value is shown in Fig. 5. 1 has a magnetic susceptibility of 2.06 emu K mol⁻¹ at room temperature and contains three spins of the ferrocenium cation: two from cation A and one from cation B. The magnetic moment of the ferrocenium cation is 0.6-0.7 emu K mol⁻¹, which is larger than the spin-only value because of orbital contributions.⁶ Hence, the total magnetic moment of the cations in 1 is expected to be 1.8–2.1 emu K mol $^{-1}$; this corresponds with the observed value. The contributions of the anion spins are small because of strong antiferromagnetic interactions in the column.^{9,10a} The gradual decrease of the magnetic moment down to about 30 K is ascribed to loss of the orbital contributions; the magnetic moment at this temperature is close to the spin-only value of $3 \times 0.375 = 1.13$ emu K mol⁻¹. This temperature-dependent loss of the orbital contribution in biferrocenium salts is exceptional^{5d,6} and likely results from the electronic effects of sulfur.¹³ The susceptibility suddenly decreases at 5 K, which is probably ascribed to singlet formation in the dication (cation A). These magnetic behaviors are consistent with the valence state of the salt.

In summary, we discovered an organometallic compound that contains Fe^{3+} and $Fe^{2.5+}$ and exhibits a magnetite-like mixed-valence state of the iron ions. Intramolecular charge separation to Fe^{3+} and $Fe^{2.5+}$ has been observed in a few trinuclear mixed-valence complexes at low temperatures;¹⁴ however, the present example involves intermolecular charge separation, which originates from the different local electronic interactions around each cation. This phenomenon is interesting from the perspective of the recent interest in charge separation in molecular charge-transfer

salts.¹⁵ A somewhat related phenomenon is the inclusion of neutral ferrocene in $[Fe(C_5H_5)_2]_2[Ni(mnt)_2]_2 \cdot [Fe(C_5H_5)_2].^{7a}$

This work was supported financially by KAKENHI grant number 23110719. We thank Y. Funasako (Kobe University) for his help with X-ray crystallography. This work was performed using facilities at the Institute for Solid State Physics, University of Tokyo.

Notes and references

‡ 1',1'''-Bis(isopropylthio)-1,1"-biferrocene was prepared *via* the reaction of dilithioferrocene and diisopropyl disulfide in hexane (ESI[†]). The cyclic voltammogram of this molecule showed two reversible redox waves at $E_{11}^{1/2} = -0.07$ V and $E_{12}^{1/2} = 0.22$ V (*vs.* [Fe(Cp)₂]⁰⁺⁺), which are similar to those of biferrocene, *i.e.*, $E_{11}^{1/2} = -0.10$ V, $E_{12}^{1/2} = 0.24$ V. Single crystals of **1** were obtained as black plates in an ~40% yield by vapor diffusion of pentane into a dichloromethane solution of equimolar amounts of biferrocene and [Fe(C₅H₅)₂][Ni(mnt)₂]. Anal. calcd for C₇₆H₆₀S₁₆N₁₂Fe₄Ni₃: C, 44.44; H, 2.94; N, 8.18%. Found: C, 44.15; H, 3.03; N, 8.04%.

- 1 (a) J. Garcia and G. Subias, *J. Phys.: Condens. Matter*, 2004, **16**, R145–R178; (b) F. Walz, *J. Phys.: Condens. Matter*, 2002, **14**, R285–R340; (c) E. J. W. Verwey and P. W. Haayman, *Physica*, 1941, **8**, 979–987.
- 2 (a) R. S. Hargrove and W. Kündig, *Solid State Commun.*, 1970, 8, 303–308; (b) N. N. Greenwood and T. C. Gibb, *Mössbauer Spectroscopy*, Chapman and Hall, London, 1971.
- 3 (a) Mixed Valency Systems: Applications in Chemistry, Physics, and Biology, Series C, ed. K. Prassides, NATO ASI Series, Kluwer, Dordrecht, 1991, vol. 343; (b) A. Heckmann and C. Lambert, Angew. Chem., Int. Ed., 2012, 51, 326–392; (c) K. D. Demadis, C. M. Hartshorn and T. J. Meyer, Chem. Rev., 2001, 101, 2655–2685.
- 4 (a) S. Barlow and D. O'Hare, *Chem. Rev.*, 1997, **97**, 637–670; (b) H. Nishihara, *Adv. Inorg. Chem.*, 2002, **53**, 41–86.
- 5 (a) T.-Y. Dong, L.-S. Chang, G.-H. Lee and S.-M. Peng, Organometallics, 2002, 21, 4192–4200; (b) H. Sano, Hyperfine Interact., 1990, 53, 97–112; (c) D. N. Hendrickson, S. M. Oh, T.-Y. Dong, T. Kambara, M. J. Cohn and M. F. Moore, Comments Inorg. Chem., 1985, 4, 329–349; (d) T. Mochida, S. Yamazaki, S. Suzuki, S. Shimizu and H. Mori, Bull. Chem. Soc. Jpn., 2003, 76, 2321–2328.

- 6 T. Mochida, K. Takazawa, M. Takahashi, M. Takeda, Y. Nishio, M. Sato, K. Kajita, H. Mori, M. M. Matsushita and T. Sugawara, *J. Phys. Soc. Jpn.*, 2005, **74**, 2214–2216.
- 7 (a) M. W. Day, J. Qin and C. Yang, Acta Crystallogr., Sect. C: Cryst. Struct. Commun., 1998, 54, 1413–1416; (b) S. Zürcher, V. Gramlich, D. von Arx and A. Togni, Inorg. Chem., 1998, 37, 4015–4021; (c) A. E. Pullen, C. Faulmann, K. I. Pokhodnya, P. Cassoux and M. Tokumoto, Inorg. Chem., 1998, 37, 6714–6720; (d) O. Jeannin, R. Clérac and M. Fourmigué, J. Am. Chem. Soc., 2006, 128, 14649–14656; (e) T. Mochida, T. Koinuma, T. Akasaka, M. Sato, Y. Nishio, K. Kajita and H. Mori, Chem.–Eur. J., 2007, 13, 1872–1881.
- 8 Crystallographic parameters for 1 at 173 K: triclinic $P\overline{1}$, a = 10.4988(14) Å, b = 12.0318(16) Å, c = 17.227(2) Å, $\alpha = 95.436(3)^{\circ}$, $\beta = 92.971(3)^{\circ}$, $\gamma = 103.641(3)^{\circ}$, V = 2099.0(5) Å³, Z = 1, $R_1 = 0.0536$, and $wR_2 = 0.1317$. See ESI† for details. The crystal structure at 295 K was unchanged from that at 173 K.
- 9 [Ni(mnt)] in 1 is monoanionic, as evidenced by the infrared CN stretching band ($\nu_{\rm CN} = 2207 \ {\rm cm}^{-1}$) and intramolecular geometry (Ni–S bond lengths: 2.138(1)–2.153(1) Å).⁹ The intratrimer and intertrimer Ni…Ni distances are 3.94 Å and 4.35 Å, respectively. The intratrimer and intertrimer overlap integrals between the SOMOs of the anions calculated using the extended Hückel method are 4.8 $\times 10^{-3}$ and 11.4 $\times 10^{-3}$, respectively.
- 10 (a) T. Mochida, K. Takazawa, H. Matsui, M. Takahashi, M. Takeda, M. Sato, Y. Nishio, K. Kajita and H. Mori, *Inorg. Chem.*, 2005, 44, 8628–8641; (b) T. Mochida, T. Kobayashi and T. Akasaka, J. Organomet. Chem., 2013, 741–742, 72–77.
- 11 Crystallographic parameters for 2 at 173 K: triclinic $P\overline{1}$, a = 11.084(2) Å, b = 12.270(3) Å, c = 17.696(3) Å, $\alpha = 100.459(4)^{\circ}$, $\beta = 99.486(4)^{\circ}$, $\gamma = 112.620(4)^{\circ}$, V = 2110.4(7) Å³, Z = 1, $R_1 = 0.0625$, and $wR_2 = 0.1284$. The crystal structure at 295 K was unchanged from that at 173 K. The intratrimer and intertrimer Pt \cdot Pt distances are 3.77 Å and 5.68 Å, respectively. See ESI† for details.
- 12 M. Nakano, M. Sorai, P. M. Hagen and D. N. Hendrickson, *Chem. Phys. Lett.*, 1992, **196**, 486–490.
- 13 T. Mochida, Y. Funasako, E. Nagabuchi and H. Mori, unpublished.
- 14 (a) M. Manago, S. Hayami, Y. Yano, K. Inoue, R. Nakata, A. Ishida and Y. Maeda, *Bull. Chem. Soc. Jpn.*, 1999, 72, 2229–2234; (b) T. Sato, F. Ambe, K. Endo, M. Katada, H. Maeda, T. Nakamoto and H. Sano, *J. Am. Chem. Soc.*, 1996, 118, 3450–3458.
- 15 H. Seo, C. Hotta and H. Fukuyama, Chem. Rev., 2004, 104, 5005–5036.