


 Cite this: *RSC Adv.*, 2025, 15, 4970

# Utilizing red mud from industrial waste as catalysts for the hydrogenation of CO<sub>2</sub> into value added chemicals†

 Mahbuba Aktary,<sup>a</sup> Mohammed A. Sanhoob,<sup>b</sup> Atif S. Alzharani,<sup>\*ac</sup> Huda S. Alghamdi,<sup>b</sup> Afnan M. Ajeebi,<sup>b</sup> Md. Abdul Aziz<sup>b</sup> and M. Nasiruzzaman Shaikh<sup>†ab</sup>

Finding environmentally acceptable and long-lasting catalysts that can convert carbon dioxide into compounds with additional value is of great interest. Using Red Mud (RM), a waste product from the aluminum industry, as a CO<sub>2</sub> reduction agent is also a great idea, given the current environmental problems. In this research, we developed, characterized, and evaluated a series of metal-promoted (M = Na, K, Cs, Ba, Mg, and Sr) RM catalysts for CO<sub>2</sub> hydrogenation to produce olefins and CO. In the beginning, we synthesized RM that had been treated with acid and base by employing hydrochloric acid (HCl) and potassium hydroxide (KOH), and then we examined the activity of these catalysts in CO<sub>2</sub> hydrogenation. Surprisingly, when tested at 375 °C and 30 bar pressure (CO<sub>2</sub>:H<sub>2</sub> = 1:3), pure RM converted 22% CO<sub>2</sub> compared to acid-and base-treated RM, which converted 16% of CO<sub>2</sub>. Under identical reaction conditions, the 3%K-promoted RM (3%K@RM) catalyst achieved over 27% of CO<sub>2</sub> conversion activity compared to the other 3%M@RM catalysts (where M = Na, Cs, Ba, Mg, and Sr) in terms of conversion and selectivity for light olefins (C<sub>2-4</sub>=).

 Received 15th December 2024  
 Accepted 28th January 2025

DOI: 10.1039/d4ra08784d

[rsc.li/rsc-advances](https://rsc.li/rsc-advances)

## 1. Introduction

Environmental concerns that become apparent from the rising levels of CO<sub>2</sub> are mostly caused by human activities.<sup>1</sup> Numerous initiatives have been undertaken to prevent catastrophic environmental disasters due to greenhouse gas emissions, including the implementation of technologies and policies to mitigate the negative consequences of using fossil fuels.<sup>2-4</sup> Carbon capture, utilization, and storage (CCUS) technologies have become vital mitigation strategies for the sustainable development of nations.<sup>1,5</sup> Specifically, a workable solution to this urgent problem is utilizing captured CO<sub>2</sub> and converting it through photoreduction,<sup>6-8</sup> electroreduction,<sup>9-11</sup> photo-chemical,<sup>12</sup> thermo-chemical,<sup>13-15</sup> electrochemical,<sup>13,16-20</sup> or biological methods into value-added products. Among these, thermo-chemical processes are preferred for CO<sub>2</sub> conversion in many

industrial applications due to the process flexibility, scalability, and economic and environmental advantages.

In this regard, catalytic hydrogenation is one well-established thermo-chemical strategy for converting CO<sub>2</sub> to a variety of high-value-added products, including CO, CH<sub>4</sub>, methanol, dimethyl ether, olefins, *etc.* For instance, the bimetallic 40CuCe(rod) catalyst showed 36.5% to 41.1% conversion with 100% CO selectivity at 400 °C.<sup>21</sup> Al-Fatesh *et al.*, demonstrated, 2.5 wt% Ni and 2.5 wt% Co supported over ZrO<sub>2</sub>/Al<sub>2</sub>O<sub>3</sub> catalysts for CO<sub>2</sub> hydrogenation and produce 83.8% CO<sub>2</sub> converted product with 73.7% CH<sub>4</sub> selectivity.<sup>22</sup> Chuan-Shu *et al.* reported a novel method using Ni-NP catalysts to hydrogenate CO<sub>2</sub> into formic acid.<sup>23</sup> Also, numerous catalytic systems for CO<sub>2</sub> hydrogenation including Zr<sub>12</sub>-bpdc-CuCs,<sup>24</sup> Pd<sub>2</sub>Cu NPs/P25,<sup>25</sup> CoMoC<sub>x</sub>,<sup>26</sup> Cu@Na-Beta,<sup>27</sup> Au/a-TiO<sub>2</sub> (ref. 28) are developed for CO<sub>2</sub> to ethanol. However, the production of olefins from CO<sub>2</sub> is an intensive research area. Because olefins are the primary raw material used in the industrial manufacturing of plastics and polymers,<sup>29,30</sup> lubricants,<sup>31</sup> and detergents<sup>32</sup> where lower-olefins (C<sub>2</sub>=-C<sub>4</sub>=), such as ethylene, propylene, and butylene are the major component.<sup>33</sup> Specifically, ethylene (C<sub>2</sub>=) is widely employed as a precursor in the synthesis of thermoplastic oligomers or polymers.<sup>34</sup> It is also employed in the synthesis of vinyl chloride, acetate, styrene, ethylene glycol, *etc.*<sup>35,36</sup> Today, lower olefins production is the few hundreds of billions dollar of industry.<sup>37</sup> However, very few studies are dedicated to CO<sub>2</sub> to lower olefin formation.<sup>38</sup>



<sup>a</sup>Department of Materials Science and Engineering (MSE), King Fahd University of Petroleum and Minerals (KFUPM), Dhahran, Saudi Arabia

<sup>b</sup>Interdisciplinary Research Center for Hydrogen Technologies and Carbon Management (IRC-HTCM), King Fahd University of Petroleum & Minerals, Dhahran 31261, Saudi Arabia

<sup>c</sup>Interdisciplinary Research Center for Sustainable Energy Systems (IRC-SES), King Fahd University of Petroleum & Minerals, Dhahran 31261, Saudi Arabia. E-mail: mnshaikh@kfupm.edu.sa; atif@kfupm.edu.sa

 † Electronic supplementary information (ESI) available. See DOI: <https://doi.org/10.1039/d4ra08784d>


In this context, several low-cost metal-based catalysts, such as Fe<sub>2</sub>O<sub>3</sub>-CT600, Fe-Co(0.17)/K(1.0)/Al<sub>2</sub>O<sub>3</sub>, ZnZrO/SAPO-34, and Na-Fe<sub>3</sub>O<sub>4</sub>/HZSM-5, have demonstrated good CO<sub>2</sub> hydrogenation performance for the production of C<sub>2+</sub> hydrocarbons through the modified Fischer-Tropsch (FT) process.<sup>39</sup> The reverse water-gas shift (RWGS) reaction (eqn (1)) transforms CO<sub>2</sub> to more reactive CO by the endothermic reaction. Further hydrogenation of CO can produce C<sub>2+</sub> hydrocarbons followed by the reactions of eqn (2)–(4)



Also, Fe-Co-K/Al<sub>2</sub>O<sub>3</sub>-400 catalysts showed 49% CO<sub>2</sub> conversion and 37% olefins selectivity at 340 °C.<sup>40</sup> The addition of Zr with K-Fe catalyst enhanced conversion (>54%) as well as olefins selectivity (>53%) at 320 °C and 2 MPa.<sup>41</sup> Researchers fabricated a bulk Fe catalyst with a large surface area that is promoted by K and activated during the hydrogenation of CO<sub>2</sub> to C<sub>2</sub>-C<sub>4</sub> olefins without the requirement for extra heteroatoms or structural stabilizers at 5 bar pressure and 300 °C. The catalysts K-FeX (X = 15, 30, 60) powdered catalyst have more activity than materials based on commercial composition, phase and structure of Fe<sub>3</sub>O<sub>4</sub> and α-Fe<sub>2</sub>O<sub>3</sub>.<sup>38</sup> The K-Fe15 catalyst achieved a CO<sub>2</sub> conversion of approximately 38% at steady-state conditions whereas the selectivity to C<sub>2</sub>-C<sub>4</sub> olefins reached about 40%.<sup>42</sup> Additionally, a moderate chain growth probability and low secondary hydrogenation of olefins contribute to the high selectivity towards these olefins. A recent study found that the K-Fe-Al-O catalyst (prepared by electrospinning method) improved CO<sub>2</sub> conversion by 48% and selectivity to C<sub>2</sub>-C<sub>5</sub> light olefins by 52%.<sup>43</sup>

Transformation of CO<sub>2</sub> focuses on direct hydrogenation of CO<sub>2</sub> to lower olefins for a while. Some research on the mixed catalyst consisting of the ZnZrO solid solution and Zn-modified SAPO-34 zeolite mentioned this heterogeneous mixture allows for selective conversion of CO<sub>2</sub> into short-chain olefins instead of alkanes and selectivity to form these compounds is close to 80–90%.<sup>44</sup>

The catalyst support has played a major role in the metal-support interaction and is essential in spreading the active metal.<sup>45</sup> Catalytic activity varies, for example, whether the active metal is uniformly immobilized on its surface chemical states and exposed crystal facet.<sup>46</sup> Metal oxides,<sup>45,47,48</sup> clays,<sup>49,50</sup> zeolites,<sup>51–54</sup> activated carbon,<sup>55–58</sup> porous silica,<sup>59–62</sup> and MOFs,<sup>63–67</sup> have all been used as supports for CO<sub>2</sub> hydrogenations. Because of their chemical, mechanical, and thermal stabilities, inorganic metal oxides are more advantageous than the others.

Recently, RM has attracted a lot of attention due to its toxic nature and, most importantly, abundant byproducts, generating hundreds of thousands of tons every year from the

aluminum industry. Eliminating it from the earth's surface is an urgent priority.<sup>68</sup> It primarily consists of a diverse mixture of metal oxides and hydroxides of iron, aluminum, titanium, silicon, and calcium in the form of very fine particles <10 μm.<sup>69</sup> Although the actual composition varies globally, it is generalized as a mixture of metal oxides. However, the potential of red mud (RM) is less explored as catalyst as well as support for CO<sub>2</sub> hydrogenation reaction. All the active components, such as Fe<sub>2</sub>O<sub>3</sub>, Fe<sub>3</sub>O<sub>4</sub> etc., are required to activate the CO<sub>2</sub> molecules and then transform them into high-value chemicals, such as lower olefins (C<sub>2</sub>=-C<sub>4</sub>=). Therefore, a combination of RM and a suitable promoter could be the best choice as a catalyst for CO<sub>2</sub> conversion in terms of economics with enhanced environmental credentials.

In this study, bifunctional catalysts were developed for CO<sub>2</sub> hydrogenation to lower olefins by inhibiting the production of CH<sub>4</sub>, using a series of alkali and alkaline earth metal-promoted RM obtained from MA'ADEN, Saudi Arabia. We also intended to study the impact of monovalent (Na<sup>+</sup> from NaCl, K<sup>+</sup> from KNO<sub>3</sub>, and Cs<sup>+</sup> from CsOH) and divalent metal cations (Mg<sup>2+</sup> from MgO, Ba<sup>2+</sup> from BaO, and Sr<sup>2+</sup> from SrCl<sub>2</sub>) on the production of olefins through CO<sub>2</sub> hydrogenation reactions. The methodology we have adopted involves only two key processes: mixing and calcination. Both of these are well-established, efficient, and cost-effective operations commonly used in industry, making them highly favorable for large-scale implementation. Since these steps do not require complex equipment or conditions, the use of Red Mud in this process is not only technically feasible but also economically viable.

## 2. Experimental


### 2.1 Reagents and chemicals

In this study, the following materials and chemicals are used without further purification:<sup>1</sup> raw red mud (RM) from MA'ADEN Bauxite and Alumina Company (MBAC) of Saudi Arabia,<sup>2</sup> deionized water (DI-H<sub>2</sub>O),<sup>3</sup> different metal salts including sodium chloride (NaCl, Sigma Aldrich), potassium nitrate (KNO<sub>3</sub>), cesium hydroxide (CsOH), magnesium oxide (MgO), barium oxide (BaO), and strontium chloride (SrCl<sub>2</sub>),<sup>4</sup> potassium hydroxide (KOH),<sup>5</sup> hydrochloric acid (HCl).

### 2.2 Catalyst preparation

A schematic diagram for the steps involved in preparing the RM and K@RM catalyst is shown in Scheme 1. The raw RM was dried in an oven at 80 °C, grinded using mortar and pestle, and then sieved to a size of <200 μm. The powdered material was calcined at 500 °C for 5 hours and then divided into two portions. One was produced *via* acid treatment and the second by base treatment. The first one was produced by adding HCl (10 mL) to a well-dispersed suspension of the calcined RM catalyst (3 g) in deionized water (DI-H<sub>2</sub>O) (50 mL) and continued stirring (250 rpm) overnight. The product of RM catalyst was then filtered, washed with DI-H<sub>2</sub>O, and dried in the oven at 80 °C overnight. The acid-treated sample was named HCl-treated RM. The second treated sample was modified using potassium





Scheme 1 Steps of RM-based catalyst preparation.

hydroxide. The sample was prepared by solid mixing method using mortar and pestle which was grinded for 30 minutes. The base-treated sample was named KOH treated RM.

**2.2.1 Preparation of K@RM catalysts.** A series of alkali and alkaline earth metal promoters, such as Na, K, Mg, Ba, Cs, and Sr each 3 wt% were mixed and grinded using mortar and pestle with the calcined RM catalyst for 30 minutes. The resulting solid mixtures were again calcined at 500 °C with a temperature gradient of 3 °C min<sup>-1</sup> with a holding time of 5 h. The catalysts are denoted as 3 wt%M@RM (where M = Na, K, Mg, Ba, Cs, and Sr). Thereafter, another series was produced by varying the concentration of KNO<sub>3</sub> to produce samples containing different concentrations of K. The selected concentrations were 1, 2, 3, and 5 wt%. The samples were prepared using the same procedure as described above, and the catalysts were marked as 1 wt%K@RM, 2 wt%K@RM, 3 wt%K@RM, and 5 wt%K@RM.

## 2.3 Analytical techniques

**2.3.1 Catalytic physiochemical properties.** X-ray diffraction (XRD) of RM and metal-promoted RM catalysts was performed using Cu-K<sub>α</sub> radiation with an instrument called Rigaku Ultima-IV diffractometer (at 40 kV and 25 mA). The XRD scan covered a range from 5 to 70° (2θ) with a step size of 0.02° at a scanning speed of 2° min<sup>-1</sup>. Fourier transform infrared spectroscopy (FTIR) is a fingerprint technique to identify the surface functional group of the catalysts. Materials' response to infrared irradiation causes stretching and vibration in particular bonds. The existing bonds were analyzed using FTIR (FTIR Thermo Scientific, Nicolet 700,

USA). KBr was employed with the catalysts as the IR transparent window material for FTIR analysis. The IR transmission spectra were collected for the wavenumber range of 500 to 4000 cm<sup>-1</sup>.

Using Quantachrome Instruments (version 6.0), the N<sub>2</sub> adsorption-desorption isotherm was used to calculate the Brunauer-Emmett-Teller (BET) to evaluate the catalytic surface area, and the pore volume. The Non-linear Density Functional Theory (NLDFT) equilibrium model is used to calculate the micropore volume. The degassing of the sample should be performed at a temperature of 150 °C for 12 hours. Raman spectroscopy was used to analyze and measure the catalyst's surface before the reaction. A 455 nm DXR laser and a Thermo Scientific DXR Raman spectroscope were used to record the Raman spectra. Temperature-programmed-reduction (H<sub>2</sub>-TPR, BELCAT II from MacrotracBEL) method was used to observe the reduction capability of catalysts by H<sub>2</sub>. H<sub>2</sub>-TPR was carried out by placing 50 mg of catalysts in a reactor tube and preheating it at 500 °C for 30 minutes with argon flow (50 mL min<sup>-1</sup>). After cooling down to 50 °C, a mixture of H<sub>2</sub> and Ar gas (containing 10% of H<sub>2</sub> with a flow rate 5 mL min<sup>-1</sup> and 90% Ar with a flow rate 50 mL min<sup>-1</sup>) was introduced into the reactor tube. The sample was then heated to 900 °C at a rate of 10 °C min<sup>-1</sup> while the TCD signal was captured concurrently.

**2.3.2 Catalytic structure and morphology.** Investigations were carried out using Field Electron Emission-Scanning Electron Microscope (FE-SEM, Lyra3, Tescan, Czech Republic) with 20 kV operating voltage for visual observation of particle size and surface morphology of the catalysts. The SEM samples were prepared by pipetting the ethanolic sample onto alumina stubs



and then Au-coated the stubs using an automated Au-coater (Quorum, Q150T E). EDS-spectra, Elemental analysis, and mapping were carried out using an SEM Lyra 3 accessory. High-resolution Transmission Electron Microscopy (HRTEM) (JEM2100F from JEOL) was used to identify the size and shape of each element present in the catalysts. The structural characterizations such as crystallinity, and planner orientations of different metals, were studied with the use of the HRTEM model operating at 200 kV as an accelerating voltage. The ethanolic suspension containing the catalyst was poured onto the copper grid that was placed at room temperature.

#### 2.4 Catalytic activity evaluation

The RM catalysts with different promoters were tested for CO<sub>2</sub> hydrogenation inside a fixed bed reactor (PID Microactivity-Effi reactor). Each time, 0.20 g of the catalyst was placed inside SS316 tube with an inner diameter of 9.11 mm in a particular location of the 300 mm long tube. The catalyst sample was heated at 500 °C for 50 min with 20 mL per min N<sub>2</sub> gas to eliminate moisture as moisture increases the reaction barrier for CO<sub>2</sub>. The catalysts were reduced in the presence of H<sub>2</sub> gas (3 mL min<sup>-1</sup>) for 30 min. The sample was cooled to 150 °C. Then, the reactor tube was pressurized to 30 bar with a CO<sub>2</sub>/H<sub>2</sub> molar ratio of 1 : 3 and then heated to the reaction temperature of 375 °C. The required activation energy for the catalyst, which has a strong drive for the creation of hydrocarbons, was guaranteed by this reaction temperature. Catalyst deterioration and unwanted side reactions can result from extremely high temperatures. The pressure of 30 bar that we chose was in line with the working limitations of our experimental apparatus and was based on best practices in CO<sub>2</sub> hydrogenation investigations.<sup>70</sup> To provide a sufficient supply of hydrogen for the process while preventing excessive H<sub>2</sub>, a CO<sub>2</sub> : H<sub>2</sub> ratio of 1 : 3 was used. Additionally, this ratio shows a compromise between the stoichiometric needs for olefin synthesis and industrial viability. The catalytic evaluation was investigated at gas hourly space velocity (GHSV) of 4500 mL g<sup>-1</sup> h<sup>-1</sup>. The evaluation of catalysts was conducted using an online gas chromatography system (Shimadzu, GC-2014) equipped with two flammable ionization detectors (FIDs) and a thermal conductivity detector (TCD). The first FID tracked anticipated hydrocarbons, and aromatics, while the second FID monitored oxygenates and acidic products. The TCD detector was responsible for monitoring permanent gases and catalytic conversions. Eqn (5)–(7) reported by Peng Gao *et al.* were used to determine CO<sub>2</sub> conversion and hydrocarbon selectivity on a carbon atom basis.<sup>71</sup>

$$\text{Conv. of CO}_2 = \frac{\text{CO}_{2 \text{ inlet}} - \text{CO}_{2 \text{ outlet}}}{\text{CO}_{2 \text{ inlet}}} \times 100\% \quad (5)$$

$$\text{Sel. of CO} = \frac{\text{CO}_{\text{outlet}}}{\text{CO}_{2 \text{ inlet}} - \text{CO}_{2 \text{ outlet}}} \times 100\% \quad (6)$$

$$\text{Sel. of } C_nH_m = \frac{nC_nH_m}{\text{CO}_{2 \text{ inlet}} - \text{CO}_{2 \text{ outlet}} - \text{CO}_{\text{inlet}}} \times 100\% \quad (7)$$

where  $C_nH_m$  indicates moles of hydrocarbon created by outlet reaction with  $n$  carbons. CO<sub>2</sub> intake and outflow indicate moles of CO<sub>2</sub>. CO outlet displays moles of CO.

## 3. Results and discussion

### 3.1 Characterization of the RM-supported catalysts

**3.1.1 Synthesis of catalysts.** In one of the samples, red mud was treated with hydrochloric acid, and its subsequent calcination was performed to enhance the physicochemical properties that directly affected its catalytic activity. In another sample, red mud was modified using potassium hydroxide solution. The catalytic performance was compared with the untreated red mud (RM) catalyst. Generally, the major components of RM and the treated samples are Si, Fe, Al, Na, Ti, and Ca, and their elemental quantifications were measured using the XRF and EDS studies. It revealed that calcium and sodium contents decreased significantly in the acid-treated samples, leading to the generation of RM structure. Also, the loss of these certain elements can be explained by the higher dissolution of alkali and alkaline earth metal ions in an acidic solution.<sup>72</sup> On the other hand, the KOH-treated red mud showed an increase in the concentration of potassium due to the addition of 3 wt% of K. The other elemental compositions were maintained, indicating that the KOH solution maintained the main elemental composition of the raw red mud with addition of K only.

**3.1.2 Characterization of catalysts.** The crystallinity and composition of pure RM and metal-promoted RM were examined using X-ray diffraction (XRD) technique, and the results are shown Fig. 1. The XRD pattern for RM reveals the existence of the primary mineral phases in the RM as Fe<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>, and TiO<sub>2</sub>.<sup>72–74</sup> The main crystalline phases of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> (hematite, JCPDS card number 89-0596, JCPDS card number 33-0664, JCPDS card number 85-098), AlO(OH) (boehmite: JCPDS card number 17-0940), Al(OH)<sub>3</sub> (gibbsite, JCPDS card number 33-0018, JCPDS card number 83-2256), FeO(OH) (lepidocrocite: JCPDS card number 74-187), CaCO<sub>3</sub> (calcite: JCPDS card number 01-086-2343), sodalite (JCPDS card number 00-037-0196) and TiO<sub>2</sub> (anatase titania, JCPDS card number 21-1272) were detected in XRD as shown in Fig. 1a. For instance, calcium carbonate as calcite (CaCO<sub>3</sub>) is observed with the appearance of diffraction peaks at  $2\theta = 26, 27, 28, 48$  and  $59^\circ$ . Similarly, the presence of Fe<sub>2</sub>O<sub>3</sub> has diffraction peaks at  $2\theta = 34, 36, 42, 49.5, 54$  and  $63^\circ$ .<sup>75</sup> The effect of K loading on XRD is also investigated. When the K content is increased from 1 to 5%, it is observed that the reflections related to all metal planes decreased, as depicted in Fig. 1a.

The peak at  $19^\circ$  for Al in RM has shown a little shift to the right with the increase of K loading which was observed as a maximum shift by  $0.3^\circ$  for the addition of 5%K in RM (Fig. 1a). This was due to the crystal lattice strain or lattice deformation resulting in smaller grain size, as evidenced in HRTEM the 5% K@RM (Fig. 5). However, the excess amount of K (5%K@RM) incorporates higher basicity, which breaks down larger crystals as supported by TEM data.<sup>76</sup>

Then, different metal ions (3%) (X= Na, Mg, Cs, Ba, and Sr) in addition to the K are loaded into the RM, and its XRD






Fig. 1 XRD of (a) pure RM and different percent K-promoted RM, (b) pure RM and 3 wt% different metal-promoted RM, (c) pure RM and 3%K@RM, KOH-treated RM (KOH-RM), and HCl-treated RM (HCl-RM).

signatures were evaluated, and the results are shown in Fig. 1b. The diffraction peaks of each individual metal ions were detected in XRD as shown in Fig. 1b. In Fig. 1c, the addition of KOH by wet method has showed the presence of many more microcrystalline structures in the catalyst. The XRD data that appeared for KOH-treated RM has many new reflection peaks (from  $2\theta = 20$  to  $2\theta = 46^\circ$ , shaded regions). These peaks were generated from different planes of the corresponding metal compounds (that were absent in RM). HCl-treated RM has mainly bigger ions as smaller ions were washed away such as Na, Al, and other composite materials  $\text{Na}_5\text{Al}_3\text{CSi}_3\text{O}_{15}$ . From the XRD data of HCl-treated RM (Fig. 1c), the diminished intensity of  $\text{Na}_5\text{Al}_3\text{CSi}_3\text{O}_{15}$ ,  $\text{CaCO}_3$ ,  $\text{Fe}_2\text{O}_3$ ,  $\text{FeO}(\text{OH})$ ,  $\text{Al}(\text{OH})_3$  established the proof of this hypothesis.

FTIR spectra of pure RM and K-promoted RM with comparable transmission bands are presented in Fig. 2(a and b) and the dominant bands are listed in Table 1. No noticeable change in the absorption band is observed when the concentration of K is increased from 1 to 5% (Fig. 2a). However, a broad peak at

$3433\text{ cm}^{-1}$  appeared in the stretching vibration of  $-\text{OH}$  groups due to adsorbed water molecules in the surface or the envelope formed by hydrogen-bonded surface  $-\text{OH}$  groups, when the data is compared with pure RM and 3%K@RM in Fig. 2b.<sup>77</sup> The bands at  $555\text{--}565\text{ cm}^{-1}$  were assigned to the Fe–O stretching vibration arising from the hematite present in the RM. Also, a prominent peak at  $1435\text{ cm}^{-1}$  appears due to  $\text{CaCO}_3$  formed after calcination of RM at  $500^\circ\text{C}$ .

Additionally, the peak at  $1113\text{ cm}^{-1}$  suggests asymmetric stretching of Si–O–Al framework in cancrinite and hibschite, as well as O–Fe–O in goethite. Furthermore, the peak at  $986\text{ cm}^{-1}$  signifies Si–O–Si(Al) bonds, corresponding to the anti-symmetric stretching vibrations ( $\nu_3$ ) in  $\text{SiO}_4$  tetrahedra of  $\text{Ca}_2\text{SiO}_4$ . The peaks at 563 and below  $500\text{ cm}^{-1}$  in RM are attributed to the stretching vibration of Fe–O, some minor peaks at the range of  $612\text{--}695\text{ cm}^{-1}$  correspond to Al–O band, which are predominant in 3% and 5%K promoted RM (Fig. 2a).<sup>77</sup> This may be due to the phase changes during the activation process.






Fig. 2 FT-IR data of (a) K-promoted RM, (b) pure RM vs. 3wt% K-promoted RM (c) Raman spectroscopy of K-promoted RM.

The presence of metal-oxides is further supplemented by Raman spectroscopy and the results are shown in Fig. 2c. The distinct Raman peaks at specific wavelengths in the analysis represent various metal oxides in RM. For example, five prominent peaks at 145, 211, 275, and 620  $\text{cm}^{-1}$ , are associated with hematite ( $\text{Fe}_2\text{O}_3$ ), which is one of the major components in RM. Additionally, the peaks at 145, 280, 400, and 508  $\text{cm}^{-1}$  could be attributed to the presence of anatase ( $\text{TiO}_2$ ), calcium carbonate ( $\text{CaCO}_3$ ), alumina ( $\text{Al}_2\text{O}_3$ ), and quartz ( $\text{SiO}_2$ ), respectively.<sup>78–81</sup> Also, the presence of  $\text{Fe}_2\text{O}_3$  is more noticeable when 3% K was added to RM.

Table 1 The main phases present in RM calcined at 500 °C for 5 h determined by FT-IR measurement

Wavenumbers ( $\text{cm}^{-1}$ )	Phases
3433	OH group, H-bond
1640	$\text{H}_2\text{O}$ in cancrinite
1435	$\text{CaCO}_3$
1113	$\text{FeO}(\text{OH})$
986	$\text{Ca}_2\text{SiO}_4$ , Si–O–Si(Al)
612–695	Al–O
563	$\text{Fe}_2\text{O}_3$

A scanning electron microscope (SEM) imaging study is performed to investigate the surface morphology of the pure RM and alkali and alkaline earth metal-promoted RM catalysts. As depicted in Fig. 3, the heterogeneous internal structure of RM is confirmed by the SEM imaging of pure RM, which is constituted by different sizes of particles and crystals with various shapes and morphology ranging from nanometer to a few microns sizes formed by agglomeration (Fig. 3). The higher agglomeration of particles was observed with the KOH-treated samples, thereby decreasing the surface area and leading to the loss of active sites.

It is noticeable in SEM that the monovalent Na, K, and Cs metal-promoted RM contributed to an increase in the particle size than in di-valent Mg, Ba, and Sr metal-promoted RM with the fixed concentration of metal ions (3%) (Fig. 3a–i). Also, no significant effect in morphology is noted when the K content is increased from 1 to 3% (Fig. 3j–l). However, a higher amount of K (5%) in RM undoubtedly promotes further agglomeration, diminishing catalytic activity. X-ray dispersive spectroscopy (EDS) attached to SEM confirms the presence of constituent elements in the RM, its promoter metal elements, and their distribution. The detailed composition and contents of Si, Fe, Al, Na, Ti, and Ca of RM and other catalysts were found by EDS






Fig. 3 SEM image of pure RM, KOH- and HCl-treated RM, and different metal-promoted and different wt% K-promoted RM.


mapping data and from XRF normalized wt% (ESI, Fig. S1, S2, and Table S1†).

The transmission electron microscopy (TEM) images are depicted in Fig. 4. The particles present in the RM and RM-based catalysts exhibit diverse sizes and shapes with different crystal planner orientations due to the presence of different metal nanocrystals. KOH-treated RM showed irregularly shaped smaller particles, while HCl-treated RM exposed longer arrays of crystal planes, which resulted in TiO<sub>2</sub> rod-like structures.<sup>82</sup> The introduction of K and other metals had an impact on the grain size and crystallinity of the constituent materials (ESI†). Pure RM crystallinity was enhanced by a slight addition of K. This trend leveled off to 3 wt% of K. However, the higher amount of K (5%) in RM starts to break the long-range order of the lattice. This claim has been justified by the XRD peak analysis presented in Fig. 1c. It caused smaller grains and a large amount of grain boundary. However, it did not bring significant changes in the morphology of the particles. Upon examination, it was noted that K-promoted RM resulted in the formation of particles with pores and rod-like structures, attributed to the contribution of quartz and rutile<sup>82</sup> in RM. The unidirectional crystal growth, which gives the tubular shape, comes from the combined effect of Al substitution on hematite.<sup>83</sup> The effect of Na, Cs, Mg, and Sr on RM particle shape and size has shown

a similar effect. However, 3%Ba@RM has produced bigger cubic particles due to the cubic nature of BaO.

HRTEM picture has shown slip dislocation, or planar defect on the structure (Fig. 5). HRTEM of 3%K@RM revealed the clear and bright surface of the particle. As mentioned earlier, RM is a complex mixture of different metal oxides, HRTEM image clearly established the presence of Al<sub>2</sub>O<sub>3</sub> with  $d_{(110)}$  = spacing 0.24 nm,<sup>84</sup> hematite Fe<sub>2</sub>O<sub>3</sub> with  $d_{(311)}$  = 0.25 nm.<sup>85</sup> Also, the presence of hexagonal anatase TiO<sub>2</sub> nanoparticles with  $d_{(101)}$  = 0.35 nm (ref. 82) and rutile phase TiO<sub>2</sub> nanorods with  $d_{(110)}$  = 0.33 nm<sup>82</sup> is confirmed by the matching of inter-planar distance ( $d$ ).

The hydrogen consumption-ability of pure and modified RM samples was assessed using temperature-programmed reducibility studies (H<sub>2</sub>-TPR) and spectra, as shown in Fig. 6a. It demonstrated the well-defined reduction peak at 502 °C for the pure RM. Generally, hematite ( $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>) is reduced by H<sub>2</sub> in the range of 220 to 680 °C,<sup>86</sup> while magnetite reduces in the range of 600 to 800 °C.<sup>87</sup> The other metals available in the RM sample such as sodium, potassium, magnesium, calcium, and titanium are also reduced in the range of 250 to 850 °C, which concludes that the broad peak is composed of overlapping of a series of peaks of each constituent element. However, modifying the RM sample with different concentrations of potassium led to a reduction in H<sub>2</sub> consumption, as shown in Fig. 6a. It was






Fig. 4 TEM image of pure RM and different metal-promoted RM.

observed that the total  $\text{H}_2$  consumption for the parent RM catalyst was  $502 \mu\text{mol g}^{-1}$  at temperatures ranging between 200 to  $850^\circ\text{C}$ . Moreover, as the concentration of the K increased to 5 wt%, a reduction in  $\text{H}_2$  consumption ( $502$  to  $423 \mu\text{mol g}^{-1}$ ) was observed. Additionally, it was observed that the first peak, centered around  $600^\circ\text{C}$ , shifted to a lower temperature as the concentration of K increased in the sample. On the other hand, the second peak located after  $800^\circ\text{C}$  was shifted toward higher temperatures, which confirms the contribution of K in changing the elemental phase of the RM.

Fig. 6b illustrates the textural properties of the pure RM and 3% alkali or alkaline earth metal-loaded RM catalysts. In the curve of RM, it is evident that the adsorption and desorption curves diverged when the relative pressure was increased. A substantial hysteresis loop was observed between relative pressures of  $>0$  and 1.0, indicating the presence of huge mesoporosity in the prepared catalysts. According to IUPAC isotherm data, type IV suggests the presence of numerous mesopores and macropores in RM with monolayer and multilayer adsorption.<sup>88</sup> In contrast, the 3%K@RM hysteresis loop demonstrated a significant decrease in adsorption capacity. When the relative pressure was below 0.2, the adsorption and desorption curves were nearly superimposed, indicating the existence of micropores. Noticeably, BET surface area decreased gradually from  $20 \text{ m}^2 \text{ g}^{-1}$  to  $11.2 \text{ m}^2 \text{ g}^{-1}$  as the K loading

increased to 5%. The adsorption of gas was probably facilitated in RM instead of K loaded RM (Table 2).

### 3.2 Catalytic evaluation

The catalytic performance for  $\text{CO}_2$  hydrogenation process was performed in a fixed bed reactor with gas hourly space velocity (GHSV) of  $4500 \text{ mL g}^{-1} \text{ h}^{-1}$ . The catalytic process was performed at  $375^\circ\text{C}$  and 30 bar using  $\text{CO}_2 : \text{H}_2$  mixture (1 : 3). As shown in Fig. 7a, the catalytic conversion of  $\text{CO}_2$  hydrogenation over pure RM promoted with different wt% of potassium was presented after 6 hours of reaction on stream. The conversion was found to have variation in catalytic activities. With pure RM acting as a control catalyst, 22% of  $\text{CO}_2$  conversion was accomplished. However, treating the pure Red Mud catalysts with HCl resulted in the reduction of the catalytic conversion to 16%, due to the role of acid in removing some of the elements such as aluminum from the catalytic structure and, consequently, a chance for enhancing the presence of oxygen vacancies required for the reduction of  $\text{CO}_2$  to CO, but with less catalytic activity due to the limitation of metal active sites. By this treatment, it is proved that  $\text{CO}_2$  hydrogenation process requires large metal active sites as well as oxygen vacancies for the process of reverse-water gas shift reaction. Similarly, treating the RM catalyst with 3% potassium driven from potassium hydroxide source led to a reduction of the catalytic conversion






Fig. 5 (a and b) TEM, (c) HRTEM and SAED image(inserted) of 3 wt%K-promoted red mud.




Fig. 6 (a) H<sub>2</sub>-TPR profile, (b) N<sub>2</sub> adsorption–desorption isotherms of RM and K-promoted RM samples.

to around 16% due to the role of potassium hydroxide in disturbing the crystallinity structure of silicon atoms within the catalyst bed. Although the catalytic conversion dropped in these two samples from 22 to 16%, the catalytic selectivity toward CO

was enhanced by acid treatment and the catalytic selectivity for CO increased from 91% to 97%. On the other hand, selectivity dropped significantly from 91% to 64% by base treatment. The aforementioned data suggest that acid and base have a significant role in influencing both the metallic composition of the catalyst and the existence of oxygen vacancies, which are necessary for the conversion of CO<sub>2</sub> to CO. Furthermore, acid and base treatment also had an impact on selectivity toward hydrocarbons. It was observed that the acid treatment led to a reduction in hydrocarbons from 9 to 3%, while base treatment led to an increase in the catalytic selectivity toward hydrocarbons from 9 to 36%, indicating that the base-treated RM catalyst has enhanced the modified Fischer–Tropsch (FT) process. On the other hand, the selectivity of light olefins with the produced hydrocarbons was also affected by acid and base

Table 2 Pore volume and surface area of pure RM and different percent K-promoted RM obtained from BET measurement

Sample	Pore volume (cc g <sup>-1</sup> )	Surface area (m <sup>2</sup> g <sup>-1</sup> )
RM	0.029	20.36
1%K@RM	0.026	14.19
3%K@RM	0.023	15.26
5%K@RM	0.019	11.2






Fig. 7 CO<sub>2</sub> conversion and olefins selectivity data of (a) pure RM and different wt% K-promoted RM (b) 3wt% different metal-promoted RM.


**Table 3** The catalytic performance data for RM and RM-based catalysts for CO<sub>2</sub> conversion, CO, hydrocarbon, olefin, and CH<sub>4</sub> selectivity<sup>a</sup>

Sample	CO <sub>2</sub> conversion	CO	Hydrocarbon	C <sub>2=4</sub>	CH <sub>4</sub>
RM	22	91	9	7	75
HCl treated RM	16	97	3	12	83
3%KOH@RM	16	64	36	1	92
1%K@RM	21	96	4	8	72
2%K@RM	21	95	5	11	70
3%K@RM	27	94	6	28	54
5%K@RM	27	93	7	21	53
3%Na@RM	26	92	8	3	82
3%Cs@RM	27	93	7	5	77
3%Ba@RM	26	91	9	3	80
3%Mg@RM	25	95	5	6	77
3%Sr@RM	25	90	10	3	84

<sup>a</sup> The converted CO<sub>2</sub> was produced as CO hydrocarbons. The main products of those hydrocarbons were olefins and CH<sub>4</sub>.

treatment. It was observed that the selectivity toward light olefins increased from 7 to 12% by acid treatment, while it decreased from 9% to 1% by base treatment. All the catalytic performance data has been summarized in Table 3 and comparative performance with conventional catalyst is presented in Table 4.

The higher olefins selectivity for HCl-treated RM and their subsequent DI-water washing may cause the removal of smaller metal cations from RM as shown in eqn (8) and enhanced the crystallinity of larger cations (as shown in HRTEM), which boosted the active sites of RM needed for the CO<sub>2</sub> hydrogenation for olefins selectivity.



Heavy elements Sr and Ba favored methanation, but lighter elements Mg enhanced CO selectivity.<sup>89</sup> At the same time, Mg



Table 4 A comparative catalytic performance data table for conventional state of art catalysts and RM-based catalysts<sup>a</sup>

Promoter	Catalyst support	Synthesis method	Conditions	Performance	Ref.
16.5% K and Ba	1% Rh/Al <sub>2</sub> O <sub>3</sub>	Flame spray pyrolysis	GHSV = 6000 h <sup>-1</sup> , H <sub>2</sub> /CO <sub>2</sub> = 4/1	X <sub>CO<sub>2</sub></sub> = 25%, S <sub>CH<sub>4</sub></sub> = 0% at 375 °C (16.5% K on 1% Rh/Al <sub>2</sub> O <sub>3</sub> )	96
2% Pt	CeO <sub>2</sub>	Wet method	WHSV, 300 L g <sup>-1</sup> h <sup>-1</sup>	X <sub>CO<sub>2</sub></sub> = 21.7%, S <sub>CO</sub> = 100% at 290 °C	97
Au@UIO-67	MOF		GHSV = 12 000 mL h <sup>-1</sup> g <sub>cat</sub> <sup>-1</sup> , CO <sub>2</sub> /H <sub>2</sub> = 1 : 3, 2.0 Pa		98
Ni	Ce-Zr-O	Co-precipitation	GHSV = 6000 mL h <sup>-1</sup> g <sub>cat</sub> <sup>-1</sup> , CO <sub>2</sub> /H <sub>2</sub> = 1 : 1, 1.0 MPa	X <sub>CO<sub>2</sub></sub> = 34%, SCO = 19.7% at 550 °C	99
2%K	30%Fe <sub>3</sub> O <sub>4</sub> /ZrO <sub>2</sub>	Dry mixing	GHSV = 15 000 mL h <sup>-1</sup> g <sub>cat</sub> <sup>-1</sup> , CO <sub>2</sub> /H <sub>2</sub> = 1 : 4, 0.1 MPa	X <sub>CO<sub>2</sub></sub> = 22%, SCO = 77%, S <sub>CH<sub>4</sub></sub> = 49%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 35%, at 375 °C	100
K	Red mud	Wet method	GHSV = 9600 mL h <sup>-1</sup> g <sub>cat</sub> <sup>-1</sup> , CO <sub>2</sub> /H <sub>2</sub> = 1 : 3, 30 bar	X <sub>CO<sub>2</sub></sub> = 45%, SCO = 36% at 375 °C	70
3%K (from KNO <sub>3</sub> )	RM	Dry mixing	GHSV = 4500 mL h <sup>-1</sup> g <sub>cat</sub> <sup>-1</sup> , CO <sub>2</sub> /H <sub>2</sub> = 1 : 3, 30 bar	X <sub>CO<sub>2</sub></sub> = 22%, SCO = 91%, S <sub>CH<sub>4</sub></sub> = 75%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 7%, at 375 °C	This work
3% Na				X <sub>CO<sub>2</sub></sub> = 27%, SCO = 94%, S <sub>CH<sub>4</sub></sub> = 54%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 28%, at 375 °C	
3% Cs				X <sub>CO<sub>2</sub></sub> = 26%, SCO = 92%, S <sub>CH<sub>4</sub></sub> = 82%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 3%, at 375 °C	
3% Mg				X <sub>CO<sub>2</sub></sub> = 27%, SCO = 93%, S <sub>CH<sub>4</sub></sub> = 77%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 5%, at 375 °C	
3% Ba				X <sub>CO<sub>2</sub></sub> = 25%, SCO = 95%, S <sub>CH<sub>4</sub></sub> = 77%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 6%, at 375 °C	
3% Sr				X <sub>CO<sub>2</sub></sub> = 26%, SCO = 91%, S <sub>CH<sub>4</sub></sub> = 80%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 3%, at 375 °C	
				X <sub>CO<sub>2</sub></sub> = 25%, SCO = 90%, S <sub>CH<sub>4</sub></sub> = 84%, S <sub>C<sub>2</sub>-C<sub>4</sub></sub> = 3%, at 375 °C	



<sup>a</sup> X<sub>CO<sub>2</sub></sub> = CO<sub>2</sub> conversion efficiency, SCO = selectivity of CO, S<sub>CH<sub>4</sub></sub> = selectivity of CH<sub>4</sub>, and S<sub>C<sub>2</sub>-C<sub>4</sub></sub> = Selectivity of light olefins (C<sub>2</sub>-C<sub>4</sub>).

enhanced the absorption of CO<sub>2</sub> over the Mg-modified Iron based catalyst, resulting in increased methanation efficacy and highly active Fe carbides.<sup>90</sup> RM contains around 29% Fe<sub>2</sub>O<sub>3</sub>, based on Table S1†'s XRF data. For RM, the CO<sub>2</sub> conversion was 22%; for 3%Mg@RM, it was 25%. While the Na and K enhanced CO selectivity, they also increased the number of basic sites.<sup>91</sup> CO<sub>2</sub> adsorption on the surface was enhanced by larger size for monovalent cations like Cs (absorption of Cs<sup>+</sup> > Na<sup>+</sup>), which directly affects CO<sub>2</sub> conversion.<sup>92</sup> That effect is clear from our observations presented in Table 3 as well.


The effect of varied concentrations of K (1, 2, 3, and 5 wt%) sourced from KNO<sub>3</sub> was found to have a vital effect on the catalytic conversion of CO<sub>2</sub> hydrogenation at high concentrations of K as shown in Fig. 7a. Though the addition of K can modify the electronic properties of RM support in a way that enhances the catalytic activity of transition metals (e.g., Fe, Al), the addition of 1% and 2% of K as a promoter (in dry mixing method) was found to have no role in improving the catalytic conversion. The interactions facilitate K<sup>+</sup> production, which creates room for direct interactions of metal oxides present in RM. It increased the number of basic sites available on the RM surface for CO<sub>2</sub> adsorption and activation. It produced CO from CO<sub>2</sub> following the modified Fischer–Tropsch (FT) process<sup>39</sup> and the reverse water-gas shift (RWGS) reaction (eqn (9)) by the endothermic reaction. The hydrogenation of CO can yield C<sub>2+</sub> hydrocarbons, which are then subjected to the processes described in eqn (10)–(12):



Besides the above-mentioned endothermic reaction can be turned into a spontaneous exothermic reaction by K impregnation as  $\text{K} \rightarrow \text{K}^+ + \text{e}^-$ . These electrons will facilitate the production of CO as



However, further increasing K concentration from 2% to 3 and 5% led to enhancing the catalytic conversion from 22% to 27%, indicating the role of potassium in enhancing the catalytic adsorption for CO<sub>2</sub> molecules. Selectivity was found to be affected by the concentration of K. The higher loading concentration leads to the high dispersion of K<sup>+</sup> ions, which could lead to better access for CO<sub>2</sub> to interact with the K<sup>+</sup> active sites. The catalysts with an appreciable amount of Fe, tend to form iron carbide after multiple reaction steps.




According to recent research, the phase transitions of Fe<sub>2</sub>O<sub>3</sub> → Fe<sub>5</sub>C<sub>2</sub> due to catalyst activation and Fe<sub>5</sub>C<sub>2</sub> → Fe<sub>3</sub>O<sub>4</sub> due to catalyst deactivation.<sup>93</sup>

Iron carbides (Fe<sub>5</sub>C<sub>2</sub>) on the catalyst surface improved CO activation and hydrocarbon chain development, leading to enhanced conversion and selectivity to olefins (Fig. 8). The carbides were more effective in CO hydrogenation, producing the required olefins.<sup>42</sup> Hägg carbide (Fe<sub>5</sub>C<sub>2</sub>) improves CO<sub>2</sub> conversion and olefin selectivity in the K–Fe15 catalyst. This phase is very active for CO activation and creation of C<sub>2</sub>–C<sub>4</sub> olefins while reducing the generation of methane and longer-chain hydrocarbons.

It was observed that the CO selectivity has increased from 91 to 96% by increasing the potassium concentration by 1%. Further increase in K concentration was found to have a negative effect on CO selectivity, and the selectivity toward CO was reduced stepwise from 96% to 93% and hydrocarbon selectivity increased from 4 to 7% by increasing K concentration from 1 to 5%. Within hydrocarbons, the selectivity toward light olefins was enhanced from 8% to 28% by increasing K concentration from 1 to 3%. This effect is attributed to its promotion of CO<sub>2</sub> adsorption and the suppression of further hydrogenation of produced olefins, which enhances selectivity.<sup>94</sup> Beyond 3% of K, the selectivity toward light olefins starts to drop slightly from 27 to 21%, indicating the optimum concentration was obtained at 3% of K, which probably anticipated to attenuate the hydrogenation activity of Fe, consequently fostering the propensity for olefin preference formation.<sup>95</sup> This, in turn, may facilitate the re-adsorption of olefins, thereby enabling extended chain growth.

A broader scope of the effect of alkali and alkaline earth metal promoters on CO<sub>2</sub> hydrogenation is investigated under the optimized reaction condition. In this regard, a series of



### Exposed K active sites on RM Catalyst

Fig. 8 CO<sub>2</sub> adsorption by the active sites on RM for higher conversion and olefins selectivity.



alkali or alkaline earth metals, such as Na, Cs, Ba, Mg, and Sr were employed in a fixed concentration (3%) and impregnated into the RM for CO<sub>2</sub> hydrogenation. It was observed that the 3% Na loaded RM demonstrated comparable CO<sub>2</sub> conversion (26%) with a very low olefins selectivity (3%) as shown in Fig. 7b. However, the Cs promoted RM, and retained its reactivity towards CO<sub>2</sub> conversion as 3%K loaded RM. Notably, a trend in very low olefins selectivity (3–6%) was established with these alkali or alkaline earth metals with the RM.

The catalytic performance of red mud (RM) can be attributed to the synergistic roles of its key metal oxides, particularly Fe<sub>2</sub>O<sub>3</sub> and TiO<sub>2</sub>. Fe<sub>2</sub>O<sub>3</sub> plays a critical role in CO<sub>2</sub> activation through its redox properties (Fe<sup>3+</sup> ↔ Fe<sup>2+</sup>), enabling CO<sub>2</sub> adsorption and dissociation, while TiO<sub>2</sub> provides oxygen vacancies that act as additional active sites and enhances the dispersion of active phases. Together, these oxides create a unique catalytic environment that facilitates electron transfer and surface interactions essential for CO<sub>2</sub> hydrogenation. The calcination process at 500 °C improves the crystallinity and distribution of these oxides, further boosting their activity. Additionally, the inclusion of potassium as a promoter modifies the electronic properties of Fe<sub>2</sub>O<sub>3</sub> and TiO<sub>2</sub>, enhancing CO<sub>2</sub> adsorption and hydrogenation efficiency.

Some significant factors affect the interacting mechanisms for CO<sub>2</sub> hydrogenation. The catalyst preparation methods, the amount of loading of active metals, the source of support materials, and promoters including their precursor source play a vital role in this case. It is worth noting that the physical and chemical behavior of RM found in different geographical locations and other sources are different due to their different elemental composition. Besides optimal process conditions such as reaction temperature, pressure, and gas flow rate, reaction bed configuration, the relative ratio of CO<sub>2</sub> and H<sub>2</sub> mixture determines the olefin selectivity. The formation of iron carbides and its effect on catalytic inhibition and activation is also a major concern. The major challenge in the scientific community is to ensure higher CO<sub>2</sub> conversion and greater selectivity for light olefin. Furthermore, understanding the feasibility of RM to be used as catalysts in processes such as CO<sub>2</sub> hydrogenation is a smart approach to minimize the accumulation of this waste material produced due to the demands of mining and alumina production. This requires extensive studies to understand the relationship between the physicochemical properties of such kind of catalysts and reaction mechanisms. We understand from our studies that the presence of potassium over Red Mud can enhance the presence of light olefins. However, a limited amount of light olefins were obtained, which made room for us to further explore the possibilities of improving Red Mud in coming studies. Besides, to ensure higher CO<sub>2</sub> conversion with appreciable hydrocarbon product selectivity, there is a huge space for research with other metals, especially transition metals such as Fe, Co, Cu, and so on. From the extended part of our study, it was observed that iron concentration has a great influence in tuning the catalytic conversion in CO<sub>2</sub> hydrogenation and enhancing the catalytic selectivity for hydrocarbons. The investigation was observed for iron concentration ranging between 5 and 20 wt% over Red

Mud (X%Fe@3%K@RM, X = 5, 10, or 20) as shown in ESI, Fig. S4.† The main finding was that these composites can lead to higher methane selectivity in the absence of light olefins, which is not the topic of interest here. This study is still in progress to find the desired product by tunable composition of metal active sites.

Our findings might be considered as a foundation of understanding the synergic effect of metals presence in natural materials.

## 4. Conclusion

In conclusion, RM-based catalysts, when paired with appropriately selected promoter materials, demonstrate a cost-effective solution for addressing the challenges posed by CO<sub>2</sub>. A straightforward catalyst preparation technique enhances environmental sustainability by minimizing the direct exposure of RM and contributes significantly to CO<sub>2</sub> reduction efforts. RM calcined at 500 °C outperformed its HCl- and KOH-treated counterparts. Different effects on CO<sub>2</sub> hydrogenation were found when several monovalent and bivalent metal promoters were used. Among them, 3% K-promoted RM emerged as the most effective, achieving 27% CO<sub>2</sub> conversion and 28% olefin selectivity. Notably, the source of potassium played a crucial role, as 3% K in RM derived from NO<sub>3</sub><sup>-</sup> and OH<sup>-</sup> sources yielded varying outcomes. This finding highlights the potential for further research to optimize catalytic performance by exploring diverse sources of the same metal promoter. Furthermore, our research indicates that one crucial factor that may be changed to attain desired olefin yields is the weight percentage of promoters. These insights cover the way for future advancements in designing efficient catalysts for CO<sub>2</sub> hydrogenation.

## Data availability

The related data have been provided in the form of ESI.†

## Conflicts of interest

The authors declare no competing financial interests.

## Acknowledgements

The authors gratefully acknowledge the support of Saudi Aramco for funding this work through grant number ORCP2390. The authors also thank the Saudi Arabian Mining Company (MAA'DEN) for providing the red mud.

## References

- 1 L. J. R. Nunes, The Rising Threat of Atmospheric CO<sub>2</sub>: A Review on the Causes, Impacts, and Mitigation Strategies, *Environments*, 2023, **10**(4), 66.
- 2 T. Kuramochi, M. Roelfsema, A. Hsu, S. Lui, A. Weinfurter, S. Chan, *et al.*, Beyond national climate action: the impact of region, city, and business commitments on global



- greenhouse gas emissions, *Clim. Policy*, 2020, **20**(3), 275–291.
- 3 A. Brdulak, G. Chaberek and J. Jagodziński, Development Forecasts for the Zero-Emission Bus Fleet in Servicing Public Transport in Chosen EU Member Countries, *Energies*, 2020, **13**(16), 4239.
  - 4 J. M. Gilligan and M. P. Vandenbergh, A framework for assessing the impact of private climate governance, *Energy Res. Soc. Sci.*, 2020, **60**, 101400.
  - 5 Z. Xiaoping, S. Baran, W. Cel and Y. Cao, Sustainable Approach to Mitigation of CO<sub>2</sub> Emission, *Ecol. Chem. Eng. S*, 2015, **21**(4), 617–622.
  - 6 W. N. Wang, J. Soulis, Y. J. Yang and P. Biswas, Comparison of CO<sub>2</sub> Photoreduction Systems: A Review, *Aerosol Air Qual. Res.*, 2014, **14**(2), 533–549.
  - 7 Q. Zeng, T. Su, J. H. Bing, Y. Jiang, in *Photocatalytic Reduction of Carbon Dioxide*, 2015, pp. 61–98.
  - 8 Y. Gao, K. Qian, B. Xu, Z. Li, J. Zheng, S. Zhao, *et al.*, Recent advances in visible-light-driven conversion of CO<sub>2</sub> by photocatalysts into fuels or value-added chemicals, *Carbon Resour. Convers.*, 2020, **3**, 46–59.
  - 9 J. Lin, S. Yan, C. Zhang, Q. Hu and Z. Cheng, Electroreduction of CO<sub>2</sub> toward High Current Density, *Processes*, 2022, **10**(5), 826.
  - 10 W. Zhang, Y. Hu, L. Ma, G. Zhu, Y. Wang, X. Xue, *et al.*, Progress and Perspective of Electrocatalytic CO<sub>2</sub> Reduction for Renewable Carbonaceous Fuels and Chemicals, *Adv. Sci.*, 2018, **5**(1), 1700275.
  - 11 D. T. Whipple and P. J. A. Kenis, Prospects of CO<sub>2</sub> Utilization via Direct Heterogeneous Electrochemical Reduction, *J. Phys. Chem. Lett.*, 2010, **1**(24), 3451–3458.
  - 12 J. Lin, Z. Pan and X. Wang, Photochemical Reduction of CO<sub>2</sub> by Graphitic Carbon Nitride Polymers, *ACS Sustain. Chem. Eng.*, 2014, **2**(3), 353–358.
  - 13 N. Ali, M. Bilal, M. S. Nazir, A. Khan, F. Ali and H. M. N. Iqbal, Thermochemical and electrochemical aspects of carbon dioxide methanation: A sustainable approach to generate fuel via waste to energy theme, *Sci. Total Environ.*, 2020, **712**, 136482.
  - 14 K. G. Burra, P. Chandna and A. K. Gupta, Thermochemical Solutions for CO<sub>2</sub> Utilization to Fuels and Value-Added Products, *Sustainable Development for Energy, Power, and Propulsion*, 2021, pp. 59–89.
  - 15 D. S. A. Simakov, in *Thermocatalytic Conversion of CO<sub>2</sub>*, 2017, pp. 1–25.
  - 16 H. R. Jhong, S. Ma and P. J. Kenis, Electrochemical conversion of CO<sub>2</sub> to useful chemicals: current status, remaining challenges, and future opportunities, *Curr. Opin. Chem. Eng.*, 2013, **2**(2), 191–199.
  - 17 N. S. Spinner, J. A. Vega and W. E. Mustain, Recent progress in the electrochemical conversion and utilization of CO<sub>2</sub>, *Catal. Sci. Technol.*, 2012, **2**(1), 19–28.
  - 18 H. Yin, X. Mao, D. Tang, W. Xiao, L. Xing, H. Zhu, *et al.*, Capture and electrochemical conversion of CO<sub>2</sub> to value-added carbon and oxygen by molten salt electrolysis, *Energy Environ. Sci.*, 2013, **6**(5), 1538.
  - 19 D. R. Kauffman, J. Thakkar, R. Siva, C. Matranga, P. R. Ohodnicki, C. Zeng, *et al.*, Efficient Electrochemical CO<sub>2</sub> Conversion Powered by Renewable Energy, *ACS Appl. Mater. Interfaces*, 2015, **7**(28), 15626–15632.
  - 20 M. R. Gonçalves, A. Gomes, J. Condeço, R. Fernandes, T. Pardal, C. A. C. Sequeira, *et al.*, Selective electrochemical conversion of CO<sub>2</sub> to C<sub>2</sub> hydrocarbons, *Energy Convers. Manage.*, 2010, **51**(1), 30–32.
  - 21 B. Lu, Z. Zhang, X. Li, C. Luo, Y. Xu and L. Zhang, High-efficiency CuCe(rod) catalysts for CO<sub>2</sub> hydrogenation with high Cu content, *Fuel*, 2020, **276**, 118135.
  - 22 A. Al-Fatesh, S. K. Singh, G. S. Kanade, H. Atia, A. H. Fakeeha, A. A. Ibrahim, *et al.*, Rh promoted and ZrO<sub>2</sub>/Al<sub>2</sub>O<sub>3</sub> supported Ni/Co based catalysts: High activity for CO<sub>2</sub> reforming, steam-CO<sub>2</sub> reforming and oxy-CO<sub>2</sub> reforming of CH<sub>4</sub>, *Int. J. Hydrogen Energy*, 2018, **43**(27), 12069–12080.
  - 23 C. S. He, L. Gong, J. Zhang, P. P. He and Y. Mu, Highly selective hydrogenation of CO<sub>2</sub> into formic acid on a nano-Ni catalyst at ambient temperature: Process, mechanisms and catalyst stability, *J. CO<sub>2</sub> Util.*, 2017, **19**, 157–164.
  - 24 B. An, Z. Li, Y. Song, J. Zhang, L. Zeng, C. Wang, *et al.*, Cooperative copper centres in a metal-organic framework for selective conversion of CO<sub>2</sub> to ethanol, *Nat. Catal.*, 2019, **2**(8), 709–717.
  - 25 S. Bai, Q. Shao, P. Wang, Q. Dai, X. Wang and X. Huang, Highly Active and Selective Hydrogenation of CO<sub>2</sub> to Ethanol by Ordered Pd-Cu Nanoparticles, *J. Am. Chem. Soc.*, 2017, **139**(20), 6827–6830.
  - 26 H. Zhang, H. Han, L. Xiao and W. Wu, Highly Selective Synthesis of Ethanol via CO<sub>2</sub> Hydrogenation over CoMo<sub>x</sub> Catalysts, *ChemCatChem*, 2021, **13**(14), 3333–3339.
  - 27 L. Ding, T. Shi, J. Gu, Y. Cui, Z. Zhang, C. Yang, *et al.*, CO<sub>2</sub> Hydrogenation to Ethanol over Cu@Na-Beta, *Chem*, 2020, **6**(10), 2673–2689.
  - 28 D. Wang, Q. Bi, G. Yin, W. Zhao, F. Huang, X. Xie, *et al.*, Direct synthesis of ethanol via CO<sub>2</sub> hydrogenation using supported gold catalysts, *Chem. Commun.*, 2016, **52**(99), 14226–14229.
  - 29 Y. V. Kissin, Olefin Polymers, Introduction, in *Kirk-Othmer Encyclopedia of Chemical Technology*, Wiley, 2015, pp. 1–11.
  - 30 G. K. Min, K. Bjerglund, S. Kramer, T. M. Gøsgis, A. T. Lindhardt and T. Skrydstrup, Generation of Stoichiometric Ethylene and Isotopic Derivatives and Application in Transition-Metal-Catalyzed Vinylation and Enyne Metathesis, *Chem.-Eur. J.*, 2013, **19**(51), 17603–17607.
  - 31 G. A. Korneeva, YuG. Noskov, T. E. Kron, S. N. Rush, O. G. Karchevskaya and D. V. Marochkin, Hydroformylation of Low Molecular Olefins and Preparation of Oxosynthesis Products Based on C<sub>4</sub>–C<sub>5</sub> Aldehydes in the Production of Ester Lubricating Oils. Part I. Catalysts and Industrial Processes, *Chem. Technol. Fuels Oils*, 2023, **636**(2), 44–56.
  - 32 P. H. Ravenscroft and M. E. Turney, Detergents from synthetic olefins, *J. Am. Oil Chem. Soc.*, 1955, **32**(7), 418–420.



- 33 L. Lloyd, in *Olefin Polymerization Catalysts*, 2011, pp. 311–350.
- 34 G. Leone, M. Mauri, F. Bertini, M. Canetti, D. Piovani and G. Ricci, Ni(II)  $\alpha$ -Diimine-Catalyzed  $\alpha$ -Olefins Polymerization: Thermoplastic Elastomers of Block Copolymers, *Macromolecules*, 2015, **48**(5), 1304–1312.
- 35 G. E. J. Reynolds, Vinyl acetate-ethylene copolymer dispersions, *Br. Polym. J.*, 1969, **1**(5), 233–238.
- 36 G. K. Min, K. Bjerglund, S. Kramer, T. M. Gøgsig, A. T. Lindhardt and T. Skrydstrup, Generation of Stoichiometric Ethylene and Isotopic Derivatives and Application in Transition-Metal-Catalyzed Vinylation and Enyne Metathesis, *Chem. - Eur. J.*, 2013, **19**(51), 17603–17607.
- 37 M. Monai, M. Gambino, S. Wannakao and B. M. Weckhuysen, Propane to olefins tandem catalysis: a selective route towards light olefins production, *Chem. Soc. Rev.*, 2021, **50**(20), 11503–11529.
- 38 C. G. Visconti, M. Martinelli, L. Falbo, A. Infantes-Molina, L. Lietti, P. Forzatti, *et al.*, CO<sub>2</sub> hydrogenation to lower olefins on a high surface area K-promoted bulk Fe-catalyst, *Appl. Catal., B*, 2017, **200**, 530–542.
- 39 W. Li, H. Wang, X. Jiang, J. Zhu, Z. Liu, X. Guo, *et al.*, A short review of recent advances in CO<sub>2</sub> hydrogenation to hydrocarbons over heterogeneous catalysts, *RSC Adv.*, 2018, **8**(14), 7651–7669.
- 40 T. Numpilai, T. Witoon, N. Chanlek, W. Limphirat, G. Bonura, M. Chareonpanich, *et al.*, Structure–activity relationships of Fe-Co/K-Al<sub>2</sub>O<sub>3</sub> catalysts calcined at different temperatures for CO<sub>2</sub> hydrogenation to light olefins, *Appl. Catal., A*, 2017, **547**, 219–229.
- 41 R. Sathawong, N. Koizumi, C. Song and P. Prasassarakich, Light olefin synthesis from CO<sub>2</sub> hydrogenation over K-promoted Fe–Co bimetallic catalysts, *Catal. Today*, 2015, **251**, 34–40.
- 42 C. G. Visconti, M. Martinelli, L. Falbo, A. Infantes-Molina, L. Lietti, P. Forzatti, *et al.*, CO<sub>2</sub> hydrogenation to lower olefins on a high surface area K-promoted bulk Fe-catalyst, *Appl. Catal., B*, 2017, **200**, 530–542.
- 43 B. Pawelec, R. Guil-López, N. Mota, J. Fierro and R. Navarro Yerga, Catalysts for the Conversion of CO<sub>2</sub> to Low Molecular Weight Olefins—A Review, *Materials*, 2021, **14**(22), 6952.
- 44 Z. Li, J. Wang, Y. Qu, H. Liu, C. Tang, S. Miao, *et al.*, Highly Selective Conversion of Carbon Dioxide to Lower Olefins, *ACS Catal.*, 2017, **7**(12), 8544–8548.
- 45 T. W. van Deelen, C. Hernández Mejía and K. P. de Jong, Control of metal-support interactions in heterogeneous catalysts to enhance activity and selectivity, *Nat. Catal.*, 2019, **2**(11), 955–970.
- 46 J. Chen, S. Tian, J. Lu and Y. Xiong, Catalytic performance of MgO with different exposed crystal facets towards the ozonation of 4-chlorophenol, *Appl. Catal., A*, 2015, **506**, 118–125.
- 47 W. Liao, C. Tang, H. Zheng, J. Ding, K. Zhang, H. Wang, *et al.*, Tuning activity and selectivity of CO<sub>2</sub> hydrogenation via metal-oxide interfaces over ZnO-supported metal catalysts, *J. Catal.*, 2022, **407**, 126–140.
- 48 X. Yuan, T. Pu, M. Gu, M. Zhu and J. Xu, Strong Metal-Support Interactions between Nickel and Iron Oxide during CO<sub>2</sub> Hydrogenation, *ACS Catal.*, 2021, **11**(19), 11966–11972.
- 49 F. C. F. Marcos, J. M. Assaf and E. M. Assaf, CuFe and CuCo supported on pillared clay as catalysts for CO<sub>2</sub> hydrogenation into value-added products in one-step, *Mol. Catal.*, 2018, **458**, 297–306.
- 50 W. K. Fan and M. Tahir, Structured clay minerals-based nanomaterials for sustainable photo/thermal carbon dioxide conversion to cleaner fuels: A critical review, *Sci. Total Environ.*, 2022, **845**, 157206.
- 51 Q. Sun, B. W. J. Chen, N. Wang, Q. He, A. Chang, C. Yang, *et al.*, Zeolite-Encaged Pd–Mn Nanocatalysts for CO<sub>2</sub> Hydrogenation and Formic Acid Dehydrogenation, *Angew. Chem., Int. Ed.*, 2020, **59**(45), 20183–20191.
- 52 I. Nezam, W. Zhou, G. S. Gusmão, M. J. Realff, Y. Wang, A. J. Medford, *et al.*, Direct aromatization of CO<sub>2</sub> via combined CO<sub>2</sub> hydrogenation and zeolite-based acid catalysis, *J. CO<sub>2</sub> Util.*, 2021, **45**, 101405.
- 53 I. Graça, L. V. González, M. C. Bacariza, A. Fernandes, C. Henriques, J. M. Lopes, *et al.*, CO<sub>2</sub> hydrogenation into CH<sub>4</sub> on NiHNaUSY zeolites, *Appl. Catal., B*, 2014, **147**, 101–110.
- 54 X. Yang, H. Duan, R. Wang, F. Zhao, F. Jin, W. Jiang, *et al.*, Tailoring Zeolite L-Supported-Cu Catalysts for CO<sub>2</sub> Hydrogenation: Insights into the Mechanism of CH<sub>3</sub> OH and CO Formation, *Inorg. Chem.*, 2023, **62**(33), 13419–13427.
- 55 W. Wang, C. Duong-Viet, L. Truong-Phuoc, J. M. Nhut, L. Vidal and C. Pham-Huu, Activated carbon supported nickel catalyst for selective CO<sub>2</sub> hydrogenation to synthetic methane under contactless induction heating, *Catal. Today*, 2023, **418**, 114073.
- 56 E. Furimsky, CO<sub>2</sub> Hydrogenation to Methanol and Methane over Carbon-Supported Catalysts, *Ind. Eng. Chem. Res.*, 2020, **59**(35), 15393–15423.
- 57 F. Mateus, P. Teixeira, J. M. Lopes, C. Henriques and C. Bacariza, CO<sub>2</sub> Methanation on Ni Catalysts Supported over Activated Carbons Derived from Cork Waste, *Energy Fuels*, 2023, **37**(12), 8552–8562.
- 58 Z. Xie, J. Hei, L. Cheng, J. Li, X. Yin and S. Meng, Influence of Cu/Al Ratio on the Performance of Carbon-Supported Cu/ZnO/Al<sub>2</sub>O<sub>3</sub> Catalysts for CO<sub>2</sub> Hydrogenation to Methanol, *Catalysts*, 2023, **13**(5), 800.
- 59 N. Koizumi, X. Jiang, J. Kugai and C. Song, Effects of mesoporous silica supports and alkaline promoters on activity of Pd catalysts in CO<sub>2</sub> hydrogenation for methanol synthesis, *Catal. Today*, 2012, **194**(1), 16–24.
- 60 V. Srivastava, Mesoporous Silica Supported Ru Nanoparticles for Hydrogenation of CO<sub>2</sub> Molecule, *Lett. Org. Chem.*, 2017, **14**(2), 74–79.
- 61 S. Ni, J. Zhu, R. Roy, C. J. Li and R. B. Lennox, Catalytic hydrogenation of CO<sub>2</sub> from air *via* porous silica-supported Au nanoparticles in aqueous solution, *Green Chem.*, 2021, **23**(10), 3740–3749.



- 62 H. Cao, W. Wang, T. Cui, H. Wang, G. Zhu and X. Ren, Enhancing CO<sub>2</sub> Hydrogenation to Methane by Ni-Based Catalyst with V Species Using 3D-mesoporous KIT-6 as Support, *Energies*, 2020, **13**(9), 2235.
- 63 A. Dhakshinamoorthy, S. Navalón, A. Primo and H. García, Selective Gas-Phase Hydrogenation of CO<sub>2</sub> to Methanol Catalysed by Metal-Organic Frameworks, *Angew. Chem., Int. Ed.*, 2024, **63**(3), e202311241.
- 64 S. A. Vali, J. Moral-Vico, X. Font and A. Sánchez, Cu/ZnO/CeO<sub>2</sub> Supported on MOF-5 as a Novel Catalyst for the CO<sub>2</sub> Hydrogenation to Methanol: A Mechanistic Study on the Effect of CeO<sub>2</sub> and MOF-5 on Active Sites, *Catal. Lett.*, 2024, **8**, 1–17.
- 65 E. S. Gutterød, A. Lazzarini, T. Fjermestad, G. Kaur, M. Manzoli, S. Bordiga, *et al.*, Hydrogenation of CO<sub>2</sub> to Methanol by Pt Nanoparticles Encapsulated in UiO-67: Deciphering the Role of the Metal-Organic Framework, *J. Am. Chem. Soc.*, 2020, **142**(2), 999–1009.
- 66 C. Zhou, Y. Nan, F. Zha, H. Tian, X. Tang and Y. Chang, Application of metal-organic frameworks in CO<sub>2</sub> hydrogenation, *J. Fuel Chem. Technol.*, 2021, **49**(10), 1444–1457.
- 67 Q. Zhang, S. Wang, M. Dong and W. Fan, CO<sub>2</sub> Hydrogenation on Metal-Organic Frameworks-Based Catalysts: A Mini Review, *Front. Chem.*, 2022, **18**, 10.
- 68 G. Yadav, N. Yadav, M. Sultana and M. Ahmaruzzaman, A comprehensive review on low-cost waste-derived catalysts for environmental remediation, *Mater. Res. Bull.*, 2023, **164**, 112261.
- 69 J. L. Cao, Z. L. Yan, Q. F. Deng, Z. Y. Yuan, Y. Wang, G. Sun, *et al.*, Homogeneous precipitation method preparation of modified red mud supported Ni mesoporous catalysts for ammonia decomposition, *Catal. Sci. Technol.*, 2014, **4**(2), 361–368.
- 70 A. Russkikh, G. Shterk, B. H. Al-Solami, B. A. Fadhel, A. Ramirez and J. Gascon, Turning Waste into Value: Potassium-Promoted Red Mud as an Effective Catalyst for the Hydrogenation of CO<sub>2</sub>, *ChemSusChem*, 2020, **13**(11), 2981–2987.
- 71 P. Gao, S. Dang, S. Li, X. Bu, Z. Liu, M. Qiu, *et al.*, Direct Production of Lower Olefins from CO<sub>2</sub> Conversion via Bifunctional Catalysis, *ACS Catal.*, 2018, **8**(1), 571–578.
- 72 X. Li, T. Zhang, G. Lv, K. Wang and S. Wang, Summary of Research Progress on Metallurgical Utilization Technology of Red Mud, *Minerals*, 2023, **13**(6), 737.
- 73 V. Mymrin, H. de Araújo Ponte, O. Ferreira Lopes and A. Vazquez Vaamonde, Environment-friendly method of high alkaline bauxite's Red Mud and Ferrous Slag utilization as an example of green chemistry, *Green Chem.*, 2003, **5**(3), 357–360.
- 74 Y. Qi, The neutralization and recycling of red mud – a review, *J. Phys.:Conf. Ser.*, 2021, **1759**, 012004.
- 75 Z. Karimi and A. Rahbar-Kelishami, Efficient utilization of red mud waste via stepwise leaching to obtain  $\alpha$ -hematite and mesoporous  $\gamma$ -alumina, *Sci. Rep.*, 2023, **13**(1), 8527.
- 76 D. V. Ribeiro, J. A. Labrincha and M. R. Morelli, Potential use of natural red mud as pozzolan for Portland cement, *Mater. Res.*, 2011, **14**(1), 60–66.
- 77 Z. P. Hu, Z. M. Gao, X. Liu and Z. Y. Yuan, High-surface-area activated red mud for efficient removal of methylene blue from wastewater, *Adsorpt. Sci. Technol.*, 2018, **36**(1–2), 62–79.
- 78 S. J. Palmer and R. L. Frost, Characterisation of bauxite and seawater neutralised bauxite residue using XRD and vibrational spectroscopic techniques, *J. Mater. Sci.*, 2009, **44**(1), 55–63.
- 79 H. Qu, Z. Ling, X. Qi, Y. Xin, C. Liu and H. Cao, A Remote Raman System and Its Applications for Planetary Material Studies, *Sensors*, 2021, **21**(21), 6973.
- 80 D. He, Y. Xiong, L. Wang, W. Sun, R. Liu and T. Yue, Arsenic (III) Removal from a High-Concentration Arsenic (III) Solution by Forming Ferric Arsenite on Red Mud Surface, *Minerals*, 2020, **10**(7), 583.
- 81 S. Barroso-Solares, I. Mediavilla-Martinez, C. Sanz-Velasco, A. C. Prieto and J. Pinto, Pigments identification and analysis of the state of conservation of the decorative elements of the castle of Coca (XV-XVI AC, Segovia, Spain) by Raman Spectroscopy, *J. Phys.:Conf. Ser.*, 2022, **2204**(1), 012010.
- 82 S. Dai, Y. Wu, T. Sakai, Z. Du, H. Sakai and M. Abe, Preparation of Highly Crystalline TiO<sub>2</sub> Nanostructures by Acid-assisted Hydrothermal Treatment of Hexagonal-structured Nanocrystalline Titania/Cetyltrimethylammonium Bromide Nanoskeleton, *Nanoscale Res. Lett.*, 2010, **5**(11), 1829–1835.
- 83 E. Di Iorio, H. G. Cho, Y. Liu, Z. Cheng, R. Angelico and C. Colombo, Arsenate retention mechanisms on hematite with different morphologies evaluated using AFM, TEM measurements and vibrational spectroscopy, *Geochim. Cosmochim. Acta*, 2018, **237**, 155–170.
- 84 W. Gong, X. C. Li and B. Q. Zhu, Modeling Calculation and Synthesis of Alumina Whiskers Based on the Vapor Deposition Process, *Materials*, 2017, **10**(10), 1192.
- 85 P. Thomas, P. Sreekanth and K. E. Abraham, Nanosecond and ultrafast optical power limiting in luminescent Fe<sub>2</sub>O<sub>3</sub> hexagonal nanomorphotype, *J. Appl. Phys.*, 2015, **117**(5), 053103.
- 86 A. Pineau, N. Kanari and I. Gaballah, Kinetics of reduction of iron oxides by H<sub>2</sub>, *Thermochim. Acta*, 2006, **447**(1), 89–100.
- 87 P. Li, Y. Li, J. Yu, P. Gao and Y. Han, Kinetics and microstructural changes during fluidized reduction of magnetite with hydrogen at low temperatures, *Int. J. Hydrogen Energy*, 2022, **47**(73), 31140–31151.
- 88 B. Abebe, H. C. A. Murthy and E. Amare, Summary on Adsorption and Photocatalysis for Pollutant Remediation: Mini Review, *J. Encapsulation Adsorpt. Sci.*, 2018, **08**(04), 225–255.
- 89 C. Liang, X. Hu, T. Wei, P. Jia, Z. Zhang, D. Dong, *et al.*, Methanation of CO<sub>2</sub> over Ni/Al<sub>2</sub>O<sub>3</sub> modified with alkaline earth metals: Impacts of oxygen vacancies on catalytic activity, *Int. J. Hydrogen Energy*, 2019, **44**(16), 8197–8213.



- 90 Z. Baysal and S. Kureti, CO<sub>2</sub> methanation on Mg-promoted Fe catalysts, *Appl. Catal., B*, 2020, **262**, 118300.
- 91 Z. Zhang, X. Zhang, L. Zhang, J. Gao, Y. Shao, D. Dong, *et al.*, Impacts of alkali or alkaline earth metals addition on reaction intermediates formed in methanation of CO<sub>2</sub> over cobalt catalysts, *J. Energy Inst.*, 2020, **93**(4), 1581–1596.
- 92 M. C. Bacariza, R. Bértolo, I. Graça, J. M. Lopes and C. Henriques, The effect of the compensating cation on the catalytic performances of Ni/USY zeolites towards CO<sub>2</sub> methanation, *J. CO<sub>2</sub> Util.*, 2017, **21**, 280–291.
- 93 Y. Zhang, C. Cao, C. Zhang, Z. Zhang, X. Liu, Z. Yang, *et al.*, The study of structure-performance relationship of iron catalyst during a full life cycle for CO<sub>2</sub> hydrogenation, *J. Catal.*, 2019, **378**, 51–62.
- 94 A. Ramirez, L. Gevers, A. Bavykina, S. Ould-Chikh and J. Gascon, Metal Organic Framework-Derived Iron Catalysts for the Direct Hydrogenation of CO<sub>2</sub> to Short Chain Olefins, *ACS Catal.*, 2018, **8**(10), 9174–9182.
- 95 V. P. Santos, T. A. Wezendonk, J. J. D. Jaén, A. I. Dugulan, M. A. Nasalevich, H. U. Islam, *et al.*, Metal organic framework-mediated synthesis of highly active and stable Fischer-Tropsch catalysts, *Nat. Commun.*, 2015, **6**(1), 6451.
- 96 R. Büchel, A. Baiker and S. E. Pratsinis, Effect of Ba and K addition and controlled spatial deposition of Rh in Rh/Al<sub>2</sub>O<sub>3</sub> catalysts for CO<sub>2</sub> hydrogenation, *Appl. Catal., A*, 2014, **477**, 93–101.
- 97 A. Goguet, F. Meunier, J. P. Breen, R. Burch, M. I. Petch and A. Faur Ghenciu, Study of the origin of the deactivation of a Pt/CeO<sub>2</sub> catalyst during reverse water gas shift (RWGS) reaction, *J. Catal.*, 2004, **226**(2), 382–392.
- 98 H. Xu, Y. Li, X. Luo, Z. Xu and J. Ge, Monodispersed gold nanoparticles supported on a zirconium-based porous metal-organic framework and their high catalytic ability for the reverse water-gas shift reaction, *Chem. Commun.*, 2017, **53**(56), 7953–7956.
- 99 F. M. Sun, C. F. Yan, Z. Da Wang, C. Q. Guo and S. L. Huang, Ni/Ce-Zr-O catalyst for high CO<sub>2</sub> conversion during reverse water gas shift reaction (RWGS), *Int. J. Hydrogen Energy*, 2015, **40**(46), 15985–15993.
- 100 H. S. Alghamdi, M. A. Sanhoob, A. M. Ajeebi, M. A. Aziz, M. Nasiruzzaman Shaikh and L. H. Voon, Ultrasmall Fe<sub>3</sub>O<sub>4</sub> Nanoparticles on ZrO<sub>2</sub> as Catalysts for CO<sub>2</sub> Hydrogenation to Lower Olefins, *Asian J. Org. Chem.*, 2024, e202400379.

