



Nanoscale

**Protein Redox by Piezoelectric Acousto-Nanodevice**

Journal:	<i>Nanoscale</i>
Manuscript ID	NR-COM-04-2023-001523.R2
Article Type:	Communication
Date Submitted by the Author:	05-Jul-2023
Complete List of Authors:	Selvarajan, Sophia; University of South Florida, Department of Medical Engineering; Sookmyung Women's University, Department of Electronics Engineering Shim, Hyunji; Sookmyung Women's University, Department of Electronics Engineering Byun, Eunjeong; Sookmyung Women's University, Department of Electronics Engineering Kim, Albert; University of South Florida, Department of Medical Engineering Song, Seung Hyun; Sookmyung Women's University, Department of Electronics Engineering

SCHOLARONE™  
Manuscripts

## Journal Name

## ARTICLE TYPE

Cite this: DOI: 00.0000/xxxxxxxxxx

Protein Redox by Piezoelectric Acousto-Nanodevice<sup>†</sup>Sophia Selvarajan,<sup>a,b</sup> Hyunji Shim,<sup>a</sup> Eunjeong Byun,<sup>a</sup> Albert Kim,<sup>\*b</sup> and Seung Hyun Song<sup>\*a</sup>

Received Date

Accepted Date

DOI: 00.0000/xxxxxxxxxx

Protein redox is responsible for many crucial biological processes; thus, the ability to modulate the redox proteins through external stimuli presents a unique opportunity to attune the system. In this work, we present the acousto-nanodevice that is capable of oxidizing redox protein under ultrasonic irradiation via surface-engineered barium titanate (BTO) nanoparticles with gold half-coating. Using cytochrome c as the model protein, we demonstrate nanodevice-mediated protein oxidation. Based on our experimental observations, we reveal that the electron transfer occurs in one direction due to the alternating electrical polarization of BTO under ultrasound. Such unique unidirectional electron transfer is enabled by modulating the work function of the gold surface with respect to the redox center. The new class of ultrasonically powered nano-sized protein redox agents could be a modulator for biological processes with high selectivity and deeper treating sites.

Redox reactions in proteins, governed by the electron transfer,<sup>1–3</sup> are at the center of the protein functionality and stability as they govern many crucial life-sustaining functions, including respiration,<sup>4</sup> photosynthesis,<sup>5</sup> metabolism,<sup>6</sup> and cell apoptosis.<sup>7,8</sup> Moreover, the conformation and aggregation behaviors of proteins that determine the protein stability and influence the development of protein misfolding diseases, such as Alzheimer's or Parkinson's diseases, as closely related to the protein redox states.<sup>9,10</sup> Thus, the ability to externally control the protein redox states has great clinical implications as it may enable the modulation of biological processes or protein conformation.<sup>11</sup> For example, it has been shown that the oxidation of cytochrome c, which functions as an electron carrier in the respiratory chain, can trigger cell apoptosis.<sup>12</sup> Also, the oxidation of the amyloid beta aggregates, a hallmark of Alzheimer's disease, has been shown to destabilize the aggregates both experimentally and theoret-

cally.<sup>13,14</sup>

The modulation and the characterization of the redox proteins have, traditionally, been achieved by electrochemical methods,<sup>15</sup> which has shown that the protein redox process is governed by the electron transfer between the redox sites of the proteins and the electrode.<sup>1–3</sup> However, the need for the wiring of electrodes makes the clinical translation using the electrochemical technique challenging. For this reason, researchers have looked for alternative methods without the use of traditional electrodes. A successful example is the optical interrogation of the redox state of cytochrome c based on the electron transfer of the plasmonically excited electrons to the heme site of the cytochrome c under light illumination.<sup>16,17</sup> On the other hand, the use of acoustics in protein redox has been relatively under-explored, despite the fact that acoustics can readily address a key limitation of the optical methods in biological systems in the limited penetration depth.

In this work, we present an ultrasonically excitable acousto-nanodevice capable of modulating the protein redox states. Ultrasound, as the external stimulus for redox modulation, offers a unique advantage in deep penetration depth in tissues without the need for wiring. The acousto-nanodevice is asymmetrically metalized barium titanate (BTO) nanoparticles (i.e., half-surface metal coating), which allows the modulation of the electron energy under acoustic waves. Our experimental results demonstrate that cytochrome c (cyt c) oxidation can be mediated by the acousto-nanodevice under ultrasonic irradiation. The oxidation mechanism is tentatively linked to the unidirectional direct electron transfer between the piezoelectric acousto-nanodevice and the heme site of cytochrome c (cyt C).

Our acousto-nanodevice system for protein redox modulation is composed of two parts: the ultrasound as the external control stimulus and the engineered piezoelectric nanoparticles that directly interface with the protein. We chose ultrasound as the controlling external stimulus for the protein redox because it offers a deep penetration depth (in the order of centimeters) and can be administrated safely.<sup>18–22</sup>

We first describe the experimental results of cyt c oxidation by the acousto-nanodevice under external acoustic waves. We chose cyt c as the model protein<sup>23</sup> in this proof-of-concept study be-

<sup>a</sup> Department of Electronics Engineering, Sookmyung Women's University, Seoul 04310, Republic of Korea; E-mail: shsong.ee@sookmyung.ac.kr

<sup>b</sup> Department of Medical Engineering, University of South Florida, Tampa, FL, 33602, USA; E-mail: akim1@usf.edu

<sup>†</sup> Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 00.0000/00000000.

cause its structure and functionality are well-established in the literature.<sup>24–26</sup> The redox states of cyt c were monitored using UV-Vis absorption measurements, which reflects the oxidation/reduction state of heme ( $\text{Fe}^{2+} \leftrightarrow \text{Fe}^{3+}$ ) (Refer to Supplementary Information for UV-Vis sample preparation and measurement conditions).<sup>27</sup> We prepared the acousto-nanodevice with a gold half-coating for cyt c oxidation experiment, as the gold surface provides an adsorption site for cyt c (direct chemisorption), retaining its native electron transfer properties.<sup>28–30</sup> (For the detailed fabrication procedure of acousto-nanodevice, refer to Supplementary Information Fig. S1.)




Fig. 1 Cytochrome c oxidation by acousto-nanodevice: (a) Schematic illustration of cyt c oxidation by nanodevice. (b) UV-Vis spectrum of oxidized and reduced cyt c (baseline) (inset shows the visual color change due to oxidation of reduced cyt c upon its interaction with BTO-Au nanoparticles in the presence of ultrasound). (c-d) UV-Vis spectrum showing cyt c oxidation mediated by acoustically triggered BTO-Au nanoparticles and schematics depicting uni-directional charge transfer from protein to BTO-Au, causing its oxidation. (e-f) UV-Vis spectrum showing the absence of a reducing effect in cyt c by acoustically triggered BTO-Au nanoparticles and its corresponding schematics depicting no charge transfer from BTO-Au to protein.

Following the acousto-nanodevice preparation, we added a low concentration of the acousto-nanodevice (in the order of 1 nM) in a cuvet with 5  $\mu\text{M}$  of reduced cyt c; the cuvet was then placed in a large water tank, and a low-intensity ultrasound ( $\sim 150$  mW/cm<sup>2</sup>) was applied for 30 minutes (Fig. 1a.). After the ultrasound irradiation, we observed the color change of cyt c from light pink (reduced cyt c) to a light orange (oxidized cyt c), as shown in Fig. 1b inset. UV-Vis absorption spectrum confirmed the oxidation of cyt c. A blueshift of  $\sim 5$  nm around the solet region (415 nm to 410 nm; Fig. 1c inset) was observed due to the oxi-

dation of heme ( $\text{Fe}^{2+}$  to  $\text{Fe}^{3+}$ ), suggesting an overall net electron transfer from the reduced cyt c to the acousto-nanodevice (Fig. 1d). This results also agree to the reported absorption peaks of oxidized (409 nm) and reduced cyt c (415 nm).<sup>27</sup> In contrast, there were no observable changes to the UV-Vis spectrum when the same system (*i.e.*, acousto-nanodevice under ultrasound) was applied to the oxidized cyt c (Fig. 1e). The spectrum remained largely unchanged from the reference oxidized cyt c (Fig. 1e), suggesting that there are little electron transfers between oxidized cyt c and the acousto-nanodevice (*i.e.*, unidirectional electron transfer) (Fig. 1f).

To find out if the oxidation of reduced cyt c is indeed due to the acousto-nanodevice under ultrasonic irradiation, we performed three different control experiments, which illuminate the role of the surface metal coating and the effect of ultrasonic irradiation. The reduced cyt c was treated with 1) pristine BTO nanoparticles (*i.e.*, no surface metal coating) without sonication, 2) pristine BTO nanoparticles with sonication, and 3) acousto-nanodevice without sonication. The degree of oxidation was quantified by the peak fitting of the UV-Vis spectra. We decomposed the peak by according to the Beer-Lambert law: the overall UV-Vis absorbance of the sample,  $A$ , is determined as below.

$$A = \alpha_{ox} \cdot c_{ox} \cdot l + \alpha_{red} \cdot c_{red} \cdot l$$

, where  $\alpha_{ox}$  ( $= 0.09 \mu\text{mol}^{-1} \text{cm}^{-1}$ ) and  $\alpha_{red}$  ( $= 0.13 \mu\text{mol}^{-1} \text{cm}^{-1}$ ) are the molar absorbance of oxidized and reduced cyt c obtained from our reference samples (Fig. 1),  $c_{ox}$  and  $c_{red}$  are the molar concentration of oxidized and reduced cyt c, and  $l$  is an optical path of cuvettes,  $l = 1$  cm (refer to Supplementary Information for peak fitting procedure). The peak decomposition of reduced cyt c reference (Fig. S2) shows that the spectra are mostly composed of the reduced cyt c-related peaks (green shade area) with a contribution of oxidation (blue shaded area).

Fig. 2a-d shows the representative UV-Vis spectra of all experimental groups (three controls and one test). While the spectra of the three control groups (Fig. 2a-c) were largely the same as the spectrum of reduced cyt c reference, the spectrum of the test group (Fig. 2d) showed significant oxidation of cyt c; the intensity of the solet peak at 415 nm decreases while the peak at 409 nm increases. For quantitative analysis of the oxidation effect caused by each group, we characterized the oxidation effects of each group by tracking the concentration of the oxidized and reduced cyt c.

The average change in the concentration of oxidized cyt c ( $\Delta c_{ox}$  [ $\mu\text{M}$ ]) following a 30-minute sonication of four independent experiments is summarized in Fig. 2e. We tentatively assign the large variation in the oxidation of the experimental group (*i.e.*, BTO-Au sonication in Fig. 2e) to the variation in the acousto-nanodevice concentrations of the different batches. Note that the collection efficiency of the acousto-nanodevice varied from batch to batch, even though we fabricated the acousto-nanodevice with the same procedure. Nevertheless, the experimental group (acousto-nanodevice and sonication) showed statistical significance compared to all three sham control groups:  $p$ -value was 0.009 for acousto-nanodevice without sonication,




Fig. 2 Acoustically triggered protein redox: the underlying mechanism. Lorentzian fit for UV-Vis spectrum of (a) BTO-reduced cyt c (no sonication) (b) BTO-reduced cyt c (sonication) (c) BTO-Au-reduced cyt c (no sonication), and (d) BTO-Au-reduced cyt c (sonication). Except for BTO-Au-reduced cyt c (sonication), there is no significant change in the degree of oxidation for other conjugates. (e) the average change in oxidation following 30 minutes of sonication (f) 2D graph showing the degree of oxidation with respect to time (obtained from Lorentzian fitting) between the sonicated and non-sonicated conjugates of reduced cyt c. Error bars represent SD;  $n \geq 4$ ; p-Value was determined using a two-tailed T-test. NS: Not significant, (\*)  $p < 0.05$ , (\*\*)  $p < 0.01$

0.016 for pristine BTO without sonication, and 0.020 for pristine BTO with sonication (refer to Supplementary Information for detailed statistical analysis). The time evolution of the change in the oxidized cyt c concentration is summarized in Fig. 2f; progressive oxidation of the cyt c by the acousto-nanodevice occurred within 10 min of sonication. In addition, we note that the overall concentration of the cyt c ( $c_{ox} + c_{red}$  remained constant throughout the experiment).

In addition, we examined the stability of reduced cyt c in both the presence and absence of ultrasound (Fig. S4). We observed no detectable changes in the UV-Vis spectra were observed in the presence/absence of sonication for an extended time. All experiments were also maintained the pH and temperature, both of which might affect the stability and redox of proteins. We used phosphate-buffered saline (Sigma-Aldrich) to maintain a pH of 7.4. We also utilized a large volume of the water tank (20 L) and a sufficiently low ultrasound intensity ( $150 \text{ mW}/\text{cm}^2$ ) to ensure that the thermal effects due to continuous ultrasound irradiation to minimal; we monitored temperature during all experiments ( $\Delta T < 0.1 \text{ }^\circ\text{C}$ ). Furthermore, we could exclude the surface plasmonic effect at the metallic surface as a contributing factor to the overall oxidation of cyt c since the ultrasonic excitation frequency was 2.3 MHz, far below the typical plasmonic frequency in the order of  $10^{14} \text{ Hz}$ <sup>31</sup>. We also performed an additional control experiment by changing the surface metal to chromium, which we observed no oxidation effect (Fig. S5). Thus, we conclude that the plasmonic effect of the metallic surface is not a dominant factor. Moreover, the fact that there is no modulation of the oxida-

tion state of cyt c by BTO-Cr is indicative of the importance of the metal's work function in determining the redox control through the acousto-nanodevice.

Based on the result presented in Fig. 2, we now discuss the mechanism of oxidation. Firstly, the fact that significant oxidation was observed only by the acousto-nanodevice under ultrasonic irradiation indicates that both the externally applied ultrasound and the presence of gold half-coating are jointly responsible for the observed oxidation effect. Based on the observation, we tentatively propose the following as the principle of acousto-nanodevice-driven protein redox (Fig. 3a).

In our proposed model, the alternating electrical polarization of BTO nanoparticles under the external ultrasound modulates the work function of the half-coated metal (Fig. 3b). With an appropriate selection of the metal work function, the electron transfer between the acousto-nanodevice and the protein redox center can only occur at a certain polarization, effectively achieving unidirectional electron transfer.

Applying this principle to induce protein oxidation by the acousto-nanodevice is schematically illustrated in Fig. 3c and 3d. The precondition to the protein oxidation by the acousto-nanodevice is that the surface metal work function should oscillate above and below the highest occupied molecular orbital (HOMO) level of the protein redox center. In more detail, we expect that when the polarization points toward the metal surface, the metal work function is increased; if the resulting band alignment is that the work function sits below the lowest unoccupied molecular orbital (LUMO) of the protein redox site,




Fig. 3 Protein oxidation by acousto-nanodevice driven under external acoustics. (a) The work function of the surface metal of the acousto-nanodevice oscillates under incoming acoustic waves, (b-c) a unidirectional electron transfer from protein to acousto-nanodevice is achieved because of the band alignment between the surface metal and the HOMO/LUMO levels of the protein redox center

but above HOMO level, there is no electron transfer (Fig. 3c). When the polarization points toward the non-metalized surface, the metal work function can be lowered below the HOMO level, allowing the acousto-nanodevice to extract an electron from the protein. As a result, the band alignment is proposed to be responsible for the unidirectional electron transfer from protein to the acousto-nanodevice (Fig. 3d). Thus, under external acoustic waves, the net effect of the oscillating work function due to alternating electrical polarization results in net oxidation effect on proteins. Similarly, protein reduction may also be possible by selecting a metal whose work function is sufficiently low (e.g., Al).

We presented the acousto-nanodevice capable of modulating the redox state of a redox protein (i.e., reduced cyt c) under ultrasonic irradiation. The results clearly demonstrated that protein oxidation occurs only when a half-surface gold-coated acousto-nanodevice was activated by ultrasound. We also experimentally confirmed that the acousto-nanodevice may be engineered to be either an oxidation or reduction agent, depending on the types of the surface metal. Based on the various sham controls, we postulate the working mechanism of the acousto-nanodevice is that the alternating electrical polarization of BTO nanoparticles can tentatively modulate the work function of the metal, thereby inducing unidirectional electron transfer from the protein redox centers to the acousto-nanodevice. To our best knowledge, the present work is the first demonstration of modulating the redox state of proteins selectively by an ultrasonic-mediated acousto-nanodevice. Provided the importance of the protein redox in biological processes, we look forward to the further development of the acousto-nanodevice for targeting specific redox proteins for external modulations, including both reduction/oxidation.

## Author Contributions

S.H.S. and A.K. conceived the idea and designed the experiment. S.H.S. and S.S. performed the sample preparation and characterization. S.H.S. and S.S. evaluated and interpreted the data. S.S. wrote the manuscript under the guidance of A.K. and S.H.S. as primary investigators. H.S. and E.B. assisted with manuscript preparation and experiments. All authors discussed the results and commented on the manuscript.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was supported by the National Research Foundation of Korea (NRF) grant funded by the Korea government (MSIT) No. 2018R1C1B5086311 (Song) and the National Science Foundation (NSF) No. ECCS-2245090 (Kim).

## Notes and references

- Q. Chi, O. Farver and J. Ulstrup, *Proceedings of the National Academy of Sciences*, 2005, **102**, 16203–16208.
- A. Lagunas, A. Guerra-Castellano, A. Nin-Hill, I. Díaz-Moreno, A. Miguel, J. Samitier, C. Rovira and P. Gorostiza, *Nature communications*, 2018, **9**, 1–7.
- J. M. Artes, I. Diez-Perez, F. Sanz and P. Gorostiza, *ACS Nano*, 2011, **5**, 2060–2066.
- X. Liu, C. N. Kim, J. Yang, R. Jemerson and X. Wang, *Cell*, 1996, **86**, 147–157.
- M. R. Wasielewski, *Chemical reviews*, 1992, **92**, 435–461.
- D. Stock, A. G. Leslie and J. E. Walker, *Science*, 1999, **286**, 1700–1705.
- J. Yuan and B. A. Yankner, *Nature*, 2000, **407**, 802–809.
- M. Giorgio, E. Migliaccio, F. Orsini, D. Paolucci, M. Moroni, C. Contursi, G. Pelliccia, L. Luzi, S. Minucci, M. Marcaccio *et al.*, *Cell*, 2005, **122**, 221–233.
- C. Soto and S. Pritzkow, *Nature neuroscience*, 2018, **21**, 1332–1340.
- W. M. Carroll, *The Lancet Neurology*, 2019, **18**, 418–419.
- Y. Ding, K. A. Ball, K. J. Webb, Y. Gao, A. D'Alessandro, W. M. Old, M. H. Stowell and X. Ding, *Small*, 2020, **16**, 2003506.
- C. Garrido, L. Galluzzi, M. Brunet, P. Puig, C. Didelot and G. Kroemer, *Cell Death & Differentiation*, 2006, **13**, 1423–1433.
- D. Bayliss, J. L. Walsh, G. Shama, F. Iza and M. G. Kong, *New Journal of Physics*, 2009, **11**, 115024.
- J. Razzokov, M. Yusupov and A. Bogaerts, *Scientific reports*, 2019, **9**, 5476.

- 15 J. J. Warren, M. E. Ener, A. Vlček Jr, J. R. Winkler and H. B. Gray, *Coordination chemistry reviews*, 2012, **256**, 2478–2487.
- 16 H. Xin, W. J. Sim, B. Namgung, Y. Choi, B. Li and L. P. Lee, *Nature communications*, 2019, **10**, 1–11.
- 17 Y. Choi, T. Kang and L. P. Lee, *Nano letters*, 2009, **9**, 85–90.
- 18 S. H. Song, A. Kim and B. Ziaie, *IEEE Transactions on Biomedical Engineering*, 2015, **62**, 2717–2723.
- 19 J. Lee, K. Ko, H. Shin, S.-J. Oh, C. J. Lee, N. Chou, N. Choi, M. T. Oh, B. C. Lee, S. C. Jun *et al.*, *Microsystems & Nanoengineering*, 2019, **5**, 28.
- 20 G. Leinenga, C. Langton, R. Nisbet and J. Götz, *Nature Reviews Neurology*, 2016, **12**, 161.
- 21 M. C. Ziskin, *Radiographics*, 1993, **13**, 705–709.
- 22 A. Abrahao, Y. Meng, M. Llinas, Y. Huang, C. Hamani, T. Mainprize, I. Aubert, C. Heyn, S. E. Black, K. Hynynen *et al.*, *Nature communications*, 2019, **10**, 1–9.
- 23 B. I. Lee, S. Lee, Y. S. Suh, J. S. Lee, A.-k. Kim, O.-Y. Kwon, K. Yu and C. B. Park, *Angewandte Chemie International Edition*, 2015, **54**, 11472–11476.
- 24 D. S. Wuttke, M. J. Bjerrum, J. R. Winkler and H. B. Gray, *Science*, 1992, **256**, 1007–1009.
- 25 C. Lange and C. Hunte, *Proceedings of the National Academy of Sciences*, 2002, **99**, 2800–2805.
- 26 T. d. F. Paulo, T. P. de Sousa, D. S. de Abreu, N. H. Felício, P. V. Bernhardt, L. G. de F. Lopes, E. H. Sousa and I. C. Diógenes, *The Journal of Physical Chemistry B*, 2013, **117**, 8673–8680.
- 27 M.-E. Aubin-Tam and K. Hamad-Schifferli, *Langmuir*, 2005, **21**, 12080–12084.
- 28 H. A. Heering, F. G. Wiertz, C. Dekker and S. de Vries, *Journal of the American Chemical Society*, 2004, **126**, 11103–11112.
- 29 M. E. Siwko and S. Corni, *Physical Chemistry Chemical Physics*, 2013, **15**, 5945–5956.
- 30 X. Ding, M. Yang, J. Hu, Q. Li and A. McDougall, *Microchimica Acta*, 2007, **158**, 65–71.
- 31 J.-J. Greffet, *Plasmonics*, Springer, 2012, pp. 105–148.