



Cite this: *Chem. Commun.*, 2021, 57, 5766

Received 8th April 2021,
Accepted 7th May 2021

DOI: 10.1039/d1cc01868j

rsc.li/chemcomm

An alginate-confined peroxygenase-CLEA for styrene epoxidation†

Friederike E. H. Nintzel,^a Yinqi Wu,^a Matteo Planchestainer,^b Martin Held,^b Miguel Alcalde^c and Frank Hollmann^{*,a}

Oxyfunctionalisation reactions in neat substrate still pose a challenge for biocatalysis. Here, we report an alginate-confined peroxygenase-CLEA to catalyse the enantioselective epoxidation of *cis*- β -methylstyrene in a solvent-free reaction system achieving turnover numbers of 96 000 for the biocatalyst and epoxide concentrations of 48 mM.


Biocatalytic oxyfunctionalisation reactions are enjoying an increasing interest in organic chemistry.¹ Especially the often very high regio- and enantioselectivity of enzymatic oxyfunctionalisation reactions such as hydroxylations or epoxidations offers synthetic chemists straightforward access to chiral building blocks, which with traditional chemical means are difficult to prepare.

Next to the well-known P450 monooxygenases,² in recent years also peroxygenases³ have been in the centre of attention. P450 monooxygenases reductively activate molecular oxygen to form the catalytically active oxyferryl-heme species. Peroxygenases form this species directly from partially reduced oxygen species (peroxides) and thereby circumvent the complex molecular architectures of P450 monooxygenases (Scheme 1).

The synthetic application of both enzyme classes, however, still suffers from the poor water solubility of the majority of starting materials, resulting in rather dilute reaction mixtures with an enormous water footprint. Therefore, increasing the starting material (and product) concentration is of utmost importance to increase the economic viability and environmental friendliness of such biocatalytic reactions.⁴

One common approach to increase the substrate loading is to use the so-called two liquid phase approach⁵ in which an aqueous, biocatalyst-containing layer is contacted with a hydrophobic, organic layer serving as substrate reservoir and product sink. To alleviate possible phase transfer rate limitations of this system, intensive mechanical stirring is needed, which however, also may impair the stability of the biocatalyst.⁶

The latter issue can be addressed by immobilising the biocatalyst to a heterogeneous carrier material and thereby physically protecting the enzyme. While a limited number of studies report immobilisation of peroxygenases, this technique is not fully explored yet for this enzyme class.^{7–12} In previous works, we could demonstrate that immobilised peroxygenases in principle can even be applied in neat (*i.e.* almost water-free) reaction media.⁹ A drawback of this approach, however, was the very poor specific activity of the immobilised enzyme, possibly due to a combination of activity losses of the enzyme during



Scheme 1 Comparison of (a) P450 monooxygenase-catalysed and (b) peroxygenase-catalysed oxyfunctionalisation reactions. (c) Both enzyme classes utilise Compound I as the oxygenating agent.

^a Department of Biotechnology, Delft University of Technology, van der Maasweg 9, 2629 HZ, Delft, The Netherlands. E-mail: f.hollmann@tudelft.nl

^b Department of Biosystems Science and Engineering, ETH Zürich, Mattenstrasse 26, Basel 4058, Switzerland

^c Department of Biocatalysis, Institute of Catalysis and Petrochemistry (CSIC), Madrid, Spain

† Electronic supplementary information (ESI) available: Detailed information about synthetic and analytical procedures as well as additional experimental results. See DOI: 10.1039/d1cc01868j

‡ Both authors contributed equally.





Scheme 2 (a) Overview of the utilised immobilisation approach consisting of CLEA formation and alginate confinement. (b) Epoxidation of *cis*- β -methylstyrene by immobilised *rAaeUPO* with *tert*-butyl hydroperoxide (*t*BuOOH) as oxidant.

immobilisation and further activity losses originating from dehydration of the enzyme surface.

Encapsulating enzymes in alginate matrices may represent an elegant compromise. The so-confined enzymes are mechanically stabilised while still situated in a micro-aqueous environment.^{8,11,13}

We therefore set out to immobilise a peroxygenase in an alginate matrix and evaluate its catalytic activity under non aqueous reaction conditions. As model enzyme we chose the recombinantly expressed, evolved peroxygenase from *Agrocyste aegerita* (*rAaeUPO*)^{14–16} as catalyst for the epoxidation of styrene and *cis*- β -methylstyrene (Scheme 2). The biocatalyst was obtained from the supernatant of the fermentation broth of recombinant *Pichia pastoris* and used without further purification.

Confining *rAaeUPO* in Ca^{2+} -hardened alginates proved to be feasible. To our surprise, however, the resulting immobilisate showed low, and somewhat irreproducible catalytic activity (Fig. 1a), which most likely was due to leaching of the enzyme from the beads during the immobilisation procedure and storage. To improve the retention of the biocatalyst in the alginate beads, we decided to increase its molecular mass by covalent cross-linking (CLEA formation).^{17–19}

Indeed, CLEA formation more than doubled the catalytic activity of the immobilised peroxygenase (Fig. 1a). Further improvements were achieved by using chitosan as coagulant^{20–23} and by increasing the enzyme load (Fig. 1a). Additional optimisation steps are reported in the ESI.[†] It is important to note that the size of the beads had a significant influence on the activity of the immobilised peroxygenase. The larger the beads, the lower the catalytic activity under otherwise identical conditions (Fig. 1b).

Overall, approximately 19% of the enzyme was immobilised (as determined *via* quantification of the amount of active heme sites using CO-differential spectra) and 11.4% of the peroxidase activity, as judged by the ABTS oxidation activity, was found




Fig. 1 (a) Activity of imm-*rAaeUPO* during optimisation of the immobilisation procedure, determined by ABTS-activity assay in aqueous environment. Reference (I) is the encapsulation of free *rAaeUPO*. The catalytic activity of imm-*rAaeUPO* was improved by CLEA formation (II), by application of chitosan as coagulant (III), and by maximising the enzyme load (IV). (b) Activity of imm-*rAaeUPO* immobilisates with different diameters, determined by ABTS-activity assay in aqueous environment. Data represents the average of duplicates. Further information on the immobilisation optimisation can be found in the ESI.[†]

back in the immobilisates. It is worth mentioning here that *rAaeUPO* immobilisation also increased its storage stability. While the free enzyme completely lost its catalytic activity after 12 days storage at room temperature, the immobilised version exhibited at least 80% of its initial activity even after two weeks (Fig. S10, ESI[†]).

Having the immobilised *rAaeUPO* preparation at hand, we decided to compare its catalytic performance in the epoxidation of *cis*- β -methylstyrene with the free enzyme in a two liquid phase approach (Fig. 2) using *t*BuOOH as oxidant.

Very much to our surprise the immobilised enzyme outperformed the free enzyme under otherwise identical conditions (such as volumetric ratio of aqueous or alginate volume to



Fig. 2 Product formation over time for the epoxidation of *cis*- β -methylstyrene in different reaction systems: imm-*rAaeUPO* in neat substrate (180 mg immobilisate in 570 μL *cis*- β -methylstyrene) (red circles), and free *rAaeUPO* in a two-liquid phase system (180 μL TRIS-HCl buffer (20 mM, pH 7): 570 μL *cis*- β -methylstyrene) (blue squares). General reaction conditions: [*rAaeUPO*] = 0.5 μM , *t*BuOOH feeding rate = 10 mM h⁻¹, room temperature, shaking at 99 rpm with 60° angle in an overhead rotator. Data represents the average of duplicates.



the organic phase and enzyme concentrations). With the immobilised enzyme the product accumulation rate was approx. 10 mM h^{-1} (corresponding to the $t\text{BuOOH}$ feed rate) while with the free enzyme it was only 3 mM h^{-1} . A plausible explanation for this may be the higher surface area of the reactions using alginate-immobilised $rAaeUPO$, largely eliminating the diffusion rate limitation of $t\text{BuOOH}$ and/or *cis*- β -methylstyrene into the aqueous reaction phase (Fig. S15, ESI†).

Overall, in this experiment, approx. 30 mM of enantiomerically pure (2*R*,3*S*)-2-methyl-3-phenyloxirane has been synthesised within 4 h corresponding to a turnover number ($\text{TN} = \text{mol}_{\text{Product}} \times \text{mol}_{rAaeUPO}^{-1}$) for the enzyme of 60 000 and an average (over 4 h) turnover frequency of 4.1 s^{-1} . It should be mentioned here, that under these reaction conditions several side products such as benzaldehyde and phenylacetone were observed (*vide infra*).

Despite the promising results, the reactions stopped after approximately 5 h. We suspected the irreversible, oxidative inactivation of the heme-containing biocatalyst by the hydroperoxide to account for the low robustness of the reaction.

Therefore, we performed a series of experiments varying the $t\text{BuOOH}$ addition rate (Fig. 3). While the initial product formation rate decreased with decreasing $t\text{BuOOH}$ feeding rates, the long-term robustness of the reaction increased: at a $t\text{BuOOH}$ feeding rate of 20 mM h^{-1} , product formation rates of 9 mM h^{-1} were observed but the product accumulation ceased after 4 h. Applying a $t\text{BuOOH}$ feeding rate of 1 mM h^{-1} approximately the same product formation rate was observed, albeit for at least 72 h. Also the formation of the undesired side products decreased considerably with lower $t\text{BuOOH}$ feeding rates (Fig. S19, ESI†). Both observations are most likely related to each other. At high $t\text{BuOOH}$ feeding rates, the peroxide availability exceeds the enzyme's epoxidation capacity resulting in oxidative inactivation of the heme prosthetic group and release of iron ions. The latter catalyse Fenton-like

transformations resulting in non-selective oxidation of the *cis*- β -methylstyrene starting material and formation of the undesired side-products.

In any case, lowering the $t\text{BuOOH}$ feeding rate not only increased the robustness of the reaction but also reduced the side-product formation. Under these conditions, 48 mM (6.4 g L^{-1}) of enantiomerically pure (2*R*,3*S*)-2-methyl-3-phenyloxirane have been synthesised within 72 h. This corresponds to excellent TN of 96 000 for the biocatalyst. This catalytic performance also favourably compares to other enzyme systems such as flavin-dependent monooxygenases.^{24–27} Admittedly, the current substrate scope of the proposed immobilised $rAaeUPO$ preparation is rather limited, preliminary experiments on styrene epoxidation indicate a similar catalytic potential for this substrate (Fig. S21, ESI†). Future experiments will broaden the synthetic scope of the proposed $rAaeUPO$ preparation.

To obtain a first overview over the environmental impact of the reaction system established in this study, we used Sheldon's E-factor^{28,29} to estimate the wastes generated in the formation of (2*R*,3*S*)-2-methyl-3-phenyloxirane. As shown in Table 1, a total of 153.3 kg of waste was generated per kg of the desired product. 70% of the E-factor contribution stems from non-reacted starting material, which in a putative preparative-scale reaction can be recovered *via* distillation. The second-largest contributor (24%) is the enzyme preparation. The latter is mostly comprised of the alginate beads and buffer (making 99% of the total mass of the immobilised enzyme).

We are convinced that further optimisation of the immobilisation protocol will improve the $rAaeUPO$ loading in the alginate beads. For example using alginate-in-oil emulsions for the bead preparation will certainly improve the $rAaeUPO$ loading.³⁰ Also the E-factor contribution of the oxidant and its by-product $t\text{BuOH}$, respectively, can be reduced significantly when co-immobilising the formate oxidase from *Aspergillus oryzae* (AoFOX) to use methanol as sacrificial electron donor for the *in situ* generation of H_2O_2 .^{31–34} Implementing this



Fig. 3 Initial rate, maximal product concentration and reaction robustness of the epoxidation of *cis*- β -methylstyrene catalysed by imm- $rAaeUPO$ at different $t\text{BuOOH}$ feeding rates. Reaction set-up: 570 μL *cis*- β -methylstyrene, supplemented with 180 mg immobilisate and continuously fed with the indicated $t\text{BuOOH}$ rate. General reaction conditions: [$rAaeUPO$] = 0.5 μM , room temperature, shaking at 99 rpm with 60° angle in an overhead rotator. Data represents the average of duplicates.

Table 1 E-Factor analysis of the epoxidation of *cis*- β -methylstyrene to (2*R*,3*S*)-2-methyl-3-phenyloxirane

Products	(2 <i>R</i> ,3 <i>S</i>)-2-methyl-3-phenyloxirane	4.8
	$t\text{BuOH}^a$	41.0
	Various side products ^b	0.9
Reactants	<i>cis</i> - β -Methylstyrene ^c	515.9
	$t\text{BuOOH}^a$	0.0
Catalyst	$rAaeUPO^d$	180.0
E-factor	SUM (waste)	737.9
	SUM (epoxide product)	4.8
	E-factor	153.3

^a It is assumed that all added $t\text{BuOOH}$ converted into $t\text{BuOH}$. The indicated $t\text{BuOH}$ mass includes decane which was used for dilution of $t\text{BuOOH}$. ^b Concentrations and masses of side products were estimated based on the GC calibration line and response factor of (2*R*,3*S*)-2-methyl-3-phenyloxirane. ^c Mass of *cis*- β -methylstyrene after reaction stop is estimated based on formation of epoxide and side products. ^d $rAaeUPO$ includes imm- $rAaeUPO$ beads.



system will eliminate the 'BuOH contribution to the E-factor (8.5 kg kg⁻¹) and reduce it to approx. 0.11 kg_{CO2} kg_{Product}⁻¹.

Overall, in this contribution we have established alginate-confined peroxxygenase-CLEAs as practical enzyme preparations for the selective epoxidation of styrene derivatives such as *cis*- β -methylstyrene to synthesise enantiomerically pure epoxides. In terms of catalyst efficiency (more than 90 000 catalytic cycles observed), the current system outperforms comparable reaction systems using chemical catalysts,³⁵ P450 monooxygenases³⁶ or other established enzymatic systems,^{26,27,37} also compared to our previous efforts using immobilised rAaeUPO.⁹ We are convinced that further optimisation will bring this approach to maturity and will establish an economically and environmentally feasible reaction system.

Financial support by the China Scholarship Council, the from the German Academic Exchange Service and the German Academic Scholarship Foundation as well as the European Research Council (ERC Consolidator Grant No. 648026) is gratefully acknowledged.

F. E. H. N., Y. W. and M. P. have performed the experiments and analysed the results. The study was conceptualised by M. H., M. A. and F. H. All authors contributed to the manuscript writing.

Conflicts of interest

There are no conflicts to declare.

Notes and references

- 1 J. Dong, E. Fernández-Fueyo, F. Hollmann, C. Paul, M. Pesic, S. Schmidt, Y. Wang, S. Younes and W. Zhang, *Angew. Chem., Int. Ed.*, 2018, **57**, 9238–9261.
- 2 V. B. Urlacher and M. Girhard, *Trends Biotechnol.*, 2019, **37**, 882–897.
- 3 M. Hobisch, D. Holtmann, P. G. de Santos, M. Alcalde, F. Hollmann and S. Kara, *Biotechnol. Adv.*, 2021, 107615, DOI: 10.1016/j.biotechadv.2020.107615.
- 4 Y. Ni, D. Holtmann and F. Hollmann, *ChemCatChem*, 2014, **6**, 930–943.
- 5 M. van Schie, J.-D. Spöring, M. Bocola, P. Dominguez de Maria and D. Rother, *Green Chem.*, 2021, DOI: 10.1039/D1GC00561H.
- 6 E. Churakova, I. W. C. E. Arends and F. Hollmann, *ChemCatChem*, 2013, **5**, 565–568.
- 7 A. Yayci, T. Dirks, F. Kogelheide, M. Alcalde, F. Hollmann, P. Awakowicz and J. E. Bandow, *J. Phys. D: Appl. Phys.*, 2021, **54**, 035204.
- 8 M. Hobisch, M. M. C. H. van Schie, J. Kim, K. Røjkjær Andersen, M. Alcalde, R. Kourist, C. B. Park, F. Hollmann and S. Kara, *ChemCatChem*, 2020, **12**, 4009–4013.
- 9 M. C. R. Rauch, F. Tieves, C. E. Paul, I. W. Arends, M. Alcalde and F. Hollmann, *ChemCatChem*, 2019, **11**, 4519–4523.
- 10 E. Fernández-Fueyo, Y. Ni, A. Gomez Baraibar, M. Alcalde, L. M. van Langen and F. Hollmann, *J. Mol. Catal. B: Enzym.*, 2016, **134**, 347–352.
- 11 M. Poraj-Kobielska, S. Peter, S. Leonhardt, R. Ullrich, K. Scheibner and M. Hofrichter, *Biochem. Eng. J.*, 2015, **98**, 144–150.
- 12 P. Molina-Espeja, P. Santos-Moriano, E. Garcia-Ruiz, A. Ballesteros, F. J. Plou and M. Alcalde, *Int. J. Mol. Sci.*, 2019, **20**, 1627.
- 13 L. Fernandez-Arrojo, B. Rodriguez-Colinas, P. Gutierrez-Alonso, M. Fernandez-Lobato, M. Alcalde, A. O. Ballesteros and F. J. Plou, *Process Biochem.*, 2013, **48**, 677–682.
- 14 R. Ullrich, J. Nüske, K. Scheibner, J. Spantzel and M. Hofrichter, *Appl. Environ. Microbiol.*, 2004, **70**, 4575–4581.
- 15 P. Molina-Espeja, S. Ma, D. M. Mate, R. Ludwig and M. Alcalde, *Enzyme Microb. Technol.*, 2015, **73–74**, 29–33.
- 16 P. Molina-Espeja, E. Garcia-Ruiz, D. Gonzalez-Perez, R. Ullrich, M. Hofrichter and M. Alcalde, *Appl. Environ. Microbiol.*, 2014, **80**, 3496–3507.
- 17 R. A. Sheldon and S. van Pelt, *Chem. Soc. Rev.*, 2013, **42**, 6223–6235.
- 18 C. Mateo, J. M. Palomo, L. M. van Langen, F. van Rantwijk and R. A. Sheldon, *Biotechnol. Bioeng.*, 2004, **86**, 273–276.
- 19 L. Q. Cao, F. van Rantwijk and R. A. Sheldon, *Org. Lett.*, 2000, **2**, 1361–1364.
- 20 M.-Q. Xu, S.-S. Wang, L.-N. Li, J. Gao and Y.-W. Zhang, *Catalysts*, 2018, **8**, 460.
- 21 S. Velasco-Lozano, F. López-Gallego, J. C. Mateos-Díaz and E. Favela-Torres, *Biocatalysis*, 2016, 166–177, DOI: 10.1515/boca-2015-0012.
- 22 S. Talekar, A. Joshi, G. Joshi, P. Kamat, R. Haripurkar and R. A. Sheldon, *RSC Adv.*, 2013, **3**, 12485–12511.
- 23 D. Grajales-Hernández, M. Armendáriz-Ruiz, S. Velasco-Lozano, F. López-Gallego and J. C. Mateos-Díaz, *Appl. Microbiol. Biotechnol.*, 2020, **104**, 10033–10045.
- 24 C. E. Paul, D. Tischler, A. Riedel, T. Heine, N. Itoh and F. Hollmann, *ACS Catal.*, 2015, **5**, 2961–2965.
- 25 H. Toda, R. Imae, T. Komio and N. Itoh, *Appl. Microbiol. Biotechnol.*, 2012, **96**, 407–418.
- 26 K. Hofstetter, J. Lutz, I. Lang, B. Witholt and A. Schmid, *Angew. Chem., Int. Ed.*, 2004, **43**, 2163–2166.
- 27 A. Schmid, K. Hofstetter, H.-J. Feiten, F. Hollmann and B. Witholt, *Adv. Synth. Catal.*, 2001, **343**, 732–737.
- 28 R. A. Sheldon, *Green Chem.*, 2017, **19**, 18–43.
- 29 R. A. Sheldon, *Chem. Commun.*, 2008, 3352–3365.
- 30 L. Mazutis, R. Vasiliauskas and D. A. Weitz, *Macromol. Biosci.*, 2015, **15**, 1641–1646.
- 31 S. J. P. Willot, M. D. Hoang, C. E. Paul, M. Alcalde, I. Arends, A. S. Bommarius, B. Bommarius and F. Hollmann, *ChemCatChem*, 2020, **12**, 2713–2716.
- 32 F. Tieves, S. J.-P. Willot, M. M. C. H. van Schie, M. C. R. Rauch, S. H. H. Younes, W. Zhang, P. G. de Santos, J. M. Robbins, B. Bommarius, M. Alcalde, A. Bommarius and F. Hollmann, *Angew. Chem., Int. Ed.*, 2019, **58**, 7873–7877.
- 33 J. M. Robbins, A. S. Bommarius and G. Gadda, *Arch. Biochem. Biophys.*, 2018, **643**, 24–31.
- 34 J. M. Robbins, M. G. Souffrant, D. Hamelberg, G. Gadda and A. S. Bommarius, *Biochemistry*, 2017, **56**, 3800–3807.
- 35 D. Banerjee, R. V. Jagadeesh, K. Junge, M.-M. Pohl, J. Radnik, A. Brückner and M. Beller, *Angew. Chem., Int. Ed.*, 2014, **53**, 4359–4363.
- 36 M. R. Sarkar, J. H. Z. Lee and S. G. Bell, *ChemBioChem*, 2017, **18**, 2119–2128.
- 37 H. Toda, R. Imae and N. Itoh, *Tetrahedron: Asymmetry*, 2012, **22–23**, 1542–1549.

