


# Energy & Environmental Science

www.rsc.org/ees

Volume 6 | Number 11 | November 2013 | Pages 3101–3388



ISSN 1754-5692

RSC Publishing

**PAPER**

Durrant *et al.*

Parameters affecting electron transfer dynamics from semiconductors to molecular catalysts for the photochemical reduction of protons



1754-5692 (2013) 6:11;1-#

Cite this: *Energy Environ. Sci.*, 2013, **6**, 3291

## Parameters affecting electron transfer dynamics from semiconductors to molecular catalysts for the photochemical reduction of protons†

Anna Reynal,<sup>a</sup> Fezile Lakadamyali,<sup>b</sup> Manuela A. Gross,<sup>b</sup> Erwin Reisner<sup>b</sup> and James R. Durrant<sup>\*a</sup>

The aim of this work is to use transient absorption spectroscopy to study the parameters affecting the kinetics and efficiency of electron transfer in a photocatalytic system for water reduction based on a cobalt proton reduction catalyst (**CoP**) adsorbed on a nanocrystalline TiO<sub>2</sub> film. In the first approach, water is used as the proton and electron source and H<sub>2</sub> is generated after band gap excitation of TiO<sub>2</sub> functionalised with **CoP**. The second system involves the use of a sacrificial electron donor to regenerate the TiO<sub>2</sub>/**CoP** system in water at neutral pH. The third system consists of **CoP**/TiO<sub>2</sub> films co-sensitised with a ruthenium-based dye (**RuP**). In particular, we focus on the study of different parameters that affect the kinetics of electron transfer from the semiconductor to the molecular catalyst by monitoring the lifetime of charge carriers in TiO<sub>2</sub>. We observe that low catalyst loadings onto the surface of TiO<sub>2</sub>, high excitation light intensities and small driving forces strongly slow down the kinetics and/or reduce the efficiency of the electron transfer at the interface. We conclude that the first reduction of the catalyst from Co<sup>III</sup> to Co<sup>II</sup> can proceed efficiently even in the absence of an added hole scavenger at sufficiently high catalyst coverages and low excitation densities. In contrast, the second reduction from Co<sup>II</sup> to Co<sup>I</sup>, which is required for hydrogen evolution, appears to be at least 10<sup>5</sup> slower, suggesting it requires efficient hole scavenging and almost complete reduction of all the adsorbed **CoP** to Co<sup>I</sup>. Dye sensitisation enables visible light photoactivity, although this is partly offset by slower, and less efficient, hole scavenging.

Received 20th March 2013  
Accepted 4th June 2013

DOI: 10.1039/c3ee40961a

[www.rsc.org/ees](http://www.rsc.org/ees)

### Broader context

The photochemical reduction of water into H<sub>2</sub> offers the possibility of harvesting sunlight and storing this energy in the form of chemical bonds. Rapid progress is currently being made in the development of synthetic and bio-inspired molecular catalysts for proton reduction, which can also be integrated in heterogeneous photocatalytic systems through the functionalisation of semiconductors such as TiO<sub>2</sub>. The development of efficient hybrid photocatalytic H<sub>2</sub> evolution systems involves not only the study of its catalytic activity, but also the analysis of the electron transfer kinetics and the control of the main recombination pathways. Molecular catalysts for H<sup>+</sup> reduction require the accumulation of two electrons in one single catalyst, which is potentially a key limiting factor of their efficiency. In this paper, we study three different photochemical systems based on TiO<sub>2</sub> functionalised with a molecular cobalt catalyst and a ruthenium photosensitiser. In particular, we address the kinetics of the two-electron transfer reactions needed for the H<sub>2</sub> production by monitoring the charge carriers (electrons and holes) of the semiconductor by transient absorption spectroscopy.

### Introduction

The development of photocatalytic systems for the hydrogen generation from water splitting is receiving renewed attention as a renewable fuel synthesis strategy.<sup>1,2</sup> The photochemical


reduction of water into H<sub>2</sub> offers the possibility of harvesting sunlight and storing its energy in the form of a chemical bond. Most of these approaches combine a photoactive element that harvests solar energy with a catalytic component to catalyse the two electron reduction of protons to molecular hydrogen.<sup>3,4</sup> In this regard, rapid progress is being made in the development of molecular catalysts for H<sup>+</sup> reduction, including Ni and Co complexes and dinuclear Fe or Ni-Fe hydrogenase mimics.<sup>4–8</sup> However, studies integrating such H<sub>2</sub> evolution electrocatalysts into photochemical systems are more limited to date,<sup>9–13</sup> and have moreover largely focused on overall system performance, rather than elucidation of the underlying electron transfer

<sup>a</sup>Department of Chemistry, Imperial College London, Exhibition Road, London SW7 2AZ, UK. E-mail: [j.durrant@imperial.ac.uk](mailto:j.durrant@imperial.ac.uk)

<sup>b</sup>Christian Doppler Laboratory for Sustainable SynGas Chemistry, Department of Chemistry, University of Cambridge, Cambridge, CB2 1EW, UK

† Electronic supplementary information (ESI) available: Additional transient absorption data and Marcus theory equation. See DOI: 10.1039/c3ee40961a





**Fig. 1** Molecular structure of the ruthenium dye (**RuP**) and the cobalt H<sup>+</sup> reduction catalyst (**CoP**).


kinetics that are critical in determining the efficiency of the system. In this paper, we focus on the electron transfer dynamics in a series of model systems based upon mesoporous, nanocrystalline TiO<sub>2</sub> films functionalised with a cobalt based H<sup>+</sup> reduction catalyst, and thereby elucidate how these charge carrier dynamics impact the proton reduction efficiency.

Electron transfer dynamics between molecular photosensitisers and TiO<sub>2</sub> has been widely studied in the context of dye sensitised solar cells.<sup>14–16</sup> Such devices are based on the electron injection from the photosensitiser into the TiO<sub>2</sub> semiconductor. In contrast, H<sup>+</sup> reduction by molecular catalysts immobilised on TiO<sub>2</sub> requires the reverse electron transfer reaction – from the TiO<sub>2</sub> conduction band to the molecular catalyst. This reverse electron transfer reaction is an undesired recombination pathway in dye sensitised solar cells. The parameters required to optimise the efficiency of this reaction have received relatively little attention to date, and are therefore the subject of this paper.

Heterogeneous photochemical systems for proton reduction require semiconductors with a conduction band above the reduction potential of water reduction (−0.42 V vs. NHE at pH 7). TiO<sub>2</sub>, the semiconductor studied herein, is one of the most widely used semiconductors for such studies due to the appropriate position of its conduction and valence bands, its high stability and availability, ease of fabrication as high surface area nanocrystalline films and particles and its low cost.<sup>17,18</sup>

However the efficiency of TiO<sub>2</sub> photocatalysts alone for proton photoreduction is typically relatively low, attributed to poor visible light absorption, fast recombination of photogenerated charge carriers, and the low driving force for the H<sup>+</sup> reduction reaction, resulting in slow H<sup>+</sup> reduction kinetics.<sup>19–22</sup> A common strategy to address these limitations, for both TiO<sub>2</sub> and alternative semiconductors, is the functionalisation of the semiconductor with a catalyst capable of accelerating the H<sup>+</sup> reduction and increasing the selectivity for H<sub>2</sub> evolution.<sup>23</sup> A particular consideration with the use of molecular catalysts for solar driven fuel synthesis is that they typically require multiple oxidation/reduction steps, which contrasts with the single electron–hole pairs generated by photon absorption in bare semiconductors. Therefore hydrogen generation typically requires photogenerated charge carriers to drive a double reduction reaction of a single molecular catalyst,<sup>11,24</sup> and this requirement is potentially a key factor limiting the system's performance. This contrasts with the use of inorganic catalysts (such as Pt nanoparticles) where separate electrons injected into the nanoparticle are likely to be able to come together to drive hydrogen generation.

In this regard, we have recently reported an example of such a hybrid photocatalytic system for H<sub>2</sub> evolution that involves the combination of anatase or mixed anatase/rutile (P25) TiO<sub>2</sub> nanoparticles with a molecular ruthenium photosensitiser (**RuP**) and a cobaloxime H<sub>2</sub> evolution catalyst (**CoP**) covalently attached to the semiconductor through phosphonic acid anchoring groups (Fig. 1).<sup>9,25</sup> Double reduction of this catalyst, from Co<sup>III</sup> to Co<sup>I</sup>, has been shown to enable proton reduction to molecular hydrogen, with an overall external quantum efficiency of the photocatalytic system of 1% under LED light irradiation at 465 nm (3 mW cm<sup>−2</sup>).<sup>9,25</sup> In this paper, we employ this as a model system for exploring the parameters influencing the efficiency of electron transfer from the semiconductor to the molecular catalyst, including the impact of catalyst loading and light intensity. Our study employs three alternative approaches based upon this experimental system, as illustrated in Scheme 1. All three approaches employ nanocrystalline TiO<sub>2</sub> films functionalised by **CoP** for the production of hydrogen in



**Scheme 1** Illustration of the three experimental systems studied herein, and the functional processes underlying their function comprising (a) TiO<sub>2</sub> functionalised by a **CoP** proton reduction catalyst in water under UV excitation, with, (b) the addition of a sacrificial electron donor (D), and (c) the addition of a photosensitiser dye to enable visible light activity. The figure illustrates the two reduction potentials of the catalyst (Co<sup>III/I</sup> and Co<sup>I/I</sup>, measured at pH 7) relevant for the H<sub>2</sub> evolution reaction. Forward electron transfer processes are represented with solid black arrows, while recombination reactions are drawn with dashed grey arrows.





aqueous solution under  $N_2$ . The first approach is based upon these materials alone, excluding any sacrificial electron donor, and therefore relying upon the ability of  $TiO_2$  holes to oxidise water to molecular oxygen as the source of electrons for proton reduction. In the second approach, a sacrificial electron donor (triethanolamine, TEOA) is used as a hole scavenger to remove photogenerated  $TiO_2$  holes. Finally, the third system involves the functionalisation of the  $TiO_2$  nanoparticles with a molecular ruthenium dye (**RuP**) and a cobalt catalyst anchored onto the surface, again using TEOA to regenerate the photosensitiser.

## Experimental section

### Materials and methods

All starting reagents for the synthetic part of the work were purchased from commercial suppliers and used without any further purification. Chemicals used for the analytical part were of the highest available purity.  $(Et_3NH)[Co^{III}Cl(dmgH)_2^-]$  (pyridyl-4-hydrophosphonate),  $(Et_3NH)[CoP]$ ,<sup>9</sup> and  $[Ru^{II}(2,2'-bipyridine)_2(2,2'-bipyridine-4,4'-diylbis(phosphonic acid))]Br_2$ ,  $[RuP]Br_2$ ,<sup>26</sup> were prepared as described previously. Triethanolamine hydrochloride buffer solutions (0.1 M) were adjusted to pH 7 upon the addition of 0.1 M NaOH.

Anatase  $TiO_2$  nanoparticles and films were prepared as reported previously.<sup>27</sup> Mesoporous nanocrystalline  $TiO_2$  films were prepared by the doctor blading technique from colloidal pastes. The resulting film thickness, determined by profilometry (Tencor Instruments), was 4  $\mu m$ .

### Preparation of dye sensitised $TiO_2$ films with and without CoP

For approach (c),  $TiO_2$  films were sensitised with **RuP** by introducing the films into an aqueous **RuP** solution (0.1 mM) and monitoring the dye loading by UV-vis spectroscopy (see below). The sensitisation time for  $TiO_2$  films was optimised in order to adjust the MLCT absorption band ( $\lambda = 450$  nm) to an absorbance of 0.6.  $TiO_2$  nanostructured films were co-sensitised with **RuP** and **CoP** by dipping the films for 48 h into a 5 mL aqueous solution containing **CoP** (16 nmol – corresponding to 80 **CoP** molecules per  $TiO_2$  particle) and **RuP** (8 nmol – corresponding to 40 **RuP** molecules per  $TiO_2$  particle).

### Loading $TiO_2$ films with CoP

Two different methods were used to functionalise  $TiO_2$  films with **CoP**.<sup>28</sup> Unless otherwise stated, monolayer coverage of **CoP** was achieved by dipping the films in a high concentration **CoP** aqueous solution (0.1 mM) for 12 h. For studies as a function of the number of **CoP** molecules anchored per  $TiO_2$  nanoparticle, the films were dipped into a low concentration **CoP** solution for a longer period of time (2 nmol, 8 nmol, 24 nmol, and 40 nmol, for 48 h). The amount of catalyst loaded was monitored by UV-vis spectroscopy after desorbing the catalyst from the nanoparticles by dipping the film into a 0.1 M NaOH solution.

### Spectroscopic characterisation

All functionalised films were kept in the fridge (4 °C) and in the dark to avoid degradation prior to measurement. Spectroscopic

measurements on functionalised films were undertaken at room temperature with films immersed in 5 mL of water under  $N_2$  for approach (a), and with the addition of 5 mL of a 0.1 M TEOA solution buffered at pH 7 for approaches (b) and (c).

The UV-vis spectra of the solutions were recorded using a quartz cuvette (one cm path length) on a Perkin Elmer Lambda 35 UV-Vis spectrophotometer.

The millisecond-second transient absorption decays were measured using a Nd:YAG laser (Big Sky Laser Technologies Ultra CFR Nd:YAG laser system, 6 ns pulse width). The third harmonic of the laser (corresponding to 355 nm) and a coupled OPO crystal fixed at 450 nm, were used to excite the band gap of  $TiO_2$  and the **RuP**, respectively. The laser intensity was adjusted using neutral density filters as appropriate, with experiments typically employing  $350 \mu J cm^{-2}$  unless otherwise stated and the frequency of the laser pulse was fixed to 1 Hz. A liquid light guide with a diameter of 0.5 cm was used to transmit the laser pulse to the sample. The probe light source was a 100 W Benthams IL1 tungsten lamp, and the probing wavelength was selected by using a monochromator (OBB-2001, Photon Technology International) placed prior to the sample. Several high pass and neutral density filters (Comar Instruments) were used to decrease the light arriving to the detector. Transient absorption data was collected with a Si photodiode (Hamamatsu S3071). The information was passed through an amplifier box (Costronics) and recorded using a Tektronics TDS 2012c oscilloscope (microsecond to millisecond timescale) and a National Instruments (NI USB-6211) DAQ card (millisecond to second timescale). The decays observed were the average between 500 and 1000 laser pulses. The data was processed using a home-built software based on Labview.

## Results

The three experimental systems studied in this paper are illustrated in Scheme 1. We address the electron transfer kinetics measured for each system, respectively, and then compare and contrast these kinetics in our discussion. For approaches (a) and (b), all transient signals exhibited spectra indicative of their assignment to  $TiO_2$  electrons or holes (see ESI for typical spectra, Fig. S1†),<sup>19,29</sup> with no signals directly from the **CoP** being apparent over the spectral range studied (460 nm–900 nm), consistent with the dominant optical absorption of **CoP** lying in the ultraviolet, and therefore masked by the strong ground state absorption of  $TiO_2$  in this region. Our study focuses on the yields and lifetimes of  $TiO_2$  holes (observed at 460 nm) and, of particular interest, electrons (observed at 900 nm), and their dependence upon experimental approach and catalyst loading. For approach (c), additional, spectrally distinct, optical signals from the **RuP** photosensitiser were observed, as detailed below.

### Band gap excitation of $TiO_2$ /CoP in water


The lifetime of charge carrier species (electrons and holes) in bare and **CoP** monolayer-functionalised  $TiO_2$  films (140 **CoP** per  $TiO_2$  nanoparticle) was monitored by transient absorption




spectroscopy after band gap excitation ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ). The decay of photoexcited electrons and holes of bare  $\text{TiO}_2$  in water under  $\text{N}_2$  show identical dynamics, exhibiting power law decay kinetics consistent with bimolecular (or 'non-geminate') recombination processes on the micro- to millisecond time scales (Fig. 2A).<sup>29–31</sup> The exponent of this power law was  $\sim 0.4$ , assigned previously to bimolecular recombination in the presence of charge trapping.<sup>32</sup> Band gap excitation of  $\text{TiO}_2$  modified with a **CoP** monolayer should allow for electron transfer from the conduction band of the semiconductor to the catalyst, resulting in an accumulation of valence band holes and a fast depletion of conduction band electrons. Consistent with this expectation, the transient absorption signal corresponding to the photoexcited electrons in  $\text{TiO}_2$  show a lower signal amplitude for  $\text{TiO}_2/\text{CoP}$  films when compared to bare  $\text{TiO}_2$  films (Fig. 2B), indicative of the electron transfer from the semiconductor to the catalyst that takes place in  $\leq 10 \text{ }\mu\text{s}$ . On the other hand, the signal amplitude of photoholes when the **CoP** is attached onto the surface of  $\text{TiO}_2$  is doubled in amplitude and longer-lived compared to that of bare  $\text{TiO}_2$  films, indicating an

increased lifetime of holes in the  $\text{TiO}_2$  valence band. The decay dynamics of these holes in functionalised  $\text{TiO}_2/\text{CoP}$  films ( $\tau_{1/2} \sim 1 \text{ ms}$ ) is slow compared to that observed in the absence of **CoP**, but faster than the oxidation of water in the presence of irreversible electron scavengers, such as  $\text{Ag}^+$ , that suppress the electron-hole recombination.<sup>29</sup>

In this simple model system, the primary process competing with electron transfer from the  $\text{TiO}_2$  to the **CoP** is the electron-hole recombination in  $\text{TiO}_2$ . This recombination is a bimolecular process, and therefore dependent upon the charge carrier densities in the film. In order to address this competition further, we undertook transient kinetic measurements as a function of excitation density (Fig. 3 and Fig. S2, see ESI†). The excitation density from  $50 \text{ }\mu\text{J cm}^{-2}$  to  $1 \text{ mJ cm}^{-2}$  corresponds to approximately 0.5 to 10 photons absorbed per  $\text{TiO}_2$  nanoparticle (*c.f.* 10 to 200 **CoP** molecules per photon). We have previously shown for bare  $\text{TiO}_2$  films that increasing the excitation densities generate more electron-hole pairs and the recombination becomes faster.<sup>29,33</sup> The signal of photoexcited electrons of  $\text{TiO}_2/\text{CoP}$  also shows faster decays with increasing laser intensity




**Fig. 2** Transient absorption decays of photoelectrons and photoholes after band gap excitation of a bare  $\text{TiO}_2$  (A), and  $\text{TiO}_2/\text{CoP}$  films (B) in water and under a  $\text{N}_2$  atmosphere. The excitation wavelength was  $355 \text{ nm}$  ( $350 \text{ }\mu\text{J cm}^{-2}$ ), the decay of photo-excited electrons was monitored at  $900 \text{ nm}$ , and the decay of photoholes was probed at  $460 \text{ nm}$ .



**Fig. 3** Transient absorption decays of photoexcited electrons (A) and holes (B) of a  $\text{TiO}_2/\text{CoP}$  film in water under  $\text{N}_2$  after band gap excitation ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ) with different laser pulse intensities, ranging from  $50 \text{ }\mu\text{J cm}^{-2}$  to  $1 \text{ mJ cm}^{-2}$ . The decay of photo-excited electrons was probed at  $900 \text{ nm}$ , while holes were monitored at  $460 \text{ nm}$ .






**Fig. 4** Signal amplitude of generated photoholes of a  $\text{TiO}_2/\text{CoP}$  film after band gap excitation ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ), assigned to the recombination of charge carriers in  $\text{TiO}_2$  ( $\text{h}^+$  fast phase) and to the holes accumulated at the valence band of  $\text{TiO}_2$  after electron transfer to  $\text{CoP}$  ( $\text{h}^+$  slow phase), using different excitation densities.

(Fig. 3A), consistent with electron–hole recombination in  $\text{TiO}_2$  being a competing reaction with the electron transfer to  $\text{CoP}$ . The decays of photoholes show a more complex behaviour as a function of excitation density, exhibiting a biphasic decay at higher excitation densities (Fig. 3B). A faster phase ( $\mu\text{s}$ – $\text{ms}$ ) increases in amplitude and becomes faster with increasing excitation density. The similarity between this behavior and that observed for the  $\text{TiO}_2$  electron signal allows us to assign this fast hole decay phase to electron–hole recombination. The slow phase (half time  $\sim 100 \text{ ms}$ ) is assigned to holes left in the  $\text{TiO}_2$  valence band following electron transfer to the  $\text{CoP}$ ; its decay dynamics are assigned to hole recombination with reduced  $\text{CoP}$  catalyst and/or water oxidation on the hundreds of milliseconds timescale (Fig. S3, see ESI†).

Fig. 4 plots the amplitudes of the two  $\text{TiO}_2$  decay phases observed for  $\text{TiO}_2/\text{CoP}$  films as a function of excitation densities. It is apparent that the fast decay phase, assigned to  $\text{TiO}_2$  electron–hole recombination, is only observed for excitation densities greater than  $\sim 100 \mu\text{J cm}^{-2}$ . In contrast, the long-lived photoholes, assigned to  $\text{TiO}_2$  holes left in the valence band following electron transfer to  $\text{CoP}$ , exhibits a strongly sub-linear increase in yield with excitation density. This sub-linear behaviour is consistent with electron–hole recombination increasingly competing with electron transfer to  $\text{CoP}$  as the excitation density is increased. At low excitation densities, the charge carrier recombination becomes dominated by electron transfer to  $\text{CoP}$  and the accumulation of  $\text{h}^+$  in the  $\text{TiO}_2$  valence band.

#### Band gap excitation of $\text{TiO}_2/\text{CoP}$ in the presence of a sacrificial electron donor

In the previous section, we have addressed the kinetic competition between electron–hole recombination within the  $\text{TiO}_2$  versus transfer to  $\text{CoP}$ . It has been widely reported that molecular hole scavengers can be effective in suppressing this




**Fig. 5** Transient absorption decays corresponding to  $\text{TiO}_2$  photoexcited electrons in bare  $\text{TiO}_2$  and  $\text{TiO}_2$ -functionalised films with different quantities of  $\text{CoP}$  under  $\text{N}_2$  and in the presence of a  $0.1 \text{ M}$  TEOA aqueous solution at  $\text{pH } 7$  as sacrificial electron donor ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ,  $\lambda_{\text{probe}} = 900 \text{ nm}$ ,  $E_{\text{ex}} = 350 \mu\text{J cm}^{-2}$ ).

competing recombination reaction. The electron transfer reactions from the  $\text{TiO}_2$  to the  $\text{CoP}$  catalysts were therefore studied when immersing the films into a  $0.1 \text{ M}$  TEOA aqueous solution as hole scavenger ( $\text{pH } 7$ , under  $\text{N}_2$ ). As shown in Fig. 5, for bare  $\text{TiO}_2$  films the addition of a sacrificial hole scavenger results in a very substantial increase in the electron lifetime to  $\sim 1 \text{ s}$ , indicating that TEOA very efficiently suppresses electron–hole recombination losses. In the presence of TEOA, no  $\text{TiO}_2$  hole signal could be observed, indicating hole scavenging by TEOA in  $< 1 \mu\text{s}$ . In the further presence of  $\text{CoP}$ , the electron decay is substantially accelerated. Due to the absence of electron–hole recombination, this acceleration can be directly assigned to electron transfer from the semiconductor to the molecular catalyst.

We now turn to the influence of  $\text{CoP}$  loading upon the kinetics of electron transfer from  $\text{TiO}_2$  to  $\text{CoP}$ . With decreasing amounts of  $\text{CoP}$  (ranging from 140 to 5 molecules per  $\text{TiO}_2$  particle), the photoinduced electron decay slows down significantly, and becomes biphasic at low coverages (Fig. 5). The decay at early timescales ( $\mu\text{s}$ – $\text{ms}$ ) is assigned to the electron transfer from the semiconductor to the molecular catalyst, while the slower phase corresponds to the decay observed in the absence of catalyst (most probably corresponding to electron transfer into the electrolyte, such as reduction of residual oxygen in the degassed solution). From these data, the half-time for electron transfer from  $\text{TiO}_2$  to  $\text{CoP}$  was estimated, as shown in Fig. 6 and Fig. S4, see ESI†<sup>34</sup>. It is apparent that this electron transfer half-time varies substantially (by five orders of magnitude) with  $\text{CoP}$  coverage.

For a simple bimolecular recombination kinetic model, the half-time ( $t_{50\%}$ ) for electron transfer from  $\text{TiO}_2$  to  $\text{CoP}$  should vary linearly with  $\text{CoP}$  coverage, corresponding to the grey line in Fig. 6. It is apparent that the observed dependence on  $\text{CoP}$






**Fig. 6** Half-time electron transfer ( $t_{50\%}$ ), calculated as the full width at half maximum, for the  $\mu\text{s}$  – ms timescale phase of the photoexcited electrons decay of  $\text{TiO}_2/\text{CoP}$  films after band gap excitation ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ) with different surface coverage of **CoP**, measured under a  $\text{N}_2$  purged 0.1 M TEOA solution at pH 7.

coverage is much greater than this simple model prediction. In order to address this surprising result, we investigated the dependence of these kinetics upon laser excitation density for a fixed (monolayer) catalyst coverage, again in the presence of TEOA (Fig. 7). Rather strikingly, the  $\text{TiO}_2$  electron decay is substantially delayed as the laser intensity is increased. This is the inverse of the behavior observed in the absence of TEOA (Fig. 3), where higher laser intensity resulted in faster decays. This observation suggests that at higher light fluxes, electron transfer from  $\text{TiO}_2$  to **CoP** is impeded.

The studies shown in both Fig. 5 and 7 vary the ratio of photogenerated electron density per **CoP** (by varying either the catalyst coverage, Fig. 5, or electron density, Fig. 7). In order to address this effect further, we compared decays measured at



**Fig. 7** Transient absorption decays corresponding to photoexcited electrons in  $\text{TiO}_2/\text{CoP}$  films sensitised with a monolayer of catalyst measured at different excitation densities ranging from  $50 \mu\text{J cm}^{-2}$  to  $1 \text{ mJ cm}^{-2}$  ( $\lambda_{\text{ex}} = 355 \text{ nm}$ ,  $\lambda_{\text{probe}} = 900 \text{ nm}$ ). The films were kept under  $\text{N}_2$  and in the presence of a 0.1 M TEOA at pH 7.

different catalyst coverages, but with laser intensity modulated in order to obtain matched ratios of electrons per **CoP** (see ESI Fig. S5†). It is apparent that decays measured at matched electron/**CoP** ratios showed very similar kinetics for a range of **CoP** coverages. This suggests that the key determinant of the observed rate of electron transfer from  $\text{TiO}_2$  to **CoP** is this ratio of photoinduced electron density per **CoP** molecules. As we discuss below, this behavior most probably is associated with the accumulation of singly reduced **CoP** (*i.e.*:  $\text{Co}^{\text{II}}$ ) species under conditions of high electron generation rates per **CoP**, with electron transfer from  $\text{TiO}_2$  to  $\text{Co}^{\text{II}}$  being substantially slower than that to the unreduced  $\text{Co}^{\text{III}}$  state.

### Dye sensitised $\text{TiO}_2/\text{CoP}$ in the presence of a sacrificial electron donor


The functionalisation of wide band gap semiconductors with a molecular dye shifts the absorption spectrum of the photocatalytic system from UV to visible light, allowing light harvesting of a broader range of the solar spectrum. In addition, this interface also enhances charge separation without the addition of sacrificial species, through the oxidation of the molecular photosensitiser after electron injection into the  $\text{TiO}_2$ . In this kind of system, the function of the semiconductor has a different role when compared to non-dye sensitised systems:  $\text{TiO}_2$  does not act as a light harvesting antenna, but acts as an electron transport layer between the dye and the catalyst. The kinetics and efficiency of dye electron injection into the  $\text{TiO}_2$  and dye regeneration by the sacrificial electron donor of this three-component system were previously reported,<sup>25</sup> and in this paper we will focus on the study of the electron transfer kinetics from the semiconductor to the molecular catalyst.

The excitation of **RuP** with visible light ( $\lambda_{\text{ex}} = 450 \text{ nm}$ ) leads to the injection of electrons to the conduction band in the  $\text{TiO}_2$ . In the presence of the sacrificial electron donor TEOA, transient absorption spectroscopy measurements of **RuP**/ $\text{TiO}_2$  monitored at  $\lambda_{\text{probe}} = 690 \text{ nm}$  (corresponding to **RuP**<sup>+</sup> maximum absorption wavelength), show a biphasic transient absorption decay, in which the faster component ( $\sim 200 \mu\text{s}$ ) is assigned to electron transfer from TEOA to **RuP**<sup>+</sup> (analogous to hole scavenging), and the slow component ( $\sim 300 \text{ ms}$ ) is assigned to the presence of long-lived electrons in the  $\text{TiO}_2$  (Fig. S6†). We note this dye regeneration timescale is at least 200 fold slower than the analogous scavenging of  $\text{TiO}_2$  holes by TEOA discussed above. It is also of similar magnitude to the recombination timescale of  $\text{TiO}_2$  electrons with **RuP**<sup>+</sup><sup>25</sup> – suggesting that kinetic competition between this recombination and dye regeneration may be a significant loss factor under the conditions studied. Fig. 8 shows the analogous data probing at  $900 \text{ nm}$ , and therefore dominated by  $\text{TiO}_2$  electron absorption. Again a biphasic decay is observed, with the electron signal showing a 50% decay on the timescale of dye regeneration and dye cation/ $\text{TiO}_2$  electron recombination, indicating that under these conditions, hole scavenging of **RuP** sensitised  $\text{TiO}_2$  by TEOA is significantly less efficient than for  $\text{TiO}_2$  holes generated by direct UV excitation.

The co-attachment of **CoP** to the dye sensitised  $\text{TiO}_2$  nanoparticles (approximately 80 **CoP** and 40 **RuP** molecules per  $\text{TiO}_2$







**Fig. 8** Transient absorption decays of  $\text{TiO}_2$  films functionalised with **CoP** and/or **RuP**, in the presence of 0.1 M TEOA at pH 7 ( $\lambda_{\text{ex}} = 450$  nm,  $\lambda_{\text{probe}} = 900$  nm). The decay of **RuP**/ $\text{TiO}_2$  is fitted to a combination of a stretched exponential equation and a monoexponential equation, and the decay of  $\text{TiO}_2$  functionalised with **RuP** and **CoP** is fitted to a stretched exponential equation.

particle) results in an acceleration of the slow phase of the decay, assigned to long lived  $\text{TiO}_2$  electrons, from  $\sim 300$  ms to  $\sim 4$  ms. This decay half-time is similar to that observed for **CoP**/ $\text{TiO}_2$  films in the absence of **RuP** and at a similar **CoP** coverage, indicating that the presence of co-attached **RuP** does not significantly impede electron transfer from  $\text{TiO}_2$  to **CoP**.

## Discussion

The surface functionalisation of semiconductor based photoelectrodes with molecular catalysts is an attractive strategy for solar driven fuel synthesis. This study focuses on the parameters determining the efficiency of electron transfer from the semiconductor to the molecular catalyst, and their potential impact on the overall solar to fuel conversion efficiency, addressing these kinetics for a model system comprising of a **CoP** proton reduction catalyst attached to a nanocrystalline, mesoporous  $\text{TiO}_2$  photoelectrode.

### Competing charge recombination reactions

From a thermodynamic point of view, photoexcited electrons in  $\text{TiO}_2$  could be used for the reduction of protons to hydrogen, while the holes that remain in the valence band could be used for water oxidation. However, in practice rapid recombination (nano- to micro-second) of photogenerated electrons and holes, and slow water oxidation/reduction kinetics prevents significant  $\text{H}_2$  and  $\text{O}_2$  evolution from  $\text{TiO}_2$  photoelectrodes alone.<sup>20</sup> Even in the presence of TEOA, which increases the lifetime of  $\text{TiO}_2$  electrons to 1 s, negligible hydrogen generation is observed, indicating that the rate constant for proton reduction by  $\text{TiO}_2$  electrons must be substantially slower than  $1 \text{ s}^{-1}$  (at least under pH 7).

One strategy to accelerate the kinetics of proton reduction to molecular hydrogen, and to aid the spatial separation of electrons and holes, is the addition of a chemical co-catalyst, such

as the **CoP** employed herein. Such co-catalysts have been shown to substantially increase the photocatalytic activity of this semiconductor towards  $\text{H}_2$  evolution.<sup>23,25</sup> Our studies show that the electron transfer from the  $\text{TiO}_2$  to the cobalt catalyst (**CoP**) indeed substantially retards electron-hole recombination. Fig. 2 indicates hole recombination with reduced **CoP** is at least four orders of magnitude slower than recombination with  $\text{TiO}_2$  conduction band electrons. However such lifetime enhancement is only useful if the electrons are able to transfer to the co-catalyst in the first place. The efficiency of this transfer depends on the rate constant for electron transfer from  $\text{TiO}_2$  to the catalyst relative to any competing pathways – primarily electron recombination with photogenerated holes.

In the presence of monolayer catalyst coverage, electron transfer from  $\text{TiO}_2$  to **CoP** can proceed reasonably fast (half time of  $\sim$  few microseconds). The competing electron-hole recombination reaction depends on density of electrons and holes, and therefore upon the incident light flux. Both processes exhibit highly dispersive kinetics (*i.e.*: spread over a broad range of timescales), indicative of the effects of charge trapping and/or inhomogeneous catalyst binding to the  $\text{TiO}_2$  surface. For low pulsed laser intensities, of most relevant to conditions of continuous solar irradiation, and monolayer catalyst coverage, electron-hole recombination is sufficiently slow to allow photogenerated electrons to avoid electron-hole recombination and efficiently transfer to the **CoP**. At lower catalyst coverages, or higher light fluxes, the efficiency of catalyst reduction is progressively reduced.

### Two electron reduction of **CoP**

The catalytic mechanism of cobaloximes is reported as a sequential two electron transfer process that involves the sequential reduction of  $\text{Co}^{\text{III}}$  species to  $\text{Co}^{\text{II}}$  and  $\text{Co}^{\text{I}}$ , with the reduction potentials of the reactions being  $-0.15$  V and  $-0.55$  V vs. NHE, respectively.<sup>25,35,36</sup> It should be noted that the non-innocent character of diimines could also result in a ligand-based reduction product ( $\text{Co}^{\text{II}}\text{L}^-$ ) instead of  $\text{Co}^{\text{I}}$  after two single-electron reduction steps of **CoP**. From a thermodynamic point of view, the first electron transfer has a larger driving force, and therefore should be faster than the second reduction reaction. Under photoexcitation conditions, we therefore expect the accumulation of  $\text{Co}^{\text{II}}$  species, with the efficiency of molecular hydrogen generation being critically dependent upon achieving the second photoreduction of **CoP** catalyst to  $\text{Co}^{\text{I}}$ .

The discussion in the preceding section was concerned with the efficiency of single electron transfers from  $\text{TiO}_2$  to **CoP**, but did not address this requirement for double reduction of **CoP** to yield molecular hydrogen. Herein, we have addressed this issue by two sets of experiments which varied the ratio of the number of photogenerated electrons per catalyst molecule: (1) varying the amount of catalyst anchored onto the surface for a fixed laser intensity, and (2) modifying the electron density in the film by using different excitation densities for a fixed catalyst coverage (Fig. 5 and 7). Both experiments were done in the presence of TEOA sacrificial electron donor to avoid electron-hole recombination losses, and maximise the lifetime of





photogenerated electrons. In both cases, increasing the ratio of photogenerated electrons per catalyst molecule resulted in a very large delay of the electron transfer timescale (by  $\geq 10^4$ ). Increasing the ratio of photoelectrons/CoP can be expected to increase the proportion of adsorbed CoP being singly reduced to Co<sup>II</sup>. Thus, this delay can be most easily understood as resulting from an increased accumulation of Co<sup>II</sup>, with electron transfer from TiO<sub>2</sub> to Co<sup>II</sup> being at least  $10^4$  fold slower than to Co<sup>III</sup>. We also note the possibility that our observation of slow electron transfer to CoP for high electron density/catalyst ratios could be associated with the accumulation of Co<sup>III</sup>-H states at the surface of TiO<sub>2</sub> or the slow H<sub>2</sub> release. However, these processes have been reported to be relatively fast in an analogous cobaloxime catalyst ( $\mu\text{s}$ - $\text{ms}$ ),<sup>37</sup> indicating that the performance of CoP is most likely to be limited by the kinetics of the second electron transfer when attached to TiO<sub>2</sub> nanoparticles.

The more negative reduction potential for the Co<sup>II</sup>-Co<sup>I</sup> couple relative to Co<sup>III</sup>-Co<sup>II</sup> reduces the thermodynamic driving force for electron transfer from the TiO<sub>2</sub> conduction band. Using a standard Marcus analysis, assuming a TiO<sub>2</sub> conduction band edge of  $-0.6$  eV vs. NHE,<sup>38,39</sup> and a value for the reorganisation energy  $\lambda$  of  $1.0$  eV,<sup>40</sup> the  $0.4$  eV difference in reduction potential can be estimated to result in  $10^5$  slower electron transfer rate constant. This difference in rate constant is consistent with our conclusion that our experimental observation of  $\geq 10^4$  slower electron transfer under conditions of high photoelectron/CoP ratios, where accumulation of Co<sup>II</sup> is expected. Thus, our observations of a kinetically slower step attributed to the second electron reduction of CoP can now explain the relatively low external quantum efficiencies (1%) observed for H<sub>2</sub> evolution with this photocatalytic system.<sup>25</sup>

We note that the reduction potential for Co<sup>II</sup>-Co<sup>I</sup> is close to the TiO<sub>2</sub> conduction band edge, thereby potentially reducing not only the electron transfer rate constant but also the equilibrium constant for this transfer. A complete analysis of this equilibrium constant would require consideration of the TiO<sub>2</sub> Fermi energy and the impact of subsequent proton double reduction and the generation of molecular hydrogen. In particular the latter effect is likely to provide a 'sink' effectively pull the equilibrium forwards. A quantitative analysis of these equilibrium effects is beyond the scope of this study.

Our observation of a  $> 10^4$  delay of electron transfer lifetime under conditions of high photoelectron/CoP ratio indicates that under these conditions, almost all the CoP is in its Co<sup>II</sup> state. In the experiments reported herein, we have employed pulsed laser excitation, at a repetition frequency of  $1$  Hz, at pulse energies corresponding to  $\sim 0.5$ – $10$  absorbed photons per TiO<sub>2</sub> particle. These laser intensities are too low to reduce all the adsorbed CoP to Co<sup>II</sup> from a single laser pulse, indicating this reduction from the accumulated effect of multiple laser pulses. Given our  $1$  Hz repetition frequency, this implies the lifetime of Co<sup>II</sup> species in the presence of TEOA is  $\gg 1$  s.

There are two key conclusions from our analysis above. Firstly, as electron transfer to Co<sup>III</sup> is at least 4 orders of magnitude faster than to Co<sup>II</sup>, significant reduction of Co<sup>II</sup> to Co<sup>I</sup>, enabling hydrogen generation, will only be possible once

almost all the adsorbed CoP has been reduced to Co<sup>II</sup>. This has significant implications for the optimum catalyst loading, Co<sup>II</sup> lifetime and light flux. The second conclusion is that efficient hydrogen generation will require the generation of TiO<sub>2</sub> electrons with sufficient lifetime to reduce not only Co<sup>III</sup> but also Co<sup>II</sup>. This lifetime requirement is relatively facile for Co<sup>III</sup> reduction – at monolayer CoP coverage electron transfer from TiO<sub>2</sub> to Co<sup>III</sup> exhibits a half time of  $\sim 4$   $\mu\text{s}$ , and can thus compete effectively with electron-hole recombination even in the absence of sacrificial electron donors, at least under reasonably low excitation conditions. However electron transfer to Co<sup>II</sup> is kinetically much slower ( $\gg 40$  ms), and therefore places a much more severe requirement on the TiO<sub>2</sub> lifetime required to enable efficient electron transfer to the catalyst. It also increases the potential for long-lived photogenerated electrons to undergo unwanted side reactions (such as the reduction of the products of TEOA oxidation), thereby reducing the efficiency of hydrogen generation.

### The role of hole scavengers and dye sensitisation

The above discussion has all focused on data collected in the presence of the hole scavenger TEOA. Such hole scavengers are typically added to remove photogenerated holes from semiconductor photocatalysts so as to enable photoreduction reactions such as the proton reduction reaction reported herein. The TEOA achieves this very efficiently, scavenging holes in  $< 1$   $\mu\text{s}$ , resulting in the generation of long lived conduction band electrons with lifetimes of  $\sim 1$  s in the absence of CoP.

It is striking that for the system studied herein, in the presence of a CoP monolayer, and employing low excitation densities, single electron transfer from TiO<sub>2</sub> to CoP can proceed efficiently even in the absence of TEOA. In other words, for a sufficiently fast electron transfer rate constant to the adsorbed catalyst (measured as  $\sim 3 \times 10^5$  s<sup>-1</sup> herein for monolayer coverage), this electron transfer can compete reasonably effectively with electron-hole recombination in the TiO<sub>2</sub>. Nevertheless the addition of TEOA is necessary to achieve measureable yields of hydrogen generation.<sup>9,25,41</sup> This can be understood as resulting from two factors. Firstly efficient electron transfer to the catalyst requires near monolayer catalyst coverage, which might be difficult to achieve in the suspension systems typically employed for hydrogen generation measurements. Secondly, and critically, hydrogen generation requires not a single but a double reduction of CoP. The second reduction reaction (Co<sup>II</sup> to Co<sup>I</sup>) is kinetically at least  $10^4$  slower than the first reduction, and therefore is unable to compete with electron-hole recombination in the absence of TEOA. Moreover this double reduction of CoP requires almost complete accumulation of singly reduced CoP (Co<sup>II</sup>) on the TiO<sub>2</sub> surface. In the absence of TEOA, these reduced CoP species would act as recombination sites for photogenerated holes (indeed even in the presence of TEOA, this recombination may be a significant loss pathway).

An attractive way to achieve visible light photoactivity is to employ a molecular sensitiser, such as the RuP dye. The addition of such dyes indeed enables visible light driven hydrogen generation.<sup>42</sup> However it should be noted that the use of such a



sensitiser significantly reduces the thermodynamic driving force available for the hole scavenging or 'regeneration' reaction. It is likely that the much slower kinetics for scavenging of 'holes' from **RuP** relative to  $\text{TiO}_2$  (100  $\mu\text{s}$  versus <1  $\mu\text{s}$  respectively) is associated with less oxidising potential of the **RuP** cations relative to the  $\text{TiO}_2$  valence band. This is offset partly by slower recombination kinetics for **RuP**<sup>+</sup>/ $\text{TiO}_2$  ( $\text{e}^-$ ) versus  $\text{TiO}_2$  ( $\text{h}^+$ )/ $\text{TiO}_2$  ( $\text{e}^-$ ) – half times of ~150  $\mu\text{s}$  versus 50  $\mu\text{s}$  respectively at matched excitation densities. Nevertheless the substantially slower hole scavenging kinetics for the **RuP**/ $\text{TiO}_2$  system results in this hole scavenging achieving (for the system studied herein) a quantum efficiency of only ~50%. This represents an additional efficiency loss not present when employing direct  $\text{TiO}_2$  band gap excitation, although under solar irradiation, this loss is more than offset by the enhanced light harvesting. Additionally, the less efficient hole scavenging by TEOA in the dye sensitised system also contributes in decreasing the yield of the slower electron transfer to the molecular catalyst, resulting in a smaller  $\text{H}_2$  evolution yield.

The use of sacrificial electron donors is clearly undesirable for any technological application, which would require these donors to be replaced by reversible redox couples or hole transport to an external circuit. It is apparent from the above discussion that any such replacement will be very challenging. If a reversible redox couple is employed, the oxidised state of this couple is likely to compete with singly reduced **CoP** as acceptors for  $\text{TiO}_2$  electrons. If hole transport to an external circuit is employed, this will have to be very rapid to prevent hole accumulation in the semiconductor and subsequent recombination with either  $\text{TiO}_2$  electrons or single reduced **CoP** species. As a consequence, such replacements are only likely to be viable in more complex system architectures, including in particular the use of heterojunctions or additional oxidation co-catalysts.

## Conclusions

In this work we explain in detail the kinetics of electron transfer processes that take place in three different molecule-functionalised systems for the photochemical  $\text{H}_2$  evolution, with special emphasis on the parameters that affect the electron transfer from the  $\text{TiO}_2$  to the molecular catalyst. The molecular catalyst employed is a cobaloxime proton reduction catalyst, which requires a two-electron reduction from  $\text{Co}^{\text{III}}$  to  $\text{Co}^{\text{I}}$  for hydrogen generation. We find that the kinetics of electron transfer from  $\text{TiO}_2$  to **CoP**, their competition with electron-hole recombination and the requirement for hole scavenging are very different for the first electron reduction from  $\text{Co}^{\text{III}}$  to  $\text{Co}^{\text{II}}$  versus the second from  $\text{Co}^{\text{II}}$  to  $\text{Co}^{\text{I}}$ . At sufficiently high catalyst coverages, and low excitation densities, the first reduction can proceed efficiently even in the absence of added hole scavenger. In contrast, the second reduction reaction appears to be at least  $10^5$  slower, suggesting it requires efficient hole scavenging and almost complete reduction of all adsorbed **CoP** to  $\text{Co}^{\text{II}}$  for it to proceed. Dye sensitisation enables visible light photoactivity, although this is partly offset by slower, and less efficient, hole scavenging by TEOA.

These results were obtained with a single semiconductor/molecular catalyst system. However, they address an issue likely to be critical to many potential implementations of such semiconductor/molecular catalyst systems, namely the requirement for photogenerated electrons and holes to drive multiple oxidation/reduction reactions on a single catalyst. Addressing this challenge is likely to be critical in developing such hybrid systems for solar driven fuel production.

## Acknowledgements

Financial support from EPSRC (EP/H046380/1 to J.D., EP/H00338X/2 to E.R.), the ERC (project Intersolar to J.D.), the Christian Doppler Research Association (Austrian Federal Ministry of Economy, Family and Youth and National Foundation for Research, Technology and Development) and the OMV Group (to E.R.), the Spanish Ministry of Education (EX2010-0479 to A.R.) and the European Commission Marie Curie CIG (PCIG10-GA-2011-303650 to A.R.) are gratefully acknowledged. The authors thank Dr Xiaoe Li for assistance in  $\text{TiO}_2$  preparation.

## Notes and references

- 1 T. R. Cook, D. K. Dogutan, S. Y. Reece, Y. Surendranath, T. S. Teets and D. G. Nocera, *Chem. Rev.*, 2010, **110**, 6474–6502.
- 2 N. Armaroli and V. Balzani, *Angew. Chem., Int. Ed.*, 2007, **46**, 52–66.
- 3 H. Krassen, S. Ott and J. Heberle, *Phys. Chem. Chem. Phys.*, 2011, **13**, 47–57.
- 4 W. T. Eckenhoff and R. Eisenberg, *Dalton Trans.*, 2012, **41**, 13004–13021.
- 5 M. L. Helm, M. P. Stewart, R. M. Bullock, M. R. DuBois and D. L. DuBois, *Science*, 2011, **333**, 863–866.
- 6 M. Wang, L. Chen and L. Sun, *Energy Environ. Sci.*, 2012, **5**, 6763–6778.
- 7 S. Losse, J. G. Vos and S. Rau, *Coord. Chem. Rev.*, 2010, **254**, 2492–2504.
- 8 J.-F. Capon, F. Gloaguen, P. Schollhammer and J. Talarmin, *Coord. Chem. Rev.*, 2005, **249**, 1664–1676.
- 9 F. Lakadamyali and E. Reisner, *Chem. Commun.*, 2011, **47**, 1695–1697.
- 10 J. M. Gardner, M. Beyler, M. Karnahl, S. Tschierlei, S. Ott and L. Hammarström, *J. Am. Chem. Soc.*, 2012, **134**, 19322–19325.
- 11 J. Huang, K. L. Mulfort, P. Du and L. X. Chen, *J. Am. Chem. Soc.*, 2012, **134**, 16472–16475.
- 12 F. Wen, X. Wang, L. Huang, G. Ma, J. Yang and C. Li, *ChemSusChem*, 2012, **5**, 849–853.
- 13 F. Lakadamyali, M. Kato, N. M. Muresan and E. Reisner, *Angew. Chem., Int. Ed.*, 2012, **51**, 9381–9384.
- 14 N. A. Anderson and T. Lian, *Coord. Chem. Rev.*, 2004, **248**, 1231–1246.
- 15 A. Listorti, B. O'Regan and J. R. Durrant, *Chem. Mater.*, 2011, **23**, 3381–3399.
- 16 A. Reynal, A. Forneli and E. Palomares, *Energy Environ. Sci.*, 2010, **3**, 805–812.



- 17 K. Nakata and A. Fujishima, *J. Photochem. Photobiol., C*, 2012, **13**, 169–189.
- 18 A. L. Linsebigler, G. Lu and J. T. Yates, *Chem. Rev.*, 1995, **95**, 735–758.
- 19 A. Yamakata, T.-a. Ishibashi and H. Onishi, *J. Phys. Chem. B*, 2001, **105**, 7258–7262.
- 20 A. J. Cowan, J. Tang, W. Leng, J. R. Durrant and D. R. Klug, *J. Phys. Chem. C*, 2010, **114**, 4208–4214.
- 21 S. G. Kumar and L. G. Devi, *J. Phys. Chem. A*, 2011, **115**, 13211–13241.
- 22 S. Sato and J. M. White, *J. Phys. Chem.*, 1981, **85**, 592–594.
- 23 P. D. Tran, L. H. Wong, J. Barber and J. S. C. Loo, *Energy Environ. Sci.*, 2012, **5**, 5902–5918.
- 24 J. L. Dempsey, J. R. Winkler and H. B. Gray, *J. Am. Chem. Soc.*, 2009, **132**, 1060–1065.
- 25 F. Lakadamyali, A. Reynal, M. Kato, J. R. Durrant and E. Reisner, *Chem.–Eur. J.*, 2012, **18**, 15464–15475.
- 26 S. A. Trammell, J. A. Moss, J. C. Yang, B. M. Nakhle, C. A. Slate, F. Odobel, M. Sykora, B. W. Erickson and T. J. Meyer, *Inorg. Chem.*, 1999, **38**, 3665–3669.
- 27 S. Ito, T. N. Murakami, P. Comte, P. Liska, C. Grätzel, M. K. Nazeeruddin and M. Grätzel, *Thin Solid Films*, 2008, **516**, 4613–4619.
- 28 B. O'Regan, L. Xiaoe and T. Ghaddar, *Energy Environ. Sci.*, 2012, **5**, 7203–7215.
- 29 J. Tang, J. R. Durrant and D. R. Klug, *J. Am. Chem. Soc.*, 2008, **130**, 13885–13891.
- 30 Y. Tamaki, A. Furube, M. Murai, K. Hara, R. Katoh and M. Tachiya, *Phys. Chem. Chem. Phys.*, 2007, **9**, 1453–1460.
- 31 M. Murai, Y. Tamaki, A. Furube, K. Hara and R. Katoh, *Catal. Today*, 2007, **120**, 214–219.
- 32 J. Nelson, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **59**, 15374.
- 33 R. Katoh, M. Murai and A. Furube, *Chem. Phys. Lett.*, 2008, **461**, 238–241.
- 34 50% was calculated considering that the maximum electron density in TiO<sub>2</sub> was achieved when no CoP was anchored onto the surface.
- 35 N. M. Muresan, J. Willkomm, D. Mersch, Y. Vaynzof and E. Reisner, *Angew. Chem., Int. Ed.*, 2012, **51**, 12749–12753.
- 36 O. Pantani, E. Anxolabéhère-Mallart, A. Aukauloo and P. Millet, *Electrochem. Commun.*, 2007, **9**, 54–58.
- 37 J. L. Dempsey, J. R. Winkler and H. B. Gray, *J. Am. Chem. Soc.*, 2010, **132**, 16774–16776.
- 38 G. Rothenberger, D. Fitzmaurice and M. Graetzel, *J. Phys. Chem.*, 1992, **96**, 5983–5986.
- 39 B. Enright, G. Redmond and D. Fitzmaurice, *J. Phys. Chem.*, 1994, **98**, 6195–6200.
- 40 B. H. Solis and S. Hammes-Schiffer, *Inorg. Chem.*, 2011, **50**, 11252–11262.
- 41 T. R. N. Kutty and M. Avudaitai, *Mater. Res. Bull.*, 1988, **23**, 725–734.
- 42 W. J. Youngblood, S.-H. A. Lee, K. Maeda and T. E. Mallouk, *Acc. Chem. Res.*, 2009, **42**, 1966–1973.

