


CrystEngComm

www.rsc.org/crystengcomm



ROYAL SOCIETY
OF CHEMISTRY

COMMUNICATION

Catherine E. Housecroft et al.

A 3-dimensional $\{4^2\cdot8^4\}$ **lvt** net built from a ditopic bis(3,2':6',3"-terpyridine) tecton bearing long alkyl tails


 Cite this: *CrystEngComm*, 2015, 17, 2070

 Received 27th November 2014,
 Accepted 13th December 2014

DOI: 10.1039/c4ce02347a

www.rsc.org/crystengcomm

Divergent bis(terpyridine) tectons are versatile ligands for the assembly of coordination networks; we demonstrate the assembly of a 3-dimensional $\{4^2\cdot8^4\}$ lvt net (still relatively sparse among 4-connected nets in metal-organic frameworks) from the reaction of 1,4-bis(*n*-octoxy)-2,5-bis(3,2':6',3"-terpyridin-4'-yl)benzene and Co(NCS)₂.


Oligopyridines¹ remain as one of the most widespread building blocks in the toolbox of a coordination chemist. The bis(chelate) 2,2':6',2"-terpyridine (2,2':6',2"-tpy) is especially popular and multitopic ligands containing peripheral 2,2':6',2"-tpy domains² have been used in a wide variety of architectures. 4,2':6',4"-Terpyridine (4,2':6',4"-tpy, Scheme 1) and 3,2':6',3"-terpyridine (3,2':6',3"-tpy, Scheme 1) are less familiar isomers of terpyridine, but in the last decade, the use of 4,2':6',4"-tpy as a building block of coordination polymers has grown significantly.³ In metal complexes of 4,2':6',4"-tpy, the central pyridine ring is non-coordinated and the remaining *N,N'*-donor set presents a divergent domain, with vectorial properties that are unaffected by inter-ring bond rotation (red bonds in Scheme 1). In contrast, rotation about the interannular bonds in 3,2':6',3"-tpy alters its divergent coordination mode.⁴

The beauty of terpyridine metal-binding domains is the ease with which substituents can be introduced into the 4'-position, for example by using Kröhnke's⁵ or Wang and Hanan's⁶ strategies. With coordinatively innocent 4'-substituents, reactions between 4,2':6',4"-terpyridines and metal ions yield metallomacrocycles, 1-dimensional chains or 2-dimensional nets.³ Extension to 3-dimensions is achieved by introducing non-innocent domains such as diphenylphosphino,⁷ carboxylato,⁸

A 3-dimensional $\{4^2\cdot8^4\}$ lvt net built from a ditopic bis(3,2':6',3"-terpyridine) tecton bearing long alkyl tails[†]

Y. Maximilian Klein, Edwin C. Constable, Catherine E. Housecroft* and Alessandro Prescimone

or pyridyl⁹ functionalities, or by using co-ligands.¹⁰ An alternative approach to increase dimensionality is through the coordination capacity of multitopic 4,2':6',4"-tpy ligands, although such compounds have received scant attention.¹¹⁻¹⁴ We have demonstrated that 1,4-bis(*n*-octoxy)-2,5-bis(4,2':6',4"-terpyridin-4'-yl)benzene reacts with ZnCl₂ to give a network consisting of (4,4)-sheets engaging in 2D \rightarrow 2D parallel interpenetration,¹⁴ and a report on a triply interpenetrating network formed between cobalt(II) and 1,3-di((4,2':6',4"-terpyridin-4'-yl)benzene has appeared.¹² We now describe the synthesis of the bis(3,2':6',3"-tpy) ligand 1 (Scheme 1) and its reaction with Co(NCS)₂ to give a 3-dimensional $\{4^2\cdot8^4\}$ lvt net.¹⁵ The inclusion of the long alkoxy chains in 1 enhances the solubility of the ligand with respect to analogues with simple phenylene spacers,¹⁴ and also has a stabilizing influence on an infinite architecture.



Scheme 1 Structures of divergent isomers of terpyridine and the ditopic ligand 1. See text for significance of the bonds marked in red.

Department of Chemistry, University of Basel, Spitalstrasse 51, CH4056 Basel, Switzerland. E-mail: catherine.housecroft@unibas.ch; Fax: +41 61 267 1018; Tel: +41 61 267 1008

† Electronic supplementary information (ESI) available: Synthetic and crystallographic details; Fig. S1-S2 solution ¹H NMR and absorption spectra of 1. CCDC 1035825. See DOI: 10.1039/c4ce02347a



Ligand **1** was synthesized[†] using the one-pot method of Wang and Hanan⁶ starting from 2,5-bis(octoxy)benzene-1,4-dicarbaldehyde and 4.7 equivalents of 3-acetylpyridine in EtOH in the presence of NH₃. Compound **1** was isolated in 41% yield. The electrospray mass spectrum exhibited a base peak at *m/z* 797.8 arising from [M+H]⁺, and ¹H (Fig. S1[†]) and ¹³C NMR spectra (assigned using COSY, DEPT, HMQC and HMBC techniques) were consistent with the symmetrical structure shown in Scheme 1. The absorption spectrum of **1** has broad and intense, high energy bands arising from $\pi^* \leftarrow n$ and $\pi^* \leftarrow \pi$ transitions which extend into the visible region (Fig. S2[†]).

Layering of MeOH and CHCl₃ solutions of Co(NCS)₂ and **1**, respectively, resulted in the formation of pink crystals of [Co(NCS)₂(**1**)-4CHCl₃]_n within 2–4 weeks in 14% yield. The crystal selected for single crystal X-ray diffraction was solved and refined in the non-centrosymmetric space group *Pna*2₁. The Flack parameter of 0.480(10) suggested that it was a twin by inversion¹⁶ as every attempt to either solve or refine the structure in *Pnma* failed and ADDSYM¹⁷ could not identify an alternative space group. The asymmetric unit contains one molecule of **1** and a Co(NCS)₂ unit; the octoxy chain containing atom C19 was refined isotropically and three of the C–C distances were restrained to chemically reasonable values. The cobalt ion is octahedrally coordinated, and **1** binds through the outer *N*-donors to four cobalt centres (Fig. 1), leaving the central nitrogen atoms N2 and N6 uncoordinated. Atom Co1 coordinates to two [NCS][−] ligands in a *trans*-arrangement and to four different **1** ligands in the equatorial plane. The two independent octoxy chains are in non-extended conformation, and each is folded over a 3,2':6',3"-tpy unit with close C–H···π contacts (H···centroid = 3.19 and 3.23 Å for the pyridine rings containing N1 and N4).

Pairs of cobalt atoms are either bridged by a single 4,2':6',4"-tpy (e.g. Co1 and Co1^v in Fig. 1) or by two *N*-donors




Fig. 1 The repeat unit (with symmetry generated Co atoms) in [Co(NCS)₂(**1**)-4CHCl₃]_n (H atoms and solvent molecules are omitted). Symmetry codes: i = 1/2 + x, 1/2 - y, z; ii = -x, 1 - y, -1/2 + z; iii = 1/2 - x, 1/2 + y, 1/2 - z; iv = 1/2 - x, -1/2 + y, 1/2 + z; v = -1/2 + x, 1/2 - y, z; vi = -x, 1 - y, 1/2 + z. Selected bond parameters: Co1-N1 = 2.185(8), Co1-N5iii = 2.212(7), Co1-N4ii = 2.204(8), Co1-N5iii = 2.181(8), Co1-N7 = 2.096(8), Co1-N8 = 2.079(8) Å; Co1-N7-C53 = 161.0(8), Co1-N8-C54 = 151.2(8), N1-Co1-N5iii = 176.2(3), N3i-Co1-N4ii = 178.6(3)°.

from each of the two 4,2':6',4"-tpy domains of **1** (e.g. Co1 and Co1^v in Fig. 1). The latter coordination mode extends to the formation of [2 + 2] metallocamacrocycles (Fig. 2a) which are interlinked through the cobalt centres, as shown in Fig. 2b. The structure propagates into a 2-nodal {4²·8⁴} *lvt* net.¹⁴ The two 4-connected nodes are Co1 and the centroid of the arene spacer in **1**, which are planar and approximately tetrahedral, respectively. Although the local {Co(N_{tpy})₄} domain in [Co(NCS)₂(**1**)-4CHCl₃]_n is square planar (N_{tpy}–Co–N_{tpy} angles = 90.9(3), 89.1(3), 92.9(3) and 87.1(3)°), the cobalt node is distorted in the topological description of the net (centroid–Co–centroid angles = 96.6, 64.6, 132.2 and 67.4°) while remaining planar. Topological representations of the framework in [Co(NCS)₂(**1**)-4CHCl₃]_n are shown in Fig. 3. The view down the *a*-axis in Fig. 3a is directly comparable with the structure in Fig. 2b.

The voids in the net are occupied by the octoxy chains and CHCl₃ molecules. Fig. 4 illustrates that the chains lie in the *ac*-plane, a consequence of the close CH···π contacts between the terminal CH₂CH₃ units of each chain and pyridine rings (see above).

In conclusion, we have shown that, by adopting a conformation in which the two 3,2':6',3"-tpy metal-binding domains




Fig. 2 (a) A [2 + 2] metallocamacrocycle formed from two Co1 atoms and two half-ligands (in orange). (b) Interconnection of metallocamacrocycles with the unit cell viewed down the *a*-axis.




Fig. 3 TOPOS¹⁸ representations of the {4²·8⁴} *lvt* net in [Co(NCS)₂(**1**)-4CHCl₃]_n: (a) view down the *a*-axis for comparison with Fig. 2b, and (b) showing the 4- and 8-membered metallocamacrocycles. Metal nodes, purple; ligand–centroid nodes, green.






Fig. 4 Superimposition of the topological representation of the lvt net in $[\text{Co}(\text{NCS})_2(1)\cdot 4\text{CHCl}_3]_n$ and the structure (H atoms and CHCl_3 molecules are omitted); the octoxy chains of one ligand are shown in the space-filling representation: views down the (a) a -axis and (b) c -axis.

are orthogonal, ligand **1** can combine with a planar 4-connecting metal node to produce a $\{4^2\cdot 8^4\}$ lvt net. Among metal-organic frameworks, the lvt topology is scarce in comparison with other 4-connected nets.¹⁹ The conformational flexibility of ditopic bis(4,2':6',4"-tpy) and bis(3,2':6',3"-tpy) ligands allows the two tpy units to lie on a path between coplanar¹³ and orthogonal (as in the current work), making these isomeric ligands attractive tectons. We are currently developing the coordination chemistry of multitopic 4,2':6',4"-tpy and 3,2':6',3"-tpy ligands to investigate which building blocks favour the assembly of 2- *versus* 3-dimensional networks.

Acknowledgements

We thank the Swiss National Science Foundation (grant 200020_149067), the European Research Council (Advanced grant 267816 LiLo) and the University of Basel for financial support.

Notes and references

- 1 R. P. Thummel, *Comprehensive Coordination Chemistry II*, ed. J. A. McCleverty and T. J. Meyer, Elsevier, Oxford, 2003, vol. 1, p. 41.
- 2 See for example: E. C. Constable, *Chem. Soc. Rev.*, 2007, **36**, 246; E. C. Constable, *Coord. Chem. Rev.*, 2008, **252**, 842; E. C. Constable, A. M. W. Cargill Thompson, P. Harveson, L. Macko and M. Zehnder, *Chem. – Eur. J.*, 1995, **1**, 360; A. Wild, A. Winter, F. Schluetter and U. S. Schubert, *Chem. Soc. Rev.*, 2011, **40**, 1459; Y. Yan and J. Huang, *Coord. Chem. Rev.*, 2010, **254**, 1072; E. C. Constable, *Chimia*, 2013, **67**, 388, and references therein and references therein.
- 3 C. E. Housecroft, *Dalton Trans.*, 2014, **43**, 6594.
- 4 E. C. Constable, C. E. Housecroft, M. Neuburger, S. Vujovic, J. A. Zampese and G. Zhang, *CrystEngComm*, 2012, **14**, 3554.
- 5 F. Kröhnke, *Synthesis*, 1976, **1**.
- 6 J. Wang and G. S. Hanan, *Synlett*, 2005, 1251.
- 7 X. Tan, X. Chen, J. Zhang and C.-Y. Song, *Dalton Trans.*, 2012, **41**, 3616.
- 8 See for example: L. Wen, X. Ke, L. Qiu, Y. Zou, L. Zhou, J. Zhao and D. Li, *Cryst. Growth Des.*, 2012, **12**, 4083; C. Niu, A. Ning, C. Feng, X. Wan and C. Kou, *J. Inorg. Organomet. Polym.*, 2012, **22**, 519; P. Yang, M.-S. Wang, J.-J. Shen, M.-X. Li, Z.-X. Wang, M. Shao and X. He, *Dalton Trans.*, 2014, **43**, 1460; Y.-L. Gai, F.-L. Jiang, L. Chen, Y. Bu, M.-Y. Wu, K. Zhou, J. Pan and M.-C. Hong, *Dalton Trans.*, 2013, **42**, 9954; Y. Li, Z. Ju, B. Wu and D. Yuan, *Cryst. Growth Des.*, 2013, **13**, 4125; F. Yuan, J. Xie, H.-M. Hu, C.-M. Yuan, B. Xu, M.-L. Yang, F.-X. Dong and G.-L. Xue, *CrystEngComm*, 2013, **15**, 1460; F. Yuan, Q. Zhu, H.-M. Hu, J. Xie, B. Xu, C.-M. Yuan, M.-L. Yang, F.-X. Dong and G.-L. Xue, *Inorg. Chim. Acta*, 2013, **397**, 117; H.-N. Zhang, F. Yuan, H.-M. Hu, S.-S. Shen and G.-L. Xue, *Inorg. Chem. Commun.*, 2013, **34**, 51; W. Yang, A. J. Davies, X. Lin, M. Suyetin, R. Matsuda, A. J. Blake, C. Wilson, W. Lewis, J. E. Parker, C. C. Tang, M. W. George, P. Hubberstey, S. Kitagawa, H. Sakamoto, E. Bichoutskaia, N. R. Champness, S. Yang and M. Schröder, *Chem. Sci.*, 2012, **3**, 2992; Y.-Q. Chen, S.-J. Liu, Y.-W. Li, G.-R. Li, K.-H. He, Y.-K. Qu, T.-L. Hu and X.-H. Bu, *Cryst. Growth Des.*, 2012, **12**, 5426; F. Yuan, J. Xie, H.-M. Hu, C.-M. Yuan, B. Xu, M.-L. Yang, F.-X. Dong and G.-L. Xue, *CrystEngComm*, 2013, **15**, 1460.
- 9 J. Heine, J. Schmedt auf der Günne and S. Dehnen, *J. Am. Chem. Soc.*, 2011, **133**, 10018; E. C. Constable, G. Zhang, C. E. Housecroft and J. A. Zampese, *CrystEngComm*, 2011, **13**, 6864; V. N. Dorofeeva, S. V. Kolotilov, M. A. Kiskin, R. A. Polunin, Z. V. Dobrokhotova, O. Cador, S. Golhen, L. Ouahab, I. L. Eremenko and V. M. Novotortsev, *Chem. – Eur. J.*, 2012, **18**, 5006; Y.-Q. Chen, G.-R. Li, Y.-K. Qu, Y.-H. Zhang, K.-H. He, Q. Gao and X.-H. Bu, *Cryst. Growth Des.*, 2013, **13**, 901; C. Liu, Y.-B. Ding, X.-H. Shi, D. Zhang, M.-H. Hu, Y.-G. Yin and D. Li, *Cryst. Growth Des.*, 2009, **9**, 1275; J. Song, B.-C. Wang, H.-M. Hu, L. Gou, Q.-R. Wu, X.-L. Yang, Y.-Q. Shangguan, F.-X. Dong and G.-L. Xue, *Inorg. Chim. Acta*, 2011, **366**, 134; K.-R. Ma, F. Ma, Y.-L. Zhu, L.-J. Yu, X.-M. Zhao, Y. Yang and W.-H. Duan, *Dalton Trans.*, 2011, **40**, 9774; Y.-Q. Chen, G.-R. Li, Z. Chang, Y.-K. Qu, Y.-H. Zhang and X.-H. Bu, *Chem. Sci.*, 2013, **4**, 3678.
- 10 See for example: N. Li, Q.-E. Zhu, H.-M. Hu, H.-L. Guo, J. Xie, F. Wang, F.-X. Dong, M.-L. Yang and G.-L. Xue, *Polyhedron*, 2013, **49**, 207; B.-C. Wang, X.-L. Chen, H.-M. Hu, H.-L. Yao and G.-L. Xue, *Inorg. Chem. Commun.*, 2009, **12**, 856; N. Li, H.-L. Guo, H.-M. Hu, J. Song, B. Xu, M.-L. Yang, F.-X. Dong and G.-L. Xue, *J. Solid State Chem.*, 2013, **198**, 416; B.-C. Wang, Q.-R. Wu, H.-M. Hu, X.-L. Chen, Z.-H. Yang, Y.-Q. Shangguan, M.-L. Yang and G.-L. Xue, *CrystEngComm*, 2010, **12**, 485.
- 11 G. W. V. Cave and C. L. Raston, *J. Chem. Soc., Perkin Trans. 1*, 2001, 3258.
- 12 J. Yoshida, S.-I. Nishikiori and H. Yuge, *J. Coord. Chem.*, 2013, **66**, 2191.
- 13 S. A. S. Ghozlan and A. Z. A. Hassanien, *Tetrahedron*, 2002, **58**, 9423.
- 14 E. C. Constable, C. E. Housecroft, S. Vujovic and J. A. Zampese, *CrystEngComm*, 2014, **16**, 3494.



15 S. R. Batten, S. M. Neville and D. R. Turner, *Coordination Polymers: Design, Analysis and Application*, RSC Publishing, Cambridge, 2009.

16 H. D. Flack, *Helv. Chim. Acta*, 2003, **86**, 905.

17 A. L. Spek, *J. Appl. Crystallogr.*, 2003, **36**, 7.

18 V. A. Blatov and A. P. Shevchenko, *TOPOS Professional v. 4.0*, Samara State University, Russia.

19 D.-S. Li, Y.-P. Wu, J. Zhao, J. Zhang and J. Y. Lu, *Coord. Chem. Rev.*, 2014, **261**, 1.

