CrossMark
click for updatesCite this: *RSC Adv.*, 2015, 5, 53776

The effect of CO₂ on the CVD synthesis of carbon nanomaterials using fly ash as a catalyst†

Nomso Hintsho,^{ab} Ahmed Shaikjee,^a Pranav K. Tripathi,^b Paul Franklyn^{ab}
and Shane Durbach^{*ab}

The efficient use of fly ash is a worldwide issue due to its high production and harmful effects on the environment. In this work the synthesis of carbon nanomaterials (CNMs) via the chemical vapour deposition (CVD) method, using fly ash as a catalyst and CO₂ as an alternate carbon source, was investigated. Here CO₂ was employed in three different ways: (1) as a sole carbon source, (2) as an additive to C₂H₂ and (3) as a carbon source prior to the reaction of C₂H₂ with fly ash. SEM, TEM and laser Raman spectroscopy confirmed that CNMs were formed in all three cases. In the first case, when CO₂ was used as a sole carbon source, CNMs were formed in low yields with a considerable amount of amorphous carbon. However, in the second case when CO₂ was used as an additive to C₂H₂, a drastic increase in CNM formation was observed. In both cases optimal yields were observed at 600 °C. However in the third case, when CO₂ was used as a carbon source prior to the reaction with C₂H₂, uniform-sized nanofibers of the highest yields of all three cases were formed. Likewise these CNMs were found to be the most thermally stable. Hence this study has shown that the use of waste materials such as fly ash as a catalyst and CO₂ as a carbon source prior to the reaction with C₂H₂, results in a very simple and cost efficient process to make uniformly shaped, thermally stable CNMs.

Received 16th April 2015

Accepted 28th May 2015

DOI: 10.1039/c5ra06892d

www.rsc.org/advances

Introduction

Since the rediscovery of carbon nanomaterials (CNMs) in 1991, their production has been found to be a costly exercise. This is mainly due to the catalysts used and the carbon sources.¹ In order to remediate this researchers across the world have tried to find more efficient and cheaper ways of synthesizing CNMs (e.g. carbon nanotubes (CNTs) and carbon nanofibres (CNFs)).^{2–5} At present, three methods are widely used for such syntheses: laser ablation, arc-discharge and chemical vapour deposition (CVD).^{5–11} CVD is the most widely used of these techniques due to its high product yield, selectivity and scale-up capabilities.¹² During CVD, a gas phase carbon rich molecule (e.g. C₂H₂) is pyrolysed in the presence of a transition metal catalyst (e.g. Fe, Mo, Cu, Co, etc.) at high temperatures (800–1000 °C).¹³ Though hydrocarbons are widely used, they do offer some disadvantages, as they are mostly hazardous and can form polyaromatic by-products during a CVD synthesis process.

CO₂ is a low energy molecule that is found in abundance on the earth.¹⁴ Due to its relative cheapness and availability, the

search for uses of CO₂ has attracted a lot of attention. The need to do this has been heightened by the current problems of global warming that face society and the impending shortage of fossil fuels. Recently when researchers used CO₂ as an alternative carbon source for CNT production, results showed that parameters such as high pressures, specific temperature ranges, high flow rates and the choice of catalyst support played a very important role.^{15–18} In one study, when FeO was used on a support of CaO, CNTs were formed.¹⁴ However, when Al₂O₃, SiO₂ and MgO were used as supports, no CNTs were produced.¹⁸ Unfortunately this approach still suffers from low CNT yields and high energy consumption due to the very high carbonization temperatures that are required. These conditions regrettably tend to be unsuitable for such approaches to be scaled up.

Recent studies have shown that an addition of a small amount of an oxygen containing species to the carbon source (e.g. C₂H₂) improves the yield of CNMs.¹⁹ For example, the addition of oxygen which has been shown to act as a scavenger of hydrogen radicals, has provided conditions that were suitable for CNM synthesis. On the other hand the addition of water, which acts as an etching agent that prevents the encapsulation of catalyst particles by amorphous carbon, increased the CNT yield, extended lifetime of the catalyst and an enhanced the initial growth rate as compared to those of classical C₂H₂ decomposition reactions.²⁸

Fly ash is an inorganic waste material generated from the burning of coal in the production of electricity. It is an

^aDST-NRF Centre of Excellence in Strong Materials, University of the Witwatersrand (Wits), Private Bag X3, Johannesburg 2050, South Africa. E-mail: Shane.Durbach@wits.ac.za

^bMolecular Sciences Institute, School of Chemistry, University of the Witwatersrand (Wits), Private Bag X3, Johannesburg, 2050, South Africa

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c5ra06892d

heterogeneous material with a variable composition depending on its source and the processes used. It is mainly composed of Al_2O_3 , SiO_2 and other materials such as Fe_2O_3 , MgO and CaO .²⁰ Disposal of this material has become a major issue due to the expense. In recent years, owing to the transition metal content in fly ash, this waste material has been at the forefront of CNM (in particular CNT/CNF) synthesis.^{12,13,20,21} In recent years, owing to the transition metal content in fly ash, this waste material has been at the forefront of CNM (in particular CNT/CNF) synthesis.^{12,13,20,21} In particular, Dunens *et al.* have shown that CNTs and CNFs could be synthesised by reaction of acetylene and Australian coal fly ash.¹³ However, unlike in this present study where no pre-treatment of the South African fly ash was required, Dunens *et al.* were required to further impregnate their fly ash with iron before these materials could be synthesised.¹³ To date, no study has reported on the use of as-received fly ash as a catalyst with CO_2 as a carbon source for CNM formation. Likewise the use of fly ash, CO_2 and C_2H_2 in one system for CNM formation has also not been reported.

This paper reports on the utilisation of two waste products, namely: fly ash and CO_2 to produce CNMs. It further demonstrates the use of fly ash as a catalyst and CO_2 as an additive or as a carbon source prior to the reaction with C_2H_2 improved the yields of CNMs, in the CVD synthesis method.

Experimental

Synthesis

Waste South African coal fly ash was obtained from the Electricity Supply Commission (ESCOM) Research and Innovation Centre (Rosherville, South Africa) and was used without any chemical pre-treatments or thermal modifications. Carbon depositions were achieved by CVD reactions of: (1) only CO_2 , (2) CO_2 together with C_2H_2 (*i.e.* $\text{CO}_2/\text{C}_2\text{H}_2$) or (3) CO_2 followed by C_2H_2 (*i.e.* $\text{CO}_2\text{-C}_2\text{H}_2$) over the waste coal fly ash. An horizontal CVD furnace was used which had been fabricated in the School of Chemistry, University of the Witwatersrand, as reported previously.²⁰ In these reactions, coal fly ash was used as a catalyst, CO_2 and C_2H_2 were used as the carbon sources and hydrogen as the carrier gas, in order to create an optimal reaction environment.^{21–23} In each synthesis run, 500 mg of fly ash was uniformly spread in a quartz boat and placed in the centre of a horizontal tube furnace. The fly ash was then heated at $10^\circ\text{C min}^{-1}$ in H_2 at a flow rate of 100 ml min^{-1} to temperatures between 500°C and 1000°C . In the cases of using only CO_2 or CO_2 together with C_2H_2 , these gases were introduced into the reaction zone at 100 ml min^{-1} for 30 min after the set temperature for reaction was reached. After 30 min of reaction time, the flows of CO_2 and $\text{CO}_2/\text{C}_2\text{H}_2$ were terminated and the reactor was cooled under H_2 to ambient temperature. For the case where CO_2 was used as carbon source prior to the reaction with C_2H_2 , the procedure followed was the same as before except that CO_2 was introduced on its own at the set reaction temperature for 30 min, then the reaction chamber was flushed out using H_2 for 15 min, followed by the introduction of C_2H_2 into the reaction chamber for 30 min. The reactor was then cooled as before. The resultant carbonaceous material was then

harvested for characterization. The percentage yield of carbon material that was formed was calculated based upon the mass of carbon obtained relative to the mass of catalyst.

Characterization

The chemical composition of fly ash was determined using X-ray fluorescence spectroscopy (S1). The morphology and particle size of the CNMs formed from these reactions were characterized by scanning electron microscopy at an applied voltage of 10 kV using an FE-SEM ZEISS SIGMA equipped with an In-lens and secondary electron detectors and transmission electron microscopy (TEM) using a FEI Tecnai G2 Spirit electron microscope at an accelerating voltage of 120 kV. For SEM analysis, carbon tape was placed on top of a specimen holder and a small representative amount of fine powder was dusted onto the tape. The specimen then was introduced into the SEM instrument. For TEM analysis, a small amount of the powder samples of CNFs were diluted in 10 ml of ethanol, followed by sonification for 5 min. Specimens were then transferred onto the holey carbon film double layered 400 mesh copper grids (sample holder) and allowed to dry at room temperature. The specimens were then characterized by TEM.

To confirm the formation of CNFs, laser Raman spectra were measured using an InVia Raman microscope (Reinshaw) at an excitation wavelength of 514 nm. Powder X-ray diffraction (PXRD) was used to identify the crystalline phases present in the ash and products using a Bruker D2 phaser with a Lynxex detector using a $\text{Co-K}\alpha$ at 30 kV and 10 mA. The thermal stabilities of the products through reaction with fly ash were determined by using a Perkin Elmer Pyris 1 thermogravimetric analyser. In these measurements, 10 mg samples were heated to 900°C at a rate of $10^\circ\text{C min}^{-1}$ under air (20 ml min^{-1}).

Results and discussion

A summary of the different approaches of using CO_2 as well as the various outcomes (to be discussed in further detail later on) is shown in Fig. 1.

CO_2 as a carbon source

The morphologies of the products from the CO_2 treated fly ash are shown in Fig. 2(a–d). These images show that various kinds

Fig. 1 Synthesis of CNMs using CO_2 as a sole carbon source, as an additive and as a carbon source prior to the reaction with C_2H_2 .

of amorphous carbon had been formed. In some cases particles exhibited spherical shapes (Fig. 2(c)) and in others irregular ones (Fig. 2(d)). These differences in the amorphous carbon could possibly be due to the various mechanisms of fly ash formation or due the incomplete oxidation of the precursor coal.²⁴

The as-received fly ash and CO₂ reacted fly ash were analysed by SEM (Fig. 3(a and b)). Fig. 3(a) shows the spherical shape of the as-received fly ash, while Fig. 3(b) shows the CO₂ reacted fly ash. Laser Raman confirmed the presence of both amorphous and graphitic carbon, as shown by a high D (disordered) peak and a low G (graphitic) peak Fig. 3(c).²⁵ The presence of the high D peak indicated that the carbon products that formed were poorly graphitised.¹⁶

When as-received fly ash was used as a catalyst it was found that the very low yields of nanocarbon materials were formed at 900 °C, while at temperatures between 500–800 °C and above 1000 °C, only irregularly shaped amorphous carbon materials were formed. This is in contrast to other studies where CO₂ was used as a sole carbon source and CNTs were formed.^{15–18} In those studies iron and cobalt were used as catalysts. The lack of CNT formation in this study could have been caused by the large quantities of Al₂O₃, SiO₂ and MgO found in the fly ash.^{19,20} On the other hand, it is possible that the rate of carbon supply exceeded the growth rate of CNTs, since this has been shown to result in the formation of amorphous carbon and fibers as compared to tubes.¹³ Our results, in a similar manner to Xu *et al.*¹⁸ have revealed that the reduction of CO₂ to graphitic CNMs is sensitive to both the catalyst and the temperature used. This work, together with other studies, has shown that more research is still required to understand the growth of CNMs from CO₂ as a sole source of carbon.

Fig. 2 TEM images of various amorphous carbon materials grown at 900 °C showing (a) sheet-like material, (b) sphere-like materials, (c) carbon with metal particles and (d) Amorphous carbon with what appears to be unreacted fly ash.

Based on the difficulties experienced in using CO₂ as a sole carbon source for CNT formation, Magrez *et al.*¹⁹ attempted a triple point junction reaction, where CO₂, C₂H₂ and the FeO metal catalyst were all used in one reaction. This was done in an effort to increase the yield and favour the production of more CNTs at lower temperatures. While their study found a dramatic increase in the yield of CNTs, it was also found that this decreased at higher temperatures. In another study using Fe/MgO as a catalyst, ethanol as a carbon source and acetonitrile as a nitrogen source, a similar trend was reported.²⁶ Here this effect was attributed to the O₂ containing species which were believed to oxidise the carbon at higher temperatures. Similarly it is known that the etching effect of OH radicals disrupts the initiation stage of CNT growth.²⁹ In this present study the reaction temperatures employed were from 500 °C to 700 °C, using as-received fly ash as a catalyst and CO₂ as an additive to C₂H₂, which was the main carbon source.

CO₂ as an additive to C₂H₂

When CO₂ was employed as an additive to C₂H₂, the results obtained indicated that there was a three-fold increase in the yield in carbonaceous materials formed from 500 °C to 600 °C, which then remained constant at 700 °C. Laser Raman spectroscopy conducted on these products (Fig. 4(c)) showed that the I_G/I_D ratio increased as the reaction temperature was increased. This suggested that the degree of ordered carbon increased as the reaction temperature was increased.

Fig. 3 SEM images of (a) as-received fly ash, (b) carbon materials grown at 900 °C (c) laser Raman of CNMs formed at 900 °C.

Fig. 4 (a) Percentage yields of CNMs produced (b) Raman spectra of CNMs grown between 500–700 °C and (c) I_D/I_G ratios of CNMs.

TGA was conducted on all of these products to test their thermal stability. As shown in Fig. 5(a), the percentage of carbonaceous products formed from the fly ash increased from 500 °C to 600 °C and then remained relatively constant at 700 °C. This trend was consistent with that of the percentage yields, as noted in Fig. 4(a).

Likewise the increase of the first weight derivative Fig. 5(b) to higher temperatures as the reaction temperature was increased (*i.e.* from *ca.* 600 °C to 640 °C), suggested an increase in the amounts of graphitic materials. This coincided with a corresponding decrease in the I_G/I_D ratio (Fig. 4(c)) and a shift from straight fibres of various diameters at 500 °C and 600 °C (Fig. 6(a–d)) to straight and coiled fibres at 700 °C (Fig. 6(e–f)). Similarly, as the graphitic nature of these materials increased it was observed that their surface areas also increased (Fig. 5(c)). Based upon the adsorption/desorption data, a type III hysteresis loop was observed, which corresponded to a material with non-porous structures.

Unlike in the previous case where CO₂ was used as the sole carbon source, it was noted that upon reaction between the two gases a popping noise was heard which became increasingly louder as the reaction temperature was increased. This was most likely due to the presence of the oxygen containing species (*i.e.* CO₂) reacting with the hydrocarbon in the presence of the fly ash catalyst.²⁷ A previous study has shown that at least two types of reactions (eqn (1) and (2)) occurred when CO₂ and C₂H₂ were co-reacted for CNT synthesis:¹⁹

here it was found that the type of catalyst with support, as well as the reaction temperature used played a huge role in terms of

the materials that were produced. Undoubtedly, the formation of carbon from the side reactions between CO₂ and C₂H₂ (eqn (1) and (2)) must have played a role in the dramatic increase in the percentage yield that was observed from 500 °C to 600 °C.

CO₂ as a carbon source prior to C₂H₂

To avoid these potentially dangerous reactions from occurring, a further study was conducted where CO₂ was introduced into the reaction zone on its own first. CO₂ was then flushed out with H₂ for 15 min. This was then followed by the introduction of C₂H₂. These reactions (as described previously) were also carried out in the temperature range between 500 °C to 700 °C.

In Fig. 7(a), it can be observed that regularly and irregularly shaped carbon nanofibers were formed when subjected to CO₂ and then C₂H₂. Small amounts of CNTs were also observed among the products. In Fig. 7(b) well-defined uniform CNFs, with a narrow particle size range, were observed. In Fig. 7(c), carbon nanofibers of various diameters were observed together with agglomerations of materials, which may have been caused by the sintering of the fly ash catalyst during the reaction.

As before the yields of CNMs formed revealed a slight increase at 500 °C with the use of CO₂ as a carbon source prior to the reaction with C₂H₂ as compared to when CO₂ was used as an additive. On the other hand, at 600 °C the yield increased to 49%, which was an increase of about 17% by comparison when CO₂ was used as an additive with C₂H₂. Unlike when CO₂ was used as an additive, in this case when the temperature was

Fig. 5 (a) TGA profile, (b) weight loss derivative, (c) adsorption isotherms and (d), Table 1: BET surface area and pore volumes of CNMs grown between 500–700 °C.

Fig. 6 TEM and SEM images of CNF/Ts formed (a and b) 500 °C, (c and d) 600 °C and (e and f) 700 °C. The block gives the size of the scale bar.

Fig. 7 TEM images of CNF/Ts formed (a) 500 °C, (b) 600 °C and (c) 700 °C.

increased to 700 °C the percentage yield of the CNMs decreased (Fig. 8(a)). This also corresponded with an increase in the crystallinity of the fly ash from 500 °C to 700 °C as observed in Fig. 8(b). The reduction in the percentage yield may either have been caused by sintering at 700 °C or by the presence of an oxygen species (*i.e.* CO₂) which has previously been shown to limit the growth of CNMs at higher temperatures.¹⁹

The thermal stabilities of the CNMs formed at the various temperatures are displayed in Fig. 9(a). As was the trend with the percentage yields (Fig. 8(a)), the percentage of carbonaceous products formed from the fly ash increased from 500 °C to 600 °C and then decreased at 700 °C. However, the first weight derivative (Fig. 9(b)) increased as the reaction temperature was

Fig. 9 (a) Thermal decomposition (b) weight loss derivative, (c) laser Raman spectra and I_G/I_D ratio of CNF products from fly ash exposed to CO₂ and then C₂H₂ at 500–700 °C.

increased, which suggested an increase in the amounts of graphitic materials. As might have been expected from the uniformity of the CNMs formed using CO₂ in this way at 600 °C (Fig. 7(b)), these materials had the highest I_G/I_D ratio of all the materials formed in all three cases and under all three temperatures (Fig. 9(c) and (d)).

Conclusions

In this study a CVD method of producing CNMs over fly ash as a catalyst by using CO₂ as a sole carbon source, an additive and a carbon source prior to the reaction with C₂H₂ was presented. Here it was shown that using CO₂ as a sole carbon source, gave low yields and poorly formed materials, which was consistent with similar studies. When CO₂ was used as either an additive or a carbon source prior to the reaction with C₂H₂ the yield of CNMs formed increased drastically between 500 °C and 600 °C. However, only in the case where the fly ash catalyst was pre-reacted with CO₂ and then C₂H₂, were the highest yields of carbon nanofibers formed which were more uniformly sized and more graphitic at 600 °C. Finally, this study has shown that the use of two waste materials, fly ash and CO₂ (together with C₂H₂) can be used to cost effectively synthesise CNMs.

Acknowledgements

This work is based on the research supported in part by the National Research Foundation of South Africa (Grant number 88076), ESCOM and the DST-NRF Centre of Excellence in Strong Materials at the University of the Witwatersrand. The authors would also like to thank the Electron and Microscopy Unit (EMU) at the University of the Witwatersrand for TEM analysis.

Fig. 8 (a) Percentage yields of CNMs produced and (b) PXRD diffractograms of the raw fly ash and the CNMs that were formed from 500–700 °C.

Notes and references

- 1 S. Iijima and T. Ichihashi, *Jpn. J. Appl. Phys.*, 1993, **32**, L107–L109.
- 2 P. J. Harris and P. J. Harris, *Carbon nanotube science: synthesis, properties and applications*, Cambridge University Press, 2009.
- 3 M. Terrones, W. K. Hsu, H. W. Kroto and D. R. Walton, in *Fullerenes and related structures*, Springer, 1999, pp. 189–234.
- 4 H.-S. P. Wong and D. Akinwande, *Carbon nanotube and graphene device physics*, Cambridge University Press, 2011.
- 5 S. Bhaviripudi, E. Mile, S. A. Steiner, A. T. Zare, M. S. Dresselhaus, A. M. Belcher and J. Kong, *J. Am. Chem. Soc.*, 2007, **129**, 1516–1517.
- 6 A. M. Cassell, J. A. Raymakers, J. Kong and H. Dai, *J. Phys. Chem. B*, 1999, **103**, 6484–6492.
- 7 A. Peigney, P. Coquay, E. Flahaut, R. E. Vandenberghe, E. De Grave and C. Laurent, *J. Phys. Chem. B*, 2001, **105**, 9699–9710.
- 8 E. Couteau, K. Hernadi, J. W. Seo, L. Thien-Nga, C. Mikó, R. Gaal and L. Forro, *Chem. Phys. Lett.*, 2003, **378**, 9–17.
- 9 A.-C. Dupuis, *Prog. Mater. Sci.*, 2005, **50**, 929–961.
- 10 S. Sharma and S. Lakkad, *Surf. Coat. Technol.*, 2009, **203**, 1329–1335.
- 11 M. H. Rummeli, F. Schäffel, A. Bachmatiuk, D. Adebimpe, G. Trotter, F. Bornert, A. Scott, E. Coric, M. Sparing and B. Rellinghaus, *ACS Nano*, 2010, **4**, 1146–1152.
- 12 N. Salah, S. S. Habib, Z. H. Khan, A. Memic and M. N. Nahas, *Dig. J. Nanomater. Bios.*, 2012, **7**, 1279–1288.
- 13 O. M. Dunens, K. J. MacKenzie and A. T. Harris, *Environ. Sci. Technol.*, 2009, **43**, 7889–7894.
- 14 G. Ordorica-Garcia, M. Nikoo, M. Carbo and I. Bolea, *J. Can. Pet. Technol.*, 2012, **51**, 362–375.
- 15 M. Motiei, Y. R. Hacohen, J. Calderon-Moreno and A. Gedanken, *J. Am. Chem. Soc.*, 2001, **123**, 8624–8625.
- 16 Z. Lou, Q. Chen, W. Wang and Y. Zhang, *Carbon*, 2003, **41**, 3063–3067.
- 17 Z. Lou, C. Chen, H. Huang and D. Zhao, *Diamond Relat. Mater.*, 2006, **15**, 1540–1543.
- 18 X.-J. Xu and S.-M. Huang, *Mater. Lett.*, 2007, **61**, 4235–4237.
- 19 A. Magrez, J. W. Seo, V. L. Kuznetsov and L. Forró, *Angew. Chem., Int. Ed.*, 2007, **119**, 445–448.
- 20 N. Hintsho, A. Shaikjee, H. Masenda, D. Naidoo, D. Billing, P. Franklyn and S. Durbach, *Nanoscale Res. Lett.*, 2014, **9**, 1–11.
- 21 Z. Yu, D. Chen, B. Tøtdal and A. Holmen, *Mater. Chem. Phys.*, 2005, **92**, 71–81.
- 22 A. V. Melechko, V. I. Merkulov, T. E. McKnight, M. Guillorn, K. L. Klein, D. H. Lowndes and M. L. Simpson, *J. Appl. Phys.*, 2005, **97**, 041301–041339.
- 23 D. L. Plata, E. R. Meshot, C. M. Reddy, A. J. Hart and P. M. Gschwend, *ACS Nano*, 2010, **4**, 7185–7192.
- 24 S. Ikeda, K. Tachi, Y. H. Ng, Y. Ikoma, T. Sakata, H. Mori, T. Harada and M. Matsumura, *Chem. Mater.*, 2007, **19**, 4335–4340.
- 25 S. K. Yadav, S. S. Mahapatra, H. J. Yoo and J. W. Cho, *Nanoscale Res. Lett.*, 2011, **6**, 122.
- 26 P. Ayala, A. Grüneis, C. Kramberger, M. Rummeli, I. Solorzano, F. Freire Jr and T. Pichler, *J. Chem. Phys.*, 2007, **127**, 184709.
- 27 G. Bepete, Z. N. Tetana, S. Lindner, M. H. Ruemmeli, Z. Chiguvare and N. J. Coville, *Carbon*, 2013, **52**, 316–325.
- 28 K. Hata, T. Yamada, K. Mizuno, M. Yumura and S. Iijima, *Science*, 2004, **306**, 1362.
- 29 K. Mackenzie, O. Dunens and A. Harris, *Ind. Eng. Chem. Res.*, 2010, **49**(11), 5323–5338.