


 Cite this: *RSC Adv.*, 2015, 5, 72069

DOI: 10.1039/c5ra90078f

www.rsc.org/advances

Correction: Solution based rapid synthesis of AgCuO₂ at room temperature

 Nagarajan Padmavathy,^a Rajagopalan Vijayaraghavan^{*a} and Giridhar U. Kulkarni^b

 Correction for 'Solution based rapid synthesis of AgCuO₂ at room temperature' by Nagarajan Padmavathy *et al.*, *RSC Adv.*, 2014, 4, 62746–62750.

The authors regret that errors were made in the interpretation of XPS results (Fig. 7 in the original article) and in the conclusions of the original article.

The sentence beginning "Cu 2p_{3/2} spectrum (Fig. 7c)..." in the **Results and Discussion** section of the original article should be replaced with the following: "Cu 2p_{3/2} spectrum (Fig. 7c) shows a peak at 933.8 eV and a shoulder at 934.7 eV, indicating the presence of Cu²⁺ and Cu³⁺ respectively. However, the assignment of Cu³⁺ is not certain, as the XPS signal of Cu³⁺ could be ambiguous".

Furthermore, the sentence beginning "The present study has significance..." in the **Conclusions** section of the original article should be replaced with the following: "The present study has significance as AgCuO₂ is an interesting material with low band gap and more importantly, with Cu *partly* in the unusual 3+ state".

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

^aCentre for Excellence in Nano Materials, Materials Chemistry Division, School of Advanced Sciences, VIT University, Vellore, Tamil Nadu 632 014, India. E-mail: rviayaraghavan@vit.ac.in

^bChemistry & Physics of Materials Unit and Thematic Unit on Nanochemistry, Jawaharlal Nehru Centre for Advanced Scientific Research, Jakkur, Bangalore 560 064, India

