

## CORRECTION

[View Article Online](#)  
[View Journal](#) | [View Issue](#)



Cite this: *J. Mater. Chem. A*, 2015, **3**, 12558

DOI: 10.1039/c5ta90117k

[www.rsc.org/MaterialsA](http://www.rsc.org/MaterialsA)

## Correction: Effects of the fabrication process on the grain-boundary resistance in $\text{BaZr}_{0.9}\text{Y}_{0.1}\text{O}_{3-\delta}$

S. Ricote,<sup>\*a</sup> N. Bonanos,<sup>b</sup> A. Manerbino,<sup>c</sup> N. P. Sullivan<sup>a</sup> and W. G. Coors<sup>c</sup>

Correction for 'Effects of the fabrication process on the grain-boundary resistance in  $\text{BaZr}_{0.9}\text{Y}_{0.1}\text{O}_{3-\delta}$ ' by S. Ricote *et al.*, *J. Mater. Chem. A*, 2014, **2**, 16107–16115.

The conductivity values at 600 °C of SSR-Ni and SSRS in Table 4 of the manuscript are incorrect. The correct values are included in the revised table below.

Table 4 Conductivity in ( $\text{mS cm}^{-1}$ ) of BZY10 in moist reducing atmosphere at 500 and 600 °C from this work and literature

Synthesis	Sintering	Total conductivity 600 °C	Total conductivity 500 °C	Atmosphere	Ref.
Solid state reaction	5 h 1800 °C	1.8	—	$\text{H}_2$ , $1.7 \times 10^3 \text{ Pa H}_2\text{O}$	6
Solid state reaction	30 h 1715 °C	0.8	—	4% $\text{H}_2$ , moist	40
Flash combustion	1500 °C	2.2	—	$\text{N}_2$ , 3% $\text{H}_2\text{O}$	41
Pechini process	10 h 1600 °C	0.8	0.55	$\text{N}_2$ , 20.65 h Pa $\text{H}_2\text{O}$	42
Solid state reaction	1700 °C	—	0.55	5% $\text{H}_2$ , moist	30
Solid state reaction	10 h 1750 °C	~6	~4	$\text{H}_2$ , 1.9 kPa $\text{H}_2\text{O}$	43
SPS	5 min 1700 °C	2.32	1.4	5% $\text{H}_2$ , 0.03 atm $\text{H}_2\text{O}$	This work
HT	2200 °C	3.43	1.7	5% $\text{H}_2$ , 0.03 atm $\text{H}_2\text{O}$	This work
SSR-Ni	12 h 1600 °C	2.7	1.1	5% $\text{H}_2$ , 0.03 atm $\text{H}_2\text{O}$	This work
SSRS	5 h 1535 °C	3.0	1.6	5% $\text{H}_2$ , 0.03 atm $\text{H}_2\text{O}$	This work

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

<sup>a</sup>Colorado Fuel Cell Center, Mechanical Engineering Dept, 1500 Illinois Street, Golden, CO 80401, USA. E-mail: sricote@mines.edu; Tel: +1 303 384 2091

<sup>b</sup>Department of Energy Conversion and Storage, Danish Technical University, Frederiksbergvej 399, 4000 Roskilde, Denmark

<sup>c</sup>Coorstek Inc., 600 9th Street, Golden, CO 80401, USA