 Cite this: *Phys. Chem. Chem. Phys.*,
2016, 18, 3359

Correction: The impact of doping rates on the morphologies of silver and gold nanowires grown in helium nanodroplets

 Alexander Volk,^a Philipp Thaler,^a Daniel Knez,^b Andreas W. Hauser,^{*a}
Johannes Steurer,^a Werner Grogger,^b Ferdinand Hofer^b and Wolfgang E. Ernst^{*a}

DOI: 10.1039/c5cp90229k

www.rsc.org/pccp

 Correction for 'The impact of doping rates on the morphologies of silver and gold nanowires grown in helium nanodroplets' by Alexander Volk et al., *Phys. Chem. Chem. Phys.*, 2016, DOI: 10.1039/c5cp06248a.

Due to a unit conversion error, the authors would like to correct the values for t_{trap} given in Table 2 of the published article, as seen in the amended Table below.

Table 2 Time t_{trap} until particles get trapped by a vortex due to the attractive force given by eqn (6) and (7). $d_{\text{D},\alpha}$ is calculated assuming an initial He_N size of $N = 1.7 \times 10^{10}$ atoms. $\bar{s}$ is calculated using eqn (8) and $d_{\text{D},\alpha}$

Element	α	d_{D}/nm	$t_{\text{trap}}/\mu\text{s}$
Ag	0.75	720	24
	0.2	1060	52
Au	0.75	720	33
	0.2	1060	71
	0.04	1130	80

These changes of t_{trap} affect some of the statements in the published article. Most notably, t_{trap} is now shorter than the pickup process that takes place over the length of the pickup cell. The so-called pickup time just means that during 130 μs new atoms are added. At first sight, one is tempted to assume a more complex growth process due to simultaneous effects of doping, cluster formation, and vortex trapping. However, this is not the case, since cluster formation times are still shorter than vortex trapping times t_{trap} . In our cluster growth model following eqn (2) and (3) of the article, metal clusters of 100 atoms for light doping ($\alpha = 0.2$) and 1000 atoms for heavy doping ($\alpha = 0.75$) have formed already within $\approx 1 \mu\text{s}$ after pickup. The size distribution in Fig. 7 obtains its final shape very quickly and the changes between 30 μs (red curve) and 150 μs (orange curve) reflect only the subsequent growth due to atoms added over the 130 μs pickup time. Most of the 'newcomers' will become embedded into that stable cluster size distribution before they are getting trapped in a vortex (compare the envelopes at 130 μs (green curve) and 150 μs in Fig. 7 of the main article). A slight shift of the maximum in the distribution functions towards larger particles with increasing time stems from the higher collision rates which occur due to the reduction of the droplet volume *via* He evaporation.

Due to this fact, the final morphology of most particles is still determined before they get captured by vortices. Our conclusions on the morphologies of the nanowires remain the same and are in agreement with the experimental results observed in the HRTEM pictures.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

^a Institute of Experimental Physics, Graz University of Technology, Petersgasse 16, A-8010 Graz, Austria. E-mail: andreas.w.hauser@gmail.com, wolfgang.ernst@tugraz.at; Fax: +43 (316) 873 108140; Tel: +43 (316) 873 8157, +43 (316) 873 8140

^b Institute for Electron Microscopy and Nanoanalysis & Graz Centre for Electron Microscopy, Graz University of Technology, Steyrergasse 17, A-8010 Graz, Austria