

Showcasing collaborative research from the R. A. Fischer and R. Gläser labs at Ruhr-University Bochum, Technical University Munich and University of Leipzig.

Simultaneous introduction of various palladium active sites into MOF via one-pot synthesis: $Pd@[Cu_{3-x}Pd_x(BTC)_2]_n$

Simultaneous incorporation of Pd^{2+}/M^{2+} -nodes and Pd^{0} nanoparticles dispersion into MOF are achieved *via* one-pot synthesis. The Pd^{2+} -sites in such designed solids play an important role in enhancing the catalytic activity on the hydrogenation of *p*-nitrophenol with NaBH₄ to *p*-aminophenol.

As featured in:



See Roland A. Fischer *et al.,* Dalton Trans., 2016, **45**, 14883.

ROYAL SOCIETY OF CHEMISTRY



Registered charity number: 207890

Dalton Transactions

COMMUNICATION



View Article Online View Journal | View Issue



CrossMark Click for updates

Cite this: *Dalton Trans.*, 2016, **45**, 14883

Received 21st July 2016, Accepted 22nd August 2016 DOI: 10.1039/c6dt02893d

www.rsc.org/dalton

Simultaneous introduction of various palladium active sites into MOF *via* one-pot synthesis: $Pd@[Cu_{3-x}Pd_{x}(BTC)_{2}]_{n}$

Wenhua Zhang,^a Zhihao Chen,^b Majd Al-Naji,^b Penghu Guo,^c Stefan Cwik,^a Olesia Halbherr,^a Yuemin Wang,^d Martin Muhler,^c Nicole Wilde,^b Roger Gläser^b and Roland A. Fischer*^{e,f}

Simultaneous incorporation of palladium within Pd–Pd and/or Pd–Cu paddlewheels as framework-nodes and Pd nanoparticle (NP) dispersion into MOF have been achieved for the first time *via* one-pot synthesis. In particular, the framework substitution of Cu²⁺ by Pd²⁺ as well as the pore loading with PdNPs have been confirmed and characterized by XPS. The obtained solids featuring such multiple Pd-sites show enhanced catalytic activity in the aqueous-phase hydrogenation of *p*-nitrophenol (PNP) with NaBH₄ to *p*-aminophenol (PAP).

High structural and compositional design ability of metalorganic frameworks (MOFs) and hence, the ability of tailoring their properties made MOFs to be among the most topical materials over last decades.^{1–7} Along with linker(s) modification^{8–10} and guest(s) inclusion,^{11,12} variation of the metal center(s) is also a powerful tool to fine tune MOFs functionalities. In fact, both control over coordinatively unsaturated metal sites (CUS) (*e.g.*, *via* "defects-engineering")¹³ and partial metal substitution (*e.g.*, *via* "solid solution" approach) could considerably enhance MOFs activity, particularly in catalysis^{14–16} and selective gas sorption/separation.^{17,18}

Combination of distinct metal-ions, which are closely related in coordination chemistry and have similar effective ionic radii (r_{ion}), such as Cu²⁺ (73 pm)/Zn²⁺ (74 pm) couple¹⁹

within single MOF, has been reported for several structural types.^{17,20,21} In fact, partial substitution of Cu²⁺ by Zn²⁺ and some other metals of 3d-row, namely, Co, Fe and Mn, in HKUST-1 ($[Cu_3(BTC)_2]_n$, BTC = benzene-1,3,5-tricarboxylate) has been recently reported.^{18,22} In a later case, doping with a second metal caused enhanced selective sorption of O2 vs. N2.^{18,23} What is more challenging, however, is to introduce more distinct metals of 4d-24 or 5d-row25 as framework-nodes. In particular, metals of the platinum group are highly attractive as catalytic/strong sorption centers. Moreover, square planar coordination is preferred such as Cu²⁺.^{26–28,29} However, due to kinetic reasons, these metal ions are difficult to be crystallized within 3D structures^{28,29} and therefore, are almost neglected in MOF field.³⁰ To the best of our knowledge, studies on integration of palladium as a framework node into a MOF are thus far in its infancy.³⁰⁻³³ Reports on MOFs featuring Pd-Pd and Pd-M paddlewheel nodes could not be found. Interestingly, bimetallic Pd/M-paddlewheel complexes have been lately found to be promising economical catalysts in the intramolecular benzylic C-H amination.³⁴ Moreover, porous metal-organic polyhedrals (MOPs) constructed with $Pd^{2+}-M^{2+}$ (M = Cu, Ni, Zn) paddlewheel nodes has been very recently described.29 Considering its structural peculiarities (i.e., paddlewheel SBUs and CUSs), choosing HKUST-1 as a matrix for palladium inframework incorporation via solid solution approach would be of interest.35 However, a rigorous exclusion of reducing conditions during MOF synthesis is difficult. Even technical activation may cause reduction at some metal sites due to decarboxylation.^{36,37} Therefore, the standard protocol for HKUST-1 synthesis is, intentionally, not changed at this stage.

On the other hand, loading of Pd^0 NPs onto MOF is widely investigated as gas adsorbents^{38–40} and catalysts used in hydrogenation^{38,41–44} and cross coupling^{42,45} reactions.⁴⁶ It can be noted that one of the most common approaches to obtain Pd^0 @MOFs is using H_2 to reduce Pd^{2+} -precursor loading MOFs that are prepared *via* solution impregnation by soluble Pd^{2+} species. In some cases, trace amount of Pd^{2+} can be still observed after reduction.⁴⁵ Actually, according to the

^aInorganic Chemistry II—Organometallics and Materials Chemistry,

Ruhr-University Bochum, Universitätsstraße 150, 44801 Bochum, Germany ^bInstitute of Chemical Technology, Universität Leipzig, Linnéstraße 3, 04103 Leipzig, Germany

^cLaboratory of Industrial Chemistry, Ruhr-University Bochum,

Universitätsstraße 150, 44801 Bochum, Germany

^dInstitute of Functional Interfaces (IFG), Karlsruhe Institute of Technology (KIT), 76344 Karlsruhe, Germany

^eChair of Inorganic and Metal-Organic Chemistry, Department of Chemistry, Technical University Munich, Lichtenbergstraße 4, 85748 Garching, Germany

¹Catalysis Research Centre, Technical University Munich, Ernst-Otto-Fischer Strasse 1, 85748 Garching, Germany. E-mail: roland.fischer@tum.de

 $[\]dagger$ Electronic supplementary information (ESI) available: Experimental details, IR, TGA, NMR, SEM-EDX, N_2 sorption, elementals analysis and catalytic reaction details. See DOI: 10.1039/c6dt02893d

Communication

concept of post-synthetic metal-ion exchange,⁴⁷ Pd²⁺ substitution in the metal nodes of MOFs could probably occur under this impregnation. Interestingly, the discrimination between the two Pd-sites (extra-framework loading or in-framework incorporation) is disregarded to some extent in the current literature. Given both facts, herein, an appropriate one-pot synthesis has been selected. Both H₂O and alcohols are found to be important components to reduce Pd²⁺ ions to Pd⁰ at elevated temperatures.^{48–50} Therefore, it is expected that utilizing a standard protocol for HKUST-1 synthesis (employing H₂O and EtOH under solvothermal conditions) can simultaneously introduce both Pd²⁺-doped nodes and Pd⁰ NPs in one step.

 $Pd@[Cu_{3-x}Pd_{x}(BTC)_{2}]_{n}$ (Cu/Pd-BTC_1-3) materials have been synthesized under solvothermal conditions by mixing corresponding metal salts (Pd(Π) acetate and Cu(NO₃)₂·3H₂O) with H₃BTC directly in the starting reactions (see ESI[†]). All Cu/ Pd-BTC_1-3 samples (both as-synthesized and dried phases) are crystalline solids and isostructural with the parent Cu-BTC (Fig. 1 and S1[†]), indicating the preserved structure integrity after the Pd-sites introduction. Recorded PXRD patterns and accordingly calculated cell parameters of Cu/Pd-BTC_1-3 match very well with the respective simulated data of the reported $[Cu_3(BTC)_2]_n$ single-crystal structure (Fig. S3 and Table S1[†]). Remarkably, intensity of the reflections at *ca.* 6.67°, 9.40° and 13.34° (2 θ) assigned to the (200), (220) and (400) planes, respectively, varies (Fig. 1). This indicates certain changes of electronic density compared to the non-doped Cuanalogue (Cu-BTC). The main contribution to the reflection of the (200) and (220) planes is due to the metal-nodes (Fig. S4[†]). Hence, such difference in intensities should primarily stem from the partial substitution of Cu^{2+} by Pd^{2+} within the M_2 paddlewheel units of MOFs, indicating Pd²⁺ framework incorporation. Considering the presence of Pd NPs in the discussed Cu/Pd-BTC_1-3, small reflections at 40.02° resulting from (111) planes of the face-centered cubic structure of Pd are observed (Fig. 1).⁵¹ This is probably due to the rather small particle size of these Pd NPs and therefore, they are difficult to be detected by PXRD technique. Finally, it should be pointed out that employing equal molar amounts of Cu- and Pd-salts



Fig. 1 PXRD patterns of activated $Pd@[Cu_{3-x}Pd_x(BTC)_2]_n$ (**Cu/Pd-BTC_1-3**) in comparison with activated non-doped Cu-BTC. The vertical lines correspond to the peak position of (111) planes of the face-centered cubic (fcc) Pd-structure.

or only Pd-precursor in the starting reaction mixtures, formation of only metal/metal-oxide products has been observed (Fig. S5 and S6[†]).

AAS analysis of the activated Cu/Pd-BTC_1-3 solids confirms quantitative incorporation of palladium. Thus, the Pd-contents and Pd:Cu ratios in the final Cu/Pd-BTC 1-3 samples remain almost unchanged with respect to the taken feeding ratios of the metal-precursors (Table S2[†]). Furthermore, SEM-EDX elemental mapping demonstrates quite homogeneous Cu/Pd distribution within the obtained Cu/Pd-BTC solids (Fig. S8[†]). Incorporation of Pd^{2+} into the framework as well as the Pd⁰ NPs loading has been subsequently corroborated by high-resolution XPS. Fig. 2 shows the Pd 3d core-level spectra of the Cu/Pd-BTC 1 and Cu/Pd-BTC_3 (representative samples with relatively low and high Pd-contents). Three Pd 3d doublets $(3d_{5/2} \text{ and } 3d_{3/2})$ are resolved in the deconvoluted spectra. The doublet located at 337.9 and 343.2 eV (Pd2) is characteristic for Pd²⁺ species (Table S3[†]).^{52,53} In addition, the higher binding energies observed at 338.9 and 344.2 eV for Pd1 reveal the presence of an electronically modified Pd²⁺ species. Moreover, we could unambiguously rule out an assignment of both Pd²⁺ species to PdO NPs, as no typical O 1s peak at about 530 eV has been detected in the corresponding spectra, which showed only one O 1s peak at 531.8 eV, originating from the carboxylate (-COO) groups in the frameworks. Therefore, both the found Pd²⁺ species (Pd1 and Pd2) are very likely associated with the formation of Pd-Pd and Cu-Pd framework-nodes. The doublet at ca. 335.8 and 341.0 eV is attributed to metallic Pd⁰ species (Pd3), indicating the existence of Pd metallic NPs in these samples. Moreover, the amount of Pd NPs in the total Pd species (Pd^{2+} and Pd^{0}) increases (from 33% for Cu/Pd-BTC 1 to 44% for Cu/Pd-BTC_3) along with the doping increase of Pd(II) acetate. TEM characterization has not been performed because of the beam sensitivity of HKUST-1, which does not allow characterization of the "pristine" $Pd@[Cu_{3-x}Pd_x(BTC)_2]_n$ sample as well.



Fig. 2 Deconvoluted XP spectra of Cu/Pd-BTC_1 and 3 in Pd 3d region.

Furthermore, any vibrations stemming neither from the non-reacted H₃BTC linker nor used metal-precursors (*i.e.*, acetate-, nitrate-groups) could be revealed in the FT-IR spectra of all prepared **Cu/Pd-BTC** solids (Fig. S12†). Moreover, ¹H-NMR spectra of the digested **Cu/Pd-BTC_1-3** samples show the presence of only BTC-linker (Fig. S13†). Thus, absence of any resonances at about 1.9 ppm, stemming from the acetate protons, fully supports the IR results ruling out any residuals of the employed starting Pd-reactant. Hence, the presence of Pd²⁺-sites should originate from the in-framework nodes rather than Pd²⁺-precursor loading.

TGA suggests that thermal stability of the obtained Cu/Pd-BTC_1-3 solids is fully preserved (in comparison with the parent Cu-BTC)³⁵ with the decomposition temperatures close to 300 °C (Fig. S14†). The N₂ (77 K) sorption isotherms recorded for obtained samples reveal type I isotherm (Fig. S15†), confirming their permanent microporosity. Brunauer–Emmett–Teller (BET) surface area of Cu/Pd-BTC_1 and _2 increase a little in comparison with the parent Cu-BTC (prepared under similar conditions) (Table S4†), indicating that the presence of Pd²⁺ incorporation as metal nodes in the framework are dominant. When it turns to Cu/Pd-BTC_3, the increasing of Pd⁰ NPs results in a slight lower BET surface area in comparison with the others samples.

Both Pd^{2+} -containing MOF ([Pd(2-pymo)_2]_n, 2-pymo = 2-pyrimidinolate)³¹⁻³³ and Pd⁰(a)MOF,^{38,42,43,45} have been reported as good reusable catalysts in typical palladium-catalyzed reactions such as Suzuki C-C couplings and hydrogenation. Owing to both Pd⁰ NPs and potential Pd²⁺-CUS (that should be available after thermal treatment and specifically promote H₂ splitting) in obtained Pd-containing Cu/Pd-BTC materials, it was of interest to test their catalytic activity in hydrogenation reactions. Herein, it should be mentioned that in order to investigate which Pd species (Pd²⁺ or Pd⁰) would play the important role on the catalysis as well, we prepared another isostructural analog Cu/Pd-BTC_4 sample employing PdCl₂ and longer reaction time instead (see ESI for the preparation and characterization: Tables S2, S3 and Fig. S2, S9, S11, S16^{\dagger}). This sample contains dominant Pd⁰ (70%) rather than Pd²⁺ on the basis of the Pd 3d region XP spectra (Fig. S11 and Table S3[†]).

As a test reaction, the aqueous-phase hydrogenation of PNP to PAP using NaBH₄ as a reducing agent has been chosen. It can be conducted at room temperature and ambient pressure within a reaction time of <10 min using a simple on-line UV-Vis spectroscopy to monitor the progress of the reaction.^{43,54,55} The concentration of PNP as a function of time as well as the initial reaction rate normalized to the amount of Pd in the catalyst for **Cu/Pd-BTC_1-4** are depicted in Fig. 3. Before addition of the solid catalyst, *i.e.*, within the first 0.5 min of the experiment, no PNP conversion was observed. Complete conversion of PNP to PAP was reached within 2 min of reaction time using **Cu/Pd-BTC_1-4**, whereas the conversion of PNP remained incomplete for the Pd-free **Cu-BTC**. This incomplete conversion is known for catalysts with low activity and results from unproductive NaBH₄ decomposition to hydrogen.⁵⁴



Fig. 3 Concentration of PNP as a function of time for non-doped Cu-BTC and Pd containing **Cu/Pd-BTC_1-4** as catalysts in the aqueousphase hydrogenation of PNP with NaBH₄ to PAP. The insert shows the initial reaction rate for **Cu/Pd-BTC_1-4** normalized to the amount of Pd in the catalyst, respectively. Reaction conditions: $c_{\rm PNP} = 0.18 \text{ mmol dm}^{-3}$, $c_{\rm NaBH_4} = 0.60 \text{ mmol dm}^{-3}$, T = 298 K, stirring speed = 1300 min⁻¹, $m_{\rm catalyst} = 5.0 \text{ mg}$, ambient pressure.

Evidently, the Pd-containing **Cu-BTC** catalysts are significantly more active than the Pd-free **Cu-BTC**. Interestingly, the initial reaction rate related to the Pd amount for **Cu/Pd-BTC_1** and 2 (*i.e.*, 4.0×10^{-3} and 2.0×10^{-3} dm⁻³ min⁻¹) is significantly higher than that achieved over a metallic Pd catalyst supported on an Al-containing mesocellular silica foam (1.0×10^{-3} dm⁻³ min⁻¹) under the same reaction conditions.⁵⁶ Note that the activity of **Cu/Pd-BTC_1** and 2 is so high that the difference in their catalytic activity cannot be distinguished under the reaction conditions used.

Surprisingly, the normalized initial reaction rate decreases with increasing overall Pd content from $4 \times 10^{-3} \text{ dm}^{-3} \text{ min}^{-1}$ for Cu/Pd-BTC 1 to 1.0×10^{-3} dm⁻³ min⁻¹ for Cu/Pd-BTC 3, respectively (insert in Fig. 3). This can be explained by considering the decreasing concentration of Pd2+ species with increasing Pd content from Cu/Pd-BTC_1 to Cu/Pd-BTC_3, as observed by XPS (Table S3[†]). Particularly, Cu/Pd-BTC_4 containing the lowest concentration of Pd²⁺ species (70%) displays the lowest initial reaction rate in comparison with the other three Cu/Pd-BTC samples. It may, therefore, be concluded that Pd²⁺ species in the catalyst are catalytically active and they are dominantly responsible for the observed high catalytic activity. Moreover, it has been reported that Pd²⁺ can act as active metal sites in olefin hydrogenations.³¹⁻³³ It can be noted that PXRD patterns of the Cu/Pd-BTC samples before and after reaction indicate that the structure of the framework remains unchanged (Fig. S17[†]). Finally, according to the ICP-OES analysis of the solution after reaction (Cu/Pd-BTC 2 as selective catalysts), leaching of palladium is negligible (*i.e.*, 0.01 mg L^{-1}), indicating the stability of the used MOF catalysts as well as the heterogeneous nature of the catalytic reaction.

In summary, via one-pot synthesis, we successfully obtained crystalline porous $Pd@[Cu_{3-x}Pd_x(BTC)_2]_n$ MOFs with various doping levels of Pd. On the basis of entire experimental data, structural incorporation of Pd²⁺ serving as frameworks-nodes (within Cu-Pd or/and Pd-Pd paddlewheels) as well as Pd⁰ NPs dispersion in the framework of HKUST-1 are concluded. To the best of our knowledge, it is the singular case of MOFs bearing both Pd²⁺-paddlewheels and Pd NPs known so far. Moreover, distinct Pd sites, especially Pd²⁺/M-CUS considerably enhances the catalytic activity of MOFs in the aqueousphase hydrogenation of PNP to PAP with respect to the "Pdfree" Cu-BTC catalysts, which affords a perspective way to tune their catalytic activity. Furthermore, a synthesis of HKUST-1 analogs excluding Pd⁰ formation and featuring exclusive Pd²⁺/ Cu²⁺ mixed-metal paddlewheels would lead to highly active catalysts.

W. Z. and Z. C. thank the China Scholarship Council (CSC) for PhD fellowships. W. Z. is also grateful to the Research School^{Plus} at Ruhr-University Bochum for the support of her PhD project. P. G. acknowledges the support of the EU innovative Training Network "DEFect NETwork materials science and engineering" (DEFNET).

Notes and references

- M. Latroche, S. Surblé, C. Serre, C. Mellot-Draznieks,
 P. L. Llewellyn, J.-H. Lee, J.-S. Chang, S. H. Jhung and
 G. Férey, *Angew. Chem., Int. Ed.*, 2006, 45, 8227–8231.
- 2 K. Sumida, D. L. Rogow, J. A. Mason, T. M. McDonald,
 E. D. Bloch, Z. R. Herm, T.-H. Bae and J. R. Long, *Chem. Rev.*, 2012, **112**, 724–781.
- 3 E. D. Bloch, W. L. Queen, R. Krishna, J. M. Zadrozny,
 C. M. Brown and J. R. Long, *Science*, 2012, 335, 1606–1610.
- 4 A. Corma, H. García and F. X. Llabrés i Xamena, *Chem. Rev.*, 2010, **110**, 4606–4655.
- 5 P. Horcajada, C. Serre, M. Vallet-Regí, M. Sebban, F. Taulelle and G. Férey, *Angew. Chem.*, *Int. Ed.*, 2006, 45, 5974–5978.
- 6 A. A. Talin, A. Centrone, A. C. Ford, M. E. Foster, V. Stavila,
 P. Haney, R. A. Kinney, V. Szalai, F. El Gabaly, H. P. Yoon,
 F. Léonard and M. D. Allendorf, *Science*, 2014, 343, 66–69.
- 7 L. E. Kreno, K. Leong, O. K. Farha, M. Allendorf, R. P. Van Duyne and J. T. Hupp, *Chem. Rev.*, 2012, **112**, 1105–1125.
- 8 H. Deng, S. Grunder, K. E. Cordova, C. Valente, H. Furukawa, M. Hmadeh, F. Gándara, A. C. Whalley, Z. Liu, S. Asahina, H. Kazumori, M. O'Keeffe, O. Terasaki, J. F. Stoddart and O. M. Yaghi, *Science*, 2012, 336, 1018– 1023.
- 9 H. Deng, C. J. Doonan, H. Furukawa, R. B. Ferreira, J. Towne, C. B. Knobler, B. Wang and O. M. Yaghi, *Science*, 2010, **327**, 846–850.
- A. Schneemann, V. Bon, I. Schwedler, I. Senkovska, S. Kaskel and R. A. Fischer, *Chem. Soc. Rev.*, 2014, 43, 6062–6096.
- 11 D. Yan, G. O. Lloyd, A. Delori, W. Jones and X. Duan, *ChemPlusChem*, 2012, 77, 1112–1118.

- 12 A. Carné-Sánchez, I. Imaz, M. Cano-Sarabia and D. Maspoch, *Nat. Chem.*, 2013, 5, 203–211.
- 13 Z. Fang, B. Bueken, D. E. De Vos and R. A. Fischer, Angew. Chem., Int. Ed., 2015, 54, 7234–7254.
- F. Vermoortele, B. Bueken, G. Le Bars, B. Van de Voorde, M. Vandichel, K. Houthoofd, A. Vimont, M. Daturi, M. Waroquier, V. Van Speybroeck, C. Kirschhock and D. E. De Vos, *J. Am. Chem. Soc.*, 2013, 135, 11465–11468.
- 15 O. Kozachuk, I. Luz, F. X. Llabrés i Xamena, H. Noei, M. Kauer, H. B. Albada, E. D. Bloch, B. Marler, Y. Wang, M. Muhler and R. A. Fischer, *Angew. Chem., Int. Ed.*, 2014, 53, 7058–7062.
- 16 C. K. Brozek and M. Dincă, J. Am. Chem. Soc., 2013, 135, 12886–12891.
- 17 G.-T. Vuong, M.-H. Pham and T.-O. Do, *Dalton Trans.*, 2013, 42, 550–557.
- 18 D. F. Sava Gallis, M. V. Parkes, J. A. Greathouse, X. Zhang and T. M. Nenoff, *Chem. Mater.*, 2015, 27, 2018–2025.
- 19 R. Shannon, Acta Crystallogr., Sect. A: Cryst. Phys., Diffr., Theor. Gen. Cryst., 1976, 32, 751–767.
- O. Kozachuk, K. Khaletskaya, M. Halbherr, A. Bétard, M. Meilikhov, R. W. Seidel, B. Jee, A. Pöppl and R. A. Fischer, *Eur. J. Inorg. Chem.*, 2012, 2012, 1688–1695.
- 21 Y. Jiao, C. R. Morelock, N. C. Burtch, W. P. Mounfield, J. T. Hungerford and K. S. Walton, *Ind. Eng. Chem. Res.*, 2015, 54, 12408–12414.
- 22 F. Gul-E-Noor, B. Jee, M. Mendt, D. Himsl, A. Pöppl, M. Hartmann, J. Haase, H. Krautscheid and M. Bertmer, *J. Phys. Chem. C*, 2012, **116**, 20866–20873.
- 23 M. V. Parkes, D. F. Sava Gallis, J. A. Greathouse and T. M. Nenoff, J. Phys. Chem. C, 2015, 119, 6556–6567.
- 24 M. A. Gotthardt, R. Schoch, S. Wolf, M. Bauer and W. Kleist, *Dalton Trans.*, 2015, 44, 2052–2056.
- 25 Q. Zhang, L. Cao, B. Li and L. Chen, *Chem. Sci.*, 2012, 3, 2708–2715.
- 26 N. Y. Kozitsyna, S. E. Nefedov, F. M. Dolgushin, N. V. Cherkashina, M. N. Vargaftik and I. I. Moiseev, *Inorg. Chim. Acta*, 2006, **359**, 2072–2086.
- 27 N. S. Akhmadullina, N. V. Cherkashina, N. Y. Kozitsyna, I. P. Stolarov, E. V. Perova, A. E. Gekhman, S. E. Nefedov, M. N. Vargaftik and I. I. Moiseev, *Inorg. Chim. Acta*, 2009, 362, 1943–1951.
- 28 G. Nickerl, U. Stoeck, U. Burkhardt, I. Senkovska and S. Kaskel, *J. Mater. Chem. A*, 2014, 2, 144–148.
- 29 J. M. Teo, C. J. Coghlan, J. D. Evans, E. Tsivion, M. Head-Gordon, C. J. Sumby and C. J. Doonan, *Chem. Commun.*, 2016, 52, 276–279.
- 30 J. A. R. Navarro, E. Barea, J. M. Salas, N. Masciocchi, S. Galli, A. Sironi, C. O. Ania and J. B. Parra, *Inorg. Chem.*, 2006, 45, 2397–2399.
- 31 F. X. Llabrés i Xamena, A. Abad, A. Corma and H. Garcia, J. Catal., 2007, 250, 294–298.
- 32 S. Schuster, E. Klemm and M. Bauer, *Chem. Eur. J.*, 2012, 18, 15831–15837.
- 33 S. Opelt, V. Krug, J. Sonntag, M. Hunger and E. Klemm, *Microporous Mesoporous Mater.*, 2012, **147**, 327–333.

- 34 X. Zhang, H. Xu, X. Liu, D. L. Phillips and C. Zhao, *Chem. Eur. J.*, 2016, 22, 7288–7297.
- 35 S. S. Y. Chui, S. M. F. Lo, J. P. H. Charmant, A. G. Orpen and I. D. Williams, *Science*, 1999, **283**, 1148–1150.
- 36 J. Szanyi, M. Daturi, G. Clet, D. R. Baer and C. H. F. Peden, *Phys. Chem. Chem. Phys.*, 2012, 14, 4383–4390.
- 37 P. St. Petkov, G. N. Vayssilov, J. Liu, O. Shekhah, Y. Wang,
 C. Wöll and T. Heine, *ChemPhysChem*, 2012, 13, 2025–2029.
- 38 M. Sabo, A. Henschel, H. Frode, E. Klemm and S. Kaskel, J. Mater. Chem., 2007, 17, 3827–3832.
- 39 C. Zlotea, R. Campesi, F. Cuevas, E. Leroy, P. Dibandjo, C. Volkringer, T. Loiseau, G. Férey and M. Latroche, *J. Am. Chem. Soc.*, 2010, **132**, 2991–2997.
- 40 G. Li, H. Kobayashi, J. M. Taylor, R. Ikeda, Y. Kubota, K. Kato, M. Takata, T. Yamamoto, S. Toh, S. Matsumura and H. Kitagawa, *Nat. Mater.*, 2014, **13**, 802–806.
- 41 S. Opelt, S. Türk, E. Dietzsch, A. Henschel, S. Kaskel and E. Klemm, *Catal. Commun.*, 2008, 9, 1286–1290.
- 42 B. Gole, U. Sanyal, R. Banerjee and P. S. Mukherjee, *Inorg. Chem.*, 2016, **55**, 2345–2354.
- 43 C. Wang, H. Zhang, C. Feng, S. Gao, N. Shang and Z. Wang, *Catal. Commun.*, 2015, **72**, 29–32.
- 44 X. Jia, S. Wang and Y. Fan, J. Catal., 2015, 327, 54-57.
- 45 B. Yuan, Y. Pan, Y. Li, B. Yin and H. Jiang, *Angew. Chem.*, *Int. Ed.*, 2010, **49**, 4054–4058.
- 46 M. Gulcan, M. Zahmakiran and S. Özkar, *Appl. Catal., B*, 2014, **147**, 394–401.

- 47 P. Deria, J. E. Mondloch, O. Karagiaridi, W. Bury, J. T. Hupp and O. K. Farha, *Chem. Soc. Rev.*, 2014, **43**, 5896– 5912.
- 48 B. P. Fors, P. Krattiger, E. Strieter and S. L. Buchwald, Org. Lett., 2008, 10, 3505–3508.
- 49 T. A. Stephenson, S. M. Morehouse, A. R. Powell, J. P. Heffer and G. Wilkinson, *J. Chem. Soc.*, 1965, 3632– 3640, DOI: 10.1039/JR9650003632.
- 50 W. A. Carole and T. J. Colacot, *Chem. Eur. J.*, 2016, 22, 7686–7695.
- 51 G. H. Jeong, S. H. Kim, M. Kim, D. Choi, J. H. Lee, J.-H. Kim and S.-W. Kim, *Chem. Commun.*, 2011, 47, 12236– 12238.
- 52 H.-F. Wang, W. E. Kaden, R. Dowler, M. Sterrer and H.-J. Freund, *Phys. Chem. Chem. Phys.*, 2012, 14, 11525– 11533.
- 53 R. Arrigo, M. E. Schuster, Z. Xie, Y. Yi, G. Wowsnick, L. L. Sun, K. E. Hermann, M. Friedrich, P. Kast, M. Hävecker, A. Knop-Gericke and R. Schlögl, *ACS Catal.*, 2015, 5, 2740–2753.
- 54 M. Goepel, M. Al-Naji, P. With, G. Wagner, O. Oeckler, D. Enke and R. Gläser, *Chem. Eng. Technol.*, 2014, 37, 551– 554.
- 55 J. Sun, Y. Fu, G. He, X. Sun and X. Wang, *Catal. Sci. Technol.*, 2014, 4, 1742–1748.
- 56 M. Al-Naji, A. M. Balu, A. Roibu, M. Goepel, W.-D. Einicke, R. Luque and R. Glaser, *Catal. Sci. Technol.*, 2015, 5, 2085–2091.