# **Green Chemistry**



View Article Online

# This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence. Open Access Article. Published on 03 April 2017. Downloaded on 8/11/2025 2:27:24 PM.

# COMMUNICATION

Check for updates

Cite this: Green Chem., 2017, **19**, 2096

Received 20th February 2017, Accepted 3rd April 2017 DOI: 10.1039/c7qc00539c

rsc.li/greenchem

# Visible-light-driven photooxidation of alcohols using surface-doped graphitic carbon nitride†

Wuyuan Zhang, 🗅 \*<sup>a</sup> Anna Bariotaki, 🕩 <sup>b</sup> Ioulia Smonou 🕩 <sup>b</sup> and Frank Hollmann 🗇 \*<sup>a</sup>

Carbon-nanodot-doped  $g-C_3N_4$  is used as a photocatalyst to promote the aerobic oxidation of alcohols and oxyfunctionalisation of activated hydrocarbons. A critical E-factor analysis of the current reaction system reveals its limitations *en route* to environmentally acceptable oxidation procedures.

In recent years, graphitic carbon nitride  $(g-C_3N_4)$  has received substantial interest as a photocatalyst for metal-free, visiblelight promoted reactions.<sup>1</sup> It exhibits a graphite-like, layered structure wherein tris-triazine units are connected through C–N-bonds forming a two-dimensional layer. g-C<sub>3</sub>N<sub>4</sub> can be synthesized *via* various methods such as pyrolysis of urea or other nitrogen-rich precursors or layer exfoliation of bulk materials.<sup>2</sup>

Pure g-C<sub>3</sub>N<sub>4</sub>, however, is a rather poor photocatalyst, mainly due to the fast recombination of photoexcited, charge-separated states. Therefore, one focus of research lies in the improvement of its photocatalytic properties by modulating the potential of g-C<sub>3</sub>N<sub>4</sub>'s conducting- and valence bands.<sup>1</sup> Particularly doping of g-C<sub>3</sub>N<sub>4</sub> with other elements such as Y,<sup>3</sup> Fe,<sup>4</sup> Pt,<sup>5</sup> Au/Pd<sup>6,7</sup> K, Ag,<sup>8,9</sup> C<sup>10</sup> or carbon-nanodots<sup>11</sup> and many more has proven to be an efficient handle to modulate its properties. Also, doping with carbon-nanodots appears promising to increase the quantum efficiency of photocatalytic processes.

Interestingly, g- $C_3N_4$  is mostly considered as a photocatalyst for (sun)-light driven water splitting, remediation of organic pollutants and catalytic CO<sub>2</sub> reduction.<sup>1</sup> Applications for preparative organic synthesis are comparably few. For example, Goettmann *et al.* reported g- $C_3N_4$  catalysed Friedel–Crafts acylation.<sup>12</sup> More recently, photocatalytic acetalisation of aldehydes and ketones,<sup>13</sup> and hydrazine-driven reductions of alkenes and alkynes were reported using g- $C_3N_4$ .<sup>14,15</sup> Selective oxidations especially of benzylic C–H-bonds have been reported using mesoporous  $g-C_3N_4$  together with N–OHcocatalysts,<sup>16–19</sup> or using transition metal doped  $g-C_3N_4$ .<sup>14,20–22</sup> Also the oxidative coupling of amines has been reported.<sup>23</sup>

However, to the best of our knowledge, carbon-nanodot doped g- $C_3N_4$  has so far not been evaluated as a catalyst for photocatalytic oxidation reactions. Therefore, we set out to evaluate carbon-nanodot-doped g- $C_3N_4$  (CD- $C_3N_4$ ) as a visible-light-driven photocatalyst for the aerobic oxidation of alcohols (Scheme 1).

For the synthesis of g- $C_3N_4$  we followed the procedure by Tang and coworkers<sup>24</sup> due to the more porous structure of the material and the resulting higher activity (due to the increased surface area). In short, calcination of urea at 600 °C for 4 h gave the desired mesoporous g- $C_3N_4$  as confirmed by TEM imaging and X-ray diffraction (Fig. S1 and S2†). Next, carbon nanodots were synthesized *via* thermal decomposition of sucrose.<sup>25</sup> The latter were deposited on the g- $C_3N_4$  surface *via* thermal treatment of both materials.<sup>11</sup> The XRD pattern of the such-obtained composite material did not change significantly compared to the starting material (g- $C_3N_4$ ) most probably due to the amorphous character of the carbon nanodots adsorbed.



Scheme 1 Photocatalytic aerobic oxidation using carbon nanodot-doped  $g-C_3N_4$  (CD- $C_3N_4$ ) as a photocatalyst.

<sup>&</sup>lt;sup>a</sup>Department of Biotechnology, Delft University of Technology, Van der Maasweg 9, 2629HZ Delft, The Netherlands. E-mail: W.Zhang-1@tudelft.nl,

F.Hollmann@tudelft.nl

<sup>&</sup>lt;sup>b</sup>Department of Chemistry, University of Crete, Heraklion-Voutes 71003, Crete, Greece

<sup>†</sup>Electronic supplementary information (ESI) available: Details of the experimental procedures and additional analytic material. See DOI: 10.1039/ c7gc00539c

The UV/Vis spectrum showed the characteristic increase in absorption at wavelengths below 600 nm (Fig. S3<sup>†</sup>), and the BET measurement revealed a surface area of 105 m<sup>2</sup> g<sup>-1</sup> (Fig. S8<sup>†</sup>).

Having both catalysts at hand, we next compared their catalytic activity in the oxidation of benzyl alcohol to benzaldehyde as a model reaction (Fig. 1). Due to the volatility of benzaldehyde and the poor water solubility of the benzyl alcohol starting material we used a two-liquid phase approach employing benzyl alcohol as the second organic phase (phase ratio 3:7 organic : aqueous).

As shown in Fig. 1, CD-C<sub>3</sub>N<sub>4</sub> excelled over g-C<sub>3</sub>N<sub>4</sub> both in terms of activity and robustness. Not only was the initial product formation rate roughly two times higher but also the long term-stability of the reaction: the reaction rate with g-C<sub>3</sub>N<sub>4</sub> levelled off significantly after several hours whereas with CD-C<sub>3</sub>N<sub>4</sub> linear product accumulation was observed for at least 48 h. Overall, with CD-C<sub>3</sub>N<sub>4</sub> more than 500 mM of product accumulated corresponding to a product to catalyst ratio of more than 4:1 (g g<sup>-1</sup>), under the non-optimized conditions.

It is worth mentioning here, that in the absence of either the photocatalyst or a light source, no noticeable conversion of the starting material was observed. Also, hydrogen peroxide as a by-product was observable in trace amounts only throughout the experiments. This observation is in line with previous findings that  $CD-C_3N_4$  is also an efficient  $H_2O_2$  decomposition catalyst.<sup>11</sup>

The rate of the oxidation reaction exhibited a saturationtype dependency on both the catalyst concentration (Fig. 2) and the intensity of the light source applied (Fig. 3).

In the case of increasing catalyst concentrations, we suspect the decreasing transparency of the reaction mixture to account



**Fig. 1** Photocatalytic oxidation of benzyl alcohol to benzaldehyde using  $g-C_3N_4$  (**A**) and  $CD-C_3N_4$  (**B**) as photocatalysts. Conditions: 5 g L<sup>-1</sup> of photocatalyst, two phase reaction: 700 µL of water + 300 µL of benzyl alcohol, 30 °C and oxygen atmosphere under visible light illumination using setup 1 ( $\lambda > 400$  nm).



**Fig. 2** Influence of the catalyst loading on the rate of the photocatalytic oxidation of benzyl alcohol.  $[CD-C_3N_4] = 5(\bullet)$ , 10 (**m**), 25 (**A**) g L<sup>-1</sup>. Conditions: Two phase reaction with 700 µL of water + 300 µL of benzyl alcohol, 30 °C and oxygen atmosphere under visible light illumination using setup 1 ( $\lambda > 400$  nm).



**Fig. 3** Influence of the light intensity on the rate of the photocatalytic oxidation of benzyl alcohol. Light intensity of 79 ( $\blacktriangle$ ), 197 ( $\blacksquare$ ), 341 ( $\blacklozenge$ ) W cm<sup>-2</sup>. Conditions: 5 g L<sup>-1</sup> of photocatalyst, two phase reaction with 700 µL of water + 300 µL of benzyl alcohol, 30 °C and oxygen atmosphere under visible light illumination using setup 2 ( $\lambda$  > 400 nm).

for this observation. The converging reaction rate at increasing light intensities may well be attributed to oxygen diffusion becoming overall rate-limiting. It should be mentioned here that for the latter experiments we utilised a specialized light-setup to control the light intensity (setup 2, Fig. S5†). Despite the much higher product formation rate attainable with this system (Fig. 3) we decided to perform the following experiment using a cheap white-light bulb in order to enable simple reproduction by others (setup 1, Fig. S4†). Nevertheless, the productivities shown in Fig. 3 (using a simple light source) of more than 0.2 g<sub>product</sub> g<sup>-1</sup><sub>catalyst</sub> h<sup>-1</sup> demonstrate the preparative potential of the photochemical alcohol oxidation system.

### Communication

We investigated the recyclability of  $\text{CD-C}_3N_4$  by performing benzyl alcohol oxidation reactions followed by filtration, washing and re-loading with reaction medium (Fig. S6†). As a result  $\text{CD-C}_3N_4$  could be recycled at least 5 times. From linear regression of the initial rates, a catalyst deactivation of less than 4% per cycle was estimated.

Encouraged by these results we further explored the product scope of the reaction system (Table 1).

Especially allylic alcohols were converted at excellent rates and selectivities while benzylic alcohols were converted somewhat slower and non-activated alcohols such as cyclohexanol were rather sluggish substrates. This is roughly in-line with the general bond-dissociation energies of the C–H bonds oxidised. However, it also should be taken into account that the reactions reported in Table 1 have been obtained from two-liquid phase systems and that, depending on the partitioning coefficient of

Table 1	Examples	of	$CD-C_3N_4$ -catalyzed,	photocatalytic	alcohol
oxidation	าร				

OH R R'	$+ O_2 \longrightarrow CD-C_3N_4 \longrightarrow R \longrightarrow R'$	+ H <sub>2</sub> O <sub>2</sub>
Product	Product <sup>a</sup> [mM]	Rate $[g g^{-1} h^{-1}]$
H H O	223	0.059
H H	60.1	0.020
H <sub>3</sub> CO <sup>2</sup>	73.0	0.023
F O	40.2	0.012
	12.7/1.9 <sup><i>a</i></sup>	0.003/0.001 <sup>a</sup>
	228 <b>.</b> 1/41 <sup><i>a</i></sup>	0.055/0.023 <sup>a</sup>
ǰ	701.2	0.193
	108.4	0.040
	247.3	0.093
	252.4	0.087

Reaction conditions: 5 g L<sup>-1</sup> of photocatalyst, two phase reaction with 700  $\mu$ L of water + 300  $\mu$ L of alcohol, 30 °C and oxygen atmosphere under visible light illumination using setup 1 ( $\lambda$  > 400 nm) for 24 h. <sup>*a*</sup> Product concentration in the aqueous phase.

the starting material, the aqueous concentrations may vary very significantly thereby influencing the reaction kinetics.

The preparative applicability of the proposed photocatalytic oxidation was exemplarily demonstrated in the oxidation of carveol to carvone. Performing this reaction on a 6.8 mmol-scale (1.03 g) gave more than 95% conversion into the desired product (GC yield) and 0.773 g of isolated carvone (74.8% isolated yield) under non-optimised reaction- and DSP conditions.

An E-factor analysis<sup>26</sup> of this reaction revealed the current limitations of this reaction setup from an environmental point-of-view (Table 2). The 'classical' E-factor (including the weighable compounds only) of the overall reaction is rather moderate (144) with solvents (used both for the reaction and for the extraction of the product) contributing over 95% to the total E-factor. Obviously, dichloromethane used in this reaction is not acceptable and will be substituted by more acceptable solvents in future studies.<sup>27</sup> Also decreasing the contribution of water (e.g. by further increasing the concentration of the starting material) will be highly desirable. In fact, preliminary experiments using neat reagents (i.e. CD-C<sub>3</sub>N<sub>4</sub> suspended in pure benzyl alcohol or cyclohexanol) showed an even faster product accumulation than in the biphasic system (Fig. S7<sup>†</sup>). Probably this is also to be attributed to a higher O<sub>2</sub> solubility in these media than in aqueous systems. Another advantage of using neat reagents is that extraction can be omitted as physical methods to separate the product (e.g. distillation) are sufficient.

However, the 'hidden' E-factor contributors demand more attention *en route* to an environmentally acceptable reaction system. Using setup 2 enabled us to quantify the power input (197 W for 90 h) and energy used for the illumination reaction (17.7 kWh). According to the European Energy Agency this corresponds to  $CO_2$  emission of approximately 9.9 kg  $CO_2$ <sup>28</sup> and an E-factor contribution of 12.800 obviously 'outshining' the values discussed above. Of course the current setup has not been optimised for efficient utilisation of light and further geometric optimisation together with the increase of the reagent payload will certainly reduce this number to acceptable values. Also, provided the aspirational trend towards renewable energies continues, less  $CO_2$  emissions and thereby a reduced ' $CO_2$ '-E-factor may be assumed. Furthermore, using sunlight will almost entirely eliminate this contribution.

Also, it should not be forgotten that the preparation of the photocatalyst (though exhibiting very low classical E-factors) is based on high-temperature calcination processes.

 Table 2
 Estimation of the waste generated in the photobiocatalytic oxidation of carveol to carvone

Contributor	E-factor contribution [kg kg <sup>-1</sup> ]		
Reaction			
Water	38.8		
CD-C <sub>3</sub> N <sub>4</sub>	0.26		
$CO_2$ from a light source	12.800		
DSP			
CH <sub>2</sub> Cl <sub>2</sub>	102.8		
$MgSO_4$	1.9		

Overall, despite the potential of photochemical, aerobic oxidation we prefer to refrain from calling the current procedure green or environmentally benign.

Finally, we evaluated oxidation/oxyfunctionalisation of nonfunctionalized C-H bonds (Table 3). In general, the same trend in the reaction rate was observed here as well whereas

Table 3 Exampl oxyfunctionalisat	les of CD ions	photocatalytic		
R <sup>H</sup> R'	+ 2 O <sub>2</sub> + H <sub>2</sub> O CD-C	$^{3}N_{4} \rightarrow \overset{0}{R} \overset{0}{R} \overset{0}{R}$	+ 2 H <sub>2</sub> O <sub>2</sub>	
Product	Product [mM]	Selectivity <sup>a</sup> (%)	Rate $[g g^{-1} h^{-1}]$	
H O	16.3	77	0.004	
H H	19.0	83.3	0.0065	
H <sub>3</sub> CO <sup>2</sup> H	3.0	86.2	0.001	
F H	12.6	_	0.0044	
CI H	3.9	_	0.002	
Br H	4.1	_	0.0018	
	7.6	76.9	10.0023	
	18.1	87.4	0.0067	
	30.3 + 37.7	_	0.008 + 0.010	
	28.14		0.011	
Ö	21.25		0.008	
	10.3/9.1 <sup>b</sup>		0.002/0.005 <sup>b</sup>	
	3.0		0.0007	

Reaction conditions: 5 g L<sup>-1</sup> of photocatalyst, two phase reaction with 700  $\mu$ L of water + 300  $\mu$ L of alkane, 30 °C and oxygen atmosphere under visible light illumination using setup 2 ( $\lambda$  > 400 nm) for 24 h. <sup>*a*</sup> Selectivity = [aldehyde/ketone]/([alcohol] + [aldehyde/ketone])%. <sup>*b*</sup> Product concentration in the aqueous phase.

the reaction rates were significantly lower than observed for the corresponding alcohols. This is in line with the higher C–H-bond dissociation energy of these non-functionalized C–H bonds. Furthermore, accumulation of the intermediate alcohol product did not occur (generally the alcohol product accounted for less than 25% of the final product) indicating that the initial C–H-bond oxidation is overall rate-limiting.

## Conclusions

With the current contribution we demonstrate that simple metal-free  $CD-C_3N_4$  is a very suitable and recyclable photocatalyst for the oxidation of primary and secondary alcohols to the corresponding aldehydes and ketones. Furthermore, also extension of this concept to the corresponding alkanes appears feasible, albeit at reduced efficiencies.

Ongoing mechanistic studies will reveal a more detailed understanding of the reaction and put the basis for optimised catalysts and reaction setups *en route* to truly practical catalysts.

The critical E-factor analysis of the current reaction setup will guide our further studies *en route* to truly environmentally acceptable oxidation processes.

# Acknowledgements

Financial support by the European Research Council (ERC Consolidator Grant No. 648026) is gratefully acknowledged. The authors thank Ben Norder (Delft University of Technology) for XRD and Dr Wiel H. Evers (Delft University of Technology) for TEM measurements.

# Notes and references

- 1 W.-J. Ong, L.-L. Tan, Y. H. Ng, S.-T. Yong and S.-P. Chai, *Chem. Rev.*, 2016, **116**, 7159–7329.
- 2 J. Liu, H. Wang and M. Antonietti, *Chem. Soc. Rev.*, 2016, 45, 2308–2326.
- 3 Y. Wang, Y. Li, X. Bai, Q. Cai, C. Liu, Y. Zuo, S. Kang and L. Cui, *Catal. Commun.*, 2016, **84**, 179–182.
- 4 Q. Wang, A. Chen, X. Wang, J. Zhang, J. Yang and X. a. Li, *J. Mol. Catal. A: Chem.*, 2016, **420**, 159–166.
- 5 X. Li, W. Bi, L. Zhang, S. Tao, W. Chu, Q. Zhang, Y. Luo, C. Wu and Y. Xie, *Adv. Mater.*, 2016, 28, 2427–2431.
- 6 C. Han, L. Wu, L. Ge, Y. Li and Z. Zhao, *Carbon*, 2015, **92**, 31–40.
- 7 T. Xiong, W. Cen, Y. Zhang and F. Dong, *ACS Catal.*, 2016, 6, 2462–2472.
- 8 Y. Fu, T. Huang, L. Zhang, J. Zhu and X. Wang, *Nanoscale*, 2015, 7, 13723–13733.
- 9 R. Kuriki, H. Matsunaga, T. Nakashima, K. Wada, A. Yamakata, O. Ishitani and K. Maeda, *J. Am. Chem. Soc.*, 2016, **138**, 5159–5170.

- 10 Y. Wang, X. Bai, H. Qin, F. Wang, Y. Li, X. Li, S. Kang, Y. Zuo and L. Cui, ACS Appl. Mater. Interfaces, 2016, 8, 17212–17219.
- 11 J. Liu, Y. Liu, N. Liu, Y. Han, X. Zhang, H. Huang, Y. Lifshitz, S.-T. Lee, J. Zhong and Z. Kang, *Science*, 2015, 347, 970–974.
- 12 F. Goettmann, A. Fischer, M. Antonietti and A. Thomas, *Angew. Chem., Int. Ed.*, 2006, **45**, 4467–4471.
- 13 M. Abdullah Khan, I. F. Teixeira, M. M. J. Li, Y. Koito and S. C. E. Tsang, *Chem. Commun.*, 2016, **52**, 2772–2775.
- 14 S. Verma, R. B. N. Baig, M. N. Nadagouda and R. S. Varma, *ACS Sustainable Chem. Eng.*, 2016, 4, 1094–1098.
- 15 R. B. N. Baig, S. Verma, R. S. Varma and M. N. Nadagouda, ACS Sustainable Chem. Eng., 2016, 4, 1661–1664.
- 16 P. Zhang, J. Deng, J. Mao, H. Li and Y. Wang, *Chin. J. Catal.*, 2015, 36, 1580–1586.
- 17 F. Z. Su, S. C. Mathew, G. Lipner, X. Z. Fu, M. Antonietti, S. Blechert and X. C. Wang, *J. Am. Chem. Soc.*, 2010, 132, 16299–16301.

- 18 B. Long, Z. Ding and X. Wang, *ChemSusChem*, 2013, 6, 2074–2078.
- 19 P. Zhang, Y. Wang, J. Yao, C. Wang, C. Yan, M. Antonietti and H. Li, *Adv. Synth. Catal.*, 2011, 353, 1447–1451.
- 20 H. Han, G. Ding, T. Wu, D. Yang, T. Jiang and B. Han, *Molecules*, 2015, **20**, 12686.
- 21 Z. Ding, X. Chen, M. Antonietti and X. Wang, *ChemSusChem*, 2011, 4, 274–281.
- 22 S. Verma, R. B. Nasir Baig, M. N. Nadagouda and R. S. Varma, *ACS Sustainable Chem. Eng.*, 2016, 4, 2333–2336.
- 23 F. Su, S. C. Mathew, L. Möhlmann, M. Antonietti, X. Wang and S. Blechert, *Angew. Chem., Int. Ed.*, 2011, **50**, 657–660.
- 24 D. J. Martin, K. Qiu, S. A. Shevlin, A. D. Handoko, X. Chen, Z. Guo and J. Tang, *Angew. Chem., Int. Ed.*, 2014, 53, 9240–9245.
- 25 J. Pan, Y. Sheng, J. Zhang, J. Wei, P. Huang, X. Zhang and B. Feng, *J. Mater. Chem. A*, 2014, 2, 18082–18086.
- 26 R. A. Sheldon, Green Chem., 2017, 19, 18-43.
- 27 P. G. Jessop, Green Chem., 2011, 13, 1391-1398.
- 28 http://www.eea.europa.eu/ (accessed on 19.02.2017).