

## PAPER

View Article Online  
View Journal | View IssueCrossMark  
click for updatesCite this: *RSC Adv.*, 2017, 7, 1498Received 21st November 2016  
Accepted 12th December 2016

DOI: 10.1039/c6ra27073e

www.rsc.org/advances


## Heterogeneous cobalt catalysts for selective oxygenation of alcohols to aldehydes, esters and nitriles†

Fei Mao, Zhengliang Qi, Haipeng Fan, Dejun Sui, Rizhi Chen and Jun Huang\*

Efficient and green oxygenation of alcohols to the corresponding aldehydes, esters and nitriles was developed with high selectivity. Functional alcohols, including some heterocyclic and allylic alcohols can be oxygenated to the corresponding aldehydes, esters and nitriles respectively. Moreover, the catalyst can be recycled and reused without significant deactivation. Noteworthy, the Co@NC (800–2h) catalyzed oxygenation of alcohols can be regulated easily by changing the reaction conditions, and then the corresponding aldehydes, esters and nitriles can be obtained in high yields respectively.

## Introduction

Selective oxygenation of alcohols is not only of wide concern in basic chemistry research, but it is also a great challenge for the production of bulk chemical.<sup>1</sup> Selective oxidation of alcohols is a powerful tool in the synthesis of complex organic molecules such as natural products, pharmaceuticals and polymers.<sup>2</sup> Generally, esters are prepared by a two-step synthetic procedure, involving the synthesis of the carboxylic acids or activated acid derivatives, and a subsequent reaction with alcohols.<sup>3</sup> As a result, the multistep process is often accompanied by the formation of toxic and harmful byproducts.<sup>4</sup> At the same time, nitriles are important building blocks of dyes, natural products, herbicides, agrochemicals, and pharmaceuticals, and the preparation of nitriles is often through multistep process using toxic HCN or metal cyanides.<sup>5</sup> The ammoxidation has been developed for the production of some nitriles under drastic conditions in industrial application.<sup>6</sup> The development of selective oxidation reactions is an important topic and is crucial for the advancement of green and sustainable industrial processes.<sup>7</sup> In recent years, much effort has been devoted to the oxidation of alcohols to esters by a single step, which could represent a big step forward toward green, economic, and sustainable processes because of the availability and low cost of alcohols in comparison to their oxidation products such as aldehydes and carboxylic acids.<sup>8</sup> But the relevant reports are limited to noble metal catalysts, such as palladium, gold, and ruthenium. Moreover, some homogeneous systems are used for the oxidation process, which are economically unfavorable.<sup>9</sup> So,



Scheme 1 Selective oxidation of alcohols to ester, aldehyde and nitriles.

it is desirable to develop cost-effective, heterogeneous catalysts with good selectivity.<sup>10</sup> A possible solution to this problem can be the increased utilization of cheap metal catalysts, such as iron, cobalt and copper catalysts.<sup>11</sup>

Recently, some cobalt and iron catalysts were reported for the oxidation of alcohols to the corresponding esters and nitriles, and good yields were obtained.<sup>12</sup> A heterogeneous Co catalyst system was reported by us for the reductive amination of aldehydes and ketones, and the Co catalyst system exhibited good activity and excellent selectivity.<sup>13</sup> Herein, the heterogeneous Co catalysts were used for the selective oxidation of alcohols. Through controlling the reaction conditions, the Co catalyzed oxygenation of alcohols can give esters, aldehydes and nitriles selectively (Scheme 1).

## Results and discussion

As developed previously, the supported cobalt catalysts (Co@NC) were prepared by pyrolysis of Co(OAc)<sub>2</sub> with 1-methyl-3-cyanomethyl-1*H*-imidazolium chloride ([MCNIm]<sup>+</sup>Cl<sup>−</sup>) in activated carbon (detailed experimental see ESI†). The prepared Co@NC catalysts were tested for the oxidative cross esterification of benzyl alcohol with methanol to methyl benzoate with O<sub>2</sub> as the oxidant with addition of K<sub>2</sub>CO<sub>3</sub> as a base. The

State Key Laboratory of Materials-Oriented Chemical Engineering, College of Chemical Engineering, Nanjing Tech University, Nanjing 210009, P. R. China. E-mail: junhuang@njtech.edu.cn; Fax: +86-25-83172261

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c6ra27073e



Table 2 (Contd.)

Entry	Alcohol	Product	Yield <sup>b</sup> (%)
11			85
12			85
13			86
14			87
15			98
16			91
17			88
18			95
19			90

<sup>a</sup> Reaction conditions: 1.0 mmol of benzyl alcohol, 3.0 mol% Co with Co@NC (800-2h), 4.0 mL of CH<sub>3</sub>OH, 0.2 mmol of K<sub>2</sub>CO<sub>3</sub>, under 1 bar O<sub>2</sub>, at 60 °C, 20 h. <sup>b</sup> Isolated yields.

esters in high yields. Benzyl alcohols substituted with *p*-OMe, *m*-OMe, *p*-Me, *m*-Me and *o*-Me groups can be converted to the corresponding methyl esters in high yields (88–97%) (Table 2, entries 2–6). Moreover, the oxidation of nitrobenzyl alcohol in

methanol gave methyl nitrobenzoate in 94% yield (Table 2, entry 7). Notably, the oxidation of halides (including F, Cl and Br) substituted benzyl alcohols afforded the corresponding methyl benzoates in good yields (Table 2, entries 8–13). Naphthalenemethanol and (methylenedioxy) phenylmethanol were oxidized into the corresponding methyl esters in good yields (Table 2, entries 14, 15). The oxidation of cinnamic alcohol in methanol gave methyl cinnamate in 91% yield. Besides, heterocycle alcohols, furfuralcohol, and pyridine-2-methanol and pyridine-3-methanol were transferred into the corresponding heterocyclic carboxylic acid esters in good yields (Table 2, entries 17–19).

As benzaldehyde was obtained as a byproduct in the cross oxidative esterification of benzyl alcohol with methanol, the selective oxidation of benzyl alcohol to benzaldehyde was tested. Without base added, Co@NC (800-2h) catalyzed selective oxidation of benzyl alcohol gave benzaldehyde in excellent yield (Table 3, entry 1). Encouraged by the success, we examined various benzyl alcohols for the oxidation, and the results are listed in Table 3. Benzyl alcohols with functional groups, such as CH<sub>3</sub>, NO<sub>2</sub>, F, Cl, Br and MeO, can be oxidized efficiently to the corresponding benzaldehydes in good to excellent yields (Table 3, entries 2–9). The Co@NC (800-2h) catalyzed oxidation of diphenylmethanol afforded the benzophenone in good yield (Table 3, entry 10). Besides, cinnamyl alcohol can also be applied in this system, and cinnamaldehyde was obtained in 90% yield (Table 3, entry 11). Additionally, heterocyclic substrates such as 2-pyridinemethanol and furfuralcohol, were converted to the pyridylaldehyde and furfuraldehyde in 90% and 89% yields respectively (Table 3, entries 12 and 13). Base can speed up the oxidation of alcohols but reduce the selectivity. Without base, aldehydes can be obtained selectively under mild conditions.

Next, we tried the ammoxidation of alcohols to nitriles, as nitriles are widely applicable in pharmaceuticals and biology active molecules. Delightedly, the Co@NC (800-2h) catalyst also allows the straightforward synthesis of nitriles from alcohols using aqueous ammonia and molecular oxygen. It was observed that the oxidation of substituted benzyl alcohols gave the corresponding nitriles in good to excellent yields (Table 4, entries 1–14). But slightly low yields of nitriles were obtained when *ortho*-substituted benzyl alcohols were used for the ammoxidation reaction (Table 4, entries 10–12). Moreover, cinnamonitrile can be obtained in high yield from the ammoxidation of cinnamyl alcohol (Table 4, entry 15).

The reusability of Co@NC (800-2h) was investigated for the oxidation of benzyl alcohol to methyl benzoate, benzaldehyde and benzonitrile respectively. The recovered catalyst was reused after filtered, washed and dried under vacuum at room temperature. Under the same reaction conditions, methyl benzoate, benzaldehyde and benzonitrile can be obtained in excellent yields respectively with the reused Co@NC (800-2h) catalyst (Fig. 1). No evident deactivation was found after 8 times of reusability of the Co@NC (800-2h) catalyst in all the 3 oxidation reactions (Fig. 1). Moreover, no Co was detected (ICP-AES) in the solution after removal of the Co@NC (800-2h) by filtration.



Table 3 The oxygenation of alcohols to aldehydes<sup>a</sup>

$\text{R-CH}_2\text{OH} \xrightarrow[\text{EtOH, 80}^\circ\text{C, 30h}]{\text{Co@NC(800-2), 1bar O}_2} \text{R-CHO}$			
Entry	Alcohol	Product	Yield <sup>b,c</sup> (%)
1			99, 96
2			99, 95
3			95, 93
4			95, 94
5			92, 88
6			96, 93
7			97, 94
8			94, 90
9			90, 87
10			94, 94
11			90, 87
12			89, 93
13			90, 85

<sup>a</sup> Reaction conditions: 1.0 mmol of alcohol, 2.0 mL of EtOH, 5.0 mol% Co with Co@NC (800-2h), under 1 bar O<sub>2</sub>, at 80 °C, 30 h. <sup>b</sup> GC yields.

<sup>c</sup> Isolated yields (isolated yields are slightly lower than related GC yields for volatile products).

Table 4 The ammoxidation of alcohols to nitriles<sup>a</sup>

$\text{R-CH}_2\text{OH} + \text{NH}_3 \xrightarrow[\text{t-amyl alcohol, 130}^\circ\text{C, 24h}]{\text{Co@NC(800-2), 5bar O}_2} \text{R-CN}$			
Entry	Alcohol	Product	Yield <sup>b,c</sup> (%)
1			99, 94
2			97, 93
3			98, 94
4			95, 92
5			92, 89
6			98, 95
7			96, 93
8			97, 93
9			97, 94
10			91, 87
11			93, 90
12			92, 90
13			95, 93



Table 4 (Contd.)

$\text{R-CH}_2\text{OH} + \text{NH}_3 \xrightarrow[\text{t-amyl alcohol, 130}^\circ\text{C, 24h}]{\text{Co@NC(800-2), 5bar O}_2} \text{R-CN}$			
Entry	Alcohol	Product	Yield <sup>b,c</sup> (%)
14			94, 92
15			97, 93

<sup>a</sup> Reaction conditions: 1.0 mmol of alcohol, 2.0 mL of *t*-amyl alcohol, 5.0 mol% Co with Co@NC (800-2h), 200  $\mu$ l of aq.  $\text{NH}_3$ , under 5 bar  $\text{O}_2$ , at 130  $^\circ\text{C}$ , 24 h. <sup>b</sup> GC yields. <sup>c</sup> Isolated yields (isolated yields are slightly lower than related GC yields for volatile products).

To investigate the relationship of the catalyst structure with the performance, the catalysts were characterized by XRD, XPS, TEM, SEM and  $\text{N}_2$  adsorption analysis. Since the catalysts were applied for the reductive amination of aldehydes with amines, and the catalyst structure was studied extensively.<sup>13</sup> As we can see only metallic  $\beta$ -Co peaks but no  $\text{CoO}$  or  $\text{Co}_3\text{O}_4$  peaks from XRD spectra, we can image that the  $\text{Co(0)}$  particles were coated with  $\text{CoO}$  in the  $\text{Co@NC(800-2h)}$  since  $\text{Co}^{2+}$  was detected by XPS spectra (Fig. S1 and S2 $^\dagger$ ). It is interesting that the recycled  $\text{Co@NC(800-2h)}$  was nearly the same XRD spectra, we can see only metallic  $\beta$ -Co peaks from the XRD spectra (Fig. S2B $^\dagger$ ), which means Co in the recycled  $\text{Co@NC(800-2h)}$  was also  $\text{Co(0)}$  particles coated with  $\text{CoO}$ . With variable chemical valences, cobalt is able to transfer electrons and act as the active site for oxygen transfer.<sup>14</sup> Thus, the obtained  $\text{Co@NC(800-2h)}$  is responsible for the catalytic activity of the oxidations. Based on above oxidation reaction results, we proposed the pathway of the oxidation of alcohols to aldehydes, esters and nitriles





Fig. 1 The reusability of  $\text{Co@NC(800-2h)}$  for the oxidative esterification of benzyl alcohol (left); oxygenation of benzyl alcohol to benzaldehyde (middle); the ammoxidation of benzyl alcohol to benzonitrile (right).



Scheme 2 Proposed pathway of the oxidation of alcohols to aldehydes, esters and nitriles.

(Scheme 2). The alcohols are oxidized to the corresponding aldehydes (A) firstly, and then reacted with methanol or  $\text{NH}_3$  to the intermediates B or C (Scheme 2). Finally, the B and the C can be oxidized to esters and nitriles respectively.

## Conclusions

In summary, effective Co catalysts were developed and applied for the selective oxygenation of alcohols to aldehydes, esters and nitriles. The catalysts  $\text{Co@NC}$  can be prepared simply and applied widely for the selective oxidations. Noteworthy, the  $\text{Co@NC(800-2h)}$  catalyzed oxygenation of alcohols can be regulated easily by changing the reaction conditions, and then the corresponding aldehydes, esters and nitriles can be obtained respectively. In addition, functional alcohols, including heterocyclic and allylic alcohols can also be oxygenated to the corresponding aldehydes, esters and nitriles respectively. Moreover, the catalyst can be recycled and reused without significant deactivation. Thus, green, economical and sustainable processes to aldehydes, esters and nitriles were developed using oxygen as final oxidant with high selectivity.

## Acknowledgements

This work was supported by the National Natural Science of Foundation of China (grant no. 21676140), the fund from the State Key Laboratory of Materials-Oriented Chemical Engineering (grant ZK201402) and the Project of Priority Academic Program Development of Jiangsu Higher Education Institutions (PAPD).

## Notes and references

- (a) C. Liu, H. Zhang, W. Shi and A. Lei, *Chem. Rev.*, 2011, **111**, 1780–1824; (b) S. Gaspa, A. Porcheddu and L. D. Luca, *Adv. Synth. Catal.*, 2016, **358**, 154–158; (c) B. Karimi, M. Rafiee, S. Alizadeha and H. Vali, *Green Chem.*, 2015, **17**, 991–1000; (d) J. B. Xie, J. J. Bao, H. X. Li, D. W. Tan, H. Y. Li and J. P. Lang, *RSC Adv.*, 2014, **4**, 54007–54017.
- (a) L. L. Chang, J. H. Yang and J. Y. Ying, *ChemSusChem*, 2015, **8**, 1916–1925; (b) R. V. Jagadeesh, H. Junge, M. Pohl, J. Radnik, A. Bruckner and M. Beller, *J. Am. Chem. Soc.*,





- 2013, **135**, 10776–10782; (c) L. Y. Wang, S. S. Shang, G. S. Li, L. H. Ren, Y. Lv and S. Gao, *J. Org. Chem.*, 2016, **81**, 2189–2193; (d) R. V. Jagadeesh, H. Junge and M. Beller, *Nat. Commun.*, 2014, **5**, 4123; (e) R. A. Molla, K. Ghosh, K. Tuhina and S. M. Islam, *New J. Chem.*, 2015, **39**, 921–930.
- 3 J. Otera, *Esterification: Methods, Reactions, and Applications*, Wiley-VCH, Weinheim, 2003.
- 4 (a) K. D. Chau, F. Duus and T. N. Le, *Green Chem. Lett. Rev.*, 2013, **6**, 89–93; (b) J. D. Nguyen, E. M. D'Amato, J. M. Narayanam and C. R. Stephenson, *Nat. Chem.*, 2012, **4**, 854–859.
- 5 (a) P. Anbarasan, T. Schareina and M. Beller, *Chem. Soc. Rev.*, 2011, **40**, 5049–5067; (b) M. Sundermeier, A. Zapf, S. Mutyala and W. Baumann, *Chem.–Eur. J.*, 2003, **9**, 1828–1836.
- 6 (a) S. J. Guo, G. Wan, S. Sun, Y. Jiang, J. T. Yu and J. Cheng, *Chem. Commun.*, 2015, **51**, 5085–5088; (b) C. P. Kumar, K. R. Reddy, V. V. Rao and K. V. R. Chary, *Green Chem.*, 2002, **4**, 513–516; (c) L. Wang, B. Guo, H. X. Li, Q. Li, H. Y. Li and J. P. Lang, *Dalton Trans.*, 2013, **42**, 15570–15580.
- 7 (a) Y. X. Zhou, Y. Z. Chen, L. N. Cao, J. L. Lu and H. L. Jiang, *Chem. Commun.*, 2015, **51**, 8292–8295; (b) J. Miura, T. Akaogi and H. Ishida, *ACS Catal.*, 2013, **3**, 1845–1849.
- 8 (a) C. Liu, J. Wang, L. Meng, Y. Deng, Y. Li and A. Lei, *Angew. Chem., Int. Ed.*, 2011, **50**, 5144–5148; (b) H. Wang, L. Li, X. F. Bai, J. Y. Shang, K. F. Yang and L. W. Xu, *Adv. Synth. Catal.*, 2013, **355**, 341–347; (c) C. H. Bai, A. Q. Li, X. F. Yao, H. L. Liu and Y. W. Li, *Green Chem.*, 2016, **18**, 1061–1069; (d) A. M. Whittaker and V. M. Dong, *Angew. Chem., Int. Ed.*, 2015, **54**, 1312–1315; (e) X. L. Lang, M. Q. Shi, Y. K. Jiang, H. Chen and C. N. Ma, *RSC Adv.*, 2016, **6**, 13873–13880.
- 9 (a) A. Corma, H. Garcia and F. X. Llabrès, *Chem. Rev.*, 2010, **110**, 4606–4655; (b) L. M. Dornan and M. J. Muldoon, *Catal. Sci. Technol.*, 2015, **5**, 1428–1432; (c) C. Liu, S. Tang and A. Lei, *Chem. Commun.*, 2013, **49**, 1324; (d) J. H. Xia, A. L. Shao, S. Tang, X. L. Gao, M. Gao and A. W. Lei, *Org. Biomol. Chem.*, 2015, **13**, 6154–6157; (e) S. Wang, S. T. Yin, G. W. Chen, L. Li and H. Zhang, *Catal. Sci. Technol.*, 2016, **6**, 4090–4104; (f) H. Miyamura, T. Yasukawa and V. Kobayashi, *Green Chem.*, 2010, **12**, 776–778; (g) K. Kaizuka, H. Miyamura and S. Kobayashi, *J. Am. Chem. Soc.*, 2010, **132**, 15096–15098; (h) C. Gunanathan, L. J. W. Shimon and D. Milstein, *J. Am. Chem. Soc.*, 2009, **131**, 3146–3147; (i) C. M. Nicklaus, P. H. Phua, T. Buntara, S. Noel, H. J. Heeres and J. G. Vries, *Adv. Synth. Catal.*, 2013, **355**, 2839–2844; (j) T. L. Gianetti, S. P. Annen, G. S. Quinones, M. Reiher, M. Driess and H. Grützmaier, *Angew. Chem., Int. Ed.*, 2016, **55**, 1854–1858.
- 10 (a) W. Zhong, H. L. Liu, C. H. Bai, S. J. Liao and Y. W. Li, *ACS Catal.*, 2015, **5**, 1850–1856; (b) C. Parmeggiani and F. Cardona, *Green Chem.*, 2012, **14**, 547–564; (c) K. Ghosh, M. A. Iqbal, R. A. Molla, A. Mishra, Kamaluddin and S. Manirul Islam, *Catal. Sci. Technol.*, 2015, **5**, 1606–1622; (d) J. Gao, Z. G. Ren and J. P. Lang, *J. Organomet. Chem.*, 2015, **792**, 88–92.
- 11 (a) A. Boddien, D. Mellmann, F. Gartner, R. Jackstell, H. Junge, P. J. Dyson, G. Laurenczy, R. Ludwig and M. Beller, *Science*, 2011, **333**, 1733–1736; (b) H. Song, B. Kang and S. H. Hong, *ACS Catal.*, 2014, **4**, 2889–2895; (c) V. Lyaskovskyy, A. I. O. Suarez, H. Lu, H. Jiang, X. P. Zhang and B. Bruin, *J. Am. Chem. Soc.*, 2011, **133**, 12264–12273; (d) K.-I. Shimizu, K. Kon, M. Seto, K. Shimura, H. Yamazaki and J. N. Kondo, *Green Chem.*, 2013, **15**, 418; (e) J. E. Hein and V. V. Fokin, *Chem. Soc. Rev.*, 2010, **39**, 1302–1315; (f) C. Chen, B. Liu and W. Chen, *Synthesis*, 2013, **45**, 3387–3391; (g) M. Liu, T. Q. Chen and S. F. Yin, *Catal. Sci. Technol.*, 2016, **6**, 690–693; (h) D. W. Tan, J. B. Xie, Q. Li, H. X. Li, J. C. Li, H. Y. Li and J. P. Lang, *Dalton Trans.*, 2014, **43**, 14061–14071.
- 12 (a) R. V. Jagadeesh, T. Stemmler, A.-E. Surkus, M. Bauer, M.-M. Pohl, J. Radnik, K. Junge, H. Junge, A. Brückner and M. Beller, *Nat. Protoc.*, 2015, **10**, 916–926; (b) T. Y. Cheng, H. Yu, F. Peng, H. J. Wang, B. S. Zhang and D. S. Su, *Catal. Sci. Technol.*, 2016, **6**, 1007–1015; (c) L. L. Geng, M. Zhang, W. X. Zhang, M. J. Jia, W. F. Yan and G. Liu, *Catal. Sci. Technol.*, 2015, **5**, 3097–3102.
- 13 F. Mao, D. J. Sui, Z. L. Qi, H. P. Fan, R. Z. Chen and J. Huang, *RSC Adv.*, 2016, **6**, 94068–94073.
- 14 (a) H. Y. Jin, J. Wang, D. F. Su, Z. Z. Wei, Z. F. Pang and Y. Wang, *J. Am. Chem. Soc.*, 2015, **137**, 2688–2694; (b) A. M. Ullman and D. G. Nocera, *J. Am. Chem. Soc.*, 2013, **135**, 15053–15061; (c) P. X. Li, R. G. Ma, Y. Zhou, Y. F. Chen, Q. Liu, G. H. Peng and J. C. Wang, *RSC Adv.*, 2016, **6**, 70763–70769.

