# RSC Advances



# PAPER



Cite this: RSC Adv., 2017, 7, 16751

Received 10th January 2017 Accepted 9th March 2017 DOI: 10.1039/c7ra00413c

rsc.li/rsc-advances

# 1 Introduction

Fullerene  $C_{60}$  has been widely studied and employed in the elaboration of many opto-electronic and photovoltaic devices because of its remarkable electronic properties. This chromophore is considered one of the best molecular electron-acceptor groups able to participate in Förster Resonance Energy Transfer (FRET) and Charge Transfer (CT) phenomena either in solution or in the solid state.<sup>1-3</sup> However, the applications of fullerene  $C_{60}$  itself are very limited because of its poor solubility in organic solvents. The incorporation of alkyl chains and other functional groups into fullerene  $C_{60}$  has led to the development of novel molecular structures with enormous potential optical applications.<sup>4</sup>–<sup>8</sup> Very recently, some hybrid systems based on azo-dyes containing fullerene  $C_{60}$  units have been investigated due to their synergistic effect. Wang et al. reported the functionalization of fullerene  $C_{60}$  via the addition of a substituted azobenzene as a carbene active intermediate.<sup>9</sup> Kay et al. reported the synthesis and optical properties of a novel azodendrimer bearing a fullerene  $C_{60}$  unit as core.<sup>10</sup> Other related structures combining azobenzene-fullerene, exhibiting interesting optical properties, have been reported in the

# Synthesis, characterization and optical properties of novel dendronized azo-dyes containing a fullerene  $C_{60}$  unit and well-defined oligo(ethylene glycol) segments†

Jesús Ortíz-Palacios,<sup>a</sup> Gerardo Zaragoza-Galán,<sup>b</sup> Edgar Aguilar-Ortíz,<sup>a</sup> Efraín Rodríquez-Alba<sup>a</sup> and Ernesto Rivera<sup>\*a</sup>

Herein, we report the preparation and characterization of a novel series of dendronized azo-dyes containing a fullerene  $C_{60}$  unit and well-defined oligo(ethylene glycol) spacers. The azobenzene units present in these dyes were substituted in the 4'-position with different functional groups ( $-H$ ,  $-OCH_3$ ,  $-C_4H_9$ ,  $-CN$  and –NO2). The optical properties of these compounds were studied by absorption spectroscopy as a function of the dipole moment of the azobenzene moieties. All fullerene  $C_{60}$ -azobenzene derivatives exhibited trans–cis photoisomerization and photoprotonation under irradiation with UV-light. The results were compared to those obtained with their precursor azo-dyes without fullerene  $C_{60}$ . It was found that the presence of the fullerene unit significantly quenches the photoisomerization yield, whereas the photoprotonation was not affected by the presence of this chromophore. PAPER<br>
Synthesis, characterization and optical properties<br>
of novel dendronized azo-dyes containing<br>
of the sum  $(2\sqrt{2})$ <br>
of novel dendronized azo-dyes containing<br>
of the sum  $(2\sqrt{2})$ <br>
of the sum  $(2\sqrt{2})$ <br>
of the sum

literature.<sup>11</sup>–<sup>13</sup> Some of them led to the development of new materials for molecular photoswitching,<sup>9,10,14</sup> smart optoelectronic devices<sup>15</sup> and organic solar cells.<sup>16,17</sup>

Rau classified azobenzenes into three main categories based on their photochemical behaviour.<sup>18</sup> Unsubstituted photochromic azobenzene belong to the first category, known as "azobenzenes". The thermally stable trans isomer exhibits an intense absorption band at 350 nm due to the  $\pi-\pi^*$  transition, as well as a weak intensity band at 440 nm related to the n- $\pi^*$ transition, whereas the cis isomer undergoes similar transitions but with a more intense  $n-\pi^*$  band. Moreover, "azobenzenes" have a relatively poor overlap of the  $\pi-\pi^*$  and n– $\pi^*$  bands. The second category, known as "aminoazobenzenes" usually includes azobenzenes that are substituted by an electron-donor group and are characterized by the significant overlap of the  $\pi$ – $\pi$ \* and n– $\pi$ \* bands. Finally, azobenzenes bearing an electrondonor and an electron-acceptor group belong to the third category, named "pseudostilbenes", where the  $\pi-\pi^*$  and n– $\pi^*$  bands are practically superimposed and inverted on the energy scale.<sup>18</sup>

When donor–acceptor substituted azobenzenes are incorporated into a polymer backbone, they generate very versatile photoactive materials. In particular, the irradiation of these polymers with linear polarized light produces rapid trans–cis cis–trans photoisomerization of "pseudostilbene" azobenzenes. In consequence, polarized light allows the selective activation of "pseudostilbenes" bearing a polarization axis parallel to the absorbing radiation, which causes the photoalignment of the azobenzene moieties until they become perpendicular to the light polarization axis.<sup>16-22</sup>

<sup>&</sup>quot;Instituto de Investigaciones en Materiales, Universidad Nacional Autónoma de M´exico, Circuito Exterior Ciudad Universitaria, C. P. 04510, D.F, Mexico. E-mail: riverage@unam.mx

<sup>&</sup>lt;sup>b</sup>Facultad de Ciencias Químicas, Universidad Autónoma de Chihuahua, Campus Universitario, #2, Apartado Postal 669, Chihuahua, Mexico

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra00413c



Fig. 1 Synthesis of the fullerene  $C_{60}$ -azobenzene derivatives.

Our research group has developed different series of azo $dyes<sup>23-26</sup>$  and azo-polymers<sup>27,28</sup> with different structures. Very recently, we reported the preparation and optical properties of some photoactive azo-dendrons and azo-dendrimers bearing a liquid crystalline behaviour, which exhibited a photoprotonation phenomenon.<sup>29</sup> In this work, we describe the synthesis and characterization of a novel series of dendronized azo-dyes containing fullerene  $C_{60}$  units, flexible alkyl and oligo(ethylene glycol) spacers. The amino-azobenzenes reported in this work were substituted in the 4'-position with different functional groups  $(-H, -OCH<sub>3</sub>, -C<sub>4</sub>H<sub>9</sub>, -CN and -NO<sub>2</sub>)$ . The Bingel reaction was used in order to obtain novel fullerene  $C_{60}$ azobenzene branched systems (Fig. 1 vide infra), which exhibit trans–cis photoisomerization and photoprotonation under irradiation with UV-light. The optical properties of these compounds were studied in detail by absorption spectroscopy. The aim of this work is to demonstrate the ability of these compounds to modify their optical properties by photoprotonation and their susceptibility to favor the energy transfer phenomenon instead of the trans-cis photoisomerization due to the strong acceptor character of the fullerene unit.

## 2 Experimental

#### 2.1 General conditions

All reagents used in the synthesis of the fullerene  $C_{60}$ -azobenzene derivatives were purchased from Aldrich and used as received without further purification. Dichloromethane was dried by distillation over calcium hydride and anhydrous toluene was employed. Precursor azo-dyes were synthesized according to the method previously reported by  $us,^{23,24,30}$ whereas N-ethyl-N-(2-hydroxyethyl)-4-(4-nitrophenylazo) aniline (Disperse Red-1, DR1) was purchased from Aldrich. The fullerene  $C_{60}$  was incorporated into azobenzene derivatives as described in the literature.<sup>31,32</sup>

 ${}^{1}$ H and  ${}^{13}$ C NMR spectra of the intermediates and final compounds involved in the synthesis were recorded in  $CDCI<sub>3</sub>$ solution at room temperature on a Bruker Avance 400 MHz spectrometer, operating at 400 MHz and 100 MHz for <sup>1</sup>H and <sup>13</sup>C, respectively. All compounds were dissolved in spectral quality solvents purchased from Aldrich, and their absorption spectra were recorded on a Varian Cary 1 Bio UV-vis (model 8452A) spectrophotometer at room temperature, using 1 cm width quartz cuvettes. MALDI-TOF mass spectra were obtained on a Bruker Daltonic Felx Analysis, using dithranol as matrix.

Photoisomerization experiments were carried out in solution and solid state (cast film). For the disubstituted malonic derivatives  $(9, 10, 11)$  and the fullerene C<sub>60</sub>-azobenzene derivatives  $(15, 10)$ 16, 17) the photoisomerization experiments were conducted in DMF solution  $(2.5 \times 10^{-4} \text{ M})$  at room temperature. Cast films were prepared by depositing a saturated solution of the azo-dye on quartz substrates. Solutions and films were irradiated using a Compact UV lamp model UVGL-25, 254/365 nm (6 W). The samples were irradiated with intervals of 10 s and the spectral changes were monitored by absorption spectroscopy. Meanwhile, photoprotonation experiments with the fullerene  $C_{60}$ -azobenzene derivatives were carried out in  $CHCl<sub>3</sub>$  solution. Compounds 15 and 19 were irradiated at 254 nm and monitored by absorption spectroscopy with intervals of 10 and 30 s, respectively.

#### 2.2 Synthesis

2.2.1 Synthesis of the 3-dodecyloxy-5-hydroxybenzyl alcohol (1). First generation dendron  $G_1OH (1)$  was prepared according to the method previously reported by us.<sup>33</sup> The coupling constants were confirmed according a previous work reported by Fréchet et al.<sup>34</sup>

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta$  = 6.49 (t, *J* = 2 Hz, 2H, H<sup>1</sup>), 6.37  $(t, J = 2 \text{ Hz}, 1\text{H}, \text{H}^2)$ , 4.61 (s, 2H, PhCH<sub>2</sub>OH), 3.93 (t, J = 7 Hz, 4H, PhOCH<sub>2</sub>), 1.79-1.72 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.47-1.26 (m, 36H,

all CH<sub>2</sub> of the aliphatic chain), 0.88 (t, *J* = 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 160.52 (2C, C<sup>c</sup>), 143.16 (1C,  $\rm C^{a}),$  105.02 (2C,  $\rm C^{b}),$  100.52 (1C,  $\rm C^{d}),$  68.03 (2C, PhOCH<sub>2</sub>), 65.44 (1C, PhCH2OH), 31.90, 29.61–29.18, 26.02, 25.70, 22.87 (20C, all  $CH<sub>2</sub>$  of the aliphatic chain), 14.09 (2C, CH<sub>3</sub>) ppm.

2.2.2 Synthesis of 3-(3,5-bis(dodecyloxy)benzyloxy)-3-oxopropanoic acid (2). The synthesis of the monosubstituted malonic ester was achieved according to the method described in the literature.<sup>31</sup>

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>)  $\delta$  = 6.47 (d, J = 2 Hz), 6.42 (t, J = 2 Hz), 5.14, (s, 2H), 3.93 (t,  $J = 6$  Hz, 4H), 3.50 (s, 2H), 1.77 (m, 4H), 1.26 (m, 36H), 0.88 (t,  $J = 6$  Hz, 6H) ppm.

<sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 171.38, 166.37, 160.39,$ 136.88, 106.38, 101.22, 68.01, 67.46, 40.78, 31.87, 29.55–29.16, 25.97, 22.62, 14.05 ppm.

#### 2.3 Synthesis of the precursor azo-dyes

Precursor azo-dyes (4), (5) and RED-PEG-4 (7) were prepared according to the method previously reported by us.<sup>30,33,35</sup>

For the synthesis of azobenzenes  $(E)$ -2-(4-(phenyldiazenyl) phenyl)-5,8,11-trioxa-2-azatridecan-13-ol (3) and  $(E)$ -4- $((4-(2-(2-5))$ (2-(2-hydroxyethoxy)ethoxy)ethoxy)ethyl)(methyl)amino)phenyl) diazenyl)benzonitrile (6) (see ESI†).

#### 2.4 Synthesis of the disubstituted malonic ester

2.4.1 Synthesis of (E)-3,5-bis(dodecyloxy)benzyl-2-(4-(phenyldiazenyl)phenyl)-5,8,11-trioxa-2-azatridecan-13-yl-malonate (9). 3 (0.26 g, 0.67 mmol), N,N-dimethyl-4-aminopyridine (DMAP) (0.013 g, 0.1 mmol) and intermediate 2 (0.489 g, 0.87 mmol) were dissolved in 10 mL of anhydrous  $CH_2Cl_2$ . After that, a solution of N,N-dimethyl-4-aminopyridine (DCC) (0.18 g, 0.87 mmol) in 5 mL of anhydrous  $CH_2Cl_2$  was added dropwise. The reaction mixture was stirred at room temperature for 8 h. Then, the crude product was filtered on Celite many times until the urea was completely removed. The crude product was concentrated at reduced pressure and purified by column chromatography on silica gel using hexanes/ethyl acetate (8 : 2) as eluent to yield compound 9 (Scheme 1a). Yield: 55%. Paper<br>
2.3. Synthesis of the presenter article presented on 16 March 2017. The creative of  $P_1$ <sup>2</sup>/2 AM detection-12 AM. This are casen as the common and the methods of article is licensed in the synthesis And the synthe

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.87$  (d, J = 9 Hz, 2H, H<sup>5</sup>), 7.84 (d, J = 9 Hz, 2H, H<sup>4</sup>), 7.47-7.37 (m, 3H, H<sup>6</sup>-H), 6.75 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.47 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.41 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.09 (s, 2H, PhCH<sub>2</sub>OOC), 4.29 (t,  $J = 5$  Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.92 (t,  $J = 6$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.68-3.59 (m, 14H,  $CH<sub>2</sub>N$  y  $OCH<sub>2</sub>$  of the tetra(ethylene glycol) chain), 3.46 (s, 2H, OOCCH<sub>2</sub>COO), 3.07 (s, 3H, CH<sub>3</sub>N), 1.80-1.71 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.46-1.39 (m, 4H, PhO(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 1.36-1.27 (m, 32H, all CH<sub>2</sub> of the aliphatic

chain), 0.90 (t, J = 6 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 166.17 (1C, C<sup>g</sup>), 166.01 (1C, C<sup>e</sup>), 160.28 (2C, C<sup>b</sup>), 153.00 (1C, C<sup>h</sup>), 151.22 (1C, C<sup>l</sup>), 143.45 (1C,  $(\mathrm{C}^\mathrm{k}), 137.08\,(\mathrm{1C},\mathrm{C}^\mathrm{d}), 129.14\,(\mathrm{1C},\mathrm{C}^\mathrm{o}), 128.70\,(\mathrm{2C},\mathrm{C}^\mathrm{n}), 124.85\,(\mathrm{2C},$ C<sup>j</sup>), 122.02 (2C, C<sup>m</sup>), 111.21 (2C, C<sup>i</sup>), 106.20 (2C, C<sup>c</sup>), 100.94 (1C, C<sup>a</sup>), 70.58-70.41, 68.37 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 68.59 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 67.85 (1C, PhCH<sub>2</sub>O), 66.96 (1C, NH<sub>2</sub>(CH<sub>2</sub>)<sub>2</sub>), 64.35 (1C, COOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 51.97 (1C, NCH<sub>2</sub>), 41.18 (1C, C<sup>f</sup>), 39.00 (1C, NCH3), 31.75, 29.50–29.07, 25.88, 22.52 (20C, all CH2 of the aliphatic chain),  $13.97$  (2C, CH<sub>3</sub>) ppm.



Scheme 1

2.4.2 Synthesis of (E)-3,5-bis(dodecyloxy)benzyl-2-(4-((4 butylphenyl)diazenyl)phenyl)-5,8,11-trioxa-2-azatridecan-13-ylmalonate (10). Procedure described for the synthesis of 9, using 4 (0.2 g, 0.5 mmol), DMAP (0.008 g, 0.07 mmol), 2 (0.329 g, 0.6 mmol) and DCC  $(0.120 \text{ g}, 0.58 \text{ mmol})$  to give compound  $10$ (Scheme 1b). Yield: 67%.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.83$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.74  $(d, J = 8$  Hz, 2H, H<sup>4</sup>), 7.26  $(d, J = 8$  Hz, 2H, H<sup>6</sup>), 6.75  $(d, J = 1)$ 9 Hz, 2H, H<sup>3</sup>), 6.46 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.09 (s, 2H, PhCH<sub>2</sub>OOC), 4.29 (t,  $J = 5$  Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.92 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.69-3.60 (m, 14H,  $CH<sub>2</sub>N$   $\gamma$  OCH<sub>2</sub> of the tetra(ethylene glycol) chain),  $3.45$  (s,  $2H$ , OOCCH<sub>2</sub>COO),  $3.09$  (s, 3H, CH<sub>3</sub>N), 2.67 (t,  $J = 8$  Hz, 2H, PhCH<sub>2</sub>), 1.79–1.70 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.68–1.57 (m, 2H, Ph(CH<sub>2</sub>)<sub>2</sub>), 1.45–1.26 (m, 38H, Ph(CH<sub>2</sub>)<sub>3</sub> and all CH<sub>2</sub> of the aliphatic chain), 0.95 (t,  $J = 7$  Hz, 6H, CH<sub>3</sub>), 0.89 (t,  $J = 6$  Hz, 3H, Ph(CH<sub>2</sub>)CH<sub>3</sub>) ppm.

6H, CH<sub>3</sub>), 0.89 (t, *J* = 6 Hz, 3H, Ph(CH<sub>2</sub>)CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 166.37 (1C, C<sup>g</sup>), 166.21 (1C, C<sup>e</sup>), 160.43 (2C, C<sup>b</sup>), 151.38 (1C, C<sup>h</sup>), 151.14 (1C, C<sup>l</sup>), 144.63 (1C, C $^{\rm o}$ ), 143.68 (1C, C $^{\rm k}$ ), 137.18 (1C, C $^{\rm d}$ ), 128.90 (2C, C $^{\rm n}$ ), 124.77 (2C, C<sup>m</sup>), 122.09 (2C, C<sup>i</sup>), 111.38 (2C, C<sup>i</sup>), 106.39 (2C, C<sup>c</sup>), 101.10 (1C,  $C<sup>a</sup>$ ), 70.74-70.57, 68.76 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 67.17 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 68.52 (1C, PhCH<sub>2</sub>O), 68.05 (1C, N(CH<sub>2</sub>)<sub>2</sub>) 64.53 (1C, COOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 52.15 (1C, NCH<sub>2</sub>), 41.34 (1C, C<sup>f</sup>) 39.18  $(1C, NCH<sub>3</sub>), 35.46 (1C, PhCH<sub>2</sub>), 33.48 (1C, PhCH<sub>2</sub>CH<sub>2</sub>), 31.88,$ 29.63–29.21, 26.01, 22.65 (20C, all CH2 of the aliphatic chain), 22.30 (1C, Ph $(CH_2)_{2}CH_2$ ), 14.08 (2C, CH<sub>3</sub>), 13.91 (1C,  $Ph(CH_2)_3CH_3)$  ppm.

2.4.3 Synthesis of (E)-3,5-bis(dodecyloxy)benzyl-2-(4-((4 methoxyphenyl)diazenyl)phenyl)-5,8,11-trioxa-2-azatridecan-13-yl-malonate (11). Procedure described for the synthesis of 9, using 5 (0.2 g, 0.5 mmol), DMAP (0.009 g, 0.7 mmol), 2 (0.309 g, 0.6 mmol) and DCC (0.118 g, 0.7 mmol), to give compound 11 (Scheme 1c). Yield: 43%.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.83$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.81 (d, J = 9 Hz, 2H, H<sup>4</sup>), 6.97 (d, J = 9 Hz, 2H, H<sup>6</sup>), 6.76 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.46 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.09 (s, 2H, PhCH<sub>2</sub>OOC), 4.29 (t,  $J = 5$  Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.92 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.86 (s, 3H, PhOCH<sub>3</sub>), 3.69-3.61 (m, 14H, CH<sub>2</sub>N y OCH2 of the tetra(ethylene glycol) chain), 3.46 (s, 2H, OOCCH2COO), 3.08 (s, 3H, CH3N), 1.78–1.75 (m, 4H, PhOCH2- CH<sub>2</sub>), 1.44–1.26 (m, 36H, all CH<sub>2</sub> of the aliphatic chain), 0.88 (t,

 $J$  = 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 166.35 (1C, C<sup>g</sup>), 166.19 (1C,  $(C^{e})$ , 160.78 (1C,  $C^{o}$ ), 160.42 (2C,  $C^{b}$ ), 150.92 (1C,  $C^{h}$ ), 147.43  $({\rm 1C},{\rm C}^{\rm l}),$  143.64  $({\rm 1C},{\rm C}^{\rm k}),$  137.18  $({\rm 1C},{\rm C}^{\rm d}),$  124.53  $({\rm 2C},{\rm C}^{\rm j}),$  123.76  $(2C, C^m)$ , 114.02  $(2C, C^n)$ , 111.41  $(2C, C^i)$ , 106.38  $(2C, C^c)$ , 101.09 (1C, C<sup>a</sup>), 70.73-70.56, 68.75 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 68.52 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 68.04 (1C, PhCH<sub>2</sub>O), 67.15 (1C, N(CH<sub>2</sub>)<sub>2</sub>), 64.52 (1C, COOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 55.43 (1C, NCH<sub>2</sub>), 52.16 (1C, OCH<sub>3</sub>), 41.33 (1C, C<sup>f</sup>), 39.15 (1C, NCH<sub>3</sub>), 31.87, 29.62–29.20, 26.00, 22.64 (20C, all CH2 of the aliphatic chain), 14.07 (2C, CH<sub>3</sub>) ppm.

2.4.4 Synthesis of  $(E)$ -3,5-bis(dodecyloxy)benzyl-2- $(4-(4-1))$ cyanophenyl)diazenyl)phenyl)-5,8,11-trioxa-2-azatridecan-13-ylmalonate (12). Procedure described for the synthesis of 9, using 6 (0.205 g, 0.5 mmol), DMAP (0.009 g, 0.8 mmol), 2 (0.363 g, 0.6 mmol) and DCC (0.133 g, 0.64 mmol) to give compound 12 (Scheme 1d). Yield: 65%.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.86$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.85 (d, J = 10 Hz, 2H, H<sup>4</sup>), 7.70 (d, J = 9 Hz, 2H, H<sup>6</sup>), 6.75 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.45 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.08 (s, 2H, PhCH<sub>2</sub>OOC), 4.29 (t,  $J = 5$  Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.91 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.68-3.60 (m, 14H, CH<sub>2</sub>N  $\gamma$  OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.45 (s, 2H, OOCCH<sub>2</sub>COO), 3.11 (s, 3H, CH<sub>3</sub>N), 1.79-1.74 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.45-1.25 (m, 36H, all CH<sub>2</sub> of the aliphatic chain), 0.88 (t,  $J = 7$  Hz, 6H, CH<sub>3</sub>) ppm.

all CH<sub>2</sub> of the aliphatic chain), 0.88 (t, J = 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 166.26$  (1C, C<sup>g</sup>), 166.09 (1C,  $(C^e)$ , 160.36 (2C,  $C^b$ ), 155.31 (1C,  $C^l$ ), 152.24 (1C,  $C^h$ ), 143.48  $(1\text{C, C}^{\text{k}}), 137.11$   $(1\text{C, C}^{\text{d}}), 132.90$   $(2\text{C, C}^{\text{n}}), 125.77$   $(2\text{C, C}^{\text{m}}),$ 122.57 (2C, C<sup>j</sup>), 118.84 (1C, C<sup>o</sup>), 111.70 (1C, PhCN), 111.34 (2C,  $\rm C^i)$ , 106.31 (2C,  $\rm C^c)$ , 100.99 (1C,  $\rm C^a)$ , 70.70–70.50, 68.68 (6C,  $OCH<sub>2</sub>$  of the tetra(ethylene glycol) chain), 67.07 (PhOCH<sub>2</sub> of the aliphatic chain), 68.44 (1C, PhCH<sub>2</sub>O), 67.97 (1C, N(CH<sub>2</sub>)<sub>2</sub>), 64.42 (1C, COOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 52.07  $(1\rm{C}, \;NCH_2), \; 41.27 \; (1\rm{C}, \; C^f), \; 39.18 \; (1\rm{C}, \;NCH_3), \; 31.80, \; 29.55-$ 29.13, 25.93, 22.56 (20C, all CH2 of the aliphatic chain), 14.01  $(2C, CH<sub>3</sub>)$  ppm. BSC Advances Worwidestray (eq. 24.4 Symbol on 16 March 2017. This article is licensed on 16 March 2017. This article is licensed on 16 March 2017. The same of the symbol on the symbol on  $\mathbb{Z}$  are the symbol of  $\mathbb{Z}$ 

2.4.5 Synthesis of (E)-3,5-bis(dodecyloxy)benzyl-2-(4-((4 nitrophenyl)diazenyl)phenyl)-5,8,11-trioxa-2-azatridecan-13-ylmalonate (13). Procedure described for the synthesis of 9, using 7 (0.208 g, 0.5 mmol), DMAP (0.009 g, 0.8 mmol), 2 (0.352 g, 0.6 mmol) and DCC (0.129 g, 0.62 mmol) to give compound 13 (Scheme 1e). Yield: 77%.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 8.27$  (d,  $J = 9$  Hz, 2H, H<sup>6</sup>), 7.88 (d, J = 9 Hz, 2H, H<sup>5</sup>), 7.86 (d, J = 9 Hz, 2H, H<sup>4</sup>), 6.75 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.45 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.38 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.08 (s, 2H, PhCH<sub>2</sub>OCO), 4.29 (t,  $J = 5$  Hz, 2H, PhOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.90 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.69-3.60 (m, 14H, CH<sub>2</sub>N y OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.45 (s, 2H, OOCCH<sub>2</sub>COO), 3.11 (s, 3H, CH<sub>3</sub>N), 1.75-1.70 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.45-1.38 (m, 4H, PhO(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 1.33-1.24 (m, 32H, all CH<sub>2</sub> of the aliphatic

chain), 0.87 (t, J = 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 166.21$  (1C, C<sup>e</sup>), 166.06 (1C, C<sup>g</sup>), 160.45 (2C, C<sup>b</sup>), 156.74 (1C, C<sup>l</sup>), 152.54 (1C, C<sup>h</sup>), 147.34 (1C, C°), 143.77 (1C, C<sup>k</sup>), 137.21 (1C, C<sup>d</sup>), 125.99 (2C, C<sup>j</sup>), 124.50 (2C, C<sup>n</sup>), 122.49 (2C, C<sup>m</sup>), 111.46 (2C, C<sup>i</sup>), 106.42 (2C, C<sup>c</sup>), 101.18 (1C,  $C<sup>a</sup>$ ), 70.77-70.57, 68.74 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 67.08 (2C, PhOCH<sub>2</sub> of aliphatic chain), 68.55 (1C, PhCH<sub>2</sub>O), 68.06 (1C, N(CH<sub>2</sub>)<sub>2</sub>), 64.44 (1C, COOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 52.17 (1C, NCH<sub>2</sub>), 41.31 (1C, C<sup>f</sup>), 39.17  $(1C, NCH<sub>3</sub>), 31.81, 29.56-29.19, 25.97, 22.57 (20C, all CH<sub>2</sub> of the$ aliphatic chain),  $13.98$  (2C, CH<sub>3</sub>) ppm.

2.4.6 Synthesis of (E)-3,5-bis(dodecyloxy)benzyl-2-(ethyl(4- ((4-nitrophenyl)diazenyl)phenyl)amino)ethyl malonate (14). Procedure described for the synthesis of 9, using DR1 (0.1 g, 0.2 mmol), DMAP (0.006 g, 0.02 mmol), 2 (0.184 g, 0.2 mmol) and DCC (0.078 g, 0.2 mmol) to give compound 14 (Scheme 1f). Yield: 80%.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 8.31$  (d,  $J = 9$  Hz, 2H, H<sup>6</sup>), 7.91 (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.89 (d,  $J = 10$  Hz, 2H, H<sup>4</sup>), 6.76 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.46 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.09 (s, 2H, PhCH<sub>2</sub>OCO), 4.36 (t,  $J = 6$  Hz, 2H, NCH<sub>2</sub>CH<sub>2</sub>OCO), 3.91 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.66 (t,  $J =$ 6 Hz, 2H, CH<sub>3</sub>CH<sub>2</sub>NCH<sub>2</sub>), 3.51–3.46 (m, 2H, OCOCH<sub>2</sub>CH<sub>2</sub>NCH<sub>2</sub>) 3.45 (s, 2H, OOCCH<sub>2</sub>COO), 1.77-1.70 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.45–1.38 (m, 4H, PhO(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 1.31–1.20 (m, 35H, all CH<sub>2</sub> of the aliphatic chain and NCH<sub>2</sub>CH<sub>3</sub>), 0.88 (t,  $J = 7$  Hz, 6H,  $CH<sub>3</sub>$ ) ppm.

<sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 166.19$  (1C, C<sup>e</sup>), 165.91 (1C, C<sup>g</sup>), 160.54 (2C, C<sup>b</sup>), 156.74 (1C, C<sup>l</sup>), 151.10 (1C, C<sup>h</sup>), 147.54 (1C, C°), 144.01 (1C, C<sup>k</sup>), 137.16 (1C, C<sup>d</sup>), 126.21 (2C, C<sup>n</sup>), 124.58 (2C, C<sup>j</sup>), 122.63 (2C, C<sup>m</sup>), 111.48 (2C, C<sup>i</sup>), 106.61 (2C, C<sup>c</sup>), 101.21 (1C,  $C^2$ ), 68.15 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 67.26 (1C, PhCH<sub>2</sub>O), 62.23 (1C, CH<sub>3</sub>CH<sub>2</sub>NCH<sub>2</sub>CH<sub>2</sub>O), 48.57 (1C, CH<sub>3</sub>CH<sub>2</sub>-NCH<sub>2</sub>), 45.67 (1C, CH<sub>3</sub>CH<sub>2</sub>N), 41.43 (1C, C<sup>f</sup>), 31.88 (2C,  $CH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>$ ), 29.63–29.25 (14C, all CH<sub>2</sub> of the aliphatic chain), 26.03 (2C, PhO(CH<sub>2</sub>)<sub>3</sub>), 22.64 (2C, CH<sub>3</sub>CH<sub>2</sub>), 14.04 (1C, CH<sub>3</sub>), 12.27 (1C, NCH<sub>2</sub>CH<sub>3</sub>) ppm.

#### 2.5 Synthesis of the fullerene  $C_{60}$ -azobenzene derivatives

2.5.1 Synthesis of the fullerene  $C_{60}$ -amino substituted azobenzene (15). 9 (0.240 g, 0.3 mmol), I<sub>2</sub> (0.065 g, 0.025 mmol) and fullerene  $C_{60}$  (0.185 g, 0.3 mmol) were dissolved in 180 mL of anhydrous toluene. After some minutes, 1,8-diazabicyclo [5,4,0]undec-7-ene (DBU) (0.185 g, 0.85 mmol) was added dropwise. The reaction mixture was stirred at room temperature for 6 h. Then, the crude product was filtered, concentrated at reduced pressure and purified by column chromatography on silica gel. In the first column, a mixture toluene/hexane  $(1:1)$ was used as eluent in order to remove unreacted fullerene  $C_{60}$ . In the second column, a mixture of hexane/ethyl acetate (7 : 3 and 6 : 4) was employed to give the pure desired compound 15 (Scheme 2a). Yield: 31%. MALDI-TOF:  $C_{115}H_{83}N_3O_9$  calcd: [M +  $H$ <sup>+</sup> 1650.90 found  $(m/z)$ :  $[M + H]$ <sup>+</sup> 1651.93.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>) (Scheme 2a):  $\delta = 7.85$  (d, J = 9 Hz,  $2H, H<sup>5</sup>$ ), 7.83 (d, J = 8 Hz, 2H, H<sup>4</sup>), 7.48-7.38 (m, 3H, H<sup>6</sup>-H), 6.75  $(d, J = 9 \text{ Hz}, 2\text{H}, \text{H}^3), 6.58 (d, J = 2 \text{ Hz}, 2\text{H}, \text{H}^2), 6.40 (t, J = 2 \text{ Hz},$ 1H, H<sup>1</sup>), 5.43 (s, 2H, PhCH<sub>2</sub>OCO), 4.63 (t, *J* = 5 Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.89 (t,  $J = 6.50$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.83 (t,  $J = 5$ , 2H, OCH<sub>2</sub>), 3.68– 3.62 (m, 14H,  $CH<sub>2</sub>N$  y OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.09 (s, 3H, CH<sub>3</sub>N), 1.77-1.73 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.43-1.25 (m, 36H, all CH<sub>2</sub> of the aliphatic chain), 0.89 (t,  $J = 7$  Hz, 6H,  $CH<sub>3</sub>$ ) ppm.

 $^{13}$ C NMR (100 MHz, CDCl<sub>3</sub>) (Scheme 2a): 163.46 (1C, C<sup>g</sup>), 163.29 (1C, C<sup>e</sup>), 160.47 (2C, C<sup>b</sup>), 153.17 (1C, C<sup>h</sup>), 151.34 (1C, C<sup>l</sup>), 145.20, 145.16, 145.11, 144.97, 144.83, 144.63, 144.60, 144.55, 144.48, 144.41, 143.80, 143.78, 143.64, 143.01, 142.96, 142.89, 142.13, 141.85, 141.77, 140.84, 140.82, 139.34, 138.66 (fullerene carbons), 136.55 (1C, C<sup>d</sup>), 129.31 (1C, C<sup>o</sup>), 128.87 (2C, C<sup>n</sup>), 125.02 (2C, C<sup>j</sup>), 122.17 (2C, C<sup>m</sup>), 111.38 (2C, C<sup>i</sup>), 107.15 (2C, C<sup>c</sup>), 101.64 (1C, C<sup>a</sup>), 71.40 (fullerene carbon), 70.75-70.64, 68.91,



68.66 (7C, OCH2 of the chain tetra(ethylene glycol) chain), 68.53  $(2C, PhOCH<sub>2</sub>$  of the aliphatic chain), 68.11  $(1C, PhCH<sub>2</sub>O)$ , 66.18  $(\text{1C, NCH}_2), \text{52.15} \, (\text{1C, C}^\text{f}), \text{39.24} \, (\text{1C, NCH}_3), \text{31.90}, \text{29.67--29.26},$ 26.10, 22.67 (20C, CH<sub>2</sub> of the aliphatic chain), 14.12 (2C,  $CH<sub>3</sub>$ ) ppm.

2.5.2 Synthesis of the fullerene  $C_{60}$ -amino-butyl substituted azobenzene (16). Procedure employed for the synthesis of 15, using 10 (0.091 g, 0.1 mmol),  $I_2$  (0.023 g, 0.1 mmol), fullerene C<sub>60</sub> (0.066 g, 0.1 mmol) dissolved in 70 mL of anhydrous toluene, and DBU (0.046 g, 0.3 mmol), to obtain compound 16 (Scheme 2b). Yield: 40%. MALDI-TOF:  $C_{119}H_{91}N_3O_9$  calcd:  $[M + H]^+$  1707.01 found  $(m/z)$ :  $[M + H]$ <sup>+</sup> 1708.59.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.83$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.75  $(d, J = 8 \text{ Hz}, 2\text{H}, \text{H}^4),$  7.27  $(d, J = 7 \text{ Hz}, 2\text{H}, \text{H}^6),$  6.75  $(d, J = 1)$ 9 Hz, 2H, H<sup>3</sup>), 6.58 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.43 (s, 2H, PhCH<sub>2</sub>OOC), 4.62 (t,  $J = 5$  Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.89 (t,  $J = 6$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.83 (t,  $J = 5$  Hz, OCH<sub>2</sub>), 3.69–3.62 (m, 14H, CH<sub>2</sub>N y OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.09 (s, 3H, CH<sub>3</sub>N), 2.67 (t,  $J = 8$  Hz, 2H, PhCH<sub>2</sub>), 1.77-1.70 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.67-1.60 (m, 2H, Ph(CH<sub>2</sub>)<sub>2</sub>), 1.42-1.25 (m, 38H, Ph(CH<sub>2</sub>)<sub>3</sub> and all CH<sub>2</sub> of the aliphatic chain), 0.95 (t,  $J = 7$  Hz, 6H, CH<sub>3</sub>), 0.89 (t,  $J = 6$  Hz, 3H, Ph(CH<sub>2</sub>)CH<sub>3</sub>) ppm.

6H, CH<sub>3</sub>), 0.89 (t, *J* = 6 Hz, 3H, Ph(CH<sub>2</sub>)CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 163.46 (1C, C<sup>g</sup>), 163.31 (1C, C<sup>e</sup>), 160.54 (2C, C<sup>b</sup>), 151.46 (1C, C<sup>h</sup>), 151.18 (1C, C<sup>l</sup>), 144.67 (1C,  $(C^0)$ , 143.84 (1C,  $C^k$ ), 145.24, 145.20, 145.15, 145.05, 145.02, 144.87, 143.05, 143.00, 142.17, 141.89, 141.82, 140.88, 139.37, 138.71 (fullerene carbons), 136.60 (1C, C<sup>d</sup>), 128.91 (2C, C<sup>n</sup>), 124.82 (2C, C<sup>m</sup>), 122.16 (2C, C<sup>i</sup>), 111.46 (2C, C<sup>i</sup>), 107.24 (2C, C<sup>c</sup>), 101.77 (1C, C<sup>a</sup>), 71.49 (fullerene carbon), 70.76-70.69, 68.94 (6C,  $OCH<sub>2</sub>$  of the tetra(ethylene glycol) chain) 68.52 (PhOCH<sub>2</sub> of the aliphatic chain), 68.61 (1C, PhOCH<sub>2</sub>), 68.18 (1C, PhCH<sub>2</sub>O), 66.22  $(\text{1C, NCH}_2), \text{52.23} \text{ (1C, C}^\text{f}), \text{39.22} \text{ (1C, NCH}_3), \text{35.49} \text{ (1C, PhCH}_2),$ 33.49 (1C, PhCH<sub>2</sub>CH<sub>2</sub>), 31.92, 29.69-29.30, 26.13, 22.68 (20C, all CH<sub>2</sub> of the aliphatic chain), 22.33 (1C, Ph(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 14.11 (2C, CH<sub>3</sub>), 13.93 (1C, Ph(CH<sub>2</sub>)<sub>3</sub>CH<sub>3</sub>) ppm.

2.5.3 Synthesis of the fullerene  $C_{60}$ -amino-methoxy substituted azobenzene (17). Procedure employed for the synthesis of 15, using 11 (0.149 g, 0.15 mmol),  $I_2$  (0.039 g, 0.15 mmol), fullerene  $C_{60}$  (0.11 g, 0.15 mmol) dissolved in 110 mL of anhydrous toluene, and DBU (0.077 g, 0.51 mmol) to obtain compound 17 (Scheme 2c). Yield: 34%. MALDI-TOF:  $C_{116}H_{85}N_3O_{10}$  calcd:  $[M + H]^+$  1680.93 found  $(m/z)$ :  $[M + H]^+$ 1681.90.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.82$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.81 (d,  $J = 9$  Hz, 2H, H<sup>4</sup>), 6.98 (d,  $J = 8.98$  Hz, 2H, H<sup>6</sup>), 6.76 (d, J  $=$  9 Hz, 2H, H<sup>3</sup>), 6.58 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H,  $H<sup>1</sup>$ ), 5.43 (s, 2H, PhCH<sub>2</sub>OOC), 4.62 (t, J = 5 Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.89 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.82 (t,  $J = 5$  Hz, OCH<sub>2</sub>), 3.87 (s, 3H, PhOCH<sub>3</sub>), 3.69–3.62 (m, 14H, CH<sub>2</sub>N  $\gamma$  OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.08 (s, 3H, CH<sub>3</sub>N), 1.77-1.70 (m, 4H, PhOCH<sub>2</sub>-CH<sub>2</sub>), 1.45–1.25 (m, 36H, all CH<sub>2</sub> of the aliphatic chain), 0.89 (t, J

= 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 163.47 (1C, C<sup>g</sup>), 163.31 (1C,  $(\text{C}^\text{e}),$  160.85  $(\text{1C, C}^\text{o}),$  160.54  $(\text{2C, C}^\text{b}),$  150.98  $(\text{1C, C}^\text{h}),$  147.54  $(\text{1C, C}^\text{b})$  $\rm C^l)$ , 145.24, 145.21, 145.16, 145.06, 144.88, 144.68, 144.60, 144.54, 144.46, 143.85, 143.06, 143.00, 142.18, 141.90, 141.83, 140.89, 139.38, 138.71 (fullerene carbons), 136.61 (1C, C<sup>d</sup>), 124.60 (2C, C<sup>j</sup>), 123.83 (2C, C<sup>m</sup>), 114.10 (2C, C<sup>n</sup>), 111.50 (2C, C<sup>i</sup>), 107.26 (2C, C°), 101.78 (1C, C<sup>a</sup>), 71.50 (fullerene carbon), 70.77-70.70, 68.71 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 68.96 (PhOCH<sub>2</sub> of the aliphatic chain), 68.63 (1C, PhCH<sub>2</sub>O), 68.20 (1C, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 66.23 (1C, NCH<sub>2</sub>), 55.50 (1C, OCH<sub>3</sub>), 52.26 (1C, C<sup>f</sup>), 39.21 (1C, NCH<sub>3</sub>), 31.93, 29.70-29.31, 26.13, 22.69 (20C, all CH<sub>2</sub> of the aliphatic chain), 14.11  $(2C, CH<sub>3</sub>)$  ppm.

2.5.4 Synthesis of the fullerene  $C_{60}$ -amine-cyano substituted azobenzene (18). Procedure employed for the synthesis of 15, using 12 (0.19 g, 0.21 mmol),  $I_2$  (0.052 g, 0.21 mmol), fullerene C<sub>60</sub> (0.148 g, 0.21 mmol) dissolved in 150 mL of anhydrous toluene, and DBU (0.103 g, 0.68 mmol) to yield product 18 (Scheme 2d). Yield: 34%. MALDI-TOF:  $C_{116}H_{82}N_4O_9$  calcd:  $[M + H]^+$  1675.91 found  $(m/z)$ :  $[M + H]$ <sup>+</sup> 1676.83.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 7.88$  (d,  $J = 9$  Hz, 2H, H<sup>5</sup>), 7.86 (d, J = 9 Hz, 2H, H<sup>4</sup>), 7.73 (d, J = 8 Hz, 2H, H<sup>6</sup>), 6.76 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.58 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.43 (s, 2H, PhCH<sub>2</sub>OOC), 4.62 (t, J = 6 Hz, 2H, OOCCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.90 (t,  $J = 6$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.83 (t,  $J = 5$  Hz, OCH<sub>2</sub>), 3.68-3.62 (m, 14H,  $CH_2N$  y OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.12 (s, 3H, CH<sub>3</sub>N), 1.78-1.68 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.45-1.25 (m, 36H, all CH<sub>2</sub> of the aliphatic chain), 0.89 (t,  $J = 6$  Hz, 6H,  $CH<sub>3</sub>$ ) ppm.

<sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 163.47$  (1C, C<sup>g</sup>), 163.33 (1C,  $(C^{e})$ , 160.48 (2C,  $C^{b}$ ), 149.98 (1C,  $C^{l}$ ), 147.83 (1C,  $C^{h}$ ), 145.21, 145.17, 145.13, 144.99, 144.84, 144.65, 144.58, 144.43, 143.80, 142.97, 142.91, 142.15, 141.86, 141.78, 140.86, 140.83, 139.36, 136.56 (fullerene carbons), 129.33 (1C, C<sup>d</sup>), 128.90 (2C, C<sup>n</sup>), 125.03 (2C, C<sup>m</sup>), 122.18 (2C, C<sup>j</sup>), 118.01 (1C, C<sup>o</sup>), 111.39 (2C, PhCN), 111.34 (1C, C<sup>i</sup>), 107.18 (2C, C<sup>c</sup>), 101.66 (1C, C<sup>a</sup>), 72.87 (fullerene carbon), 70.76-70.66, 68.67 (6C, OCH<sub>2</sub> of the tetra $\left(-\right)$ ethylene glycol) chain) 68.44 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 68.93 (1C, PhCH<sub>2</sub>O), 68.54 (1C, PhCH<sub>2</sub>O), 68.12 (1C, OOCCH2 of the tetra(ethylene glycol) chain), 66.19 (1C, NCH2), 52.16 (1C, C<sup>f</sup> ), 39.25 (1C, NCH3), 31.91, 29.68–29.27, 26.11, 22.68 (20C, all CH<sub>2</sub> of the aliphatic chain), 14.13 (2C, CH<sub>3</sub>) ppm.

2.5.5 Synthesis of the fullerene  $C_{60}$ -amino-nitro substituted azobenzene (19). Procedure employed for the synthesis of 15, using 13 (0.153 g, 0.15 mmol), I<sub>2</sub> (0.039 g, 0.15 mmol), fullerene  $C_{60}$  (0.113 g, 0.15 mmol) dissolved in 120 mL of anhydrous toluene, and DBU (0.078 g, 0.51 mmol) to give the desired compound 19 (Scheme 2e). Yield: 69%. MALDI-TOF:  $C_{115}H_{82}N_4O_{11}$  calcd:  $[M + H]^+$  1695.90 found  $(m/z)$ :  $[M + H]^+$ 1696.85.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 8.32$  (d,  $J = 9$  Hz, 2H, H<sup>6</sup>), 7.91 (d, J = 9 Hz, 2H, H<sup>5</sup>), 7.88 (d, J = 9 Hz, 2H, H<sup>4</sup>), 6.77 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.58 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.40 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.43 (s, 2H, PhCH<sub>2</sub>OCO), 4.63 (t,  $J = 5$  Hz, 2H, PhOCH<sub>2</sub> of the tetra(ethylene glycol) chain), 3.89 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.83 (t,  $J = 5$  Hz, OCH<sub>2</sub>), 3.69-3.62 (m, 14H,  $CH<sub>2</sub>N$  and  $OCH<sub>2</sub>$  of the tetra(ethylene glycol) chain), 3.13 (s, 3H, CH<sub>3</sub>N), 1.76-1.70 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.45-1.37 (m, 4H, PhO(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 1.35-1.25 (m, 32H, all CH<sub>2</sub> of the aliphatic

chain), 0.89 (t, J = 7 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta = 163.45$  (1C, C<sup>e</sup>), 163.30 (1C, C<sup>g</sup>), 160.56 (2C, C<sup>b</sup>), 156.83 (1C, C<sup>l</sup>), 152.55 (1C, C<sup>h</sup>), 147.44 (1C, C<sup>o</sup>), 145.24, 145.23, 145.17, 145.04, 145.01, 144.88, 144.69, 144.64, 144.59, 144.46, 143.84, 143.06, 143.01, 142.95, 142.18, 141.90, 141.81, 140.88, 139.36, 138.71 (fullerene carbons), 136.59  $({\rm 1C},{\rm C}^{\rm d}),$  126.12  $({\rm 2C},{\rm C}^{\rm j}),$  124.65  $({\rm 2C},{\rm C}^{\rm n}),$  122.60  $({\rm 2C},{\rm C}^{\rm m}),$ 111.54 (2C, C<sup>i</sup>), 107.27 (2C, C<sup>c</sup>), 101.75 (1C, C<sup>a</sup>), 71.49 (fullerene carbon), 70.85-70.71, 68.72 (6C, OCH<sub>2</sub> of the tetra(ethylene glycol) chain), 68.96 (2C, PhOCH<sub>2</sub> of the aliphatic chain), 68.62  $(1C, PhCH<sub>2</sub>O), 68.20 (1C, COOCH<sub>2</sub>), 66.20 (1C, NCH<sub>2</sub>), 52.25$  $({\rm 1C},{\rm C}^{\rm f}),$  39.35  $({\rm 1C},{\rm NCH_3}),$  31.92, 29.69–29.30, 26.13, 22.68 (20C, all CH<sub>2</sub> of the aliphatic chain), 14.10 (2C, CH<sub>3</sub>) ppm.

2.5.6 Synthesis of the fullerene  $C_{60}$ -DR1 (20). Procedure employed for the synthesis of 15, using 14 (0.1094 g, 0.13 mmol),  $I_2$  (0.032 g, 0.13 mmol) and fullerene  $C_{60}$  (0.091 g, 0.13 mmol) were dissolved in 100 mL of anhydrous toluene and DBU (0.006 g, 0.038 mmol) to obtain the desired compound 20 (Scheme 2f). Yield: 70%. MALDI-TOF:  $C_{110}H_{72}N_4O_8$  calcd: [M +  $H$ <sup>+</sup> 1577.77 found  $(m/z)$ :  $[M + H]$ <sup>+</sup> 1578.47.

<sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>):  $\delta = 8.30$  (d,  $J = 9$  Hz, 2H, H<sup>6</sup>), 7.88 (d, J = 7 Hz, 2H, H<sup>5</sup>), 7.87 (d, J = 7 Hz, 2H, H<sup>4</sup>), 6.83 (d, J = 9 Hz, 2H, H<sup>3</sup>), 6.60 (d, J = 2 Hz, 2H, H<sup>2</sup>), 6.41 (t, J = 2 Hz, 1H, H<sup>1</sup>), 5.41 (s, 2H, PhCH<sub>2</sub>OCO), 4.68 (t,  $J = 6$  Hz, 2H, NCH<sub>2</sub>CH<sub>2</sub>OCO), 3.89 (t,  $J = 7$  Hz, 4H, PhOCH<sub>2</sub> of the aliphatic chain), 3.79 (t,  $J =$ 6 Hz, 2H,  $CH_3CH_2NCH_2$ ), 3.57-3.51 (m, 2H, OCOCH<sub>2</sub>CH<sub>2</sub>-NCH<sub>2</sub>), 1.76-1.68 (m, 4H, PhOCH<sub>2</sub>CH<sub>2</sub>), 1.43-1.36 (m, 4H, PhO(CH<sub>2</sub>)<sub>2</sub>CH<sub>2</sub>), 1.34-1.24 (m, 35H, all CH<sub>2</sub> of the aliphatic

chain and NCH<sub>2</sub>CH<sub>3</sub>), 0.89 (t, *J* = 6 Hz, 6H, CH<sub>3</sub>) ppm.<br><sup>13</sup>C NMR (100 MHz, CDCl<sub>3</sub>):  $\delta$  = 163.35 (1C, C<sup>e</sup>), 163.18 (1C, C<sup>g</sup>), 160.53 (2C, C<sup>b</sup>), 156.63 (1C, C<sup>l</sup>), 151.20 (1C, C<sup>h</sup>), 147.40 (1C, C<sup>o</sup>), 145.21, 145.18, 145.11, 144.89, 144.83, 144.59, 144.56, 144.43, 143.99, 143.79, 143.76, 142.98, 142.86, 142.80, 142.11, 142.08, 141.81, 141.69, 140.78, 140.75, 139.21, 138.60 (fullerene  $\text{carbons}$ ), 136.47  $\text{(1C, C^d)}$ , 126.47  $\text{(2C, C^n)}$ , 124.61  $\text{(2C, C^j)}$ , 122.63  $(2C, C<sup>m</sup>),$  111.56  $(2C, C<sup>i</sup>),$  107.33  $(2C, C<sup>c</sup>),$  101.52  $(1C, C<sup>a</sup>),$  71.18 (fullerene carbon), 68.95 (1C, PhCH<sub>2</sub>O), 68.15 (2C, PhOCH<sub>2</sub>), 63.96 (1C, NCH<sub>2</sub>CH<sub>2</sub>O), 51.59 (1C, C<sup>f</sup>), 48.23 (1C, CH<sub>3</sub>CH<sub>2</sub>-NCH<sub>2</sub>), 45.34 (1C, NCH<sub>2</sub>), 31.91 (2C, CH<sub>3</sub>(CH<sub>2</sub>)<sub>2</sub>), 29.68-29.25

(14C, all CH<sub>2</sub> of the aliphatic chain), 26.10 (2C, PhO(CH<sub>2</sub>)<sub>3</sub>), 22.68 (2C, CH<sub>3</sub>CH<sub>2</sub>), 14.13 (2C, CH<sub>3</sub>), 12.29 (1C, NCH<sub>2</sub>CH<sub>3</sub>) ppm.

# 3 Results and discussion

#### 3.1 Synthesis of the fullerene  $C_{60}$ -azobenzene derivatives

Generally, the synthesis of the fullerene  $C_{60}$ -azobenzene derivatives was carried out according to the synthetic sequence illustrated in Fig. 1. Six different substituted azobenzenes (amino, amino-butyl, amino-methoxy, amino-cyano, aminonitro, DR1) (3, 4, 5, 6, 7 and 8) bearing different dipole moment values were prepared and incorporated into a substituted malonate containing a phenyl group with aliphatic chains, to give the corresponding precursor compounds (9, 10, 11, 12, 13 and 14). The last step consisted on the incorporation of fullerene  $C_{60}$  into the precursor malonates by means of a Bingel reaction to give six different fullerene  $C_{60}$ azobenzene derivatives (15, 16, 17, 18, 19 and 20).

Precursor substituted azobenzenes 4, 5, and 7 have been prepared according to the method previously reported by us,<sup>30,33</sup> whereas substituted azobenzenes 3 and 6 were synthesized using a similar procedure.<sup>23</sup> Intermediate  $2-(2-\{2-\{2-\{2-\{1-\}(\} )\})$ phenyl-amino)-ethoxy]-ethoxy}-ethoxy)-ethanol was prepared according to our method previously reported in the literature and the diazonium salts were prepared in situ. Aniline (1 eq.) was reacted with NaNO<sub>2</sub> (1 eq.) in an HCl solution (30%) at 0 °C. Afterwards,  $2-(2-\{2-\lceil 2-(\text{methyl-phenyl-amino})-\text{ethoxy}\rceil-\text{ethoxy}\}$ ethoxy)-ethanol (1 eq.) was added dropwise to the reaction mixture in order to obtain the amino substituted azobenzene (3) with 68% yield.<sup>30</sup> Similarly, the diazonium salt of 4-cyanoaniline was used to give the corresponding amino-cyano substituted azobenzene (ESI†). BSC Advances Article on the thermatoplay of the published of 16 C, Plays Article (2017), Downloaded on 16 March 2017. The company of the published on 16 March 2017. Downloaded on 16 March 2017. The same of the common and

Dendron GIOH (1) (1 eq.) was treated in the presence of Meldrum's acid (1 eq.) to afford the monosubstituted malonic ester (2). This intermediate was further reacted with intermediate  $(3)$  in the presence of N,N-dimethyl-4-aminopyridine (DCC) and N,N-dimethyl-4-aminopyridine (DMAP) in dry dichloromethane to give the azobenzene containing disubstituted malonic ester (9). Finally, this compound was reacted with fullerene  $C_{60}$ , iodine and 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU) in anhydrous toluene to give the corresponding fullerene  $C_{60}$ -azobenzene derivative (15). The other fullerene  $C_{60}$ -azobenzene systems were obtained according to the same synthetic method, under the same reaction conditions described above. In the same manner, compounds (10), (11), (12), (13) and (14) were reacted under the Bingel reaction conditions to give the corresponding fullerenes  $C_{60}$ -azobenzene derivatives (16), (17), (18), (19) and (20), respectively (Fig. 1).

#### 3.2 Characterization of the fullerene  $C_{60}$ -azobenzenes derivatives

The precursor disubstituted malonic azo-dyes and their corresponding fullerene  $C_{60}$ -azobenzene derivatives were fully characterized by  ${}^{1}H$  and  ${}^{13}C$  NMR spectroscopies. The molecular weights and purity of the final products were confirmed by MALDI-TOF mass spectrometry using dithranol as matrix.

For instance, in the  $^{1}$ H NMR spectrum of compound 9 (Fig. 2a), we observe six signals in the aromatic region at 7.87, 7.84, 7.47–7.37, 6.75, 6.47 and 6.41 ppm, due to the aromatic protons present in the azobenzene unit and the phenyl group, corresponding to  $H^5$ ,  $H^4$ ,  $H^6$ –H,  $H^3$ ,  $H^2$  and  $H^1$ , respectively. In the aliphatic zone, we can see a singlet at  $5.09$  (PhCH<sub>2</sub>OCO), and two triplets at 4.29 (OOCCH<sub>2</sub>) and 3.92 ppm (PhOCH<sub>2</sub>). In addition, we perceive a multiplet at 3.68–3.59 ppm related to the protons OCH2 of the oligo(ethylene glycol) segments, as well as two singlets at 3.46 and 3.07 ppm due to the  $\alpha$  protons of the malonate (OOCCH<sub>2</sub>COO) and the methyl group (NCH<sub>3</sub>), respectively. Finally, the protons corresponding to methylenes  $(CH<sub>2</sub>)$  present in the aliphatic chain appear at 1.80–1.71, 1.46– 1.39, 1.36–1.27 and 0.90 ppm. Paper<br>
For instance, in the <sup>14</sup> NMR spectrum of compound 9 corresponding to carbons PhrCl<sub>2</sub>O, (N, 2C), and (NC11, (P), alt<sub>1</sub> (P), alt<sub>1</sub> (P), alticle. Published on the article is licensed under a Creatively, the minimal

In the  ${}^{1}H$  NMR spectrum of fullerene  $C_{60}$ -azobenzene derivative 15, the chemical shifts of the protons are very similar (Fig. 2b). As we can notice, the signal due to the  $\alpha$  protons of the malonate ( $OOCCH<sub>2</sub>COO$ ), previously observed at 3.46 ppm, totally disappeared. This is an indication that the Bingel coupling reaction between the fullerene  $C_{60}$  and the precursor malonic azo-dye successfully occurred.

On the other hand, in the aromatic region of the  $^{13}$ C NMR spectrum of the malonic azo-dye 9, there are 14 signals at 163.46, 163.29, 160.47, 153.17, 151.34, 143.78, 136.55, 129.31, 128.87, 125.02, 122.17, 111.38, 107.15, 101.64 ppm, assigned to the aromatic carbons of the phenyl groups present in the structure. Moreover, in the aliphatic region, we observe various signals at 70.75–70.64, 68.91, 68.66 ppm due to the methylenes present in the tetra(ethylene glycol) spacers. In addition, the carbons PhOCH<sub>2</sub> of the aliphatic chain appear at 68.53. Four more signals at 68.11, 66.18, 52.15 and 32.24 ppm,



Fig. 2  $^{-1}$ H NMR spectra in CDCl<sub>3</sub>: (a) precursor malonic azo-dye 9, (b) fullerene  $C_{60}$ -azobenzene derivative 15

corresponding to carbons (PhCH<sub>2</sub>O), (NCH<sub>2</sub>), (C<sup>f</sup>) and (NCH<sub>3</sub>), respectively, were also observed. Finally, the signals due to all the  $CH<sub>2</sub>$  and  $CH<sub>3</sub>$  present in the aliphatic chains appeared at 31.90, 29.67–29.26, 26.10, 22.67, and 14.12 ppm.

In the <sup>13</sup>C NMR spectrum of fullerene C<sub>60</sub>-azobenzene derivative 15, the signals of the aromatic rings did not show any significant chemical shift with respect to its precursor compound 9 (Fig. 3). However, we observe the appearance of the signals arising from the fullerene  $C_{60}$  sp<sup>2</sup> carbons at 145.20, 145.16, 145.11, 144.97, 144.83, 144.63, 144.60, 144.55, 144.48, 144.41, 143.80, 143.78, 143.64, 143.01, 142.96, 142.89, 142.13, 141.85, 141.77, 140.84, 140.82, 139.34, and 138.66 ppm. Meanwhile, in the aliphatic region, we can notice an additional signal of the fullerene  $C_{60}$  sp<sup>3</sup> carbons and the carbon  $\alpha$  to the carbonyl group (C $^{\rm f})$  at 71.40 and 52.15 ppm, respectively.

The structure and purity of these compounds were confirmed by MALDI-TOF mass spectrometry. All fullerene  $C_{60}$ azobenzene derivatives showed the expected molecular ion peaks, which are in agreement with the calculated molecular weights. The  $^{13}$ C NMR the fullerene-azobenzene derivatives reported here can be found in the ESI.†

### 3.3 Optical properties of the fullerene  $C_{60}$ -azobenzene derivatives

The optical properties of the fullerene  $C_{60}$ -azobenzene derivatives were studied by absorption spectroscopy in the UV-vis region; the results are summarized in Tables 1 and 2. The absorption spectra of the precursor malonic azo-dyes without fullerene were recorded in CHCl<sub>3</sub>, MeOH and DMF solution, whereas those of the fullerene  $C_{60}$ -azobenzene derivatives were carried out in CHCl<sub>3</sub> and DMF.

The absorption spectra of the precursor malonic azo-dyes without fullerene were normalized for a better comparison. As we can notice, the absorption spectra of compounds 9, 10 and 11, in CHCl<sub>3</sub> solution, showed a maximum absorption band at  $\lambda_{\text{max}} =$ 410 nm followed by red-shifted shoulder at 421 nm due to the  $\pi$ - $\pi^*$  and n– $\pi^*$  transitions, respectively. These compounds have a low dipole moment value and belong to aminoazobenzenes category, according to Rau's classification.<sup>18,19</sup> By contrast,



Fig. 3  $13^{\circ}$ C NMR spectra of fullerene C<sub>60</sub>-azobenzene derivative 15 in CDCl3.







<sup>a</sup> Absorbance of the precursor malonic azo-dyes. <sup>b</sup> Absorbance of the fullerene C<sub>60</sub>-azobenzene system.

compounds 12, 13 and 14 exhibited well defined absorption bands at 448, 478 and 468 nm, respectively (Fig. 4a). These compounds possess high dipole moment values and belong to the pseudostilbenes category, so that they exhibit a total overlap of the  $\pi$ – $\pi$ <sup>\*</sup> and n– $\pi$ <sup>\*</sup> bands in other words, only one absorption band can be observed in the UV-vis spectra.<sup>18,19</sup> However, the absorption bands of these compounds in MeOH solution did not show any significant red shift. On the contrary, compound 14 showed a redshift of 10 nm in its absorption band with respect to that observed in CHCl<sub>3</sub> (Table 1), and in DMF a significant solvatochromic effect was observed. Compounds having low dipole moments (9, 10 and 11) showed a red-shift of 8 nm in their adsorption bands, whereas compounds bearing high dipole moments (12, 13 and 14) exhibited red-shifts of 14, 18 and 22 nm, respectively (Fig. 4b, Table 1). On the other hand, malonic azo-dyes bearing  $NO<sub>2</sub>$  as acceptor group (13, 14) exhibited a maximum absorption band at  $\lambda_{\text{max}} = 478$  nm in MeOH solution, showing slight shifts of 10 and 6 nm in CHCl3 and DMF solution, respectively (Table 1).



Fig. 4 Normalized absorption spectra of the precursor azo-dyes: (a) in CHCl<sub>3</sub>, and (b) in DMF solution.

Regarding the optical properties of the fullerene  $C_{60}$ -azobenzene derivatives, we noticed that in  $CHCl<sub>3</sub>$  solution the absorption band of compounds 15, 16 and 17 (low dipole moment) are blue-shifted by 2 nm with respect to their precursor malonic azo-dyes without fullerene (Table 2). These compounds exhibited a maximum absorption band at  $\lambda_{\text{max}} =$ 408 nm with a red-shifted shoulder at 422 nm arising from the  $\pi$ – $\pi$ \* and n– $\pi$ \* transitions, respectively. In addition, we note the presence of a blue-shifted shoulder at 394 nm, which reveals the presence of H-aggregates (Fig. 5). Alternatively, azocompounds bearing high dipole moment values (18, 19, 20) show adsorption bands at 448, 480 and 472 nm, respectively.



Fig. 5 Absorption spectra of the fullerene  $C_{60}$ -azobenzene derivatives in CHCl $<sub>5</sub>$  solution.</sub>

As well, the optical properties of fullerene  $C_{60}$ -azobenzene derivatives were studied in DMF solution (ESI, Fig. S6†). These hybrid systems having low dipole moments (15, 16, 17) exhibited a maximum absorption band which is 8 nm red-shifted with respect to the absorption value in  $CHCl<sub>3</sub>$  solution. However, fullerene  $C_{60}$ -azobenzene derivatives bearing high dipole moment values (18, 19 and 20) showed maximum absorption bands at  $\lambda_{\text{max}} = 462, 492-494, 488,$  respectively. They also exhibited a blue-shifted shoulder at 428 nm, which can be due to intramolecular azobenzene-fullerene interactions.<sup>36</sup>

### 3.4 Protonation effect upon irradiation

We decided to study the photoprotonation effect on the series of azo-dyes containing first generation Fréchet type dendrons. In these compounds, the formation of an azo-hydrazone via tautomerism can be induced by irradiating with UV light at 254 nm.29,37 Particularly, we investigated the photoprotonation effect of the fullerene  $C_{60}$ -azobenzene derivatives 15 and 19, having the lowest and the highest dipole moment value, respectively. After irradiation with UV light for 140 s, compound 15 reached a photostationary state (PPS). However, over time we noticed that absorption band at 410 nm decreases drastically in intensity and two new absorption bands appear in the visible region at 524 nm and 546 nm, respectively; the isobestic point was located at 430 nm (Fig. 6a). Similarly, fullerene  $C_{60}$ -azobenzene derivative 19, bearing a high dipole moment value, exhibited the same photochromic effect as its homologue with low dipole moment 15. Upon irradiation the absorption band at 480 nm decreased drastically in intensity and the appearance of two additional bands at 520 and 552 nm was observed; in this case the isosbestic point was situated at 500 nm (Fig. 6b). This fullerene  $C_{60}$ -azobenzene system reached a photostationary state (PPS) after irradiation for 600 s. From these results, we can remark that the photochromic behavior of this azo-dye was not perturbed at all by the incorporation of the fullerene unit (Fig. 8). Paper<br>
These compounds exhibited also a blue-hilled shoulder at  $\frac{1}{2}$  the state of the present of Figures Article is licensed under the present of Figures Article is licensed under the state of a march 2017. This arti

#### 3.5 trans–cis photoisomerization

Photoisomerization experiments were performed with the samples in DMF solution, which were irradiated with UV light at



Fig. 6 Photoprotonation effect of [60] fullerene  $C_{60}$ -azobenzene derivatives irradiated with UV light at 254 nm: (a) derivative 15, and (b) derivative 19 (Conc. 2.5  $\times$  10<sup>-4</sup> M in CHCl<sub>3</sub> at room temperature).



Fig. 7 Absorption spectra upon irradiation with UV light at 365 nm for 10 minutes: (a) precursor azo-dyes 9, 10 and 11, (b) fullerene  $C_{60}$ azobenzene derivatives 15, 16 and 17 (Conc. 2.5  $\times$  10<sup>-4</sup> M in DMF at room temperature).

365 nm for 10 min. After this time, we noticed that the intensity of the absorption band as well as the extinction molar coefficient of compounds 9, 10 and 11 decreased, due to the photoisomerization from the *trans*  $(E)$  to the *cis*  $(Z)$  isomer. Moreover, in the UV region of the absorption spectrum of these compounds there is a shoulder at 450 nm, related to the n- $\pi^*$ transition of the cis isomer (Fig. 7a). Meanwhile, in the absorption spectra of the fullerene  $C_{60}$ -azobenzenes derivatives 15, 16 and 17 the intensity of the bands did not vary significantly (Fig. 7b). The photoisomerization yield in these compounds depends in large measure on the donor/acceptor character of the substituents present in the azobenzene units (Table 2). Fullerene  $C_{60}$ -azobenzene derivative 17 exhibited a photoisomerization yield of 13%, which can attributed to the electron-donor effect of the  $(OCH<sub>3</sub>)$  group. Finally, compounds 15 and 17 bearing low dipole moment values exhibited



Fig. 8 Photoisomerization and photoprotonation of  $C_{60}$ -azobenzene derivative 19



Fig. 9 Absorption spectra of fullerene  $C_{60}$ -azobenzene derivatives 19 in CHCl<sub>3</sub>, DMF and cast film.

photoisomerization yields of 6.4 and 3.0%, respectively (Table 2). These low yields are due to the fact that the fullerene  $C_{60}$ strongly absorb in the UV region, which causes a partial quenching the photoisomerization process (Fig. 8).

### 3.6 Optical properties and trans–cis photoisomerization in cast films

The optical properties of the fullerene  $C_{60}$ -azobenzenes derivatives were also studied in cast films, and the results are summarized in Table 2. The normalized absorption spectra of the fullerene  $C_{60}$ -azobenzene derivative 19 in CHCl<sub>3</sub>, DMF and cast film are shown in Fig. 9. As we can see, the absorption band in a cast film did not show any significant shift with respect to the absorption band observed in  $CHCl<sub>3</sub>$  solution. However, in DMF this absorption band was red-shifted by 8 nm, and we note a shoulder at 524 nm due to the presence of J-aggregates, $28$ followed by two discrete shoulders at 580 and 702 nm, respectively (Table 2).<sup>38</sup>

On the other hand, photoisomerization experiments were carried out in cast film samples. The precursor malonic azodyes without fullerene bearing low dipole moments (9, 10 and 11) exhibited trans-cis photoisomerization when they were irradiated with UV light at 365 nm for 10 minutes. After this time, we noticed a decrease in intensity of the absorption band



Fig. 10 Absorption spectrum in casted film of: (a) precursor azo-dye 9, (b) fullerene  $C_{60}$ -azobenzene derivative 15, after irradiation for 10 minutes.

at 410 nm, jointly with the appearance of a shoulder at 450 nm due to the n– $\pi^*$  transition of the *cis* isomer (Fig. 10a). On the contrary, when the fullerene  $C_{60}$ -azobenzene derivatives (15, 16, 17) were irradiated with UV light for 10 minutes, the absorption bands did not change at all (Fig. 10b). This is certainly due to a quenching of the photoisomerization process by the presence of the fullerene unit in these derivatives.

### 4 Conclusions

Six different fullerene C<sub>60</sub>-azobenzene derivatives  $(15, 16, 17, 18,$ 19 and 20) were successfully synthesized and fully characterized by <sup>1</sup>H, <sup>13</sup>C NMR and MALDI-TOF. The optical properties of the fullerene  $C_{60}$ -azobenzene dyes were studied by UV-vis spectroscopy and compared to those of their precursor malonic azodyes without fullerene (9, 10, 11, 12, 13 and 14).

Fullerene  $C_{60}$ -azobenzene derivatives bearing low dipole moment (15, 16 and 17) in CHCl<sub>3</sub> exhibited a maximum absorption band at  $\lambda_{\text{max}} = 408$  nm and a shoulder at 422 nm due to  $\pi-\pi^*$  and n– $\pi^*$  transitions, respectively. The presence of a blue-shifted shoulder at 394 nm revealed the presence of Haggregates. Fullerene  $C_{60}$ -azobenzene derivatives bearing a high dipole moment (18, 19 and 20) showed maximum absorption bands between 448 and 472 nm; the presence of Haggregates was also detected.

The photoprotonation effect in the fullerene  $C_{60}$ -azobenzene derivatives 15 and 19, having the lowest and the highest dipole moment, respectively, was studied by absorption spectroscopy. Compound 15 (lowest dipole moment) reached a photostationary state (PPS). The absorption band at 410 nm decreased drastically in intensity and two absorption bands appeared at 524 and 546 nm. Compound 19 (highest dipole moment) behaved similarly and exhibited the same photochromic effect. It was found that the photoprotonation behavior of these azodyes was not perturbed by the incorporation of the fullerene unit.

Photoisomerization experiments were performed with the precursor dyes with low dipole moment (9, 10 and 11) in DMF solution. A typical trans-cis photoisomerization behavior was observed. The absorption band at 410 nm decreased in intensity and a shoulder at 450 nm due to the n- $\pi^*$  transition (*cis* isomer) appeared. On the contrary, in the UV-vis spectra of the fullerene  $C_{60}$ -azobenzenes derivatives (15, 16 and 17) the intensity of the bands did not vary remarkably. It was found that the presence of the fullerene moiety drastically decreases the photoisomerization yield because of a strong quenching effect.

The optical properties of the fullerene  $C_{60}$ -azobenzenes derivatives were also studied in cast films, where the presence of J-aggregates was detected. Malonic azo-dyes without fullerene (9, 10 and 11) exhibited typical trans–cis photoisomerization, whereas the fullerene  $C_{60}$ -azobenzene derivatives (15, 16, 17) did not since the fullerene moiety acts as quencher.

## Acknowledgements

We are grateful to Miguel Angel Canseco for his assistance with UV-vis spectroscopy and Gerardo Cedillo for his help with <sup>1</sup>H

and  $^{13}$ C NMR spectroscopy. This project was financially supported by PAPIIT (Project IN-100316) and CONACyT (Projects 253155 and 222847).

# References

- 1 H. W. Kroto, A. W. Allaf and S. P. Balm,  $C_{60}$ : Buckminsterfullerene, Chem. Rev., 1991, 91, 1213–1235.
- 2 B. C. Thompson and J. M. J. Fréchet, Organic Photovoltaics Polymer–Fullerene Composite Solar Cells, Angew. Chem., Int. Ed., 2008, 47, 58–77.
- 3 D. M. Guldi and N. Martin, Fullerenes: From Synthesis to Optoelectronic Properties, Kluwer Academic Publishers, Dordrecht, The Netherlands, 2002.
- 4 F. Wudl, Fullerene materials, J. Mater. Chem., 2002, 12, 1959– 1963.
- 5 A. M. López, A. Mateo-Alonso and M. Prato, Materials chemistry of fullerene  $C_{60}$  derivatives, *J. Mater. Chem.*, 2011, 21, 1305–1318.
- 6 M. Parto, [60] Fullerene chemistry for materials science applications, J. Mater. Chem., 1997, 7, 1097–1109.
- 7 F. Wudl, The Chemical Properties of Buckminsterfullerene  $(C_{60})$  and the Birth and Infancy of Fulleroids, Acc. Chem. Res., 1992, 25, 157–161.
- 8 S. A. Backer, K. Sivula, D. F. Kavulak and J. M. J. Fréchet, High Efficiency Organic Photovoltaics Incorporating a New Family of Soluble Fullerene Derivatives, Chem. Mater., 2007, 19, 2927–2929.
- 9 N.-X. Wang, C. H. Sun and W. Liu, Synthesis of fullerene azobenzene derivatives, Fullerene Sci. Technol., 2001, 9, 429–432.
- 10 K.-Y. Kay, K. J. Han, Y. J. Yu and Y. D. Park, Dendritic fullerenes  $(C_{60})$  with Photoresponsive Azobenzene Groups, Tetrahedron Lett., 2002, 43, 5053–5056.
- 11 D. I. Schuster, K. Li, D. M. Guldi, A. Palkar, L. Echegoyen, C. Stanisky, R. J. Cross, M. Niemi, N. V. Tkachenko and H. Lemmetyien, Azobenzene-linked porphyrin fullerene dyads, J. Am. Chem. Soc., 2007, 129, 15973–15982.
- 12 K. S. Kumar and A. Patnaik, Tunable One-, two-, and three dimensional self assemblies from an acceptor–donor fullerene-N,N-dimethylaminoazobenzene dyad: Interfacial geometry and temporal evolution, Langmuir, 2011, 27, 11017–11025.
- 13 K. S. Kumar and A. Patmaik, Solvent-polaritydimeric association of a fullerene  $(C_{60})$ -N,N-dimethylaminoazobenzene dyad: Modulated electronic coupling of the azochromophore with a substituted 3D fullerene, Chem.–Eur. J., 2011, 17, 5327–5343.
- 14 Y. Shirai, T. Sasaki, J. M. Guerrero, B. C. Yu, P. Hodge and J. M. Tour, Synthesis and Photoisomerization of Fullerene and Oligo(phenyleneethynylene) Azobenzene Derivatives, ACS Nano, 2008, 2, 97–106.
- 15 M. E. El-Khouly, J. H. Kim, K. Y. Kay and S. Fukuzumi, Silicon phthalocyanine-azobenzene-[60] fullerene light harvesting pendant: synthesis, characterization and electron transfer reaction studied by laser flash photolysis, J. Porphyrins Phthalocyanines, 2013, 17, 1055–1063.
- 16 S. Ma, H. Ting, L. Zhang, Y. Ma, L. Zheng, L. Xiao and Z. Chen, Reversible photoinduced bi-state polymer solar cells based on fullerene derivatives with azobenzene groups, Org. Electron., 2015, 23, 1–4.
- 17 M. Wang, E. Chesnut, Y. Sun, M. Tong, M. Guide, Y. Zhang, D. N. Treat, A. Varotto, A. Mayer, L. M. Chabinyc, T.-Q. Nguyen and F. Wudl, PCBM Disperse-Red Ester with Strong Visible-Light Absorption: Implication of Molecular Design and Morphological Control for Organic Solar Cells, J. Phys. Chem. C, 2012, 116, 1313–1321. Paper<br>
McCess Articles. Published on 16 March 2017. Download articles. Published published under the state is licent<br>
2017 Paper IV-100316] and CrNACyT (Projects. 2. Downloaded prior state in the common state is licent in
	- 18 H. Rau, in Photochemistry and Photophysics, ed. J. K. Rabek, CRC Press. Boca Raton, Florida, 1990, vol. 2, p. 119.
	- 19 A. Natansohn and P. Rochon, Photoinduced Motions in Azo Containing Polymers, Chem. Rev., 2002, 102, 4139–4176.
	- 20 T. Todorov, L. Nikalova and N. Tomova, Polarization Holography. 1: A new high-efficiency organic material with reversible photoinduced birefringence, Appl. Opt., 1984, 23, 4309–4312.
	- 21 S. Xie, A. Natansohn and P. Rochon, Recent Developments in Aromatic Azo Polymers Research, Chem. Mater., 1993, 5, 403–411.
	- 22 N. K. Viswanathan, D. Y. Kim, S. Bian, J. Williams, W. Liu, L. Li, L. Samuelson, J. Kumar and S. K. Tripathy, Surface relief structures on azo polymer films, J. Mater. Chem., 1999, 9, 1941–1955.
	- 23 E. Rivera, M. Belletête, A. Natansohn and G. Durocher, Synthesis, characterization, and optical properties of a novel azo-dye bearing an oligo(ethylene glycol) methyl ether side chain in solution and in the solid state, Can. J. Chem., 2003, 81, 1076–1082.
	- 24 E. Rivera, M. P. Carreón-Castro, I. Buendía and G. Cedillo, Optical properties and aggregation of novel azo-dyes bearing an end-capped oligo(ethylene glycol) side chain in solution, solid state and Langmuir-Blodgett films, Dyes Pigm., 2006, 68, 217–226.
	- 25 E. Rivera, M. P. Carreón-Castro, L. Rodriguez, G. Cedillo, S. Fomine and O. G. Morales-Saavedra, Amphiphilic azodyes (RED-PEGM). Part 2: Charge transfer complexes, preparation of Langmuir Blodgett films and optical properties, Dyes Pigm., 2007, 74, 396–403.
	- 26 C. Caicedo, E. Rivera, Y. Valdez-Hernández and M. P. Carreón-Castro, Synthesis and characterization of novel liquid-crystalline azo-dyes bearing two amino-nitro substituted azobenzene units and a well-defined, oligo(ethylene glycol) spacer, Mater. Chem. Phys., 2011, 130, 471–480.
	- 27 T. García, M. P. Carreón-Castro, A. Gelover-Santiago, P. Ponce, M. Romero and E. Rivera, Synthesis and Characterization of Novel Amphiphilic Azo-Polymers Bearing Well-Defined Oligo(Ethylene Glycol) Spacers, Des. Monomers Polym., 2012, 15, 159–174.
	- 28 F. Tapia, J. M. Reyna-González, G. Huerta, S. Almeida and E. Rivera, Synthesis and characterization of novel polythiophenes bearing oligo(ethylene glycol) segments and azobenzene units, Polym. Bull., 2010, 64, 581–594.
	- 29 J. Ortíz-Palacios, E. Rodríguez-Alba, G. Zaragoza-Galán, J. R. León-Carmona, A. Martínez and E. Rivera,

Incorporation of novel azobenzene dyes bearing oligo(ethylene glycol) spacers into first generation dendrimers, Dyes Pigm., 2015, 116, 1–12.

- 30 E. Rivera, M. P. Carreón-Castro, R. Salazar, G. Huerta, C. Becerril and L. Rivera, Preparation and characterization of novel grafted polyethylene based azo-polymers bearing oligo(ethylene glycol) spacers, Polymer, 2007, 48, 3420–3428.
- 31 D. Felder, M. Gutiérrez-Nava, M. P. Carreón-Castro, J. F. Eckert, M. Luccisano, C. Schall, P. Masson, J. L. Gallani, B. Heinrich and D. Gillonand, Synthesis of amphiphilic fullerene derivatives and their incorporation in Langmuir and Langmuir-Blodgett films, Helv. Chim. Acta, 2002, 85, 288–319. **BSC Articles.** Providences Articles. Published on 16 March 2017. Downloaded on 16 March 2017. Developed the common American Creative Commons Article. Published National Published Published Commons Article. Unport and Lice
	- 32 X. Camps and A. Hirsch, Efficient cyclopropanation of  $C_{60}$ starting from malonates, *J. Chem. Soc., Perkin Trans. 1*, 1997, 1595.
	- 33 J. Ortíz-Palacios, E. Rodríguez-Alba, M. Avelar, A. Martínez, M. P. Carreón-Castro and E. Rivera, Synthesis and characterization of novel dendrons bearing amino-nitrosubstituted azobenzene units and oligo(ethylene glycol) spacers: thermal, optical properties, Langmuir Blodgett

films and liquid-crystalline behaviour, Molecules, 2013, 18, 1502–1527.

- 34 C. J. Hawker and J. M. J. Fréchet, Preparation of Polymers with Controlled Molecular Architecture. A new Convergent Approach to Dendritic Macromolecules, *J. Am. Chem. Soc.*, 1990, 112, 7638–7647.
- 35 J. Ortíz-Palacios, E. Rodríguez-Alba, G. Zaragoza-Galán and E. Rivera, Fréchet-type dendrons bearing azobenzene units and flexible oligo(ethylene glycol) spacers: synthesis, characterization, thermal and optical properties, Des. Monomers Polym., 2013, 16, 578–591.
- 36 M. Kasha, Energy transfer mechanisms and the molecular exciton model for molecular aggregates, Radiat. Res., 1963, 20, 55–71.
- 37 K. S. Kumar and A. Patnaik, Tunable electronic properties of a proton-responsive N,N-dimethylaminoazobenzene fullerene  $(C_{60})$  dyad, *ChemPhysChem*, 2010, 11, 3645-3655.
- 38 S. K. Lin, L. L. Shiu, K. M. Chien, T. L. Luh and T. I. Lin, Fluorescence of Fullerene Derivatives at Room Temperature, J. Phys. Chem., 1995, 99, 105–111.