RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2017, 7, 27454

Received 15th April 2017 Accepted 17th May 2017 DOI: 10.1039/c7ra04274d rsc.li/rsc-advances

Introduction

Hexagonal Fe₂P-type transition metal FeMn-based magnetocaloric materials (FeMnP_{1-x} T_x , T = As, Si, Ge) are driving tremendous research interest because of their promising application in solid-state refrigeration as energy efficient, environment friendly alternative to the traditional gascompressor based cooling scheme.1-9 This family of materials exhibit a first-order magnetoelastic transition close to room temperature.¹⁰⁻¹² Significant exchange striction, in which the hexagonal lattice parameter c decreases and a increases with a very small volume change, is observed during the paramagnetic (PM) to ferromagnetic (FM) transition.^{10,13} This leads to large local strain in the polycrystalline samples, and therefore good mechanical stability across the phase transition becomes very important for FeMn-based giant magnetocaloric (GMC) materials because they work under repeated magnetic and thermal cycles.^{5,6,10,14}

To obtain materials with good performance in magnetic refrigeration, extensive experimental investigation of $\text{FeMnP}_{1-x}\text{Si}_x$ compounds has been performed.^{8,9,11-17} The thermal hysteresis decreases to less than 1 K and the isothermal

Ab initio mechanical and thermal properties of $FeMnP_{1-x}Ga_x$ compounds as refrigerant for room-temperature magnetic refrigeration

Shuang Ma,^a B. Wurentuya,^{ab} Xiaoxia Wu,^c Yongjing Jiang,^a O. Tegus,^a Pengfei Guan^d and B. Narsu^b*^a

Density functional theory was used to identify possible Fe_2P -type giant magnetocaloric $FeMnP_{1-x}Ga_x$ compounds. The calculated formation energies, elastic constants and phonon spectra confirm the energetic, mechanical and dynamical stability of hexagonal $FeMnP_{1-x}Ga_x$ compounds in both the ferromagnetic and paramagnetic states. The predicted magnetic moment, elastic properties, and Curie temperature of $FeMnP_{0.67}Ga_{0.33}$ are close to those obtained for $FeMnP_{0.67}Ge_{0.33}$ compounds using the same calculation scheme. The entropy changes and latent heat of $FeMnP_{0.67}Ga_{0.33}$ are similar with those of $FeMnP_{0.67}Ge_{0.33}$. The electronic density of states and charge density analysis indicate that the $FeMnP_{1-x}Ga_x$ compounds have similar electronic structures to those of $FeMnP_{1-x}Ge_x$. These results predict that $FeMnP_{1-x}Ga_x$ is a possible candidate refrigerant for room-temperature magnetic refrigeration.

entropy change $|S_{iso}|$ increases to ~9.0 J kg⁻¹ K⁻¹ around the Curie temperature,12 which can be continuously tailored.4,5,16,18 However, the weak mechanical stability across the phase transition restricts the applicability of $FeMnP_{1-x}Si_x$ compounds in practical devices. One way to optimize the mechanical stability of $FeMnP_{1-x}Si_x$ compounds is to dope them with interstitial B atoms.10,12,14,18-20 Another viable way to improve the mechanical properties of these compounds is to replace Si atoms with other elements to adjust the bonding between atoms.21,22 Si and Al have been suggested to be the most ideal substitutes for the toxic As element in MnFeP_{1-x}As_x compounds,^{23,24} although experimentalists have failed to alloy Al into hexagonal Fe₂P-type magnetocaloric materials. From the viewpoint of alloying, Ga is a possible candidate because it has a similar outermost electronic structure and atomic size to Ge. However, no theoretical investigations have been performed to determine the structural, magnetic, and electronic properties of $FeMnP_{1-x}Ga_x$ and $FeMnP_{1-x}Ge_x$ compounds.

Here, we report the possibility of developing GMC compounds by alloying Ga into hexagonal Fe₂P-type compounds by quantum mechanical calculations. The static and dynamic stabilities of FeMnP_{1-x}Ga_x compounds in different states are verified by total energy and elastic constant calculations. In addition, the mechanical properties of FeMnP_{1-x}T_x (T = Ga, Ge) in different magnetic states are evaluated. The thermodynamic properties of FeMnP_{1-x}Ga_x compounds were calculated and they are compared with those of FeMnP_{1-x}Ge_x compounds to determine the possibility of using them in magnetic refrigeration.

^aCollege of Physics and Electronic Information, Inner Mongolia Key Lab for Physics and Chemistry of Functional Materials, Inner Mongolia Normal University, Hohhot 010022, China. E-mail: nars@imnu.edu.cn

^bShenyang National Laboratory of Materials Science, Institute of Metal Research, Chinese Academy of Sciences, Shenyang 110016, China

^cDepartment of Physics, Inner Mongolia University of Science and Technology, Baotou 014022, China

^dBeijing Computational Science Research Center, Beijing 100193, China

Computational details

The Fe₂P-type hexagonal structure has the symmetry of space group P6(2m), in which three atoms occupy four different crystal sites. Usually, the Fe atom prefers the $3f(x_1, 0, 0)$ site and the Mn atom occupies the 3g $(x_2, 0, 0.5)$ site.²⁵ There are two different atomic sites for the metalloid atoms, namely, 2c (0.333, 0.667, 0) and 1b (0, 0, 0.5). Local occupation disorder of P and Si atoms at 2c and 1b sites in FeMnP_{1-x}Si_x compounds was observed in the experiment.26 However, site occupation order between 2c and 1b sites is expected for $FeMnP_{1-x}Ge_x$ and $FeMnP_{1-x}Ga_x$ compounds because of the larger atomic radii of these dopant atoms than P and Si atoms. Therefore, we chose the occupation of Ga (or Ge) atom at the 1b site for x = 0.33 and at the 2c for x =0.67. The FM state was calculated self consistently with the primitive cell (half of the cell shown in Fig. 1), while the PM state was modeled by an antiferromagnetically ordered 1 \times 1 \times 2 supercell structure (Fig. 1). Antiferromagnetic model is usually used to simulate the paramagnetic state of transition metals and their alloys, and it can practically capture the physics observed in experiment.²⁷⁻²⁹ The magnetic moments of the transition metal atoms were set to be parallel in the primitive cells and an antiparallel alignment of magnetic moments between primitive cells was established to form the antiferromagnetic (AFM) order. In this case, the long-range FM order along the c axis is broken, but short-range magnetic order still exits,³⁰ so this supercell structure models the magnetic state just above the Curie temperature.

The total electronic energy was calculated by the projector augmented wave method³¹ in the framework of density functional theory,^{32,33} as implemented in the Vienna *ab initio* simulation package (VASP).^{34,35} The exchange correlation effect was evaluated by the generalized gradient approximation parameterized by Perdew, Burke, and Ernzerhof.³⁶ The accuracy of PBE functional for FeMn based Fe₂P type alloys has previously been confirmed.^{17,51} The scalar relativistic scheme was used and the spin–orbit coupling effect was omitted. Mn (3d⁶4s¹), Fe (3d⁷4s¹), P (3s²3p³), Ga (3d¹⁰4s²4p¹), and Ge (3d¹⁰4s²4p²) electrons were treated as valance states.³⁷ The



Fig. 1 Cell structure of hexagonal phase FeMnP_{1-x}Ga_x compounds. For the case of x = 0.33, Ga occupies the 1b site, and for x = 0.67, Ga occupies the 2c site. For the FM state, the magnetic moments of the unit cells are aligned parallel, and for the AFM state the magnetic moments in the upper and lower unit cells are aligned antiparallel.

cutoff energy of the plane wave basis was set to 530 eV, and the convergence criterion of self-consistent electronic relaxation was set to 10^{-5} eV per atom. For ionic relaxation, the force convergence criterion of 0.01 eV Å⁻¹ was used. The Monkhorst-Pack scheme³⁸ was used for Brillouin zone sampling, with an 11 \times 11 \times 17 *k*-point mesh for the FM state and an 11 \times 11 \times 9 *k*point mesh for the AFM state. With these computational settings, the total energies of compounds with different magnetic states were calculated for different volume V and c/ a values. The equation of state was fitted with the Murnaghan equation,³⁹ and then the bulk modulus and the equilibrium volume were obtained. The five independent elastic constants were calculated by the energy-strain method used in ref. 40, with isochoric strain δ of 0.00 to ± 0.05 . The phonon spectra were calculated by phonopy code.41 For FM and AFM states, 72 atom and 144 atom $2 \times 2 \times 2$ supercells were used, respectively. An accurate prediction of the thermodynamic properties should be based on the quasiharmonic approximation (QHA)⁴² with a direct *ab initio* phonon spectrum calculation.⁴¹ However, this is a very difficult task for multicomponent compounds with large unit cells. An alternative method is based on Debye theory.43 This method has been used to calculate the thermodynamic properties of the FeMnP_{1-x}Si_x system⁴⁴ and gives good agreement with the properties obtained from the QHA.26

Therefore, the thermodynamic properties of the FeMnP_{1-x}- Ga_x compounds were calculated by the quasiharmonic Debye–Slater model implemented in the Gibbs2 code.⁴⁵

Results and discussion

Structure and stability

 $FeMnP_{1-x}T_x$ (T = Si, Ge, As) compounds crystallize in a hexagonal structure with space group P6(2m). They exhibit a firstorder FM to PM transition at the Curie temperature. Lattice constant a decreases and c increases with almost zero change in the volume during the phase transition. For FeMnP_{0.8}Ge_{0.2} compounds, the experimentally observed lattice constants a and c are 6.18 and 3.31 Å for the FM state and 6.06 and 3.46 Å for the PM state, respectively. The calculated a and c values for 33 atom% Ge compounds are very close to the experimental results, as listed in Table 1. A small increase in the cell volume is observed in FeMnP_{0.8}Ge_{0.2} compounds⁴⁶ across the FM-PM transition, although the compounds with the AFM configuration have smaller cell volumes than those with FM order. This deviation can be understood by the anharmonic effect. Taking into account thermal expansion, the cell volume of FeMnP_{0.67}-Ge_{0.33} calculated with AFM order (*i.e.*, the PM state) will increase to 36.93 Å³, which is larger than the value of 36.51 Å³ obtained for FM order at 0 K. The total and local magnetic moments of FM FeMnP_{0.67}Ge_{0.33} obtained from the calculation are very close to those from experiments (Table 1). Unfortunately, no experimental local magnetic moments of PM FeMnP_{1-x}Ge_x have been reported, and thus quenching of the local moment at 3f (Fe) cannot be verified. DFT level calculations of PM state in Fe2P21 and FeMnP_{1-x}Si_x (ref. 8) indicate that the magnetic moment at 3f sites will disappear in the PM state. Hence, our results are in agreement with those calculations. A recent experimental study

Ge

FM

AFM

| | | Mag. Ord. | a (Å) | c (Å) | V (Å ³ per f.u.) | <i>E</i> ₀ (eV per f.u.) | $\mu_{ m tot} \ (\mu_{ m B} \ { m per} \ { m f.u.})$ | $\mu_{ m Fe}\left(\mu_{ m B} ight)$ | $\mu_{\mathrm{Mn}}\left(\mu_{\mathrm{B}} ight)$ | <i>x</i> ₁ | <i>x</i> ₂ |
|------------------------|--------------|------------|-------|-------|-----------------------------------|-------------------------------------|--|-------------------------------------|---|-----------------------|-----------------------|
| FeMnP _{1-r} | [r | | | | | | | | | | |
| x = 0.33 | Ga | FM | 6.14 | 3.36 | 36.61 | -22.74 | 4.38 | 1.49 | 2.96 | 0.274 | 0.588 |
| | | AFM | 5.83 | 3.67 | 35.90 | -22.68 | 0.00 | 0.00 | 2.83 | 0.262 | 0.570 |
| | Ge | FM | 6.16 | 3.33 | 36.51 | -23.46 | 4.39 | 1.46 | 2.99 | 0.271 | 0.591 |
| | | AFM | 5.86 | 3.61 | 35.71 | -23.38 | 0.00 | 0.00 | 2.80 | 0.262 | 0.575 |
| FeMnP _{0 8} G | e_{02}^{a} | | | | | | | | | | |
| 0.0 | 0.2 | FM (10 K) | 6.18 | 3.31 | 36.43 | _ | _ | 1.71 | 3.01 | 0.2558 | 0.5956 |
| | | PM (295 K) | 6.06 | 3.46 | 36.70 | _ | _ | _ | _ | 0.2527 | 0.5916 |
| x = 0.67 | Ga | FM | 6.56 | 3.05 | 37.83 | -21.69 | 4.63 | 1.68 | 3.03 | 0.252 | 0.623 |
| | | AFM | 6.66 | 2.91 | 37.27 | -21.52 | 0.00 | 1.29 | 2.99 | 0.256 | 0.622 |

-22.99

-22.70

4.44

0.00

Table 1 Lattice parameters (*a*, *c*, *V*), magnetic moments, energy E_0 , and factional atomic positions x_1 (Fe) and x_2 (Mn) of the FeMnP_{1-x}Ga_x compounds. For reference, both the theoretical and experimental values of FeMnP_{1-x}Ge_x compounds are shown

^a Experimental results for Mn_{1.1}Fe_{0.9}P_{0.8}Ge_{0.2} compounds. FM are the values at 10 K and PM are those 295 K from ref. 46 and 47.

37.39

37.51

of FeMnP_{0.5}Si_{0.5} compounds suggested that DFT calculations underestimate the magnetic moment of PM compounds at the 3f site.¹⁹ However, we attribute this discrepancy between theory and experiment to local disorder of P and Si atoms in FeMnP_{0.5}Si_{0.5} compounds. Because Fe moment quenching at 3f site is not observed in the AFM state for FeMnP_{0.33}Ge_{0.67} compounds (Table 1), there is a strong local environment dependence of the magnetic moment at the 3f site in this class of compounds. The significantly lower, but not zero, Fe moment at 3f site in PM FeMnP_{0.5}Si_{0.5} compounds¹⁹ can be easily understood. The predicted relative positions of 3f and 3g sites (x_1 and x_2) for FeMnP_{0.67}Ge_{0.33} are significantly different from the experimental values shown in Table 1, which can be ascribed to Fe/Mn disorder and the lower concentration of Ge in Mn_{1.1}Fe_{0.9}P_{0.8}Ge_{0.2} compounds.

6.42

6.47

3.15

3.10

For the FeMnP_{1-x}Ga_x compounds considered in this study, the structural and magnetic parameters are very close to those obtained for FeMnP_{1-x}Ge_x compounds. This is in accordance with our expectation because of the similar atomic sizes and electronic configurations of Ga and Ge, with the only difference between these atoms being that Ga has one less p electron. Interestingly, a decrease in the *c* parameter and expansion is observed across the FM–PM transition in both FeMnP_{0.33}Ge_{0.67} and FeMnP_{0.33}Ga_{0.67} compounds. This has not been reported in experiment and should be further discussed in detail.

The atomic distances between the four components of the compounds were measured from the fully relaxed cell structures with different magnetic order, and they are listed in Table 2. Experimental observation shows that the interplane metal-tometal and metal-to-metalloid distances D(Fe-Mn), D(Fe-Ge), and D(Mn-P) increase while the intraplane atomic distances D(Fe-P) and D(Mn-Ge) decrease across the FM–PM phase transition. *Ab initio* calculation and AFM modeling of the FeMnP_{0.67}Ge_{0.33} compounds show the same trend for variation of the atomic distances with the phase transition. These conclusions are still valid even though the volume expansion

effect was taken into account. For instance, the predicted Curie temperature T_c is 590 K and the corresponding coefficient of thermal expansion (CTE) is approximately 3.6×10^{-5} K⁻¹ (see Fig. 5). Considering thermal expansion, D(Fe-P) at 590 K is 2.240 Å, which is still smaller than D(Fe-P) = 2.271 Å of the FM state at 0 K. Similarly, the relaxed D(Fe-Mn) of the AFM FeMnP_{0.67}Ge_{0.33} compounds at 590 K will be larger than that obtained for the FM state at 0 K, even though the calculated D(Fe-Mn) for AFM is smaller at 0 K. The predicted evolution of the atomic distances of the FeMnP_{1-x}Ga_x compounds shows almost the same features as those of FeMnP_{1-x}Ge_x. Interestingly, FeMnP_{0.33}Ga_{0.67} and FeMnP_{0.33}Ge_{0.67} compounds show the opposite atomic distance evolution trend during the phase transition. This result can be attributed to *c* decreasing with the phase transition.

1.55

1.49

2.98

2.95

0.250

0.251

0.612

0.614

To evaluate the stability of the predicted $\text{FeMnP}_{1-x}\text{Ga}_x$ compounds, the formation energies were calculated by

$$\Delta E_{\text{FeMnP}_{1-x}\text{Ga}_x} = E_{\text{FeMnP}_{1-x}\text{Ga}_x} - E_{\text{Fe}} - E_{\text{Mn}} - (1-x)E_{\text{P}} - xE_{\text{Ga}}$$

here, $E_{\rm Fe}$, $E_{\rm Mn}$, $E_{\rm P}$, and $E_{\rm Ga}$ are the energy per atom for α -Fe, α -Mn, white phosphorus, and α -Ga, respectively. Fig. 2 shows the c/a dependence of the formation energy of FeMnP_{1-x}Ga_x compounds with different magnetic configurations. The FM state is energetically more stable than its AFM counterpart. The energy difference between the two magnetic states $E = E_{\rm AFM} - E_{\rm FM}$ is 0.02 eV per atom for FeMnP_{0.67}Ga_{0.33} and 0.06 eV per atom for FeMnP_{0.33}Ga_{0.67}, suggesting that FeMnP_{0.33}Ga_{0.67} could have a much larger $T_{\rm c}$ than FeMnP_{0.67}Ga_{0.33}.

The negative formation energies of all of the compounds in the different magnetic states indicate that alloying of these elements is an exothermic reaction. The formation energies of the FM and AFM states of FeMnP_{0.67}Ga_{0.33} are -0.224 and -0.206 eV per atom, respectively. These values are close to those obtained for the FeMnP_{0.67}Ge_{0.33} compounds, as shown in Fig. 2(a). The absolute values of the formation energies of FeMnP_{0.33}Ga_{0.67} are smaller than those of FeMnP_{0.67}Ga_{0.33}. The

| | | Mag. Ord. | D(Fe-Mn) | D(Fe-P) | D(Fe-Ga/Ge) | D(Mn-P) | D(Mn-Ga/Ge) | D(P-Ga/Ge) |
|-------------------------|-----|------------|----------|---------|-------------|---------|-------------|------------|
| $FeMnP_{1-x}T_x$ | | | | | | | | |
| x = 0.33 | Ga | FM | 2.561 | 2.254 | 2.376 | 2.502 | 2.530 | 3.925 |
| | | AFM | 2.565 | 2.180 | 2.384 | 2.520 | 2.505 | 3.830 |
| | Ge | FM | 2.581 | 2.271 | 2.358 | 2.500 | 2.522 | 3.927 |
| | | AFM | 2.575 | 2.192 | 2.367 | 2.511 | 2.486 | 3.832 |
| FeMnP _{0.8} Ge | a.2 | | | | | | | |
| | | FM (10 K) | 2.672 | 2.358 | 2.2874 | 2.5026 | 2.499 | _ |
| | | PM (295 K) | 2.686 | 2.311 | 2.3039 | 2.5225 | 2.476 | _ |
| x = 0.67 | Ga | FM | 2.662 | 2.247 | 2.496 | 2.473 | 2.560 | 4.081 |
| | | AFM | 2.617 | 2.236 | 2.519 | 2.518 | 2.531 | 4.094 |
| | Ge | FM | 2.694 | 2.246 | 2.451 | 2.491 | 2.534 | 4.024 |
| | | AFM | 2.622 | 2.244 | 2.476 | 2.501 | 2.523 | 4.011 |

Table 2 Atomic distances (D in Å) of $FeMnP_{1-x}Ga_x$ and $FeMnP_{1-x}Ge_x$ compounds

^a Experimental results for Mn_{1.1}Fe_{0.9}P_{0.8}Ge_{0.2} compounds. FM are the values at 10 K and PM are those 295 K from ref. 46 and 47.



Fig. 2 *c/a* dependence of the formation energies of $\text{FeMnP}_{1-x}\text{Ga}_x$ compounds in different magnetic states. The formation energies of the FeMnP_{1-x}Ge_x compounds at equilibrium are also shown for comparison. (a) x = 0.33. (b) x = 0.67.

formation energy curves of the FM and AFM states of FeMnP_{0.67}Ga_{0.33} overlap around *c/a* of the equilibrium AFM state, which suggests that the FM to AFM transition could occur by simple axial elongation. The curves of the FeMnP_{0.33}Ga_{0.67} compounds show different characteristics. According to the analysis presented above, the predicted FeMnP_{1-x}Ga_x compounds are energetically stable.

Mechanical properties

Magnetocaloric materials work in a repeated thermal and magnetization cycle, so good mechanical stability around their phase transition temperature is required. In addition, for crystals with hexagonal symmetry, a dynamical stability condition of $C_{44} > 0$, $C_{11} > C_{12}$, $C_{11}C_{33} > (C_{13})^2$, and C_{33} $(C_{11} + C_{12}) > 2(C_{13})^2$ must be satisfied.⁴¹ The calculated elastic constants of the FeMnP_{1-x}Ga_x and FeMnP_{1-x}Ge_x compounds are listed in Table 3. According to the elastic constants, the predicted FeMnP_{1-x}-Ga_x compounds are mechanically stable. In combination with the formation energy analysis, we can conclude that the hexagonal phases of the FeMnP_{1-x}Ga_x compounds are stable in both the FM and AFM states. Namely, this class of compounds could exhibit a FM to PM transition similar to those of FeMnP_{1-x}Ge_x and FeMnP_{1-x}Si_x compounds.

For both the FeMnP_{0.67}Ga_{0.33} and FeMnP_{0.67}Ge_{0.33} compounds, there are marginal decreases in the bulk modulus *B* and shear moduli C_{44} and C_{66} with the FM to AFM transition. However, there are large differences in the C_s and *c* axial compressibility values of the hexagonal crystals of both the FeMnP_{0.67}Ga_{0.33} and FeMnP_{0.67}Ge_{0.33} compounds in the FM and AFM states, suggesting that the magnetic order has a strong effect on the crystal structure (*c/a*) of this class of compounds. For FeMnP_{0.33}Ga_{0.67} and FeMnP_{0.33}Ge_{0.67}, the elastic constants show the opposite trend for the FM and AFM states compared with those for the compounds with lower Ga and Ge concentration. This can be ascribed to the opposite trends of the lattice parameters during the phase transition.

Exchange strain (lattice parameter changes) is always accompanied by the FM–PM phase transition. Therefore, magnetocaloric materials should be sufficiently mechanically stable to bear a large internal strain. The polycrystalline bulk and shear moduli obtained by different averaging schemes,^{40,41} Young's modulus *E*, Poisson's ratio *v*, the Debye temperature θ_D , and the Grüneisen constant γ are listed in Table 4. According to the Pugh criteria,⁴⁸ the FeMnP_{1-x}Ga_x and FeMnP_{1-x}Ge_x compounds with x = 0.33 are ductile (B/G > 1.75 and v > 0.26) in the FM state and brittle (B/G < 1.75 and v < 0.26) in the AFM state. The situation is reversed for x = 0.67, where the FM state is brittle and AFM state is ductile.

The cases investigated in this study are the two extreme cases where Ga (or Ge) only occupies the 1b or 2c site. According to

Table 3 Elastic constants (in GPa) of FeMnP_{1-x}Ga_x and FeMnP_{1-x}Ge_x compounds

| $FeMnP_{1-x}T_x$ | | Mag. Ord. | C_{11} | C_{12} | C_{13} | C ₃₃ | C_{44} | В | R | $C_{\rm s}$ | C_{66} |
|------------------|----|-----------|----------|----------|----------|-----------------|----------|-------|-------|-------------|----------|
| x = 0.33 | Ga | FM | 219.3 | 68.96 | 114.5 | 150.2 | 107.7 | 130.7 | -0.18 | 130.6 | 75.2 |
| | | AFM | 240.6 | 94.74 | 88.86 | 227.1 | 95.1 | 139.1 | -0.04 | 434.2 | 72.9 |
| | Ge | FM | 282.4 | 108.1 | 129.0 | 197.0 | 112.4 | 162.5 | -0.24 | 268.6 | 87.2 |
| | | AFM | 273.5 | 103.2 | 102.8 | 260.1 | 104.5 | 158.2 | -0.03 | 484.7 | 85.3 |
| x = 0.67 | Ga | FM | 216.0 | 79.61 | 76.97 | 169.6 | 90.3 | 117.1 | -0.15 | 327.0 | 68.2 |
| | | AFM | 214.0 | 97.57 | 87.06 | 152.3 | 97.92 | 120.5 | -0.27 | 267.9 | 58.2 |
| | Ge | FM | 265.4 | 95.28 | 105.5 | 198.2 | 108.6 | 146.9 | -0.17 | 335.3 | 85.1 |
| | | AFM | 229.2 | 91.53 | 117.7 | 168.9 | 104.1 | 141.0 | -0.18 | 187.9 | 68.8 |

the current result, we speculate that site occupation disorder of P and Ga/Ge elements may increase the ductility of compounds with x = 0.33 in the AFM state.

Phonon spectra

The phonon band structures and densities of states of FeMnP_{0.67}Ga_{0.33} compounds in different magnetic states are shown in Fig. 3. No imaginary frequency was observed in phonon modes for both FM (Fig. 3(a)) and AFM (Fig. 3(b)) states, confirming the dynamical stability of the compounds in different magnetic state. Comparing the phonon DOS of compounds in different magnetic state, the acoustic modes in the low frequency (0-2 THz) part are similar. The optical modes are reasonably different for FM and AFM states, especially the optical mode between frequency range 9.5-14 THz. In the moderate temperature, the difference between low frequency part of optical phonon modes for FM and AFM states determines the evolution of thermal properties of the compounds across FM-PM (AFM) phase transition. From Fig. 3(c) one can find that the phonon of AFM state is a bit softer than that of FM state for frequency larger than 2 THz. A small difference in optical modes of FM and AFM states for frequency above 2 THz, thus a small difference in the vibrational entropy and the heat capacity $C_{\rm v}$ is expected in the isothermal process. The quantitative analysis on thermal properties of the compounds is given in next section.

Electronic structure

To understand the structural and magnetic properties calculated above, the electronic density of states (DOS) and charge density difference (CDD) were analyzed. In the total DOS (TDOS) of $FeMnP_{1-x}Ga_x$ and $FeMnP_{1-x}Ge_x$ compounds with different magnetic states shown in Fig. 4, the overall shapes of the TDOS are similar for $FeMnP_{1-x}Ga_x$ and $FeMnP_{1-x}Ge_x$ compounds, although the Fermi level of $FeMnP_{1-x}Ga_x$ moves towards a lower energy state because Ga has one less electron than Ge. This leads to a larger DOS value at the Fermi level for FeMnP_{1-x}Ga_x compounds, and thus results in smaller shear moduli compared with those of FeMnP_{1-x}Ge_x (Table 3).49 According to the force theorem,⁵⁰ alloy system having larger density of state at Fermi level is more sensitive to lattice strain and endows the system with smaller elastic modulus. Comparing TDOS of FeMnP_{0.67}Ga_{0.33} in different magnetic states, one can find that AFM state always has larger DOS value at Fermi level than that of FM state, namely AFM state should have smaller shear moduli. This qualitative analysis is in line with the self consistent results of shear moduli C44 and C66 for FM and AFM states.

The two spin channels are symmetric for the AFM state of all of the compounds, indicating disappearance of the overall magnetic moment of the AFM cell. Because of the breaking symmetry, several bands split and new states appear close to the Fermi level as the compounds undergo the FM to PM transition. Comparing the electronic DOS of the AFM and FM states, significant electronic redistribution occurs during the phase transition.

To estimate the evolution of the bonding characteristics and local magnetic moment with the phase transition, the siteprojected density of states (pDOS) of $\text{FeMnP}_{1-x}\text{Ga}_x$ are plotted in Fig. 5. In the FM phase, Mn and Fe share almost all of the pDOS peak for both x = 0.33 and 0.67, that means there is strong covalent-like bonding between Fe and Mn. As the FM

Table 4 Polycrystalline bulk modulus (*B*) and shear modulus (*G*) in GPa under the Voigt, Reuss, and Hill averaging schemes, Young's modulus (*E*) in GPa, Poisson's ratio v, Debye temperature θ_D in K, and Grüneisen constant γ for the FeMnP_{1-x}T_x compounds

| FeMnP _{1-x} T _x | | Mag. Ord. | $B_{\rm V}$ | $B_{\rm R}$ | $G_{\rm V}$ | $G_{\mathbf{R}}$ | $A_{\rm VR}$ | $G_{\rm H}$ | $B_{\rm H}$ | $B_{\rm H}/G_{\rm H}$ | Ε | ν | $\theta_{\rm D}$ | γ |
|-------------------------------------|----|-----------|-------------|-------------|-------------|------------------|--------------|-------------|-------------|-----------------------|-------|-------|------------------|------|
| x = 0.33 | Ga | FM | 131.6 | 130.7 | 77.48 | 54.68 | 0.17 | 66.08 | 131.2 | 1.985 | 169.7 | 0.284 | 441.7 | 1.82 |
| | | AFM | 139.3 | 139.1 | 81.69 | 80.27 | 0.01 | 80.98 | 139.2 | 1.718 | 203.5 | 0.256 | 486.5 | 1.83 |
| | Ge | FM | 166.0 | 162.5 | 88.77 | 78.68 | 0.06 | 83.72 | 164.3 | 1.962 | 214.7 | 0.282 | 493.6 | 1.85 |
| | | AFM | 158.3 | 158.2 | 92.08 | 90.96 | 0.01 | 91.52 | 158.3 | 1.729 | 230.2 | 0.258 | 515.3 | 1.85 |
| <i>x</i> = 0.67 | Ga | FM | 118.7 | 117.1 | 74.31 | 71.36 | 0.02 | 72.83 | 117.9 | 1.692 | 182.0 | 0.244 | 445.0 | 1.85 |
| | | AFM | 124.9 | 120.5 | 71.83 | 64.11 | 0.05 | 67.74 | 122.7 | 1.811 | 171.6 | 0.267 | 427.0 | 1.83 |
| | Ge | FM | 149.0 | 146.9 | 88.63 | 83.21 | 0.03 | 85.92 | 148.0 | 1.722 | 216.0 | 0.257 | 480.3 | 2.22 |
| | | AFM | 142.3 | 141.0 | 75.43 | 62.10 | 0.10 | 68.77 | 141.7 | 2.060 | 177.6 | 0.291 | 432.2 | 1.98 |



Fig. 3 Phonon spectra of $FeMnP_{0.67}Ga_{0.33}$ compounds. (a) Ferromagnetic state, (b) antiferromagnetic state. (c) Phonon densities of states.

order breaks, the pDOS behaves differently. For FeMnP_{0.67}-Ga_{0.33}, the spin-up and spin-down channels of Fe become symmetric, indicating disappearance of the local magnetic moment at the 3f Fe site. For FeMnP_{0.33}Ga_{0.67}, the pDOS of Fe is still asymmetric and has a certain local moment. While the bonding characteristics between Mn and Fe significantly change during the phase transition, only the spin-down channels of Fe and Mn have obvious overlap in the pDOS peaks.

Fig. 6 shows the charge redistribution characteristics with the FM-PM transition. Comparing the CDD in the ac plane of FeMnP_{0.67}Ga_{0.33} in the FM (Fig. 6(a)) and AFM (Fig. 6(c)) states, there is significant redistribution of electrons around Fe. However, no significant electronic redistribution close to Fe is detected for FeMnP_{0.33}Ga_{0.67}. These results indicate that occupation of P atoms on different sites is crucially important for the magnetic properties of this family of compounds. Surprisingly, the electronic distribution between $Fe(\downarrow)$ and Mn atoms with different magnetic polarization is symmetric for AFM FeMnP_{0.67}Ga_{0.33} (Fig. 6(c)). However, asymmetric electronic distribution between $Fe(\downarrow)$ atoms and $Mn(\uparrow)$ and $Mn(\downarrow)$ atoms is observed for $FeMnP_{0.33}Ga_{0.67}$, where the magnetic moment of 3f Fe survives during the phase transition. There is more electron density between $Fe(\downarrow)$ and $Mn(\downarrow)$ atoms than between $Fe(\downarrow)$ and $Mn(\uparrow)$ atoms. This picture indicates that the 3f-Fe site of FeMnP_{0.67}Ga_{0.33} cannot show spin polarization in the AFM states.

From the viewpoint of the energetics,^{17,51} FeMnP_{0.67}Ga_{0.33} in the AFM state shows shrinkage in the basal plane, and thus a large overlap in the electron cloud between Fe and P occurs. Hence, the kinetic energy, which is lower for the spin-degenerate states and leads to a decrease of the magnetic moment, becomes the dominant term in the total energy. Asymmetric electronic distribution in the rectangle formed by two Mn atoms and two P atoms is also detected, indicating the strong influence of the magnetic order in the electronic distribution.



Fig. 4 Calculated TDOS of the FeMnP_{1-x}Ga_x and FeMnP_{1-x}Ge_x compounds. (a) FeMnP_{0.67}Ga_{0.33}, (b) FeMnP_{0.33}Ga_{0.67}. (c) FeMnP_{0.67}Ge_{0.33}. (d) FeMnP_{0.33}Ge_{0.67}.



Fig. 5 Calculated pDOS of the FeMnP_{1-x}Ga_x compounds. (a) Ferromagnetic state of FeMnP_{0.67}Ga_{0.33}, (b) ferromagnetic state of FeMnP_{0.67}Ga_{0.33}. (c) Antiferromagnetic state of FeMnP_{0.67}Ga_{0.33}. (d) Antiferromagnetic state of FeMnP_{0.33}Ga_{0.67}.

Comparing CDD in Fig. 6(a) and (c), denser charge is observed around Ga for AFM state, indicating that Ga–Fe and Ga–Mn bonding is strengthened. In other words, the redistribution of charge around Ga is responsible for the splitting and right shift of optical mode (\sim 10 THz) of Ga in AFM state. Due to the shrinkage of Fe–P distance in AFM state, the covalent like interaction between Fe and P become stronger (CDD between Fe and P become much denser for AFM state) and thus the vibration frequency of optical mode of P and Fe increased reasonably from \sim 11.5 THz for FM state to \sim 13 THz for AFM state.

Thermodynamic properties

Materials for magnetic refrigeration usually work under constant pressure and elevated temperature. Therefore, the

Gibbs free energy of compounds with different magnetic order are calculated and compared for elevating temperature to determine T_c .²⁶ The Gibbs free energy is expressed as

$$G(P, T; \mathbf{m}) = \min_{V} [U(V; \mathbf{m}) + F_{\text{vib}}(V, T; \mathbf{m}) + F_{\text{el}}(V, T; \mathbf{m}) + P(V, T; \mathbf{m})V]$$

where m represents the FM or AFM magnetic state. The vibrational free energy was estimated by the Debye model,⁴⁵ and the free energy of thermal electronic excitation was calculated within the single electron excitation picture.⁴¹

Another term that should be taken into account for the PM state is the magnetic entropy. The static energy of the PM state was simulated with an ordered AFM cell and did not include the entropy contribution from magnetic disorder. The magnetic



Fig. 6 CDD of FeMnP_{1-x}Ga_x compounds in the FM and AFM states. (a) Ferromagnetic state of FeMnP_{0.67}Ga_{0.33}, (b) ferromagnetic state of FeMnP_{0.67}Ga_{0.33}Ga_{0.67}.

entropy of the PM state can be estimated using the mean-field approximation:⁵² $S_{\rm m} = k_{\rm B} \sum \ln(\mu_i + 1)$, where μ_i is the magnetic moment at the ith site. The total Gibbs free energy of the PM state then becomes $G_{\rm tot}(P,T) = G(P,T,AFM) - S_{\rm m}T$.

The Gibbs free energy difference $\Delta G(P,T) = G(P,T,AFM) - G(P,T,FM) - S_m T$ was calculated for FeMnP_{1-x}Ga_x as a function of temperature. $\Delta G(P,T)$ for FeMnP_{0.67}Ge_{0.33} is also shown in Fig. 7(a) for comparison. $\Delta G(P,T)$ gradually decreases and intersects with the abscissa axis at a certain temperature, which defines T_c , as shown in Fig. 7(a). The decrease of $\Delta G(P,T)$ at elevated temperature is mainly from magnetic entropy, but the non-constant slope of $\Delta G(P,T)$ suggests that the anharmonic effect is still playing a considerable role.

The predicted T_c for FeMnP_{0.67}Ge_{0.33} is 590 K, which is close to the measured $T_c = 405$ K for FeMnP_{0.67}Ge_{0.33} compounds and $T_c = 580$ K for FeMnP_{0.5}Ge_{0.5} compounds,^{44,53} verifying that the present scheme can give a reliable prediction of T_c . The difference between experiment and theory could be ascribed to the missing entropy contributions from spin wave excitation and phonon–phonon interactions. The T_c values of FeMnP_{1-x}Ga_x are 500 and 770 K for x = 0.33 and 0.67, respectively, indicating T_c increases as a function of the Ga concentration. Similar characteristics have also been found for Fe₂P_{1-x}Si_x,⁵⁴ FeMnP_{1-x}Si_x,¹⁶ and FeMnP_{1-x}Ge_x (ref. 46 and 47) compounds.

The temperature dependence of the total entropy of the compounds is plotted in Fig. 7(b). The entropy change of FeMnP_{0.67}Ge_{0.33} around the phase transition is $\Delta S = 66.69 \text{ J K}^{-1} \text{ kg}^{-1}$, which is comparable with the experimental value of 49.74 J K⁻¹ kg⁻¹ for Fe_{1.1}Mn_{0.9}P_{0.8}Ge_{0.2} at $T_c = 278$ K.⁴⁶

FeMnP_{0.67}Ga_{0.33} exhibits an entropy change of $\Delta S = 69.34$ J K⁻¹ kg⁻¹ around T_c , which is similar in magnitude to ΔS of FeMnP_{0.67}Ge_{0.33} and close to the experimental value for FeMnP_{0.67}Gi_{0.33} of $\Delta S = 58.6$ J K⁻¹ kg⁻¹.⁵⁵ FeMnP_{0.67}Ga_{0.33} of $\Delta S = 89.26$ J K⁻¹ kg⁻¹.

The entropy change can be divided into the vibrational and magnetic entropy changes: $\Delta S = \Delta S_{\rm vib} + \Delta S_{\rm m}$. Here, the contribution of thermal electronic excitation is omitted because it is too small to have a measurable effect. For FeMnP_{0.67}Ga_{0.33} and FeMnP_{0.67}Ge_{0.33}, the $\Delta S_{\rm vib}$ values are -2.78 and -4.56 J K⁻¹ kg⁻¹ for the FM-PM transition, respectively. And $\Delta S_{\rm vib} = -20.4$ J K⁻¹ kg⁻¹ for FeMnP_{0.33}Ga_{0.67}, and thus adding the magnetic entropy term $\Delta S_{\rm m}$ the total entropy change becomes 89.26 J K⁻¹ kg⁻¹. Therefore, the magnetic entropy is playing major role on the entropy change of the compounds. And further, the decrease in the vibrational entropy is partially account for the relatively higher $T_{\rm c}$ for FeMnP_{1-x}Ga_x and FeMnP_{1-x}Ge_x compounds than that of FeMnP_{1-x}Si_x.^{26,27}

Fig. 7(c) and (d) shows the temperature dependence of the heat capacity under constant pressure and the linear CTE, respectively. They are discontinuous at T_c , which is a feature of first-order phase transitions. For first-order phase transition, the latent heat is defined as $L = \Delta S \times T_c$. The estimated latent heats for FeMnP_{1-x}Ga_x are 34.67 (x = 0.33) and 68.73 kJ kg⁻¹ (x = 0.67), and the value for FeMnP_{0.67}Ge_{0.33} is 39.35 kJ kg⁻¹.

The jump in the CTE does not contradict with experimental observations of a very small volume change of $\sim 1\%$ at T_c for FeMnP_{1-x}Si_x and FeMnP_{1-x}Ge_x compounds.²⁴ Assuming that



Fig. 7 Calculated Gibbs free energy G (a), entropy S (b), specific heat at constant pressure C_P (c), and linear CTE (d) as a function of temperature.

FeMnP_{0.67}Ge_{0.33} is in full FM order just before the phase transition and in the PM state just above T_c , the volume per unit formula at $T_c = 590$ K for FM order is 38.83 Å³ and that for AFM order is 38.57 Å³. The change in volume is at most ~1%, which is still in line with experimental findings. Similar results were obtained for the FeMnP_{1-x}Ga_x compounds.

Conclusions

Density functional theory was used to investigate the mechanical and thermophysical properties of Fe₂P-type FeMnP_{1-x}T_x (T = Ga, Ge; x = 0.33, 0.67) compounds, and thus identify the possibility of substituting phosphorus with gallium rather than silicon or germanium and obtaining GMC compounds with better mechanical stability with FM to PM phase transitions. The predicted formation energies, elastic constants and phonon spectra show that the different magnetic states of the hexagonal phase of FeMnP_{1-x}Ga_x are energetically and mechanically stable. The predicted magnetic moment, Curie temperature, and entropy change of FeMnP_{0.67}Ga_{0.33} are very close to those of FeMnP_{0.67}Ge_{0.33}, a well-known GMC compounds. Therefore, it is expected that FeMnP_{1-x}Ga_x could be a candidate for room temperature magnetic refrigeration.

The relatively large single crystalline elastic constants show the mechanical stability of this family of compounds in both the FM and AFM states. This ensures the long-term applicability of $FeMnP_{1-x}Ga_x$ in magnetic refrigeration facilities under repeated thermal and magnetic cycles. Both FeMnP_{0.67}Ga_{0.33} and FeMnP_{0.67}Ge_{0.33} show good ductility in the FM state. However, their AFM states are brittle. Conversely, the FM states of FeMnP_{0.33}Ga_{0.67} and FeMnP_{0.33}Ge_{0.67} are brittle and their AFM states exhibit good ductility. However, it is expected that the occupation disorder of P and Ga/Ge could increase the ductility of the compounds in the AFM states. Our DFT calculations indicate that elements like Ga with three valence electrons could also be alloyed into the hexagonal phase of FeMnbased Fe₂P type GMC compounds. Experimental synthesis of $FeMnP_{1-x}Ga_x$ compounds, and thus verification of their magnetocaloric properties, is expected.

Acknowledgements

The authors acknowledge financial support from the National Natural Science Foundation of China (grant numbers 11464037 and 50901039) and the Inner Mongolia Natural Science Foundation (grant number 2016MS0113), and the support from NJYT-12-B07.

Notes and references

- 1 K. A. Gschneidner Jr, V. K. Pecharsky and A. O. Tsokol, *Rep. Prog. Phys.*, 2005, **68**, 1479–1539.
- 2 A. Smith, C. Bahl, R. Bjork, K. Engelbrecht, K. K. Nielsen and N. Pryds, *Adv. Energy Mater.*, 2012, **2**, 1288–1318.
- 3 O. Tegus, E. Brück, K. H. J. Buschow and F. R. de Boer, *Nature*, 2002, **415**, 150–152.

- 4 E. Brück, O. Tegus, D. T. C. Thanh and K. H. J. Buschow, J. Magn. Magn. Mater., 2007, **310**, 2793–2799.
- 5 E. Brück, O. Tegus, L. Zhang, X. W. Li, F. R. de Boer and K. H. J. Buschow, *J. Alloys Compd.*, 2004, **383**, 32–36.
- 6 L. Song, G. F. Wang, Z. Q. Ou, O. Haschaolu, O. Tegus,
 E. Brück and K. H. J. Buschow, *J. Alloys Compd.*, 2009, 474, 388–390.
- 7 N. T. Trung, Z. Q. Ou, T. J. Gortenmulder, O. Tegus,
 K. H. J. Buschow and E. Brück, *Appl. Phys. Lett.*, 2009, 94, 102513.
- 8 N. H. Dung, Z. Q. Ou, L. Caron, L. Zhang, D. T. C. Thanh, G. A. de Wijs, R. A. de Groot, K. H. J. Buschow and E. Brück, *Adv. Energy Mater.*, 2011, 1, 1215–1219.
- 9 V. Hoglin, M. S. Andersson, T. Sarkar, P. Nordblad and M. Sahlberg, *J. Magn. Magn. Mater.*, 2015, **374**, 455–458.
- Z. Gercsi, E. K. Delczeg-Czirjak, L. Vitos, A. S. Wills,
 A. Daoud-Aladine and K. G. Sandeman, *Phys. Rev. B:* Condens. Matter Mater. Phys., 2013, 88, 024417.
- 11 N. H. Dung, L. Zhang, Z. Q. Ou and E. Brück, *Appl. Phys. Lett.*, 2011, **99**, 092511.
- 12 F. Guillou, G. Porcari, H. Yibole, N. van Dijk and E. Brück, *Adv. Mater.*, 2014, **26**, 2671–2675.
- 13 S. Berri, J. Supercond. Novel Magn., 2016, 29, 1309-1315.
- 14 P. Roy, E. Torun and R. A. de Groot, *Phys. Rev. B*, 2016, **93**, 094110.
- L. Caron, M. Hudl, N. H. Hoglin, C. P. Gomez, M. Sahlberg,
 E. Brück, Y. Andersson and P. Nordblad, *Phys. Rev. B:* Condens. Matter Mater. Phys., 2013, 88, 094440.
- 16 V. Hoglin, J. Cedervall, M. S. Andersson, T. Sarkar, M. Hudl, P. Nordblad, Y. Andersson and M. Sahlberg, *RSC Adv.*, 2015, 5, 8278–8284.
- 17 M. Hudl, P. Nordblad, T. Bjorkman, O. Eriksson, L. Haggstrom, M. Sahlberg, Y. Andersson, E. K. Delczeg-Czirjak and L. Vitos, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2011, 83, 134420.
- 18 X. F. Miao, L. Caron, P. Roy, N. H. Dung, L. Zhang, W. A. Kockelmann, R. A. de Groot, N. H. van Dijk and E. Brück, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2014, 89, 174429.
- 19 H. Yibole, F. Guillou, L. Caron, E. Jimenez, F. M. F. de Groot, P. Roy, R. de Groot and E. Brück, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2015, **91**, 014429.
- 20 F. Guillou, K. Ollefs, F. Wilhelm and A. Rogalev, *Phys. Rev. B:* Condens. Matter Mater. Phys., 2015, **92**, 224427.
- 21 H. Wang, Z. D. Zhang, R. Q. Wu and L. Z. Sun, *Acta Mater.*, 2013, **61**, 2919–2925.
- 22 S. Berri, J. Magn. Magn. Mater., 2016, 401, 667-672.
- 23 E. Brück, Handb. Magn. Mater., 2007, 17, 235-291.
- 24 E. Brück, J. Phys. D: Appl. Phys., 2005, 38, 381-391.
- 25 M. J. Neish, M. P. Oxley, J. Guo, B. C. Sales, L. J. Allen and M. F. Chisholm, *Phys. Rev. Lett.*, 2015, **114**, 106101.
- 26 D. T. Cam Thanh, E. Brück, O. Tegus, J. Klaasse and K. Buschow, J. Magn. Magn. Mater., 2007, 310, e1012–e1014.
- 27 X. Moya, S. Kar-Narayan and N. D. Mathur, *Nat. Mater.*, 2014, 13, 439–450.
- 28 P. Roy, E. Torun and R. A. de Groot, *Phys. Rev. B*, 2016, **93**, 165101.

- 29 M. E. Gruner, W. Keune, B. Roldan Cuenya, C. Weis, J. Landers, S. I. Makarov, D. Klar, M. Y. Hu, E. E. Alp, J. Zhao, M. Krautz, O. Gutfleisch and H. Wende, *Phys. Rev. Lett.*, 2015, **114**, 057202.
- 30 X. F. Miao, L. Caron, J. Cedervall, P. C. M. Gubbens, P. D. de Réotier, A. Yaouanc, F. Qian, A. R. Wildes, H. Luetkens, A. Amato, N. K. van Dijk and E. Brück, *Phys. Rev. B*, 2016, 94, 014426.
- 31 P. E. Blöchl, Phys. Rev. B, 1994, 50, 17953-17979.
- 32 P. Hohenberg and W. Kohn, *Phys. Rev.*, 1964, **136**, B864–B871.
- 33 W. Kohn and L. J. Sham, Phys. Rev., 1965, 140, A1133-A1138.
- 34 G. Kresse and J. Hafner, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1993, **47**, 558–561.
- 35 G. Kresse and J. Furthmüller, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, 54, 11169.
- 36 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, 77, 3865–3868.
- 37 S. Berri, Chin. Phys. B, 2017, 55, 195-202.
- 38 H. J. Monkhorst and J. D. Pack, *Phys. Rev. B: Solid State*, 1976, 13, 5188–5192.
- 39 F. D. Murnaghan, Proc. Natl. Acad. Sci. U. S. A., 1994, 244–247.
- 40 L. Vitos, Computational Quantum Mechanics for Materials Engineers: the EMTO Method and Applications, Springer-Verlag, 2007, pp. 107–113.
- 41 G. Grimvall, *Thermophysical Properties of Materials*, Elsevier Science B V, 1999, pp. 27–40.
- 42 A. Togo, L. Chaput, I. Tanaka and G. Hug, *Phys. Rev. B*, 2010, **81**, 174301.

- 43 J. Slater, *Introduction to Chemical Physics*, McGraw-Hill, 1939, vol. 152, pp. 488–489.
- 44 B. Wurentuya, S. Ma, O. Tegus, et al., J. Phys.: Condens. Matter, submitted.
- 45 A. Otero-de-la-Roza, D. Abbasi-Perez and V. Luana, *Comput. Phys. Commun.*, 2011, **182**, 2232–2248.
- 46 M. Yue, H. G. Zhang, D. M. Liu and J. X. Zhang, *Chin. Phys. B*, 2015, **24**, 017505.
- 47 D. Liu, M. Yue, J. X. Zhang, T. M. McQueen, J. W. Lynn, X. L. Wang, Y. Chen, J. Y. Li, R. J. Cava, X. B. Liu, Z. Altounian and Q. Huang, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2009, **79**, 014435.
- 48 S. F. Pugh, Philosophical Magazine, 1954, 45, 823-843.
- 49 H. L. Zhang, M. P. J. Punkkinen, B. Johansson, S. Hertzman and L. Vitos, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, 81, 184105.
- 50 A. R. Mackintosh and O. K. Anderson, *Electrons at the Fermi Surface*, Cambridge University Press, 1980, pp. 149–224.
- 51 G. J. Li, W. Li, S. Schönecker, X. Q. Li, E. K. Delczeg-Czirjak, Y. O. Kvashnin, O. Eriksson, B. Johansson and L. Vitos, *Appl. Phys. Lett.*, 2014, **105**, 262405.
- 52 G. Grimvall, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1989, 39, 12300–12301.
- 53 X. W. Li, O. Tegus, L. Zhang, W. Dagula, E. Brück,
 K. H. J. Buschow and F. R. de Boer, *IEEE Trans. Magn.*, 2003, 39, 3148–3150.
- 54 P. Jernberg, A. A. Yousif, L. Häggström and Y. Andersson, J. Solid State Chem., 1984, 53, 313–322.
- 55 Z. Ou, Magnetic structure and phase formation of magnetocaloric Mn-Fe-P-X compounds, Delft University of Technology, 2013.