# **RSC Advances**

## PAPER

Check for updates

Cite this: RSC Adv., 2017, 7, 33568

Received 28th April 2017 Accepted 26th June 2017 DOI: 10.1039/c7ra04797e rsc.li/rsc-advances

## I. Introduction

Presently, one of the greatest challenges for researchers is finding a thermodynamically efficient process for separating and capturing CO<sub>2</sub>.<sup>1</sup> It has been commonly accepted that global warming is related directly to the increased levels of CO2.<sup>2-4</sup> CO2 is mainly emitted as a result of the combustion of fossil fuels, certain chemical plant processes, and production of synthesis gas.<sup>5</sup> Currently, the principal CO<sub>2</sub> separation technologies for post-combustion capture include physical adsorption, physical or chemical absorption, cryogenic distillation, and membrane separation.<sup>6,7</sup> Among the various types of CO<sub>2</sub> separation technologies, membrane technology promises excellent separation performance while being relatively less energy- and capital However, current commercial intensive.8-11 polymeric membranes, such as polyimide and cellulose acetate membranes, have low CO<sub>2</sub> selectivity and permeability, since they are based on a solution-diffusion mechanism and rely chiefly on the subtle size differences of the penetrants to accomplish separation.12,13 To overcome the low separation performance of polymeric membranes, facilitated transport was introduced so that higher gas permeability and outstanding selectivity could be achieved.14-16 The facilitated transport membrane has attracted attention due to the reversible reaction with a specific gas component.17 Hence, the reaction in the membrane can generate another transport mechanism alongside the simple solution-diffusion mechanism.18,19

## Highly permeable ionic liquid 1-butyl-3methylimidazoliumtetrafluoroborate (BMIMBF<sub>4</sub>)/ CuO composite membrane for CO<sub>2</sub> separation

Young Sung Park, Chaeyeon Ha and Sang Wook Kang D\*

An ionic liquid (IL) 1-butyl-3-methylimidazoliumtetrafluoroborate (BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>)/CuO composite was prepared for CO<sub>2</sub> transport membranes. CuO nanoparticles (NPs) were successfully generated in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>. The formation of CuO NPs was ascribed to the favorable interaction between the ions of BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> and the surface of the CuO particles. To confirm the coordination behavior of the BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO membrane, TGA and FT-Raman spectroscopy were employed. The ideal CO<sub>2</sub>/N<sub>2</sub> selectivity in the case of the composite material was 21.0, with a CO<sub>2</sub> permeance of 52.4 GPU, while the neat BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> membrane showed a selectivity of 5.0 and a CO<sub>2</sub> permeance of 17.0 GPU. The enhanced separation performance was attributed to (1) the synergistic effect of well-dispersed CuO nanoparticles, resulting in enhanced CO<sub>2</sub> solubility due to the increased surface of the oxide particle layer and (2) the abundant free ions in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>.

Given the above, ionic liquids (ILs) have been utilized to prepare facilitated CO2 transport membranes.20,21 ILs have attracted great attention because of their highly tunable properties such as low flammability, high chemical and thermal stability, and extremely low volatility.22 Moreover, ILs based on imidazolium cations present outstanding CO2 separation performance since the amine group in the imidazolium ring acts a CO<sub>2</sub> carrier in CO<sub>2</sub>/CH<sub>4</sub> and CO<sub>2</sub>/N<sub>2</sub> separation.<sup>23</sup> For example, CO2 separation performance utilizing 1-butyl-3methylimidazolium tetrafluoroborate (BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>) showed that CO<sub>2</sub>/N<sub>2</sub> and CO<sub>2</sub>/CH<sub>4</sub> ideal selectivity were 5 and 4.8, respectively.24 Surprisingly, the CO2 permeance was 17 GPU.24 Furthermore, in the case of CO<sub>2</sub> separation utilizing pure 1butyl-3-methylimidazolium nitrate (BMIM<sup>+</sup>NO<sub>3</sub><sup>-</sup>), the ideal CO<sub>2</sub>/N<sub>2</sub> selectivity and CO<sub>2</sub> permeance were 4.7 and 5.2 GPU, respectively.25

To enhance the CO<sub>2</sub> separation performance of neat ILs, our group investigated selective CO<sub>2</sub> separation utilizing ILs with lithium tetrafluoroborate (LiBF<sub>4</sub>).<sup>26</sup> It was established that the facilitated transport membrane consisting of lithium tetrafluoroborate as a CO<sub>2</sub> carrier and BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> exhibits an ideal selectivity of 8.40 for CO<sub>2</sub>/N<sub>2</sub> with a CO<sub>2</sub> permeance of 13.36 GPU.<sup>26</sup> Lee *et al.* reported that a 1-methyl-3-octylimidazolium tetrafluoroborate (MOIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>)/positively polarized Cu nanoparticle membrane shows CO<sub>2</sub>/N<sub>2</sub> and CO<sub>2</sub>/CH<sub>4</sub> selectivities of 25.2 and 24.3, respectively, with a CO<sub>2</sub> permeance of 24.2 GPU.<sup>27</sup> In addition, our group reported that BMIM<sup>+</sup>NO<sub>3</sub><sup>-</sup>/Cu nanoparticle membranes demonstrate a CO<sub>2</sub> permeance of 9.8 GPU with an ideal selectivity of 12.25 for CO<sub>2</sub>/N<sub>2</sub> and CO<sub>2</sub>/CH<sub>4</sub>.<sup>25</sup> These results indicated that Cu NPs could be an excellent carrier for CO<sub>2</sub> separation in ILs.

Open Access Article. Published on 03 July 2017. Downloaded on 8/13/2025 5:15:22 AM.



View Article Online

View Journal | View Issue

Department of Chemistry, Sangmyung University, Seoul 110-743, Republic of Korea. E-mail: swkang@smu.ac.kr; Fax: +82 2 2287 5362; Tel: +82 2 2287 5362

Very recently, our group reported that metal oxide nanoparticles could be utilized for a CO<sub>2</sub> separation membrane. For example, an MOIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup>AgO composite membrane showed a high ideal selectivity of 23.4 for CO<sub>2</sub>/N<sub>2</sub>, with a CO<sub>2</sub> permeance of 18.7 GPU; on the other hand, the neat MOIM<sup>+</sup>BF<sub>4</sub><sup>--</sup> membrane showed a selectivity of 15.9, with a CO<sub>2</sub> permeance of 12.7 GPU.<sup>28</sup> Furthermore, when AgO particles were added to BMIM<sup>+</sup>BF<sub>4</sub><sup>--</sup>, a CO<sub>2</sub>/N<sub>2</sub> selectivity of 28.2 and CO<sub>2</sub> permeance of 14.1 GPU were reported.<sup>29</sup> These results indicated that the dissociated AgO nanoparticles have strong affinity for CO<sub>2</sub> due to the oxide layer.<sup>29</sup>

In this study, in order to clarify the effect of the metal oxide in ILs, experiments were conducted with other oxides. Copper(n) oxide was selected because its properties are similar to those of silver oxide. For the BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO composite membrane, the dissociated CuO particles were expected to enhance the solubility of the CO<sub>2</sub> molecules due to the nano-oxide particle layer. Moreover, when CuO was incorporated into BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, the free ions could also enhance the solubility of CO<sub>2</sub> molecules since the quadrupole moment of CO<sub>2</sub> was relatively higher than N<sub>2</sub>, resulting in the increased separation performance.

## II. Experimental

### 2.1 Materials

Paper

 $BMIM^+BF_4^-$  was purchased from Merck KGaA (Darmstadt, Germany). CuO was purchased from Sigma-Aldrich Chemical Co. Ethyl alcohol (>94.0% purity) was purchased from Daejung Chemicals & Metals. All chemicals were used as received.

#### 2.2 Characterization

A sonifier (Branson 450, Branson Ultrasonics Corporation, Danbury CT, USA) with a standard tip was used. Scanning electron microscopy (SEM) images were obtained using a JEOL JSM-5600LV system. Transmission electron microscopy (TEM) images were obtained using a JEM-2010 system operating at 200 kV. The weight loss was measured by thermogravimetric analysis (TGA, TGA Q50, TA Instrument) of the complex membrane in flowing N<sub>2</sub>. FT-Raman measurements were performed for the BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup>/CuO solution at room temperature using a Horiba Jobin Yvon LabRam Aramis apparatus with a diode laser beam at an excitation wavelength of 785 nm.

#### 2.3 Membrane preparation

The membranes were prepared utilizing BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, copper( $\pi$ ) oxide, and ethanol. First, copper( $\pi$ ) oxide was sonicated to disperse in ethanol for 5 min, and then, BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> was added into the mixture. The dispersion was heated at 85 °C for 24 h to evaporate ethanol. The final solution was coated onto a polysulfone support (Toray Chemical Korea Inc.) and then cast using an RK control coater (Model 202, Control Coater RK Print-Coat Instruments Ltd., UK). The best performance of BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO was observed at a weight ratio of 1/0.007.

#### 2.4 Gas separation performance

Gas flow rates were measured with a bubble flow meter at an upstream pressure of 2 kgf  $\cdot$  cm<sup>-2</sup> and atmospheric downstream

pressure. The unit of gas permeance is GPU, with 1 GPU =  $1 \times 10^{-6}$  cm<sup>3</sup> (STP)/(cm<sup>2</sup> s cmHg). Selectivity was defined as ideal selectivity (CO<sub>2</sub> permeance/N<sub>2</sub> permeance).

## III. Results and discussion

# 3.1 Transmission electron microscope (TEM) image of BMIM $^{+}BF_{4}^{-}/CuO$

TEM images were recorded to investigate the size and dispersity of the dissociated copper oxide particles in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>. As shown in Fig. 1, no significant copper(II) oxide agglomerates were present, and CuO particles were mostly observed as small nanoparticles with an average diameter of 10 nm. These results indicated that the dissociated CuO nanoparticles are advantageous for increasing the solubility of CO<sub>2</sub> molecules.

#### 3.2 Separation performance

Fig. 2 presents the cross-section structures of the BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup> CuO composite membrane. The utilized polysulfone support had a finger-like structure. The thickness of the coated selective layer was approximately 4.1  $\mu$ m. Based on the SEM image, it was suggested that the selective layer was not penetrated into the polysulfone microporous support.

To investigate the effect of CuO concentration in the BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup>CuO membrane on the CO<sub>2</sub> separation performance, the pure gas permeance of CO<sub>2</sub> and N<sub>2</sub> through the BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup>CuO composite membrane was measured at increasing weight ratios of CuO, as shown in Fig. 3. As the CuO weight ratio increased, the CO<sub>2</sub> selectivity also sharply increased. As shown in Table 1, the highest CO<sub>2</sub> permeance (52.4 GPU) and  $CO_2/N_2$  selectivity (21.0) were observed at a BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup>CuO weight ratio of 1/0.007. At CuO weight ratios higher than 0.007, both CO<sub>2</sub> permeance and selectivity remained unchanged. However, above a CuO weight ratio of 0.04, the copper oxide was not well dispersed in  $BMIM^+BF_4^-$ , and therefore, significant copper oxide agglomerates were present. A previous study revealed that for neat BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, the  $CO_2$  permeance and  $CO_2/N_2$  selectivity were 17.0 GPU and 5.0, respectively, as shown Table 1.24 On the other hand, when CuO was added to  $BMIM^+BF_4^-$ , the  $CO_2$  permeance increased from 17 to 52.4 GPU and the CO<sub>2</sub>/N<sub>2</sub> selectivity increased from 5.0 to



Fig. 1 (a) TEM image of the dissociated CuO nanoparticles in  ${\sf BMIM^+BF_4^-}$  and (b) enlarged image.



Fig. 2 SEM image of BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO composite membrane.



Fig. 3 Gas separation performance of  $BMIM^+BF_4^-/CuO$  composite membranes: (a) pure gas permeance and (b) ideal  $CO_2/N_2$  selectivity.

21.0. Furthermore, it was confirmed that  $CO_2$  permeance was much higher than the value reported in previous study consisting of BMIMBF4/AgO composite. (CO<sub>2</sub> permeance: 14.1 GPU)<sup>29</sup> These results were ascribed to two factors: (1) well-dispersed CuO nanoparticles, which could lead to enhanced CO<sub>2</sub> solubility due to the increased oxide layer and (2) abundant free ions in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, enabling the enhanced CO<sub>2</sub> transport.

Table 1 Pure gas permeance and selectivity of neat BMIM  $^{+}BF_{4}^{-}$  and  $BMIM \,^{+}BF_{4}^{-}/CuO$  membranes with a weight ratio of 1/0.007

	CO <sub>2</sub> permeance (GPU)	N <sub>2</sub> permeance (GPU)	CO <sub>2</sub> /N <sub>2</sub> selectivity
Neat BMIM <sup>+</sup> BF <sub>4</sub> <sup>-</sup> (ref. 24)	17.0	3.4	5.0
BMIM <sup>+</sup> BF <sub>4</sub> <sup>-</sup> /AgO <sup>29</sup>	14.1	0.5	28.2
BMIM <sup>+</sup> BF <sub>4</sub> <sup>-/</sup> CuO	52.4	2.5	21.0

#### 3.3 Thermogravimetric analysis

The thermal properties of the neat  $BMIM^+BF_4^-$  and  $BMIM^+BF_4^-/CuO$  composite membranes were analyzed by TGA. Fig. 4 presents weight loss at temperatures from 350 to 500 °C. The major weight loss was ascribed to the structural decomposition of the IL  $BMIM^+BF_4$ . The  $BMIM^+BF_4^-/CuO$  composite showed slower decomposition with a smaller weight loss of 70.6% at 450 °C, as compared to that (53.2%) of neat  $BMIM^+BF_4^-$  at the same temperature. If the agglomeration of CuO particles in  $BMIM^+BF_4^-$  occurred, the decomposition temperature would remain constant. However, this result indicates that CuO particles were well dispersed in the IL  $BMIM^+BF_4^-$ , because of the coordinative interaction between the CuO surface and  $BMIM^+BF_4^-$ . Thus, the thermal stability of the  $BMIM^+BF_4^-/CuO$  composite membrane increased.

#### 3.4 FT-Raman spectroscopy

Interactions between BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> and CuO in the BMIM<sup>+</sup>BF<sub>4</sub><sup>-/</sup> CuO composite membranes were investigated by FT-Raman spectroscopy. The Raman spectrum in the region of the BF<sub>4</sub><sup>-</sup> stretching bands is shown in Fig. 5. Three different ionic species were observed in the FT-Raman spectra of the ILs: free ions, ion pairs, and ionic aggregates. The BF<sub>4</sub><sup>-</sup> stretching bands at 765, 770, and 774 cm<sup>-1</sup> were assigned to the free ions, ion pairs, and ion aggregates, respectively.<sup>30</sup> BMIM<sup>+</sup> forms ion aggregates and ion pairs with BF<sub>4</sub><sup>-</sup> in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> through hydrogen bonding.<sup>24</sup> A previous report showed that the Raman spectrum of neat BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> included signals attributed to ion



Fig. 4 TGA results for neat  $BMIM^+BF_4^-$  (blue) and  $BMIM^+BF_4^-/CuO$  composite (red).





Fig. 5 FT-Raman spectrum of  $BMIM^+BF_4^-/CuO$  nanoparticles.

pairs and ion aggregates.<sup>24</sup> As the copper oxide is well dispersed in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, free BMIM<sup>+</sup> and BF<sub>4</sub><sup>-</sup> ions are observed. These results can be explained by the coordinative interaction between BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup> and the surface of the CuO nanoparticles, which results in weakened interactions between BMIM<sup>+</sup> and BF<sub>4</sub><sup>-</sup>. Therefore, CO<sub>2</sub> separation performance could be enhanced by the increase of solubility due to abundant free ions.

## IV. Conclusions

We have successfully stabilized CuO nanoparticles by employing an ionic liquid BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>. The coordinative interactions of the BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO composite membrane were characterized by TEM, TGA, and FT-Raman analyses. The separation performance of the BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>/CuO composite membrane was considerably enhanced compared to that of the neat BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>. When CuO was incorporated into BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>, the CO<sub>2</sub>/N<sub>2</sub> selectivity increased to 21.0, with a CO<sub>2</sub> permeance of 52.4 GPU. These results were attributed to (1) the synergistic effect of well-dispersed CuO nanoparticles, which result in enhanced CO<sub>2</sub> solubility due to the increased surface of the oxide particle layer and (2) the abundant free ions in BMIM<sup>+</sup>BF<sub>4</sub><sup>-</sup>.

## Acknowledgements

This work was supported by an Energy Efficiency & Resources grant from the Korea Institute of Energy Technology Evaluation and Planning (KETEP), funded by the Korean Government *via* the Ministry of Trade, Industry, and Energy (20122010100040). This work was also supported by the Basic Science Research Program (2017R1D1A1B03032583) through the National Research Foundation of Korea (NRF), and funded by the Ministry of Science, ICT, and Future Planning.

## Notes and references

1 N. V. Blinova and F. Svec, J. Mater. Chem. A, 2014, 2, 600-604.

- 2 N. Du, H. B. Park, M. M. Dal-Cin and M. D. Guiver, *Energy Environ. Sci.*, 2012, **5**, 7306–7322.
- 3 D. Aaron and C. Tsouris, Sep. Sci. Technol., 2005, 40, 321-348.
- 4 H. Q. Yang, Z. H. Xu, M. H. Fan, R. Gupta, R. B. Slimane, A. E. Bland and I. Wright, *J. Environ. Sci.*, 2008, **20**, 14–27.
- 5 J. Huang, J. Zou and W. S. Winston Ho, *Ind. Eng. Chem. Res.*, 2008, 47, 1261–1267.
- 6 C. H. Yu, C. H. Huang and C. S. Tan, Aerosol Air Qual. Res., 2012, 12, 745–769.
- 7 O. Davidson and B. Metz, *International Panel on Climate Change*, 2005.
- 8 P. Jungho, K. Deukju and N. Sangyong, *Membr. J.*, 2015, 25, 547–557.
- 9 P. arume and K. Sungjoong, Membr. J., 2016, 26, 126-134.
- 10 R. W. Baker and K. Lokhandwala, *Ind. Eng. Chem. Res.*, 2008, 47, 2109–2121.
- 11 W. Yave, A. Car, J. Wind and K. V. Peinemann, *Nanotechnology*, 2010, **21**, 395301.
- 12 A. Meisen and X. Shuai, *Energy Convers. Manage.*, 1997, 38, S37–S42.
- 13 W. J. Koros and R. Mahajan, *J. Membr. Sci.*, 2000, 175, 181– 196.
- 14 L. Deng, T. J. Kim and M. B. Hagg, *J. Membr. Sci.*, 2009, **340**, 154–163.
- 15 W. J. Ward and W. L. Robb, Science, 1957, 156, 1481-1484.
- 16 R. Yegani, H. Hirozawa, M. Teramoto, H. Himei, O. Okada, T. Takigawa, N. Ohmura, N. Matsumiya and H. Matsuyama, *J. Membr. Sci.*, 2007, **291**, 157–164.
- 17 S. Kasahara, E. Kamio, T. Ishigami and H. Matsuyama, Chem. Commun., 2012, 48, 6903-6905.
- 18 S. U. Hong, J. H. Jin, J. Won and Y. S. Kang, *Adv. Mater.*, 2000, 12, 968–971.
- 19 Y. Suzuki, H. Nishide and E. Tsuchida, *Macromol. Res.*, 2000, 33, 2530–2534.
- 20 C. Yu, T. Zhu, X. Zhang and H. Liu, *Sci. Adv. Mater.*, 2015, 7, 1213–1220.
- 21 J. Chang, G. H. Hong and S. W. Kang, *RSC Adv.*, 2015, 5, 69698–69701.
- 22 P. T. Nguyen, B. A. Voss, E. F. Wiesenauer, D. L. Gin and R. D. Noble, *Ind. Eng. Chem. Res.*, 2013, **52**, 8812–8821.
- 23 K. E. Gutowski and E. J. Maginn, J. Am. Chem. Soc., 2008, 130, 14690–14704.
- 24 J. H. Lee, J. Hong, J. H. Kim, Y. S. Kang and S. W. Kang, *Chem. Commun.*, 2012, **48**, 5298–5300.
- 25 G. H. Hong, J. H. Oh, D. Ji and S. W. Kang, *Chem. Eng. J.*, 2014, **252**, 263–266.
- 26 Y. Choi, G. H. Hong and S. W. Kang, J. Nanosci. Nanotechnol., 2016, 16, 2832–2835.
- 27 J. H. Lee, J. Hong, J. H. Kim, D. Song, Y. S. Kang and S. W. Kang, *Chem. Eng. J.*, 2014, 235, 252–256.
- 28 D. Ji and S. W. Kang, *Korean J. Chem. Eng.*, 2016, 33(2), 666–668.
- 29 D. Ji, Y. S. Kang and S. W. Kang, Sci. Rep., 2015, 5, 16362.
- 30 S. W. Kang, D. H. Lee, J. H. Park, K. Char, J. H. Kim, J. Won and Y. S. Kang, *J. Membr. Sci.*, 2008, **322**, 281–285.