# **RSC Advances**



View Article Online

View Journal | View Issue

# PAPER



Cite this: RSC Adv., 2017, 7, 34442

Received 14th May 2017 Accepted 2nd July 2017 DOI: 10.1039/c7ra05445a rsc.li/rsc-advances

## Introduction

With the development of electronic devices and electric vehicles, rechargeable lithium-ion batteries (LIBs) are playing a more and more important role in daily life because of their high energy densities and long cycle life.1 To meet people's increasing requirement of LIBs, extensive efforts have been made to search for novel anode materials with high capacity and outstanding cycle performance. Graphite is regarded as a classical anode material due to its specific layer-to-layer structure, but it is far from meeting the future need because of its low theoretical capacity of 372 mA h  $g^{-1}$ .<sup>2</sup> To address this issue, lots of studies have been carried out on Si-based materials,3 metal alloys,4 metal oxides5 and metal chalcogenides.6 As SnO<sub>2</sub> possesses the advantages of low cost and high theoretical capacity of 790 mA h g<sup>-1</sup>, SnO<sub>2</sub> based materials are deemed to be one of the most promising anode materials to LIBs.<sup>7</sup> However, SnO<sub>2</sub> suffers from the defect of huge volume change of 250% during the processes of lithiation and delithiation, leading to pulverization and rapid capacity fading in cycling.8

School of Materials and Energy, Guangdong University of Technology, Guangzhou 510006, China. E-mail: hyzhang@gdut.edu.cn; lizhengh@gdut.edu.cn

# Rapid preparation of SnO<sub>2</sub>/C nanospheres by using organotin as building blocks and their application in lithium-ion batteries<sup>†</sup>

Liuqing Li, Haiyan Zhang, 吵 \* Zhaopeng Li, Weihao Zhong, Haiyang Liao and Zhenghui Li\*

Constructing an electrode integrating ultralow SnO<sub>2</sub> size, stable carbon barriers and well-developed pore structure are effective to address the issues of crack and pulverization for SnO<sub>2</sub>-based electrode during lithiation/delithiation process. But until now, it is still a challenge to exploit simple and robust method to fabricate ultrasmall SnO<sub>2</sub> particles embedded in a carbon matrix. Herein, we develop a rapid strategy to prepare SnO<sub>2</sub>/C nanospheres using a simple Friedel–Crafts crosslinking of triphenyltin chloride for only 15 min and subsequent carbonization. The SnO<sub>2</sub>/C nanospheres (~500 nm) have ultrasmall SnO<sub>2</sub> particles of 4 nm, which were dispersed in carbon continuous phase. Moreover, the pyrolysis of the polymer during carbonization creates considerable micropores inside the carbon phase and leads to a surface area of 463.3 m<sup>2</sup> g<sup>-1</sup>. When used as electrode materials in a lithium-ion battery, the ultrasmall SnO<sub>2</sub> particles can prevent the cracking of the electrode, the carbon continuous phase can act as a buffer to protect SnO<sub>2</sub> particles from aggregation, and micropores will supply expansive space for volume change. Thus, the SnO<sub>2</sub>/C nanosphere exhibits superior electrochemical performance, e.g., the first discharge and charge capacities can reach 1453 and 719 mA h g<sup>-1</sup> respectively, and 120 cycles later, its capacity remains 629 mA h g<sup>-1</sup>, indicating a capacity retention of 87.4% ( $C^{120th}/C^{2nd}$ ).

Integrating ultralow SnO<sub>2</sub> size, stable carbon barriers and well-developed pore structure in one electrode material is an effective way to overcome crack and pulverization of SnO2-based electrode. First, it was reported that nanosized SnO2 particles can mitigate the strain generated during discharge/charge process at a certain extent.9,10 Inspired by this phenomenon, a SnO<sub>2</sub>/C nanocomposite with 4.3 nm-sized SnO<sub>2</sub> nanoparticles dispersed in carbon network was prepared by Wang's group via decomposition of Sn(OH)<sub>4</sub> in polyacrylic acid hydrogel and subsequent carbonization. This SnO<sub>2</sub>/C displayed an initial discharge capacity of 1460 mA h g<sup>-1</sup> and maintained a reversible capacity of 597.3 mA h  $g^{-1}$  at a current density of 100 mA g<sup>-1</sup> after 200 cycles.<sup>11</sup> Second, constructing stable carbon barrier has also been proved to be efficient way to improve electrochemical performance.12 For example, coreshell SnO<sub>2</sub>/C composite developed by Yang's group showed a stable capacity of 430 mA h g<sup>-1</sup> after 100 cycles.<sup>13</sup> It is believed that the carbon shell protects SnO<sub>2</sub> particles from self aggregation and cracking during lithiation/delithiation process. Besides, porous structure can serve as the transport access of lithium ions and provide expansive space to accommodate the volume change of SnO<sub>2</sub> particles, which is another frequentlyused way to enhance the rate performance and cycle stability of SnO<sub>2</sub>-based electrode. Ko and coworkers developed porous SnO<sub>2</sub>/C nanocomposite by spray pyrolysis process, and the composite exhibited a reversible capacity of 509 mA h  $g^{-1}$  after

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra05445a



Fig. 1 Schematic figure of the preparation process for  ${\rm SnO_2/C}$  nanospheres.

1000 discharge/charge cycles at a current density of 1.5 A  $g^{-1}$ .<sup>14</sup> These above-mentioned strategies have achieved great success in exploiting novel SnO<sub>2</sub>-based anode materials with high capacity and stable cycling performance. However these methods are based on inorganic Sn-containing salts with complicated preparation steps, and there are still few SnO<sub>2</sub>-based anode materials that incorporate ultralow SnO<sub>2</sub> particle size (<10 nm), carbon matrix and porous structure, simultaneously.

In this paper, we elaborate a novel, facile and rapid method of preparing SnO<sub>2</sub>/C nanosphere with ultrasmall SnO<sub>2</sub> particles simply by using a Friedel-Crafts crosslinking of triphenyltin chloride (Sn-Ph) in a short time of 15 min (Fig. 1). Crosslinking induced phase separation creates spherical crosslinked product with a diameter of ca. 600 nm, and Sn atoms are embedded in the nanospheres uniformly. During carbonization, the crosslinked polymer converts into carbon framework, meanwhile, Sn atoms aggregate in situ and result in the generation of 4 nmsized SnO<sub>2</sub> particles. In addition, pyrolyzation of polymer creates considerable micropores inside the carbon continuous phase and SnO<sub>2</sub>/C nanospheres present a surface area of 463.3 m<sup>2</sup> g<sup>-1</sup>. When the SnO<sub>2</sub>/C nanospheres are applied in lithium-ion batteries, it exhibits four advantages: (i) an average diameter of  $\sim$ 500 nm can shorten the transport distance of lithium ions, (ii) ultralow size of SnO<sub>2</sub> particles can prevent the crack of electrode, (iii) carbon matrix will act as buffer to protect SnO<sub>2</sub> particles from aggregation and mitigate the absolute strain induced by large volume change during lithiation/delithiation process, (iv) porous structure provides pathways of lithium-ion transport and supplies nanospace for volume change of SnO<sub>2</sub> particles to prevent cracking. Owning to these unique structure features, SnO<sub>2</sub>/C nanospheres present high initial discharge and charge capacities of 1453 and 719 mA h g<sup>-1</sup> respectively. 120 cycles later, the capacity remains 629 mA h  $g^{-1}$ , demonstrating a high capacity retention rate of 87.4% ( $C^{120th}/C^{2nd}$ ). Furthermore, the simple and rapid process of preparation, and low cost of raw materials make it easy to realize large-scale production while put the method into application.

## Experimental

#### Preparation of SnO<sub>2</sub>/C nanospheres

The SnO<sub>2</sub>/C nanospheres were prepared using a method of organic crosslinking. At first, 2 g triphenyltin chloride and 4 g anhydrous AlCl<sub>3</sub> were dissolved in 80 mL 1,2-dichloroethane at 60 °C for several minutes, and then 4 mL dimethoxymethane was transferred into the liquor. 15 minutes later, the product was filtered off and washed with deionized water and ethanol

for four times. After drying in vacuum at 80 °C for 8 h, crosslinked triphenyltin chloride was collected. To obtain SnO<sub>2</sub>/C nanospheres, crosslinked triphenyltin chloride was carbonized at 600 °C for 1 h with a heating rate of 2 °C min<sup>-1</sup> under the atmosphere of nitrogen.

#### Material measurements

XRD patterns were gained from a powder X-ray diffraction system (XRD, D/MAX-UItima IV, Rigaku Corporation, Japan). Thermal behavior of the composites was investigated by thermo-gravimetric analysis (TGA, Q50, TA Instruments Ltd, USA) in air from 100 to 800 °C. Micro-morphologies were observed by the scanning electron microscopy (SEM, SU8010, Hitachi, Japan) and transmission electron microscopy (TEM, JEM 2100F, Japan). Porosity test was performed on Nitrogen adsorption-desorption porosity measurement machine (ASAP 2460, Micromeritics, USA). Fourier Transform reflectioninfrared spectra were measured using a Nicolet 6700 FTIR spectroscopy (Nicolet, USA).

#### **Electrochemical characterization**

The electrochemical performances of  $SnO_2/C$  nanospheres were tested by a coin-type cell (CR 2032). Working electrode was fabricated by pasting a mixture of  $SnO_2/C$  nanosphere (84 wt%), super P (10 wt%), sodium carboxymethyl cellulose (CMC) (3 wt%) and styrene-butadiene rubber emulsion (SBR) (3 wt%) on copper foil and then dried in vacuum at 80 °C for 24 h. Coin cells were assembled in an argon-filled glove box, taking polypropylene microporous film (Celgard 2400) as separator and lithium foil as the counter electrode.

Galvanostatic charge/discharge property was measured on LAND CT 2001A batteries measuring system (CT2001A, Wuhan LAND Corporation, China) with a voltage window from 0.01 to 3.0 V at room temperature. The cyclic voltammograms (CV) data of the material was tested on electrochemical workstation (CHI660E, Shanghai Chenhua, China) at a scan rate of 0.2 mV s<sup>-1</sup> from 0.01 to 3 V.

### Results and discussion

Generally, SnO<sub>2</sub> nanoparticles were prepared by hydrolysis, condensation process of SnCl4 or SnCl2. But the hydrolysis process of SnCl<sub>4</sub>/SnCl<sub>2</sub> is hard to control because of the high reaction speed. In this paper, for the first time, we used an organic precursor, i.e., Sn-Ph, to prepare SnO<sub>2</sub>/C nanospheres. Normally, Sn-Ph boils and decomposes during heat-treatment process, which makes it hard to synthesize SnO<sub>2</sub>/C composites. To conquer this question, Friedel-Crafts reaction was adopted to immobile Sn-Ph and dimethoxymethane was chosen as the crosslinker (the obtained product was denoted as xSn-Ph).<sup>15</sup> The Friedel-Crafts crosslinking mechanism is described in Fig. S1,<sup> $\dagger$ </sup> in which methylene (-CH<sub>2</sub>-) was generated between phenyl rings of Sn-Ph owing to the replacement of hydrogen. FT-IR was measured to confirm the crosslinking (Fig. 2). The absorption peak of methylene ( $\sim 2800 \text{ cm}^{-1}$ ) appeared and the absorption peak of C-H in phenyl (~3100 cm<sup>-1</sup>) disappeared



after crosslinking, demonstrating the successful crosslinking between Sn-Ph and dimethoxymethane.

Owing to crosslinked-induced phase separation, xSn-Ph presents spherical morphology with an average diameter of 600 nm (Fig. 3a). It is not difficult to imagine that Sn atoms would be wrapped during crosslinking and dispersed in the polymer network. Judging from the TEM images, the Sn atoms are distributed in molecular scale with no aggregations (Fig. 3b and c). Accordingly, the XRD pattern of xSn-Ph shows no diffraction peaks, indication of no crystals (Fig. 4a). To obtain SnO<sub>2</sub>/C nanospheres, xSn-Ph was carbonized at 600 °C for 1 h with a heating rate of 2 °C min<sup>-1</sup> under the atmosphere of N<sub>2</sub> (denoted as SnO<sub>2</sub>/C-2-600-1). Because of rigid polymer network from highly crosslinked density, nanospherical shape was maintained integrally after carbonization (Fig. 3d). Meanwhile, owing to the pyrolyzation of polymer precursor, the diameter of SnO<sub>2</sub>/C-2-600-1 was reduced to ca. 500 nm slightly (Fig. 3d). Fig. 3e presents the TEM image of SnO<sub>2</sub>/C-2-600-1, it is unexpected that many ultrasmall SnO<sub>2</sub> particles are embedded in amorphous carbon matrix uniformly, without any big aggregations (Fig. 3f). According to the high-resolution TEM image, the diameter of such SnO<sub>2</sub> particles is ca. 4 nm, which is lower than most of current SnO<sub>2</sub> nanomaterials.<sup>16</sup> It is believed that rigid xSn-Ph network is significant for the formation of ultrasmall SnO<sub>2</sub> particles, that is, highly crosslinked framework is strong



Fig. 3 (a) SEM, (b) TEM and (c) high-resolution TEM images of xSn-Ph. (d) SEM, (e) TEM and (f) high-resolution TEM images of SnO<sub>2</sub>/C-2-600-1.



Fig. 4 (a) XRD patterns of xSn-Ph,  $SnO_2/C-2-600-1$  and commercial nano-SnO<sub>2</sub>. (b) TGA curve of  $SnO_2/C-2-600-1$ . (c) N<sub>2</sub> adsorption-desorption isotherm and (d) pore size distribution of  $SnO_2/C-2-600-1$ .

enough to keep away from melt and soften, which acts like barrier to prevent  $SnO_2$  from agglomeration.

To confirm the crystal structure of  $\text{SnO}_2/\text{C-2-600-1}$ , XRD pattern is given (Fig. 4a). The wide peaks at 26.6, 33.8 and 51.8° can be ascribed to the crystal planes (110), (101) and (211) of  $\text{SnO}_2$  (JCPDS file no. 41-1445), further confirming ultrasmall  $\text{SnO}_2$  particles embedded in carbon continues phase after carbonization. The  $\text{SnO}_2$  content was estimated by thermogravimetric analysis (TGA) under air, in which process the carbon component would burn off completely. As shown in Fig. 4b, the  $\text{SnO}_2$  percentage of  $\text{SnO}_2/\text{C-2-600-1}$  was tested to be 20%.

Pore structure of SnO<sub>2</sub> nanospheres was measured by N<sub>2</sub> adsorption method. The adsorption amount shows a rapid step at low relative pressure (Fig. 4c), demonstrating the generation of abundant of micropores owing to the pyrolysis of polymer network. Moreover, the coincidence of adsorption and desorption branches and no dramatic increase at  $P/P_o = 1.0$  certified nearly no mesopores and macropores in SnO<sub>2</sub>/C-2-600-1. According to the DFT (density functional theory) pore size distribution (Fig. 4d), the micropore size is around 0.7 nm. Due to the well-developed pore structure, the SnO<sub>2</sub>/C-2-600-1 nanospheres present a specific surface area of 463.3 m<sup>2</sup> g<sup>-1</sup>.

We further find that pyrolysis temperature, holding time and heating rate of carbonization play significant roles in determining the size and content of  $\text{SnO}_2$  in the composites. Primarily, to study the impact of temperature, *x*Sn-Ph was carbonized at 700 ( $\text{SnO}_2/\text{C-2-700-1}$ ), 800 ( $\text{SnO}_2/\text{C-2-800-1}$ ) and 900 °C ( $\text{SnO}_2/\text{C-2-900-1}$ ) for 1 h with a heating rate of 2 °C min<sup>-1</sup>. It is found that the diffraction peaks of  $\text{SnO}_2$  crystal become sharper with increasing the pyrolysis temperature, indication of a size growth of  $\text{SnO}_2$  nanoparticles (Fig. 5a). Obviously, higher pyrolysis temperature accelerates the aggregation of Sn atoms and leads to the generation of larger nanoparticles. This size growth process also can be observed in TEM images, in which  $\text{SnO}_2/\text{C-2-800-1}$  and  $\text{SnO}_2/\text{C-2-900-1}$  have larger  $\text{SnO}_2$  nanoparticles than  $\text{SnO}_2/\text{C-2-700-1}$  (Fig. 6). To

Fig. 5 (a) XRD patterns and (b) TGA curves of SnO<sub>2</sub>/C-2-700-1, SnO<sub>2</sub>/C-2-800-1 and SnO<sub>2</sub>/C-2-900-1.



Fig. 6 SEM and TEM images of (a) SnO\_2/C-2-700-1, (b) SnO\_2/C-2-800-1, (c) SnO\_2/C-2-900-1.

further confirm the results, we statisticed the average diameter of SnO<sub>2</sub> nanoparticles according to the TEM images (Fig. S5<sup>†</sup>). It can be found that SnO<sub>2</sub>/C-2-700-1 has a lowest SnO<sub>2</sub> diameter of ca. 7 nm, and SnO<sub>2</sub>/C-2-800-1 has larger SnO<sub>2</sub> nanoparticles with an average diameter of ca. 13 nm. Accordingly, when pyrolysis temperature is elevated to 900 °C, SnO<sub>2</sub>/C-2-900-1 has a highest SnO<sub>2</sub> diameter of ca. 16 nm. Unexpectedly, diffraction peaks of Sn element appear at 30.6, 32.0 and 44.9° when the pyrolysis temperature is 900 °C (JCPDS file no. 04-673), illustrating the carbothermal reduction of SnO<sub>2</sub>. Content of SnO<sub>2</sub>/Sn was measured via TGA (Fig. 5b). The contents of SnO<sub>2</sub> are around 20% when the pyrolysis temperature was varied from 600 to 800 °C. But it drops to 15.5% at 900 °C, which can be ascribed to the volatilization of Sn (melting point: 232 °C). Besides, the specific surface area rises from 463.3, 511.6, 763.9 to 966.7  $m^2 g^{-1}$  along with the increase of carbonization temperature (Fig. 4c and S2-S4<sup>†</sup>).

Furthermore, heating rate and holding time of carbonization have been studied as well. As the holding time was extended, XRD patterns of obtained samples were sharpening, *i.e.*, the SnO<sub>2</sub> size increased (Fig. S6a<sup>†</sup>). Similarly, the acceleration of the heating rate results in a distinct increase of SnO<sub>2</sub> size and faster reduction of SnO<sub>2</sub> crystal, which can be ascribed to that the aggregation of Sn atoms was intensified with the increasing of heating rate (Fig. S6b<sup>†</sup>).

The SnO<sub>2</sub>/C nanospheres have unique nanostructure integrating ultrasmall SnO<sub>2</sub> particles, continuous carbon buffer and microporous structure, which motivate us to further investigate its electrochemical performance. Fig. 7 displays the cyclic voltammogram of SnO<sub>2</sub>/C-2-600-1 electrode at a scan rate of  $0.2 \text{ mV s}^{-1}$  from 0.01 to 3 V. The peak from 0.1 to 0.6 V of the first cathodic sweep indicates the formation of solid electrolyte interphase (SEI), irreversible reduction of SnO<sub>2</sub> to Sn and formation Li<sub>x</sub>Sn alloy, associating with loss of capacity during first cycle.<sup>17</sup> In the anodic sweep, the peak at 0.6 V can be ascribed to the dealloying reaction of Li<sub>x</sub>Sn alloy to Sn, which is consistent with the curves of commercial nano-SnO<sub>2</sub> (Fig. S7†). All peaks except the first cycle are reproducible and stabile, implying superior cycling stability of the SnO<sub>2</sub>/C nanospheres electrode.

Fig. 8a shows the 1<sup>st</sup>, 2<sup>nd</sup> and 60<sup>th</sup> voltage profiles of SnO<sub>2</sub>/C-2-600-1 between 0.01 to 3 V at a current density of 200 mA g<sup>-1</sup>. In discharge curves, the slopes at 0.6 V and between 0.5 and 0 V can be associated with the reduction of SnO<sub>2</sub> to metallic Sn and formation of Li<sub>x</sub>Sn alloy. In charge curves, the platform from 0.3 to 0.8 can be associated with the delithiation of Li<sub>x</sub>Sn, which are consistent with the CV results. The first discharge and charge show specific capacities of 1453 and 719 mA h g<sup>-1</sup> respectively.



Fig. 7 Cyclic voltammograms of the initial 3 cycles scanned between 0.01 and 3 V at 0.2 mV s^{-1} of SnO\_2/C-2-600-1.



**Fig. 8** (a) Galvanostatic charge/discharge curves of  $SnO_2/C-2-600-1$  at the current density of 200 mA g<sup>-1</sup>. (b) Rate performance of  $SnO_2/C-2-600-1$ . (c) Cycling performance of  $SnO_2/C-2-600-1$ , carbon and commercial nano- $SnO_2$  at the current density of 200 mA g<sup>-1</sup>. (d) Cycling performance of  $SnO_2/C-2-600-1$  at the current density of 1 A g<sup>-1</sup>.

The capacity loss can be attributed to the formation of SEI and irreversible insertion of lithium-ion in porous carbon. Except first discharge curve, the almost overlapped initial cycle curves demonstrate good cycling stability of the composites.

SnO<sub>2</sub>/C-2-600-1 also shows remarkable rate performance. Fig. 8b illustrates the reversible capacities of SnO<sub>2</sub>/C-2-600-1 electrode testing at the current densities of 200, 500, 1000, 2000 and 5000 mA  $g^{-1}$  respectively. Thirty-six cycles of testing at different current densities later, the capacity returns to 705 mA h  $g^{-1}$  at 200 mA  $g^{-1}$ , explaining the tolerance of SnO<sub>2</sub>/C-2-600-1 at high current charge and discharge. Fig. 8c displays the cycle performance of SnO<sub>2</sub>/C-2-600-1 at the current density of 200 mA g<sup>-1</sup> between 0.01 and 3.0 V. For comparison, naked nano-SnO<sub>2</sub> and pure carbon were chosen as control samples (Fig. S8<sup>†</sup>). It can be observed that commercial nano-SnO<sub>2</sub> shows high discharge and charge capacities of 1239 and 809 mA h  $g^{-1}$ respectively, but its capacity decreases seriously to 47 mA h  $g^{-1}$ after 120 cycles. Carbon exhibits a stable capacity of 213 mA h  $g^{-1}$ near to the theoretical capacity of graphite (372 mA h  $g^{-1}$ ). On contrast, SnO<sub>2</sub>/C-2-600-1 presents a high and stable capacity of 629 mA h  $g^{-1}$  for 120 cycles later, which is 3 and 13 times of the capacity of carbon and commercial nano-SnO<sub>2</sub>, respectively. Accordingly, capacity retention of SnO<sub>2</sub>/C-2-600-1 is as high as 87.4% ( $C^{120th}/C^{2nd}$ ), which is much higher than that of SnO<sub>2</sub> (5%). As shown in Fig. 8d, SnO<sub>2</sub>/C-2-600-1 composite presents a capacity of 360 mA h g<sup>-1</sup> even after 1000 cycles at the current density of 1 A  $g^{-1}$ , implying an outstanding long-term cycling capability. This result is also superior to many SnO<sub>2</sub>/C composites reported previously,10,11,18 and comparable to SnO2/CNT19 and SnO<sub>2</sub>/graphene nanocomposite (Table S1<sup>+</sup>).<sup>20</sup> Moreover, SnO<sub>2</sub>/C composites pyrolysized at 700 (SnO2/C-2-700-1) and 800 °C  $(SnO_2/C-2-800-1)$  with a heating rate of 2 °C min<sup>-1</sup> are studied for electrochemical testing (Fig. S9<sup>†</sup>), in order to confirm the structural advantages of ultrasmall SnO2 particles. It can be observed that the capacities of SnO<sub>2</sub>/C-2-700-1 and SnO<sub>2</sub>/C-2-800-1 decline at first 30 cycles followed by stable plateaus. After cycling for 120 times, SnO<sub>2</sub>/C-2-700-1 remains a stable capacity of 448.1 mA h  $g^{-1}$ , which is inferior to that of SnO<sub>2</sub>/C-2-600-1. In addition, SnO<sub>2</sub>/C-2-800-1 with largest SnO<sub>2</sub> nanoparticle has lower stable capacity of 379.4 mA h  $g^{-1}$ . Due to the rising of holding temperature, Sn atoms form bigger SnO2 particles, leading rapider capacity fading during the cycling process.

The superior performance of  $SnO_2/C$  nanosphere should be attributed to three aspects: (i) ultrasmall  $SnO_2$  nanoparticle dispersed in porous carbon could reduce aggregation and strain caused by volume change during discharge/charge process, (ii) porous carbon structure would provide nanospace to mitigate the volume change of  $SnO_2$  nanoparticles to prevent cracking and pulverization, (iii) micropores could enlarge the accessible surface area to electrolyte and favor the diffusion of lithium ions.

# Conclusion

In conclusion,  $SnO_2/C$  nanospheres with ultrasmall  $SnO_2$  particles have been prepared by facile and rapid Friedel–Crafts crosslinking. Benefiting from the ultralow size of  $SnO_2$ 

nanoparticles (~4 nm) and porous carbon buffer, the asprepared sample presents a superior electrochemical performance, including high first discharge and charge capacity of 1453 and 719 mA h g<sup>-1</sup> respectively, and high capacity remaining of 629 mA h g<sup>-1</sup> after 120 cycles at the current density of 200 mA g<sup>-1</sup>. What's more, rapid synthesis and low cost make this method easier to be put into application and realize large scale production.

# Acknowledgements

This work is supported by National Natural Science Foundation of China (U1401246, 51502042), Science and Technology Program of Guangdong Province of China (2014B010106005, 2015B010135011), the Science and Technology Program of Guangzhou City of China (201508030018) and Postdoctoral Science Foundation of China (2015M572278, 2016T90770).

# References

- (a) M. Armand and J.-M. Tarascon, *Nature*, 2008, **451**, 652–657; (b) S. Xin, Y.-G. Guo and L.-J. Wan, *Acc. Chem. Res.*, 2012, **45**, 1759–1769; (c) L. Zou, L. Gan, F. Kang, M. Wang, W. Shen and Z. Huang, *J. Power Sources*, 2010, **195**, 1216–1220; (d) Z. Li, Z. Li, W. Zhong, C. Li, L. Li and H. Zhang, *Chem. Eng. J.*, 2017, **319**, 1–8.
- 2 (a) G. Li, H. Yang, F. Li, J. Du, W. Shi and P. Cheng, *J. Mater. Chem. A*, 2016, 4, 9593–9599; (b) J. R. Dahn, T. Zheng, Y. Liu and J. Xue, *Science*, 1995, 270, 590; (c) M.-H. Park, M. G. Kim, J. Joo, K. Kim, J. Kim, S. Ahn, Y. Cui and J. Cho, *Nano Lett.*, 2009, 9, 3844–3847.
- 3 (a) H. Zhang, X. Qin, J. Wang, Y. He, H. Du, B. Li and F. Kang, J. Mater. Chem. A, 2015, 3, 7112–7120; (b) Z. Luo, Q. Xiao,
  G. Lei, Z. Li and C. Tang, Carbon, 2016, 98, 373–380; (c)
  M. A. Rahman, G. Song, A. I. Bhatt, Y. C. Wong and
  C. Wen, Adv. Funct. Mater., 2016, 26, 647–678; (d) J. Wang,
  T. Xu, X. Huang, H. Li and T. Ma, RSC Adv., 2016, 6, 87778–87790.
- 4 (a) F. F. Cao, S. Xin, Y. G. Guo and L. J. Wan, *Phys. Chem. Chem. Phys.*, 2011, 13, 2014–2020; (b) G. Ferrara, C. Arbizzani, L. Damen, M. Guidotti, M. Lazzari, F. G. Vergottini, R. Inguanta, S. Piazza, C. Sunseri and M. Mastragostino, *J. Power Sources*, 2012, 211, 103–107; (c) Y. Li, L. Huang, P. Zhang, X. Ren and L. Deng, *Nanoscale Res. Lett.*, 2015, 10, 414; (d) I. Tetsu, O. Shinya, K. Tomoya, K. Yu, O. Fumiyasu, Y. Shunsuke, G. Natsumi, D. Takayuki and M. Eiichiro, *J. Mater. Chem. A*, 2015, 3, 10188–10194.
- 5 (a) C. D. Gu, Y. J. Mai, J. P. Zhou, Y. H. You and J. P. Tu, J. Power Sources, 2012, 214, 200-207; (b) F. Cao, X. Wu, S. Xin, Y. Guo and L. Wang, J. Phys. Chem. C, 2010, 114, 10308-10313; (c) Z. Yang, G. Du, Q. Meng, Z. Guo, X. Yu, Z. Chen, T. Guo and R. Zeng, J. Mater. Chem., 2012, 22, 5848; (d) C. D. Gu, Y. J. Mai, J. P. Zhou and J. P. Tu, Funct. Mater. Lett., 2011, 4, 377.
- 6 (a) C. Zhang, H. B. Wu, Z. Guo and X. W. Lou, *Electrochem. Commun.*, 2012, 20, 7–10; (b) S. Yu, J. W. Jung and I. D. Kim, *Nanoscale*, 2015, 7, 11945–11950; (c) D. H. Youn,

C. Jo, J. Y. Kim, J. Lee and J. S. Lee, *J. Power Sources*, 2015, **295**, 228–234; (*d*) Y. Han, Y. Wang, W. Gao, Y. Wang, L. Jiao, H. Yuan and S. Liu, *Powder Technol.*, 2011, **212**, 64–68.

- 7 (a) F. Li, J. Du, H. Yang, W. Shi and P. Cheng, *RSC Adv.*, 2017,
  7, 20062–20067; (b) C. Gu, H. Zhang, X. Wang and J. Tu, *Mater. Res. Bull.*, 2013, 48, 4112–4117.
- 8 (a) J. M. Tarascon and M. Armand, *Nature*, 2001, 414, 359–367; (b) D. Larcher, S. Beattie, M. Morcrette, K. Edström, J.-C. Jumas and J.-M. Tarascon, *J. Mater. Chem.*, 2007, 17, 3759.
- 9 (a) F. M. Courtel, E. A. Baranova, Y. Abu-Lebdeh and I. J. Davidson, J. Power Sources, 2010, 195, 2355-2361; (b) M. Gao, X. Chen, H. Pan, L. Xiang, F. Wu and Y. Liu, *Electrochim. Acta*, 2010, 55, 9067-9074; (c) Q. Tian, Y. Tian, Z. Zhang, L. Yang and S.-i. Hirano, J. Power Sources, 2014, 269, 479-485.
- 10 H. Xue, J. Zhao, J. Tang, H. Gong, P. He, H. Zhou, Y. Yamauchi and J. He, *Chem.-Eur. J.*, 2016, **22**, 4915–4923.
- 11 F. Wang, H. Jiao, E. He, S. Yang, Y. Chen, M. Zhao and X. Song, *J. Power Sources*, 2016, **326**, 78–83.
- 12 (a) X. W. Guo, X. P. Fang, Y. Sun, L. Y. Shen, Z. X. Wang and L. Q. Chen, *J. Power Sources*, 2013, 226, 75–81; (b) X. W. Lou, C. M. Li and L. A. Archer, *Adv. Mater.*, 2009, 21, 2536–2539; (c) R. S. Kalubarme, J. Y. Lee and C. J. Park, *ACS Appl. Mater. Interfaces*, 2015, 7, 17226–17237; (d) X. Li, Y. Zhang, H. Zhang, Y. Feng and Y. Wang, *Electrochim. Acta*, 2016, 195, 208–215.

- 13 R. Yang, W. Zhao, J. Zheng, X. Z. Zhang and X. G. Li, *J. Phys. Chem. C*, 2010, **114**, 20272–20276.
- 14 Y. N. Ko, S. B. Park and Y. C. Kang, *Small*, 2014, **10**, 3240–3245.
- 15 (a) Z. Li, D. Wu, Y. Liang, R. Fu and K. Matyjaszewski, J. Am. Chem. Soc., 2014, 136, 4805–4808; (b) Z. Li, L. Li, Z. Li, H. Liao and H. Zhang, Electrochim. Acta, 2016, 222, 990–998.
- 16 (a) H.-Q. Wang, G.-H. Yang, Y.-G. Huang, X.-H. Zhang, Z.-X. Yan and Q.-Y. Li, *Mater. Chem. Phys.*, 2015, 167, 303–308; (b) L. Xia, S. Wang, G. Liu, L. Ding, D. Li, H. Wang and S. Qiao, *Small*, 2016, 12, 853–859.
- 17 (a) J. S. Cho, H. S. Ju and Y. C. Kang, *Sci. Rep.*, 2016, 6, 23915;
  (b) L. Zhang, K. Zhao, W. Xu, Y. Dong, R. Xia, F. Liu, L. He,
  Q. Wei, M. Yan and L. Mai, *Phys. Chem. Chem. Phys.*, 2015,
  17, 7619–7623; (c) R. Liu, D. Li, C. Wang, N. Li, Q. Li,
  X. Lü, J. S. Spendelow and G. Wu, *Nano Energy*, 2014, 6,
  73–81.
- 18 (a) M. Ara, V. R. Chitturi, S. O. Salley and K. Y. S. Ng, *Electrochim. Acta*, 2015, 161, 269–278; (b) M. Wang, S. Li, Y. Zhang and J. Huang, *Chem*, 2015, 21, 16195–16202.
- 19 G. Du, C. Zhong, P. Zhang, Z. Guo, Z. Chen and H. Liu, *Electrochim. Acta*, 2010, 55, 2582–2586.
- 20 (a) X. Li, X. Zhang, Y. Zhao, D. Feng, Z. Su and Y. Zhang, *Electrochim. Acta*, 2016, **191**, 215–222; (b) C. Zhang, X. Peng, Z. Guo, C. Cai, Z. Chen, D. Wexler, S. Li and H. Liu, *Carbon*, 2012, **50**, 1897–1903.