# RSC Advances



# PAPER

Cite this: RSC Adv., 2017, 7, 37508

Received 20th May 2017 Accepted 23rd July 2017 DOI: 10.1039/c7ra05692c

rsc.li/rsc-advances

# 1. Introduction

As the major ingredient of natural gas,  $CH<sub>4</sub>$  is widely employed as a clean fuel and is also a common carbon source for chemical production. In view of its effect on improving the living quality of human beings, the discharge of CH<sub>4</sub> has been considered to be negligible for a long time, which results in an ever-increasing  $CH<sub>4</sub>$  concentration in the atmosphere.<sup>1,2</sup> Recently, with the increasing concern surrounding atmospheric contamination and global warming, the negative effects of  $CH<sub>4</sub>$  emission receive more and more attention.<sup>3,4</sup> According to a report of the

# Efficient photocatalytic oxidation of methane over  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>/activated carbon composites†

Jianping Wei,<sup>a</sup> Juan Yang,\*ab Zhihui Wen,<sup>ab</sup> Jun Dai,<sup>ab</sup> Yao Li<sup>ab</sup> and Banghao Yao<sup>a</sup>

Efficient oxidation of methane over heterogeneous catalysts under ambient conditions is still a challengeable study toward C1 utilization and atmospheric cleansing. In this study, by using a hydrolysis method combined with an impregnation process,  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> nanoparticles supported uniformly on activated carbon (AC) can be obtained readily. The as-prepared  $Ga_2O_3/AC$  composites show efficient performance for photocatalytic oxidation of  $CH<sub>4</sub>$  under ultraviolet irradiation. The experimental results indicate that photocatalytic activity toward CH<sub>4</sub> oxidation is strongly dependent on the weight ratio of  $Ga_2O_3$  to AC. 15%- $Ga_2O_3$ /AC exhibits the highest catalytic activity, which is more than sixfold of P25, a benchmark photocatalyst. The photoluminescence spectra show the decreased recombination centers and the diminished recombination of photo-generated electrons ( $e^-$ ) and holes  $(h<sup>+</sup>)$  when Ga<sub>2</sub>O<sub>3</sub> nanoparticles were deposited on AC. Further investigation reveals that the excellent photo-oxidation activity for CH<sub>4</sub> over Ga<sub>2</sub>O<sub>3</sub>/AC can be ascribed to a synergistic effect involving strong adsorption capacity and improved separation of photo-generated  $e^-/h^+$  pairs. Moreover, the photocatalytic oxidation of CH<sub>4</sub> obeys pseudo-first-order kinetics and the cycling experiment indicates that Ga<sub>2</sub>O<sub>3</sub>/AC composites possess stable photocatalytic performance for CH<sub>4</sub> oxidation. The underlying photo-oxidation mechanism is also investigated using electron paramagnetic resonance (ESR) and radical scavenging experiments. This study demonstrates that photocatalysis with  $Ga_2O_3/AC$  is a highly efficient method toward the oxidation of low concentrations of  $CH<sub>a</sub>$ , which provides valuable information for atmospheric environmental cleansing. **PAPER**<br> **Example the Construction of the Columbial Constrained C** 

Intergovernmental Panel on Climate Change,  $CH<sub>4</sub>$  is responsible for about twenty percent of man-made global warming and the greenhouse gas effect of  $CH<sub>4</sub>$  is nearly 28 times greater than that of an equivalent mass of  $CO_2$ .<sup>5</sup> More seriously, coal-bed gas or shale gas exploitation results in the increase of  $CH<sub>4</sub>$  release into the atmosphere. Therefore, the conversion of atmospheric methane into equimolar amounts of carbon dioxide is extremely important for retarding global warming.

Due to the high energy of C-H bond  $(434 \text{ kJ mol}^{-1})$  and nonpolar characteristics of  $CH_4$  molecule, oxidation of  $CH_4$  has been mainly studied via thermal catalysis with noble metal and transition-metal oxide catalysts in the past decades.<sup>6,7</sup> However, the high reaction temperature  $(\sim 673 \text{ K})$  and inefficiency in oxidizing low concentration of  $CH<sub>4</sub>$  are the defects of conventional thermo-catalysis. Although the microorganism treatments using methane oxidative bacteria could decompose CH<sub>4</sub>,<sup>8,9</sup> it has been proved to be inefficient for the practical application because this approach is time consuming and difficult to control. Wei and his co-workers have recently reported the oxidation of  $CH_4$  with hydroxyl radicals ('OH) generated via Fenton reagent.<sup>10</sup> The results demonstrate that 'OH derived from Fenton reagent can drive the oxidation of  $CH<sub>4</sub>$ under a certain reaction condition. However, the homogeneous Fenton systems have some limitations because  $Fe^{2+}$  and  $H_2O_2$ 

<sup>&</sup>quot;State Key Laboratory Cultivation Base for Gas Geology and Gas Control, The Collaborative Innovation Center of Coal Safety Production of Henan, School of Safety Science and Engineering, Henan Polytechnic University, Jiaozuo, 454000, P. R. China. E-mail: yangjuanhpu@163.com

b Institute of Chemical Safety, School of Safety Science and Engineering, Department of Applied Chemistry, College of Chemistry and Chemical Engineering, Henan Polytechnic University, Jiaozuo, 454000, P. R. China

<sup>†</sup> Electronic supplementary information (ESI) available: The schematic diagram of photocatalytic experimental apparatus; SEM image of bare  $Ga_2O_3$ nanoparticles; the effect of light intensity on the photocatalytic oxidation of  $CH_4$ ; XRD pattern and SEM image of as-prepared 15%-TiO<sub>2</sub>/AC composite; the amount of produced  $CO<sub>2</sub>$  during the photocatalytic oxidation of  $CH<sub>4</sub>$ ; the comparison of XRD patterns and XPS spectra between freshly prepared and recycled 15%-Ga<sub>2</sub>O<sub>3</sub>/AC photocatalyst. See DOI: 10.1039/c7ra05692c

cannot be separated from the reaction system and reused for the next cycle. Additionally, iron ions are easy to precipitate under an alkaline condition, which restricts the  $CH<sub>4</sub>$  removal with Fenton reagent can be only performed in a narrow pH range.

Heterogeneous photocatalysis is regarded as an ideal technology for solving the urgent energy and environmental issues,<sup>11</sup>–<sup>13</sup> especially in removing various gaseous pollutants at ambient pressure and temperature.<sup>14,15</sup> Previous studies have also indicated CH4 molecules can be activated and subsequently oxidized via TiO<sub>2</sub> photocatalytic technology,<sup>16,17</sup> however, the efficiency of  $CH_4$  photo-oxidation remains notoriously low. Adsorption and photoreaction are two successively key steps, which are generally interactional during the heterogeneous photocatalytic process. Surface adsorption and the diffusion of reactants to active sites are the preconditions of photocatalytic reactions. Strong adsorption of target reactants facilitates the catalytic reaction between the adsorbed reactant and surface active species. As a result, the efforts toward improving the adsorption of reactants in photocatalytic system have been made through constructing porous materials<sup>18,19</sup> or adsorbent-loaded composites.<sup>20,21</sup> Fabricating of the composites with adsorptive support and traditional photocatalyst is considered as an effective approach to obtain the adsorptionenhanced photocatalyst. Adsorbent-loaded photocatalysts usually possess excellent synergistic effect because of the continuous transfer of adsorbed reactants to the supported photocatalytic active sites. Meanwhile, the prolonged retentiontime of intermediates on the composite catalyst facilitates improving the mineralization of pollutants. Paper We we can compute the matches are enoy of prediction and the methods are enoy of prediction and the common article is method and the common are enoy of the methods are are enoy of the methods are are enormal proposa

Carbon materials, such as graphene oxides  $(GO)$ ,<sup>22</sup> carbon nanotube  $(CNT)^{23,24}$  and activated carbon  $(AC)^{25}$  have been extensively used as one kind of excellent supports for semiconductor-based photocatalyst nanoparticles, which can efficiently improve the distribution of active components, the electron-transfer from semiconductor particles to carbon supports, and the stability of catalysts. Furthermore, in the field of CH4 adsorption and storage, porous carbon materials have also received wide attention due to their outstanding adsorption capacity.26,27 Among these carbon-based supports, AC is commonly used owing to its unique advantages, including abundant microporous structure, high adsorption capacity, low production cost, and facile recycling.

 $\beta$ -Gallium oxide (β-Ga<sub>2</sub>O<sub>3</sub>) has wider band-gap energy (4.8 eV) than classic photocatalyst TiO<sub>2</sub> (3.2 eV). The reported valence-band potential ( $-7.75$  eV) of  $Ga<sub>2</sub>O<sub>3</sub>$  is lower than that  $(-7.41$  eV) of TiO<sub>2</sub> (relative to the vacuum energy level) and the conduction-band potential (-2.95 eV) of  $Ga_2O_3$  is higher than that  $(-4.21 \text{ eV})$  of TiO<sub>2</sub>.<sup>28,29</sup> In consequence, the photo-holes and photo-electrons generated upon the surface of  $Ga<sub>2</sub>O<sub>3</sub>$  possess stronger redox capacity than those formed over  $TiO<sub>2</sub>$ . This contributes to the oxidation of persistent organic pollutants and the mineralization of stable intermediates upon the surface of  $Ga_2O_3$ .<sup>29</sup> In addition,  $Ga_2O_3$  is also an environmental friendly material according to Worksafe Australia criteria. Fu and his colleagues have reported the photocatalytic degradation of volatile organic contaminants (e.g. benzene and

methylbenzene) over  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> nanoparticles under ambient conditions and found that the photocatalytic activity of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> particles was much superior to commercial P25.<sup>28,29</sup> Porous  $\beta$ - $Ga<sub>2</sub>O<sub>3</sub>$  was highly photoactive for mineralizing benzene to  $CO<sub>2</sub>$ and no obvious deactivation was observed during the prolonged irradiation about 80 h.<sup>28</sup> The high activity and long-term stability of  $Ga<sub>2</sub>O<sub>3</sub>$  could be primarily ascribed to its wider band gap energy and the resulting stronger oxidative capacity.

In this study, activated carbon (AC) supported  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> composites (Ga<sub>2</sub>O<sub>3</sub>/AC) were prepared via an in situ synthetic method, including facile hydrolysis and impregnation process. The structure and physical–chemical properties of as-prepared  $Ga_2O_3/AC$  were characterized by using various analysis techniques.  $Ga_2O_3/AC$  composites demonstrate excellent photocatalytic activity for methane oxidation under ultraviolet irradiation.  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> is chosen because it is an environmental friendly semiconductor with wide band-gap satisfying the requirement of strong oxidation capability. AC facilitates the adsorption of  $CH<sub>4</sub>$  molecules and the uniform distribution of  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles. The effects of  $Ga<sub>2</sub>O<sub>3</sub>$  weight ratios, irradiation intensity, and initial  $CH<sub>4</sub>$  concentration on the photocatalytic oxidation efficiency were studied systematically. The results of dark-adsorption experiments and PL spectra indicate that the superior photocatalytic activity of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites can be ascribed to a synergistic effect involving strong adsorption capacity and improved separation of photo-generated  $e^-/h^+$ pairs. Besides, the photocatalytic oxidation of  $CH_4$  over  $Ga_2O_3/$ AC obeys pseudo-first-order kinetics. The underlying photooxidation mechanism is also investigated using electron paramagnetic resonance (ESR) and radicals scavenging experiments. The present work provides theoretical support and green approach to CH<sub>4</sub> oxidation and atmospheric environmental cleansing.

# 2. Experimental section

### 2.1 Materials and agents

Gallium nitrate hydrate was purchased from Strem Chemicals. Anhydrous ethanol, tetrabutyl orthotitanate, acetic acid and ammonia solution were obtained from Aladdin Industrial Inc. (Shanghai, P.R. China). The standard gas of  $N_2$ , CH<sub>4</sub> and O<sub>2</sub> (purity > 99.99%) were obtained from Jinggao Gas Inc. (Beijing, P.R. China). All chemicals from commercial sources were used without further purification except AC (AP4-60, purchased by Suzhou Calgon Carbon Inc.).

### 2.2 Preparation of photocatalyst

The commercial AC was firstly grinded and filtrated using a 60 mesh filter. The obtained AC particles were treated successively with 10% NaOH solution and 10%  $HNO<sub>3</sub>$  solution. The products were collected, washed with deionized (DI) water several times and dried at 70 $\degree$ C.

Ga<sub>2</sub>O<sub>3</sub>/AC composite photocatalysts were fabricated using hydrolysis method combined with impregnation process. In a typical synthesis, 2 g of treated AC was dispersed into 30 mL DI water, followed by vigorous stirring 30 min to obtain a uniform suspension. 1.0 g of gallium nitrate hydrate was dissolved in 20 mL of anhydrous ethanol to form a homogenous solution, which was added dropwise into the above suspension under magnetic stir. After 1 h, the mixed solution of ethanol and ammonia solution (volume ratio  $1:1$ ) was added slowly into the obtained suspension, which kept continuous stirring for 3 h at room temperature.<sup>28</sup> The resulting precipitate was centrifuged, washed with DI water, dried at 80 $\degree$ C and calcinated at 600 °C for 2 h to prepare  $Ga<sub>2</sub>O<sub>3</sub>/AC$ . For simplicity, it is assumed that all of gallium nitrate hydrate was converted to  $Ga_2O_3$ . By changing the amount of gallium nitrate,  $Ga_2O_3/AC$ composites with different weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$  were obtained and labeled as  $x$ -Ga<sub>2</sub>O<sub>3</sub>/AC, which x represents the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  in the as-prepared composites. According to the abovementioned way, a series of  $Ga_2O_3/AC$  composites with  $Ga_2O_3$ weight ratio of 5%, 10%, 15%, 20% and 25% were prepared and denoted as  $5\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC,  $10\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC,  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC,  $20\%$ - $Ga_2O_3/AC$  and 25%- $Ga_2O_3/AC$ , respectively.

For comparison,  $TiO<sub>2</sub>/AC$  nanocomposite sample was also synthesized via in situ compositing process according to the recent report.<sup>30</sup> Briefly, a certain amount of treated AC was dispersed into 30 mL DI water, which was stirred for 30 min to ensure the thorough dispersion of AC. Then, 2 mL of tetrabutyl titanate (TBOT) was mixed with 10 mL anhydrous alcohol and added dropwise to the above suspension of AC with magnetic stirring. After stirring for 3 h, the suspension was treated under microwave irradiation at 700 W for 15 min. The precipitates thus obtained were centrifuged, washed with DI water, and dried at 80 °C in an electric oven to prepare TiO<sub>2</sub>/AC.

#### 2.3 Characterization of photocatalyst

The crystalline structure of as-synthesized  $Ga_2O_3/AC$  was identified by X-ray diffraction (XRD) on a Bruker D8 Advance diffractometer with Cu K $\alpha$  radiation ( $\lambda = 0.15405$  nm) in the region  $2\theta = 5-80^\circ$ . The morphology of composites was observed with a scanning electron microscope (SEM, Hitachi, SU8010). Transmission electron microscopy (TEM) imaging was performed on a FEI Tecnai G2 microscope at an accelerating voltage of 200 kV. The X-ray photoelectron spectroscopy measurements were performed on a Thermo scientific ECALAB 250xi system with Mg Ka source. The binding energies were calibrated using that of C 1s (284.6 eV). Nitrogen adsorption and desorption measurements were performed at 77 K using Micromeritics ASAP2020 equipment. The samples were degassed at 200 °C before measurements. Photoluminescence spectra (PLs) of the composite catalysts were recorded using a FLsp 920 luminescence spectrophotometer (Edinburgh) at room temperature with an excitation wavelength of 220 nm. Electron spin resonance (ESR) signals were obtained by using a Bruker ER200-SRC spectrometer at ambient temperature with a Philip lamp of 254 nm as light source. 50  $\mu$ L of sample solutions were put into quartz capillary tubes and sealed. The capillary tubes were inserted in the ESR cavity, and the spectra were recorded during the irradiation at a selected time. All the ESR measurements were performed using the following settings: 20 mW microwave power, 100 G scan range and 1 G field modulation.

#### 2.4 Photocatalytic oxidation of CH<sub>4</sub>

Photocatalytic oxidation of  $CH<sub>4</sub>$  was implemented with a homemade fixed bed tubular quartz reactor of 500 mL capacity. The schematic diagram of photocatalytic experimental apparatus was shown in Fig. S1 (see, ESI†). All of the photocatalytic experiments were carried out at ambient temperature and pressure unless indicated otherwise. Firstly, 200 mg of composite catalyst was added to 10 mL of  $H<sub>2</sub>O$  and ultrasonicated for 20 min. The aqueous suspension was then coated uniformly on the surface of five glass sheets (each glass sheet is 2 cm  $\times$  8 cm), followed by drying at 60 °C until the water was completely removed. The as-obtained supported catalysts were horizontally put into the middle of the tubular reactor. Then, the reactor was vacuumed repeatedly to remove  $H_2O$  and  $CO_2$ that adsorbed on the surface of catalysts and reactor inner-wall.  $CH<sub>4</sub>, O<sub>2</sub>$ , and N<sub>2</sub> were mixed at a certain percentage via a gas mixer. The obtained gaseous mixture was used to afford a reactant stream. The initial concentration of  $CH<sub>4</sub>$  in the stream was 1.56 mmol  $L^{-1}$ . Before the irradiation, the reaction system was kept in the dark for 2 h to ensure an adsorption– desorption equilibrium state established between photocatalysts and reactants. Then, the photocatalysts were irradiated using a 10 W Philips low-pressure mercury lamp (with a wavelength centered at 254 nm) located in the middle of the quartz reactor. At a given time interval, 1.0 mL gas was collected from the reactor and analyzed using a Thermo gas chromatograph (GC) with a molecular sieve  $13 \times$  column and a HP-Plot/U capillary column equipped with a thermal conductivity detector and a flame ionization detector. The experimental temperature was maintained at 25  $\pm$  1 °C by recirculating a cooling water system. For comparison, the photocatalytic activity of  $15\%$ -TiO<sub>2</sub>/AC was also investigated under the same experimental conditions, as those used for  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC. BSC Advances<br>
a uniform suspension, they cylindric include by the plane is the plane is the component on 31 AM. This are the common access the common access Article in the mass are the common access are the common access

In general, photocatalytic activity is determined by the formation of radical species, such as photo-holes  $(h<sup>+</sup>)$ , electrons (e<sup>-</sup>), superoxide (O<sub>2</sub><sup>--</sup>), and 'OH. Comparative investigations of the effect of active species on the photocatalytic activity were conducted by using scavenger reagents to remove the different radicals. Potassium iodide (KI), potassium dichromate  $(K_2Cr_2O_7)$ , tert-butyl alcohol (TBA), and benzoquinone were employed as scavengers for  $h^+$ ,  $e^-$ ,  $O_2$ <sup>--</sup>, and 'OH, respectively. Typically, 200 mg of photocatalyst was mixed with 1 mM of the different trapping reagents in 10 mL of water and ultrasonicated for 20 min. Then, the aqueous suspensions were coated onto the glass sheets followed by drying at 60  $\degree$ C until H<sub>2</sub>O was completely removed. The coated sheets were used in the photocatalytic experiments of  $CH<sub>4</sub>$  oxidation as described above.

## 3. Results and discussion

### 3.1 Characterization of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>/AC composites

The crystallographic structure of as-synthesized  $Ga_2O_3/AC$ composites was investigated by XRD and the results were indicated in Fig. 1, as well as with the XRD patterns of bare  $Ga<sub>2</sub>O<sub>3</sub>$ and AC shown for comparison. As can be seen from Fig. 1A, the XRD pattern of AC showed two weak broad peaks at about 24.7



Fig. 1 (A) XRD patterns of bare AC,  $Ga_2O_3$  and  $15\%$ - $Ga_2O_3/AC$ , (B) XRD patterns of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites with different weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$ 

and  $43.8^\circ$ , indicating that AC possessed a mainly amorphous structure. A sharp peak at  $26.7^\circ$  assigned to  $(002)$  crystallographic plane of hexagonal graphitic structure was also observed,<sup>31</sup> which could be due to small regions of crystallinity in the commercially-obtained AC substrate. Bare  $Ga<sub>2</sub>O<sub>3</sub>$ prepared by the hydrolysis of  $Ga(NO<sub>3</sub>)<sub>3</sub>$  in ammonium solution exhibited the characteristic peaks at  $2\theta$  values of  $31.7^{\circ}$ ,  $35.4^{\circ}$ , 43.5 $^{\circ}$  and 64.5 $^{\circ}$ , which can be indexed as (002), (111), (311) and (512) planes of monoclinic  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> (JCPDS no. 76-0573).<sup>32</sup> It suggests that the as-prepared  $Ga<sub>2</sub>O<sub>3</sub>$  was predominantly nanosized  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> after the hydrolysis product was calcined at 600 °C for 2 h. This result is well consistent with the previous research.<sup>28</sup> Among the four polymorphs of  $Ga<sub>2</sub>O<sub>3</sub>$  reported in the field of catalysis,  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> is the most stable on thermodynamics and all the other polymorphs can be ultimately transformed into  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> by calcination.<sup>33</sup> As indicated in Fig. 1B, except the characteristic peaks at 24.7°, 26.7° and 43.8° belonging to amorphous AC, the diffraction peaks at about  $31.7^{\circ}$ ,  $35.4^{\circ}$  and 64.5° corresponding to  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> were also observed, which indicated that  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites were successfully fabricated via the present experimental method. Additionally, it was obvious that the diffraction peak intensity of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> increased with increasing the amount of  $Ga<sub>2</sub>O<sub>3</sub>$  loaded on AC support.

To investigate the morphology of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites and the distribution of  $Ga<sub>2</sub>O<sub>3</sub>$  particles on the surface of AC, SEM

imaging was carried out and the results were presented in Fig. 2. Fig. 2a showed that AC had a clean and porous surface, which was usually employed as the support owing to its huge specific surface. When the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  was low (e.g. 5.0%- $Ga<sub>2</sub>O<sub>3</sub>/AC$ , nano- $Ga<sub>2</sub>O<sub>3</sub>$  particles were primarily dispersed on the meso-pore or macro-pore mouths of AC support, as indicated in Fig. 2b. With the increase of  $Ga<sub>2</sub>O<sub>3</sub>$  weight ratios, spherical  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles occupied both the pore mouths and the outer surface of AC, as observed from Fig. 2c and d. This is similar to the previously reported  $TiO<sub>2</sub>/AC$  composites.<sup>34</sup> Additionally, it was clearly seen from Fig. S2 of ESI† that bare  $Ga<sub>2</sub>O<sub>3</sub>$  was composed of nanoparticles with an average size of 6-15 nm, whereas the obvious aggregation could be noted for bare  $Ga<sub>2</sub>O<sub>3</sub>$  particles. By comparing SEM images of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  and bare  $Ga<sub>2</sub>O<sub>3</sub>$ , it can be easily found that the loading on AC facilitates the uniform distribution of  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles.

To further investigate the microstructure of  $Ga_2O_3/AC$ composites, the TEM images were provided and shown in Fig. 3. It is clearly indicated that  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles (black dots) with nanosized dimension were uniformly deposited on the surface of AC (gray region), and the large scale agglomerate was not detected in  $5.0\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC and  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC composites (Fig. 3a and b). A high-resolution TEM image of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC was shown in Fig. 3d. The lattice fringes of  $d = 0.282$  nm and  $d = 0.255$  nm matched those of (002) and (111) crystallographic planes of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>, respectively.<sup>35</sup> The intimate contact of activated carbon with  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> lattice was also evidenced from the HRTEM image. However, when the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$ increased up to 25%, the as-formed  $Ga<sub>2</sub>O<sub>3</sub>$  particles were inclined to agglomerate (Fig. 3c). It indicates that the  $Ga<sub>2</sub>O<sub>3</sub>$ nanoparticles are easier to agglomerate on the surface of  $Ga<sub>2</sub>O<sub>3</sub>$ AC composites with increasing  $Ga<sub>2</sub>O<sub>3</sub>$  weight ratios. It is well known that the catalytic activities of nanocomposite photocatalysts strongly depend on the distribution of active components on the surface of support. Compared with  $Ga<sub>2</sub>O<sub>3</sub>$  particles deposited homogeneously on the surface of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, the agglomerated  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles in 25%- $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites may hamper the light incidence on the photoreactive sites and consequently reduce the photocatalytic oxidation efficiency.

The chemical components and surface chemical states of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites were confirmed using XPS, and the results were presented in Fig. 4. The typical XPS survey spectrum with energy ranging from 0 to 1200 eV obtained from 15%-  $Ga<sub>2</sub>O<sub>3</sub>/AC$  was shown in Fig. 4a, which reveal the peaks of the core level from Ga 2p, Ga 3d, Ga LMM Auger peak, C 1s and O 1s. The energy peaks positioned at 1149.2 and 1121.5 eV in Fig. 4b are known to stem from Ga  $2p_{1/2}$  and Ga  $2p_{3/2}$ , representing the Ga-O bonding.<sup>36</sup> The energy peak of Ga 3d centered at 23.6 eV can be ascribed to the presence of gallium in  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> (Fig. 4a). The O1s XPS signal observed at a binding energy of 532.4 eV (Fig. 4c) corresponded to the characteristic peak of  $\beta$ - $Ga_2O_3$ .<sup>37</sup> The XPS analysis confirmed that the as-prepared  $Ga_2O_3$ was mainly nanosized  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>, which accords with the XRD measurement. Fig. 4d showed the C 1s peak of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC was at 284.6 eV, which was mainly owed to the AC and the pollutant carbon from the XPS instrument.<sup>38</sup> Besides, the

![](_page_4_Picture_3.jpeg)

Fig. 2 SEM images of (a) AC, (b)  $5.0\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, (c)  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, and (d)  $25\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC.

![](_page_4_Figure_5.jpeg)

Fig. 3 TEM images of (a)  $5.0\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, (b)  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, (c)  $25\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, and (d) high-resolution TEM image of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC.

atomic contents of Ga and C in different  $Ga_2O_3/AC$  nanocomposite samples were calculated from XPS peak areas, which can be converted to the weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC. As indicated in Table 1, the calculated weight ratios for  $Ga<sub>2</sub>O<sub>3</sub>$  and AC are closely equal to the adding ratios in the preparation process, implying that gallium nitrate hydrate can be

![](_page_5_Figure_2.jpeg)

Fig. 4 XPS of 15%-Ga<sub>2</sub>O<sub>3</sub>/AC nanocomposite sample: (a) survey spectrum, (b) Ga 2p, (c) O 1s, and (d) C 1s.

Table 1 The calculated weight ratios of Ga<sub>2</sub>O<sub>3</sub> to AC based on XPS measurements and textural characteristics of bare Ga<sub>2</sub>O<sub>3</sub> and Ga<sub>2</sub>O<sub>3</sub>/AC composites obtained from  $N_2$  adsorption–desorption experiments<sup>a</sup>

Samples	Weight ratio of $Ga2O3$ to AC	$S_{BET}$ $(m^2 g^{-1})$	$V_T$ (cm <sup>3</sup> g <sup>-1</sup> )	$V_{\rm M}$ (cm <sup>3</sup> g <sup>-1</sup> )	Pore size (nm)
AC		907	0.618	0.269	1.61
Ga <sub>2</sub> O <sub>3</sub>		101	0.125	0.017	3.85
$5\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	5.6%	836	0.420	0.120	2.26
$10\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	10.9%	758	0.302	0.056	3.09
$15\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	14.3%	685	0.237	0.025	3.48
$20\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	21.0%	652	0.226	0.023	3.53
$25\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	26.4%	630	0.219	0.022	3.51

 $^a$  S<sub>BET</sub>, specific surface area obtained by BET equation; V<sub>T</sub>, total pore volume; V<sub>M</sub>, micropore volume; average pore size from pore size distribution by BJH method.

completely converted to  $Ga<sub>2</sub>O<sub>3</sub>$  via the as-mentioned hydrolysis method.

Since heterogeneous photocatalysis is generally influenced by the specific surface area of catalysts, the pore structure and BET surface area of the synthesized composites were studied on the basis of  $N_2$  adsorption and desorption measurements. Fig. 5 showed  $N_2$  adsorption–desorption isotherms of bare  $Ga_2O_3$  and 15%- $Ga_2O_3/AC$  and the corresponding pore size distribution was given in the inset of Fig. 5. According to the IUPAC classification, the adsorption isotherms of bare  $Ga<sub>2</sub>O<sub>3</sub>$ and  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC were of type IV isotherm, indicating the presence of mesoporous structures. The structural and textural characteristics of as-prepared composites can be obtained from  $N_2$  adsorption–desorption isotherms and the corresponding data were summarized in Table 1. For bare Ga<sub>2</sub>O<sub>3</sub>, the BET specific surface area ( $S_{\text{BET}}$ ) was 101 m<sup>2</sup> g<sup>-1</sup> and the average pore size was 3.85 nm with a narrow distribution of pore size. As indicated in Table 1, bare AC had a large  $S<sub>BET</sub>$  of 907  $m^2$  g<sup>-1</sup> and high total pore volume of 0.618 cm<sup>3</sup> g<sup>-1</sup> because of the porous property. After introducing  $Ga<sub>2</sub>O<sub>3</sub>$ particles into AC matrix,  $S<sub>BET</sub>$ , total pore volume and micropore volume of the obtained  $Ga_2O_3/AC$  composites decreased significantly. Whereas the average pore diameter in the composites increased slightly, compared to bare AC, which could be due to the formation of meso-pores or macro-pores in the channels between the deposited  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles on the surface of AC. The decrease in micro-pore volume of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  could be ascribed to the effects of meso-pores blocking by deposited  $Ga<sub>2</sub>O<sub>3</sub>$ , since these meso-pores acted as the primary passageway to micro porous regions in AC. On the other hand, small grain size and uniform distribution of  $Ga<sub>2</sub>O<sub>3</sub>$  particles could inhibit the reduction of  $S<sub>BET</sub>$  and pore volume of Ga<sub>2</sub>O<sub>3</sub>/AC composites to some extent. A larger  $S<sub>BET</sub>$ can give rise to more active adsorption sites and photocatalytic reaction centers, which means higher  $S_{\text{BET}}$  will be beneficial to improving the photocatalytic activity.<sup>39</sup>

![](_page_6_Figure_3.jpeg)

Fig. 5 Nitrogen adsorption–desorption BET isotherms and pore size distribution curves (inset) of bare  $Ga_2O_3$  and  $15\%$ - $Ga_2O_3$ /AC.

#### 3.2 Photocatalytic properties of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites

Surface adsorption is the precondition of photocatalytic reaction and strong adsorption of target reactants facilitates the catalytic oxidation between the adsorbed reactants and surface active species. Therefore, the dark-adsorption of  $CH<sub>4</sub>$  on the surface of as-synthesized samples was investigated firstly. The adsorption capacity of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites as well as bare  $Ga<sub>2</sub>O<sub>3</sub>$  and AC was estimated by studying the removal rate of  $CH<sub>4</sub>$  in a fixed-bed reactor and the results were presented in Fig. 6. For bare AC, the removal of  $CH<sub>4</sub>$  increased gradually with the increase of adsorption time and about 45.1% of the initial CH4 was removed until reaching an adsorption equilibrium at the end of 120 min in the dark. Whereas, for bare  $Ga<sub>2</sub>O<sub>3</sub>$ , only 8.9% of the initial  $CH_4$  was removed in the dark-adsorption process. In the case of  $Ga_2O_3/AC$  composites, the initial removal of  $CH<sub>4</sub>$  driven by dark adsorption was lower than unmodified AC. It can be obtained from Fig. 6B that the adsorption-induced removal percentages of  $CH<sub>4</sub>$  were 20.4%, 18.1%, 16.2%, 15.5%, and 14.6% for 5%-Ga<sub>2</sub>O<sub>3</sub>/AC, 10%-Ga<sub>2</sub>O<sub>3</sub>/ AC,  $15\% - Ga_2O_3/AC$ ,  $20\% - Ga_2O_3/AC$ , and  $25\% - Ga_2O_3/AC$ , respectively. It was clearly found that the adsorption-induced removal of CH<sub>4</sub> decreased gradually with the increased  $Ga<sub>2</sub>O<sub>3</sub>$ loading. The results could be explained by SEM images and  $N_2$ adsorption–desorption experimental results, as indicated in Fig. 2 and Table 1. SEM images in Fig. 2 demonstrated that most

![](_page_6_Figure_7.jpeg)

Fig. 6 The dark adsorption of CH<sub>4</sub> over (A) bare AC and  $Ga_2O_3$ , (B) different  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites.

of AC surface was covered by  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles. It would result in a negative effect on the adsorption ability of AC, especially for the internal adsorption sites in AC because of the pore blocking by  $Ga_2O_3$  particles.

In the present system,  $CH_4$  removal via the gas-solid catalytic reaction can be divided into two steps. One is the abovementioned adsorption process in the darkness, the other step is photocatalytic oxidation process under UV illumination. For the unmodified AC, only 4.0% of  $CH<sub>4</sub>$  was further removed after UV irradiation for 150 min, as indicated in Fig. 6A. In contrast to AC, after dark adsorption for 120 min,  $CH<sub>4</sub>$  could be significantly decomposed by the photocatalytic oxidation over bare  $Ga<sub>2</sub>O<sub>3</sub>$ . It can be seen from Fig. 6A that CH<sub>4</sub> removal increased dramatically with prolonging the time of UV illumination and  $CH<sub>4</sub>$  removal efficiency reached approximately 36.5% after 150 min irradiation, which was mainly attributed to the photocatalytic oxidation process.

To investigate the kinetic behavior of  $CH<sub>4</sub>$  oxidation, the concentration data of photocatalytic  $CH<sub>4</sub>$  degradation were normalized by the initial concentration at the start of illumination, which was also regarded as the equilibrium concentration of dark-adsorption. The as-obtained degradation percentage  $(C/C_0)$  of CH<sub>4</sub> as a function of irradiation time was presented in Fig. 7A. The blank experiment in Fig. 7A referred to the photocatalytic oxidation of  $CH<sub>4</sub>$  under UV irradiation in the absence of  $Ga_2O_3$  or  $Ga_2O_3/AC$  composites. No obvious photocatalytic oxidation of  $CH<sub>4</sub>$  was observed after illumination for 150 min in the absence of catalysts. Careful analysis of  $CH<sub>4</sub>$ photo-oxidation revealed that the reactions follow pseudo-firstorder kinetics and the integrated rate equation can be expressed by:

$$
\ln\left(\frac{C_0}{C}\right) = k't
$$

where  $k'$  represents the pseudo-first-order rate constant  $(min^{-1})$ . It is valid for the comparison of various composite photocatalysts since the as-obtained photocatalytic activity is independent of dark-adsorption. Fig. 7B described the liner relationship between  $ln(C_0/C)$  and illumination time t, where the slopes of lines denoted pseudo-first-order rate constant  $k'$ . The corresponding data were summarized in Table 2.

The photocatalytic oxidation of  $CH<sub>4</sub>$  primarily proceeded on the outer surface of catalysts. Thus, the weight proportion and distribution of Ga<sub>2</sub>O<sub>3</sub> particles on the exterior surface of Ga<sub>2</sub>O<sub>3</sub>/ AC are the crucial factors in CH<sub>4</sub> oxidation. The effect of  $Ga<sub>2</sub>O<sub>3</sub>$ weight proportion on  $CH_4$  oxidation rate was shown in Fig. 7. From Fig. 7A, it can be found the oxidation rate of  $CH_4$ increased with the increase of irradiation time, possibly because of continuous formation of active radicals upon the surface of irradiated  $Ga<sub>2</sub>O<sub>3</sub>$  particles. Photocatalytic CH<sub>4</sub> oxidation rates of as-synthesized composites were greatly

![](_page_7_Figure_7.jpeg)

Fig. 7 (A) Photocatalytic oxidation of CH<sub>4</sub> over bare Ga<sub>2</sub>O<sub>3</sub> and  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites under UV irradiation, (B) pseudo-first-order reaction kinetics curves of photocatalytic  $CH<sub>4</sub>$  oxidation over assynthesized samples.

Table 2 First-order kinetic constants and relative coefficients toward photocatalytic oxidation of methane with bare  $Ga_2O_3$  and  $Ga_2O_3/AC$ composites

Samples	$k'$ (min <sup>-1</sup> )	$R^2$
Bare $Ga_2O_3$	0.0023	0.9775
$5\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	0.0039	0.9949
$10\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	0.0081	0.9959
$15\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	0.0171	0.9981
$20\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	0.0113	0.9987
$25\%$ -Ga <sub>2</sub> O <sub>3</sub> /AC	0.0067	0.9970

dependent on the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC. It could be obtained from Fig. 7B, the pseudo-first-order rate constant of photocatalytic oxidation CH<sub>4</sub> over bare Ga<sub>2</sub>O<sub>3</sub>, 5%-Ga<sub>2</sub>O<sub>3</sub>/AC,  $10\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC, 15%-Ga<sub>2</sub>O<sub>3</sub>/AC, 20%-Ga<sub>2</sub>O<sub>3</sub>/AC, and 25%-Ga<sub>2</sub>O<sub>3</sub>/AC was 0.0023, 0.0039, 0.0081, 0.0171, 0.0113, and 0.0067  $min^{-1}$ , respectively. The photocatalytic oxidation rate firstly increased with increasing the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC, and then reduced when the weight ratio was higher than 15%. The similar result has been reported in  $TiO<sub>2</sub>/AC$  photocatalytic system.<sup>39</sup> When the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  was low, photocatalytic rate of  $CH_4$  oxidation was also low, which might be due to the limited  $Ga<sub>2</sub>O<sub>3</sub>$  particles loaded on the composites. With the increase of  $Ga<sub>2</sub>O<sub>3</sub>$  loading, more  $Ga<sub>2</sub>O<sub>3</sub>$  were deposited on the surface of AC. As a result, photo-reactive sites available on the surface of catalysts increased, which is beneficial for the gas–solid catalytic reaction of  $CH<sub>4</sub>$  oxidation. It was clearly seen from Fig. 7 that  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC exhibited highest oxidation rate of CH<sub>4</sub>, revealing that appropriate weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC was able to well disperse  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles and thus improve the migration of photogenerated electrons. This facilitated the separation of photoinduced electrons and holes, which could efficiently promote photocatalytic rate. However, when the weight proportion of  $Ga<sub>2</sub>O<sub>3</sub>$  exceeded 15%, photocatalytic oxidation rates decreased with the increasing of  $Ga<sub>2</sub>O<sub>3</sub>$  weight proportion. The reason could be due to the fact that a certain amount of nanosized  $Ga<sub>2</sub>O<sub>3</sub>$  particles aggregated on the surface of  $Ga<sub>2</sub>O<sub>3</sub>/AC$ , which would reduce the efficient light absorption and reactive sites for photocatalytic oxidation. Besides, the reduction of  $S<sub>BET</sub>$  and pore volume (as shown in Table 1) resulted in the decrease of  $CH<sub>4</sub>$  adsorption on the surface of  $Ga<sub>2</sub>O<sub>3</sub>/AC$ , which partly reduced the photo-activity for CH<sub>4</sub> oxidation. The results further indicate that the weight proportion and dispersibility of  $Ga<sub>2</sub>O<sub>3</sub>$  particles on the surface of composite photocatalysts are crucial for the improved photocatalytic activity. Paper<br>
Access Article Control on 31 July 2017. Downloaded on 21 July 2017. The control of the common and the article is licensed under the creative Commons are the common and the article is licensed under the common and t

> To further understand the oxidation process of  $CH<sub>4</sub>$  removal over as-prepared  $Ga_2O_3/AC$  samples, the effect of light intensity on the photocatalytic activity was investigated. Photocatalytic oxidation of methane upon the optimal composites  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/ AC was normalized by the initial concentration at the end of dark adsorption. As indicated in Fig. S3 of ESI, $\dagger$  the CH<sub>4</sub> removal driven by photocatalytic oxidation process on 15%-  $Ga<sub>2</sub>O<sub>3</sub>/AC$  was proportional to the irradiation intensity. This obviously demonstrates that a higher intensity of irradiation gives rise to a more efficient removal of  $CH<sub>4</sub>$ , suggesting the

incident light intensity plays an important role in  $CH<sub>4</sub>$  photocatalytic oxidation system. Under UV irradiation, stronger light intensities can excite more  $Ga<sub>2</sub>O<sub>3</sub>$  catalysts and generate more charge carriers or active radical species, leading to higher CH4 oxidation rates. Meanwhile, the results confirm that the methane removal over  $Ga_2O_3/AC$  composite photocatalyst is truly driven by a photocatalytic oxidation process.

Photocatalytic oxidation of  $CH<sub>4</sub>$  under different initial concentrations was also carried out and the results were indicated in Fig. 8. The photo-oxidation reactions under various initial  $CH<sub>4</sub>$  concentrations also followed pseudo-first-order kinetics and the apparent rate constants  $k'$  obtained from Langmuir–Hinshelwood model were 0.0171, 0.0134, 0.0102,  $0.0070$  and  $0.0051$  min<sup>-1</sup>, respectively, with increasing the initial CH<sub>4</sub> concentration from 1.56 to 7.90 mmol  $L^{-1}$  (Fig. 8B). This clearly demonstrates that photocatalytic technique is more competent for eliminating low concentration of CH4. It is totally different from traditional thermal catalysis, which usually exhibits poor catalytic activity when the concentration of reactant is low.

For the photocatalytic methane oxidation, the photogenerated holes or the lattice oxygen activated by photo-holes are considered as the primary active species toward abstracting H from CH4. <sup>40</sup> This step is closely related to energy and intensity of irradiation. That is, when fixing the irradiation

conditions, the reaction rates are primarily dependent on  $CH<sub>4</sub>$ initial concentration, and proceed more quickly for lower concentration. To elucidate the excellent performance of  $Ga<sub>2</sub>O<sub>3</sub>$ based photocatalysts for  $CH_4$  oxidation, dark-adsorption and photocatalytic process of commercial P25 and  $15\%$ -TiO<sub>2</sub>/AC were also investigated under the same experimental conditions. Commercial P25, as a recognized benchmark photocatalyst, is selected to compare with bare  $Ga<sub>2</sub>O<sub>3</sub>$ . As shown in Fig. 9A, only 5.7% of the initial  $CH_4$  was removed over commercial P25 at the end of dark-adsorption, which was slightly lower than that of bare Ga<sub>2</sub>O<sub>3</sub> (8.9%). It can be due to the smaller  $S_{BET}$  of P25 ( $\sim$ 50)  $\text{m}^2 \text{ g}^{-1}$ ), compared to as-prepared Ga<sub>2</sub>O<sub>3</sub> (~101 m<sup>2</sup> g<sup>-1</sup>). 15%  $TiO<sub>2</sub>/AC$  composite was also prepared via in situ synthesis strategy, as presented in the Experimental section. Similar to the synthesis of  $Ga_2O_3/AC$  composites, the preparation of nanosized TiO<sub>2</sub> and the compositing of as-prepared TiO<sub>2</sub> with AC were simultaneously carried out. The XRD pattern and SEM image of  $15\%$ -TiO<sub>2</sub>/AC sample were depicted in Fig. S4 and S5 of ESI.† The characteristic diffraction peaks at  $25.4^{\circ}$ ,  $37.9^{\circ}$ ,  $48.1^{\circ}$ , 54.7 $\degree$  and 63.1 $\degree$  were observed, indicating that as-obtained TiO<sub>2</sub> was anatase phase. SEM images of  $15\%$ -TiO<sub>2</sub>/AC showed that TiO2 nanoparticles were uniformly dispersed and loaded upon the surface of AC. It can be found from Fig. 9B that although 15%-TiO<sub>2</sub>/AC and 15%-Ga<sub>2</sub>O<sub>3</sub>/AC exhibited similar adsorption **BSC Arbaness**<br>
incident light intensity plays an important role in CIT, phose conditions, the reaction system intention contribution of commons are properties and the commons are properties and the commons are properties

![](_page_8_Figure_6.jpeg)

 $30$  $60$  $90$  $120$ Time (min)  $1.0$  $(B)$  $0.8$  $(C / C_n)$  $0.6$  $\vec{t}$  $0.4$ bare  $Ga<sub>2</sub>O$ commercial P25 Tin  $0.2$ 15%-Ga O / AC 15%-TiO<sub>2</sub>/AC  $0.0$ 30 60 90 120 150  $\overline{0}$ Irradiation time (min)

Fig. 8 (A) Time evolution of methane photocatalytic oxidation over 15%-Ga<sub>2</sub>O<sub>3</sub>/AC under UV illumination with various initial CH<sub>4</sub> concentrations, (B) the corresponding pseudo-first-order reaction kinetics plots of photocatalytic  $CH<sub>4</sub>$  oxidation.

Fig. 9 (A) Dark-adsorption of CH<sub>4</sub> over bare Ga<sub>2</sub>O<sub>3</sub>, commercial P25, 15%-Ga<sub>2</sub>O<sub>3</sub>/AC and 15%-TiO<sub>2</sub>/AC; (B) photocatalytic oxidation of CH<sub>4</sub> upon bare Ga<sub>2</sub>O<sub>3</sub>, commercial P25, 15%-Ga<sub>2</sub>O<sub>3</sub>/AC and 15%-TiO<sub>2</sub>/AC under UV irradiation.

capacity for CH<sub>4</sub>, the photocatalytic oxidation of CH<sub>4</sub> over 15%- $Ga_2O_3/AC$  was significantly greater than 15%-TiO<sub>2</sub>/AC. It suggests that high catalytic performance of  $Ga_2O_3/AC$  cannot be simply explained by the surface adsorption.  $CH<sub>4</sub>$  removal induced by photocatalytic oxidation over bare  $Ga_2O_3$  and  $Ga_2O_3/$ AC was higher than that over P25 and TiO<sub>2</sub>/AC. It could be associated with the band gap structures of  $Ga_2O_3$  and  $TiO_2$ . For semiconductor  $TiO<sub>2</sub>$ , the conduction band and valence band consist of Ti 3d and O 2p orbitals, respectively. In the case of  $Ga<sub>2</sub>O<sub>3</sub>$ , the valence band is composed of O 2p orbital, whereas the conduction band consists of hybridized Ga 4s4p orbital. The bandgap energy of  $Ga_2O_3$  is 4.8 eV, much wider than that of TiO<sub>2</sub> (3.2 eV). Additionally, the reported valence-band potential of Ga<sub>2</sub>O<sub>3</sub> is  $-7.75$  eV, which is lower than that of TiO<sub>2</sub>  $-7.41$  eV. Whereas, the conduction-band potential of  $Ga<sub>2</sub>O<sub>3</sub>$  is -2.95 eV, which is higher than that of TiO<sub>2</sub>  $-4.21$  eV.<sup>28,29</sup> As a result, the photo-holes and photo-electrons generated on  $Ga<sub>2</sub>O<sub>3</sub>$  possess stronger redox ability than those formed on  $TiO<sub>2</sub>$ . The intrinsic energy-band structure of  $Ga<sub>2</sub>O<sub>3</sub>$  contributes to the excellent photocatalytic activity for  $CH<sub>4</sub>$  oxidation. Paper<br>
Copyl<sub>26</sub> We we significantly generate than 0.5% from 2017.<br>
Since the significant properties and the significant common and collection of  $\alpha$  and  $\alpha$ 

To examine the mineralization ratio during photocatalytic CH<sub>4</sub> oxidation, the production of  $CO_2$  over 15%-Ga<sub>2</sub>O<sub>3</sub>/AC photocatalysts was detected and the corresponding result was presented in Fig. S6 of ESI.† Before UV light was turned on, no CO2 was detected, which indicated the dark-adsorption process cannot produce  $CO<sub>2</sub>$ . After the light was turned on, the concentration of  $CH<sub>4</sub>$  decreased significantly with the irradiation time. Meanwhile, the amount of  $CO<sub>2</sub>$  increased gradually and around 0.93 mmol  $L^{-1}$  of CO<sub>2</sub> was produced from CH<sub>4</sub> photooxidation under UV irradiation for 150 min. Besides, no other intermediate products, such as CO or ethane, were detected by GC during the CH4 photocatalytic oxidation. Carbon mass balance of 79.0% could be obtained based on the proportion of the sum of remaining CH $_4$  (0.105 mmol  $\text{L}^{-1})$  and produced CO $_{\rm 2}$  (0.93 mmol  ${\rm L}^{-1})$  to carbon input (1.31 mmol  ${\rm L}^{-1}$  $CH<sub>4</sub>$  at the end of adsorption process). This suggests that about 79.0% CH<sub>4</sub> is mineralized to  $CO<sub>2</sub>$  after UV irradiation for 150 min.

The stability or recyclability of a catalyst is an extremely crucial parameter for practical utilization. To test the stability of as-prepared  $Ga_2O_3/AC$  photocatalysts, a cycling  $CH_4$  photooxidation test over the optimal composite  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC was thus performed and the results were indicated in Fig. 10. After six cycles, the activity of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC almost remained unchanged. Moreover, the crystal structure and chemical composition of recycled  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC sample were also investigated by XRD and XPS analysis. No noticeable differences between the freshly made and the repeatedly used samples were observed from Fig. S7 of ESI.<sup>†</sup> The results demonstrate  $Ga_2O_3/$ AC composites are stable and can be recycled toward CH4 photocatalytic oxidation.

### 3.3 Photocatalytic mechanism of CH<sub>4</sub> oxidation over  $Ga_2O_3/$ AC composites

Photoluminescence (PL) generally arises from the charge recombination process of photoinduced electron and hole and

![](_page_9_Figure_7.jpeg)

Fig. 10 Recycled test of photocatalytic oxidation of  $CH_4$  over 15%- $Ga<sub>2</sub>O<sub>3</sub>/AC$ 

thus the intensity of PL peak can represent the recombination extent of photogenerated charges. Low PL intensity usually demonstrates low recombination degree and efficient separation of h<sup>+</sup> and e<sup>-</sup>. Fig. 11 showed the PL spectra of bare  $Ga_2O_3$ and various  $Ga_2O_3/AC$  composites. The as-prepared samples exhibited the same PL peaks and similar curve shapes, which indicated introduction of AC did not generate new luminescence phenomena but the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  indeed affected the PL intensity. The major luminescence signals were observed in the wavelength range of 350–480 nm. The peak at around 370 nm and 400 nm could be assigned to the recombination of self-trapped excitons, which mainly originated from the band edge emission.<sup>41,42</sup> Furthermore, based on the previous reports,  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> contains two kinds of Ga<sup>3+</sup> ions.<sup>41,42</sup> One is Ga<sup>3+</sup> ion in the tetrahedral site coordinated by four oxygen atoms and the other is that in the octahedral site coordinated by six oxygen atoms. An emission centered at 465 nm might be derived from the recombination of electrons trapped by oxygen vacancy and holes generated by either gallium vacancy or gallium–oxygen

![](_page_9_Figure_10.jpeg)

Fig. 11 Photoluminescence spectra of bare  $Ga_2O_3$  and  $Ga_2O_3/AC$ composites.

vacancy pairs.41,42 These vacancies could be formed by the thermal treatment during the synthesis process.

More importantly, the incorporation of AC led to the decrease in the intensity of PL spectra, which suggests that the composite photocatalysts possess low recombination of  $h^+$  and e<sup>-</sup>. The intensity of luminescence peaks decreased in the order of bare  $Ga_2O_3 > 5\% - Ga_2O_3/AC > 10\% - Ga_2O_3/AC \approx 25\% - Ga_2O_3/$  $AC > 15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC. When the weight ratio of Ga<sub>2</sub>O<sub>3</sub> was low,  $Ga<sub>2</sub>O<sub>3</sub>$  particles were mainly dispersed on the meso-pore or macro-pore mouths of AC, as presented in Fig. 2b, resulting in the moderate decrease of PL intensity. As the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC increased, the PL intensity of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites gradually decreased. A lower PL intensity usually indicates a slower recombination rate and higher separation efficiency of photoinduced charge carriers.  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC sample exhibited lowest PL intensity, which could be due to the highly dispersed  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles supported onto the surface of AC. It was beneficial for the separation of photo-induced electron/hole pairs and consequently improved the photocatalytic activity. However, when the weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  was too high, nanosized  $Ga_2O_3$  particles could aggregate on the surface of AC, which reduced the efficient light absorption and separation of photogenerated  $h^+$  and  $e^-$ .

The photocatalytic oxidation of methane generally involves the surface reactions of photogenerated holes and electrons, which may also produce oxidizing species, such as  $O_2$   $\bar{~}$  and 'OH to further the oxidation reactions. To identify the generation of reactive species and investigate the photocatalytic mechanism of  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites toward CH<sub>4</sub> oxidation, ESR spectroscopy with spin trapping and labeling was chosen as an effective characterization technique. Here, we selected 5,5-dimethyl-1 pyrroline-N-oxide (DMPO)<sup>43</sup> as a spin-trapping agent for  $O_2$ <sup>--</sup> radicals and  $2,2,6,6$ -tetramethylpiperidine-1-oxyl (TEMPO) $^{44}$  as a spin-labeling agent for photogenerated electrons.

Photo-holes are considered as the predominant active species for photocatalytic oxidation of methane. It is demonstrated that the triplet ESR signal of TEMPO can diminish or even vanish if it is reduced by photogenerated electrons from semiconductors.<sup>44</sup> As a result, the generation of photo-electrons can be monitored accurately by observing the changes in the intensity of TEMPO signals. ESR spectrum of an aqueous TEMPO solution showed a stable signal having triplet peaks with intensity of  $1:1:1$  (Fig. 12A). The signal intensity decreased moderately after 3 min irradiation in the presence of bare  $Ga<sub>2</sub>O<sub>3</sub>$ ; however, a considerable decrease in the ESR signal was observed during the irradiation of  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC suspension. It indicates that the introduction of AC can enhance the generation of photoelectrons greatly. Furthermore, the presence of photoelectrons is invariably accompanied by the generation of photoholes. Hence, the reduction of ESR signal intensity shown in Fig. 12A can reflect the formation of photoholes over  $Ga_2O_3/AC$  composites indirectly. In addition, as shown in Fig. 12B, the characteristic peaks of  $\mathrm{DMPO\text{-}O_2}^{\ast-}$  can be observed in methanol suspensions of bare  $Ga<sub>2</sub>O<sub>3</sub>$  upon irradiation for 3 min.<sup>43</sup> For  $15\%$ -Ga<sub>2</sub>O<sub>3</sub>/AC composites, the signal intensity of DMPO-O<sub>2</sub><sup>--</sup> increased obviously (about 3 times of bare  $Ga<sub>2</sub>O<sub>3</sub>$ ) under the same conditions. These results

![](_page_10_Figure_6.jpeg)

Fig. 12 ESR spectra obtained from bare  $Ga_2O_3$  and  $15\%$ - $Ga_2O_3/AC$ suspensions (A) 40 mM DMPO methanol solution and (B) 0.02 mM TEMPO aqueous solution. All spectra were recorded after 3 min of UV irradiation. The blank represented the solution containing spin probes alone under light illumination.

demonstrate that  $O_2$ <sup>--</sup> can be generated over bare Ga<sub>2</sub>O<sub>3</sub> or Ga<sub>2</sub>O<sub>3</sub>/AC composites under UV irradiation and introduction of AC significantly enhanced the photogeneration of  $O_2$ <sup>--</sup>.

The photocatalytic oxidation of  $CH_4$  over 15%-Ga<sub>2</sub>O<sub>3</sub>/AC composites was further explored through a series of control experiments. As depicted in Fig. 13, the oxidation of  $CH<sub>4</sub>$  was almost unchanged after adding TBA (a scavenger of 'OH<sup>45</sup>) into the reaction system, indicating that 'OH had little effect on photocatalytic oxidation of  $CH_4$  over  $Ga_2O_3/AC$  composites. When KI was added to the reaction system to trap the holes,<sup>46</sup> the  $CH<sub>4</sub>$  oxidation was significantly inhibited, revealing that photogenerated holes were the major oxidative species for the photocatalytic  $CH_4$  oxidation. Addition of BQ (a scavenger of superoxide radicals<sup>47</sup>) clearly suppressed the  $CH<sub>4</sub>$  oxidation, which suggests that  $O_2$ <sup>--</sup> also play a critical role in the photocatalytic oxidation of CH<sub>4</sub>. Adding  $K_2Cr_2O_7$  (an electron scavenger<sup>48</sup>) into the reaction system led to moderate decrease of photocatalytic oxidation for  $CH<sub>4</sub>$ . All of the above experimental results were obtained in the presence of 79%  $N_2$  gas, 21%  $O_2$  gas and 1.56 mmol  $L^{-1}$  CH<sub>4</sub>.

However, when adding electron scavenger  $K_2Cr_2O_7$  in the presence of 100%  $O_2$  gas and 1.56 mmol  $L^{-1}$  CH<sub>4</sub>, the oxidation of CH4 exhibited slight increase. It might be ascribed to the fact

![](_page_11_Figure_2.jpeg)

Fig. 13 Controlled experiments using different radical scavengers for the photocatalytic oxidation of  $CH_4$  over 15%-Ga<sub>2</sub>O<sub>3</sub>/AC catalyst: (a) no scavenger, (b) TBA, (c) KI, (d) BQ, (e) K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub>, (f) K<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> + 100% O<sub>2</sub> gas, and (g)  $K_2Cr_2O_7 + 100\% N_2$  gas.

that trapping of photogenerated electrons with  $K_2Cr_2O_7$  could benefit the generation of photoinduced holes. But the oxidation of CH<sub>4</sub> was significantly restrained in the presence of  $K_2Cr_2O_7$ , 100% N<sub>2</sub> gas and 1.56 mmol L<sup>-1</sup> CH<sub>4</sub>. During the photocatalytic process of CH<sub>4</sub> oxidation, CH<sub>4</sub> was activated primarily via extracting hydrogen by photoinduced holes, consequently generating methyl radicals ( $\text{CH}_3$ ). These experimental results imply that high concentration of  $O_2$  can also react with  $CH_3$ , although there is no superoxide radicals.

As it is known,  $CH_4$  is a highly flammable gas.  $CH_4$  is unstable under high concentration of  $O<sub>2</sub>$  and can cause combustion and even explosive reactions. Hence, from the view of experimental safety, the photocatalytic experiments of  $CH<sub>4</sub>$  oxidation were performed in the presence of 79%  $N_2$  gas and 21%  $O_2$  gas unless otherwise stated. On the basis of the above experimental results, it is concluded that the reaction between  $\text{CH}_3$  and  $O_2$ <sup>--</sup> is predominant for the photocatalytic oxidation of  $CH<sub>4</sub>$  in the presence of 79%  $N_2$  gas and 21%  $O_2$  gas.

The ESR results in Fig. 12 indicate that  $Ga_2O_3/AC$  composites facilitate the generation of photo-induced active species, such as  $O_2$ <sup>--</sup> and photo-holes. Meanwhile, the weight ratios of  $Ga_2O_3$ have a decisive role in the photocatalytic activity of  $Ga<sub>2</sub>O<sub>3</sub>/AC$ composites (Fig. 7). Therefore, it was critical to investigate whether the weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$  had similar effects on the photoinduced generation of active species. The effects of  $Ga<sub>2</sub>O<sub>3</sub>$ weight ratios on the ESR signal intensity of  $\text{DMPO-O}_2^{\bullet -}$  and TEMPO were depicted in Fig. 14. A similar dependence on  $Ga<sub>2</sub>O<sub>3</sub>$ weight ratios was observed for  $O_2$ <sup>-–</sup> radicals and photoholes. An initial increase in the ESR signal intensity was noted for  $Ga<sub>2</sub>O<sub>3</sub>/$ AC composites with weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$  up to 15%. Diminishing ESR signal intensities were observed for composite samples having a higher weight ratio of  $Ga<sub>2</sub>O<sub>3</sub>$ . Importantly, it is of interest to note that the changes of ESR signals obtained for  $DMPO-O_2$ <sup>--</sup> or TEMPO and the photocatalytic activity of CH<sub>4</sub> oxidation had a similar dependence on the weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$ . This correlation implied a mechanistic connection between the generation of photoholes or  $O_2$ <sup>--</sup> radicals and the photocatalytic performance. The results also indicate

![](_page_11_Figure_7.jpeg)

Fig. 14 Effect of  $Ga_2O_3$  weight ratios on the enhancement of photoinduced generation of superoxide radicals and photoelectrons.

photogenerated holes and  $O_2$ <sup>--</sup> radicals play dominant roles in the photocatalytic oxidation of  $CH_4$  over  $Ga_2O_3/AC$  composites, consistent with the results of active species trapping experiments.

For the photocatalytic oxidation of  $CH_4$ ,  $Ga_2O_3/AC$  catalysts are thought to act through a dynamic adsorption-photocatalysis process under UV irradiation.  $Ga_2O_3/AC$  composites exhibit higher performance for  $CH<sub>4</sub>$  oxidation compared with bare  $Ga<sub>2</sub>O<sub>3</sub>$ , which might be due to the following two aspects. One is the excellent adsorption capacity of AC for  $CH<sub>4</sub>$  molecules. The interface created between AC and  $Ga<sub>2</sub>O<sub>3</sub>$  phase facilitates the adsorption of  $CH_4$  onto AC and the transfer of adsorbed  $CH_4$  to catalytic active component  $Ga<sub>2</sub>O<sub>3</sub>$ . More importantly, AC support facilitates the dispersion of deposited  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles (Fig. 2), inhibiting the agglomeration of catalytic active components. On the basis of above results, the proposed mechanism for photocatalytic oxidation of  $CH<sub>4</sub>$  upon  $Ga<sub>2</sub>O<sub>3</sub>/AC$ composites is depicted in Scheme 1. Under UV irradiation, photoinduced electrons and holes are generated upon the surface of  $Ga<sub>2</sub>O<sub>3</sub>$  nanoparticles. The initial step of CH<sub>4</sub> activation primarily involves the reaction with photogenerated holes. The photogenerated electrons can react with the adsorbed  $O<sub>2</sub>$ upon the surface of catalysts and generate  $O_2$ <sup>--</sup> radicals. The obtained methyl radicals via abstracting the hydrogen of  $CH<sub>4</sub>$ are further oxidized by superoxide anion radicals. The Puper<br>  $\frac{1}{2}$  Open Access Article . Published on 31 July 2017. Download on 21 July 2017. Download on 21 July 2017. The Creative Commons Articles. The Creative Commons Attribution-NonCommercial 3.0 Unported Unported Unp

![](_page_11_Figure_11.jpeg)

Scheme 1 Proposed mechanism for photocatalytic oxidation of CH<sub>4</sub> over Ga<sub>2</sub>O<sub>3</sub>/AC composites.

introduction of AC would enhance the surface adsorption of CH4 molecules, the charge separation of photoinduced electron–hole pairs and the generation of active radical species, improving the photocatalytic properties toward  $CH<sub>4</sub>$  oxidation.

## 4. Conclusions

A high-performance  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composite photocatalysts were successfully synthesized via a facile hydrolysis method combined with impregnation process. Photocatalytic oxidation of CH<sub>4</sub> was systematically investigated over bare  $Ga<sub>2</sub>O<sub>3</sub>$  and  $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites in a fixed-bed tubular quartz reactor. The adsorption capacity and photocatalytic activity of  $Ga_2O_3/AC$ were greatly affected by the weight ratios of  $Ga<sub>2</sub>O<sub>3</sub>$  to AC. 15%- $Ga<sub>2</sub>O<sub>3</sub>/AC$  composites exhibited the highest photocatalytic activity and 91.5% of  $CH<sub>4</sub>$  was decomposed after 150 min UV irradiation, which could be ascribed to strong adsorption ability and efficient separation of photo-generated electrons and holes. Besides, the photocatalytic oxidation of  $CH<sub>4</sub>$  obeys pseudo-firstorder kinetics and the cycled experiment indicates that  $Ga<sub>2</sub>O<sub>3</sub>/$ AC composites possess stable photocatalytic performance for CH4 oxidation. Moreover, the underlying photo-oxidation mechanism is also proposed on the basis of the results of ESR measurements and radicals scavenging experiments. The adsorbed CH<sub>4</sub> molecules upon the surface of  $Ga_2O_3/AC$  were activated primarily via the reaction with photo-generated holes and the as-obtained methyl radicals were further oxidized by superoxide anion radicals. The introduction of AC can enhance the surface adsorption of  $CH<sub>4</sub>$  molecules, the separation of photoinduced electron–hole pairs and the generation of active radical species, thus improving the photocatalytic performance of CH4 oxidation. Hence, the photocatalytic technique with  $Ga_2O_3/AC$  composites could be considered as a promising method toward the removal of low concentration  $CH<sub>4</sub>$ . **BSC** Advances Section of AC could enhance the sarface adsorption of  $\sim$  2017. V. Choulhary, S. Barejee and V. R. Choulhary, Age).<br>
CH, molecules, the competent of published order details are  $\sim$  2026, A, 2002, B, 24, 2

# 5. Conflict of interest

There are no conflicts of interest to declare.

## Acknowledgements

This work was supported by the National Natural Science Foundation of China (21307027, 51574112, 51404100), the Program for Innovative Research Team in University of Ministry of Education of China (IRT\_16R22), the Natural Science Foundation of Henan Province (14A440007), the Key Project of Chinese Ministry of Education (213022A), the Innovation Scientists and Technicians Troop Construction Projects of Henan Province (164100510013) and the Funding scheme for the young backbone teachers of higher education institutions in Henan Province (2015GGJS-071).

# Notes and references

1 J. Schmale, D. Shindell, E. von Schneidemesser, I. Chabay and M. Lawrence, Nature, 2014, 515, 335–337.

- 2 T. V. Choudhary, S. Banerjee and V. R. Choudhary, Appl. Catal., A, 2002, 234, 1–23.
- 3 R. A. Alvarez, S. W. Pacala, J. J. Winebrake, W. L. Chameides and S. P. Hamburg, Proc. Natl. Acad. Sci. U. S. A., 2012, 109, 6435–6440.
- 4 J. Schmale, D. Shindell, E. V. Schnedemesser, I. Chabay and M. Lawrence, Nature, 2014, 515, 335–337.
- 5 D. A. Lashof and D. R. Ahuja, Nature, 1990, 344, 529–531.
- 6 P. G´elin and M. Primet, Appl. Catal., B, 2002, 39, 1–37.
- 7 A. J. Zarur and J. Y. Ying, Nature, 2000, 403, 65–67.
- 8 S. Hu, R. J. Zeng, L. C. Burow, P. Lant, J. Keller and Z. G. Yuan, Environ. Microbiol. Rep., 2009, 1, 377–384.
- 9 A. Boetius, K. Ravenschlag, C. J. Schubert, D. Rickert, F. Widdel, A. Gieseke, R. Amann, B. B. Jørgensen, U. Witte and O. Pfannkuche, Nature, 2000, 407, 623–626.
- 10 J. P. Wei, B. S. Yu, J. Yang and J. Dai, Saf. Sci., 2012, 50, 873–877.
- 11 N. Tian, Y. H. Zhang, X. W. Li, K. Xiao, X. Du, F. Dong, G. I. N. Waterhouse, T. R. Zhang and H. W. Huang, Nano Energy, 2017, 38, 72–81.
- 12 R. Y. Zhang, W. C. Wan, D. W. Li, F. Dong and Y. Zhou, Chin. J. Catal., 2017, 38, 313–320.
- 13 H. W. Huang, K. Xiao, Y. He, T. R. Zhang, F. Dong, X. Du and Y. H. Zhang, Appl. Catal., B, 2016, 199, 75–86.
- 14 X. Chen, X. Huang and Z. Yi, Chem.–Eur. J., 2014, 20, 17590– 17596.
- 15 I. Dhada, P. K. Nagar and M. Sharma, Ind. Eng. Chem. Res., 2015, 54, 5381–5387.
- 16 C. F. Lien, M. T. Chen, Y. F. Lin and J. L. Lin, J. Chin. Chem. Soc., 2004, 51, 37–42.
- 17 S. I. In, M. G. Nielsen, P. C. K. Vesborg, Y. D. Hou, B. L. Abrams, T. R. Henriksen, O. Hansen and I. Chorkendorff, Chem. Commun., 2011, 47, 2613–2615.
- 18 Z. Zhang, Y. Zhou, Y. Zhang, S. Zhou, J. Shi, J. Kong and S. Zhang, Dalton Trans., 2013, 42, 5004–5012.
- 19 S. M. Chang and C. Y. Lee, Appl. Catal., B, 2013, 132–133, 219–228.
- 20 J. Taranto, D. Frochot and P. Pichat, Ind. Eng. Chem. Res., 2009, 48, 6229–6236.
- 21 Y. Yang, K. Chiang and N. Burke, Catal. Today, 2011, 178, 197–205.
- 22 J. Yang, X. X. Shen, Y. J. Li, L. Y. Bian, J. Dai and D. S. Yuan, ChemCatChem, 2016, 8, 1399–1409.
- 23 Y. K. Chih and M. Ch. Yang, J. Taiwan Inst. Chem. Eng., 2014, 45, 833–839.
- 24 H. Q. Wang, J. Z. Li, M. J. Zhou, Q. F. Quan, Z. Y. Lu, P. W. Huo and Y. S. Yan, J. Ind. Eng. Chem., 2015, 30, 64–70.
- 25 J. G. McEvoy and Z. S. Zhang, Appl. Catal., B, 2014, 160–161, 267–278.
- 26 Y. Li, D. W. Li, Y. Rao, X. B. Zhao and M. B. Wu, Carbon, 2016, 105, 454–462.
- 27 A. Arami-Niya, T. E. Rufford and Z. H. Zhu, Carbon, 2016, 103, 115–124.
- 28 Y. D. Hou, X. C. Wang, L. Wu, Z. X. Ding and X. Z. Fu, Environ. Sci. Technol., 2006, 40, 5799–5803.
- 29 Y. D. Hou, L. Wu, X. C. Wang, Z. X. Ding, Z. H. Li and X. Z. Fu, J. Catal., 2007, 250, 12–18.
- 30 M. Q. Yang, N. Zhang and Y. J. Xu, ACS Appl. Mater. Interfaces, 2013, 5, 1156–1164.
- 31 W. Z. Li, C. H. Liang, W. J. Zhou, J. S. Qiu, Z. H. Zhou, G. Q. Sun and Q. Xin, J. Phys. Chem. B, 2003, 107, 6292–6299.
- 32 S. Q. Jin, X. Wang, X. L. Wang, M. G. Ju, S. Shen, W. Z. Liang, Y. Zhao, Z. C. Feng, H. Y. Playford, R. I. Walton and C. Li, J. Phys. Chem. C, 2015, 119, 18221–18228. Paper<br>
The C. S. Lincoln, May, W. J. Zhou, J. S. Qiu, Z. H. Zhou, 2017. Downloaded on 5/2007. Downloaded on 5/2017. The state of the C
	- 33 H. Y. Playford, A. C. Hannon, E. R. Barney and R. I. Walton, Chem.–Eur. J., 2013, 19, 2803–2813.
	- 34 X. Zhang and L. Lei, J. Hazard. Mater., 2008, 153, 827–833.
	- 35 X. F. Li, X. Z. Zhen, S. G. Meng, J. J. Xian, Y. Shao, X. Z. Fu and D. Z. Li, Environ. Sci. Technol., 2013, 47, 9911–9917.
	- 36 L. W. Chang, J. W. Yeh, C. F. Li, M. W. Huang and H. C. Shih, Thin Solid Films, 2009, 518, 1434–1438.
	- 37 H. D. Xiao, H. L. Ma, C. S. Xue, H. Z. Zhuang, J. Ma, F. J. Zong and X. J. Zhang, Mater. Chem. Phys., 2007, 101, 99–102.
	- 38 H. Q. Wang, X. Q. Yang, J. Z. Zi, M. J. Zhou, Z. F. Ye, J. Z. Li, Q. F. Guan, P. Lv, P. W. Huo and Y. S. Yan, J. Ind. Eng. Chem., 2016, 35, 83–92.
	- 39 D. D. Liu, Z. S. Wu, F. Tian, B. C. Ye and Y. B. Tong, J. Alloys Compd., 2016, 676, 489–498.
- 40 X. X. Chen, Y. P. Li, X. Y. Pan, D. Cortie, X. T. Huang and Z. G. Yi, Nat. Commun., 2016, 7, 12273.
- 41 K. Girijia, S. Thirumalairajan, G. S. Avadhani, D. Mangalaraj, N. Ponpandian and C. Viswanathan, Mater. Res. Bull., 2013, 48, 2296–2303.
- 42 K. Girija, S. Thirumalairajan and D. Mangalaraj, Chem.–Eur. J., 2014, 236, 181–190.
- 43 H. B. Fu, W. Zhang, S. C. Zhang, Y. F. Zhu and J. C. Zhao, J. Phys. Chem. B, 2006, 110, 3061–3065.
- 44 J. N. Schrauben, R. Hayoun, C. N. Valdez, M. Braten, L. Fridley and J. M. Mayer, Science, 2012, 336, 1298–1301.
- 45 S. C. Yan, Z. S. Li and Z. G. Zou, Langmuir, 2010, 26, 3894– 3910.
- 46 Z. J. Wang, S. Ghasimi, K. Landfester and K. A. I. Zhang, Adv. Mater., 2015, 27, 6265–6270.
- 47 T. T. Zhang, W. Y. Lei, P. Liu, J. A. Rodriguez, J. G. Yu, Y. Qi, G. Liu and M. H. Liu, J. Phys. Chem. C, 2016, 120, 2777–2786.
- 48 L. Wang and X. Z. Jiang, Environ. Sci. Technol., 2008, 42, 8492–8497.