# **RSC Advances**



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2017, 7, 48238

Received 26th July 2017 Accepted 9th October 2017 DOI: 10.1039/c7ra08254a

rsc.li/rsc-advances

# 1. Introduction

In the past decades, rare earth doped materials, which are able to exhibit infrared DC emission in addition to their visible UC emission of lanthanide ions, have attracted considerable attention due to their favorable merits, such as large anti-Stokes shifts, long excited-state lifetimes, narrow emission bandwidths and high photostability.1-4 Based on these inherent advantages, rare earth doped materials play an important role in fabricating the active optical components in optoelectronic applications like laser materials, flat-panel displays, and optical sensors.<sup>5-9</sup> Notably, rare earth doped nano/microcrystals are of great importance for expanding the applications of miniaturized and integrated optoelectronics.<sup>10,11</sup> Among the rare earth ions, Er<sup>3+</sup> is especially attractive because of its NIR emission wavelength of approximately 1530 nm, which lies in the low-loss telecommunication window in optical communication.12,13 However, the low intra-4f-configurational absorption cross section of Er<sup>3+</sup> commonly leads to a weak emission intensity upon inefficient pumping.<sup>14</sup> Fortunately, Yb<sup>3+</sup> ions possess a higher absorption cross section and its  ${}^{2}F_{5/2}$  energy level is resonant with the  ${}^{4}I_{11/2}$ 

# Morphology control and enhancement of 1.5 $\mu m$ emission in Ca^{2+}/Ce^{3+} codoped NaGdF\_4:Yb^{3+}, Er^{3+} submicrorods

Jiangyun Dai, ம<sup>a</sup> Chao Yang, ம<sup>a</sup> Hong Zhang,<sup>a</sup> Hua Zhang,<sup>a</sup> Guoying Feng<sup>\*a</sup> and Shouhuan Zhou<sup>\*ab</sup>

The successful synthesis of rare earth doped nano/microcrystals with the desired morphology, uniform monodispersity, and intense infrared emission is of fundamental significance, and would facilitate their application in infrared emission-related miniaturization and integration in optoelectronics. However, simultaneously controlling the morphology and enhancing the infrared emission through simple and effective methods has not been well explored. In this study, *via* Ca<sup>2+</sup> doping with an optimized concentration of 25 mol% in the hydrothermal solution, irregular NaGdF<sub>4</sub>:Yb/Er submicrocrystals converted into highly uniform submicrorods. Meanwhile, an obvious enhancement of visible upconversion (UC) and near-infrared (NIR) downconversion (DC) emission were obtained, probably due to the improved morphology and lowering the local crystal field symmetry around the rare earth ions induced by Ca<sup>2+</sup> doping. Furthermore, Ce<sup>3+</sup> ions with an optimized concentration of 2 mol% were codoped to intentionally tailor the branching ratio through efficient energy transfer from Er<sup>3+</sup> to Ce<sup>3+</sup>. As a result, the ~1530 nm emission intensity of the NaGdF<sub>4</sub>: 25Ca/2Ce/20Yb/2Er submicrorods increased by about 6.4 times in comparison with the NaGdF<sub>4</sub>:20Yb/2Er counterpart.

energy level of  $Er^{3+}$ . Thus, introduction of  $Yb^{3+}$  as an ideal sensitizer can realize efficient NIR emission of  $Er^{3+}$  upon excitation at 980 nm.

It is well established that the optical, electrical and magnetic properties of nano/microcrystals are depended on not only their composition, but also their geometrical factors including phase, morphology and size. Especially, when the rare earth doped materials are synthesized in the form of the onedimensional nano/microstructures, they would stimulate great attention due to their marked shape-specific and quantumconfinement effects.<sup>15,16</sup> Although several methods have been used to synthesize the one-dimensional nano/microcrystals with a well defined morphology, finding a novel and facile strategy is still imperative.<sup>15</sup> Furthermore, to realize their practical applications, simultaneously obtaining an efficient infrared optical signal is also desired. Hence, many efforts have been devoted to optimizing the performance of rare earth doped materials by adopting novel strategies, such as dye sensitizing,<sup>17</sup> core-shell structure,18,19 and host lattice manipulation.20 Impressively, host lattice manipulation via impurity doping, which has the ability to modify the electron charge density and crystal symmetry of rare earth ions, could simultaneously enhance the emission intensity and control the well-defined morphology in a facile and straightforward way.<sup>21,22</sup> Although many previous works have adopted this strategy to enhance the visible or NIR UC emission,<sup>23-25</sup> enhancing the luminescence in the NIR DC emission range has rarely been studied.

<sup>&</sup>lt;sup>a</sup>Institute of Laser and Micro/Nano Engineering, College of Electronics and Information Engineering, Sichuan University, Chengdu 610064, China. E-mail: guoing\_feng@scu. edu.cn

<sup>&</sup>lt;sup>b</sup>North China Research Institute of Electro-Optics, Beijing 100015, China. E-mail: zhoush@scu.edu.cn

#### Paper

For Er<sup>3+</sup> doped materials, NIR emission at 1530 nm is always accompanied by the visible UC emission upon excitation at 980 nm. However, the visible emission is undesired in the field of infrared application (*e.g.*, optical amplifiers), which would reduce the intensity of NIR emission (~1530 nm) of Er<sup>3+</sup> ions. One of the approaches to circumvent these obstacles is to improve the low branching ratio for the NIR emission. Recent reports show doping with Ce<sup>3+</sup> ions can significantly enhance the <sup>4</sup>I<sub>11/2</sub>  $\rightarrow$  <sup>4</sup>I<sub>13/2</sub> transition probability of Er<sup>3+</sup>.<sup>26,27</sup> The possible mechanism is the non-radiative phonon-assisted energy transfer <sup>2</sup>F<sub>5/2</sub>(Ce<sup>3+</sup>) + <sup>4</sup>I<sub>11/2</sub>(Er<sup>3+</sup>)  $\rightarrow$  <sup>2</sup>F<sub>7/2</sub>(Ce<sup>3+</sup>) + <sup>4</sup>I<sub>13/2</sub>(Er<sup>3+</sup>) which facilitates the population of <sup>4</sup>I<sub>13/2</sub> of Er<sup>3+</sup> and decreases UC emission. Therefore, based on the forementioned theories, codoping Ca<sup>2+</sup> and Ce<sup>3+</sup> in the crystals would synergistically enhance NIR emission.

In this work, *via* doping impurity  $Ca^{2+}$  ions into the host lattices by substituting  $Gd^{3+}$  ions, we demonstrated the irregular NaGdF<sub>4</sub>:Yb/Er submicrocrystals converted into well-defined submicrorods, and the visible UC and NIR DC emission were enhanced through a facile and effective hydrothermal method. Additionally, benefiting from the highly efficient energy transfer from  $Er^{3+}$  to  $Ce^{3+}$  by co-doping  $Ce^{3+}$ , the NIR DC was further enhanced by about 6.4 times in comparison with that of the NaGdF<sub>4</sub>:Yb/Er counterpart.

## 2. Experimental

#### 2.1 Materials and reagents

Ethylenediamine tetraacetic acid (EDTA > 99.4%) was supplied by Sigma-Aldrich.  $Gd(NO_3)_3 \cdot 6H_2O$  (99.99%),  $Er(NO_3)_3 \cdot 5H_2O$ (99.9%),  $Yb(NO_3)_3 \cdot 5H_2O$  (99.9%), sodium hydroxide (NaOH > 96.0%), ammonium fluoride (NH<sub>4</sub>F > 98.0%), and highly concentrated nitric acid were purchased from Aladdin Chemical Reagent Co. All chemicals were of analytical grade and were used directly as received without further purification, deionized water was used throughout.

#### 2.2 Synthesis of 20% Yb<sup>3+</sup>, 2% Er<sup>3+</sup>:NaGdF<sub>4</sub> submicrocrystals

The rare-earth doped NaGdF<sub>4</sub> (1 mmol) submicrocrystals were synthesized by a hydrothermal method. Firstly, 12.5 ml of aqueous solution containing 0.4 g EDTA and 1.05 ml of NaOH aqueous solution (5.0 M) were mixed under stirring until the solution becomes even. Subsequently, 5 ml of  $Ln(NO_3)_3$  (Ln = Gd, Yb, Er) aqueous solutions (0.2 M), 8 ml of NH<sub>4</sub>F (2.0 M) aqueous solutions and 7 ml dilute nitric acid (1 M) were added to the mixture. After agitating at room temperature for 90 min, the resultant solution was poured into a 50 ml Teflon-lined autoclave and heated subsequently to 190  $^\circ \mathrm{C}$  for 48 h. Finally, the autoclave was cooled to room temperature naturally. The products deposited at the bottom of the vessel were collected by centrifugation, washed with deionized water and ethanol several times, and then dried at 60 °C for 24 h in air. The procedure for the synthesis of the Ca<sup>2+</sup> doped, Ce<sup>3+</sup> doped and Ca<sup>2+</sup>/Ce<sup>3+</sup> codoped 20% Yb<sup>3+</sup>, 2% Er<sup>3+</sup>:NaGdF<sub>4</sub> submicrocrystals were similar to the case of the 20% Yb3+, 2% Er3+:NaGdF4 submicrocrystals.

#### 2.3 Characterization

The X-ray powder diffraction (XRD) patterns were carried out with a powder diffractometer (Japan Rigaku D/max-rB) with Cu Ka radiation ( $\lambda = 0.154$  178 nm). The morphology was studied using a field-emission scanning electron microscope (FESEM) operated at an acceleration voltage of 5 kV (HitachiSU-8220). The NIR luminescence spectroscopy was recorded by a monochromator (Princeton Instrument SP2750) equipped with an InGaAs infrared detector (ACTON), the UC luminescence spectroscopy were measured by a single mode fiber with an Ocean Optics USB4000 spectrometer (optical resolution  $\sim 0.2$  nm) using a continuous 980 nm laser from an semiconduct laser as the excitation source, and the area of the samples that were exposed to the laser radiation was about 1.5 mm<sup>2</sup>. The decay time was measured by a digital phosphor oscilloscope (Tektronix DPO 4032) using the 980 nm laser from an OPO (an optical parametric oscillation, INNOLAS) as the excitation source. All the measurements were implemented at room temperature (RT).

# 3. Results and discussion

#### 3.1 Morphology and crystal structure

It should be pointed out that rare earth doped fluorides with high quality and anisotropic morphology could be synthesized in an appropriately surplus F<sup>-</sup>/Ln<sup>3+</sup> molar ratio.<sup>28-31</sup> In this view, the  $F^{-}/Ln^{3+}$  molar ratio was set to be 16. A series of 20% Yb/2% Er:NaGdF<sub>4</sub> crystals doped with different Ca<sup>2+</sup> and Ce<sup>3+</sup> concentration were synthesized and the corresponding XRD patterns are shown in Fig. 1. XRD patterns (Fig. 1a) suggest that the samples of different Ca<sup>2+</sup> doping concentration are identical with JCPDS Card (no. 27-0699), showing that the Ca<sup>2+</sup> are completely embedded into the crystal lattice of NaGdF4 by replacing the sites of Gd<sup>3+</sup> ions, without finding obvious shifting of diffraction peaks due to the F<sup>-</sup> vacancies and ionic radius difference between Gd<sup>3+</sup> and Ca<sup>2+</sup>.<sup>24</sup> Fig. 1b shows the X-ray diffraction patterns of 20% Yb/2% Er:NaGdF4 crystals doped with different Ce3+ concentration. No additional peaks are observed, indicating that the doping Ce<sup>3+</sup> ions have a negligible effect on the phase structure and Ce<sup>3+</sup> ions have substituted the Gd<sup>3+</sup> sites in the NaGdF<sub>4</sub> host. Notably, the X-ray diffraction patterns of 20% Yb/2% Er:NaGdF<sub>4</sub> crystals codoped with 25%  $Ca^{2+}$  and 2%  $Ce^{3+}$  are also given in Fig. 1b, which can be still indexed to the  $\beta$ -NaGdF<sub>4</sub> phase. The schematic diagram of  $\beta$ -NaGdF<sub>4</sub> crystal structure and coordination environment of Na<sup>+</sup>/ Gd<sup>3+</sup> ions are shown in Fig. 1c. There are three types of cationic sites in the unit cell of β-NaGdF<sub>4</sub>: a six-fold coordinated one occupied by Na<sup>+</sup> and vacancies, a nine-fold coordinated position occupied by Gd<sup>3+</sup>, and another nine-fold coordinated site occupied randomly by Na<sup>+</sup> and Gd<sup>3+</sup>. The two different Gd<sup>3+</sup> sites are coordinated in the form of tricapped trigonal prisms.<sup>32</sup>

FESEM were then carried out to study the morphology and size of NaGdF<sub>4</sub>:20% Yb/2% Er samples doped with different Ca<sup>2+</sup> and Ce<sup>3+</sup> doping concentrations. Fig. 2a presents the FESEM image of the NaGdF<sub>4</sub>:20% Yb/2% Er submicrocrystals without Ca<sup>2+</sup> doping and shows irregular microrods. Notably,



Fig. 1 XRD patterns of the NaGdF<sub>4</sub>:xCa/yCe/20Yb/2Er samples, (a) x = 0%, 20%, 25%, 30%, y = 0; (b) x = 0, y = 1%, 2%, 3%, 4%. (c) Schematic illustration of  $\beta$ -NaGdF<sub>4</sub> structure and coordination environment of the Na<sup>+</sup>/Gd<sup>3+</sup>.

many cracks are observed on the surface, which could be ascribed to the microrods deriving from decreasing the core of spherical aggregates and extruding between the growing microrods.<sup>33</sup> Interestingly, once doped 20% Ca<sup>2+</sup> in the NaGdF<sub>4</sub>:20% Yb/2% Er sample, the crystals (Fig. 2b) exhibit uniform hexagonal submicrorods, although with a wide size distribution. Further increasing the doping content of Ca<sup>2+</sup> results in a more even size distribution. Furthermore, when the crystal size is denoted as "length × radius", the mean size of NaGdF<sub>4</sub>:xCa/20Yb/2Er (x = 0%, 20%, 25%, 30%) crystals are measured to be 0.38 × 0.96, 0.24 × 1.26, 0.21 × 1.34 and 0.33 × 1.82 µm, respectively. Without the help of Ca<sup>2+</sup> doping, the morphology of NaGdF<sub>4</sub>:xCe/20Yb/2Er (x = 1%, 2%, 3%, 4%)



Fig. 2 FESEM images of NaGdF<sub>4</sub>:20% Yb/2% Er submicrocrystals doped with (a) 0% Ca<sup>2+</sup>, (b) 20% Ca<sup>2+</sup>, (c) 25% Ca<sup>2+</sup>, (d) 30% Ca<sup>2+</sup>, (e) 2% Ce<sup>3+</sup>, (f) 2% Ce<sup>3+</sup>, 25% Ca<sup>2+</sup>.

crystals still inherit irregular submicrorods as that of NaGdF<sub>4</sub>:20Yb/2Er, the typical FESEM image of NaGdF<sub>4</sub>:2Ce/ 20Yb/2Er crystal is shown in Fig. 2e. With codoping of 25%  $Ca^{2+}$  and 2%  $Ce^{3+}$ , the sample keep highly uniform submicrorods (Fig. 2f).

Based on the results stated above, the effect induced by Ca<sup>2+</sup> doping on the morphology evolution of NaGdF<sub>4</sub> submicrocrystals is proposed, as schematically shown in Fig. 3. First of all, it is essential to have a full understanding of the crystal growth of NaGdF<sub>4</sub> submicrocrystals without Ca<sup>2+</sup> doping. As is well known, hexagonal NaGdF<sub>4</sub> has a very close crystalline structure with hexagonal NaYF<sub>4</sub>, so they may undergo a same crystal growth kinetic process in the similar hydrothermal condition.31 The irregular NaGdF4 submicror-ods with cracked surface were obtained due to two main factors. One is that final submicrorods originate from decreasing the core of spherical aggregates and extruding between the growing submicrods.33 And another one is that the fast growth rate of the top/bottom planes would hinder the continuing growth of six energetically equivalent prismatic side planes.<sup>29,34</sup> Once upon doping  $Ca^{2+}$  in the reaction solution, extra  $F^-$  ions are remaining in system due to charge compensation and a transient electric dipole with the positive pole pointing outward is also formed on the grain surface.<sup>24,35,36</sup> Both of them accelerate the diffusion of F<sup>-</sup> ions in the system under the control of monomer diffusion to the grain surface by attractive interaction,<sup>36,37</sup> finally facilitating the anisotropic growth of NaGdF<sub>4</sub> submicrorods. Hence,



Fig. 3 Schematic illustration of possible mechanism of  $Ca^{2+}$  doping and its effect on morphology evolution of NaGdF<sub>4</sub> submicrocrystals.

along with increasing  $Ca^{2+}$  doping content, the surface is becoming more smooth and the size distribution more even. It should be noting that the sharp ends of NaGdF<sub>4</sub> crystals tend to be more flat ends, which is indirect evidence of F<sup>-</sup> concentration increasing only induced by Ca<sup>2+</sup> doping.<sup>38</sup>

#### 3.2 Optical properties

Fig. 4a shows the visible UC emission spectra of the NaGdF<sub>4</sub>:20% Yb/2% Er submicrocrystals doped with different Ca<sup>2+</sup> concentrations, which are recorded under 980 nm laser excitation with the pump power of 150 mW. It is observed that there are three UC bands, centred at 519, 537, and 652 nm, which are ascribed to  ${}^{2}H_{11/2} \rightarrow {}^{4}I_{15/2}$  (519 nm),  ${}^{4}S_{3/2} \rightarrow {}^{4}I_{15/2}$ (537 nm),  ${}^{4}F_{9/2} \rightarrow {}^{4}I_{15/2}$  (652 nm), respectively. Meanwhile, an obvious enhancement of the UC emission is observed upon 20% Ca<sup>2+</sup> doping. The enhancement reaches the most at 25% Ca<sup>2+</sup> doping, then declining with further increasing the Ca<sup>2+</sup> concentration to 30%. Furthermore, the integrated visible UC emission intensity of crystals doped with 25% Ca<sup>2+</sup> is about 5.1 times higher than that of the crystals without  $Ca^{2+}$  doping. To investigate the effect of Ca<sup>2+</sup> doping on the UC emission, we first determined the number of photons required for the red and green luminescence intensity, which obey the following relationship with the pumping power:39

$$I_{\rm up} = P^n \tag{1}$$

where  $I_{up}$  is the UC emission intensity, P is the infrared pumping power, and *n* is the number of pumping photons required for emitting one UC photon. From the logarithmic plots of the UC luminescence intensity as a function of the excitation power (Fig. 4c and d), it can be concluded that both green and red emission are two-photon absorption process in the presence and absence of Ca<sup>2+</sup>, indicating that Ca<sup>2+</sup> doping does not alter the UC mechanism. The gradual enhancement in UC luminescence induced by Ca<sup>2+</sup> doping is ascribed to two factors including lowering the local crystal field symmetry around rare earth ions and improving the morphology of the NaGdF<sub>4</sub> submicrocrystals. However, when  $Ca^{2+}$  doping concentration is beyond 25%, more F<sup>-</sup> vacancies are forming, which reduce the UC emission intensity.24,36 Based on these results, we expect that the 1530 nm emission intensity of Er<sup>3+</sup> ion could also be enhanced upon doping Ca<sup>2+</sup>.

Fig. 5 shows the NIR emission spectra of the submicrocrystals, which are recorded at the pump power of 270 mW. Obviously, the characteristic emission peak centered at 1535 nm is attributed to the  ${}^{4}I_{13/2} \rightarrow {}^{4}I_{15/2}$  transitions of Er<sup>3+</sup> ions. The NIR emission intensity increases with Ca<sup>2+</sup> dopant concentrations from 0% to 25% before declining as Ca<sup>2+</sup> dopant concentration is increased to 30% (Fig. 5a). The integrated NIR DC emission intensity shows an identical trend to that of the visible UC emission. Therefore, the optimum Ca<sup>2+</sup> dopant concentration is determined to be 25%. Next, to further



Fig. 4 UC emission spectra of NaGdF<sub>4</sub>:20Yb/2Er/xCa (x = 0%, 20%, 25%, 30%) under 980 nm laser excitation. (b) The corresponding photographs of the submicrocrystals dispersed in water. log–log plots of the UC emission intensity against laser excitation power for NaGdF<sub>4</sub>:20Yb/2Er (c), and NaGdF<sub>4</sub>:25Ca/20Yb/2Er (d).



Fig. 5 NIR emission spectra of the sample NaGdF<sub>4</sub>:xCa/yCe/20% Yb/ 2% Er, (a) x = 0%, 20%, 25%, 30%, y = 0; (b) x = 0, y = 1%, 2%, 3%, 4% under 980 nm laser excitation.

investigate the effect of  $Ce^{3+}$  concentration on the NIR emission properties, we systematically investigated the NIR emission spectra of NaGdF<sub>4</sub>:20Yb/2Er/xCe (x = 1%, 2%, 3%, 4%) crystals obtained upon excitation at 980 nm and the results are summarized in Fig. 5b. As the concentration of  $Ce^{3+}$  ions increases from 0 to 2%, the NIR emission significantly increases and reaches the most. The enhanced NIR emission arises from the efficient non-radiative phonon-assisted energy transfer between the  ${}^{4}I_{11/2} \rightarrow {}^{4}I_{13/2}$  transition of  $Er^{3+}$  ions and the  ${}^{2}F_{5/2}$  $\rightarrow {}^{2}F_{7/2}$  transition of  $Ce^{3+}$  ions, which improves the branching ratio of NIR emission and suppress the visible emission by



Fig. 6 Energy level diagram of  $Yb^{3+}$  ion,  $Er^{3+}$  ion,  $Ce^{3+}$  ion, as well as the relevant transitions under the 980 nm laser excitation.

altered the UC pathways.<sup>26,27</sup> All these transitions are illustrated in an energy levels diagram in Fig. 6.

It is essential to compare the NIR emission intensity of samples doped with the optimum Ca<sup>2+</sup> and Ce<sup>3+</sup> dopant concentration. Through measuring the integrated NIR emission intensity (Fig. 7a), the NIR emission of the 20Yb/2Er:NaGdF<sub>4</sub> submicrorods doped with 25% Ca<sup>2+</sup> and 2% Ce<sup>3+</sup> is about 6.4 times higher than that of 20Yb/2Er:NaGdF<sub>4</sub> submicrocrystals. Notably, the enhanced factor of the sample doped with 25% Ca<sup>2+</sup> and 2% Ce<sup>3+</sup> is only 2.3, 2.7, respectively. These results suggest that codoping  $Ca^{2+}/Ce^{3+}$  can greatly enhance the NIR emission intensity. Fig. 7b shows the log-log plots of the NIR emission intensity against laser excitation power of the submicrocrystals doped with no extra ions, 25% Ca<sup>2+</sup>, 2% Ce<sup>3+</sup>, and coped with 25%  $Ca^{2+}/2\%$   $Ce^{3+}$ , the experimental data were fitted well with a linear relationship. The quasi-linear power dependence of 1530 nm emission in submicrocrystals doped without Ce<sup>3+</sup> and quasi-quadratic power dependence in submicrocrystals doped with Ce<sup>3+</sup> can be observed. The different character of the powerdependent luminescence for the  ${}^{4}I_{13/2}$  manifold is possibly due to the competition between UC and linear decay.40

To further characterize the NIR emitting properties of the obtained samples, the fluorescence decay curves of the 1530 nm emission for the crystals are shown in Fig. 8. To obtain the decay constants, the luminescence decay curves were fitted by a biexponential equation,



Fig. 7 NIR emission spectra (a) and log–log plots of the NIR emission intensity against laser excitation power (b) of samples single doped with no extra ions,  $25\% \text{ Ca}^{2+}$ ,  $2\% \text{ Ce}^{3+}$ , and coped with  $25\% \text{ Ca}^{2+}/2\% \text{ Ce}^{3+}$ , the experimental data were fitted well with a linear relationship.

8



Fig. 8 The decay curves of Er<sup>3+</sup> 1530 nm emission wavelength upon 980 nm excitation.

$$I(t) = A_1 \times \exp\left(-\frac{t}{\tau_1}\right) + A_2 \times \exp\left(-\frac{t}{\tau_2}\right)$$
(2)

where I(t) is the luminescence intensity for the 1530 nm emission,  $A_1$  and  $A_2$  are constants, t is the time, and  $\tau_1$  and  $\tau_2$  are the corresponding lifetimes for the bi-exponential components. The possible explanations for the double exponential decay of the luminescence could be attributed to two luminescence centers in the host. The ions on the outside of the particles are more susceptible to the defects and high energy vibrational oscillators of ligands or impurities, leading to a larger rate of non-radiative transitions. Therefore, the lifetime of radiative transition of activator ions on the surface  $(\tau_2)$  is much lower than that in core sites  $(\tau_1)$ . And there is a fact that the decay time can characterize the contributions of both radiative and nonradiative relaxation pathways from a particular excited state. In general, the increased decay time indicates high emission efficiency, which is most likely due to the increased radiative transitions or suppressed non-radiative losses.27,41,42 The average fluorescence decay time ( $\tau_{ave}$ ) is obtained using the following expression,43

$$\tau_{\text{ave}} = \frac{A_1 \tau_1^2 + A_2 \tau_2^2}{A_1 \tau_1 + A_2 \tau_2} \tag{3}$$

The estimated decay time increases from ~609.2  $\mu$ s for NaGdF<sub>4</sub>:20% Yb/2% Er to ~1319.6  $\mu$ s for crystals doped with 20% Ca<sup>2+</sup>, ~1416.1  $\mu$ s for crystals doped with 2% Ce<sup>3+</sup>, and ~2942.5  $\mu$ s for crystals doped with 20% Ca<sup>2+</sup>/2% Ce<sup>3+</sup>, respectively. These results show that Ca<sup>2+</sup>/Ce<sup>3+</sup> codoping can effectively improve the NIR emission efficiency for NaGdF<sub>4</sub>:20% Yb/ 2% Er submicrorods.

## 4. Conclusions

In summary, we have disclosed morphology evolution mechanism and increased visible UC emission intensity of NaGdF<sub>4</sub>:20% Yb/2% Er submicrocrystals induced by Ca<sup>2+</sup> doping. The influence of Ca<sup>2+</sup> and Ce<sup>3+</sup> doping concentration on the NIR emission intensity have been systematically investigated and the optimized Ca<sup>2+</sup> and Ce<sup>3+</sup> doping concentration was 25% and 2%, respectively. The NIR emission intensity was enhanced by ~6.4 fold after introducing both of 25% Ca<sup>2+</sup> and 2% Ce<sup>3+</sup>. The doping of Ca<sup>2+</sup> mainly lowers the local crystal field symmetry around the rare earth and improves the morphology of NaGdF<sub>4</sub>:20% Yb/2% Er submicrocrystals. And the doping of Ce<sup>3+</sup> facilitates the energy transfer between Ce<sup>3+</sup> and Er<sup>3+</sup>. Hence, codoping Ca<sup>2+</sup>/Ce<sup>3+</sup> synergistically enhance the NIR emission intensity. We believe that this novel strategy for simultaneous control of morphology and improving the NIR emission of rare earth doped nano/microcrystals may expand the application in IR-related miniaturization and integration of optoelectronics.

# Conflicts of interest

There are no conflicts to declare.

# Acknowledgements

The authors would like to acknowledge funding support from the National Natural Science Foundation of China (NSFC) (11574221) and "the Fundamental Research Funds for the Central Universities" (2016SCU11003).

### Notes and references

- T. Soukka, K. Kuningas, T. Rantanen, V. Haaslahti and T. Lövgren, J. Fluoresc., 2005, 15, 513–528.
- 2 F. Wang and X. Liu, Chem. Soc. Rev., 2009, 38, 976-989.
- 3 X. Xie, N. Gao, R. Deng, Q. Sun, Q.-H. Xu and X. Liu, *J. Am. Chem. Soc.*, 2013, **135**, 12608–12611.
- 4 X. Zhu, Q. Su, W. Feng and F. Li, *Chem. Soc. Rev.*, 2017, **46**, 1025–1039.
- 5 T. Wang, H. Yu, C. K. Siu, J. Qiu, X. Xu and S. F. Yu, ACS Photonics, 2017, 4, 1539–1543.
- 6 R. Dey, A. Pandey and V. K. Rai, *Spectrochim. Acta, Part A*, 2014, **128**, 508–513.
- 7 P. Du and J. S. Yu, Chem. Eng. J., 2017, 327, 109-119.
- 8 D. Chen, M. Xu and P. Huang, *Sens. Actuators, B*, 2016, 231, 576–583.
- 9 D. Chen, M. Xu, P. Huang, M. Ma, M. Ding and L. Lei, J. Mater. Chem. C, 2017, 5, 5434–5443.
- 10 K. Korthout, P. F. Smet and D. Poelman, *Appl. Phys. Lett.*, 2009, **94**, 051104.
- 11 J. D. Bradley and M. Pollnau, *Laser Photonics Rev.*, 2011, 5, 368–403.
- 12 N. Mais, J. P. Reithmaier, A. Forchel, M. Kohls, L. Spanhel and G. Müller, *Appl. Phys. Lett.*, 1999, **75**, 2005–2007.
- 13 J. Wang, J. Hu, D. Tang, X. Liu and Z. Zhen, *J. Mater. Chem.*, 2007, **17**, 1597–1601.
- F. Rivera-López, P. Babu, L. Jyothi, U. R. Rodríguez-Mendoza,
  I. R. Martín, C. K. Jayasankar and V. Lavín, *Opt. Mater.*, 2012,
  34, 1235–1240.
- 15 Y. P. Fang, A. W. Xu, L. P. You, R. Q. Song, J. C. Yu, H. X. Zhang, Q. Li and H. Q. Liu, *Adv. Funct. Mater.*, 2003, 13, 955–960.

- 16 G. Gao, C. Zhang, Z. Zhou, X. Zhang, J. Ma, C. Li, W. Jin and D. Cui, *Nanoscale*, 2013, 5, 351–362.
- 17 A. Shalav, B. S. Richards, T. Trupke, K. W. Krämer and H. U. Güdel, *Appl. Phys. Lett.*, 2005, **86**, 013505.
- 18 D. Chen and P. Huang, Dalton Trans., 2014, 43, 11299-11304.
- 19 M. Mondal, V. K. Rai and C. Srivastava, *Chem. Eng. J.*, 2017, 327, 838–848.
- 20 D. Chen, L. Liu, P. Huang, M. Ding, J. Zhong and Z. Ji, *J. Phys. Chem. Lett.*, 2015, **6**, 2833–2840.
- 21 D. Chen and Y. Wang, Nanoscale, 2013, 5, 4621-4637.
- 22 A. K. Singh, S. K. Singh and S. B. Rai, *RSC Adv.*, 2014, 4, 27039–27061.
- 23 X. Wang, Y. Bu, Y. Xiao, C. Kan, D. Lu and X. Yan, *J. Mater. Chem. C*, 2013, **1**, 3158–3166.
- 24 L. Lei, D. Chen, J. Xu, R. Zhang and Y. Wang, *Chem.–Asian J.*, 2014, **9**, 728–733.
- 25 L. Mukhopadhyay and V. K. Rai, New J. Chem., 2017, 41, 7650-7661.
- 26 X. Gao, X. Liu, Q. Wen, X. Yang and S. Xiao, *J. Appl. Phys.*, 2014, **116**, 173105.
- 27 X. Zhao and M. C. Tan, J. Mater. Chem. C, 2015, 3, 10207– 10214.
- 28 Y. Wang, R. Cai and Z. Liu, *CrystEngComm*, 2011, **13**, 1772–1774.
- 29 X. Liang, X. Wang, J. Zhuang, Q. Peng and Y. Li, *Adv. Funct. Mater.*, 2007, **17**, 2757–2765.
- 30 L. Tian, L. Tan, Q. Sun, S. Xiang, Q. Xiao, J. Tang and G. Zhu, J. Rare Earths, 2012, 30, 1260–1264.

- 31 T. Zhou, X. Jiang, C. Zhong, X. Tang, S. Ren, Y. Zhao, M. Liu, X. Lai, J. Bi and D. Gao, *J. Lumin.*, 2016, **175**, 1–8.
- 32 M. Karbowiak, A. Mech, A. Bednarkiewicz, W. Stręk and L. Kępiński, *J. Phys. Chem. Solids*, 2005, **66**, 1008–1019.
- 33 F. Tao, F. Pan, Z. Wang, W. Cai and L. Yao, *CrystEngComm*, 2010, **12**, 4263–4267.
- 34 Z. Chen, Z. Liu, Y. Liu, K. Zheng and W. Qin, *J. Fluorine Chem.*, 2012, **144**, 157–164.
- 35 D. Chen, Y. Yu, F. Huang, P. Huang, A. Yang and Y. Wang, *J. Am. Chem. Soc.*, 2010, **132**, 9976–9978.
- 36 L. Lei, D. Chen, P. Huang, J. Xu, R. Zhang and Y. Wang, *Nanoscale*, 2013, 5, 11298–11305.
- 37 X. Peng, J. Wickham and A. Alivisatos, J. Am. Chem. Soc., 1998, 120, 5343–5344.
- 38 M. Ding, D. Chen, S. Yin, Z. Ji, J. Zhong, Y. Ni, C. Lu and Z. Xu, *Sci. Rep.*, 2015, 5, 12745.
- 39 Z. Xiong, Y. Yang and Y. Wang, *RSC Adv.*, 2016, **6**, 75664–75668.
- 40 D. Xu, C. Liu, J. Yan, S. Yang and Y. Zhang, *J. Phys. Chem. C*, 2015, **119**, 6852–6860.
- 41 J. W. Stouwdam and F. C. J. M. van Veggel, *Nano Lett.*, 2002, 2, 733–737.
- 42 J. Wu, S. Shi, X. Wang, J. Li, R. Zong and W. Chen, *J. Mater. Chem. C*, 2014, **2**, 2786–2792.
- 43 T. Fujii, K. Kodaira, O. Kawauchi, N. Tanaka, H. Yamashita and M. Anpo, *J. Phys. Chem. B*, 1997, **101**, 10631–10637.