




Cite this: *RSC Adv.*, 2017, 7, 43380

# Surface modification and magnetic alignment of hexagonal boron nitride nanosheets for highly thermally conductive composites†

Feng Yuan,<sup>a</sup> Weicheng Jiao, \*<sup>a</sup> Fan Yang,<sup>a</sup> Wenbo Liu,<sup>b</sup> Zhonghai Xu<sup>a</sup> and Rongguo Wang\*<sup>a</sup>

With the current development of microelectronic technology, thermally conductive and electrically insulating encapsulation materials are in urgent demand. Hexagonal boron nitride nanosheets (BNNs) possess a highly anisotropic thermal property. Therefore, the thermal conductivity of the BNNs-based composites can be dramatically increased through the orientation of fillers. However, it is still difficult to well align BNNs at high loadings due to the intensive aggregation. Herein, highly ordered thermoplastic polyurethane elastomer (TPU)/BNNs composites are successfully fabricated by the combination of filler modification and magnetic alignment. The effective covalent modification with 2,4-tolylene diisocyanate (TDI) greatly increases the dispersibility of fillers, thus making it easy to well orient BNNs at high loadings. The highly aligned fillers result in much higher in-plane thermal conductivity than the composites filled with disordered or less-ordered unmodified BNNs. The thermal conductivity is as high as  $5.15 \text{ W m}^{-1} \text{ K}^{-1}$  at 30 wt% loading. Moreover, the composite simultaneously exhibits low dielectric constant, low dielectric dissipation factor and excellent thermomechanical properties. These results reveal the promising application of such highly-ordered composites in advanced electronic packing.

Received 2nd August 2017  
 Accepted 2nd September 2017

DOI: 10.1039/c7ra08516h

[rsc.li/rsc-advances](http://rsc.li/rsc-advances)

## 1. Introduction

With the continued trend toward faster, higher integration and miniaturization of modern electronics, considerable heat is accumulated. Thermal management has thus emerged as a critical problem to the performance and reliability of electronic devices. Polymer composites filled with highly thermally conductive fillers have been demonstrated to be effective thermal management materials. Many inorganic fillers, such as AlN,<sup>1-3</sup> Al<sub>2</sub>O<sub>3</sub>,<sup>4,5</sup> SiC,<sup>6,7</sup> and SiO<sub>2</sub>,<sup>8</sup> *etc.*, are widely used as thermally conductive fillers. With the development of carbon nanomaterials, carbon nanotubes,<sup>9-12</sup> and graphene<sup>13-16</sup> have also been widely employed to fabricate heat conductive composites owing to their super-high thermal conductivity. However, the high electrical conductivity of such carbon nanomaterials severely limits their applications in certain areas where electrical insulation is concerned. Being structurally analogous to graphene, hexagonal boron nitride nanosheets (BNNs) have drawn far attention in the microelectronic

industry due to their uniquely thermally conductive but electrically insulating properties.<sup>17</sup> Moreover, BNNs show a higher thermal conductivity and a lower density in comparison with the above ceramic fillers.<sup>18</sup> Therefore, BNNs perform as a preferential selection for fabricating highly thermally conductive but insulating composites.

BNNs have been widely applied in composites for improving thermal conductivity. However, the improvement in thermal conductivity is usually limited in previous reports.<sup>19,20</sup> Besides the intrinsic properties of filler, the performances of composite are also closely associated with filler dispersion,<sup>21</sup> alignment,<sup>22</sup> and interfacial property.<sup>3,23</sup> BNNs occurs as typical anisotropic nanosheets, which show a super high in-plane thermal conductivity of  $2000 \text{ W m}^{-1} \text{ K}^{-1}$ , whereas a very low through-plane thermal conductivity of  $100 \text{ W m}^{-1} \text{ K}^{-1}$ .<sup>17,24</sup> Therefore, it is widely accepted that the orientation of BNNs along the heat flux can significantly increase the thermal conductivity of the composite. Recently, several approaches, such as electrostatic flocking,<sup>25</sup> doctor blading,<sup>18,26</sup> stretching,<sup>27</sup> chemical vapor deposition,<sup>11</sup> freeze-casting,<sup>28</sup> tape-casting,<sup>29</sup> and magnetic field,<sup>24,30-34</sup> have been developed to construct aligned microstructures in composites. Among these fillers array strategies, magnetic alignment is an attractive method duo to easy operation, low cost, and the possibility of aligning filler at arbitrary directions.<sup>32,34</sup> However, it is still a challenging issue to well align fillers at high filler loadings due to the severe aggregation and high viscosity.<sup>26,30</sup>

<sup>a</sup>Science and Technology on Advanced Composites in Special Environments Laboratory, Harbin Institute of Technology, Harbin 150086, China. E-mail: xiaojiao458@163.com; wrq@hit.edu.cn

<sup>b</sup>School of Materials Science and Engineering, Harbin Institute of Technology, Harbin 150001, China

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra08516h






Fig. 1 Schematic illustration of the fabrication process of highly ordered mBNNNS-TDI/TPU composite.

In addition to the orientation of the anisotropic fillers, the homogeneous dispersion as well as the strong interfacial interaction between BNNNSs and polymer matrices are both critical for sufficiently taking advantage of the super high in-plane thermal conductivity of BNNNSs. Many efforts have been devoted to surface modification of BNNNSs to increase the dispersion and interfacial compatibility of BNNNSs within polymer matrices.<sup>21,35–37</sup> However, the improvement of thermal conductivity is still limited due to the inadequate surface modification and deteriorated intrinsic thermal conductivity of BNNNSs during modification.

Elastomers have been considered to be materials of choice in electronic packaging systems, owing to excellent properties, including high elasticity, abrasion resistance and easy processibility. In this paper, based on the combination of filler modification and magnetic orientation, highly-ordered thermoplastic polyurethane elastomer (TPU)/BNNNSs composites with high thermal conductivity are successfully prepared. The whole preparation process is schematically illustrated in Fig. 1. Firstly, the BNNNSs with magnetic response (mBNNNSs) are prepared through the introduction of magnetic Fe<sub>3</sub>O<sub>4</sub> nanoparticles on their surfaces. By utilizing the hydroxyl groups (–OH) on the Fe<sub>3</sub>O<sub>4</sub> surfaces, mBNNNSs are further covalently modified with 2,4-tolylene diisocyanate (TDI) molecules. Finally, due to the homogeneous dispersibility of fillers, the highly ordered BNNNS-TDI/TPU composite can be obtained by applying a rotating magnetic field during resin curing. By virtue of high orientation degree of fillers and the strong interfacial interaction, the mBNNNS-TDI/TPU composites possess the simultaneous properties of high thermal conductivity, low dielectric constant, low dielectric dissipation factor, as well as excellent thermomechanical performances, which are envisaged to be particularly valuable for advanced electronic packaging.

## 2. Experimental

### 2.1 Materials

4,4'-Phenyl methane diisocyanate (MDI), 1,4-butanediol (BDO), ferrous chloride tetrahydrate (FeCl<sub>2</sub>·4H<sub>2</sub>O), sodium hydroxide (NaOH), hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>), 2,4-tolylene diisocyanate (TDI), organotin catalyst (DBTDL) and all organic solvents were purchased from J&K Chemicals. Poly(butylene adipate) glycol

(PBA) was kindly supplied by Qingdao Xinyutian Chemical Co., Ltd, China. Deionized water was used throughout all experiments, and all reagents were used directly, without any purification.

### 2.2 Preparation of magnetically responsive BNNNSs (mBNNNSs)

The mBNNNSs were prepared through an *in situ* generation method, in which Fe<sub>3</sub>O<sub>4</sub> nanoparticles were nucleated on the surface of BNNNSs by oxidizing the aqueous Fe(OH)<sub>2</sub> suspension at room temperature. Firstly, 2 g BNNNSs (prepared by the method reported in our previous literature,<sup>38</sup> 500 nm to 2 μm in diameter, about 2 nm in thickness, Fig. S1†) were dispersed into 100 ml deionized water through bath sonication for 30 h at 25 °C. 1 g FeCl<sub>2</sub>·4H<sub>2</sub>O was then added into the above solution under rapid mechanical stirring. At this stage, the positive Fe ions are attracted onto the BNNNSs surface. Subsequently, 120 ml NaOH aqueous solution (0.1 mol l<sup>-1</sup>) was slowly added to form an dark-green Fe(OH)<sub>2</sub> colloidal solution. Finally, this colloid was oxidized into magnetic Fe<sub>3</sub>O<sub>4</sub> nanoparticles by H<sub>2</sub>O<sub>2</sub> at room temperature. As a result, the white BNNNSs change into black particles (Fig. S2†). After vigorous bath-sonication for 2 h, the obtained black product was subjected to vacuum-assisted filtration using a 0.45 μm pore size membrane to remove free Fe<sub>3</sub>O<sub>4</sub> nanoparticles. The final product was re-dispersed in water through sonication and collected by magnetic separation, followed by vacuum drying.

### 2.3 Surface modification of mBNNNSs

1 g mBNNNSs was dispersed into 200 ml dry toluene by ultrasonication for 30 min at room temperature. Then, 100 mg TDI and three drops of organotin catalysts were added. The mixture was stirred for 8 h at 80 °C under a steady nitrogen flow. After the reaction, the modified mBNNNSs particles, named as mBNNNS-TDI, were centrifuged, washed by acetone and vacuum dried at 60 °C for 8 h.

### 2.4 Fabrication of highly ordered composites with mBNNNS-TDI

MDI, PBA and BDO were used to synthesize hydroxyl-terminated TPU resin and the highly ordered mBNNNS-TDI/TPU composites were fabricated through magnetic orientation strategy, as the following process: firstly, mBNNNS-TDI with various weights were dispersed into appropriate amount of *N,N*-dimethylformamide (DMF) and sonicated for 2 h. At the same time, PBA were vacuum dehydrated for 2 h at 100–120 °C. After cooling to 70–80 °C, the mBNNNS-TDI suspension was slowly dropped into the cooled PBA liquid within 2 h under rapid stirring. Then, the required quantity of MDI was added to trigger prepolymerization under N<sub>2</sub> protection, until the –NCO % content approached the predetermined value. Finally, BDO was introduced to start the expanding chain process (the molar ratio of PBA : MDI : BDO was set at 1 : 1.98 : 1). The mixture was further stirred vigorously for 30 min. After that, the solution was poured into a Teflon mold and then placed into a horizontal magnetic field for 5 h at room temperature. The sample was further dried at



60 °C for 12 h without a magnetic field and followed by curing at 120 °C for 24 h.

## 2.5 Characterization

Powder X-ray diffraction (XRD) detection was carried on a PANalytical diffractometer using Cu K $\alpha$  radiation. Raman study was taken on a confocal Raman spectroscopic system (Renishaw, InVia) with a 532 nm excitation laser. Fourier transform infrared (FT-IR) spectra was obtained using an AVATAR 360 Fourier transform infrared spectrometer, with the range of 500–4000 cm<sup>-1</sup>. Thermal gravimetric analysis (TGA) was conducted on a thermoanalyzer (SDT Q600 V20.9 Build 20, TA Instruments) with a heating rate of 10 °C min<sup>-1</sup> under a nitrogen atmosphere. Transmission electron microscope (TEM) characterization was performed on a FEI Tecnai G2 F20 transition electron microscope. The TEM specimen was prepared by evenly dispersing Fe<sub>3</sub>O<sub>4</sub> nanoparticles or mBNNs into a mixed solvent of deionized water and ethanol through sonication, and then dropping a small volume of the dispersion on a carbon coated copper grid. Scanning electron microscopy (SEM) observation was conducted on a FEI Helios Nanolab 600i scanning electron microscope. Differential scanning calorimetry analyses (DSC) were obtained by using a 200 F3 instrument (NETZSCH, Germany) at a heating rate of 10 °C min<sup>-1</sup> under a nitrogen atmosphere. The magnetic properties of Fe<sub>3</sub>O<sub>4</sub> nanoparticles, mBNNs and mBNNs-TDI were studied through using a vibrating scanning magnetometer (VSM, Lake Shore VSM 7307). The in-plane thermal conductivities of the samples were tested on a Hot Disk thermal analyzer (Hot Disk AB, Uppsala, Sweden). At least three separate tests were carried on each sample, and the average value was reported. The dielectric properties of the blank TPU resin and corresponding composites were detected by using a Novocontrol Concept 40 broadband dielectric spectroscopy at room temperature. Before measurements, gold nanoparticles were deposited on both surfaces of the circular specimens. The thermal-mechanical properties of TPU resin and various composites were investigated using a dynamic mechanical analyzer (DMA, Q800, TA Instruments) at the stretch mode with at a heating rate of 3 °C min<sup>-1</sup>.

## 3. Results and discussion

### 3.1 Characterization of mBNNs

During powerful sonication of BNNs, a large number of defects, including dislocations, topological defects and vacancies, can be formed on the surface.<sup>39</sup> To reduce the energy at defect positions, the highly reactive defects will capture -OH groups in aqueous solution.<sup>40</sup> As revealed by XPS analysis (Fig. 2a), apart from the typical B-N peak (190.3 eV), a small peak attributed to the B-O bond also appears at 191.1 eV. This result is in good agreement with the result reported by Sun *et al.*<sup>41</sup> and implies the successful introduction of a small number -OH groups on BNNs surface. As a result, it is rational to speculate that the positive Fe ions would be attracted onto the BNNs surface through the electrostatic attraction between Fe<sup>2+</sup>

and -OH, thus forming the initial Fe<sub>3</sub>O<sub>4</sub> “seeds”.<sup>41</sup> Fig. 2b shows the XPS spectra of BNNs and mBNNs. It is noticed that a signal assigned to Fe (2p<sub>1/2</sub>, 2p<sub>3/2</sub>) appears and an increase in the intensity of the O1s peak in the spectrum of mBNNs, indicating the successful formation of Fe<sub>3</sub>O<sub>4</sub> on the BNNs surface. It is worth noting that the peaks of Fe2p<sub>1/2</sub> (724.3 eV) and Fe2p<sub>3/2</sub> (710.6 eV) are both shifted to lower binding energies in comparison with the reported values (724.8 eV and 711.2 eV).<sup>42</sup> which is consistent with the result reported by Yao *et al.* who carried out XPS detection on BNNs-Ag hybrid<sup>43</sup> and reveals the interaction between Fe<sub>3</sub>O<sub>4</sub> nanoparticles and BNNs. The successful synthesis of Fe<sub>3</sub>O<sub>4</sub> nanoparticles on the BNNs surface is further verified by the XRD analyses of BNNs and mBNNs (Fig. 2c). Clearly, compared with BNNs, the XRD spectrum of mBNNs exhibits four new peaks, which appear at  $2\theta = 30.21^\circ, 35.51^\circ, 57.43^\circ$  and  $62.91^\circ$ , respectively. In accordance with the reference date (JCPDS card no. 19-0629), these feature peaks are attributed to the (220), (311), (511) and (440) planes of Fe<sub>3</sub>O<sub>4</sub>, respectively. Also it could be seen that no impurity peaks are detected, revealing the high purity of the as-obtained mBNNs. The TEM characterization reveals that the as-prepared Fe<sub>3</sub>O<sub>4</sub> is nanosphere-like particles with an average particle size of about 23 nm. Furthermore, due to the size effect and surface adsorption of nanoparticles, the Fe<sub>3</sub>O<sub>4</sub> nanoparticles are severely agglomerated together (Fig. 2d). Fig. 2e clearly confirms that the successful formation of a hybrid filler, in which the surface of BNNs is covered with spherical Fe<sub>3</sub>O<sub>4</sub> nanoparticles, a result that is consistent with the analyses of XPS and XRD. In addition, as revealed by TEM image, after strong ultrasonic dispersion (200 W, 2 h) of mBNNs during the preparation of TEM specimen, Fe<sub>3</sub>O<sub>4</sub> nanoparticles are detected only on the BNNs surface, without any free nanoparticles. This result implies strong interaction between Fe<sub>3</sub>O<sub>4</sub> nanoparticles and BNNs.

It should also be noted that, due to the size effect, there is a large amount of -OH groups on the surfaces of Fe<sub>3</sub>O<sub>4</sub> nanoparticles in aqueous solution, as confirmed by FTIR analysis (Fig. 2f). The absorption peak resulting from Fe-O stretching vibration is observed at 586 cm<sup>-1</sup>. In addition, a broadened peak assigned to -OH stretching vibration, and the one corresponding to the bending vibration of -OH are also observed at  $\sim 3200$  cm<sup>-1</sup> and at 1392 cm<sup>-1</sup>, respectively. An small peak at 1635 cm<sup>-1</sup> is the result of O-H<sup>+</sup> bending vibration for hydrogen bond. All these results reveal the presence of -OH functional groups on Fe<sub>3</sub>O<sub>4</sub> surface, which make it possible to covalently modify mBNNs, as discussed below.

### 3.2 Characterization of mBNNs-TDI

As is well known, the thermal transport performance of composites is closely associated with the dispersibility and interfacial compatibility of filler within resin matrices. However, the low chemical activity of the BNNs usually results in a poor interfacial interaction between BNNs and polymer matrices. Therefore, surface modification is necessary to enhance the adhesion of BNNs to resin matrix. However, the reliable and effective approaches for BNNs surface






Fig. 2 (a) Narrow B1s scan of BNNs. (b) XPS spectra of BNNs and mBNNs. Inset is the Fe2p XPS spectrum of mBNNs. (c) XRD patterns of BNNs and mBNNs, the hollow labels refer to diffraction peaks from BNNs, and the solid labels refer to peaks from  $\text{Fe}_3\text{O}_4$  nanoparticles. TEM images of (d)  $\text{Fe}_3\text{O}_4$  nanoparticles and (e) mBNNs. (f) FTIR spectrum of  $\text{Fe}_3\text{O}_4$  nanoparticles.

functionalization are still lacking because of their chemical inertia. It is thus highly attractive to introduce active groups onto BNNs surface for increasing chemical activity. The above characterizations of  $\text{Fe}_3\text{O}_4$  nanoparticles demonstrate that the synthesis of  $\text{Fe}_3\text{O}_4$  nanoparticles on BNNs surface can introduce a large number of  $-\text{OH}$  groups on their surfaces. This makes it possible to covalently functionalize mBNNs. Isocyanates are highly chemically active and can react with many compounds, such as amines, alcohols, carboxylic acids, and so on. They are considered to be ideal functional reagents for the surface modification of inorganic nanoparticles. Herein, the low viscosity 2,4-diisocyanate (TDI) was employed to covalently modify the surface of mBNNs. TDI molecular contains two isocyanate groups ( $-\text{NCO}$ ), in which one can react with the  $-\text{OH}$  groups on the surface of the mBNNs, another one makes mBNNs highly chemically active.<sup>44–46</sup>

In order to confirm the successful covalent modification of mBNNs by TDI molecules, FTIR analyses for the BNNs, mBNNs and mBNNs-TDI were performed, as shown in Fig. 3a.

The pure BNNs exhibit two strong absorption peaks at 817 and  $1375\text{ cm}^{-1}$ , which result from the B–N–B out-of-plane bending mode and B–N in-plane stretching vibration, respectively. The unimpressive peak around  $3440\text{ cm}^{-1}$  is the result of a trace amount of surface moisture.<sup>47</sup> For mBNNs, as expected, in addition to the absorption peaks assigned to BNNs, the absorption peak attributed to Fe–O bond stretching mode ( $\sim 586\text{ cm}^{-1}$ ) and a broadened peak corresponding to the  $-\text{OH}$  groups ( $\sim 3200\text{ cm}^{-1}$ ) are also observed. In the case of mBNNs-TDI, the peak assigned to the  $-\text{OH}$  groups disappears, while some additional peaks clearly appear, including the stretching vibrations of  $-\text{NCO}$  ( $2274\text{ cm}^{-1}$ ),  $-\text{NHCOO}-$  ( $1728\text{ cm}^{-1}$ ) and phenyl ring ( $1618$  and  $1510\text{ cm}^{-1}$ ). The existence of these new peaks confirm that TDI molecules are successfully grafted onto the surface of mBNNs. Moreover, because of the effect of strong covalent bonds between  $\text{Fe}_3\text{O}_4$  nanoparticles and TDI molecules on the Fe–O lattice, the Fe–O bond stretching peak shifts from  $586\text{ cm}^{-1}$  to  $575\text{ cm}^{-1}$ .






Fig. 3 FTIR spectra (a) and TGA curves (b) of BNNs, mBNNs and mBNNs-TDI.

TGA study was further performed to comparatively characterize the BNNs, mBNNs and mBNNs-TDI. As depicted in Fig. 3b, the unmodified BNNs possess high thermal stability, with only 0.32% water evaporation until 800 °C. After magnetic modification, the samples begin to lose weight around 160 °C. This weight loss is attributed to the removal of -OH groups on the surface of Fe<sub>3</sub>O<sub>4</sub> nanoparticles. Regarding of mBNNs-TDI, however, there is a significant weight loss between 220 °C and 500 °C. This weight loss is due to the thermal degradation of TPU molecular chains grafted onto the surface of mBNNs, in good agreement with FTIR analysis. In combination with the weight loss data of mBNNs, the weight grafting degree of TDI on mBNNs surface is calculated to be 8.31 wt%. It should be pointed out that the hexagonal structure of BNNs is well preserved after modification, as the Raman spectra of mBNNs and mBNNs-TDI both show the E<sub>2g</sub> phonon mode at 1365.4 cm<sup>-1</sup>, which is identical to that of the pure BNNs (Fig. S3a†). In addition, a small peak appears at ~680 cm<sup>-1</sup>, further indicating the presence of Fe<sub>3</sub>O<sub>4</sub> nanoparticles.<sup>48</sup> Moreover, the intrinsic crystalline properties of BNNs and Fe<sub>3</sub>O<sub>4</sub> are also well retained after modification, as revealed by XRD results (Fig. S3b†), in which mBNNs-TDI shows essentially the same diffraction peaks as the mBNNs.

To obtain quantitative information about the magnetic properties of mBNNs-TDI, the room-temperature magnetization characteristics of mBNNs-TDI along with mBNNs and Fe<sub>3</sub>O<sub>4</sub> nanoparticles were investigated by VSM. As shown in Fig. 4, the pure Fe<sub>3</sub>O<sub>4</sub> nanoparticles exhibit superparamagnetic behavior with a saturation magnetization of 72.46 emu g<sup>-1</sup>. The mBNNs are also superparamagnets with negligible remanence (0.14 emu g<sup>-1</sup>) and coercivity (1.2 Oe). Such magnetic properties are agreement with the fact that most of the Fe<sub>3</sub>O<sub>4</sub> nanoparticles anchored on BNNs surface possess diameters less than 25 nm and are typical single domain magnets.<sup>49</sup> However, the magnetization of mBNNs decreases to 38.99 emu g<sup>-1</sup> because of the existence of non-magnetic BNNs. For mBNNs-TDI, they show the same superparamagnetic behavior with a slightly reduced magnetization of 35.25 emu g<sup>-1</sup>. The magnetic response of mBNNs-TDI can be easily and quickly visualized by placing the mBNNs-TDI water solution close to a small magnet. As shown in the illustration (right below) in Fig. 4, all mBNNs-TDI particles are attracted to the magnetic source, illustrating

their good magnetism. As discussed above, the effective magnetic modification and TDI covalent functionalization of BNNs were successfully achieved through covering their surfaces with Fe<sub>3</sub>O<sub>4</sub> nanoparticles followed by treating with TDI. The as-obtained mBNNs-TDI is the promising filler to be used as building block for the preparation of thermoconductive composites with a perfect alignment of mBNNs-TDI.

### 3.3 Orientation of mBNNs-TDI in TPU matrix

During the preparation of composites with magnetic oriented fillers, the external magnetic field plays a crucial role in engineering the alignment of filler in polymer matrix. In this work, a method reported by Jiao *et al.*<sup>33</sup> was adopted to theoretically predict the minimum magnetic field ( $H_m$ ) required to align mBNNs-TDI in TPU matrix. Briefly, according to the elliptical shell model, there are magnetic torque ( $T_m$ ), gravitational torque ( $T_g$ ), and viscous torque ( $T_v$ ) acting on the mBNNs-TDI during the orientation process, where  $T_m$ ,  $T_g$  and  $T_v$  can be calculated according to the eqn (S1)–(S3),† respectively.

When the probability of mBNNs-TDI having the orientation angle ( $\theta$ ) in the range from 0° to 5° reaches up 90%, it is believed that the orientation structure is achieved. The probability ( $P$ ) of mBNNs-TDI within this range (0–5°) can be predicted through Boltzmann statistics, as following:




Fig. 4 Magnetic hysteresis cycles of Fe<sub>3</sub>O<sub>4</sub>, mBNNs and mBNNs-TDI.



$$P = \int_0^{90^\circ} e^{(T_m+T_g+T_v)/K_B T} d\theta / Z = 0.9 \quad (1)$$

$$Z = \int_0^{90^\circ} e^{T_m+T_g+T_v/K_B T} d\theta \quad (2)$$

where  $Z$  is the sum of the Boltzmann factors of any possible states of alignment of fillers,  $T$  is actual temperature,  $K_B$  is the Boltzmann factor ( $1.38 \times 10^{-23} \text{ J K}^{-1}$ ). Following the eqn (S1)–(S3†) and eqn (1) and (2), the  $H_m$  is calculated to be about 60 mT for the composites with 10 wt% loading, suggesting that the mBNNs-TDI can be well oriented in TPU resin under a very low magnetic field.

The mBNNs-TDI/TPU composite with an in-plane-aligned structure (ImBNNs-TDI/TPU) was fabricated by applying a low magnetic field during resin curing. For comparative purposes, in-plane-aligned mBNNs/TPU composite (ImBNNs/TPU) and randomly aligned mBNNs/TPU composites (RmBNNs/TPU) were also prepared. SEM characterization was performed on the fractured surfaces of various composites, and the representative results are shown in Fig. 5. For RmBNNs/TPU, many mBNNs platelets and aggregates are randomly dispersed in TPU matrix (Fig. 5a). The aggregation is so strong that the magnetic field cannot lead to a well oriented structure, as revealed by the cross-section SEM image of ImBNNs/TPU composite, in which some aggregations and unaligned mBNNs are clearly observed (Fig. 5b). In the case of ImBNNs-TDI/TPU, mBNNs-TDI is uniformly dispersed in TPU matrix and well orientated along the direction of the magnetic field (Fig. 5c), implying the importance of surface modification. The –NCO groups from TDI grafted onto the mBNNs surface can react with the terminal –OH groups of TPU, thereby increasing the dispersibility and interfacial affinity of mBNNs-TDI within the TPU matrix, which in turn greatly promote the orientation of mBNNs-TDI. Such homogeneous dispersion and strong interfacial interaction are also confirmed by the “disappearance” of most mBNNs-TDI in composite. The orientation features of

fillers can be more clearly visualized from low magnification SEM images, as shown in Fig. 5d–f. In sharp contrast to the disordered feature of RmBNNs-TDI/TPU (Fig. 5d), ImBNNs-TDI/TPU presents a ordered architecture (Fig. 5f). However, for HmBNNs/TPU composites, the ordered features become less noticeable due to many unaligned fillers (Fig. 5e).

The XRD detection of composites can provide further support for the magnetic orientation of fillers in matrix. As reported in previous works,<sup>26,50</sup> the (002) and (100) plane peaks, which are centered at  $26.7^\circ$  and  $41.6^\circ$ , correspond to the horizontally and vertically aligned BNNs, respectively. Therefore, the intensity ( $I$ ) ratio between (002) and (100) peaks can represent the horizontal orientation degree ( $\delta$ ) of fillers. Fig. 6 gives the XRD patterns of three different composites with 10 wt% loading. Clearly, there is a great difference in  $\delta$  values among these three composites. The magnetic field only promotes the orientation of mBNNs a little due to the severe aggregation of mBNNs. After the TDI covalent modification, the horizontal orientation degree of mBNNs-TDI dramatically increases. The same tendency of the orientation degree variation for the composites containing 5, 20 and 30 wt% fillers are depicted in




Fig. 6 XRD patterns of different composites with 10 wt% fillers.




Fig. 5 Cross-section SEM images of composites containing 10 wt% fillers at different magnifications: (a, d) RmBNNs/TPU; (b, e) ImBNNs/TPU; (c, f) ImBNNs-TDI/TPU. Blue circles indicate the aggregates, red arrows indicate the state of orientation of fillers.



Fig. S4.† These results further reveal that TDI covalent modification significantly enhances the orientation of mBNNs-TDI in TPU resin under magnetic field. The XRD results are in consistent with the SEM observation, and can also be employed to explain the difference in the thermal transport performances for the three composites, as discussed below.

### 3.4 Properties of ImBNNs-TDI/TPU composites

The in-plane thermal conductivities of different composites with various loadings were measured. As shown in Fig. 7, all composites show the same tendency, *i.e.*, the thermal conductivity increases with the increase of filler loading. This tendency can be ascribed to the increasing contribution of heat transport through fillers at higher loadings. At the same loading, however, the thermal conductivity is greatly different among these three composites. The differences can be explained by the different arrangement of fillers in various cases. BNNs exhibit a highly anisotropic thermal property: the in-plane thermal conductivity is almost 20 times higher than the through-plane thermal conductivity. Therefore, the ImBNNs-TDI/TPU composite with the well aligned structure exhibits the highest effectiveness in increasing the thermal conductivity. For polymer composites, the relationship between the thermal conductivity and filler loading can be fitted the mode proposed by Agari *et al.* as follows:<sup>51</sup>

$$\log \lambda_c = (1 - V)\log(C_m\lambda_m) + VC_f\log \lambda_f$$

where  $\lambda_c$ ,  $\lambda_m$  and  $\lambda_f$  and are the thermal conductivities of composites, polymer matrices and fillers, respectively;  $V$  is the filler volume fraction;  $C_m$  is a parameter that relates to the polymer structure,  $C_f$  represents the ease in forming conductive pathways by fillers. In this fitting, the average value of  $C_f$  shows the order of RmBNNs/TPU (3.6) < ImBNNs/TPU (3.8) < ImBNNs-TDI/TPU (4.4). The sequence is well consistent with




Fig. 7 In-plane thermal conductivities of RmBNNs/TPU, ImBNNs/TPU and ImBNNs-TDI/TPU composites. The red numbers show the thermal conductivity enhancement of ImBNNs/TPU in comparison with the RmBNNs/TPU composites. The blue numbers show the thermal conductivity enhancement of ImBNNs-TDI/TPU in comparison with the ImBNNs/TPU composites.

that of the orientation degree of filler given by XRD investigation, implying that the oriented mBNNs can easily construct thermally conductive paths along the aligned direction. Therefore, the ultra-high in-plane thermal conductivity of BNNs and the formation of efficient thermally conductive pathways both are responsible for the high thermal conductivity of ImBNNs-TDI/TPU composites. Together with uniform dispersion and strong interfacial interaction, the heat in ImBNNs-TDI/TPU composite can, thus, be easily collected and conducted by highly-oriented mBNNs-TDI particles.

It is also noted that the difference in the thermal conductivity between RmBNNs/TPU and ImBNNs/TPU is greatly diminished at 30 wt% loading. The thermal enhancement (defined as the thermal conductivity improvement percentage with that of RmBNNs/TPU as a reference) initially increases with the increasing filler content, being as high as 159.91% at 10 wt%, whereas drops quickly to 40.09% at 30 wt% loading. The reduction of thermal enhancement at high filler content can be explained according to the orientation degree given by XRD detection (Fig. 6 and S4†). The orientation degree of ImBNNs/TPU with 30 wt% loading only increases from 46.1 of RmBNNs/TPU to 96.8. The corresponding orientation degree enhancement is much lower than those obtained at low loading. With an increase in the loading of fillers, the aggregation increase correspondingly, thus severely hindering the magnetic orientation of mBNNs in TPU matrix. The relatively disordered arrangement of mBNNs results in the decrease of the heat transfer efficiency parallel to the in-plane direction, thus a lower increase in the thermal conductivity at high loadings. However, in the case of ImBNNs-TDI/TPU composites, owing to uniform dispersion of fillers, it is possible to obtain a high orientation degree at high loading ( $\delta$  is 1015.3 at 30 wt%). Therefore, with the thermal conductivity of ImBNNs/TPU as a reference, the thermal enhancement of ImBNNs-TDI/TPU composites increases with the increasing filler loading. At 30 wt% loading, the thermal conductivity of the ImBNNs-TDI/TPU composite is dramatically increased to 5.15 W m<sup>-1</sup> K<sup>-1</sup>, displaying 105.22% and 190.97% increases with respect to the ImBNNs/TPU and RmBNNs/TPU composites, respectively.

Besides in-plane thermal conductivity, the through-plane thermal conductivities of as-prepared composites were also measured (Fig. S5†). For RmBNNs/TPU composites, the through-plane thermal conductivity is slightly lower than the in-plane thermal conductivity. For instance, at 30 wt% loading, the in-plane thermal conductivity is 1.771 W m<sup>-1</sup> K<sup>-1</sup>, whereas the through-plane thermal conductivity is only 1.635 W m<sup>-1</sup> K<sup>-1</sup>. This is mainly attributed the large aspect ratio of mBNNs, which facilitates the mBNNs to arrange along the horizontal direction spontaneously,<sup>18</sup> as revealed by XRD characterization. After magnetic orientation, the through-plane thermal conductivity is further reduced in comparison with that of RmBNNs/TPU composite. Moreover, the difference in the through-plane thermal conductivity between RmBNNs/TPU and ImBNNs/TPU is gradually diminished with the increasing filler loadings, which can be explained by the fact that the horizontal orientation degree of fillers is gradually reduced with the increase of mBNNs loadings. Due to more horizontally



arranged fillers, the ImBNNs-TDI/TPU composite exhibits the minimum efficiency in increasing the through-plane thermal conductivity. With 30 wt% loading, the through-plane thermal conductivity of the ImBNNs-TDI/TPU composite is merely reaches  $1.283 \text{ W m}^{-1} \text{ K}^{-1}$ , corresponding to 17.33% and 21.35% reductions compared to the ImBNNs/TPU and RmBNNs/TPU composites, respectively.

The effects of filler orientation and modification on the dielectric properties of composites were investigated, as presented in Fig. 8. For RmBNNs/TPU composites, the addition of mBNNs has no negative impact on the dielectric constant and dielectric loss tangent. This should be attributed to the high electrical insulation of mBNNs. After magnetic alignment, the ImBNNs/TPU composite exhibits slightly lower dielectric constant and dielectric dissipation factor compared with those of RmBNNs/TPU composite, and their values at 1 kHz drop from 6.01 to 5.61 and 0.038 to 0.035, respectively. As revealed by DSC analysis (Fig. S6†), the ImBNNs/TPU composite possess a higher  $T_g$  value than that of RmBNNs/TPU composite. This indicates that the orientation of mBNNs are more effective to inhibit the movement of the TPU molecular chains in comparison with randomly dispersed mBNNs in TPU. As a result, the bulk polarization in TPU resin and the mobility of the charge carrier are restricted, which result in a decrease in

dielectric constant and dielectric dissipation factor. For ImBNNs-TDI/TPU composite, benefiting from the higher degree of orientation, homogeneous dispersion and strong interfacial interaction, the immobility of TPU molecular chain is further enhanced, as confirmed by the DSC result, in which the  $T_g$  of ImBNNs-TDI/TPU is increased from  $-31.11 \text{ }^\circ\text{C}$  of ImBNNs/TPU to  $-27.25 \text{ }^\circ\text{C}$ . Consequently, a significantly reduction in dielectric constant (4.69 at 1 kHz) and dielectric dissipation factor (0.029 at 1 kHz) is achieved in ImBNNs-TDI/TPU composite. Furthermore, with the increasing mBNNs-TDI loading, the more highly immobile interfaces will be formed, therefore, the dielectric constant and dielectric dissipation factor even decrease with the increase of BNNs-TDI content, as shown in Fig. S7.†

Table 1 summarizes previously reported thermal conductivity and dielectric property for polymer composites with various fillers. The thermal conductivity enhancement ( $\Delta K$ ) is defined as  $\Delta K = K_c/K_m$ , where  $K_c$  and  $K_m$  are the thermal conductivity of the composite and resin matrix, respectively. The variation of dielectric constant ( $\Delta\lambda$ ) is defined as  $\Delta\lambda = \lambda_c/\lambda_m$ , where  $\lambda_c$  and  $\lambda_m$  are the dielectric constants of the composite and resin matrix. The variation of dielectric dissipation factor ( $\Delta\tan\delta$ ) is defined as  $\Delta\tan\delta = \tan\delta_c/\tan\delta_m$ , where  $\tan\delta_c$  and  $\tan\delta_m$  are the dielectric dissipation factor of




Fig. 8 Frequency dependence of dielectric constant (a) and dielectric dissipation factor (b) of blank TPU resin and different composites with 10 wt% fillers.

Table 1 Comparison of thermal conductivity and dielectric property of our ImBNNs-TDI/TPU with other reported polymer composites

Filler	Matrix	$\Delta K$ (%)	$\Delta\lambda$ (%)	$\Delta\tan\beta$ (%)	Loading	Reference
SiC	Epoxy	198	187	147	13.8 vol%	52
$\text{Al}_2\text{O}_3$	Epoxy	138	137	140	20 wt%	53
$\text{Si}_3\text{N}_4$	Epoxy	545	151	533	30 vol%	54
AlN	Epoxy	187	120	265	27.4 wt%	55
BNNT	Epoxy	1360	87	18	30 wt%	56
h-BN	Cyanate ester	204	109	85	15 vol%	21
h-BN	Epoxy	190	122	255	30 wt%	57
Aggregated BN	Epoxy	1910	—	—	42.8 vol%	58
h-BN	Bismaleimide	276	—	—	20 wt%	59
h-BN + graphene	Polyimide	1623	—	—	50 wt%	60
BNNs	Epoxy	416	—	—	30 wt%	19
Aligned h-BN	Epoxy	567	—	—	20 wt%	30
Aligned BNNs	Natural rubber	1486	—	—	30 vol%	22
Aligned mBNNs-TDI	TPU	3012	61	45	30 wt%	This work






Fig. 9 (a) Storage modulus and (b) tan delta of the blank TPU resin and different composites with 10 wt% fillers.

the composite and resin matrix, respectively. Obviously, the thermal conductivity enhancement of our ImBNNs-TDI/TPU composites is extremely high. In addition, the observed decrease of  $\lambda_c$  and  $\tan \delta_c$  in ImBNNs-TDI/TPU composites is attractive, as the incorporation of inorganic particles into insulating polymers usually results in high  $\lambda_c$  and  $\tan \delta_c$ , such as SiC, Al<sub>2</sub>O<sub>3</sub>, and AlN, *etc.* The simultaneous properties of high  $K_c$ , low  $\lambda_c$  and low  $\tan \delta_c$  pave the way for promising application in electronic packaging.

The thermomechanical properties of the composites were also investigated through DMA analysis (Fig. 9). As expected, all composites exhibit a higher dynamic storage modulus ( $E'$ ) than that of the pure TPU resin due to the inherent hardness and high storage modulus of BNNs. The ImBNNs-TDI/TPU composite show the maximum increase over the whole temperature range. In glassy region, the  $E'$  value is up to 5823 MPa, 2.2-fold higher than that of the TPU resin (1829 MPa). However, the RmBNNs/TPU composite exhibit the minimum efficiency in increasing the  $E'$ . The sequence of the enhancement in  $E'$  of the three composites is well agreement with that of thermal conductivity, which can be explained by the orientation degree and interfacial strength. Fig. 9b presents the variation of loss tangent ( $\tan \delta$ ) with temperature. Obviously, the  $T_g$ , defined as the temperature corresponding to the peak of  $\tan \delta$  curve, is well consistent with the values obtained from DSC curves, with the order of the blank TPU resin < RmBNNs/TPU < ImBNNs/TPU < ImBNNs-TDI/TPU, further confirming a strong interfacial interaction in ImBNNs-TDI/TPU.

## 4. Conclusions

In this study, we investigated the thermal conductivity of BNNs-based composites as a function of filler alignment. The BNNs surfaces were firstly modified with strong paramagnetic Fe<sub>3</sub>O<sub>4</sub> nanoparticles to make them magnetically responsive. Then, TDI molecules were covalently grafted onto the mBNNs surfaces to increase the dispersibility and interfacial affinity of mBNNs-TDI within TPU matrix. Finally, the highly-ordered mBNNs-TDI/TPU composites were easily fabricated through a low magnetic field. Owing to the effective surface modification, it is possible to obtain a high orientation degree at high loadings. With the highest filler loading, the in-plane thermal

conductivity of ImBNNs-TDI/TPU composite reaches up to 5.15 W m<sup>-1</sup> K<sup>-1</sup>, whereas the ImBNNs/TPU composite show a relatively low thermal conductivity of 2.48 W m<sup>-1</sup> K<sup>-1</sup> due to a low orientation degree of fillers at high loading. Furthermore, the ImBNNs-TDI/TPU composites have low dielectric constant, low dielectric dissipation factor and outstanding thermo-mechanical properties. This work opens a new avenue for the fabrication of high-thermal-performance BNNs-based elastomer composites, which have great potential in advanced electronic packaging techniques.

## Conflicts of interest

The authors declare no competing financial interest.

## Acknowledgements

The works were financially supported by National Natural Science Foundation of China (No. 51402067), and the Foundation for Innovative Research Groups of the National Natural Science Foundation of China (Grant No. 11421091). We are grateful for the constructive comments and valuable advices from all the reviewers for further improvement of our work.

## References

- 1 Y. Zhou, H. Wang, L. Wang, K. Yu, Z. Lin, L. He and Y. Bai, *Mater. Sci. Eng., B*, 2012, **177**, 892–896.
- 2 X. Huang, T. Iizuka, P. Jiang, Y. Ohki and T. Tanaka, *J. Phys. Chem. C*, 2012, **116**, 13629–13639.
- 3 Z. Shi, M. Radwan, S. Kirihaara, Y. Miyamoto and Z. Jin, *Appl. Phys. Lett.*, 2009, **95**, 224104.
- 4 Y. Zhou, H. Wang, F. Xiang, H. Zhang, K. Yu and L. Chen, *Appl. Phys. Lett.*, 2011, **98**, 182906.
- 5 Y. Yao, X. Zeng, K. Guo, R. Sun and J.-b. Xu, *Composites, Part A*, 2015, **69**, 49–55.
- 6 J.-P. Cao, X. Zhao, J. Zhao, J.-W. Zha, G.-H. Hu and Z.-M. Dang, *ACS Appl. Mater. Interfaces*, 2013, **5**, 6915–6924.
- 7 Y. Li, X. Huang, Z. Hu, P. Jiang, S. Li and T. Tanaka, *ACS Appl. Mater. Interfaces*, 2011, **3**, 4396–4403.
- 8 L. Ren, K. Pashayi, H. R. Fard, S. P. Kotha, T. Borca-Tasciuc and R. Ozisik, *Composites, Part B*, 2014, **58**, 228–234.



- 9 H. Chen, M. Chen, J. Di, G. Xu, H. Li and Q. Li, *J. Phys. Chem. C*, 2012, **116**, 3903–3909.
- 10 Z. Han and A. Fina, *Prog. Polym. Sci.*, 2011, **36**, 914–944.
- 11 M. Wang, H. Chen, W. Lin, Z. Li, Q. Li, M. Chen, F. Meng, Y. Xing, Y. Yao, C.-p. Wong and Q. Li, *ACS Appl. Mater. Interfaces*, 2014, **6**, 539–544.
- 12 W. Cui, F. Du, J. Zhao, W. Zhang, Y. Yang, X. Xie and Y.-W. Mai, *Carbon*, 2011, **49**, 495–500.
- 13 X. Huang, C. Zhi and P. Jiang, *J. Phys. Chem. C*, 2012, **116**, 23812–23820.
- 14 S. Araby, L. Zhang, H.-C. Kuan, J.-B. Dai, P. Majewski and J. Ma, *Polymer*, 2013, **54**, 3663–3670.
- 15 K. M. F. Shahil and A. A. Balandin, *Nano Lett.*, 2012, **12**, 861–867.
- 16 C.-C. Teng, C.-C. M. Ma, C.-H. Lu, S.-Y. Yang, S.-H. Lee, M.-C. Hsiao, M.-Y. Yen, K.-C. Chiou and T.-M. Lee, *Carbon*, 2011, **49**, 5107–5116.
- 17 D. Golberg, Y. Bando, Y. Huang, T. Terao, M. Mitome, C. Tang and C. Zhi, *ACS Nano*, 2010, **4**, 2979–2993.
- 18 H. Shen, J. Guo, H. Wang, N. Zhao and J. Xu, *ACS Appl. Mater. Interfaces*, 2015, **7**, 5701–5708.
- 19 Z. Lin, A. McNamara, Y. Liu, K.-s. Moon and C.-P. Wong, *Compos. Sci. Technol.*, 2014, **90**, 123–128.
- 20 X. Wang, A. Pakdel, J. Zhang, Q. Weng, T. Zhai, C. Zhi, D. Golberg and Y. Bando, *Nanoscale Res. Lett.*, 2012, **7**, 662.
- 21 H. Wu and M. R. Kessler, *ACS Appl. Mater. Interfaces*, 2015, **7**, 5915–5926.
- 22 Z. Kuang, Y. Chen, Y. Lu, L. Liu, S. Hu, S. Wen, Y. Mao and L. Zhang, *Small*, 2015, **11**, 1655–1659.
- 23 S. Yangyang, Z. Zhuqing and C. P. Wong, *IEEE Trans. Compon. Packag. Technol.*, 2006, **29**, 190–197.
- 24 T. Kawai and T. Kimura, *Polymer*, 2000, **41**, 155–159.
- 25 K. Uetani, S. Ata, S. Tomonoh, T. Yamada, M. Yumura and K. Hata, *Adv. Mater.*, 2014, **26**, 5857–5862.
- 26 B.-H. Xie, X. Huang and G.-J. Zhang, *Compos. Sci. Technol.*, 2013, **85**, 98–103.
- 27 W.-L. Song, P. Wang, L. Cao, A. Anderson, M. J. Meziani, A. J. Farr and Y.-P. Sun, *Angew. Chem., Int. Ed.*, 2012, **51**, 6498–6501.
- 28 E. Munch, M. E. Launey, D. H. Alsem, E. Saiz, A. P. Tomsia and R. O. Ritchie, *Science*, 2008, **322**, 1516–1520.
- 29 R. Libanori, F. H. L. Münch, D. M. Montenegro and A. R. Studart, *Compos. Sci. Technol.*, 2012, **72**, 435–445.
- 30 Z. Lin, Y. Liu, S. Raghavan, K.-s. Moon, S. K. Sitaraman and C.-p. Wong, *ACS Appl. Mater. Interfaces*, 2013, **5**, 7633–7640.
- 31 C. Yuan, B. Duan, L. Li, B. Xie, M. Huang and X. Luo, *ACS Appl. Mater. Interfaces*, 2015, **7**, 13000–13006.
- 32 K. Kim, M. Kim, J. Kim and J. Kim, *Ceram. Int.*, 2015, **41**, 12280–12287.
- 33 W. Jiao, M. Shioya, R. Wang, F. Yang, L. Hao, Y. Niu, W. Liu, L. Zheng, F. Yuan, L. Wan and X. He, *Compos. Sci. Technol.*, 2014, **99**, 124–130.
- 34 R. M. Erb, R. Libanori, N. Rothfuchs and A. R. Studart, *Science*, 2012, **335**, 199–204.
- 35 H. Xingyi, W. Shen, Z. Ming, Y. Ke, J. Pingkai, B. Yoshio, G. Dmitri and Z. Chunyi, *Nanotechnology*, 2015, **26**, 015705.
- 36 J. Yu, X. Huang, C. Wu, X. Wu, G. Wang and P. Jiang, *Polymer*, 2012, **53**, 471–480.
- 37 D. S. Muratov, D. V. Kuznetsov, I. A. Il'inykh, I. N. Burmistrov and I. N. Mazov, *Compos. Sci. Technol.*, 2015, **111**, 40–43.
- 38 F. Yuan, W. Jiao, F. Yang, W. Liu, J. Liu, Z. Xu and R. Wang, *J. Mater. Chem. C*, 2017, **5**, 6359–6368.
- 39 Z. Cui, A. J. Oyer, A. J. Glover, H. C. Schniepp and D. H. Adamson, *Small*, 2014, **10**, 2352–2355.
- 40 H. Zhu, Y. Li, Z. Fang, J. Xu, F. Cao, J. Wan, C. Preston, B. Yang and L. Hu, *ACS Nano*, 2014, **8**, 3606–3613.
- 41 J. Sun, Y. Yao, X. Zeng, G. Pan, J. Hu, Y. Huang, R. Sun, J.-B. Xu and C.-P. Wong, *Adv. Mater. Interfaces*, 2017, 1700563.
- 42 A. Prakash, S. Chandra and D. Bahadur, *Carbon*, 2012, **50**, 4209–4219.
- 43 Y. Yao, X. Zeng, R. Sun, J.-B. Xu and C.-P. Wong, *ACS Appl. Mater. Interfaces*, 2016, **8**, 15645–15653.
- 44 Q. Liu, J. R. de Wijn, K. de Groot and C. A. van Blitterswijk, *Biomaterials*, 1998, **19**, 1067–1072.
- 45 H.-W. Di, Y.-L. Luo, F. Xu, Y.-S. Chen and Y.-F. Nan, *J. Nanosci. Nanotechnol.*, 2010, **10**, 8210–8216.
- 46 M. T. Huang and H. Ishida, *Surf. Interface Anal.*, 2005, **37**, 621–627.
- 47 J. Hou, G. Li, N. Yang, L. Qin, M. E. Grami, Q. Zhang, N. Wang and X. Qu, *RSC Adv.*, 2014, **4**, 44282–44290.
- 48 M. Sousa, F. A. Tourinho and J. Rubim, *Use of Raman microspectroscopy in the characterization of  $M\text{IIFe}_2\text{O}_4$  ( $M = \text{Fe}, \text{Zn}$ ) electric double layer ferrofluids*, 2000.
- 49 Y. Huang, J. Lin, Y. Bando, C. Tang, C. Zhi, Y. Shi, E. Takayama-Muromachi and D. Golberg, *J. Mater. Chem.*, 2010, **20**, 1007–1011.
- 50 H. J. Ahn, Y. J. Eoh, S. D. Park and E. S. Kim, *Thermochim. Acta*, 2014, **590**, 138–144.
- 51 Y. Agari, A. Ueda, M. Tanaka and S. Nagai, *J. Appl. Polym. Sci.*, 1990, **40**, 929–941.
- 52 T. Zhou, X. Wang, X. Liu and D. Xiong, *Carbon*, 2010, **48**, 1171–1176.
- 53 J. Yu, R. Huo, C. Wu, X. Wu, G. Wang and P. Jiang, *Macromol. Res.*, 2012, **20**, 816–826.
- 54 M. Terrones, J. M. Romo-Herrera, E. Cruz-Silva, F. López-Urías, E. Muñoz-Sandoval, J. J. Velázquez-Salazar, H. Terrones, Y. Bando and D. Golberg, *Mater. Today*, 2007, **10**, 30–38.
- 55 W. Peng, X. Huang, J. Yu, P. Jiang and W. Liu, *Composites, Part A*, 2010, **41**, 1201–1209.
- 56 X. Huang, C. Zhi, P. Jiang, D. Golberg, Y. Bando and T. Tanaka, *Adv. Funct. Mater.*, 2013, **23**, 1824–1831.
- 57 J. Gu, Q. Zhang, J. Dang and C. Xie, *Polym. Adv. Technol.*, 2012, **23**, 1025–1028.
- 58 K. Kim, M. Kim and J. Kim, *Compos. Sci. Technol.*, 2014, **103**, 72–77.
- 59 W. Jin, L. Yuan, G. Liang and A. Gu, *ACS Appl. Mater. Interfaces*, 2014, **6**, 14931–14944.
- 60 M.-H. Tsai, I. H. Tseng, J.-C. Chiang and J.-J. Li, *ACS Appl. Mater. Interfaces*, 2014, **6**, 8639–8645.

