Cite this: *RSC Adv.*, 2017, 7, 47507

Precision polymers containing main-chain-amino acids: ADMET polymerization and crystallization†

Jan Freudenberg,^a Silvio Poppe^b and Wolfgang H. Binder^{*,a}

The synthesis of new poly(alkyl)-precision oligomers and polymers displaying different types of amino acids (chiral/achiral, polar/non-polar) placed at every 19th carbon atom are presented. Placing ω -alkenyl moieties onto appropriately *N*- and *C*-terminus functionalized amino acids successfully enabled ADMET-polymerization of these monomers. Grubbs 1st catalyst under melt-polycondensation-conditions was found to be the most effective with respect to the obtained molecular weights of the polymers, the isomerization of the olefins and their final yield, yielding molecular weights up to ~22 kDa. The obtained polymers and the subsequent hydrogenation of the double bonds with *p*-toluenesulfonylhydrazide (TsNHNH₂) was proven by NMR, GPC, MALDI-ToF-MS and IR measurements. Investigation of the thermal behavior of the monomers and polymers *via* DSC measurements displays amorphous structures for monomers and polymers with unpolar amino acid side chains, whereas for polymers bearing the polar glutamic- and aspartic acid moieties crystalline morphologies are observed. An ordered lamellar crystal phase is observed where the amino acid branches are either incorporated or excluded from the unit cell, as proven by WAXS data.

Received 2nd September 2017
Accepted 29th September 2017

DOI: 10.1039/c7ra10485e

rsc.li/rsc-advances

Introduction

Understanding the ordering within specific domains of a polymer, based on regular arrangements of (sub-)units is among the fundamental principles in biological and synthetic macromolecules. In contrast to synthetic macromolecules, in which structure formation is based on only a few, often constrained hierarchical levels,^{1–3} intra- and intermolecular interaction *via* supramolecular bonds of exactly placed amino acids, combined with rotational constraints caused by rigid bonds in a polypeptide chain are the basis for the formation of regular ordering phenomena in biological macromolecules.⁴ Such inter- and intrachain macromolecular ordering is often kinetically driven by nucleation dependent processes,^{5,6} in which the formation of higher structure levels *e.g.* crystal lamellae,⁷ an (oligomeric- or peptidic-) gel,⁸ or an fibrillar aggregate⁹ strongly depends on the initial formation of primary nuclei.

Introducing amino acids as structuring and folding elements into synthetic polymers thus is an important element of molecular design, enabling to determine the molecular shape in the solid state. Different mechanical and thermal properties as well as the crystallization behaviour of such polymers can be

engineered by repetitively placing monomers at specific positions within a polymer chain of defined origin.^{10–15} Acyclic diene metathesis polymerization (ADMET)¹⁶ has been proven to be an excellent tool to achieve a polyethylene (PE)-like chain with functional monomers at precise locations.^{17,18} Size, chemical structure and the steric structure of such “defects” to a large extent determine the final crystallization behaviour in the solid state: when the precisely placed chemical elements are small (such as methyl^{19,20}, ethyl²¹ or halogen^{22–26}-groups) they can be incorporated into the crystalline region of a semicrystalline polymer, whereas larger defects (higher alkyl substituents,^{19,27} phosphoesters^{28,29} or triazol-rings³⁰ and sulfonic-moieties³¹) are excluded from the final crystal-lattice.

The synthetic preparation of biosimilar oligomers and polymers with repetitive amino acid units in the main chains has stimulated a plethora of different methods.^{32,33} Thus *e.g.* the synthesis of optically active linear and branched poly(meth)acrylamides bearing α -amino acid moieties by radical polymerization^{34–37} or the periodically incorporation of amino acid units *via* ROMP using Grubbs catalysts has been accomplished.^{38–40} Especially ROMP was found to be an excellent tool for synthesizing polyolefin-*graft*-oligopeptide polyelectrolytes which can form extended, pearl-like, or multi-molecular structures.⁴¹ A periodic arrangement of amino acid branches in precision polymers *via* ADMET polymerization has been previously achieved allowing to prepare polyolefines bearing ester-terminated and amide-terminated amino acids in the backbone.⁴² Currently, only lysine as a side-chain moiety and cysteine (within the main chain) have been placed within a poly(alkyl)-

^aMartin Luther University Halle-Wittenberg, Faculty of Natural Sciences II, Chair of Macromolecular Chemistry, D-06120 Halle, Germany

^bMartin Luther University Halle-Wittenberg, Faculty of Natural Sciences II, Chair of Organic Chemistry, D-06120 Halle, Germany

† Electronic supplementary information (ESI) available: ¹H and ¹³C NMR data of monomers as well as ¹H- and ¹³C-NMR-, IR-data and MALDI-ToF-MS-data of polymers. See DOI: 10.1039/c7ra10485e

Fig. 1 Schematic representation of the synthesis of PE precision polymers with amino acid defects.

chain^{43,44} resulting in a semi-crystalline morphology of such polymers.

We here report on the introduction of five different amino acids (chiral/achiral, polar/non-polar) as basic bio-building blocks into the main chain of PE-polymers, placed precisely at every 19th carbon within the main chain by functionalizing the N- and C-terminus of the amino acid (see Fig. 1). Our main interest concerned the synthetic/preparative issue, most of all how ADMET will comply with different amino acids to furnish – after hydrogenation – the final polymers with precisely placed amino acids. On the other hand we were interested in the structure formation of such polymers in the solid (semi-crystalline) state: which amino acid will allow crystallization of the poly(alkyl)-chain, which one will inhibit the crystal-formation, and what will happen to the crystal structure if formed.

Experimental section

Materials

Amino acids L-glutamic acid γ -benzyl ester and L-aspartic acid β -benzyl ester were purchased from carbolution-chemicals, 1-aminocyclohexanecarboxylic acid, 2-aminoisobutyric acid and LiAlH₄ were purchased from ABCR and 10-undecenoyl chloride was purchased from Acros Organics. All other chemicals were purchased from Sigma-Aldrich. All chemicals were used without further preparations or purification steps. The solvents which were used for reactions were dried and freshly distilled before using. THF was dried and distilled over sodium

and benzophenone under N₂ atmosphere, for drying of dichloromethane (DCM) and dimethyl formamide (DMF) CaH₂ was used. For the reactions under protective gas atmosphere nitrogen (N₂) was used, which was purchased from LINDE.

Instrument and measurements

Nuclear magnetic resonance (NMR) spectra were recorded at 27 °C on a NMR spectrometer of VARIAN. The ¹H-NMR spectroscopy were performed at 400 MHz and ¹³C-NMR spectroscopy at 100 MHz. For all samples CDCl₃ or DMSO-d₆ were used as solvents, in case of the hydrogenated polymers **4a–4e** 15 vol% TFA were added. The splitting patterns were subdivided in singulets (s), dubletts (d), triplets (t) and multiplett (m) during analysis. Chemical shifts (δ) were given in ppm referred to the solvent residue peak and tetramethylsilane were used as internal standard.

Infrared-spectroscopy (IR) was measured by VERTEX 70 IR spectrometer of Bruker by using a single reflex-diamond-ATR-unit. The absorption bands are reported in cm⁻¹ in an area of 400–4000 cm⁻¹. The software OPUS was used for interpretation of the obtained bands.

Matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-ToF-MS) measurements were performed on a Bruker Autoflex III system (Bruker Daltonics) using a nitrogen laser operating at a wave length of $\lambda = 337$ nm in reflection or linear modes. The polymer was dissolved in THF with a concentration of 10 mg mL⁻¹. The matrix dithranol was dissolved in THF with a concentration of 10 mg mL⁻¹, for the salt KTFA a concentration of 5 mg mL⁻¹ in THF was used. The

volume ratio of the components was matrix : analyt : salt was for all measurements 100 : 10 : 1. Calibration was done with PEG-standard ($M_p = 2000 \text{ g mol}^{-1}$ and 4200 g mol^{-1}). Data evaluation was carried out on flexAnalysis software (3.4).

For gel permeation chromatography (GPC) measurements a Viscotek GPCmax VE 2002 with a HHR-HGuard-17369 and a GMH HR-N-18055 column in tetrahydrofuran (THF) was used. Measurements were done at 22°C and concentration of the samples were $c = 5 \text{ mg ml}^{-1}$. Detection was realized by refractive index with a VE3580 RI detector of Viscotek at a temperature of 35°C and a flow rate of 1 mL min^{-1} . External calibration was done with polystyrene ($M_p = 1000\text{--}115\,000 \text{ g mol}^{-1}$).

For differential scanning calorimetry (DSC) measurements a NETZSCH DC 204F1 Phoenix, which was calibrated with indium, tin, bismuth, and zinc was used. Nitrogen was used as purge gas and all samples (3g–8g) were placed in standard aluminum pans. For analysis of obtained data Netzsch Proteus – Thermal Analysis (version 5.2.1.) and OriginPro 8G was used. For calculation of the crystallinity α equation below was used:

$$\alpha = \frac{\Delta H_m}{\Delta H_m^0} \times 100$$

where H_m^0 is the fusion enthalpy of eicosane $\Delta H_m = 247.3 \text{ J g}^{-1}$.

X-ray diffraction (XRD) 2D patterns were detected on Vantec 500 detector (Bruker AXS) with a detector to sample distance of 9.00 cm. Measurements of the samples were done as droplet which was heated up on a glass plate to isotropic state followed by cooling the sample with a define cooling rate of 5 K min^{-1} on a temperature-controlled heating stage. Measuring temperature for **4a** was 60.0°C and for **4b** 70.0°C , measuring time for both samples were 30 min.

Dialysis tube (MWCO: 1000 g mol^{-1}) was purchased from Carl Roth GmbH.

Monomer synthesis

N-terminus functionalization

General procedure for the amino acids bearing a benzyl protection group in the side chain (method A) (1a–1b). N-terminus functionalization was realized by the Einhorn method for the amino acids bearing a benzyl protection group in the side chain. Therefore, the protected amino acid (1 eq.) was dissolved in THF (12 mL) and pyridine (10 mL) was added to the solution. The mixture was cooled to 0°C and 10-undecenoyl chloride (1.3 eq.) was added dropwise to the solution, which then was stirred for 24 h at room temperature. Then the reaction mixture was poured into cold 1 M HCl-solution (300 mL) and diethyl ether (200 mL) was added. The organic phase were separated, extracted two times with 1 M HCl solution ($2 \times 100 \text{ mL}$) and dried over Na_2SO_4 . After filtration the mixture was concentrated in vacuum and recrystallized three times in ethyl acetate : *n*-hexane (1 : 40) mixture to yield a white solid **1a–1b** (72–76%).

N-Glu (1a): $^1\text{H-NMR}$ (CDCl_3 , 27°C , 400 MHz): δ [ppm] 1.27 (m, 10H, $H_d - H_h$), 1.60 (m, 2H, H_i), 2.02–2.20 (m, 6H, $H_4 + H_c + H_j$), 2.49 (m, 1H, H_3), 2.57 (m, 1H, H_3), 4.54 (m, 1H, H_2), 4.93 (m, 2H, H_a), 5.12 (s, 2H, H_6), 5.79 (m, 1H, H_b), 6.56 (d, $^3J_{H,H} = 7.2 \text{ Hz}$, 1H, H_{13}), 7.31–7.45 (m, 5H, $H_8 - H_{12}$).

N-Glu (1a): $^{13}\text{C-NMR}$ (CDCl_3 , 27°C , 100 MHz): δ [ppm] 25.4 (C_i), 26.5 (C_3), 28.9–29.5 ($C_d - C_h$), 30.5 (C_4), 33.7 (C_c), 36.3 (C_j), 52.3 (C_2), 66.9 (C_6), 114.1 (C_a), 128.2–128.7 ($C_8 - C_{12}$), 135.5 (C_7), 139.1 (C_b), 171.5 (C_1), 173.6 (C_5), 174.1 (C_k).

N-Asp (1b): $^1\text{H-NMR}$ (CDCl_3 , 27°C , 400 MHz): δ [ppm] 1.27 (m, 10H, $H_d - H_h$), 1.61 (m, 2H, H_i), 2.02 (m, 2H, H_c), 2.20 (m, 2H, H_j), 2.92 (m, 1H, H_3), 3.09 (m, 1H, H_3), 4.91 (m, 1H, H_2), 4.96 (m, 2H, H_a), 5.14 (s, 2H, H_5), 5.81 (m, 1H, H_b), 6.56 (d, $^3J_{H,H} = 7.2 \text{ Hz}$, 1H, H_{12}), 7.31–7.45 (m, 5H, $H_7 - H_{11}$).

N-Asp (1b): $^{13}\text{C-NMR}$ (CDCl_3 , 27°C , 100 MHz): δ [ppm] 25.4 (C_i), 28.9–29.3 ($C_d - C_h$), 33.8 (C_c), 36.3 (C_j), 36.5 (C_3), 48.5 (C_2), 67.0 (C_5), 114.1 (C_a), 128.2–128.6 ($C_7 - C_{11}$), 135.23 (C_6), 139.1 (C_b), 171.1 (C_1), 173.8 (C_4), 174.1 (C_k).

General procedure for the amino acids without a protection group in the side chain (method B) (1c–1e). N-terminus functionalization was realized by Schotten–Baumann synthesis for the water soluble amino acids. The amino acid (1 eq.) and NaOH (2 eq.) was dissolved in water (20 mL) and the mixture was cooled in an ice-bath. 10-Undecenoyl chloride (1.1 eq.), dissolved in dichloromethane (20 mL), was added dropwise to the solution which was allowed to stir at room temperature for 24 h. The mixture was poured into cold 1 M HCl-solution (200 mL) and the organic phase were then separated, dried over Na_2SO_4 , filtrated and concentrated in vacuum. The crude product was recrystallized three times in ethyl acetate : *n*-hexane (1 : 40) mixture to yield a white solid **1c–1e** (64–75%).

N-Leu (1c): $^1\text{H-NMR}$ (CDCl_3 , 27°C , 400 MHz): δ [ppm] 0.95 (m, 6H, $H_5 + H_6$), 1.28 (m, 10H, $H_d - H_h$), 1.60–1.71 (m, 5H, $H_i + H_3 + H_4$), 2.02 (m, 2H, H_c), 2.23 (m, 2H, H_j), 4.61 (m, 1H, H_2), 4.94 (m, 2H, H_a), 5.79 (m, 1H, H_b), 5.96 (m, 1H, H_7).

N-Leu (1c): $^{13}\text{C-NMR}$ (CDCl_3 , 27°C , 100 MHz): δ [ppm] 21.9–22.8 ($C_5 + C_6$), 24.9 (C_4), 25.5 (C_i), 28.9–29.5 ($C_d - C_h$), 33.7 (C_c), 36.5 (C_j), 41.1 (C_3), 50.8 (C_2), 114.1 (C_a), 139.1 (C_b), 173.9 (C_1), 176.3 (C_k).

N-Aib (1d): $^1\text{H-NMR}$ (CDCl_3 , 27°C , 400 MHz): δ [ppm] 1.27–1.36 (m, 10H, $H_d - H_h$), 1.57–1.62 (m, 8H, $H_2 + H_3 + H_i$), 2.04 (m, 4H, H_c), 2.20 (m, 2H, H_j), 4.96 (m, 2H, H_a), 5.79 (m, 1H, H_b), 6.02 (m, 1H, H_5).

N-Aib (1d): $^{13}\text{C-NMR}$ (CDCl_3 , 27°C , 100 MHz): δ [ppm] 24.9 ($C_2 + C_3$), 25.5 (C_i), 28.9–29.5 ($C_d - C_h$), 33.7 (C_c), 36.8 (C_j), 57.0 (C_1), 114.1 (C_a), 139.1 (C_b), 174.4 (C_k), 177.2 (C_4).

N-ACHC (1e): $^1\text{H-NMR}$ (CDCl_3 , 27°C , 400 MHz): δ [ppm] 1.29–1.45 (m, 12H, $H_d - H_i$), 1.66 (m, 6H, $H_3 + H_4 + H_5$), 1.89 (m, 2H, $H_2 + H_6$), 2.04 (m, 4H, $H_c + H_2 + H_6$), 2.26 (m, 2H, H_j), 4.94 (m, 2H, H_a), 5.69 (m, 1H, H_7), 5.79 (m, 1H, H_b).

N-ACHC (1e): $^{13}\text{C-NMR}$ (CDCl_3 , 27°C , 100 MHz): δ [ppm] 21.3 ($C_3 + C_5$), 25.1–25.5 ($C_i + C_4$), 28.9–29.5 ($C_d - C_h$), 32.0–33.7 ($C_2 + C_6 + C_c$), 36.6 (C_j), 59.7 (C_1), 114.1 (C_a), 139.1 (C_b), 175.1 (C_k), 176.0 (C_4).

C-terminus functionalization

General procedure for chiral AA (2a–2c). Reactions were performed under N_2 atmosphere. N-terminus functionalized amino acid **1a–1c** (1.0 eq.) was dissolved in dried dichloromethane (20 mL) and then **A2** (1.0 eq.) was added to the mixture. The solution was cooled down to 0°C and the coupling reagents DIPEA (3.6 eq.), HOBt (13% H_2O ; 1.6 eq.) and EDC·HCl (1.6 eq.) were added successively. The mixture was allowed to

stir at room temperature for 4 hours before it was refluxed overnight. Then the solution was cooled and extracted with brine (20 mL), 1 M HCl (20 mL), brine (20 mL), saturated NaHCO₃-solution (20 mL) and brine (20 mL). The organic phase was concentrated under vacuum and the crude product was dissolved in THF (5 mL), precipitated in cold NaHCO₃ (150 mL) solution and isolated by filtration. Afterwards the obtained brown solid was dissolved in Et₂O (20 mL), dried over Na₂SO₄, filtrated and concentrated in vacuum to yield products **2a–2c** (63–86%).

N- + C-Glu (2a): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.26–1.34 (m, 20H, H_d – H_h), 1.44–1.60 (m, 4H, H_i + H_j), 2.03–2.20 (m, 6H, H₄ + H_c + H_j), 2.40 (m, 1H, H₃), 2.54 (m, 1H, H₃), 3.18 (m, 2H, H_m), 4.42 (m, 1H, H₂), 4.93 (m, 4H, H_a), 5.10 (s, 2H, H₆), 5.77 (m, 2H, H_b), 6.43 (d, ³J_{H,H} = 7.2 Hz, 1H, H₁₃), 7.31–7.45 (m, 5H, H₈ – H₁₂).

N- + C-Glu (2a): ¹³C-NMR (CDCl₃, 27 °C, 100 MHz): δ [ppm] 25.5 (C_i), 26.8 (C_i), 27.8 (C₃), 28.9–29.5 (C_d – C_h + C_j), 30.6 (C₄), 33.8 (C_c), 36.5 (C_j), 39.6 (C_m), 52.3 (C₂), 66.6 (C₆), 114.1 (C_a), 128.2–128.7 (C₈ – C₁₂), 135.8 (C₇), 139.1 (C_b), 170.9 (C₁), 173.4 (C₅), 173.4 (C_k).

N- + C-Asp (2b): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.27–1.40 (m, 22H, H_d – H_h + H_j), 1.59 (m, 2H, H_i), 2.02–2.20 (m, 6H, H₄ + H_c + H_j), 2.91 (m, 1H, H₃), 3.08 (m, 1H, H₃), 3.17 (m, 2H, H_m), 4.91 (m, 1H, H₂), 4.94 (m, 2H, H_a), 5.14 (s, 2H, H₅), 5.79 (m, 1H, H_b), 6.56 (d, ³J_{H,H} = 7.2 Hz, 1H, H₁₂), 7.31–7.45 (m, 5H, H₇ – H₁₁).

N- + C-Asp (2b): ¹³C-NMR (CDCl₃, 27 °C, 100 MHz): δ [ppm] 25.5 (C_i), 26.8 (C_i), 28.9–29.3 (C_d – C_h + C_j), 33.7 (C_c), 35.7 (C_j), 36.5 (C₃), 39.6 (C_m), 49.1 (C₂), 66.9 (C₅), 114.1 (C_a), 128.2–128.6 (C₇ – C₁₁), 135.4 (C₆), 139.2 (C_b), 170.1 (C₁), 172.1 (C₄), 173.3 (C_k).

N- + C-Leu (2c): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 0.95 (m, 6H, H₅ + H₆), 1.28–1.43 (m, 22H, H_d – H_h + H_j), 1.60–1.71 (m, 5H, H_i + H₃ + H₄), 2.02 (m, 2H, H_c), 2.20 (m, 2H, H_j), 3.22 (m, 2H, H_m), 4.61 (m, 1H, H₂), 4.94 (m, 2H, H_a), 5.79 (m, 1H, H_b), 5.96 (m, 1H, H₇).

N- + C-Leu (2c): ¹³C-NMR (CDCl₃, 27 °C, 100 MHz): δ [ppm] 21.9–22.6 (C₅ + C₆), 25.0 (C₄), 25.6 (C_i), 26.8 (C_i), 28.9–29.5 (C_d – C_h), 33.7 (C_c), 36.6 (C_j), 39.5 (C_m), 41.1 (C₃), 51.6 (C₂), 114.1 (C_a), 139.1 (C_b), 172.0 (C₁), 173.1 (C_k).

General procedure for achiral AA (2d–2e). Reactions were performed under N₂ atmosphere. To a solution of N-terminus functionalized amino acids **1d–1e** (1.0 eq.) and **A2** (1.0 eq.) in 0 °C cold dried dichloromethane (20 mL) DIPEA (4.5 eq.), DMAP (0.02 eq.) and EDC·HCl (2.6 eq.) were added successively. The solution was heated to reflux for 24 h followed by extraction with brine (20 mL), 1 M HCl (20 mL), brine (20 mL), saturated NaHCO₃-solution (20 mL) and brine (20 mL). The organic layer was separated, dried over Na₂SO₄ and concentrated in vacuum to yield **2d–2e** (78–82%).

N- + C-Aib (2d): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.27–1.36 (m, 20H, H_d – H_h), 1.50 (m, 2H, H_i), 1.55–1.62 (m, 8H, H₂ + H₃ + H_j), 2.04 (m, 4H, H_c), 2.16 (m, 2H, H_j), 3.23 (m, 2H, H_m), 4.96 (m, 2H, H_a), 5.81 (m, 1H, H_b), 6.08 (m, 1H, H₅), 6.65 (m, 1H, H₅).

N- + C-Aib (2d): ¹³C-NMR (CDCl₃, 27 °C, 100 MHz): δ [ppm] 24.8 (C₂ + C₃), 25.5 (C_i), 26.8 (C_i), 28.9–29.5 (C_d – C_h), 33.8 (C_c),

37.4 (C_j), 39.8 (C_j), 57.4 (C₁), 114.1 (C_a), 139.1 (C_b), 173.4 (C_k), 174.5 (C₄).

N- + C-ACHC (2e): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.29–1.47 (m, 24H, H_d – H_i + H_j), 1.64 (m, 6H, H₃ + H₄ + H₅), 1.88 (m, 2H, H₂ + H₆), 2.04 (m, 6H, H_c + H₂ + H₆), 2.21 (m, 2H, H_j), 3.20 (m, 2H, H_m), 4.97 (m, 4H, H_a), 5.30 (m, 1H, H₇), 5.79 (m, 2H, H_b).

N- + C-ACHC (2e): ¹³C-NMR (CDCl₃, 27 °C, 100 MHz): δ [ppm] 21.6 (C₃ + C₅), 25.1–25.5 (C_i + C₄), 26.9 (C_i), 28.9–29.5 (C_d – C_h + C_j), 32.0–33.8 (C₂ + C₆ + C_c), 37.5 (C_j), 39.5 (C_m), 59.7 (C₁), 114.1 (C_a), 139.1 (C_b), 175.1 (C_k), 176.0 (C₄).

ADMET-polymerization. Polymerization of the monomers **2a–2e** was done as bulk polymerization, following the methods proposed by Wagener *et al.* in the past.¹⁶ The solid monomers were placed in a dried Schlenk tube, removing oxygen by flushing with nitrogen, subsequently heating in an oil bath to 65 °C. After the monomer becomes liquid, the appropriate amount of the chosen catalyst (100 : 1 monomer to catalyst ratio) was added to the bulk. Vacuum and repeated cycles flushing with nitrogen are applied during the reaction to remove evolving ethylene, further small amount of catalyst were additionally added to the bulk-reaction mixture after several hours. Due to increasing viscosity during polymerization the reaction temperature was increased stepwise starting from 65 °C up to 165 °C (for the last hour) and afterwards the reaction was quenched by adding THF and precipitating of the obtained polymer into cold MeOH to yield **3a–3e** (61–87%).

ADMET-Glu (3a): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.26–1.34 (m, H_{rep.unit}, H_d – H_h), 1.44–1.59 (m, H_{rep.unit}, H_i + H_j), 1.95–2.01 (m, H_{rep.unit}, H₄ + H_c), 2.16 (m, H_{rep.unit}, H_j), 2.41 (m, H_{rep.unit}, H₃), 2.55 (m, H_{rep.unit}, H₃), 3.20 (m, H_{rep.unit}, H_m), 4.41 (m, H_{rep.unit}, H₂), 4.96 (m, 4H, H_a), 5.10 (s, H_{rep.unit}, H₆), 5.36 (m, H_{rep.unit}, H_x + H_y), 5.79 (m, 2H, H_b), 7.34 (m, H_{rep.unit}, H₈ – H₁₂).

ADMET-Asp (3b): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.19–1.28 (m, H_{rep.Einheit}, H_d – H_h), 1.43 (m, H_{rep.Einheit}, H_i), 1.58 (m, H_{rep.Einheit}, H_i), 1.95 (m, H_{rep.Einheit}, H_c), 2.18 (m, H_{rep.Einheit}, H_j), 2.68 (m, H_{rep.Einheit}, H₃), 2.90 (m, H_{rep.Einheit}, H₃), 3.16 (m, H_{rep.Einheit}, H_m), 4.78 (m, H_{rep.Einheit}, H₂), 4.96 (m, 4H, H_a), 5.13 (m, H_{rep.Einheit}, H₅), 5.36 (m, H_{rep.Einheit}, H_x + H_y), 5.79 (m, 2H, H_b), 7.33 (m, H_{rep.Einheit}, H₇ – H₁₁).

ADMET-Leu (3c): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 0.87 (m, H_{rep.Einheit}, H₅ + H₆), 1.19–1.38 (m, 12H, H_d – H_h + H_j), 1.46–1.66 (m, H_{rep.Einheit}, H₃ + H₄ + H_i), 2.03 (m, H_{rep.Einheit}, H_c), 2.17 (m, H_{rep.Einheit}, H_j), 3.19 (m, H_{rep.Einheit}, H_i), 4.48 (m, H_{rep.Einheit}, H₂), 4.90 (m, 4H, H_a), 5.35 (m, H_{rep.Einheit}, H_x + H_y), 5.78 (m, 2H, H_b).

ADMET-Aib (3d): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.27–1.36 (m, H_{rep.unit}, H_d – H_h), 1.48 (m, H_{rep.unit}, H_i), 1.55–1.59 (m, H_{rep.unit}, H₂ + H₃ + H_j), 1.94 (m, H_{rep.unit}, H_c), 2.16 (m, H_{rep.unit}, H_j), 3.23 (m, H_{rep.unit}, H_m), 4.96 (m, 2H, H_a), 5.36 (m, H_{rep.unit}, H_x + H_y), 5.76 (m, 1H, H_b), 6.08 (m, H_{rep.unit}, H₅), 6.65 (m, H_{rep.unit}, H₆).

ADMET-ACHC (3e): ¹H-NMR (CDCl₃, 27 °C, 400 MHz): δ [ppm] 1.23–1.47 (m, H_{rep.unit}, H_d – H_h + H_i + H_j), 1.62 (m, H_{rep.unit}, H₃ + H₄ + H₅), 1.86 (m, H_{rep.unit}, H₂ + H₆), 1.94–2.12 (m, H_{rep.unit}, H_c + H₂ + H₆), 2.21 (m, H_{rep.unit}, H_j), 3.20 (m, H_{rep.unit}, H_m), 4.91 (m, 4H, H_a), 5.35 (m, H_{rep.unit}, H_x + H_y), 5.78 (m, 2H, H_b).

Monomer synthesis

Conceptually, the amino acids were introduced in the polymer structure by the fixation of two ω -alkenyl-chains of equal length on either side. Therefore, *N*- and *C*-terminus functionalization was realized by reaction of the amino acid with 10-undecenoyl chloride and afterwards coupling with 10-undecen-1-amine (**A2**) (see Scheme 1).

ADMET-Glu H (**4a**): $^1\text{H-NMR}$ ($\text{CDCl}_3 + 15 \text{ vol\% TFA}$, 27°C , 400 MHz): δ [ppm] 0.87 (m, 6H, H_z), 1.25–1.34 (m, $H_{\text{rep.unit}}$, $H_b - H_h + H_x + H_y$), 1.54–1.60 (m, $H_{\text{rep.unit}}$, $H_i + H_l$), 2.00–2.16 (m, $H_{\text{rep.unit}}$, H_3), 2.39 (m, $H_{\text{rep.unit}}$, H_4), 2.54 (m, $H_{\text{rep.unit}}$, H_j), 3.29 (m, $H_{\text{rep.unit}}$, H_m), 4.73 (m, $H_{\text{rep.unit}}$, H_2), 7.21 (m, $H_{\text{rep.unit}}$, H_{13}), 7.81 (m, $H_{\text{rep.unit}}$, H_{14}).

ADMET-Asp H (**4b**):¹H-NMR (CDCl₃ + 15 vol% TFA, 27 °C, 400 MHz): δ [ppm] 0.87 (m, 6H, H_z), 1.19–1.28 (m, $H_{\text{rep.unit}}$, $H_b - H_h + H_x + H_y$), 1.59 (m, $H_{\text{rep.Einheit}}$, $H_i + H_l$), 2.35 (m, $H_{\text{rep.Einheit}}$, H_j), 3.01 (m, $H_{\text{rep.Einheit}}$, H_3), 3.24 (m, $H_{\text{rep.Einheit}}$, H_3), 3.59 (m, $H_{\text{rep.Einheit}}$, H_m), 4.50 (m, $H_{\text{rep.Einheit}}$, H_2), 7.05 (m, $H_{\text{rep.unit}}$, $H_{12} + H_{13}$).

General procedure for hydrogenation of the polymers without a protecting group in the side chain (4c–4e). To a solution of the polymer **3c–3e** (1.0 eq.) in DMF TsNHNH₂ (5.0 eq. per double bond) and DIPEA (5.0 eq.) were added. The solution was heated up to 150 °C for 6 hours. The resulting mixture was cooled to room temperature and dialyzed against MeOH for 3 days to yield the hydrogenated polymers **4c–4e** (67–83%).

ADMET-Leu H (**4c**): $^1\text{H-NMR}$ ($\text{CDCl}_3 + 15 \text{ vol\% TFA}$, 27°C , 400 MHz): δ [ppm] 0.89 (m, $\text{H}_{\text{rep.Einheit}}$, $H_5 + H_6 + H_z$), 1.19–1.38 (m, 12H , $H_b - H_h + H_x + H_y$), 1.50–1.59 (m, $\text{H}_{\text{rep.Einheit}}$, $H_3 + H_4 + H_i + H_l$), 2.32 (m, $\text{H}_{\text{rep.Einheit}}$, H_j), 3.25 (m, $\text{H}_{\text{rep.Einheit}}$, H_m), 4.54 (m, $\text{H}_{\text{rep.Einheit}}$, H_2), 7.19 (m, $\text{H}_{\text{rep.Einheit}}$, H_7), 7.39 (m, $\text{H}_{\text{rep.Einheit}}$, H_8).

ADMET-Aib H (**4d**): $^1\text{H-NMR}$ ($\text{CDCl}_3 + 15 \text{ vol\% TFA}$, 27°C , 400 MHz): δ [ppm] 0.88 (m, 6H, H_z), 1.25 (m, $H_{\text{rep.unit}}$, $H_b - H_h + H_i + H_x + H_y$), 1.55–1.59 (m, $H_{\text{rep.unit}}$, $H_2 + H_3 + H_i$), 2.28 (m, $H_{\text{rep.unit}}$, H_j), 3.29 (m, $H_{\text{rep.unit}}$, H_m), 6.70 (m, $H_{\text{rep.unit}}$, H_5), 6.99 (m, $H_{\text{rep.unit}}$, H_6).

ADMET-ACHC H (**4e**): $^1\text{H-NMR}$ ($\text{CDCl}_3 + 15 \text{ vol\% TFA}$, 27°C , 400 MHz): δ [ppm] 0.88 (m, 6H, H_z), 1.27–1.46 (m, $H_{\text{rep.unit}}$, $H_b - H_h + H_l + H_x + H_y + H_i$), 1.74 (m, $H_{\text{rep.unit}}$, $H_3 + H_4 + H_5$), 1.96–2.31 (m, $H_{\text{rep.unit}}$, $H_j + H_2 + H_6$), 3.37 (m, $H_{\text{rep.unit}}$, H_m), 7.12–7.26 (m, $H_{\text{rep.unit}}$, $H_7 + H_8$).

Results and discussion

The synthesis of the polymers was accomplished by ADMET polymerization of the chosen *N*- and *C*-terminus ω -alkene-chain functionalized amino acids. For the investigation of the influence on the chiral/achiral and polar/nonpolar nature of the amino acids on the crystallization behavior, chiral/polar amino acids glutamic (Glu) and aspartic acid (Asp), chiral/unpolar ι -leucine (Leu) and achiral/unpolar 2-amino-2-methylpropanoic (Aib) acid and 1-aminocyclohexane-carboxylic acid (ACHC) were functionalized with terminal ω -alkenyl-group, polymerized by ADMET and hydrogenated (Fig. 1).

Scheme 1 Synthesis for (a) *N*- + C-terminus functionalized monomers **2a–2e** and (b) ADMET-polymers **3a–3e** and hydrogenated/deprotected polymers **4a–4e**.

This journal is © The Royal Society of Chemistry 2017

Table 2 Obtained molecular weights calculated by NMR and GPC, PDI's, yields and *trans* : *cis* ratio of the internal double bonds for ADMET-polymerization of the monomers **2a–2e** to polymers **3a–3e** by using different types of catalyst

Polymer	R ₁	R ₂	Cat.	M _n GPC (Da)	M _n NMR (Da)	DP (<i>n</i>)	PDI	<i>trans</i> : <i>cis</i> ratio	Yield (%)
3a		H	Grubbs 1 st	7600	9200	17	1.7	68 : 32	77
			Grubbs 2 nd	700	800	2	1.5	89 : 11	67
			GH 1 st	2300	2400	5	2.2	78 : 22	70
3b		H	Grubbs 1 st	10 500	22 000	41	1.9	68 : 32	87
			Grubbs 2 nd	800	700	2	1.4	82 : 18	61
			GH 1 st	4000	5400	10	1.5	72 : 28	72
3c		H	Grubbs 1 st	3500	4300	10	1.8	75 : 25	73
			Grubbs 2 nd	1000	700	2	1.4	78 : 22	69
			GH 1 st	4100	5500	12	1.6	76 : 24	71
3d	Me	Me	Grubbs 1 st	2500	3000	7	1.4	79 : 21	73
			Grubbs 1 st	9400	14 600	32	1.9	76 : 24	70
			GH 1 st	11 500	18 200	40	1.9	79 : 21	62

Table 3 Obtained molecular weights calculated by NMR, DP and yields of the unsaturated ADMET polymers **3a–3e** obtained with Grubbs 1st catalyst and saturated polymers **4a–4e**

Polymer	M _n NMR (Da)	DP (<i>n</i>)	Yield (%)
3a	9200	17	77
4a	8400	19	72
3b	22 000	41	87
4b	18 500	43	79
3c	4300	10	73
4c	— ^a	—	62
3d	3000	7	73
4d	3100	7	55
3e	14 600	32	70
4e	15 500	33	85

^a Calculation of M_n not possible due to overlapping of the methyl end groups and methyl groups in the repeating unit.

NMR spectra of **4c**. Furthermore, protons next to the terminal double bonds at 2.0 ppm are disappearing and signals for the methyl groups at 0.9 ppm become broader due to protons of the resulting methyl end group. The successful deprotection of the benzyl-group in the case of **4a** and **4b** can be proven by the disappearance of the signals of the CH₂-group next to the aromatic system at 5.1 ppm as well as the characteristic aromatic system signals at 7.3 ppm which is shown in Fig. 3. New methyl end-group can be detected at 0.9 ppm and was used for calculation of the molecular weight, indicating successful hydrogenation of the double bonds, whereas all other signals are still present showing slightly changed chemical shifts due to interaction with TFA molecules. Degree of polymerization (DP) calculated for the hydrogenated polymers **4a**, **4b**, **4d** and **4e** are always higher as for unsaturated polymers.

All other NMR-spectra of the ADMET- and hydrogenated polymers are shown in the ESI (Fig. S31–S36†). The successful hydrogenation can also be proven in IR-spectroscopy by disappearance of the deformation vibration band of the double bonds at 990 cm^{−1} and 915 cm^{−1} in the IR spectrum (Fig. S42–S51†).

MALDI-ToF-MS analysis

In Fig. 4 and 5 MALDI-ToF-MS spectra of the ADMET-polymer **3b** and the hydrogenated polymer **4e** are shown. All other MALDI-ToF-MS spectra are shown in Fig. S42–S51† with the exception of **3d**, **4a** and **4d**, which cannot be detected under the chosen conditions. The MS spectra of the ADMET-polymer **3b** (Fig. 4) shows a mass distribution from 1091 g mol^{−1} to 4165 g mol^{−1} (Fig. 4a) with a maximum peak at 1604.041 g mol^{−1}. Two series can be assigned and the distance between signals of the same series amounts to 512 g mol^{−1}. The distance between signals of different series is 14 g mol^{−1}, in which the signal with the lower molecular weight has always a lower intensity (Fig. 4b). This signal indicates the loss of a CH₂-group during ADMET-polymerization due to olefin isomerization, leading to polymers having a slightly different chain length of the alkyl chain,^{46,54} with a small amount of isomerization in *e.g.* **3b**. The low isomerization rate can be proven by the appearance of only one series displaying isomerization products for **3b** and three series for **4e** (Fig. 5), whereas high isomerization rates have been observed at cysteine functionalized polymers, resulting in 6 series of isomerized side products.⁵⁴ The signal at 2117 g mol^{−1} can be assigned to the polymer [E-M₂-EK]⁺ with potassium as counter ion, which is confirmed by the agreement of the experimental and simulated data (see Fig. 4c). Thus, the obtained main series definitely indicates the expected polymer structure by ADMET polymerization including internal and

Fig. 2 ^1H -NMR spectra of monomer **2c** (top), ADMET-polymer **3c** (middle) and hydrogenated polymer **4c** (bottom) in CDCl_3 . For **4c** 15 vol%. TFA was added.

external double bonds and the loss of ethylene in the repeating unit.

For polymer **4e** (Fig. 5) a mass distribution from 937 g mol^{-1} to 2242 g mol^{-1} is obtained, in which the highest absorption peak at 1372 g mol^{-1} indicates the polymer structure $[\text{E-M-EK}]^+$. Distance

between the main series is 434 g mol^{-1} , which is in agreement with the molecular weight of the repetitive unit. In addition to the obtained main series up to three different series with a distance of 14 g mol^{-1} can be observed, again indicating the isomerization of the olefin. In comparison to **3b**, the isomerization is higher and

Fig. 3 ^1H -NMR spectra of monomer **2b** (top), ADMET-polymer **3b** (middle) and hydrogenated polymer **4b** (bottom) in CDCl_3 . For **4b** 15 vol%. TFA was added.

Fig. 4 (a) MALDI-ToF-MS of ADMET polymer **3b** (b) zoom in to $[E-M_2-EK]^+$ to show isomerization of the olefin (c) measured and simulated pattern for $[E-M_2-EK]^+$.

occurs at more than one site. The main series however proves the complete hydrogenation of the polymer.

DSC analysis

The thermal properties of the hydrogenated polymer in comparison to the monomer and the unsaturated polymers were investigated by DSC-measurements. Fig. 6 shows the cooling and heating curve for the monomers **2a** and **2b** (dotted lines) and the polymers **4a** and **4b** (straight lines) after ADMET and hydrogenation.

For monomer **2a** melting at 53 °C and crystallization at −10 °C could be observed, whereas monomer **2b** has

a significant higher melting and crystallization point ($T_m = 64.4$ °C; $T_c = 34.7$ °C). After ADMET-polymerization the investigated compounds **3a–3e** become completely amorphous, presumably due to sterically hindrance caused by incorporation of the internal double bonds into the polymer. Crystallization of such polymers strongly depends on the packing of the alkyl chains, which in this case is limited due to the presence of the thus different olefin isomers and the incorporated amino acid in the polymer backbone.

After hydrogenation and deprotection the polymers **4a** and **4b** display a crystalline structure as visible by their melting points. In comparison to the corresponding monomer, melting and crystallization of **4a** and **4b** shifts to significantly higher temperatures, in which **4b** has a higher melting and crystallization temperature than **4a**. However, in comparison to the unsaturated monomers and polymer **4a**, DSC-curves of **4b** are more complex. Melting at 122.8 °C and 142.9 °C indicate a melting-recrystallization, which can be due to formation of metastable crystals during the cooling process.⁵⁵ Such crystals are melting first and reorganizing again into more stable areas resulting in an exothermal signal in the DSC curve. These areas are melting later, similar to the behavior found for precision polyolefines with different functional groups acting as defects.⁵⁶ Furthermore, two crystallization temperatures can be observed at 103.6 °C and 74.4 °C, which may be due to microphase separation. In Table 4 thermal behavior as well as characteristic melting and crystallization data of these samples are summarized.

These observations indicate the big influence of the molecular size and hydrogen-bonding of the amino acids acting as

Fig. 5 (a) MALDI-ToF-MS of ADMET polymer **4e** (b) zoom in to $[E-M-EK]^+$ to show isomerization of the olefin (c) measured and simulated pattern for $[E-M-EK]^+$.

Fig. 6 (a) DSC thermograms of monomer **2a** (dotted lines) and the hydrogenated polymer **4a** (straight lines) (b) DSC thermograms of monomer **2b** (dotted lines) and the hydrogenated polymer **4b** (straight lines).

defects, in which the polymer **4b** bearing aspartic acid after every 19th carbon shows a higher melting and crystallization temperatures than **4a**. Such effects of the defect size on the melting and crystallization were reported early *e.g.* for alkyl branches²⁷ and butyl branched polyethylene's and polyphosphoester's.²⁸

For all other monomers **2c–2e** and polymers **4c–4e** no crystalline behavior could be observed as those amino acids with an aliphatic backbone disturbed crystallinity, whereas amino acids with a functional group able to form defined crystal structures. Thus, an additional intermolecular interaction of the carboxylic-acid-defects is proposed for crystallization of the samples, *e.g.* by dimerization of the carboxylic-acid moieties.

XRD-analysis

Crystalline structure of polymers **4a** and **4b** was pre-investigated by WAXS measurements (Fig. 7), observing four reflections for both polymers (Table 5). The first reflection in the small angle

area at a 2θ of 3.09° for **4a** and 3.60° and **4b** is the (001) reflection, indicative of the distance between two amino acid groups along the chain of 2.86 nm for **4a** and 2.45 nm for **4b**, which is in good agreement with the length of the precision polymers. At almost exactly the doubled value of 2θ higher order reflection (002) can be detected which was also found for precision sulfone polyethylenes,³¹ demonstrating that the reflection intensity for **4a** is not as intensive as for **4b**. These (002) reflections are describing the evolution of a lamellar morphology and both (001) and (002) reflections could have also been observed for other precision PE-polymers of different methylene sequences lengths bearing DAP-units at 16th, 18th or 20th carbon atom, shifting to higher 2θ values with decreasing length of the alkyl chain.⁵⁷ Formation of lamellae in **4a** could be more hindered than in **4b**, caused by the glutamic acid as a major defect, so that the intensity of this reflex for **4a** is significantly smaller than for **4b**. As previously reported for ADMET-PE and high density polyethylene, two characteristic reflections at scattering angles of 21.7° and 24.0° can be detected, containing information about crystal morphology of the alkyl chains and corresponding to (110) and (200) reflections of a orthorhombic crystal system.⁵⁸ For both polymers **4a** and **4b**, broad reflections with maxima at 2θ of 19.58° and 21.33° and 18.98° and 20.68° can be observed and thus the crystalline structure is definitely dissimilar to ADMET-PE.^{19,27} The width of the signals can be explained due to the low crystallinity as the defects are large, in accordance with DSC data and literature.²⁷ Similar to other precision PE-polymers of different methylene spacer length bearing alkyl moieties^{19,27} chlorines²⁵ and *meta*-substituted aryl ether branches⁵⁶ in the main backbone it is likely that orthorhombic, triclinic and other metastable crystal systems are coexistent as supported by the strong asymmetric distribution of the reflections.^{19,27} Corresponding to the observations for ADMET-polyethylene containing *m*-substituted arylene the amino acid defect presumably can either be excluded from or included into the PE crystals.⁵⁶

Table 4 Thermal behavior of the monomers and polymers with aspartic acid and glutamic acid acting as defects (**2a–4a** and **2b–4b**)

Amino acid	R ₁	T _m (°C)	T _c (°C)	ΔH (J g ⁻¹)	α (%)
Glu	2a	52.8	-10.1	60.9	25
	3a	—	—	—	—
	4a	88.2	69.5	26.1	11
	2b	64.4	34.7	51.4	21
Asp	3b	—	—	—	—
	4b	142.8	103.6	60.9	25

Fig. 7 Wide-angle-X-ray diffraction patterns for precision oligomers **4a** and **4b**.

Table 5 Obtained WAXS data for hydrogenated polymers **4a** and **4b**

Sample	Reflection	$2\theta/^\circ$	q/nm^{-1}	d/nm
4a	1	3.09	2.20	2.86
	2	6.21	4.42	1.42
	3	19.58	13.87	0.45
	4	21.33	15.10	0.42
4b	1	3.60	2.56	2.45
	2	7.14	5.08	1.24
	3	18.98	13.46	0.47
	4	20.68	14.64	0.43

Conclusion

We here report a strategy for the synthesis and characterization of newly developed precision polyalkyl-polymers with amino acid defects at every 19th CH₂ carbon atom. Chiral/achiral as well as polar/nonpolar amino acids were functionalized on the *N*- and *C*-terminus with alkyl branches, bearing terminal double bonds at each end. The synthesis of precision polymers with molecular weights up to 22 kDa was realized by ADMET polymerization under melt-polymerization conditions, followed by complete hydrogenation of the internal double bonds with *p*-toluenesulfonylhydrazide (TsNHNH₂). For ADMET polymerization Grubbs 1st, Grubbs 2nd and Grubbs Hoveyda 1st catalyst were tested, the former was found to be the best catalyst in handling and in synthesizing low isomerized, high molecular weight polymers in good yields, proving the structures of the obtained products by ¹H-NMR, GPC, MALDI-ToF-MS and IR. Thermal investigation of the monomers and polymers demonstrated that all compounds having unpolar amino acids (*L*-leucine, 2-amino-2-methylpropanoic acid, 1-aminocyclohexanecarboxylic acid) in the chain are amorphous, whereas the monomers and the hydrogenated polymers of polar amino acids (glutamic and aspartic acid) show crystalline morphologies. Melting points for glutamic acid modified monomers and

polymers are lower in comparison to aspartic acid, demonstrating that the bigger the size of the defect the lower the ability to pack into an ordered structure. The hydrogenated polymer bearing aspartic acid moieties (**4b**) shows a complex thermal behavior, which is represented by melting-recrystallization and two crystallization points. WAXD-measurements show four reflections for both **4a** and **4b**, indicating a distance between the two amino acid groups of 2.86 nm for **4a** and 2.45 nm for **4b** along the PE-chain, together with the formation of a lamellar structure. We also assume an orthorhombic crystal in which amino acids can either be excluded from or included into the PE crystals – a final statement however cannot be accomplished on basis of the current data.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The author grateful acknowledge the grant within the Sonderforschungsbereich SFB TRR 102 (Polymers under multiple constraints) (SR, WHB, Project A03). We also thank Sophie Reimann for MALDI-ToF-MS and Silvio Poppe and Matthias Fischer for providing WAXS measurement.

References

- 1 R. M. Michell, A. Mugica, M. Zubitur and A. J. Müller, in *Polymer Crystallization I: From Chain Microstructure to Processing*, ed. F. Auriemma, G. C. Alfonso and C. de Rosa, Springer International Publishing, Cham, 2017, pp. 215–256, DOI: 10.1007/12_2015_327.
- 2 F. S. Bates, *Macromolecules*, 1984, **17**, 2607–2613.
- 3 G. Strobl, in *The Physics of Polymers Concepts for Understanding Their Structures and Behavior*, Springer

- International Publishing, Berlin, Heidelberg, New York, 2007, pp. 215–256, DOI: 10.1007/12_2015_327.
- 4 E. Haber and C. B. Anfinsen, *J. Biol. Chem.*, 1961, **236**, 1361.
 - 5 V. Percec, G. Ungar and M. Peterca, *Science*, 2006, **313**, 55–56.
 - 6 P. Jonkheijm, P. van der Schoot, A. P. H. J. Schenning and E. W. Meijer, *Science*, 2006, **313**, 80–83.
 - 7 B. Heck, T. Hugel, M. Iijima and G. Strobl, *Polymer*, 2000, **41**, 8839–8848.
 - 8 J. Adamcik and R. Mezzenga, *Macromolecules*, 2012, **45**, 1137–1150.
 - 9 I. W. Hamley, *Chem. Rev.*, 2012, **112**, 5147–5192.
 - 10 F. J. Baltá-Calleja and R. Hosemann, *J. Polym. Sci., Polym. Phys. Ed.*, 1980, **18**, 1159–1165.
 - 11 J. Martinez De Salazar and F. J. Baltá-Calleja, *J. Cryst. Growth*, 1980, **48**, 283–294.
 - 12 F. Gutzler and G. Wegner, *Colloid Polym. Sci.*, 1980, **258**, 776–786.
 - 13 J. M. Salazar and F. J. B. Calleja, *Polym. Bull.*, 1980, **2**, 163–167.
 - 14 E. Martuscelli and M. Pracella, *Polymer*, 1974, **15**, 306–314.
 - 15 C. L. F. De Ten Hove, J. Penelle, D. A. Ivanov and A. M. Jonas, *Nat. Mater.*, 2004, **3**, 33–37.
 - 16 H. Li, L. Caire da Silva, M. D. Schulz, G. Rojas and K. B. Wagener, *Polym. Int.*, 2017, **66**, 7–12.
 - 17 P. Atallah, K. B. Wagener and M. D. Schulz, *Macromolecules*, 2013, **46**, 4735–4741.
 - 18 H. Mutlu, L. M. de Espinosa and M. A. R. Meier, *Chem. Soc. Rev.*, 2011, **40**, 1404–1445.
 - 19 B. Inci, I. Lieberwirth, W. Steffen, M. Mezger, R. Graf, K. Landfester and K. B. Wagener, *Macromolecules*, 2012, **45**, 3367–3376.
 - 20 G. Lieser, G. Wegner, J. A. Smith and K. B. Wagener, *Colloid Polym. Sci.*, 2004, **282**, 773–781.
 - 21 W. Qiu, J. Sworen, M. Pyda, E. Nowak-Pyda, A. Habenschuss, K. B. Wagener and B. Wunderlich, *Macromolecules*, 2006, **39**, 204–217.
 - 22 M. Tasaki, H. Yamamoto, M. Hanesaka, K. Tashiro, E. Boz, K. B. Wagener, C. Ruiz-Orta and R. G. Alamo, *Macromolecules*, 2014, **47**, 4738–4749.
 - 23 P. Kaner, C. Ruiz-Orta, E. Boz, K. B. Wagener, M. Tasaki, K. Tashiro and R. G. Alamo, *Macromolecules*, 2014, **47**, 236–245.
 - 24 E. Boz, A. J. Nemeth, K. B. Wagener, K. Jeon, R. Smith, F. Nazirov, M. R. Bockstaller and R. G. Alamo, *Macromolecules*, 2008, **41**, 1647–1653.
 - 25 R. G. Alamo, K. Jeon, R. L. Smith, E. Boz, K. B. Wagener and M. R. Bockstaller, *Macromolecules*, 2008, **41**, 7141–7151.
 - 26 E. Boz, K. B. Wagener, A. Ghosal, R. Fu and R. G. Alamo, *Macromolecules*, 2006, **39**, 4437–4447.
 - 27 G. Rojas, B. Inci, Y. Wei and K. B. Wagener, *J. Am. Chem. Soc.*, 2009, **131**, 17376–17386.
 - 28 Y.-R. Zheng, H. T. Tee, Y. Wei, X.-L. Wu, M. Mezger, S. Yan, K. Landfester, K. Wagener, F. R. Wurm and I. Lieberwirth, *Macromolecules*, 2016, **49**, 1321–1330.
 - 29 K. N. Bauer, H. T. Tee, I. Lieberwirth and F. R. Wurm, *Macromolecules*, 2016, **49**, 3761–3768.
 - 30 M. Pulst, M. H. Samiullah, U. Baumeister, M. Prehm, J. Balko, T. Thurn-Albrecht, K. Busse, Y. Golitsyn, D. Reichert and J. Kressler, *Macromolecules*, 2016, **49**, 6609–6620.
 - 31 T. W. Gaines, E. B. Trigg, K. I. Winey and K. B. Wagener, *Macromol. Chem. Phys.*, 2016, **217**, 2351–2359.
 - 32 T. W. Baughman and K. B. Wagener, in *Metathesis Polymerization*, ed. M. R. Buchmeiser, Springer Berlin Heidelberg, Berlin, Heidelberg, 2005, pp. 1–42, DOI: 10.1007/b101318.
 - 33 F. Sanda and T. Endo, *Macromol. Chem. Phys.*, 1999, **200**, 2651–2661.
 - 34 H. Kudo, F. Sanda and T. Endo, *Macromolecules*, 1999, **32**, 8370–8375.
 - 35 F. Sanda, T. Abe and T. Endo, *J. Polym. Sci., Part A: Polym. Chem.*, 1997, **35**, 2619–2629.
 - 36 J. Morcellet-Sauvage, M. Morcellet and C. Loucheux, *Makromol. Chem.*, 1981, **182**, 949–963.
 - 37 J. Morcellet-Sauvage, M. Morcellet and C. Loucheux, *Makromol. Chem.*, 1982, **183**, 821–829.
 - 38 H. D. Maynard, S. Y. Okada and R. H. Grubbs, *J. Am. Chem. Soc.*, 2001, **123**, 1275–1279.
 - 39 H. D. Maynard, S. Y. Okada and R. H. Grubbs, *Macromolecules*, 2000, **33**, 6239–6248.
 - 40 J. K. Kammeyer, A. P. Blum, L. Adamiak, M. E. Hahn and N. C. Gianneschi, *Polym. Chem.*, 2013, **41**, 3929–3933.
 - 41 R. B. Breitenkamp, Z. Ou, K. Breitenkamp, M. Muthukumar and T. Emrick, *Macromolecules*, 2007, **40**, 7617–7624.
 - 42 T. E. Hopkins, J. H. Pawlow, D. L. Koren, K. S. Deters, S. M. Solivan, J. A. Davis, F. J. Gómez and K. B. Wagener, *Macromolecules*, 2001, **34**, 7920–7922.
 - 43 F. N. Behrendt and H. Schlaad, *Polym. Chem.*, 2017, **8**, 366–369.
 - 44 J. K. Leonard, T. E. Hopkins, K. Chaffin and K. B. Wagener, *Macromol. Chem. Phys.*, 2008, **209**, 1485–1494.
 - 45 K. M. Lambert, J. M. Bobbitt, S. A. Eldirany, L. E. Kissane, R. K. Sheridan, Z. D. Stempel, F. H. Sternberg and W. F. Bailey, *Chem.-Eur. J.*, 2016, **22**, 5156–5159.
 - 46 V. I. Petkovska, T. E. Hopkins, D. H. Powell and K. B. Wagener, *Anal. Chem.*, 2006, **78**, 3624–3631.
 - 47 F. C. Courchay, J. C. Sworen, I. Ghiviriga, K. A. Abboud and K. B. Wagener, *Organometallics*, 2006, **25**, 6074–6086.
 - 48 S. E. Lehman and K. B. Wagener, *Macromolecules*, 2002, **35**, 48–53.
 - 49 Y. Schrodi, *Aldrichimica Acta*, 2007, **40**, 45.
 - 50 S. Kobayashi, L. M. Pitet and M. A. Hillmyer, *J. Am. Chem. Soc.*, 2011, **133**, 5794–5797.
 - 51 Z.-L. Li, L. Li, X.-X. Deng, L.-J. Zhang, B.-T. Dong, F.-S. Du and Z.-C. Li, *Macromolecules*, 2012, **45**, 4590–4598.
 - 52 E. B. Berda and K. B. Wagener, *Macromolecules*, 2008, **41**, 5116–5122.
 - 53 S. Reimann, U. Baumeister and W. H. Binder, *Macromol. Chem. Phys.*, 2014, **215**, 1929.
 - 54 V. I. Petkovska, T. E. Hopkins, D. H. Powell and K. B. Wagener, *Macromolecules*, 2005, **38**, 5878–5885.
 - 55 S. Song, W. Miao, Z. Wang, D. Gong and Z.-R. Chen, *Polymer*, 2015, **64**, 76–83.

- 56 S.-F. Song, Y.-T. Guo, R.-Y. Wang, Z.-S. Fu, J.-T. Xu and Z.-Q. Fan, *Macromolecules*, 2016, **49**, 6001–6011.
- 57 S. Reimann, V. Danke, M. Beiner and W. H. Binder, *J. Polym. Sci., Part A: Polym. Chem.*, 2017, **55**, 3736–3748.
- 58 M. F. Butler, A. M. Donald, W. Bras, G. R. Mant, G. E. Derbyshire and A. J. Ryan, *Macromolecules*, 1995, **28**, 6383–6393.