RSC Advances



PAPER

View Article Online
View Journal | View Issue



Cite this: RSC Adv., 2018, 8, 14654

Carbon-free energetic materials: computational study on nitro-substituted BN-cage molecules with high heat of detonation and stability†

Xin Zeng, D Nan Li * and Qingjie Jiao*

A new series of high-energy density materials (HEDMs) $B_6N_6H_{6-n}(NO_2)_n$ (n=1-6) are studied at the M06-2X/6-311++G**, ω B97XD/6-311++G** and B3LYP/6-311++G** levels. Analysis of the structural changes caused by substituting the NO_2 and the electronic structures, such as electron localization function (ELF), Wiberg bond index (WBI), charge transfer and bond dissociation energies (BDE), provide important insights into the essence of the chemical characteristics and stability. Moreover, the Born–Oppenheimer molecular dynamic (BOMD) simulation is performed to verify their stability, which suggests that only the BN-cage derivatives with one and two nitro groups bonding with boron atoms (NO₂-1-1 and NO₂-2-1) can remain stable under ambient conditions. To predict the detonation performance and sensitivity of these two stable BN-cage energetic molecules accurately, the density, gas phase enthalpy of formation, enthalpy of sublimation, detonation performance, impact sensitivity and BDE are calculated systematically. The calculation results show that both NO_2 -1-1 and NO_2 -2-1 have a higher heat of detonation, higher value of h_{50} , and larger BDE of trigger bonds than CL-20.

Received 19th December 2017 Accepted 3rd April 2018

DOI: 10.1039/c7ra13476b

rsc.li/rsc-advances

Introduction

High-energy density materials (HEDMs) with both superior detonation performance and low sensitivity have always drawn the attention of research scientists. ¹⁻¹¹ The increased energy density often comes at the expense of molecular stability. Seeking new HEDMS with a fine balance between high detonation performance and low sensitivity remains to be an interesting, but very challenging task.

It is recognized that the best known explosive with superior detonation performance is 2,4,6,8,10,12-hexanitro-2,4,6,8,10,12-hexaazatetracyclo[5.5.0.0.0]dodecane (HNIW or CL-20), which was successfully synthesized by Nielsen in 1987. Besides the energetic functional groups, the large strain energy of its cage skeleton also allows CL-20 to store a high amount of energy. Currently, boron containing energetic materials have captured a great deal of attention in energetic materials research. The addition of boron in both micro and nano sizes into energetic materials can increase the energy output effectively and improve the detonation properties due to its high heat of combustion (36.3 kJ mol⁻¹, 1.9 times than that of aluminum). Thus, from the point of view of energy release during combustion, boron-

and nitrogen-containing complexes could be a good choice for developing high energy materials.

Inspired by this, we attempted to replace the C atoms of CL-20 with B atoms to develop a new carbon-free BN-cage energetic system. The nitro (NO_2) groups are bonded to the BN-cage structure to increase the nitrogen and oxygen content, which can achieve a good oxygen balance. In this theoretical study, the BN-cage and its NO_2 derivates are systematically investigated to understand their stability, electronic structures, safety and detonation properties at the M06-2X/6-311++G**, ω B97XD/6-311++G** and B3LYP/6-311++G** levels of density functional theory (DFT). Through the systemic study of the above compounds, it is predicted that two BN-cage derivatives, NO_2 -1-1 and NO_2 -2-1, will have a superior detonation performance and low sensitivity, and could therefore potentially be new HEDMs.

2. Theoretical methods

All quantum mechanical calculations in this paper were performed using the Gaussian-09 software package²² at the M06-2X, ω B97XD and B3LYP level with the 6-311++G** basis set. The M06-2X meta-hybrid density functional developed by Zhao and Truhlar is an advanced method to calculate energies, which have shown a good performance for main group chemistry and kinetics studies.^{23,24} For comparison, the theoretical methods of ω B97XD and B3LYP were also employed with the basis set of 6-311++G**. The ω B97XD method includes a 100% long-range exact exchange, a small fraction (about 22%) of the short-

State Key Laboratory of Explosion Science and Technology, School of Mechatronical Engineering, Beijing Institute of Technology, Beijing 100081, China. E-mail: leen04@bit.edu.cn; leen04@163.com; jqj@bit.edu.cn; jqjbit@126.com

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra13476b

RSC Advances Paper

range exact exchange, a modified B97 exchange density functional for a short-range interaction, and the B97 correlation density functional and empirical dispersion correction. 25,26 ωB97XD yields satisfactory accuracy for thermochemistry and kinetics. The DFT method of B3LYP combines Becke's threeparameter (B3)27 functional with the Lee-Yang-Parr (LYP)28 correlation functional, which has been considered to be capable of accurately predicting the structural parameters and frequencies of many nitro-substituted compounds.²⁹⁻³¹ Moreover, the 6-311++G** basis set can generally give satisfactory geometries.32 All of the optimized molecular structures in this paper belong to local minima on their singlet spin state potential surface and have no imaginary frequency. Structures of the nitro-substituted BN-cage compounds are denoted as NO_2 -n-N in the present article, where n is the number of energetic groups, N orders the structures according to their relative energies using the M06-2X method.

Calculation of the electron localization function (ELF), deformation energies, net charge and charge transfer at the same level are used to analyze the electronic structure and stability of the NO2-n-N series. Moreover, Born-Oppenheimer molecular dynamic simulations (BOMD) are employed to exam the stability of the designed cage compounds to select the stable BN-cage derivates with a DFT in the level of M06-2X/6-311++G**. BOMD deals with the electronic and nuclear problems separately. In this method, the electronic structure in the ground state is calculated at each set of atomic positions, usually by optimization of the Kohn-Sham orbitals using an iterative method.33 The BOMD method in general needs more CPU time than for other MD software, but the method is more robust and stable.

Heat of detonation, detonation velocity and detonation pressure were calculated using EXPLO 5,34 using the density and solid phase enthalpy of formation $(\Delta_f H^{\circ}(s))$. The gas phase enthalpy of formation $(\Delta_f H^{\circ}(g))$ and the enthalpy of sublimation $(\Delta H_{\mathrm{sub}}^{^{\circ}})$ were used to calculate the solid phase enthalpy of formation $(\Delta_f H^{\circ}(s))$.

The following isodesmic reactions (1) combined with the computational Formula (2) were used to calculate the $\Delta_f H^{\circ}(g)$ of the studied compounds.

$$B_6N_6H_6 + nNO_2 \rightarrow B_6N_6H_{6-n}(NO_2)_n + \frac{n}{2}H_2$$
 (1)

$$\Delta H_{298} = \Delta E + \Delta Z P E + \Delta H_{T} \tag{2}$$

In eqn (1) and (2), n is the number of nitro groups, ΔH_{298} is the enthalpy change of the reaction at 298 K, ΔE is the change in total energy between the products and the reactants, Δ ZPE is the change of zero-point energy between the products and the reactants, and $\Delta H_{\rm T}$ is the thermal correction from 0 to 298 K.

Electrostatic potential analysis (ESP) is employed to analyze the molecular surface at the M06-2X/6-311++G level of theory. In the eqn (3)-(7), the electrostatic potential on the surface is characterized by $V_s(r)$. $V_s^+(r_i)$, $V_s^-(r_i)$ and $V_s(r_i)$ represents the positive, negative and the overall value of $V_s(r)$ at any point r_i on the surface. The $\overline{V_s^+}$, $\overline{V_s^-}$ and $\overline{V_s}$ represent their averages, and

 σ_{+}^{2} , σ_{-}^{2} , and σ_{tot}^{2} are the corresponding variances. ν is the electrostatic balance parameter, m and n are the number of positions with positive and negative potentials on the molecular surface. The parameters mentioned above will be used to further calculate the enthalpy of sublimation, density and impact sensitivity in the corresponding equations.

$$\overline{V_s}^+ = \frac{1}{n} \sum_{i=1}^n V_s^+(r_i)$$
 (3)

$$\overline{V_s^-} = \frac{1}{m} \sum_{i=1}^m V_s^-(r_i)$$
 (4)

$$\overline{V_s} = \frac{1}{m+n} \left[\sum_{i=1}^n V_s^+(r_i) + \sum_{i=1}^m V_s^-(r_i) \right]$$
 (5)

$$\sigma_{\text{tot}}^{2} = \sigma_{+}^{2} + \sigma_{-}^{2}$$

$$= \frac{1}{n} \sum_{i=1}^{n} \left[V_{\text{s}}^{+}(r_{i}) - \overline{V_{\text{s}}^{+}} \right]^{2} + \frac{1}{m} \sum_{i=1}^{m} \left[V_{\text{s}}^{-}(r_{i}) - \overline{V_{\text{s}}^{-}} \right]^{2}$$
 (6)

$$V = \frac{{\sigma_{+}}^{2} {\sigma_{-}}^{2}}{\left[{\sigma_{\text{tot}}}^{2}\right]^{2}} \tag{7}$$

The enthalpy of sublimation $(\Delta H_{\text{sub}}^{\circ})$ can be evaluated using the developed method by Rice and Politzer et al.35

$$\Delta H_{\text{sub}}^{\circ} = \alpha (A_{\text{s}})^2 + \beta (\nu \sigma_{\text{tot}}^2)^{0.5} + \gamma$$
 (8)

In eqn (8), $\alpha = 0.000267$, $\beta = 1.650087$, and $\gamma = 2.966078$.

Then, the solid phase enthalpy of formation $(\Delta_f H^{\circ}(s))$ can be calculated using eqn (9).

$$\Delta_{f} H^{\circ}(s) = \Delta_{f} H^{\circ}(g) - \Delta H_{\text{sub}}^{\circ}$$
 (9)

The crystal density (ρ) of the studied compounds can be calculated using $\rho = \alpha_1 \left(\frac{M}{V_{vv}}\right) + \beta_1 (\nu \sigma_{tot}^2) + \gamma_1$, ³⁶ in which $\alpha_1 = 0.9183$, $\beta_1 = 0.0028$, and $\gamma_1 = 0.0443$.

In order to understand the sensitivity and safety of the studied cage compounds, the impact sensitivity,37 Wiberg bond index (WBI),38,39 and bond dissociation energy (BDE)40 were calculated. Impact sensitivity can be tested using the drop hammer test, which is measured by dropping a given mass (2.5 kg) upon the compound and recording the height (h_{50}) which has a 50% probability of producing an explosion. The value of h_{50} is calculated using eqn (10).³⁷

$$h_{50} = \alpha_2 \sigma_+^2 + \beta_2 \nu + \gamma_2 \tag{10}$$

In eqn (10), $\alpha_2 = -0.0064$, $\beta_2 = 241.42$, and $\gamma_2 = -3.43$.

The BDE is calculated using eqn (11). In general, if the value of BDE is greater than 84 kJ mol⁻¹, the corresponding bond is considered to be stable.

$$BDE_{(A-B)} = [E_{A'} + E_{B'}] - E_{(A-B)}$$
(11)

RSC Advances Paper

Results and discussion 3.

3.1. Configuration

Fig. 1 shows an optimized structure of the designed BN-cage that was confirmed to be a global minimal without imaginary frequencies at the M06-2X level. The distances of B3-N7, B5-N6 and B16-N15 are 1.716 Å, 1.716 Å and 2.803 Å, respectively. The corresponding WBI, determined using natural bond orbital (NBO) analysis were 0.5085, 0.5085 and 0.0049, respectively. The relatively long distance and small WBI between B16 and N15 suggests the absence of the corresponding bond. Additionally, the bond lengths (WBI) of B1-N8, B2-N9 and B4-N10 were found to be 1.370 Å (1.2746), 1.403 Å (1.0820) and 1.403 Å (1.0820), respectively. The shorter bond lengths and larger WBI of these three bonds compared with the other B-N bonds are indicative that double bonds exist between B1-N8, B2-N9 and B4-N10. Also, the topological analysis of the ELF was performed to understand the bond character of the B-N bonds in the designed BN-cage. The corresponding color-filled maps and the curve maps of ELF for these bonds are shown in Fig. S1,† which further confirms the existence of the B3-N7, B5-N6, B1-N8, B2-N9, and B4-N10 covalent bonds, and the inexistence of the B16-N15 bond.

The H atoms in the designed BN-cage were replaced by nitro groups to construct a series of new energetic molecules. All of the optimized structures could retain the integrity of the BNcages. Moreover, the calculation results indicated that the energetic groups bond with boron atoms in the cage led to lower-energy structures than that with nitrogen atoms. Fig. 2 shows the optimized geometries of the NO₂-n-1 (n = 1-6).

The four mononitro-substituted BN-cage compounds shown in Fig. S1 and Table S2† were found to lie less than 200 kJ mol⁻¹ in energy above the lowest-energy structure NO₂-1-1. The nitro group in the lowest-lying structures NO2-1-1 is bonded to the B5 atom by replacing H12 in the BN-cage. It should be pointed out that the distance between B3 and N7 in NO₂-1-3 is 2.621 Å, the




Fig. 1 Optimized structure (bond lengths in Å) for the designed BNcage at the M06-2X/6-311++G** level. Wiberg bond indexes are underlined

long distance of the bond and the corresponding ELF analysis (shown in Fig. S3†) suggests that the B3-N7 bond does not exist.

The five dinitro-substituted BN-cage compounds shown in Fig. S2 and Table S3[†] are found to lie less than 200 kJ mol⁻¹ in energy above NO₂-2-1. Similar to the mononitro-substituted compounds, the nitro groups bond with B3 and B5 in NO₂-2-1 to obtain the lowest-energy structure with the symmetry of the C_s . The NO₂-2-2 lies at an energy of 27.2 kJ mol⁻¹ above the NO₂-2-1S at the M06-2X level, having the B5-NO2 and B16-NO2 bonds. However, the NO₂-2-3, NO₂-2-4 and NO₂-2-5, with the N-NO₂ bonds have much higher total energies than the NO2-2-1 and NO2-2-2 due to the high energy of the N-N bonds.

The four trinitro-substituted BN-cage compounds shown in Fig. S3 and Table S4[†] are found to lie less than 200 kJ mol⁻¹ in energy above the lowest-energy structure NO₂-3-1. The three nitro groups in NO₂-3-1 with a C_s symmetry are bonded with the B3, B5 and B16 atoms. The NO_2 -3-2, NO_2 -3-3 and NO_2 -3-4 with one N-NO₂ bond are, respectively, 126.0, 150.5 and 161.2 kJ mol^{-1} at the M06-2X level, higher than NO₂-3-1.

As shown in Fig. S4 and Table S5,† three tetranitrosubstituted BN-cages are found to lie less than 200 kJ mol⁻¹ in energy above NO₂-4-1. Both of the first two structures NO₂-4-1 and NO₂-4-2 have three B-NO₂ bonds and one N-NO₂ bonds, while the NO2 groups in NO2-4-3 bond with two B atoms and two N atoms. It should be pointed out that the distances between the B3 and N7 atoms in NO2-4-2 and NO2-4-3 are 2.534 and 2.491 Å, respectively. The relatively long distances and the corresponding ELF analysis shown in Fig. S7 and S8† suggests the absence of corresponding bonds.

Only the two pentanitro-substituted BN-cages were found, which are shown in Fig. S5 and Table S6.† In NO₂-5-1, the five nitro groups bond with the three boron atoms and two nitrogen atoms. Additionally, the distance of B3...N7 and B16...N15 in NO₂-5-1 are 2.608 and 2.629 Å respectively, which are about 1 Å longer than the other B-N bonds. This is indicative of the absence of these two bonds, combined with the color-filled map and the curve map of ELF (shown in Fig. S10†).

Finally, only one hexanitro-substituted BN-cage NO2-6-1 is found, as shown in Fig. S6 and Table S7.† All of the H atoms in the designed BN-cage are replaced by nitro groups leading to the C_s symmetry for NO₂-6-1.

3.2. Electronic structure and thermal stability

To study the change caused by substituting the H of the designed BN-cage with NO2, the deformation energies of the skeleton ($\Delta E_{\rm cage}$) and the relative (ΔBDE) are calculated and summarized in Table 1. \triangle BDE can be calculated using eqn (12), which is the relative BDE of cage-NO2 bonds to the corresponding cage-H bonds in the designed BN-cage without substitution.

$$\Delta BDE = BDE_{cage-NO_2} - BDE_{cage-H}$$
 (12)

 $\Delta E_{\rm cage}$ corresponds to the change of the BN-cage skeleton. The $\Delta E_{\rm cage}$ shown in Table 1 indicates that the substitution of the nitro groups leads to the deformation of the cage skeleton. Adding nitro groups to the nitrogen atoms of the BN-cage brings

Paper

NO₂-1-1(C1)

NO₂-2-1(Cs)

NO₂-3-1(Cs)

NO₂-3-1(Cs)

NO₃-1-1(S)

NO₄-1-1(S)

NO₅-1-1(S)

Fig. 2 Optimized geometries (bond lengths in Å) at the M06-2X/6-311++ G^{**} level for the NO₂-n-1 (n = 1-6). Symmetries are labeled in parentheses.

NO2-5-1(C1)

more changes to the skeleton compared with the boron atoms. It should be pointed out that NO_2 -1-3 has the most skeleton changes among the four isomers, caused by the breaking of the B3–N7 bond. Negative values of Δ BDE suggest that the bond strengths of all the cage- NO_2 bonds are lower than that of the corresponding cage-H bonds.

NO2-4-1(Cs)

To further study the stability of the mononitro-substituted BN-cage isomers, the deformation energies of the BN-cage skeletons $(\Delta E_{\rm cage}^*),\;$ the deformation energies of the nitro groups $(\Delta E_{\rm NO_2}^*),\;$ and the relative BDE of the cage-NO₂ bonds $(\Delta {\rm BDE}^*)$ to NO₂-1-1 are calculated and the results are shown in Table 2.

Table 1 The deformation energies of the BN-cage skeleton ($\Delta E_{\rm cage}$, kJ mol $^{-1}$) and the relative BDE (Δ BDE, kJ mol $^{-1}$) to the designed BN-cage without substitution

Compounds	Methods	NO ₂ -1-1	NO ₂ -1-2	NO ₂ -1-3	NO ₂ -1-4
$\Delta E_{ m cage}$	M06-2X	0.5	1.6	53.4	44.4
	ω B97XD	2.83	4.0	54.0	43.4
	B3LYP	3.9	1.6	55.5	30.5
$\Delta \mathrm{BDE}$	M06-2X	-24.6	-55.4	-212.8	-226.8
	ω B97XD	-39.5	-62.8	-226.2	-241.4
	B3LYP	-37.0	-61.0	-225.5	-228.2

As shown in Table 2, comparing with NO₂-1-1, the decrease of the BDE of the B–NO₂ bond in the NO₂-1-2 structure leads to an increase of its energy, and the deformation of its skeleton could be ignored due to its small $\Delta E_{\rm cage}^*$ value. For the N-mononitrosubstituted isomers NO₂-1-3 and NO₂-1-4, the difference of the B–NO₂ and N–NO₂ bond is the primary reason leading to their energy increase. Compared to the global

NO2-6-1(Cs)

Table 2 The relative energies (ΔE, kJ mol $^{-1}$), relative BDE (ΔBDE*, kJ mol $^{-1}$), and the deformation energies of the BN-cage skeletons ($\Delta E^*_{\rm cage}$, kJ mol $^{-1}$) and nitro groups ($\Delta E^*_{\rm NO_2}$, kJ mol $^{-1}$) among the mononitro-substituted BN-cage compounds

Compounds	Methods	NO ₂ -1-1	NO ₂ -1-2	NO ₂ -1-3	NO ₂ -1-4
ΔE	M06-2X	0	24.6	129.7	151.3
- E	ωB97XD	0	20.3	124.7	149.4
	B3LYP	0	17.2	126.0	152.4
$\Delta E_{\mathrm{cage}}^*$	M06-2X	0	-0.2	-26.0	-18.9
cage	ω B97XD	0	-0.2	-45.7	-35.8
	B3LYP	0	-1.3	-50.2	-48.1
$\Delta E_{ ext{NO}_2}^*$	M06-2X	0	-4.2	-4.7	-6.1
NO ₂	ω B97XD	0	-4.3	-5.2	-6.5
	B3LYP	0	-3.2	-3.0	-4.5
$\Delta \mathrm{BDE}^*$	M06-2X	0	-29.0	-160.4	-176.2
	ω B97XD	0	-24.7	-175.6	-191.6
	B3LYP	0	-22.9	-179.3	-204.9

RSC Advances Paper




Fig. 3 The valence-bond structures of the nitro group

minimum of NO₂-1-1, the NO₂ bonding in the N atom brings the relative heavy deformation of the BN-cage skeletons, which is another reason for the lower NO₂-1-3 and NO₂-1-4 structural stability. For the nitro group, the isomers have a small $\Delta E_{\rm NO_2}^*$ value and the change of the NO₂ could be ignored, as shown in Table 2.

The charge transfer calculated using the NBO analysis is also employed to analyze the stability differences among the different substitution positions. The valence-bond structure of the nitro group, shown in Fig. 3, indicates that the nitro is an electrophilic group, in which the nitrogen atom tends to combine with the boron atom in the cage to provide a stable configuration. Fig. 4 and Table 3 describe the molecular structures, net charge, charge transfer and BDE of the cage-NO₂

bonds for the mononitro or dinitro-substituted cages. As listed in Table 3, the results show that all the nitro groups in the B(N)-mononitro or dinitro-substituted cages are electron accepters, and the charge transfers of the B-mononitro or dinitro-substituted cage is always larger than those of the N-mononitro or dinitro-substituted cage, suggesting the higher dissociation energies of the B-NO $_2$ bonds compared with the N-NO $_2$ bonds.

The above calculations suggest that the B-nitrosubstituted cages have a relatively better stability than the N-nitrosubstituted cages. As such, the NO₂-1-1, NO₂-2-1 and NO₂-3-1 structures were selected for further study, as discussed in the subsequent sections.

3.3. Dynamic simulation

Based on the above calculation results for the stability of these designed BN-cage derivatives, molecular dynamic calculations of the B-substituted NO₂-n-1 (n = 1, 2, 3) structures were carried out to exam their dynamic stability. BOMD were employed to perform the molecular dynamic simulation. The static configurations calculated at the M06-2X/6-311++G** level were run as seeds for the BOMD trajectories using the Gaussian-09 program package. Equilibration steps were performed over 1 ps and production runs are 3 ps long with the time step of 1 fs.




Fig. 4 Optimized geometries, net charge (e), and charge transfer (e) of the B(N)-mononitro(dinitro)-substituted BN-cage compounds at the M06-2X/6-311++ G^* level. The BDE (kJ mol⁻¹) of the cage-NO₂ bonds are underlined.

Table 3 The net charge (e) on the nitro groups in the B(N)-mononitro(dinitro)-substituted BN-cage compounds at the M06-2X/6-311++ G^{**} , ω B97XD/6-311++ G^{**} , and B3LYP/6-311++ G^{**} levels

a 1	Net charge			
positions	M06-2X	ωB97XD	B3LYP	
В	-0.652	-0.627	-0.740	
N	-0.536	-0.497	-0.504	
В	-0.426	-0.388	-0.696	
В	-0.426	-0.388	-0.696	
N	-0.360	-0.322	-0.349	
N	-0.344	-0.317	-0.349	
	B N B B	Substitution positions M06-2X B -0.652 N -0.536 B -0.426 B -0.426 N -0.360	Substitution positions M06-2X ωB97XD B -0.652 -0.627 N -0.536 -0.497 B -0.426 -0.388 B -0.426 -0.388 N -0.360 -0.322	

The simulation results of the NO₂-n-1 (n = 1, 2, 3) structures show that the NO₂-1-1 and NO₂-2-1 remain stable at 298 K during the whole simulation, while the nitro groups in NO₂-3-1 cannot remain stable at 298 K, as shown in Fig. 5. As can be seen from Fig. 5, the nitro groups in NO₂-3-1 decompose from the cage with the cage-NO2 bond breaking. Oxygen atoms in the nitro groups in the NO₂-3-1 bond with the cage directly at 298 K, with B-O bond lengths of 1.452 and 1.316 Å, while the NO groups decompose from the BN-cage compounds, with the distances between O and NO groups being \sim 1.55 Å. Moreover, deformation of the cage skeleton occurs with the distance between B5 and N6 being 2.821 Å. Thus, the NO₂-3-1 structure cannot remain stable at room temperature. Above all, the NO₂-1-1 and NO₂-2-1 structures have exhibited an attractive potential for application in the areas of energetic materials and the details are discussed in the following study on detonation performance.

3.4. Detonation performance

In order to quantitatively evaluate the detonation performance of the NO₂-1-1 and NO₂-2-1 structures, the predicted density (ρ), enthalpy of sublimation ($\Delta H_{\text{sub}}^{\circ}$), solid phase enthalpy of




Fig. 5 The dynamic simulation results of NO $_2$ -3-1 at 298 K, taken from the simulations performed at the M06-2X/6-311++G** level.

formation ($\Delta_f H^{\circ}(s)$), oxygen balance and detonation parameters (Q, D, P) were calculated systematically using EXPLO 5. The results, together with the related information for CL-20, are listed in Table 4 for comparison.

The results in Table 4 show that the ρ of NO₂-1-1 and NO₂-2-1 are 1.808 g cm⁻³ (1.789 g cm⁻³, 1.732 g cm⁻³) and 1.931 g cm⁻³ (1.871 g cm⁻³, 2.059 g cm⁻³) respectively at the M06-2X (ω B97XD, B3LYP)/6-311++G** level. In the meantime, the calculated densities of CL-20 are 1.954 g cm⁻³ at the M06-2X level, 1.907 g cm⁻³ at the ω B97XD level and 2.022 g cm⁻³ at the B3LYP level, which indicates the relatively high densities of these two newly proposed designed molecules. The Q of NO₂-2-1 is 31.25% (M06-2X), 31.26% (ω B97XD) or 24.79% (B3LYP) higher than that of CL-20 (6314 kJ kg⁻¹), with a D of over 6800 m s⁻¹. The superior detonation heat of both the NO₂-1-1 and NO₂-2-1 structures indicate the great potential of these two energetic compounds to be HEDMs.

3.5. Sensitivity and safety

To test the sensitivity and safety of the above NO₂-1-1 and NO₂-2-1 structures, two methods have been employed in the present work: (1) impact sensitivity; and (2) BDE of the trigger bonds.

3.5.1 Impact sensitivity. The impact sensitivity is a crucial parameter responsible for effectiveness. It reflects whether the explosive is stable enough to be handled or stored under typical conditions. In this paper, the theoretical impact sensitivity of NO₂-1-1, NO₂-2-1 and CL-20 were calculated at the M06-2X, ω B97XD and B3LYP level to compare their safety and practicability (see Table 5). The calculation results show that the h_{50} of the NO₂-1-1 and NO₂-2-1 structures were 49.498 cm (47.745 cm, 50.555 cm) and 34.459 cm (34.089 cm, 36.115 cm) at the M06-2X (ω B97XD, B3LYP)/6-311++G** level, respectively, which are higher than that of CL-20. Such a result illustrates their high value of application.

3.5.2 Bond dissociation energy. The BDE of the trigger bond is often a key factor in investigating the thermal stability and pyrolysis mechanism of energetic compounds. Generally, the smaller the energy needed for breaking a bond, the weaker the bond.

To elucidate the pyrolysis mechanism and thermal stability of the NO₂-1-1 and NO₂-2-1 structures, the bond dissociation energies of the cage-NO₂ bonds in NO₂-1-1, NO₂-2-1 and CL-20, as well as the corresponding WBI have been investigated in the present work, as shown in Table 6. Obviously, the BDE of the cage-NO2 bonds in the NO2-1-1 and NO2-2-1 structures are $402.245 \text{ kJ mol}^{-1} (447.635 \text{ kJ mol}^{-1}, 393.573 \text{ kJ mol}^{-1}) \text{ and}$ $389.882 \text{ kJ mol}^{-1} (358.869 \text{ kJ mol}^{-1}, 381.905 \text{ kJ mol}^{-1}) \text{ with WBI}$ of 0.6640 (0.6657, 0.6852) and 0.6716 (0.6731, 0.6916) respectively, at the M06-2X (ω B97XD, B3LYP)/6-311++G** level. Thus, the designed NO₂-1-1 and NO₂-2-1 BN-cage molecules meet the stability requirement suggested previously, that is, a molecule could be considered as a practical energetic material if it has its BDE larger than 84 kJ mol $^{-1}$. Moreover, the BDE of the cage-NO $_2$ bonds in NO₂-1-1 and NO₂-2-1 are much higher than that of CL-20 at the same calculation level, which implies that they have a better stability than CL-20.

Table 4 Theoretical density (ρ), enthalpy of sublimation ($\Delta H_{\text{sub}}^{\circ}$), solid phase enthalpy of formation ($\Delta_{\text{f}} H^{\circ}$ (s)), detonation velocity (D), detonation pressure (P), heat of detonation (Q) and oxygen balance of the NO₂-1-1 and NO₂-2-1 structures. Experimental parameters of CL-20 are labeled in parentheses (the theoretical densities of CL-20 are 1.954 g cm⁻³ at M06-2X, 1.907 g cm⁻³ at ωB97XD and 2.022 g cm⁻³ at B3LYP)

compounds	NO ₂ -1-1	NO ₂ -1-1			NO ₂ -2-1		
Methods	M06-2X	ωB97XD	B3LYP	M06-2X	ωB97XD	B3LYP	CL-20
$\rho (\mathrm{g cm^{-3}})$	1.808	1.789	1.732	1.931	1.871	2.059	(2.04)
$\Delta H_{\text{sub}}^{\circ}(\text{kJ mol}^{-1})$	124.900	123.909	125.908	132.842	134.435	137.619	<u> </u>
$\Delta_f H^{\circ}(s) (kJ \text{ mol}^{-1})$	-289.545	-269.297	-274.313	-449.511	-413.859	-554.623	_
$D \left(\text{m s}^{-1} \right)$	6485.349	6409.758	6132.865	7222.655	6881.267	7019.696	(9580)
P (GPa)	15.449	14.783	13.427	24.959	18.518	26.566	(43.2)
$Q(kJ kg^{-1})$	8131.956	8180.25	8115.766	8287.309	8287.938	7879.410	(6314)
Oxygen balance	-76.011%			-45.720%			-10.953%

Table 5 Calculated impact sensitivity (h_{50}) of the predicted BN-cage compounds and CL-20. Experimental parameters of CL-20 are labeled in parentheses

Compounds	Methods	NO ₂ -1-1	NO_2 -2-1	CL-20
$\sigma_{\scriptscriptstyle +}^{\ 2}$	M06-2X	292,859	417.062	231.351
	ωΒ97ΧD	302.761	437.273	233.923
	B3LYP	278.559	422.418	306.392
ν	M06-2X	0.227	0.168	0.068
	ω B97XD	0.220	0.167	0.065
	B3LYP	0.231	0.175	0.058
h_{50} (cm)	M06-2X	49.498	34.459	11.506
	ω B97XD	47.745	34.089	10.765
	B3LYP	50.555	36.115	8.611

Table 6 Calculated bond dissociation energies (BDE) and Wiberg bond index (WBI) of the trigger bonds (cage- NO_2 bonds) in NO_2 -1-1 and NO_2 -3-1 at the M06-2X, ω B97XD and B3LYP level

Compounds	WBI			BDE(kJ mol ⁻¹)		
Methods	M06-2X	ωB97XD	B3LYP	M06-2X	ωB97XD	B3LYP
NO ₂ -1-1 NO ₂ -2-1 CL-20	0.6640 0.6716 0.9421	0.6657 0.6731 0.9460		402.245 389.882 153.092	358.869	393.573 381.905 148.656

4. Conclusions

Inspired by the high combustion heat of the boron atom and the large strain energy of the HNIW cage skeleton, we proposed several molecules with a new BN-cage skeleton by replacing C with B atoms in this study. A series of energetic molecules $B_6\text{-}N_6H_{6-n}(\text{NO}_2)_n~(n=1\text{-}6)$ were subsequently constructed through systematically substituting NO $_2$ groups for the H atoms of the BN-cage. Then, all the $B_6N_6H_{6-n}(\text{NO}_2)_n~(n=1\text{-}6)$ structures were optimized at the M06-2X/6-311++G**, ω B97XD/6-311++G** and B3LYP/6-311++G** level of DFT. Analysis of the structural changes caused by substituting the NO $_2$ and the electronic structures including ELF, WBI, charge transfer and BDE reveal the essence of the stability and chemical characteristics of these $B_6N_6H_{6-n}(\text{NO}_2)_n~(n=1\text{-}6)$ molecules. The results show that these B-nitro substituted cages have a higher stability than the

N-nitro substituted cages. The corresponding molecular dynamic simulations, which were performed to test the stability of NO₂-1-1, NO₂-2-1 and NO₂-3-1, indicate that only the NO₂-1-1 and NO2-2-1 structures remain stable under ambient conditions. Then, the density, detonation performance and safety of the NO₂-1-1 and NO₂-2-1 structures were calculated systematically. The results show that the two BN-cage energetic molecules have a much higher detonation heat than traditional energetic materials such as CL-20, due to their high densities and the particular characteristics of the "BN" groups. Calculations also showed much higher h_{50} values of NO₂-1-1 (49.489 cm at the M06-2X level) and NO₂-2-1 (34.459 cm at the M06-2X level) than CL-20 (11.506 cm at the M06-2X level) in the same level of calculation, as well as the high bond dissociation energies over 84 kJ mol⁻¹. Above all, a new type of energetic material based on the BN-cage was put forward and could be a new field of research to find more HEDMs with a superior performance.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

We are indebted to the National Natural Science Foundation of China (21643015 and U1530262). We also acknowledge financial support from the Open Project (LHKF2014-C15) in the Key Laboratory of Theoretical Chemistry of Environment, Ministry of Education.

References

- 1 O. S. Bushuyev, P. Brown and A. Maiti, Ionic polymers as a new structural motif for high-energy-density materials, *J. Am. Chem. Soc.*, 2012, **134**(3), 1422–1425.
- 2 J. Song, Z. Zhou and X. Dong, Super-high-energy materials based on bis (2, 2-dinitroethyl) nitramine, *J. Mater. Chem.*, 2012, 22(7), 3201–3209.
- 3 Y. Zhang, D. A. Parrish and J. M. Shreeve, 4-Nitramino-3, 5-dinitropyrazole-Based Energetic Salts, *Chem.-Eur. J.*, 2012, **18**(3), 987–994.

RSC Advances Paper

- 4 J. Zhang and J. M. Shreeve, 3, 3'-Dinitroamino-4, 4'azoxyfurazan and its derivatives: an assembly of diverse N-O building blocks for high-performance energetic materials, J. Am. Chem. Soc., 2014, 136(11), 4437-4445.
- 5 D. M. Badgujar, M. B. Talawar and S. N. Asthana, Advances in science and technology of modern energetic materials: an overview, J. Hazard. Mater., 2008, 151(2), 289-305.
- 6 W. J. Chi and Z. S. Li, Molecular design of prismane-based potential energetic materials with high detonation performance and low impact sensitivity, C. R. Chim., 2015, **18**(12), 1270–1276.
- 7 D. E. Chavez, M. A. Hiskey and R. D. Gilardi, 3, 3'-Azobis (6amino-1, 2, 4, 5-tetrazine): A Novel High-Nitrogen Energetic Material, Angew. Chem., 2000, 112(10), 1861-1863.
- 8 M. A. Hiskey, N. Goldman and J. R. Stine, High-nitrogen energetic materials derived from azotetrazolate, J. Energ. Mater., 1998, 16(2-3), 119-127.
- 9 A. Hammerl, T. M. Klapötke and H. Nöth, [N2H5]+ 2 [N4C-N N-CN4] 2-: A New High-Nitrogen High-Energetic Material, Inorg. Chem., 2001, 40(14), 3570-3575.
- 10 E. G. Gillan, Synthesis of nitrogen-rich carbon nitride networks from an energetic molecular azide precursor, Chem. Mater., 2000, 12(12), 3906-3912.
- 11 C. Zhang, C. Sun and B. Hu, Synthesis and characterization of the pentazolate anion cyclo-N5 in (N5) 6 (H3O) 3 (NH4) 4Cl, Science, 2017, 355(6323), 374-376.
- 12 A. T. Nielsen, U.S. Department and Navy, US Pat. Office Application Case No. 70631, 24 June, 1987.
- 13 K. K. Kuo, G. A. Risha and B. J. Evans, Potential usage of energetic nano-sized powders for combustion and rocket propulsion, MRS Online Proc. Libr., 2003, 800, 3-14.
- 14 G. Risha, E. Boyer and R. Wehrman. Nano-sized aluminum and boron-based solid fuel characterization in a hybrid rocket engine, 39th AIAA/ASME/SAE/ASEE joint propulsion conference and exhibit, 2003, p. 4593.
- 15 P. D. McCrary, P. A. Beasley and O. A. Cojocaru, Hypergolic ionic liquids to mill, suspend, and ignite boron nanoparticles, Chem. Commun., 2012, 48(36), 4311-4313.
- 16 A. MaČeic and J. M. K. Semple, Combustion of boron particles at atmospheric pressure, Combust. Sci. Technol., 1969, 1(3), 181–191.
- 17 G. Young, K. Sullivan and M. R. Zachariah, Combustion characteristics of boron nanoparticles, Combust. Flame, 2009, 156(2), 322-333.
- 18 E. C. Koch and T. M. Klapötke, Boron-Based High Explosives, Propellants, Explos., Pyrotech., 2012, 37(3), 335-344.
- 19 V. I. Pepekin, M. N. Makhov and A. Y. Apin, The reactions of boron in the presence of an explosion, Combust., Explos. Shock Waves, 1972, 8(1), 109-111.
- 20 L. N. Akimova, A. Y. Apin and L. N. Stesik, Detonation of explosives containing boron and its organic derivatives, Combust., Explos. Shock Waves, 1972, 8(4), 387-390.
- 21 S. C. Li and F. A. Williams, Ignition and combustion of boron particles, Int. J. Energ. Mater. Chem. Propul., 1993, 2(1-6), 248-271.
- 22 J. Frisch, G. W. Trucks, H. B. Schlegel, G. E. Scuseria, M. A. Robb, J. R. Cheeseman, J. A. Montgomery Jr.,

- T. Vreven, K. N. Kudin, J. C. Burant, J. M. Millam, S. S. Iyengar, J. Tomasi, V. Barone, B. Mennucci, M. Cossi, G. Scalmani, N. Rega, G. A. Petersson, H. Nakatsuji, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J. Hasegawa, M. Ishida, T. Nakajima, Y. Honda, O. Kitao, H. Nakai, M. Klene, X. Li, J. E. Knox, H. P. Hratchian, J. B. Cross, Bakken, C. Adamo, J. Jaramillo, R. Gomperts, R. E. Stratmann, O. Yazyev, A. J. Austin, R. Cammi, C. Pomelli, J. W. Ochterski, P. Y. Ayala, K. Morokuma, G. A. Voth, P. Salvador, J. J. Dannenberg, V. G. Zakrzewski, S. Dapprich, A. D. Daniels, M. C. Strain, O. Farkas, Malick, A. D. Rabuck, K. Raghavachari, J. B. Foresman, J. V. Ortiz, Q. Cui, A. G. Baboul, S. Clifford, J. Cioslowski, B. B. Stefanov, G. Liu, A. Liashenko, P. Piskorz, I. Komaromi, R. L. Martin, D. J. Fox, T. Keith, Al-Laham, C. Y. Peng, A. Nanayakkara, M. Challacombe, P. M. W. Gill, B. Johnson, W. Chen, M. W. Wong, C. Gonzalez and J. A. Pople, Gaussian 09, Revision A.02, Gaussian Inc, Wallingford, 2009.
- 23 W. H. James III, E. G. Buchanan and C. W. Müller, Evolution of amide stacking in larger γ-peptides: triamide H-bonded cycles, J. Phys. Chem. A, 2011, 115(47), 13783-13798.
- 24 Y. Zhao and G. T. Donald, Density functionals with broad applicability in chemistry, Acc. Chem. Res., 2009, 41(2), 157-167.
- 25 J. D. Chai and M. Head-Gordon, Systematic Optimization of Long-range Corrected Hybrid Density Functionals, J. Chem. Phys., 2008, 128, 084106.
- 26 J. D. Chai and M. Head-Gordon, Long-Range Corrected Hybrid Density Functionals with Damped Atom-Atom Dispersion Corrections, Phys. Chem. Chem. Phys., 2008, 10, 6615-6620.
- 27 (a) A. D. Becke, Phys. Rev. A, 1988, 38, 3098; (b) J. Becke, Chem. Phys., 1993, 98, 5648.
- 28 C. Lee, W. Yang and R. G. Parr, Development of the Colle-Salvetti correlation-energy formula into a functional of the electron density, Phys. Rev. B: Condens. Matter Mater. Phys., 1988, 37(2), 785.
- 29 J. Zhang, Q. Zhang and T. T. Vo, Energetic salts with π stacking and hydrogen-bonding interactions lead the way to future energetic materials, J. Am. Chem. Soc., 2015, 137(4), 1697-1704.
- 30 A. G. Roknabadi, M. H. Keshavarz and K. Esmailpour, Structural, thermochemical and detonation performance of derivatives of 1, 2, 4, 5-tetrazine and 1, 4 N-oxide 1, 2, 4, 5tetrazine as new high-performance and nitrogen-rich energetic materials, J. Iran. Chem. Soc., 2017, 14(1), 57-63.
- 31 J. Yang, X. Gong and G. Wang, Structure, aromaticity, stability, and energetic performance of the analogues and derivatives of s-heptazine, J. Mol. Model., 2014, 20(8), 2379.
- 32 K. B. Wiberg, Basis set effects on calculated geometries: 6-311++ G** vs. aug-cc-pVDZ, J. Comput. Chem., 2004, 25(11), 1342-1346.
- 33 M. C. Payne, M. P. Teter, D. C. Allan, T. A. Arias and J. D. Joannopoulos, Iterative minimization techniques for ab initio total-energy calculations: molecular dynamics and conjugate gradients, Rev. Mod. Phys., 1992, 64(4), 1045.

34 M. Suceska, *EXPLO5 Program. Version 5.04*, Brodarski Institute, Zagreb, Croatia, 2010.

RSC Advances

- 35 P. Politzer and J. S. Murray, Some perspectives on estimating detonation properties of C, H, N, O compounds, *Cent. Eur. J. Energ. Mater.*, 2011, **8**(3), 209–220.
- 36 P. Politzer, J. Martinez, J. S. Murray, M. C. Concha and A. ToroLabbe, An electrostatic interaction correction for improved crystal density prediction, *Mol. Phys.*, 2009, 107(19), 2095–2101.
- 37 M. Pospíšil, P. Vávra, M. Concha, J. Murray and P. Politzer, A possible crystal volume factor in the impact sensitivities of

- some energetic compounds, J. Mol. Model., 2010, 16, 895-901.
- 38 E. D. Glendening, J. K. Badenhoop and A. E. Reed, *et al.*, *NBO* 5.0, Theoretical Chemistry Institute, University of Wisconsin, Madison, WI, 2001, there is no corresponding record for this reference, 2004.
- 39 A. E. Reed, L. A. Curtiss and F. Weinhold, Intermolecular interactions from a natural bond orbital, donor-acceptor viewpoint, *Chem. Rev.*, 1988, **88**(6), 899–926.
- 40 S. J. Blanksby and G. B. Ellison, Bond dissociation energies of organic molecules, *Acc. Chem. Res.*, 2003, **36**(4), 255–263.