RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2018, 8, 5433

Received 24th November 2017 Accepted 4th January 2018

DOI: 10.1039/c7ra12766a

rsc.li/rsc-advances

1. Introduction

In recent years, water pollution has become a serious problem all around the world. A large number of pollutants, such as organic dyes, heavy metal ions, drugs etc. are discharged into both industrial waste water and domestic sewage. Until now, the conventional water treatment methods such as adsorption, coagulation, microbial degradation, and ultra-filtration were commonly used to treat waste water, however, this approach has the disadvantage of low removal efficiency and difficulty in removing low concentrations of contaminants.1-3 As a kind of green energy technology, semiconductor photocatalytic technology can remove all kinds of pollutants under the irradiation of sunlight and thus, has attracted a large amount of attention. Photocatalysis possesses a number of advantages, such as the room-temperature oxidation of contaminants even at low concentrations, reduced secondary pollution, non-toxicity and low-cost, which is suitable for the degradation of

The synthesis of a $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction photocatalyst with enhanced visible-light-driven photocatalytic activity⁺

Chol-Nam Ri, (2)*^{ab} Song-Gol Kim,^a Kyong-Sik Ju,^c Hyok-Su Ryo,^d Chol-Ho Mun^a and U-Hyon Kim^a

A novel $Bi_2MoO_6/Bi_4V_2O_{11}$ heterostructured photocatalyst was successfully fabricated using a facile onepot solvothermal method. This heterojunction consists of homogeneous dispersed $Bi_4V_2O_{11}$ nanocrystals anchored on the surface of Bi_2MoO_6 nanoflakes, endowing the heterojunction with nanosized interfacial contact. Based on the favorable interfacial contact, the band alignment at the heterojunction effectively facilitated photo-generated carrier transfer, which was verified by photoelectrochemical and photoluminescence measurements. Thereby, in contrast with pristine Bi_2MoO_6 and $Bi_4V_2O_{11}$, the assynthesized heterojunction with nanoscale contact exhibited significantly enhanced photocatalytic activity towards the degradation of MB and the reduction of $Cr(v_i)$. In addition, the as-fabricated $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction exhibited good cycling stability for MB degradation after 4 cycles. Finally, a plausible photocatalytic mechanism for MB degradation over the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction was discussed in detail. This work not only reports a highly efficient photocatalyst but also sheds light on the design and optimization of a heterojunction.

> contaminants.^{4,5} To date, titanium dioxide (TiO₂) is undoubtedly considered to be the most exceptional photocatalyst for solar energy conversion and environmental applications under UV illumination ($\lambda < 400$ nm). As is well known, among the solar spectrum, ultraviolet-light makes up only less than 5%, while visible-light (760 nm> $\lambda > 400$ nm) makes up approximately 40%. However, the major drawback of TiO₂ is the wide band gap (3.2 eV), which greatly reduces the efficiency of solar energy utilization and limits its commercial applications.^{6,7} Therefore, over the past few decades, a great deal of effort has been made to exploit more efficient visible-light-responding photocatalysts in which Bi-based semiconductors have attracted a substantial amount of attention due to their peculiar electronic structure and the low cost of raw materials.⁸

> Recently, as an example of a Bi-based semiconductor, Bi₂MoO₆ has been regarded as a promising photocatalyst because of its narrow band gap (2.5–2.8 eV), high chemical stability and non-toxicity. Unfortunately, the rapid recombination of photo-induced electron–hole pairs and sluggish charge transport in pristine Bi₂MoO₆ greatly restrict its photocatalytic activity.^{9,10} To overcome the obstacles of rapid charge carrier recombination, many strategies have been developed, such as controlling the morphology,¹¹ doping¹² and constructing a heterojunction. Among them, the method of constructing a heterojunction has been the most popular, since it can boost charge carrier separation and transfer efficiently originating from the as-introduced built-in electric field at the heterostructured interface. To date, different types of Bi₂MoO₆-based composite

[&]quot;Institute for Electronic Materials, Kim Il Sung University, Pyongyang, Democratic People's Republic of Korea

^bSchool of Chemistry and Chemical Engineering, Harbin Institute of Technology, Harbin, 150001, China. E-mail: rcn906@yahoo.com

^cInstitute of Advanced Science, Kim Il Sung University, Pyongyang, Democratic People's Republic of Korea

^dFaculty of Physics, Kim Il Sung University, Pyongyang, Democratic People's Republic of Korea

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra12766a

photocatalysts, such as g-C₃N₄/Bi₂MoO₆,¹³ BiOCl/Bi₂MoO₆,¹⁴ BiOBr/Bi₂MoO₆¹⁵ BiOI/Bi₂MoO₆¹⁶ Bi₂MoO₆/TiO₂¹⁷ α-Fe₂O₃/ Bi₂MoO₆,¹⁸ Bi₂O₃/Bi₂MoO₆,¹⁹ Bi₂S₃/Bi₂MoO₆,²⁰ CdS/Bi₂MoO₆ (ref. 21) Bi₂MoO₆/Bi₂WO₆ (ref. 22) etc. have been fabricated with enhanced photocatalytic efficiency.

Very recently, Bi₄V₂O₁₁ with a peculiar layered structure that has intrinsic oxygen vacancies in perovskite $(VO_{3,5} \square_{0,5})^{2-} (\square$ represents the intrinsic oxygen vacancies) slabs sandwiched between $(Bi_2O_2)^{2+}$ layers, has been considered as an excellent photocatalyst for oxygen evolution and water purification.²³⁻²⁵ Because of the narrow band gap ($\sim 2.1 \text{ eV}$) and excellent charge carrier transport originating from its unique crystalline structure, Bi₄V₂O₁₁ has been employed to construct heterojunction photocatalysts, such as BiVO4/Bi4V2O11 (ref. 26) and Bi₂₄O₃₁Br₁₀/Bi₄V₂O₁₁.²⁷ All of above heterojunctions realize considerably enhanced photocatalytic activity due to the effective separation and transfer of photo-induced charge carriers. However, to the best of our knowledge, the construction of a Bi₂MoO₆/Bi₄V₂O₁₁ heterojunction has not been reported, which might enhance the photocatalytic properties of Bi₂MoO₆ considerably.

In this study, a Bi₂MoO₆/Bi₄V₂O₁₁ heterojunction was fabricated using a one-pot solvothermal method. This heterojunction was constructed from Bi₄V₂O₁₁ nanocrystals anchored on the Bi₂MoO₆ nanoflakes surface, achieving a nanosized interfacial contact. The photocatalytic performance of the asfabricated pristine Bi2MoO6, Bi4V2O11 and different Bi2MoO6/ $Bi_4V_2O_{11}$ heterojunctions was evaluated by the photocatalytic degradation of methylene blue (MB) and photocatalytic reduction of Cr(vi) under visible-light illumination. The results indicated that the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction exhibited superior photocatalytic activity than pristine Bi2MoO6 and $Bi_4V_2O_{11}$. Furthermore, the as-fabricated $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction exhibited good cycling stability for MB degradation after 4 cycles. Finally, the enhanced photocatalytic mechanism of the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction has also been discussed.

2. Experimental

2.1 Photocatalysts preparation

All chemicals reagents were received from Aladdin Chemical Co. Ltd. and used without further purification.

2 mmol of Bi(NO₃)₃·5H₂O was added into 15 mL of ethylene glycol and magnetically stirred in a water bath at 80 °C to form a clear solution. Then, appropriate stoichiometric amounts of $(NH_4)_6Mo_7O_{24} \cdot 4H_2O$ and NH_4VO_3 were added into the abovementioned bismuth nitrate solution, which was continuously stirred for 20 min at 80 °C to obtain a transparent solution. Subsequently, the pH of the above solution was adjusted to about 8 by the slow dropwise addition of 2 M sodium hydroxide solution. Then, the abovementioned solution was poured into a 25 mL Teflon-lined stainless autoclave, which was subsequently sealed and maintained at 160 °C for 16 h in an oven. After the reactor cooled down to room temperature, the asobtained product was centrifuged three times using water and absolute ethanol.

Finally, the photocatalyst was obtained after drying at 80 °C in air for 4 h. According to the abovementioned method, Bi₂MoO₆/Bi₄V₂O₁₁ heterojunction photocatalysts with different molar amounts of Mo and V at 0.2 mmol and 0.8 mmol (denoted as BMV-28), 0.4 mmol and 0.6 mmol (denoted as BMV-46), 0.5 mmol and 0.5 mmol (denoted as BMV-55), and 0.6 mmol and 0.4 mmol (denoted as BMV-64), respectively, were prepared. In addition, pristine Bi₂MoO₆ and Bi₄V₂O₁₁ were also fabricated for the purpose of comparison.

2.2 Characterization

The crystalline structures of the as-fabricated samples were analyzed using X-ray diffraction (XRD) on a Rigaku D/max-2000 diffractometer with Cu K α radiation ($\lambda = 1.5406$ Å) in the range of $2\vartheta = 20-90^\circ$ at a scanning rate of 4 °C min⁻¹ with a scan width of 0.02°. The morphology of the samples was observed using field emission scanning electron microscopy (FE-SEM, HELIOS NanoLab 600i) at an accelerating voltage of 20 kV. The transmission electron microscopy (TEM) and highresolution TEM (HRTEM) analyses were carried out on a JEM-2100 transmission electron microscope at an accelerating voltage of 200 kV. The X-ray photoelectron spectroscopy (XPS) was conducted on a Thermo Scientific ESCALAB 250Xi X-ray photoelectron spectrometer coupled with a pass energy of 20.00 eV and an Al Ka excitation source (1486.6 eV). The UV-vis diffuse reflectance spectra (DRS) were obtained on a spectrophotometer (HITACHI UH-4150) using BaSO₄ as the reflectance standard. Photoluminescence (PL) analysis was accomplished on a HORIBA FluoroMax-4.

2.3 Photocatalytic activity and photoelectrochemical measurements

The photocatalytic performance of the as-fabricated samples was evaluated by the degradation of methylene blue (MB) and reduction of Cr(vi) under visible-light illumination using a 300 W Xe lamp (Trusttech PLS-SXE 300, Beijing) with a UV cutoff filter ($\lambda \ge 400$ nm). In a typical photocatalytic process, 0.05 g of the as-fabricated sample was added into 100 mL of MB solution (10 mg L^{-1}) or Cr(vi) solution (10 mg L^{-1} , which was based on Cr in a dilute K2Cr2O7 solution). The photocatalyst was dispersed in the above solution under ultrasonic treatment for 10 min, and the mixed solution was magnetically stirred in the dark for 30 min to achieve an adsorption-desorption equilibrium between the photocatalyst and the pollutants. When the photodegradation experiment began, 4 mL of the solution was collected from the suspension at fixed-time intervals, centrifuged at 10⁴ rpm for 5 min to remove catalyst powders, and the MB and Cr(vi) concentrations were determined using a HITA-CHI UH-5300 UV-vis spectrometer at 664 and 352 nm, respectively. The photoelectrochemical measurements were carried out on a CHI604C electrochemical workstation using a standard three-compartment cell with the $Bi_4V_2O_{11}$, Bi_2MoO_6 and Bi2MoO6/Bi4V2O11 samples coated on FTO glass used as the working electrode, a piece of Pt sheet as the counter electrode, standard Ag/AgCl in saturated KCl as the reference electrode, and a 0.5 M Na₂SO₄ aqueous solution as the electrolyte.

Converting between the measured potential (*vs.* Ag/AgCl) and NHE was achieved using eqn (1).²⁸

$$E_{\rm NHE} = E_{\rm Ag/AgCl} + 0.1976 \ (25 \ ^{\circ}{\rm C}) \tag{1}$$

The light source employed was a 300 W Xe lamp. The Mottschottky measurements were carried out at a frequency of 100 Hz and an amplitude of 10 mV.

3. Results and discussion

Fig. 1 shows the XRD patterns of the as-prepared pristine Bi2MoO6 and Bi4V2O11 samples, and the BMV-55 composite sample. The diffraction peaks of the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples can be well indexed to the orthorhombic phase Bi₂MoO₆ (JCPDS No. 72-1524) and the orthorhombic phase Bi₄V₂O₁₁ (JCPDS No. 42-0135), respectively. The XRD pattern of the BMV-55 composite contains both Bi₂MoO₆ and Bi₄V₂O₁₁ phases, indicating the coexistence of the two phases in the BMV-55 composite in which the extremely weak diffraction intensity of Bi₄V₂O₁₁ can be ascribed to its tiny size and uniform dispersion on the surface of Bi₂MoO₆. In addition, the XRD patterns of the BMV-28, BMV-46 and BMV-64 samples are shown in Fig. S1 in the ESI.[†] It can be seen that the diffraction peaks of BMV-28 and BMV-46 samples belong to the characteristic peaks of Bi₄V₂O₁₁, while no peaks corresponding to Bi_2MoO_6 can be detected, which might be attributed to the relatively lower content of Bi₂MoO₆ in the samples. Meanwhile, the diffraction peaks of BMV-64 samples correspond to those of $Bi_4V_2O_{11}$; however, the peak intensities are significantly weakened relative to those of pristine Bi₄V₂O₁₁. The morphology and microstructure of the samples are investigated using SEM, TEM and HRTEM. Fig. 2 shows the SEM images of the as-fabricated samples. The FESEM image in Fig. 2a shows that pristine Bi₂MoO₆ possesses an irregular flake-like morphology with a thickness of ca. 55 nm. In contrast, pristine Bi₄V₂O₁₁ (Fig. 2b) displays hierarchical microspheres with diameters of



Fig. 1 The XRD patterns of pristine ${\rm Bi}_2{\rm MoO}_6$ and ${\rm Bi}_4{\rm V}_2{\rm O}_{11}$ samples and the BMV-55 composite.



Fig. 2 FESEM images of (a) pristine $Bi_2MoO_{6\prime}$ (b) pristine $Bi_4V_2O_{11}$ and (c) the BMV-55 composite.

approximately 1–2 μ m. In addition, Fig. 2c shows the morphology of the BMV-55 composite, showing that the BMV-55 composite has a fluffy structure stacked in a disorderly manner by the nanoflakes. Moreover, the SEM images of the BMV-28, BMV-46 and BMV-64 samples are shown in Fig. S2 in the ESI.[†] To obtain a more detailed structural information about the BMV-55 composite, TEM analysis has been carried out. The TEM images of the BMV-55 composite are shown in Fig. 3. The TEM image of the BMV-55 composite at low magnification (Fig. 3a) illustrates that the BMV-55 composite is comprised of nanoflakes with a thickness of about 10 nm and length of about 100–200 nm, which is consistent with the SEM results described above. Interestingly, as observed from the magnified TEM image (Fig. 3b), nanocrystals with a size of *ca.* 10 nm are



Fig. 3 TEM images of the BMV-55 composite. The (a) TEM image at low magnification, (b) magnified TEM image, and (c) HRTEM image of the BMV-55 composite.

homogeneously dispersed and tightly adhered to the surface of the nanoflakes. By observing the HRTEM image of the BMV-55 composite (Fig. 3c), it can be further confirmed that the nanoflakes are Bi2MoO6 and the as-anchored nanocrystals are Bi₄V₂O₁₁ because the observed interplanar spacings of 0.811 nm and 0.312 nm correspond well to the (020) plane of the orthorhombic Bi_2MoO_6 and the (113) plane of the orthorhombic $Bi_4V_2O_{11}$, respectively. These results suggest that the $Bi_4V_2O_{11}$ nanocrystals are embedded on the Bi₂MoO₆ nanoflakes in the BMV-55 composite, forming a Bi2MoO6/Bi4V2O11 heterojunction with a nanosized interfacial contact. With the aim of further verifying the coexistence of Bi₂MoO₆ and Bi₄V₂O₁₁, surface electronic states analysis of the BMV-55 composite have been performed using the X-ray photoelectron spectroscopy (XPS). Fig. 4 shows the high-resolution XPS spectra of the asfabricated BMV-55 composite photocatalyst. The full survey spectra and C 1s spectra of BMV-55 are shown in Fig. S3 in the ESI.†

The peak positions in all of the XPS spectra were calibrated using the C 1s peak (284.6 eV) as the reference. First, the two characteristic peaks located at 164.5 and 159.1 eV in the Bi 4f spectra (Fig. 4a) were assigned to Bi $4f_{5/2}$ and Bi $4f_{7/2}$, respectively, which corresponded to Bi3+.29 Then, in the Mo 3d XPS spectra (Fig. 4b), the binding energies for Mo 3d_{3/2} and Mo 3d_{5/2} located at 235.5 and 232.4 eV, respectively were assigned to Mo⁶⁺ in Bi₂MoO₆.^{9,29} Furthermore, for the V 2p peaks (Fig. 4c), the two peaks located at 524.1 and 516.7 eV were assigned to V $2p_{1/2}$ and V $2p_{3/2}$, respectively and belonged to V⁵⁺ in Bi₄V₂O₁₁.^{27,30} Moreover, as shown in Fig. 4d, the O 1s spectra could be divided into three peaks, and the binding energies located at 529.8, 530.3 and 531.2 eV could be assigned to the lattice oxygen in Bi-O,13 lattice oxygen in Mo-O,18 and intrinsic oxygen vacancy (V_o) in Bi₄V₂O₁₁,³¹ respectively. The XPS results further indicated the simultaneous existence of Bi₂MoO₆ and Bi₄V₂O₁₁ species in the BMV-55 composite photocatalyst. In a bid to investigate the optical absorption capacity of the asprepared photocatalysts, UV-vis diffuse reflection spectra (DRS) analysis was carried out and is displayed in Fig. 5. As can



Fig. 4 The XPS spectra of the BMV-55 composite: (a) Bi 4f, (b) Mo 3d, (c) V 2p, and (d) O 1s.

be seen from Fig. 5a, the absorption edges of pristine Bi_2MoO_6 , $Bi_4V_2O_{11}$ and the BMV-55 composite were observed at about 475, 624 and 600 nm, respectively. Obviously, the absorption edge of the BMV-55 composite exhibited a red shift compared with that of pristine Bi_2MoO_6 , which illustrated that the introduction of $Bi_4V_2O_{11}$ was conducive to enhancing the light absorption capacity of the BMV-55 composite. In addition, the band gaps of pristine Bi_2MoO_6 and $Bi_4V_2O_{11}$ were calculated using the Kubelka–Munk function (eqn (2)).³²

$$\alpha h\nu = A(h\nu - E_g)^{n/2} \tag{2}$$

where α , h, ν , A, and E_g represent the absorption coefficient, Planck constant, light frequency, a constant, and band gap, respectively. In this function, n is determined by the type of optical transition in the semiconductor. Generally, n = 1 for direct transition and n = 4 for indirect transition. Both Bi₂MoO₆ (ref. 21) and Bi₄V₂O₁₁ (ref. 33) are direct transition semiconductors and their n value is 1. Fig. 5b shows the curves of $(\alpha h\nu)^2$ vs. photon energy $(h\nu)$ of the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, which indicate that the band gaps of pristine Bi₂MoO₆ and Bi₄V₂O₁₁ are approximately 2.62 and 2.02 eV, respectively. The photocatalytic performance of the as-prepared photocatalysts was evaluated by the degradation of MB in the presence of H₂O₂ (0.1 mL) under visible light irradiation. Fig. 6a presents the variation plots of MB concentration (C/C_0) versus light irradiation time for the different Bi2MoO6/Bi4V2O11 composites along with the pristine Bi2MoO6 and Bi4V2O11 samples. As shown in the figure, the degradation rate of MB over the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples reached *ca*. 83% and 46% after 60 min, respectively. Among the asfabricated Bi₂MoO₆/Bi₄V₂O₁₁ composites, with the exception of BMV-55, there was no obvious enhancement in the photocatalytic efficiency over the three other samples (BMV-28, BMV-46 and BMV-64) compared with that of pristine Bi_2MoO_6 . In contrast, the BMV-55 composite exhibited a significantly enhanced photocatalytic activity towards the degradation of MB among the samples and the photodegradation rate of MB achieved was almost 100% after 15 min of light irradiation. Fig. 6b-d display the UV-vis absorption spectra of the degradation solution obtained at certain time intervals over the BMV-55 composite and pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, respectively, which showed the superiority of the BMV-55 composite for MB degradation relative to those of pristine



Fig. 5 The (a) UV-vis diffuse reflectance spectra (DRS) and (b) $(\alpha h\nu)^2 vs.$ $h\nu$ curves of the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, and the BMV-55 composite.



Fig. 6 (a) The photocatalytic degradation plots of MB over the various photocatalysts in the presence of H_2O_2 . The UV-vis absorption spectral changes observed during the degradation of MB over (b) BMV-55, (c) pristine Bi_2MOO_6 and (d) pristine $Bi_4V_2O_{11}$.

 ${\rm Bi}_2{\rm MoO}_6$ and ${\rm Bi}_4{\rm V}_2{\rm O}_{11}$ samples. To explore the effect of ${\rm H}_2{\rm O}_2$ on the degradation efficiency of MB, the degradation experiment of MB without the addition of ${\rm H}_2{\rm O}_2$ was also conducted, and the result is shown in Fig. S4.†

Obviously, the photocatalytic activity of BMV-55 in the absence of H_2O_2 is much lower than that found upon adding H_2O_2 into the system of which the degradation rate is only 75% after 90 min, indicating that H_2O_2 plays a key role in our photocatalytic reactions. To further study the photocatalytic application of the as-fabricated photocatalysts, we have also used a toxic heavy metal ion, $Cr(v_1)$, as a model pollutant, and we have conducted the photocatalytic reduction of $Cr(v_1)$ over the pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$ samples, and the BMV-55 composite samples with the results illustrated in Fig. 7. As can be seen from the figure, the BMV-55 composite shows a distinctly enhanced photocatalytic activity for the reduction of $Cr(v_1)$ compared with pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$, demonstrating that our heterojunction photocatalysts have a good application in wastewater purification. It is speculated that the highest



Fig. 7 The photocatalytic Cr(vi) reduction plots over pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$, and the BMV-55 composite samples under visible-light irradiation.

activity of the BMV-55 composite could be associated with the higher separation and transport efficiency of the photo-induced carriers originating from the construction of the heterojunction between the Bi₂MoO₆ nanoflakes and Bi₄V₂O₁₁ nanocrystals. Aiming at confirming this viewpoint, two important approaches, including photoelectrochemical and photoluminescence (PL) analyses, have been used to evaluate the separation and transport efficiency of photo-induced carriers. Fig. 8 illustrates the results of the electrochemical measurements consisting of the photocurrent and electrochemical impedance spectroscopy (EIS) over the as-prepared pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, and the BMV-55 composite, under visible irradiation. As demonstrated in Fig. 8a, the BMV-55 composite exhibits a remarkably enhanced photocurrent response in striking contrast with the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples. In detail, the photocurrent intensity of the BMV-55 composite is approximately 8- and 18-fold larger than that of pristine Bi_2MoO_6 and $Bi_4V_2O_{11}$, implying that the separation and transport of the photoexcited charge carriers can be effectively promoted by the construction of the heterogeneous structure by anchoring the Bi4V2O11 nanocrystals on the Bi2MoO6 nanoflakes. Fig. 8b shows the EIS Nyquist plots. Apparently, the BMV-55 composite exhibits a smaller arc radius relative to that of the pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, indicating the significantly enhanced interfacial charge carrier transport ability of the BMV-55 composite. These results can furnish the valid evidence that the BMV-55 composite possesses facilitated charge carrier separation and transport properties compared with pristine Bi₂MoO₆ and Bi₄V₂O₁₁. To shed light on the recombination rate and fluorescence lifetime of the photoinduced charge carriers, PL analysis has been performed, as shown in Fig. 9. As depicted in Fig. 9a, the BMV-55 composite exhibits a lower PL emission intensity compared with pristine Bi₂MoO₆ and Bi₄V₂O₁₁ samples, manifesting that the recombination of the photo-induced charge carriers is effectively suppressed in the Bi2MoO6/Bi4V2O11 heterojunction. Moreover, Fig. 9b presents the time-resolved fluorescence decay spectra monitored at 460 nm under an excitation wavelength of 345 nm and the corresponding fitting curve of pristine Bi2MoO6 and Bi₄V₂O₁₁, and the BMV-55 composite. Obviously, the decay kinetics of the BMV-55 composite are slower when compared to those of pristine Bi₂MoO₆ and Bi₄V₂O₁₁. Consequently, the radiative lifetimes are extracted by means of a reconvolution fit using a 3-exponential model (eqn (3)).34



Fig. 8 The (a) transient photocurrent plots and (b) electrochemical impedance spectroscopy (EIS) Nyquist plots obtained for the pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$, and the BMV-55 composite samples.



Fig. 9 (a)The PL spectra of pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$, and the BMV-55 composite ($\lambda_{ex}=345$ nm). (b) The time-resolved fluorescence decay spectra and corresponding fitting curves of pristine Bi_2MOO_6 and $Bi_4V_2O_{11}$, and the BMV-55 composite.

$$I(t) = I_0 \sum_{i=1}^{3} B_i e^{-t/\tau_i}$$
(3)

where *t* is the decay time after the absorption, *I*(*t*) is the fluorescence intensity at time *t*, *I*₀ is the intensity at time *t* = 0, τ_i is the lifetime and *B_i* is the pre-exponential factor. In addition, the averaged-lifetime τ is calculated using eqn (4).³⁴

$$\overline{\tau} = \sum_{i=1}^{3} B_i \tau_i^2 / \sum_{i=1}^{3} B_i \tau_i$$
(4)

The best fitting curve and kinetic parameters observed for pristine Bi₂MoO₆ and Bi₄V₂O₁₁, and the BMV-55 composite are displayed in Fig. S5 in the ESI.[†] In detail, the average-lifetime of carriers in pristine Bi₂MoO₆ and Bi₄V₂O₁₁ were shortened to *ca*. 1.983 and 0.487 ns, respectively. In contrast, the averagelifetime of the BMV-55 composite was distinctly prolonged to 7.059 ns, indicating that the formation of the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction is tremendously beneficial to prolong the radiative lifetimes of the photo-induced charge carriers, and the greatly prolonged lifetime of the charge carriers could be closely related to the high separation efficiency of the charge carriers. The results of the PL spectra and time-resolved fluorescence decay spectra analysis further reveal that the BMV-55 composite exhibits a significantly enhanced separation and transport efficiency for the photo-induced charge carriers relative to those of pristine Bi₂MoO₆ and Bi₄V₂O₁₁, which is very consistent with the results of the photoelectrochemical analysis.

From a practical point of view, the cycle stability of the photocatalysts is a very important factor in evaluating the photocatalytic performance. To evaluate the cycle stability, a cycling experiment for the photodegradation of MB over the BMV-55 composite upon adding 0.1 mL of H_2O_2 was carried out. Prior to the next cycle experiment, the previously used photocatalyst was subjected to ultrasonic cleaning with distilled water and drying at 60 °C. Fig. 10 depicts the results of the recycling experiment after 4 cycles. It was be clearly seen that the photodegradation rate of MB for 15 minutes remained above 95% after 4 cycles, which indicated that the as-fabricated BMV-55 composite photocatalyst possessed good cycle stability. For the purpose of unraveling the mechanism of the enhanced photocatalytic activity of the Bi₂MOO₆/Bi₄V₂O₁₁ heterojunction, the energy band structures of pristine Bi₂MOO₆ and Bi₄V₂O₁₁



Fig. 10 The results of the recycling experiment after 4 cycles for the photodegradation of MB in the presence of H_2O_2 over the BMV-55 composite sample.

were investigated by determining their band gaps and flat-band potentials. Using the above UV-vis diffuse reflection spectra (DRS) analysis (Fig. 5b), the band gaps of pristine Bi_2MoO_6 and $Bi_4V_2O_{11}$ were determined to be 2.62 and 2.02 eV, respectively.

In addition, the flat-band potentials of pristine Bi₂MoO₆ and Bi₄V₂O₁₁ are determined via Mott-Schottky analysis, and the results are shown in Fig. 11. It can be seen that both of them show a positive slop, indicating that they are all n-type semiconductors. In addition, the flat-band potentials of pristine Bi_2MoO_6 and $Bi_4V_2O_{11}$ are *ca.* -0.39 and 0.26 V, respectively, *vs.* Ag/AgCl (-0.19 and 0.46 V vs. NHE), which indicates that the flat-band potential of Bi₂MoO₆ is more negative than that of $Bi_4V_2O_{11}$ by 0.65 V. According to the semiconductor theory, the conduction band potential (E_{CB}) of n-type semiconductors is very close to (0.1-0.2 V more negative) their flat-band potential.35 Therefore, it can be concluded that the CB position of Bi_2MoO_6 is more negative than that of $Bi_4V_2O_{11}$. Based on above results, possible photo-induced electron-hole pair separation and the photocatalytic degradation of MB mechanism over the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction with the assistance of H_2O_2 as an electron-trapping agent are proposed, as shown in Scheme 1. On one hand, because of the fact that the CB potential of Bi_2MoO_6 is more negative than that of $Bi_4V_2O_{11}$, the photo-induced electrons can easily migrate from the CB of Bi_2MoO_6 to the CB of $Bi_4V_2O_{11}$ driven by the built-in electric field at the heterostructured interface; it could be then captured



Fig. 11 The Mott–Schottky plots of (a) pristine ${\rm Bi}_2 MoO_6$ and (b) pristine ${\rm Bi}_4 V_2 O_{11}.$



Scheme 1 A schematic illustration of the photo-induced charge carrier separation and photocatalytic reaction mechanism over the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction.

by H_2O_2 and reacted to generate hydroxide radicals ('OH) with strong oxidizing ability, which will completely degrade MB. On the other hand, since the VB potentials of Bi_2MoO_6 (2.43 V) and $Bi_4V_2O_{11}$ (2.48 V) are very close to each other, the migration of the photo-induced holes is very difficult, leading to the holes staying in their valence band positions.³⁶ In this way, the rapid migration of the photo-induced electrons and the immobilization of the photo-induced holes can lead to the effective separation of the photo-induced electrons and holes over the $Bi_2MoO_6/Bi_4V_2O_{11}$ heterojunction, which ultimately results in the enhanced photocatalytic activity observed during the photodegradation of MB.

4. Conclusions

In summary, a novel visible-light responsive Bi₂MoO₆/Bi₄V₂O₁₁ heterojunction photocatalyst with a nanosized interfacial contact has been successfully fabricated using a facile one-pot solvothermal method. The Bi2MoO6/Bi4V2O11 heterojunctions show excellent photocatalytic MB degradation efficiency under visible-light illumination. In particular, the BMV-55 composite exhibits significantly enhanced photocatalytic activity during the photodegradation of MB and photoreduction of Cr(vi) compared with pristine Bi₂MoO₆ and Bi₄V₂O₁₁. In addition, the Bi₂MO₆/Bi₄V₂O₁₁ heterojunctions also display an enhanced transient photocurrent response, lower electrochemical impedance, lower PL intensity and greatly prolonged lifetime, which indicates that the photo-induced charge carriers are more effectively separated and transferred in the Bi2MoO6/ Bi₄V₂O₁₁ heterojunctions. The significantly enhanced photocatalytic activity and charge carrier separation effect are attributed to the formation of a heterojunction with a nanosized interfacial contact between the Bi2MoO6 nanoflakes and Bi₄V₂O₁₁ nanocrystals. Moreover, the Bi₂MoO₆/Bi₄V₂O₁₁ heterojunctions exhibit excellent cycle stability after 4 cycles. This work may be further extended to the research and development of a novel semiconductor heterojunction containing a new kind of Bi₄V₂O₁₁ photocatalyst for water purification and related applications.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was financially supported by the National Nature Science Foundation of China (21501035).

References

- 1 S. Vadivel, D. Maruthamani, A. Habibi-Yangjeh, B. Paul, S. S. Dhar and K. Selvam, *J. Colloid Interface Sci.*, 2016, **480**, 126.
- 2 H. Y. Li, S. Y. Gan, H. Y. Wang, D. X. Han and L. Niu, *Adv. Mater.*, 2015, 27, 6906.
- 3 S. Y. Dong, J. L. Feng, M. H. Fan, Y. Q. Pi, L. M. Hu, X. Han, M. L. Liu, J. Y. Sun and J. H. Sun, *RSC Adv.*, 2015, 5, 14610.
- 4 J. W. Tang, Z. G. Zou and J. H. Ye, *Angew. Chem.*, 2004, **116**, 4563.
- 5 A. D. Paola, E. García-López, G. Marcì and L. Palmisano, J. Hazard. Mater., 2012, 211–212, 3.
- 6 L. Zhao, X. F. Chen, X. C. Wang, Y. J. Zhang, W. Wei, Y. H. Sun, M. Antonietti and M. M. Titirici, *Adv. Mater.*, 2010, 22, 3317.
- 7 B. Huang, W. J. Yang, Y. W. Wen, B. Shan and R. Chen, ACS Appl. Mater. Interfaces, 2015, 7, 422.
- 8 R. A. He, S. W. Cao, P. Zhou and J. G. Yu, *Chin. J. Catal.*, 2014, 35, 989.
- 9 Y. S. Xu and W. D. Zhang, Dalton Trans., 2013, 42, 1094.
- 10 M. Y. Zhang, C. L. Shao, J. B. Mu, X. M. Huang, Z. Y. Zhang, Z. C. Guo, P. Zhang and Y. C. Liu, *J. Mater. Chem.*, 2012, 22, 577.
- 11 G. H. Tian, Y. J. Chen, W. Zhou, K. Pan, Y. Z. Dong, C. G. Tian and H. G. Fu, *J. Mater. Chem.*, 2011, 21, 887.
- 12 Z. Dai, F. Qin, H. P. Zhao, J. Ding, Y. L. Liu and R. Chen, *ACS Catal.*, 2016, **6**, 3180.
- 13 H. P. Li, J. Y. Liu, W. G. Hou, N. Du, R. J. Zhang and X. T. Tao, *Appl. Catal.*, *B*, 2014, **160–161**, 89.
- 14 D. Yue, D. M. Chen, Z. H. Wang, H. Ding, R. L. Zong and Y. F. Zhu, *Phys. Chem. Chem. Phys.*, 2014, **16**, 26314.
- S. Y. Wang, X. L. Yang, X. H. Zhang, X. Ding, Z. X. Yang, K. Dai and H. Chen, *Appl. Surf. Sci.*, 2017, **391**, 194.
- 16 T. Yan, M. Sun, H. Y. Liu, T. T. Wu, X. J. Liu, Q. Yan, W. G. Xu and B. Du, *J. Alloys Compd.*, 2015, **634**, 223.
- 17 M. Y. Zhang, C. L. Shao, J. B. Mu, Z. Y. Zhang, Z. C. Guo, P. Zhang and Y. C. Liu, *CrystEngComm*, 2012, 14, 605.
- 18 J. Zhao, Q. F. Lu, M. Z. Wei and C. Q. Wang, J. Alloys Compd., 2015, 646, 417.
- 19 Y. S. Xu, Z. J. Zhang and W. D. Zhang, *Mater. Res. Bull.*, 2013, 48, 1420.
- 20 J. L. Zhang, L. S. Zhang, N. Yu, K. B. Xu, S. J. Li, H. L. Wang and J. S. Liu, *RSC Adv.*, 2015, 5, 75081.
- 21 Y. Feng, X. Yan, C. B. Liu, Y. Z. Hong, L. Zhu, M. J. Zhou and W. D. Shi, *Appl. Surf. Sci.*, 2015, **353**, 87.
- 22 F. J. Zhang, S. F. Zhu, F. Z. Xie, J. Zhang and Z. D. Meng, *Sep. Sci. Technol.*, 2013, **113**, 1.

- 23 X. F. Chen, J. B. Liu, H. Wang, Y. L. Ding, Y. X. Sun and H. Yan, *J. Mater. Chem. A*, 2013, **1**, 877.
- 24 Z. Y. Jiang, Y. Y. Liu, M. M. Li, T. Jing, B. B. Huang, X. Y. Zhang, X. Y. Qin and Y. Dai, *Sci. Rep.*, 2016, 6, 22727.
- 25 S. Kumar and P. D. Sahare, Nano, 2013, 8, 1350007.
- 26 C. D. Lv, G. Chen, J. X. Sun, Y. S. Zhou, S. Fan and C. M. Zhang, *Appl. Catal.*, *B*, 2015, **179**, 54.
- 27 Z. S. Liu, J. N. Niu, P. Z. Feng, Y. W. Sui and Y. B. Zhu, *RSC Adv.*, 2014, 4, 43399.
- 28 X. Yang, X. J. Lian, S. J. Liu, J. Tian, C. P. Jiang and G. Wang, *Int. J. Electrochem. Sci.*, 2013, 8, 3721.
- 29 J. Di, J. X. Xia, M. X. Ji, H. P. Li, H. Xu, H. M. Li and R. Chen, *Nanoscale*, 2015, 7, 11433.
- 30 Y. T. Lu, Y. F. Pu, J. Wang, C. X. Qin, C. L. Chen and H. J. Seo, *Appl. Surf. Sci.*, 2015, **347**, 719.

- 31 K. K. Banger, Y. Yamashita, K. Mori, R. L. Peterson, T. Leedham, J. Rickard and H. Sirringhaus, *Nat. Mater.*, 2011, 10, 45.
- 32 J. Cao, B. Y. Xu, H. L. Lin, B. D. Luo and S. F. Chen, *Dalton Trans.*, 2012, 41, 11482.
- 33 W. S. D. Santos, L. D. Almeida, A. S. Afonso, M. Rodriguez, J. P. Mesquita, D. S. Monteiro, L. C. A. Oliveira, J. D. Fabris and M. C. Pereira, *Appl. Catal.*, *B*, 2016, **182**, 247.
- 34 H. L. Gao, S. C. Yan, J. J. Wang, Y. A. Huang, P. Wang, Z. S. Li and Z. G. Zou, *Phys. Chem. Chem. Phys.*, 2013, 15, 18077.
- 35 C. M. Li, G. Chen, J. X. Sun, H. J. Dong, Y. Wang and C. D. Lv, *Appl. Catal.*, B, 2014, 160–161, 383.
- 36 J. Su, X. X. Zou, G. D. Li, X. Wei, C. Yan, Y. N. Wang, J. Zhao, L. J. Zhou and J. S. Chen, *J. Phys. Chem. C*, 2011, **115**, 8064.