# **RSC Advances**



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2018, 8, 4695

Received 25th December 2017 Accepted 18th January 2018

DOI: 10.1039/c7ra13629c

rsc.li/rsc-advances

# 1. Introduction

Dialkyl carbonates have attracted widespread interest during the last decades due to their extensive industrial applications.<sup>1</sup> As an important homologue of the dialkyl carbonate family, diethyl carbonate (DEC) has become increasingly important as a green solvent, a replacement of some toxic substances such as phosgene, dimethyl sulphate and alkyl halide in carbonylation and alkylation reactions, and an electrolyte in lithium ion batteries.<sup>2-4</sup> Additionally, DEC can be used as an ideal additive for gasoline for its higher oxygen content and favorable fuel/ water distribution coefficient with negligible environmental pollution.5 Up to now, DEC can be synthetized via several routes: phosgenation of ethanol,6 oxidative carbonylation of ethanol,7,8 transesterification of organic carbonates,9,10 and ethanolysis of urea,11,12 among which ethanolysis of urea is particularly promising due to cost effectiveness, mild reaction conditions and safe operations. Furthermore, this process involves an indirect utilization of CO2: the by-product ammonia can be recycled and further reacts with CO<sub>2</sub> to produce urea,

# Acid-base sites synergistic catalysis over Mg–Zr–Al mixed metal oxide toward synthesis of diethyl carbonate†

Tingting Yan, Weihan Bing, Ming Xu, Yinwen Li, Yusen Yang, Guoqing Cui, Lan Yang<sup>10</sup> \* and Min Wei<sup>10</sup> \*

In heterogeneous catalysis processes, development of high-performance acid-base sites synergistic catalysis has drawn increasing attention. In this work, we prepared Mg/Zr/Al mixed metal oxides (denoted as  $Mg_2Zr_xAl_{1-x}$ -MMO) derived from Mg-Zr-Al layered double hydroxides (LDHs) precursors. Their catalytic performance toward the synthesis of diethyl carbonate (DEC) from urea and ethanol was studied in detail, and the highest catalytic activity was obtained over the  $Mg_2Zr_{0.53}Al_{0.47}$ MMO catalyst (DEC yield: 37.6%). By establishing correlation between the catalytic performance and Lewis acid-base sites measured by  $NH_3$ -TPD and  $CO_2$ -TPD, it is found that both weak acid site and medium strength base site contribute to the overall yield of DEC, which demonstrates an acid-base synergistic catalysis in this reaction. In addition, *in situ* Fourier transform infrared spectroscopy (*in situ* FTIR) measurements reveal that the Lewis base site activates ethanol to give ethoxide species; while Lewis acid site facilitates the activated adsorption of urea and the intermediate ethyl carbamate (EC). Therefore, this work provides an effective method for the preparation of tunable acid-base catalysts based on LDHs precursor approach, which can be potentially used in cooperative acid-base catalysis reaction.

which is sustainable and friendly process. Zinc oxide (ZnO) catalyst has been commonly used in this reaction with a relatively high yield of DEC, but suffered from dissolution of solid ZnO during the reaction.<sup>13</sup> Therefore, the exploration of highly efficient, stable catalysts is desirable. Previous studies have shown that both acidity and basicity are crucial to determine the catalytic performance in ethanolysis of urea;<sup>14,15</sup> however, the cooperation of acid-base sites as well as their respective contribution to catalytic performance are unclear. Thus, how to tune the acid-base properties of catalysts so as to achieve a synergistic catalysis with a high stability and efficiency remains a challenge.

Layered double hydroxides (LDHs)<sup>16,17</sup> are a class of anionic clay materials with alternating cationic brucite-type layers and charge-balancing anions located in the interlayer region, which can be represented by the formula  $[M_{1-x}^{2+}M_x^{3+}(OH)_2](A^{n-})_{x/n} \cdot mH_2O$ . In recent years, LDHs materials have attracted an intensive attention as catalysts and catalyst supports in heterogeneous catalysis, owing to their tunability in chemical composition and phase transformation from metal hydroxides to mixed metal oxides (MMOs) upon calcination treatments.<sup>18</sup> If the chemical composition and element ratio in LDHs host matrix are modulated, the resulting MMOs would possess versatility in concentration and intensity of Lewis acid-base sites. This inspires us to explore the synthesis of LDH precursors and precise control over their

State Key Laboratory of Chemical Resource Engineering, Beijing Advanced Innovation Center for Soft Matter Science and Engineering, Beijing University of Chemical Technology, Beijing 100029, P. R. China. E-mail: yanglan@mail.buct.edu.cn; weimin@mail.buct.edu.cn

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/c7ra13629c

structural transformation process, for the purpose of attaining acid–base sites synergistic catalysis toward synthesis of DEC.

In this work, Mg/Zr/Al mixed metal oxides (denoted as  $Mg_2Zr_xAl_{1-x}$ -MMO) were prepared by a facile phase transformation process from Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH precursors, and their catalytic performance toward DEC synthesis from urea and ethanol was investigated. A tunable acid-base site can be obtained via changing the Zr/Al molar ratio in the LDHs precursors. The Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>MMO catalyst demonstrates the best catalytic behavior with a DEC yield of 37.6%, which is among the highest level compared with previous studies. It is found that the synergistic catalysis between weak Lewis acid and medium strength Lewis base site is responsible for the DEC production: medium strength base site facilitates the activated adsorption of ethanol while weak acid site activates urea and intermediate ethyl carbamate (EC, the intermediate production from the reaction of ethanol and urea), which is revealed by in situ FTIR measurements.

# 2. Experiment section

#### 2.1 Materials

Chemical reagents, including  $Mg(NO_3)_2 \cdot 6H_2O$ ,  $ZrO(NO_3)_2 \cdot xH_2O$ ,  $Al(NO_3)_3 \cdot 9H_2O$ , NaOH, Na<sub>2</sub>CO<sub>3</sub>, ethanol, urea, and cyclohexanol was purchased and used without further purification. Deionized water was used in all the experimental processes.

# 2.2 Synthesis of MgZrAl–LDH precursors and MgZrAl–MMO catalysts

MgZrAl-LDH precursors with various compositions were synthesized by a co-precipitation method. Typically,  $Mg(NO_3)_2$ - $\cdot$  6H<sub>2</sub>O, ZrO(NO<sub>3</sub>)<sub>2</sub> $\cdot$  xH<sub>2</sub>O and Al(NO<sub>3</sub>)<sub>3</sub> $\cdot$  9H<sub>2</sub>O with a Mg<sup>2+</sup>/(Zr<sup>4+</sup> +  $Al^{3+}$ ) molar ratio of 2 were dissolved in 200 mL of deionized water to give a solution with a total cationic concentration of 0.1 M (solution A). NaOH (2 M) and Na<sub>2</sub>CO<sub>3</sub> (0.3 M) were dissolved in water (100 mL) to obtain a base solution (solution B). Solution B was added dropwise to solution A at 45 °C with vigorous stirring until the pH value of the slurry reached to 10. The slurry was aged at 75 °C for 12 h, and the obtained precipitate was washed thoroughly and dried in an oven at 60 °C overnight. The resulting sample is labeled as Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH, where x is the molar ratio of Zr/(Zr + Al). Subsequently, the Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH precursor was calcined at 550 °C for 4 h in a N<sub>2</sub> atmosphere at a heating rate of 5  $^{\circ}$ C min<sup>-1</sup>. The calcination process results in the phase transformation from Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH precursor to MgO-ZrO2-Al2O3 mixed metal oxides (denoted as  $Mg_2Zr_xAl_{1-x}$ -MMO).

#### 2.3 Catalytic evaluation

The catalytic performance was conducted on a stainless steel autoclave (50 mL) equipped with a magnetic stirrer. In a typical method, the catalyst, urea, and ethanol were packed into the reaction reactor. The air in the reaction reactor was replaced by  $N_2$  three times and then sealed. The reaction was performed at 200 °C for 5 h. The product was analyzed off-line by using gas

chromatograph (Shimadzu GC-2014C equipped with a flame ionization detector). The internal standard method was applied for the quantitative analysis with cyclohexanol as internal standard. For recycling tests, the used catalyst was separated from the liquid by centrifugation, washed thoroughly and dried, and then reused for the next reaction cycle.

For the reaction of urea and ethanol, the yield of diethyl carbonate (DEC) or ethyl carbamate (EC) was determined by the formulas:

$$Y = \frac{M}{\text{starting urea (mol)}} \times 100\%$$
 (1)

where *M* represents the cumulative mole number of DEC or EC, respectively.

#### 2.4 Characterization

Transmission electron microscopy (TEM) and high-resolution TEM (HRTEM) observations were carried out on a JEOL JEM-2100 transmission electron microscope. The morphology of the samples was investigated using a Zeiss Supra 55 scanning electron microscope (SEM) with an accelerating voltage of 20 kV. Powder X-ray diffraction (XRD) patterns were obtained on a Rigaku XRD-6000 diffractometer, using Cu K $\alpha$  radiation ( $\lambda =$ 0.15418 nm) at 40 kV, 30 mA, a scanning rate of 10° min<sup>-1</sup>, and a 2 $\theta$  angle ranging from 3 to 90°. Low-temperature N<sub>2</sub> adsorption-desorption isotherms of the samples were obtained on a Quantachrome Autosorb-1C-VP analyzer. Prior to N<sub>2</sub> adsorption, the sample was outgassed at 200 °C overnight. The total specific surface area was evaluated from the multipoint Brunauer-Emmett-Teller (BET) method.

In situ Fourier-transformed infrared absorption of pyridine (Py-IR) spectra were obtained using a Nicolet 380 instrument spectrophotometer. The sample (20 mg) was pressed into a self-supporting wafer and installed in an IR cell with  $CaF_2$  window, activated at 450 °C for 1 h in a flow of  $N_2$ , and then the temperature was cooled down to 150 °C for recording the background spectrum. Subsequently, pyridine was introduced into the cell at 150 °C for 1 h. The spectra were recorded after the sample was purged with flowing  $N_2$  to remove physisorbed pyridine.

Temperature-programmed desorption (TPD) was performed by using a Micromeritics AutoChem II 2920 apparatus, equipped with a thermal conductivity detector (TCD). Prior to adsorption, the sample (100 mg) was pretreated in a helium flow (50 cm<sup>3</sup> min<sup>-1</sup>) at 823 K for 1 h (heating rate: 10 °C min<sup>-1</sup>) and then cooled to 50 °C. The sample was exposed to CO<sub>2</sub> or NH<sub>3</sub> for 0.5 h, and then was maintained in a He flow for 1 h to remove physisorbed CO<sub>2</sub> or NH<sub>3</sub>. Afterwards, the temperature was increased linearly at a rate of 10 °C min<sup>-1</sup> to 600 °C for recording the signal of CO<sub>2</sub> or NH<sub>3</sub>.

In situ Fourier transform infrared spectroscopy (in situ FTIR) measurements were carried out using a Nicolet 380 instrument spectrophotometer with 4 cm<sup>-1</sup> of resolution. For the adsorption study of urea (or EC), 2 mg of urea (or EC) and 20 mg of catalyst were pressed into a self-supporting wafer, and then was packed into the IR cell. In the case of ethanol adsorption, the

catalyst (20 mg) was pressed into a self-supporting wafer and installed in the IR cell, followed by the introduction of ethanol vapor. IR spectra were recorded in the temperature range 30–210  $^{\circ}$ C.

#### 3. Results and discussion

#### 3.1 Structural and morphological studies on catalysts

Fig. 1A shows the XRD patterns of as-synthesized Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH precursors with various Mg/Zr/Al molar ratios. All the samples exhibit characteristic Bragg reflections at  $2\theta$  12° and 24°, which can be indexed to (003) and (006) of an LDH structure (JCPDS no. 35-0964), respectively. However, the crystallinity of Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-LDH decreases gradually with the increase of Zr content, probably owing to the distortion in LDH layers caused by the substitution of Al<sup>3+</sup> (ionic radius 0.053 nm) by Zr<sup>4+</sup> (ionic radius 0.072 nm). Calcination of LDH precursors at 550 °C results in the structural transformation from LDHs to mixed metal oxides. XRD patterns of Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-MMO samples (Fig. 1B) give superimposition of two kinds of oxide phases: Bragg reflections at  $2\theta$  36°, 43° and 63° are indexed to (111), (200) and (220) of periclase MgO phase (JCPDS no. 45-0946) and those at  $2\theta$  30° and 51° indicate the existence of tetragonal ZrO<sub>2</sub>



Fig. 1 (A) XRD patterns of LDH precursors: (a) Mg<sub>2</sub>Al-LDH, (b) Mg<sub>2</sub>-Zr<sub>0.22</sub>Al<sub>0.78</sub>-LDH, (c) Mg<sub>2</sub>Zr<sub>0.33</sub>Al<sub>0.67</sub>-LDH, (d) Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-LDH, and (e) Mg<sub>2</sub>Zr<sub>0.67</sub>Al<sub>0.33</sub>-LDH. (B) XRD patterns of (a) Mg<sub>2</sub>Al-MMO, (b) Mg<sub>2</sub>Zr<sub>0.22</sub>Al<sub>0.78</sub>-MMO, (c) Mg<sub>2</sub>Zr<sub>0.33</sub>Al<sub>0.67</sub>-MMO, (d) Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO, and (e) Mg<sub>2</sub>Zr<sub>0.67</sub>Al<sub>0.33</sub>-MMO. Crystalline phase: ( $\bullet$ ) ZrO<sub>2</sub>, ( $\blacksquare$ ) MgO.

(t-ZrO<sub>2</sub>) phase (JCPDS no. 42-1164). Interestingly, with the increase of Zr/Mg molar ratio, the peak intensity of MgO phase decreases gradually while that of  $ZrO_2$  phase enhances progressively. Additionally, no reflection of  $Al_2O_3$  is observed, indicating an amorphous phase.

As a typical sample, the structural transformation from  $Mg_2Zr_{0.53}Al_{0.47}$ -LDH precursor to  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO was studied by SEM, TEM and HRTEM measurements (Fig. 2). The  $Mg_2Zr_{0.53}Al_{0.47}$ -LDH precursor (Fig. 2A and C) shows smooth and uniform thin platelet nanocrystal;  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO still inherits the original lamellar morphology of LDH precursor (Fig. 2B and D), but with a porous structure resulting from the calcination process. In addition, HRTEM image of  $Mg_2Zr_{0.53}$ -Al<sub>0.47</sub>-MMO sample (Fig. 2E) exhibits two identified lattice fringe distances of 0.210 nm and 0.295 nm, which are indexed to the (200) plane of MgO and (101) plane of t-ZrO<sub>2</sub> phase, respectively. This displays a homogeneous dispersion of MgO and t-ZrO<sub>2</sub> in an amorphous Al<sub>2</sub>O<sub>3</sub> platelet matrix, in good accordance with the XRD results.

Specific surface area and pore-size distribution of all these  $Mg_2Zr_xAl_{1-x}$ -MMO samples were studied by the nitrogen adsorption-desorption isotherms and porosity measurements. All the samples display IV type isotherms with H3 shaped hysteresis loops, which are typical characteristic of mesoporous materials and plate-like particles (Fig. 3). As listed in Table 1, with the increase of Zr content, the surface area shows an increase trend from 113.27 m<sup>2</sup> g<sup>-1</sup> to 159.45 m<sup>2</sup> g<sup>-1</sup> and then decreases to 143.64 m<sup>2</sup> g<sup>-1</sup>, with an average pore diameter ranging in 8–10 nm. Noticeably, in comparison with the Mg<sub>2</sub>Al-MMO sample (111.12 m<sup>2</sup> g<sup>-1</sup>), the Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-MMO samples show higher surface area (113.27–159.45 m<sup>2</sup> g<sup>-1</sup>), as a result of the introduction of Zr, which would be favorable in heterogeneous catalysis process.

#### 3.2 Acid-base properties of catalysts

CO2-TPD, NH3-TPD and IR spectroscopy of adsorbed pyridine (Py-IR) are powerful measurements to investigate the concentration and strength of basic and acid sites of catalyst,19 which were performed in this work (Fig. 4 and Table 2). For the CO<sub>2</sub>-TPD profiles, the samples show a broad CO<sub>2</sub> desorption peak in the range 50-550 °C, which can be deconvoluted into three peaks with maximal temperatures  $(T_M)$  in the region 120-130 °C, 170-220 °C, 300-350 °C by a Gaussian peak fitting method, corresponding to the weak, medium and strong base site, respectively. According to previous studies, the weak, medium and strong base site are derived from OH group, metal-oxygen pair and low-coordination oxygen anion, respectively.20 In the case of NH3-TPD profiles, three desorption peaks with  $T_{\rm M}$  at ~130 °C, 250 °C and 350 °C are denoted as the weak, medium and strong acid site, respectively.<sup>21,22</sup> Notably, it is observed that with the increase of  $Zr^{4+}/(Zr^{4+} + Al^{3+})$  ratio from 0.22 to 0.53, the amount of medium basic site or weak acid site enhances significantly, and then decreases from 0.53 to 0.67. The sample of Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO gives the largest amount of both medium basic site and weak acid site, showing a Zr<sup>4+</sup>/Al<sup>3+</sup> ratio-dependent acid-base site. The increment of medium basic



Fig. 2 SEM images of (A)  $Mg_2Zr_{0.53}Al_{0.47}$ -LDH, (B)  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO. TEM images of (C)  $Mg_2Zr_{0.53}Al_{0.47}$ -LDH, (D)  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO. (E) HRTEM image of  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO.



Fig. 3 (A) N<sub>2</sub> adsorption–desorption curves and (B) pore size distributions of: (a) Mg<sub>2</sub>Al–MMO, (b) Mg<sub>2</sub>Zr<sub>0.22</sub>Al<sub>0.78</sub>–MMO, (c) Mg<sub>2</sub>Zr<sub>0.33</sub>–Al<sub>0.67</sub>–MMO, (d) Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO, (e) Mg<sub>2</sub>Zr<sub>0.67</sub>Al<sub>0.33</sub>–MMO.

Table 1 Structural parameters of various samples

Sample	$S_{\rm BET}^{a}/{ m m}^2~{ m g}^{-1}$	<i>D</i> <sub>BJH</sub> <sup>b</sup> /nm	$V_{\rm BJH}^{\ \ c}/{\rm cm}^3~{\rm g}^{-1}$
Mg <sub>2</sub> Al-MMO	111.12	30.87	1.11
Mg <sub>2</sub> Zr <sub>0.22</sub> Al <sub>0.78</sub> -MMO	113.27	10.28	0.41
$Mg_2Zr_{0.33}Al_{0.67}-MMO$	129.16	9.78	0.57
$Mg_2Zr_{0.53}Al_{0.47}-MMO$	159.45	8.32	0.43
Mg <sub>2</sub> Zr <sub>0.67</sub> Al <sub>0.33</sub> -MMO	143.64	8.21	0.42

 $^a$  BET surface area.  $^b$  BJH desorption average pore diameter.  $^c$  BJH desorption cumulative pore volume.

site can be attributed to the enrichment of  $Zr^{4+}-O^{2-}$ , in light of a constant Mg content (Mg<sup>2+</sup>-O<sup>2-</sup>) in all these samples. As for the increase of weak acid site, we propose that  $ZrO_2$  phase gives predominant contribution, since  $Al_2O_3$  mainly provides medium-strong acid site.<sup>23-25</sup> It should be noted that the sample of Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO possesses the largest specific surface area (159.45 m<sup>2</sup> g<sup>-1</sup>), which is favorable for the exposure of medium basic or weak acid site. In addition, Py-IR measurements were performed over Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>–MMO samples to study Lewis and Brønsted acid site.<sup>26,27</sup> All these samples display a characteristic band of pyridine adsorption at 1444 cm<sup>-1</sup>, indicating the presence of Lewis acid site originating from ZrO<sub>2</sub> and Al<sub>2</sub>O<sub>3</sub>. Moreover, as the Zr/Al ratio increases, the peak intensity at 1444 cm<sup>-1</sup> strengthens gradually and reaches to maximum value over the sample of Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO, consistent with the results of NH<sub>3</sub>-TPD.

#### 3.3 Catalytic performance of catalysts

The catalytic performance of Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-MMO catalysts toward the synthesis of DEC from ethanol and urea was studied. As shown in Fig. 5A, the yield of DEC shows an increase trend (from 19.9% to 37.6%) as the reaction temperature rises from 180 to 200 °C, followed by a decrease (from 37.6% to 33.0%) within 200-210 °C. In contrast, the intermediate product, ethyl carbamate (EC), shows an opposite change tendency, with the lowest vield at 200 °C. The reason is that a higher reaction temperature will lead to the reverse reaction from DEC to EC as well as the decomposition of EC to N-ethyl ethyl carbamate (side reactions).<sup>14</sup> Thus, the reaction temperature is chosen as 200 °C. Fig. 5B displays the DEC synthesis as a function of reaction time, from which the largest yield of DEC is obtained at 5 h. Afterwards, the influence of catalyst weight on the catalytic behavior was also studied, and it was found that DEC yield reached the maximal value at 10% catalyst weight (Fig. 5C). Finally, as for the urea/ethanol molar ratio (Fig. 5D), the yield of DEC achieves the largest one with the ethanol/urea molar ratio of 15.

Furthermore, the catalytic performance of various  $Mg_2Zr_x$ -Al<sub>1-x</sub>-MMO catalysts were evaluated under the optimum



Fig. 4 (A)  $CO_2$ -TPD, (B) NH<sub>3</sub>-TPD profiles and (C) Py-IR spectra of (a) Mg<sub>2</sub>Zr<sub>0.22</sub>Al<sub>0.78</sub>-MMO, (b) Mg<sub>2</sub>Zr<sub>0.33</sub>Al<sub>0.67</sub>-MMO, (c) Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO, and (d) Mg<sub>2</sub>Zr<sub>0.67</sub>Al<sub>0.33</sub>-MMO.

catalytic reaction (Fig. 5E and Table 3). The Mg<sub>2</sub>Al–MMO catalyst shows catalytic activity toward DEC synthesis, yielding 21.5% DEC. The introduction of element Zr results in a significant enhancement: the DEC yield increases gradually from



**Fig. 5** Effects of reaction conditions on the yield of DEC over Mg<sub>2</sub>-Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO catalyst: (A) temperature, (B) reaction time, (C) the amount of catalyst and (D) ethanol/urea molar ratio as a function of DEC yield, respectively. (E) DEC yield over various catalysts under the following reaction conditions: 10 wt% catalyst (by urea), ethanol/urea molar ratio of 15, T = 200 °C, t = 5 h. (F) Catalytic performances of Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO in 5 consecutive recycles.

21.5% to 37.6% with the increase of Zr content, and then decreases to 34.0%; the maximum value is present in the sample of  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO. This is, to the best of our knowledge, among the highest level compared with previous reports.<sup>6,11,12,14</sup> In addition, the reusability of  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO catalyst was also studied (Fig. 5F). The used catalyst was

Table 2	Concentrations	of base and	acid site	according to	CO <sub>2</sub> -TPD	and NH <sub>3</sub> -TF	D profiles
	concentrations	or buse und	uciu site	according to	CO2 11 D	und with the	D promes

	Base sites (mmol $g^{-1}$ )				Acid sites (mmol $g^{-1}$ )			
Sample	$B_{\rm TOTAL}^{a}$	$B_{\mathrm{W}}{}^{b}$	$B_{\mathbf{M}}^{\ \ b}$	$B_{\rm S}{}^b$	$A_{\mathrm{TOTAL}}^{c}$	$A_{\mathrm{W}}{}^{d}$	$A_{\mathbf{M}}{}^{d}$	$A_{s}^{d}$
Mg <sub>2</sub> Zr <sub>0.22</sub> Al <sub>0.78</sub> -MMO	0.311	0.045	0.151	0.115	0.277	0.074	0.143	0.060
Mg <sub>2</sub> Zr <sub>0.33</sub> Al <sub>0.67</sub> -MMO	0.367	0.060	0.209	0.098	0.299	0.115	0.132	0.052
$Mg_2Zr_{0.53}Al_{0.47}$ -MMO	0.543	0.103	0.315	0.125	0.436	0.160	0.224	0.052
Mg <sub>2</sub> Zr <sub>0.67</sub> Al <sub>0.33</sub> -MMO	0.411	0.076	0.254	0.081	0.306	0.143	0.107	0.056

<sup>*a*</sup>  $B_{\text{TOTAL}}$  is the total concentration of base sites calculated based on CO<sub>2</sub>-TPD. <sup>*b*</sup>  $B_{W}$ ,  $B_{M}$ , and  $B_{S}$  represent the concentration of weak, medium, and strong base site, respectively, which are calculated according to CO<sub>2</sub>-TPD and the deconvoluted TPD profiles in the temperature range 50–550 °C. <sup>*c*</sup>  $A_{\text{TOTAL}}$  is the total concentration of acid sites calculated based on NH<sub>3</sub>-TPD. <sup>*d*</sup>  $A_{W}$ ,  $A_{M}$ , and  $A_{S}$  denote the concentration of weak, medium, and strong acid site, respectively, which are calculated according to NH<sub>3</sub>-TPD and the deconvoluted TPD profiles in the temperature range 50–550 °C.

Table 3 Catalytic performance of various catalysts

	Product yield (%)		
Sample	EC	DEC	
Mg <sub>2</sub> Al-MMO	53.2	21.5	
$Mg_2Zr_{0,22}Al_{0,78}$ -MMO	53.6	28.4	
Mg <sub>2</sub> Zr <sub>0.33</sub> Al <sub>0.67</sub> -MMO	50.9	31.9	
$Mg_2Zr_{0.53}Al_{0.47}$ -MMO	45.3	37.6	
Mg <sub>2</sub> Zr <sub>0.67</sub> Al <sub>0.33</sub> -MMO	51.9	34.0	

separated from the liquid product by centrifugation, washed thoroughly and dried, directly reused for the next recycle evaluation. The catalytic performance toward DEC yield shows a slight decrease after five recycles but still remains at 32.0%, indicating a satisfactory reusability.

#### 3.4 Studies on structure-property correlation

Previous studies have shown that both acidity and basicity are important to determine the catalytic activity in ethanolysis of urea.14 Herein, to give a deep insight into the relationship between the catalytic performance and acid-base sites of Mg<sub>2</sub>- $Zr_xAl_{1-x}$ -MMO samples, we correlate the DEC yield with surface acidity and basicity measured by NH<sub>3</sub>- and CO<sub>2</sub>-TPD. As shown in Fig. 6, it's interesting that the DEC yield increases along with the specific surface concentration of medium strength basicity or weak acidity, respectively, demonstrating a synergistic acidbase catalysis for the ethanolysis of urea reaction to synthesize DEC. To further investigate the cooperation mechanism between medium strength basicity and weak acidity and their respective contribution, in situ FTIR of reactants on the catalysts was conducted. The ethanolysis of urea includes two consecutive steps: the formation of intermediate ethyl carbamate (EC) from urea and ethanol, followed by the subsequent conversion to DEC. The second step (reaction of EC with ethanol), is regarded as the rate-limiting step for its unfavorable thermodynamics.<sup>2</sup> Thus, we carried out the adsorption measurements of urea, EC and DEC over Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO and control sample (Mg<sub>2</sub>Al-MMO), respectively. Fig. 7A shows the urea adsorption over Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO within the temperature range 30-210 °C. At room temperature, the characteristic bands of urea are observed: bands at 3436 cm<sup>-1</sup> and 3345 cm<sup>-1</sup> are



Fig. 6 Correlations between the DEC yield and (A) the surface weak acid site  $(A_W)$  or (B) surface medium strength basic site  $(B_M)$  over Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>-MMO samples.



Fig. 7 In situ FTIR spectra of (A) urea and (B) EC over  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO sample, respectively, within the temperature range 30–210 °C.

due to N–H stretching vibrations; bands at 3213 cm<sup>-1</sup> is attributed to the N–H stretching vibration with intermolecular association; bands at 1681 cm<sup>-1</sup> and 1161 cm<sup>-1</sup> are assigned to C=O and C–N stretching vibrations. A new band at 2165 cm<sup>-1</sup> appears at 130 °C with gradually enhanced intensity until 200 °C, accompanied with decreased bands of urea. This band is assigned to the formation of metal isocyanato group: O=C=N bound to the metal oxide surface (O=C=N–M asymmetric stretching, M represent Al<sup>3+</sup>, Zr<sup>4+</sup>),<sup>15</sup> as a result of the adsorption of urea onto Lewis acid sites (ZrO<sub>2</sub> and Al<sub>2</sub>O<sub>3</sub> in Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO catalyst).

Furthermore, the adsorption of EC on the catalysts was studied. As shown in Fig. 7B, a band at 2165 cm<sup>-1</sup> corresponding to the stretching vibration of O=C=N bound to the metal oxide surface (O=C=N-M asymmetric stretching, M represent Al<sup>3+</sup>, Zr<sup>4+</sup>) is observed, whose intensity increases as the temperature rises from 100 to 200 °C, indicating that EC is effectively activated. Compared with EC adsorption on Mg<sub>2</sub>Al-MMO catalyst (Fig. S4:† O=C=N-M stretching at 2160 cm<sup>-1</sup>) adsorption temperature at 180 °C), a higher frequency of 2165 cm<sup>-1</sup> and a lower temperature of 100 °C are observed for Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO catalyst. This lower temperature implies the activation of EC on Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO is more favorable than that on Mg<sub>2</sub>Al-MMO catalyst. A higher frequency indicates a stronger O=C=N bond but a weaker interaction between O and acid site in Mg2Zr0.53Al0.47-MMO.2 As discussed above, Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO catalyst possesses mainly weak acid site deprived from ZrO2 while Mg2Al-MMO offers medium-strong acid site (Fig.  $S2^{\dagger}$ ) provided by  $Al_2O_3$ . In other words, weak Lewis acid site serves as main active site to activate EC over Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO while medium-strong Lewis acid site accounts for the activated adsorption of EC over Mg<sub>2</sub>Al-MMO. This is in accordance with the correlation between DEC yield and surface weak acidity measured by NH<sub>3</sub>-TPD (Fig. 4). The activation of EC by weak Lewis acid site over Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO catalyst is more efficient than by the medium-strong Lewis acid site over Mg<sub>2</sub>Al-MMO sample, which promotes the conversion of EC to DEC (the rate-limiting step) with a higher vield of DEC.

Finally, we investigated the adsorption behavior of ethanol over  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO at various temperatures (Fig. 8). In the  $CH_2/CH_3$  stretching region, two peaks at 2962 and



Fig. 8 In situ FTIR spectra evolution of ethanol over  $Mg_2Zr_{0.53}Al_{0.47}$ - MMO at: (a) 100 °C, (b) 120 °C, (c) 150 °C, (d) 180 °C, (e) 200 °C, respectively.

2923 cm<sup>-1</sup> are attributed to CH<sub>3</sub> stretching and the peak at 2865 cm<sup>-1</sup> is due to CH<sub>2</sub> stretching in ethoxide.<sup>28</sup> In C-C-O stretching regions, the band at 1064 cm<sup>-1</sup> and 1118 cm<sup>-1</sup> are assigned to adsorbed ethoxide species<sup>28</sup> over the catalyst, which indicates that ethanol is effectively activated over Mg2Zr0.53- $Al_{0.47}$ -MMO through the abstraction of  $H^{\delta+}$  by Lewis basic site. Additionally, the peaks intensity of ethoxide species increases gradually when the temperature rises from 100 °C to 200 °C, indicating an enhanced activation of ethanol over Mg<sub>2</sub>Zr<sub>0.53</sub>-Al<sub>0.47</sub>-MMO at a higher temperature. In comparison, Mg<sub>2</sub>Al-MMO sample displays two peaks at 1102 cm<sup>-1</sup> and 1165 cm<sup>-1</sup> (Fig. S5<sup>†</sup>) in C-C-O stretching region, corresponding to the adsorbed ethoxide species.29 The large difference in band position suggests that the basic sites provided by the two catalysts are different for the activation of ethanol: Zr<sup>4+</sup>–O<sup>2–</sup> as main basic site is responsible for the activated adsorption of ethanol (ethoxide species) over Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO while Mg<sup>2+</sup>-O<sup>2-</sup> serves as predominant active center in Mg<sub>2</sub>Al-MMO sample. Previous study reported that weak basic site can not activate ethanol in this catalytic system.4 Thus, based on the combination of in situ FTIR spectra and CO2-TPD results, it is proposed that the presence of medium strength Lewis basic sites (Zr<sup>4+</sup>-O<sup>2-</sup>, Mg<sup>2+</sup>-O<sup>2-</sup>) in Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>-MMO facilitates the activated adsorption of ethanol to produce ethoxide which is involved in the following reaction.

## 4. Conclusions

In summary, acid–base Mg/Zr/Al mixed metal oxides (denoted as Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>–MMO) were successfully synthesized *via* the calcination transformation of Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>–LDH precursors. The obtained Mg<sub>2</sub>Zr<sub>x</sub>Al<sub>1-x</sub>–MMO catalysts are evaluated by the ethanolysis of urea reaction to produce DEC, and the sample of Mg<sub>2</sub>Zr<sub>0.53</sub>Al<sub>0.47</sub>–MMO demonstrates the largest DEC yield of 36.7%. Studies on structure–activity correlation reveal a cooperative catalysis between medium strength base site and weak acid site of  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO in this reaction. Moreover,  $CO_2$ - and  $NH_3$ -TPD study as well as the *in situ* FTIR measurements verify that the medium strength Lewis base sites  $(Zr^{4+}-O^{2-}, Mg^{2+}-O^{2-})$  serve as active center to activate ethanol to produce ethoxide species; while weak Lewis acid sites (mostly  $ZrO_2$ ) act as active site toward EC activation to produce O=C=N-M. Therefore, a synergistic acid-base catalysis is demonstrated in the  $Mg_2Zr_{0.53}Al_{0.47}$ -MMO catalyst, accounting for its higher DEC yield toward ethanolysis of urea reaction.

# Conflicts of interest

There are no conflicts to declare.

# Acknowledgements

This work was supported by the National Key Research and Development Program (Grant No. 2017YFA0206804), the National Natural Science Foundation of China (NSFC) and the Fundamental Research Funds for the Central Universities (buctylkxj01).

### Notes and references

- 1 S. Huang, B. Yan, S. Wang and X. Ma, *Chem. Soc. Rev.*, 2015, 44, 3079–3116.
- 2 F. Li, H. Li, L. Wang, P. He and Y. Cao, *Catal. Sci. Technol.*, 2015, 5, 1021–1034.
- 3 K. Shukla and V. C. Srivastava, *RSC Adv.*, 2016, 6, 32624–32645.
- 4 D. Wang, X. Zhang, C. Liu, T. Cheng, W. Wei and Y. Sun, *Appl. Catal., A*, 2015, **505**, 478-486.
- 5 D. Wang, B. Yang, X. Zhai and L. Zhou, *Fuel Process. Technol.*, 2007, **88**, 807–812.
- 6 I. E. Muskat and F. Strain, US Pat., 2,379,250, 1941.
- 7 I. Prymak, V. N. Kalevaru, S. Wohlrab and A. Martin, *Catal. Sci. Technol.*, 2015, **5**, 2322–2331.
- 8 J. Wang, Z. Hao and S. Wohlrab, *Green Chem.*, 2017, 19, 3595–3600.
- 9 I. Zielinska-Nadolska, K. Warmuzinski and J. Richter, *Catal. Today*, 2006, **114**, 226–230.
- 10 S.-J. Wang, S.-H. Cheng, P.-H. Chiu and K. Huang, *Ind. Eng. Chem. Res.*, 2014, 53, 5982–5995.
- 11 W. Zhao, W. Peng, D. Wang, N. Zhao, J. Li, F. Xiao, W. Wei and Y. Sun, *Catal. Commun.*, 2009, **10**, 655–658.
- 12 A. Angelini, A. Dibenedetto, D. Curulla-Ferré and M. Aresta, *RSC Adv.*, 2015, 5, 88401–88408.
- A. Dibenedetto, A. Angelini, M. Aresta, S. Fasciano, M. E. Cucciolito, F. Ruffo, B. M. Aresta, D. Curulla-Ferré and E. De Giglio, *Appl. Catal.*, A, 2015, 493, 1–7.
- 14 K. Shukla and V. C. Srivastava, *Fuel Process. Technol.*, 2017, 161, 116–124.
- 15 Y. Gao, W. Peng, N. Zhao, W. Wei and Y. Sun, *J. Mol. Catal. A: Chem.*, 2011, **351**, 29–40.
- 16 Q. Wang and D. O'Hare, Chem. Rev., 2012, 112, 4124-4155.

- 17 C. Li, M. Wei, D. G. Evans and X. Duan, *Small*, 2014, **10**, 4469–4486.
- 18 J. Liu, W. Bing, X. Xue, F. Wang, B. Wang, S. He, Y. Zhang and M. Wei, *Catal. Sci. Technol.*, 2016, **6**, 3976–3983.
- 19 J. Xie, W. Zhuang, W. Zhang, N. Yan, Y. Zhou and J. Wang, *ChemCatChem*, 2017, **9**, 1076–1083.
- 20 P. Liu, M. Derchi and E. J. M. Hensen, *Appl. Catal., A*, 2013, **467**, 124–131.
- 21 F. Jiang, L. Zeng, S. Li, G. Liu, S. Wang and J. Gong, ACS Catal., 2014, 5, 438-447.
- 22 H. Chen, S. He, M. Xu, M. Wei, D. G. Evans and X. Duan, *ACS Catal.*, 2017, 7, 2735–2743.
- 23 S.-K. Wu, P.-C. Lai, Y.-C. Lin, H.-P. Wan, H.-T. Lee and Y.-H. Chang, ACS Sustainable Chem. Eng., 2013, 1, 349–358.

- 24 W. Li, X. Nie, X. Jiang, A. Zhang, F. Ding, M. Liu, Z. Liu, X. Guo and C. Song, *Appl. Catal.*, B, 2018, 220, 397–408.
- 25 J. R. Copeland, I. A. Santillan, S. M. Schimming, J. L. Ewbank and C. Sievers, *J. Phys. Chem. C*, 2013, **117**, 21413–21425.
- 26 G. S. Foo, D. Wei, D. S. Sholl and C. Sievers, *ACS Catal.*, 2014, 4, 3180–3192.
- 27 J. Sun, K. Zhu, F. Gao, C. Wang, J. Liu, C. H. Peden and Y. Wang, J. Am. Chem. Soc., 2011, 133, 11096–11099.
- 28 J. J. Bravo-Suárez, B. Subramaniam and R. V. Chaudhari, *Appl. Catal.*, *A*, 2013, 455, 234–246.
- 29 T. W. Birky, J. T. Kozlowski and R. J. Davis, *J. Catal.*, 2013, **298**, 130–137.