RSC Advances



View Article Online

View Journal | View Issue

REVIEW

Check for updates

Cite this: RSC Adv., 2018, 8, 11778

Role of ceria in the improvement of NO removal of lanthanum-based perovskite-type catalysts

Xiaochen Li and Hongwei Gao 💷*

Lanthanum-based perovskite-type oxides represented by LaBO₃ (B = Co, Fe, Mn) have been thought to present strong limitations for practical application although they are active for catalytic removal of NO. Cerium (Ce) substitution has been extensively studied to modify the properties of perovskites. It is noted that a new phase of ceria (CeO₂) can be separated from perovskites when the doping ratio exceeds the solution limit (x > S). This review outlines the relationship between the existence of CeO₂ phase and catalytic activity. CeO₂ dispersing on the lattice surface or small particles are beneficial for catalytic activity, but larger particles are adverse. Ce-doped LaBO3 perovskites exhibiting the best activity must contain additional CeO₂ phases. In addition, CeO₂-supported LaBO₃ perovskite catalysts are discussed.

Received 16th January 2018 Accepted 19th March 2018

DOI: 10.1039/c8ra00456k

rsc.li/rsc-advances

Introduction 1.

The major pollutants discharged from vehicle engines to the environment are particulate matter (PM), carbon dioxide, hydrocarbons and nitrogen oxides (NO_x) . Among these contaminants, NO_x is paid increasing attention, owing to the fact that it is not only harmful to human health but also responsible for acid rain and photochemical smog.1-3 The main component of NO_x that we refer to is NO which is generated from nitrogen and oxygen at an appropriate temperature.⁴ In the past 40 years, great efforts have been carried out for minimizing NO emission.

From the thermodynamic view, the process (NO = $1/2N_2 + 1/2N_2$ 2O₂; $\Delta G_{\rm f}^0 = -86 \text{ kJ mol}^{-1}$)⁵ is favored, but it is kinetically hindered because of its high activation energy $(364 \text{ kJ mol}^{-1})$.⁶ To solve the afore-mentioned problem, a good deal of catalytic methods and catalysts have been studied. Currently, NO removal methods that we have learned can be roughly classified as two major technologies: NO decomposition and NO reduction. The former can be regarded as a "green" process since no additional toxic reactant, such as ammonia, is required and the NO_x gases are decomposed into N_2 and O_2 as harmless components. Oppositely, the latter (e.g. NO_x storage and reduction (NSR), selective catalytic reduction (SCR), etc.) usually requires the addition of a supplemental reductant which causes further problems, such as higher equipment cost and secondary pollution. At present, three principal types of catalysts active for NO removal are zeolites,7-9 noble metals10,11 and composite mixed oxides.12-16 However, the first, zeolites, are subject to

hydrothermal deactivation and are only active at high temperature while the second, noble metals, are costly and easily agglomerated during the reaction. In contrast to the above two catalysts, composite mixed oxides, especially perovskite-type catalyst with the general formula of ABO₃, have considered as a group of promising catalysts for NO removal as they are lower price, mixed valence states of the transition metals and higher stability.17-19

Lanthanum-based perovskites (LaBO₃), some of which exhibit excellent performance for NO removal,20-22 have been extensively investigated. As far as we know, unmodified LaBO3 perovskites present strong limitations (e.g. comparatively small surface area and low catalytic activity at low temperatures)^{21,22} and therefore reliable technologies need to be developed. Among these technologies tackling aforementioned problems, we find that doping Ce into perovskite (e.g. $La_{0.6}Ce_{0.4}CoO_3$) or CeO₂ as a "support" (e.g. LaCoO₃/CeO₂) are effective. In addition, it have been reported that the solubility of Ce in LaBO₃ perovskites is low and CeO2 appears in the mixed-oxides when Ce addition exceeds its solubility limit (S). The valence alternation ability of Ce³⁺/Ce⁴⁺ makes CeO₂ a good oxygen reservoir which stores and releases oxygen under oxidizing and reducing conditions, respectively.^{23,24} In this review, CeO₂ is focused because of its significant role in improving catalytic activity of LaBO₃ perovskites catalysts. The roles played CeO_2 by will be introduced by the following two topics: (i) CeO₂ as separated phase (ii) CeO_2 as the support.

Description of lanthanum-based 2. perovskite-type catalysts

The perovskite-type oxides mentioned here adopt LaBO₃ structure (Fig. 1), in which B-sites are occupied by small transition metals such as Fe, Mn.²⁵⁻²⁷ For the resulting compounds, each

Key Laboratory of Plant Resources and Chemistry in Arid Regions, Xinjiang Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, Urumqi 830011, China. E-mail: gaohongw369@ms.xjb.ac.cn; Fax: +86-991-3858319; Tel: +86-991-3858319



Fig. 1 Crystal structure of the LaBO₃ perovskite oxide.⁴

La cation is surrounded by 12 oxygen anions whereas each B cation is surrounded by 6 oxygen anions.28 In the ideal unit cell where the atoms are packed closely, La–O distance is equal to *a*/ $\sqrt{2}$ (a is the cubic unit cell parameter) while B–O distance is a/2. Besides, La, B and O ions should satisfy the requirement that the value of tolerance factor $(t)^{28-30}$ is equal to 1. The parameter is defined by the expression $t = (r_{\text{La}} + r_{\text{B}})/{\sqrt{2(r_{\text{B}} + r_{\text{O}})}}$, where r_{La} , $r_{\rm B}$ and $r_{\rm O}$ correspond to the crystal radii for cations La and B and the anion O, respectively. However, the perovskite structure is also found for lower values of t in the range 0.75 to $1.^{28,30}$ The simple perovskite structure could be partially replaced by foreign ions with appropriate size difference, preserving matrix perovskite structure. In such cases, the cubical structure can be distorted into tetragonal, rhombohedral, or other lower symmetries.^{29,30} Besides the ionic radii requirement, electroneutrality is another condition. For example, the substitution of La³⁺ cation in LaMnO₃ with Sr²⁺ is accompanied by a change of the oxidation state of Mn cation ($Mn^{3+} \rightarrow Mn^{4+}$) and exhibits oxidative non-stoichiometry.31 The substitution may stabilize an unusual oxidation state of the cation in position B and/or produce oxygen vacancies or structural defects.³¹⁻³³ These excellent characteristics can enhance substantially the catalytic activity and therefore have frequently been exploited in perovskite-type catalysis.

Ce often appears as a good promoter in perovskite lattice because of its two different valence states Ce^{4+} or Ce^{3+} .^{4,34,35} The substitution of La^{3+} cation in LaBO₃ with higher valence Ce^{4+} will affect indirectly the electronic state of the B-site ion. As mentioned above, Sr^{2+} are used to partially substitute the A-site ions in order to increase the basicity and to produce oxide anion vacancies by charge compensation. To get a better and clearer understanding about Ce doping, we take LaCoO₃ as an example to explain the process of defect formation. Three reactions have been considered for Ce doping,^{36,37} the first two of which are for doping stoichiometric LaCoO₃. The substitution of La^{3+} cation in LaCoO₃ with Ce^{4+} leads to creation of La^{3+} vacancies (eqn (1)) or reduction of Co^{3+} to Co^{2+} (eqn (2)).

$$3\text{CeO}_2 + 4\text{La}_{\text{La}}^{\times} \rightarrow 3\text{Ce}_{\text{La}}^{\cdot} + V^{\prime\prime\prime}_{\text{La}} + 2\text{La}_2\text{O}_3 \tag{1}$$

$$4\text{CeO}_2 + 4\text{La}_{\text{La}}^{\times} + 4\text{Co}_{\text{Co}}^{\times} \rightarrow 4\text{Ce}_{\text{La}}^{\cdot} + 4\text{Co}_{\text{Co}}^{\prime} + 2\text{La}_2\text{O}_3 + \text{O}_2$$
 (2)

However, as prepared LaCoO₃ calcined at \geq 900 °C is typically slightly reductively non-stoichiometric.³⁸ Therefore, the third reaction that Ce is doped into the LaCoO₃ lattice containing oxygen lattice vacancies was considered. This means that those oxygen vacancies were refilled.

$$2\mathrm{La}_{\mathrm{La}}^{\times} + 2\mathrm{CeO}_2 + \mathrm{V}_{O}^{\sim} \rightarrow 2\mathrm{Ce}_{\mathrm{La}}^{\sim} + \mathrm{La}_2\mathrm{O}_3 + \mathrm{O}_{\mathrm{O}}^{\times}$$
(3)

These defects caused by Ce doping lead to the fact that perovskite-type oxides show promising structural, surface and catalytic properties for catalyst application. In addition, supported lanthanum-based perovskite-type catalysts, *e.g.* LaBO₃/ CeO₂, were also extensively studied.

3. CeO₂ as separated phase

Among various perovskites, lanthanum-based samples represented by $LaBO_3$ (B = Co, Fe, Mn) are known to be excellent catalysts for NO removal.^{21,22} Also, it has been reported that the Ce often appeared as a crucial component for perovskites because of its two different valence states Ce^{4+} or Ce^{3+} , which is important to the catalytic reaction. This is the reason why people have been paying increasing attention to Ce-doped LaBO₃ perovskites.

For a low Ce content (which is below its solubility in perovskite structure), Ce can be incorporated into the LaBO₃ lattice to form a solid solution. The valence change of B is complicated due to the addition of Ce. The substitution of La³⁺ in LaBO₃ with Ce^{3+} result in no change of valence state of B ions (Bⁿ⁺). The higher valence Ce⁴⁺ substitution lead to the fact that electroneutrality of the lattice is not maintained. As such, cation vacancies are formed and valence state of B ions is changed. No interstitial oxygen ions, however, are detected because perovskite lattice cannot accommodate them.^{39,40} For high Ce content (which exceed their solubility limit in perovskite structure), CeO₂ are formed and segregated from perovskite oxides. The extra phase, CeO₂, is either highly dispersed on the surface of $La_{1-x}Ce_xBO_3$ for comparatively low Ce content or found as larger particles for higher Ce content. The presence of CeO2 result in appearance of Ce vacancy sites or migration of (excess) B ions outside the perovskite lattice to yield ByOx or both.41 In this case, CeO_2 are believed to play a key role in enhancement of catalytic performance.

3.1 Ce doped LaCoO₃

The influence of Ce substitution on structural characteristics has been discussed in previous literatures.^{42–48} Based on the Xray diffraction (XRD) results, Fig. 2, no peaks of CeO₂ are detected when Ce addition was below 0.05, indicating that the doped Ce atoms might have embodied into the LaCoO₃ lattice to form a solid solution. For x = 0 and 0.05, the structures were the rhombohedral LaCoO₃-type (JCPDS 25-1060). As the content of doped Ce increasing, the other minor phase, CeO₂, was also detected in addition to the major ABO₃ perovskite phase. This is attributed to that Ce addition exceeds its solubility limit ($x \ge$ 0.1).^{45,46} Although no Co₃O₄ peaks were detected in the XRD



Fig. 2 XRD patterns of the $La_{1-x}Ce_xCoO_3$ perovskites (x = 0, 0.05, 0.10 and 0.15).⁴⁶

diffraction spectroscopy, Co₃O₄ is proposed to be separated from perovskite oxides accompanying with the separation of CeO₂ phase, which has been proved by previous literatures.^{43,45,47} According to Erdenee's study on samples with x =0.2 and 0.4,43 the structure of LaCoO₃ transforms from rhombohedral to cubic and peaks corresponding to Co₃O₄ and CeO₂ were visible. The severe lattice distortion perhaps leads to form more oxygen vacancies.42 Table 1 lists the values of specific surface area (ssa) of La_{1-x}Ce_xCoO₃ perovskites. It is observed that the increment of the ssa values of the obtained perovskites follows the sequence: LaCoO₃ (ssa = 8.9 m² g⁻¹) < La_{0.7}Ce_{0.3}- CoO_3 (ssa = 9.8 m² g⁻¹) < La_{0.6}Ce_{0.4}CoO₃ (ssa = 10.8 m² g⁻¹) < $La_{0.8}Ce_{0.2}CoO_3$ (ssa = 11.0 m² g⁻¹) < $La_{0.95}Ce_{0.05}CoO_3$ (ssa = $11.4 \text{ m}^2 \text{ g}^{-1}$ < La_{0.9}Ce_{0.1}CoO₃ (ssa = 12.6 m² g⁻¹). So we reach the conclusion that substituted samples have a larger ssa values than pure perovskites and the enhancement was not linear with substitution concentration. When Ce addition was below its solubility limit ($x \le 0.1$), it was noticed that the value of ssa significantly increase as pore volume was enlarged. However, with the increased proportion of Ce, their ssa decrease, which might be related to that the CeO₂ was segregated out and filled in the pores of the perovskite.46

In addition to above-mentioned physical structures, the effect of Ce substitution on redox properties have also been discussed in this paper. Firstly, it has been reported that partial substitution with Ce can affect the surface characteristics which are always more important than lattice. The surface characteristics obtained from X-ray photoelectron spectroscopy (XPS) has been observed in the reports of Erdenee *et al.*⁴³ and Wen *et al.*⁴⁵ In their work, no change of La valence state (La³⁺) was detected

Table 1 Brunauer–Emmett–Teller (BET) analysis results of $La_{1-x}Ce_x$ -CoO₃ perovskites calcined at 700 °C for 2 h⁴⁵

La _{1-x} Ce _x CoO ₃							
	x = 0	x = 0.05	<i>x</i> = 0.1	x = 0.2	<i>x</i> = 0.3	x = 0.4	
$SSA(m^2 g^{-1})$	8.9	11.4	12.6	11.0	9.8	10.8	

Table 2 The percentage of adsorption oxygen obtained from XPS⁴⁵

La ₁₋	$x Ce_x CoO_3$	3				
%	x = 0	x = 0.05	x = 0.1	x = 0.2	x = 0.3	x = 0.4
	46.6	42.2	43.5	48.4	39.8	38.3

when La was substituted with Ce. But they all agreed that the trivalent Co ion is partly changed. As has been reported by Wen et al.,⁴⁵ when the doping ratio was below 0.1, tetravalent Ce ions were fully dissolved into the perovskite structure so that electronic unbalance was generated. As a result, a part of Co³⁺ in the B-site became Co²⁺ or La³⁺ vacancies were created as a charge compensation mechanism.^{36,37} When x was larger than 0.1, the average oxidation state of the Co cation increased because the existence of CeO₂ might lead to deficiency of A-cation. Of course, they also showed XPS spectra of O 1s. According to ref. 43, 45 and 47, there are three different forms of oxygen including lattice oxygen (O_{latt}), adsorbed oxygen (O_{ads}), and surface adsorbed water species. Wen et al.45 found that the La_{0.8}Ce_{0.2}CoO₃ achieved the highest percentage of adsorption oxygen which participated in oxidation reactions. It is generally accepted that among Ce doped LaCoO₃ samples, La_{0.8}Ce_{0.2}CoO₃ shows the best activity.43,45 However, we cannot directly draw the conclusion that the improvement of catalytic activities are due to high amount of adsorbed oxygen, owing to the fact that although the perovskite LaCoO3 also gets high amount of adsorbed oxygen (Table 2), its activity is low. Additionally, it was proved that Ce ions were present in the trivalent and tetravalent form.^{43,46,47} The relative concentration of Ce³⁺, defined as Ce³⁺/ $(Ce^{3+} + Ce^{4+})$, was listed in Table 3. It varied from 19.2% to 21.0%, indicating that Ce^{4+} was dominant in all the samples. Secondly, a result of temperature programmed reduction of H₂ (H₂-TPR) experiment investigating effect of Ce addition on the redox ability of LaCoO₃ is shown in Fig. 3. The literature⁴⁶ also displayed the H₂-TPR profiles of $La_{1-x}Ce_xCoO_3$ in which two obvious reduction peaks were observed, which could be attributed to the reduction of Co³⁺ to Co²⁺ and Co²⁺ to Co⁰, respectively. As was seen from Fig. 3, two reduction peaks respectively located at about 400 °C and 600 °C. When a certain amount of Ce was introduced into the LaCoO₃ perovskite structure, the two peaks moved forward to lower temperature direction correspondingly, indicating that Ce⁴⁺ insertion increased the catalyst reducibility. In other word, Ce-doped catalysts showed a better reducibility as the reduction temperatures of these catalysts were lower than pure LaCoO3. And the sample with La1-xCex- CoO_3 (x = 0.2) leads to the highest decrease in the reduction peak temperatures. This may be because (1) it creates an easier

Table 3 The relative concentration of Ce^{3+} of $La_{1-x}Ce_{x}CoO_{3}$ catalysts^47

 $La_{1-x}Ce_xCoO_3$

	x = 0	x = 0.05	x = 0.1	x = 0.3	x = 0.5
$Ce^{3+}/(Ce^{3+}+Ce^{4+})$ (%)		20.6	21.0	20.3	19.2

reducibility of the Co^{3+} into Co^{2+} and, (2) Ce^{4+} increases the number of cation vacancies within the lattice.

According to Wen's paper,⁴⁵ the La_{1-x}Ce_xCoO₃ samples synthesized through a citrate show the highest conversion (80%) at about 300 °C in a flow of NO + O₂ + He when *x* was 0.2. However, the catalytic activities decreased at higher *x* values. They thought that these factors including the presence of CeO₂ and the decrease of adsorbed oxygen amount caused the decrease of activity. Combined with his results of XRD, when *x* > 0.1, the peaks of CeO₂ were observed. This means that small CeO₂ appeared in the mixed-oxide. Thus, it is concluded that the existence of small CeO₂ nano-particles is beneficial to the improvement of catalytic activities, but catalytic activities decreased because larger particles are formed at higher Ce content.

3.2 Ce doped LaFeO₃

Like $La_{1-x}Ce_xCoO_3$ samples, a series of $La_{1-x}Ce_xFeO_3$ perovskite-type oxide catalysts are also characterized by XRD, BET, XPS and TPR to illustrate the influence of Ce substitution. In these literatures,^{49–51} it is found that the substitution of La by Ce can increase the value of ssa and change the reducibility of Fe cation and Fe⁴⁺/Fe³⁺ ratios. The influence of Ce substitution on LaFeO₃ is very similar to that on LaCoO₃. Therefore, changes in its physicochemical properties are not explained in this part, but effect of catalytic performances is paid more attention here.

Giannakas *et al.*⁵⁰ investigated and compared the catalytic performance of LaFeO₃, La_{0.85}Sr_{0.15}FeO₃, La_{0.8}Sr_{0.1}Ce_{0.1}FeO₃ and La_{0.8}Ce_{0.2}FeO₃ which were prepared *via* a reverse micelles microemulsion route for NO reduction by CO, finding that the full sequence of catalytic activity of tested solids is La_{0.8}Ce_{0.2}-FeO₃ > La_{0.8}Sr_{0.1}Ce_{0.1}FeO₃ > La_{0.85}Sr_{0.15}FeO₃ \geq LaFeO₃. They pointed that (1) the above sequence is in accordance with the sequence of increment of ssa of the solids and, (2) La_{0.8}Ce_{0.2}-FeO₃ and La_{0.8}Sr_{0.1}Ce_{0.1}FeO₃ show much higher catalytic activity than the solids containing no Ce, which may be caused by the presence of CeO₂ phase in these two solids. Qin *et al.*⁵¹ also reported that catalytic reaction of La_{1-x}Ce_xFeO₃ for NO



Fig. 3 H₂-TPR profiles of the La_{1-x}Ce_xCoO₃ ($0 \le x \le 0.4$) catalysts.⁴³

reduction with CO and illustrated the influence of Ce substitution on SO₂ resistance. It was found that although LaFeO₃ exhibited an excellent catalytic performance without SO₂ (100% NO conversion at 500 °C), catalytic reaction decreased drastically when SO₂ gas was added to the CO + NO system(conversion rate decreased to 40–50% after approximately 100 min). Doping a certain amount of Ce into the LaFeO₃ perovskite structure could obviously improve the SO₂ resistance. For example, La_{0.6}Ce_{0.4}FeO₃ sample maintained a conversion rate of 80% during the latter 270 min after addition of SO₂ gas into the CO + NO reaction system. The reason was suggested to be the addition of Ce⁴⁺ which could prevent the adverse effect of SO₂ on the LaFeO₃ perovskite by absorbing SO₂ and forming Ce(SO₄)₂. Thus, the presence of Ce⁴⁺ is the key factor to the improvement of SO₂ resistance in LaFeO₃ perovskite catalysts.

Recently, attapulgite (ATP) was considered as support for $La_{1-x}Ce_xFeO_3$ catalysts, not only because of its inexpensive but also for its adsorption of many pollutants. A recent research⁵² on $La_{1-x}Ce_xFeO_3/ATP$ was conducted for testing its photocatalytic reduction of NO at low temperature. Following investigation on photo-SCR activity and stability of $La_{1-x}Ce_xFeO_3/ATP$ samples (Fig. 4) proves that the substitution of Ce is helpful for the improvement of catalytic performance. It is noteworthy that the conversion rate of NO reaches close to 80% when Ce doping amount is 0.3 at room temperature. Combined with XRD results, CeO₂ is precipitated from the solid solution when the Ce doping ratio is 0.3. This implies that the existence of CeO₂ is no harm for NO_x reduction.

Besides the NO removal, $La_{1-x}Ce_xFeO_3$ was also considered as promising catalyst in some reactions. For example, Xiang *et al.*⁴⁹ reported that the temperature of CH₄ conversion at 90% was as low as 510 °C when x = 0.3. According to Ma's report,⁵³ in the case of x = 0.5, the conversion of CO is about 68% at 530 °C.

3.3 Ce doped LaMnO₃

As mentioned earlier, we have systematically studied the effect of Ce in $La_{1-x}Ce_xCoO_3$ and $La_{1-x}Ce_xFeO_3$ perovskites.



Fig. 4 Photo-SCR denitrification activity and stability of $La_{1-x}Ce_x$ -FeO₃/ATP (x = 0.1-0.5).⁵²

Therefore, the properties of $La_{1-x}Ce_xMnO_3$ are not discussed here, because the influences of Ce in $La_{1-x}Ce_xMnO_3$ are similar to that in former two perovskites except that segregation of CeO₂ is not accompanied by segregation of some manganese oxide according to cases.^{43,54–56} This may be ascribed to that manganese oxide can be dissolved in the segregated CeO₂.⁵⁴ In this part, the simultaneous substitution of Ce at the A-site and other ions (B') at the B-site in a LaMnO₃ lattice will be made concentrates mainly.

For $La_{1-x}Ce_xMn_{1-y}B'_yO_3$ catalysts, the effect of the substitution of La by Ce in these catalysts is more complex than that in $La_{1-x}Ce_{x}MnO_{3}$ since the Ce cation not only changes the reducibility of Mn cation ($Mn^{3+} \leftrightarrow Mn^{4+}$), but also may affect the oxidation state of the B' cation. In the case of $La_{1-x}Ce_xMn_{1-y}B'_yO_3$, the redox couple can be Ce^{4+}/Ce^{3+} , $Mn^{4+}/$ Mn^{3+} and $B'^{n+}/B'^{(n-1)+}$ since oxidation state of B' cation may be variable. According to He's paper,⁵⁷ the reaction ($Ce^{3+} + Cu^{2+} \rightarrow$ $Ce^{4+} + Cu^{+}$ taken place during the preparation process of the $La_{0.8}Ce_{0.2}Mn_{0.6}Cu_{0.4}O_3$ catalysts. The presence of Cu⁺ and its redox equilibrium ($Cu^+ \leftrightarrow Cu^{2+}$) would facilitate the NO adsorption and reduction by CO. Similarly, Tarjomannejad et al.58 studied the LaMn_{1-x}Fe_xO₃ and La_{0.8}Ce_{0.2}Mn_{0.3}Fe_{0.7}O₃ perovskites catalysts, finding that the substitution of La³⁺ by Ce^{4+} result in decrease of Mn^{4+}/Mn^{3+} and Fe^{4+}/Fe^{3+} ratios. Of course, the substituted samples can also lead to the formation of oxygen vacancies and the increase of Oads/Olatt ratio. An integration of all these factors resulted in the enhancement of catalytic activity (90% NO conversion at 323 °C). In addition, if the B' cation exists in a permanent valence state, Ce^{4+}/Ce^{3+} and Mn⁴⁺/Mn³⁺ are the redox couples. The role of Ce is just to adjust the valence state of Mn cation or/and the ratio of $O_{\rm ads}/O_{\rm latt}$ However, the catalytic performance of $La_{1-x}Ce_xMn_{1-y}B'_yO_3$ samples have no relation to whether the valence state is varied or not. Sometimes the B' cation with a varied valence state can promote the catalytic reaction,57,58 sometimes inhibit. In the literature,⁵⁹ the substitution of Mn by Co in La_{0.8}Ce_{0.2}MnO₃ catalysts results in decreasing catalyst activity.

Besides, it has been reported that preparation methods interfere with the generation of CeO_2 phase. In the paper,⁵⁷ a considerable amount of CeO_2 was found by XRD in the $La_{0.8}Ce_{0.2}Cu_{0.4}Mn_{0.6}O_3$ and $La_{0.8}Ce_{0.2}Ag_{0.4}Mn_{0.6}O_3$ samples synthesized by sol–gel method, but not in samples synthesized by the reverse microemulsion method.

4. CeO₂ as the support

Aiming at resolving the problem that powder perovskites have much lower surface area, the scheme that perovskites are dispersed on thermally stable supports has been adopted and is being put into operation. Presently, perovskites are often supported on Al₂O₃, CeO₂, attapulgite and other supports.⁶⁰⁻⁶⁴ Among a variety of support materials, CeO₂ is one of the most popular supports because of its particular redox property. These supported perovskite oxides are usually prepared by impregnation methods and their performances depend closely on the support. In the paper,⁶⁵ Zhang *et al.* investigated and compared the catalytic performance of LaMnO₃/CeO₂ and LaMnO₃/TiO₂ for the SCR of NO by NH_3 in the presence of O_2 , finding that the former showed higher activity than the latter. The reason was suggested to be the difference of support. The phenomenon that TiO_2 supporting led to a remarkable decrease in redox capacity, contrasting with the pure LaMnO₃, has been also reported by Zhang *et al.*⁶⁵ Thus, the conclusion that the catalytic performance of all supported samples can be higher than that of ABO₃ perovskite alone is wrong.

Another factor for catalytic performance of supported samples is preparation method. H₂-TPR experiment has been done to investigate the structure and reducibility of the catalysts prepared by two methods.66 The result shown in Fig. 5 indicated that preparation method had relation to the amount of H₂ consumed, and it was suggested that LaMnO₃/CeO₂ prepared by the dry impregnation (DI) method showed higher activity than that by the precipitation-deposition (PD) method. In order to find the reason, the catalysts were characterized by XRD, BET and EXAFS. In the result of XRD, the peaks corresponding to the perovskite were detected for LaMnO₃/CeO₂-PD catalysts but hardly detected for the LaMnO₃/CeO₂-DI catalysts, indicating that LaMnO₃ perovskite phases were highly dispersed on the CeO₂ support. The BET surface areas of LaMnO₃/CeO₂-DI (46 m² g^{-1}) was lower than that of LaMnO₃/CeO₂-PD (68 m² g⁻¹). The formation of a perovskite oxide phase for the LaMnO₃/CeO₂ catalysts was confirmed by the EXAFS studies. Combined with the H₂-TPR study results, they propose that the higher activity may be ascribed to the strong interaction between the perovskite phase and the CeO₂ support although this catalyst has smaller surface area. Oppositely, Alifanti et al.67 concluded that there was no interaction between the support and the elements of the perovskite.

In addition, the morphology of CeO_2 has also a great influence on the catalytic activity, which has been studied by Wang *et al.*⁶⁸ It was found that the supported catalysts were more active than the unsupported catalyst ($\text{La}_{0.8}\text{Ce}_{0.2}\text{MnO}_3$) and $\text{La}_{0.8}\text{Ce}_{0.2}\text{MnO}_3$ /CeO₂ nanopolyhedra exhibited the higher catalytic activity than the other two morphologies of CeO₂



Fig. 5 H₂-TPR profiles of LaMnO₃/CeO₂ catalysts and LaMnO₃.⁶⁶

supported samples. The results described above are possible due to higher specific surface area and larger number of oxygen vacancies.

In summary, the modification method of perovskite oxides is effective for improving their catalytic activity, even though the promotion mechanism is still not clearly explained. Such a supported perovskite-type catalysts can have wide application prospects for the possibility of increasing its activity by simple preparation methods.

5. Conclusion

For Ce doped LaBO₃ (B = Co, Fe, Mn), all catalysts exhibit relatively larger specific surface areas compared with pure perovskites. The introduction of Ce changes the reducibility of B cations and $B^{n+}/B^{(n-1)+}$ ratios and these factors induce the generation of crystal lattice defects which lead to higher catalytic activities. This review outlined the relationship between the existence of CeO₂ phase and catalytic activity. When the Ce addition is below its solubility in perovskite structure ($x \le S$), Ce atoms can be totally incorporated in the perovskite lattice. Of course, Ce substitution at higher levels (x > S) can lead to the formation of separated CeO₂ phase. CeO₂ is either highly dispersed on the lattice surface or is found as larger particles. The former amorphous CeO₂ cannot be detected by XRD, while the latter can be done.41 What is more, it is found that Ce content of perovskite-type catalysts exhibiting the best activity exceeds its solubility in perovskites, indicating the presence of CeO₂. CeO₂, however, does not show good catalytic activity by itself.45,69 This means that the effect of separated CeO₂ on the catalytic performance is an indirect one, *i.e.*, by regulating the $B^{n+}/B^{(n-1)+}$ ratios and by forming B_yO_x phase. The interaction between different phases may also play a key role in improving catalytic activity to some extent. Nonetheless, it is found that as the content of doped Ce increasing, catalytic activity begins to decrease slightly. Thus, the CeO2 dispersing on lattice surface or small particles are beneficial for catalytic activity, but larger particles are adverse. As such, improving preparation methods to delay the generation and growth of CeO₂ phase may be effective for further improvement of activity. But beyond that, more researches still need to go further in order to improve the catalytic efficiency of NO transformation. For example, effective support materials which can dramatically promote the activity of Ce-doped LaBO3 catalysts still need to be studied. On the basis of Ce-doped LaBO₃, partial substitution of the A and/or B cations by cations on different oxidation states should also be attempted. Photocatalytic efficiency of $La_{0.7}Ce_{0.3}FeO_3/ATP$ that we mentioned previously can reach as high as 80% at room temperature. This make us get some great inspiration: in addition to improving catalysts, the reaction conditions must also be concerned.

For LaBO₃/CeO₂ catalysts, promotion mechanism is still not clearly explained. However, comparing with CeO₂ support or pure LaBO₃ perovskite catalyst, the catalytic activities of the majority of supported catalysts are enhanced. The simple preparation methods provide a feasible scheme for improvement of catalytic activity of LaBO₃ perovskites.

Conflicts of interest

Authors declare no conflict of interest.

Acknowledgements

This work was financially supported by Natural Science Foundation of Xinjiang, China, Grant No. 2016D01A073. This work was also financially supported by Recruitment Program of Global Experts, and the Director Foundation of XTIPC, CAS, Grant No. 2015RC011.

References

- 1 J. Li, S. Wang, L. Zhou, G. Luo and F. Wei, *Chem. Eng. J.*, 2014, 255, 126–133.
- 2 V. Ferrer, D. Finol, R. Solano, A. Moronta and M. Ramos, *J. Environ. Sci.*, 2015, 27, 87–96.
- 3 M. Li, V. G. Easterling and M. P. Harold, *Appl. Catal., B*, 2016, **184**, 364–380.
- 4 N. Imanaka and T. Masui, Appl. Catal., A, 2012, 431, 1-8.
- 5 A. Fritz and V. Pitchon, Appl. Catal., B, 1997, 13, 1-25.
- 6 S. Roy, M. S. Hegde and G. Madras, *Appl. Energy*, 2009, **86**, 2283–2297.
- 7 M. Iwamoto and H. Hamada, Catal. Today, 1991, 10, 57-71.
- 8 M. Iwamoto, H. Furukawa, Y. Mine, F. Uemura, S. Mikuriya and S. Kagawa, *J. Chem. Soc., Chem. Commun.*, 1986, 16, 1272–1273.
- 9 T. Selleri, F. Gramigni, I. Nova and E. Tronconi, *Appl. Catal.*, *B*, 2018, 225, 324–331.
- 10 R. Burch and M. D. Coleman, *Appl. Catal., B*, 1999, **23**, 115–121.
- 11 T. Chafik, D. I. Kondarides and X. E. Verykios, *J. Catal.*, 2000, **190**, 446–459.
- 12 Z. Wang, Z. Qu, X. Quan, Z. Li, H. Wang and R. Fan, *Appl. Catal.*, *B*, 2013, **134**, 153–166.
- 13 Z. Wang, Z. Qu, X. Quan and H. Wang, *Appl. Catal.*, A, 2012, 411, 131–138.
- 14 L. Chmielarz, P. Kustrowski, A. Rafalska-Lasocha and R. Dziembaj, *Appl. Catal.*, *B*, 2005, **58**, 235–244.
- 15 Q. Zhang, Y. Huang, S. Peng, Y. Zhang, Z. Shen, J. Cao, W. Ho, S. C. Lee and D. Y. H. Pui, *Appl. Catal., B*, 2017, 204, 346–357.
- 16 Y. Niu, T. Shang, S. Hui, X. Zhang, Y. Lei, Y. Lv and S. Wang, *Fuel*, 2016, **185**, 316–322.
- 17 C. Zhou, Z. Feng, Y. Zhang, L. Hu, R. Chen, B. Shan, H. Yin, W. G. Wang and A. Huang, *RSC Adv.*, 2015, 5, 28054–28059.
- 18 Z. Li, M. Meng, Q. Li, Y. Xie, T. Hu and J. Zhang, *Chem. Eng. J.*, 2010, **164**, 98–105.
- 19 X. Guo, M. Meng, F. Dai, Q. Li, Z. Zhang, Z. Jiang, S. Zhang and Y. Huang, *Appl. Catal.*, *B*, 2013, **142**, 278–289.
- 20 J. Chen, M. Shen, X. Wang, G. Qi, J. Wang and W. Li, *Appl. Catal.*, B, 2013, 134, 251–257.
- 21 J. Chen, M. Shen, X. Wang, J. Wang, Y. Su and Z. Zhao, *Catal. Commun.*, 2013, **37**, 105–108.
- 22 A. E. Giannakas, A. K. Ladavos and P. J. Pomonis, *Appl. Catal.*, *B*, 2004, **49**, 147–158.

This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

Dpen Access Article. Published on 27 March 2018. Downloaded on 7/31/2025 10:11:26 AM.

- 23 R. Q. Long and R. T. Yang, Appl. Catal., B, 2000, 27, 87-95.
- 24 A. Logan and M. Shelef, J. Mater. Res., 1994, 9, 468-475.
- 25 S. Keav, S. K. Matam, D. Ferri and A. Weidenkaff, *Catalysts*, 2014, **4**, 226–255.
- 26 A. Ashok, A. Kumar, R. R. Bhosale, F. Almomani, S. S. Malik, S. Suslov and F. Tarlochan, *J. Electroanal. Chem.*, 2018, 809, 22–30.
- 27 K.-Y. A. Lin, Y.-C. Chen and Y.-F. Lin, *Chem. Eng. Sci.*, 2017, 160, 96–105.
- 28 M. A. Pena and J. L. G. Fierro, Chem. Rev., 2001, 101, 1981– 2017.
- 29 V. M. Goldschmidt, Naturwissenschaften, 1926, 14, 477-485.
- 30 N. Labhasetwar, G. Saravanan, S. K. Megarajan, N. Manwar, R. Khobragade, P. Doggali and F. Grasset, *Sci. Technol. Adv. Mater.*, 2015, 16, 036002.
- 31 S. Ponce, M. A. Pena and J. L. G. Fierro, *Appl. Catal., B*, 2000, 24, 193–205.
- 32 R. Leanza, I. Rossetti, L. Fabbrini, C. Oliva and L. Forni, *Appl. Catal., B*, 2000, **28**, 55–64.
- 33 G. Saracco, F. Geobaldo and G. Baldi, *Appl. Catal., B*, 1999, **20**, 277–288.
- 34 B. Zhao, R. Ran, L. Sun, Z. Yang, X. Wu and D. Weng, *Catal. Commun.*, 2018, **105**, 26–30.
- 35 Z. Guguchia, T. Adachi, Z. Shermadini, T. Ohgi, J. Chang, E. S. Bozin, F. von Rohr, A. M. dos Santos, J. J. Molaison, R. Boehler, Y. Koike, A. R. Wieteska, B. A. Frandsen, E. Morenzoni, A. Amato, S. J. L. Billinge, Y. J. Uemura and R. Khasanov, *Phys. Rev. B*, 2017, **96**, 094515.
- 36 S. Khan, R. J. Oldman, C. R. A. Catlow, S. A. French and S. A. Axon, J. Phys. Chem. C, 2008, 112, 12310–12320.
- 37 S. A. French, C. R. A. Catlow, R. J. Oldman, S. C. Rogers and S. A. Axon, *Chem. Commun.*, 2002, 2706–2707.
- 38 K. Huang, H. Y. Lee and J. B. Goodenough, J. Electrochem. Soc., 1998, 145, 3220–3227.
- 39 B. Tofield and W. Scott, J. Solid State Chem., 1974, 10, 183– 194.
- 40 J. Topfer and J. B. Goodenough, *J. Solid State Chem.*, 1997, **130**, 117–128.
- 41 V. MathieuDeremince, J. B. Nagy and J. J. Verbist, Catalysis and Automotive Pollution Control III, *Stud. Surf. Sci. Catal*, 1995, **96**, 393–404.
- 42 R. Zhang, N. Luo, B. Chen and S. Kaliaguine, *Energy Fuels*, 2010, 24, 3719–3726.
- 43 N. Erdenee, U. Enkhnaran, S. Galsan and A. Pagvajav, J. Nanomater., 2017, 9120586.
- 44 L. Forni, C. Oliva, F. P. Vatti, M. A. Kandala, A. M. Ezerets and A. V. Vishniakov, *Appl. Catal., B*, 1996, 7, 269–284.
- 45 Y. Wen, C. Zhang, H. He, Y. Yu and Y. Teraoka, *Catal. Today*, 2007, **126**, 400–405.

- 46 J. Zhu, Y. Zhao, D. Tang, Z. Zhao and S. A. C. Carabineiro, *J. Catal.*, 2016, **340**, 41–48.
- 47 X. Zhu, S. Zhang, Y. Yang, C. Zheng, J. Zhou, X. Gao and X. Tu, *Appl. Catal.*, *B*, 2017, **213**, 97–105.
- 48 M. Ghasdi, H. Alamdari, S. Royer and A. Adnot, *Sens. Actuators, B*, 2011, **156**, 147–155.
- 49 X.-P. Xiang, L.-H. Zhao, B.-T. Teng, J.-J. Lang, X. Hu, T. Li, Y.-A. Fang, M.-F. Luo and J.-J. Lin, *Appl. Surf. Sci.*, 2013, 276, 328–332.
- 50 A. E. Giannakas, A. A. Leontiou, A. K. Ladavos and P. J. Pomonis, *Appl. Catal., A*, 2006, **309**, 254–262.
- 51 Y. Qin, L. Sun, D. Zhang and L. Huang, *Catal. Commun.*, 2016, **79**, 53–57.
- 52 H. Zhang, X. Li, Y. Hui, L. Yu, Q. Xia, S. Luo and C. Yao, J. Mater. Sci.: Mater. Electron., 2017, 28, 9371–9377.
- 53 H. Q. Ma, H. M. Zhu, X. Tan, J. Y. Zhang and L. Chang, *J. Rare Earths*, 2004, 22, 357–360.
- 54 M. Alifanti, J. Kirchnerova and B. Delmon, *Appl. Catal., A*, 2003, **245**, 231–243.
- 55 B. He, Q. Song, Q. Yao, Z. Meng and C. Chen, *Korean J. Chem. Eng.*, 2007, 24, 503–507.
- 56 T. Nitadori, S. Kurihara and M. Misono, *J. Catal.*, 1986, **98**, 221–228.
- 57 H. He, M. Liu, H. Dai, W. Qiu and X. Zi, *Catal. Today*, 2007, 126, 290–295.
- 58 A. Tarjomannejad, A. Farzi, M. J. I. Gomez, A. Niaei, D. Salari and V. Albaladejo-Fuentes, *Catal. Lett.*, 2016, 146, 2330– 2340.
- 59 S. Wu, C. Song, F. Bin, G. Lv, J. Song and C. Gong, *Mater. Chem. Phys.*, 2014, **148**, 181–189.
- 60 A. Di Benedetto, G. Landi, V. Di Sarli, P. S. Barbato, R. Pirone and G. Russo, *Catal. Today*, 2012, **197**, 206–213.
- 61 R. You, Y. Zhang, D. Liu, M. Meng, Z. Jiang, S. Zhang and Y. Huang, *Chem. Eng. J.*, 2015, **260**, 357–367.
- 62 C. Orak, S. Atalay and G. Ersoz, *Sep. Sci. Technol.*, 2017, **52**, 1310–1320.
- 63 X. Li, Y. Yin, C. Yao, S. Zuo, X. Lu, S. Luo and C. Ni, *Particuology*, 2016, **26**, 66–72.
- 64 X. Yin, L. Hong and Z. L. Liu, J. Membr. Sci., 2006, 268, 2-12.
- 65 R. Zhang, W. Yang, N. Luo, P. Li, Z. Lei and B. Chen, *Appl. Catal.*, *B*, 2014, **146**, 94–104.
- 66 H. Einaga, W. Yoshida, C. Lee and K. Kusaba, *Catal. Lett.*, 2016, **146**, 2495–2503.
- 67 M. Alifanti, M. Florea and V. I. Parvulescu, *Appl. Catal., B*, 2007, **70**, 400–405.
- 68 Y. Wang, Y. Xue, C. Zhao, D. Zhao, F. Liu, K. Wang and D. D. Dionysiou, *Chem. Eng. J.*, 2016, **300**, 300–305.
- 69 M. Alifanti, J. Kirchnerova and B. Delmon, *Appl. Catal., A*, 2003, **245**, 231–244.