RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2018, 8, 11693

Effect of pretreatment atmosphere of WO_x/SiO_2 catalysts on metathesis of ethylene and 2-butene to propylene

Krittidech Gayapan, Sirada Sripinun, Joongjai Panpranot, D Piyasan Praserthdam and Suttichai Assabumrungrat *

The effect of a gas pretreatment atmosphere (pure N₂, pure H₂ and mixed H₂/N₂) on the metathesis reaction between ethylene and 2-butene to propylene over calcined and non-calcined WO₃/SiO₂ catalysts was investigated. The non-calcined catalysts exhibited higher activity than the calcined catalysts under different gas pretreatment atmospheres. The non-calcined catalyst with the use of pure H₂ pretreatment showed the highest catalytic performances. As revealed by various characterization results from N₂ physisorption, XRD, XPS, TEM, SEM-EDX, UV-Vis, Raman, H₂-TPR, and NH₃-TPD techniques, the WO_{2.83} phase occurring from the H₂ pretreatment of the non-calcined catalyst played an important role on the high activity of the catalyst. In addition, better tungsten dispersion, higher isolated surface tetrahedral tungsten oxide species, and W⁵⁺ species were obtained on the H₂-treated non-calcined WO₃/SiO₂ catalyst.

Received 4th February 2018 Accepted 19th March 2018

DOI: 10.1039/c8ra01093e

rsc.li/rsc-advances

1. Introduction

Light olefins have played an important role in the petrochemical industry. In the past, the most important raw material in the petrochemical industry was ethylene and the second one was propylene.1 However, nowadays propylene demand has increased since it is used for production of organic chemicals such as polypropylene, acrylonitrile, propylene oxide, alcohol and acrylic acid.² Propylene production can be obtained from several processes such as catalytic and thermal crackers,³ methanol to olefins,⁴ propane dehydrogenation⁵ and olefin metathesis.6 At present, the metathesis of light olefins has become of particular interest because it could regulate the stocks of light olefins (ethylene, propylene, and butene) upon the market demand at low energy and environmental cost.⁷ Supported tungsten oxide catalysts (especially, WO₃/SiO₂) are the most widely used catalysts because of their better resistance to poisoning, lower price, better stability and easy regeneration.8 The metathesis of ethylene and 2-butene to propylene on WO₃/SiO₂ catalyst has been commercialized as the olefin conversion technology (OCT).² The reaction takes place in a fixed-bed reactor at a temperature > 553 K and pressure of 3.0-3.5 MPa. Since then, many studies have been carried out to develop WO₃/SiO₂ catalysts with improved performances. The mechanism of the metathesis reaction of ethylene and 2-butene

over WO₃/SiO₂ catalysts involves the formation of W–carbene species on the WO₃ surface, followed by metathesis on these active sites to propylene product.⁹ Many factors affect catalytic activity including the content of tungsten oxide loading,¹⁰ oxidation state of tungsten species,¹¹ conditions of preparation,^{12–14} properties of support,^{8,15} and pretreatment conditions.^{16,17} Experimental studies have reported that the tetrahedral tungsten oxide species are the active sites for metathesis^{2,18} and that WO₃ crystals are not active in metathesis and catalyst sites should be contained in the amorphous surface.¹⁹

In order to improve performance of supported WO_x/SiO₂ catalysts in metathesis reaction, the effect of pretreatment has been investigated. Conventional pretreatment in most studies involves high temperature calcination and inert gas purging.20,21 Choung and Weller²² showed that some intermediate nonstoichiometric tungsten oxide (WO_{3-x}) occurring from N₂ or H₂ gas pretreatments on WO₃/SiO₂ catalysts was the most active species for propylene self-metathesis. Westhoff and Moulijn²³ found that the slight reduction by H₂ over WO₃/SiO₂ catalysts exhibited activity in propylene self-metathesis better than calcined sample and the sample intermediate between WO3 and WO_{2.95} (formed by hydrogen treatment) exhibited the maximum activity. Zaki et al.24 reported that the formation of WO3 catalysts intermediates in the forms of WO_{2.96}, WO_{2.9}, and WO_{2.72} oxidation states could be adjusted by controlling the H2 reduction conditions. Liu et al.17 studied effect of gas pretreatments including N2, mixed H2/N2, H2 and air over the mixed catalysts between MgO and WO3/SiO2 catalysts on metathesis reaction of 1-butene and ethylene. The results showed that H₂

Center of Excellence in Catalysis and Catalytic Reaction Engineering, Department of Chemical Engineering, Faculty of Engineering, Chulalongkorn University, Bangkok 10330, Thailand. E-mail: suttichai.a@chula.ac.th; Fax: +66-2218-6877; Tel: +66-2218-6868

content for pretreatment caused the catalyst transformed to the tetragonal WO_3 and partially reduced $W_{2.92}$, which were active phases for the reaction.

From the previous studies mentioned above, all the researchers used the air-calcined catalysts for further pretreatment or experimental study. To the best of our knowledge, the effect of pretreatment atmosphere on the non-calcined catalysts has not been reported yet. In addition, most studies reported in the literatures performed the reaction tests under atmospheric pressure and high temperature around 723 K,10-14,25 while study on high pressure operation was scarce. In this research, the calcined and non-calcined WO3/SiO2 catalysts for metathesis of ethylene and 2-butene to propylene were studied by using the various gas pretreatments (pure N_2 , pure H_2 and mixed H_2/N_2). The catalytic activity was performed at the temperature of 623 K under low and high pressure conditions at 0.1 and 2.1 MPa. The properties of pretreated catalysts were characterized by the Brunauer-Emmett-Teller (BET) method of N₂ physisorption, Xray diffraction (XRD), X-ray photoelectron spectroscopy (XPS), transmission electron microscopy (TEM), scanning electron microscopy (SEM) together with energy dispersive X-ray (EDX) spectroscopy, diffuse reflectance ultraviolet-visible spectra (UV-Vis DRS), Raman microscopy, temperature-programmed reduction of hydrogen (H_2-TPR) and temperatureprogrammed desorption of ammonia (NH₃-TPD) to investigate the relationship of activity, crystallinity, dispersion and interaction of tungsten on the support, and acidity of the catalysts.

2. Experimental

2.1 Catalyst preparation

The 9 wt% WO_3/SiO_2 catalysts were prepared by wetness impregnation using an aqueous solution of ammonium metatungstate hydrate (Aldrich, 99.9%) over silica gel (Davisil Grade 646, 40–60 mesh, supplied by Aldrich). The impregnated sample was dried at room temperature for 2 h and subsequently in an oven at 383 K for 24 h. The catalysts were grouped into two types as the calcined and non-calcined catalysts before pretreatment and reaction testing. For calcined catalysts, the samples were calcined at temperature of 823 K in air for 8 h and then the catalysts were packed in a fixed bed reactor for further pretreatment and reaction. For non-calcined catalysts, the samples after drying were packed in a fixed bed reactor for further pretreatment and reaction.

2.2 Pretreatment atmosphere and catalytic evaluation

WO₃/SiO₂ catalyst of 3 g was packed at the center of the stainless steel tubular fixed-bed reactor (internal diameter = 19.05 mm). The catalyst was heated to 773 K by a furnace under N₂ gas at a flow rate of 30 ml min⁻¹ and held at 773 K for 1 h. After that, pretreatment gas (pure N₂, pure H₂ or mixed 1 : 1 H₂/N₂) at a total flow rate of 30 cm³ min⁻¹ was fed to the reactor for 1 h. The reactor was then cooled down to operating temperature of 623 K under N₂ gas at the same flow rate. The reaction was started by introducing a feed containing 4% 2-butene (2% *cis*-2-butene and 2% *trans*-2-butene) and 8% ethylene balanced in

nitrogen gas. The reaction condition was kept at 623 K with a WHSV of 0.52 h⁻¹. The operating pressure was varied at 0.1 and 2.1 MPa. The catalysts were denoted as W-cal-fresh and Wnoncal-fresh for calcined and non-calcined fresh catalysts, but catalysts with different gas pretreatments were denoted as Wcal-xxx and W-noncal-xxx represented the calcined and noncalcined catalyst where "xxx" represents the gas pretreatment including N₂, H₂ and H₂/N₂ for gas pretreatment with pure N₂, pure H₂ and mixed H₂/N₂, respectively.

The products from the reaction tests were analyzed by using an online gas chromatography (Agilent 7820A), which was equipped with a flame ionization detector (FID). The reaction pathways were illustrated in Scheme 1 in details.^{26,27} The main reaction was the metathesis of ethylene and 2-butene to produce propylene as the conventional reaction for propylene production in industrial plants and the side reactions included isomerization, cross-metathesis and self-metathesis reaction as shown in this scheme. The 2-butene conversion, product selectivity and yields were determined by the following equations:

2-Butene conversion = ((amount of *trans*- and *cis*-2-butene in feed – amount of *trans*- and *cis*-2-butene in products)/amount of *trans*- and *cis*-2-butene in feed) \times 100

Product selectivity = (amount of any product/amount of total product) \times 100

Product yield = (2-butene conversion \times product selectivity)/100

2.3 Catalyst characterization

XRD patterns of the catalysts were determined by using a D8 Advance of Bruker AXS using Ni-filter Cu K_{α} radiation in the 2θ range of 20° to 80°. For phase composition identification purposes, the diffraction patterns were matched with standard diffraction data files. The BET surface areas, pore volumes and pore sizes were obtained using Micromeritics Chemisorbs 2750 with nitrogen adsorption studies. The surface structures of tungsten oxide species were examined by Raman microscopy under ambient conditions using a Senterra Dispersive Raman Microscopy (Bruker Optics) equipped with the laser wavelength



Scheme 1 Reaction pathways of ethylene and 2-butene.

Paper

at 532 nm and a TE-cooled CCD detector. The UV-Vis DRS was used to investigate surface structure of tungsten oxide species. The catalyst samples were recorded on Lambda 650 spectrophotometer in the range between 200 and 800 nm. The XPS was carried out using an AMICUS photoelectron spectrometer equipped with an Mg K_{α} X-ray as a primary excitation and KRATOS VISION2 software. XPS elemental spectra were acquired with 0.1 eV energy step at a pass energy of 75 eV.

The TEM images were used to investigate the particle morphology and lattice spacing of the samples, which was conducted on a JEOL JEM-2010 microscope equipped with a LaB_6 electron gun in the voltage range of 200 kV. TEM samples were prepared by dispersing in ethanol by sonication and a few drops of suspension onto a carbon-coated copper grid followed by solvent evaporation in air at room temperature. The tungsten distribution over the silica support were investigated by SEM (Hitachi S3400N) equipped with EDX (EDAX Apollo-X).

 H_2 -TPR was performed to investigate the reducibility of catalysts by a Micromeritics Chemisorb 2750 automated system. The catalyst was loaded into a quartz U-tube reactor. Prior to H_2 -TPR experiment, the sample was pretreated under N_2 flow at 773 K for 1 h and then cooled to 313 K. Subsequently, the catalyst was reduced by using 10% H_2 /Ar with a flow rate of 25 ml min⁻¹ at a heating rate of 5 K min⁻¹ from 313 to 1173 K. The amount of hydrogen uptake was determined by measuring the areas of the reduction profiles on the thermal conductivity detector (TCD).

 $\rm NH_3$ -TPD was used to determine the acidity of catalysts by a Micromeritics Chemisorb 2750 automated system. The catalyst packed in a quartz U-tube reactor was pretreated with a He flow rate of 25 ml min⁻¹ at 773 K for 1 h and then cooled down to 313 K. After that, it was exposed to a 15% $\rm NH_3/He$ mixed gas with a flow rate of 25 ml min⁻¹ for 30 min. Subsequently, the sample was purged with a He gas stream (25 ml min⁻¹) for 1 h and the temperature was increased linearly with a rate of 5 K min⁻¹ to 773 K. The desorbed ammonia was detected by using the TCD.

3. Results and discussion

3.1 Catalytic performances of the calcined and non-calcined catalysts

The metathesis performance was measured for the calcined and non-calcined catalysts in metathesis of 2-butene (*trans-* and *cis-*)

and ethylene to produce propylene with different gas pretreatments. The reaction conditions were operated at 623 K, 0.52 h^{-1} of WHSV at two pressures (0.1 and 2.1 MPa) with the reactant of 2% cis-2-butene, 2% trans-2-butene and 8% ethylene in N2 balanced, and the reaction tests were terminated after 12 h. Table 1 shows the activity and product yields of the calcined and non-calcined catalysts with different gas pretreatment atmospheres for operation of 1 h. The 2-butene conversion at 0.1 MPa for the calcined catalysts with different gas pretreatments was around 12-23%, while those of the non-calcined catalysts were around 22-24%. For operation at 2.1 MPa, the 2-butene conversion for the calcined and non-calcined catalysts were around 24-26% and 48-69%, respectively. These results showed that the non-calcined catalysts exhibited the 2-butene conversion higher than the calcined catalysts. Considering the effect of gas pretreatment at pressure of 0.1 MPa, the increase of H₂ content in the gas pretreatment was likely to increase 2butene conversion in both calcined and non-calcined catalysts. At pressure of 2.1 MPa, the difference in 2-butene conversion with increasing H₂ content between the calcined and noncalcined catalysts was more pronounced. The pure H₂ pretreatment of the non-calcined catalyst exhibited the highest 2-butene conversion. Considering the product yields, when comparing the propylene and 1-butene yields, the non-calcined catalysts also exhibited the propylene yield higher than the calcined catalysts, while the 1-butene yield for the non-calcined catalysts was lower than the calcined catalysts at both pressures. In addition, when considering isobutene and C_5^+ yields, the non-calcined catalysts were higher than the calcined catalysts. Comparing among different gas pretreatments, the use of pure H_2 for pretreatment increased the propylene yield for both 0.1 and 2.1 MPa pressures, while the yields of side reaction products such as 1-butene, isobutene, and C_5^+ were slightly decreased, except for the pure N2 pretreatment of the calcined catalyst that the side product yields were lower than the others.

The 2-butene conversion and product yields at operation of 0.1 and 2.1 MPa as a function of time on stream for 12 h were presented in Fig. 1 and 2, respectively. For operation at 0.1 MPa as shown in Fig. 1, the 2-butene conversion was unchanged among the different gas pretreatments for both calcined and non-calcined catalysts and rather constant through 12 h time-on-stream, except the case of N_2 pretreatment of the calcined

Table 1 2-Butene conversion and product yields of the calcined and non-calcined WO_3/SiO_2 catalysts under different gas pretreatment atmospheres at pressure of 0.1 and 2.1 MPa^a

	2-Butene conversion (%)		Yield (%) at 0.1 MPa				Yield (%) at 2.1 MPa			
Catalysts	0.1 MPa	2.1 MPa	Propylene	1-Butene	Isobutene	$C_5^+ =$	Propylene	1-Butene	Isobutene	C_5^+ =
W-noncal-N ₂	22.3	48.4	0.71	21.1	0.32	0.18	35.3	7.41	1.55	4.05
W-noncal-H ₂ /N ₂	23.4	66.6	1.10	20.8	1.25	0.23	56.7	5.05	1.33	3.60
W-noncal-H ₂	23.7	68.8	1.31	20.8	1.38	0.18	59.3	5.05	1.02	3.46
W-cal-N ₂	12.4	24.6	0.32	11.8	0.09	0.18	8.10	15.4	0.42	0.70
W-cal-H ₂ /N ₂	22.7	45.3	0.31	21.4	0.79	0.15	33.2	8.14	1.18	2.71
W-cal-H ₂	22.8	46.2	0.40	21.3	0.95	0.18	34.8	7.82	1.02	2.58

^{*a*} Reaction conditions: T = 623 K; WHSV = 0.52 h⁻¹; time on stream = 1 h.

catalyst, it showed the lower 2-butene conversion than the other pretreatments. However, the 2-butene conversion of the noncalcined catalysts was better than the calcined samples. The propylene yields (see Fig. 1b) of the catalysts followed the order: W-noncal-H₂ > W-noncal-H₂/N₂ > W-noncal-N₂ > W-cal-H₂ > W $cal-H_2/N_2 > W-cal-N_2$, while the 1-butene yield (see Fig. 1c) indicated the opposite trend to that of the propylene yield. In addition, the C_5^+ yield (see Fig. 1d) was very low and insignificantly different for all the catalysts. Nevertheless, the propylene yield of the non-calcined catalysts decreased initially and became constant after 8 h, whereas 1-butene yield of the noncalcined catalyst was slightly constant. When operating at pressure of 2.1 MPa as shown in Fig. 2, the differences in 2butene conversion and product yields of the calcined and noncalcined catalysts were more pronounced. The non-calcined catalysts exhibited the activity of 2-butene conversion and propylene yield higher than the calcined samples, while the 1butene yield of the non-calcined catalysts was lower than the calcined catalyst and the C_5^+ yield of the non-calcined catalysts was higher than the calcined catalysts. Considering the effect of gas pretreatment, it was found that the results of 2.1 MPa were the same trend as the operation at 0.1 MPa. The increasing H₂ content for pretreatment exhibited the high 2-

butene conversion and propylene yield and caused the lower 1butene yield. Pure H₂ pretreatment of the non-calcined catalysts exhibited the best catalytic activity and performances for the metathesis of ethylene and 2-butene.

3.2 Characterization of the calcined and non-calcined catalysts

The study of pretreatment atmospheres of the WO_3/SiO_2 catalysts on metathesis reaction of ethylene and 2-butene showed that the non-calcined catalysts exhibited the activity and performance higher than the calcined catalysts and the pure H_2 pretreatment of the non-calcined catalyst exhibited the highest activity. Different gas pretreatments could lead to the changes of the dispersion of tungsten species, the interaction of the tungsten and support, the structure of surface tungsten compounds, and the partial oxidation state of the catalysts, which played an important role in activity of metathesis reaction. The calcined and non-calcined WO_3/SiO_2 catalysts pretreated under different gas atmospheres were characterized by BET, XRD, XPS, TEM, SEM-EDX, UV-Vis, Raman, H_2 -TPR and NH_3 -TPD techniques.

3.2.1 N_2 physisorption. The BET surface areas, pore volumes, and average pore sizes of fresh catalysts obtained from



Fig. 1 2-Butene conversion and product yields of the calcined (continuous lines) and non-calcined (dotted lines) WO₃/SiO₂ catalysts under different pressures and gas pretreatments at pressure of 0.1 MPa: (a) 2-butene conversion, (b) propylene yield, (c) 1-butene yield and (d) C_5^+ = yield (reaction condition: T = 623 K; WHSV = 0.52 h⁻¹).



Fig. 2 2-Butene conversion and product yields of the calcined (continuous lines) and non-calcined (dotted lines) WO₃/SiO₂ catalysts under different pressures and gas pretreatments at pressure of 2.1 MPa: (a) 2-butene conversion, (b) propylene yield, (c) 1-butene yield and (d) C_5^+ yield (reaction condition: T = 623 K; WHSV = 0.52 h⁻¹).

different gas pretreatments were analyzed and the results are shown in Table 2. It was found that the calcined and noncalcined catalysts showed no significant differences in the specific surface area, pore volume, and average pore size. In other words, the gas pretreatment did not affect the physical properties of the calcined and non-calcined catalysts.

3.2.2 X-ray diffraction (XRD). The XRD diffraction patterns of catalysts with different gas pretreatments are shown in Fig. 3. The as-prepared non-calcined WO₃/SiO₂ catalyst (W-noncalfresh) showed no obvious peaks corresponding to crystalline phase of WO₃, indicating that the W phase was well dispersed on the supports forming an amorphous phase.¹⁰ The fresh catalyst after calcination (W-cal-fresh) at 823 K for 8 h exhibited XRD patterns assigned to monoclinic WO₃. When the catalysts (calcined and non-calcined) were pretreated with different gases including pure N₂ (W-xxx-N₂), mixed H₂/N₂ (W-xxx-H₂/N₂), and pure H₂ (W-xxx-H₂), the diffraction peaks based on standard data reference in JCPDS showed different patterns. Pure N2 pretreatment for the calcined and non-calcined catalysts exhibited the same XRD patterns as monoclinic WO₃, but the patterns of the non-calcined catalysts exhibited a lower crystallinity than those of the calcined catalysts, indicating the

better dispersed tungsten species on the surface.²⁵ As shown in the activity results (Fig. 1 and 2), the N_2 pretreatment of the noncalcined catalyst exhibited higher activity than the calcined catalyst, indicating that less WO₃ crystallinity was active in metathesis.¹⁹ For the mixed H₂/N₂ and pure H₂, the noncalcined catalysts exhibited the patterns assigned to WO_{2.83} phase, while the calcined catalysts exhibited WO_{2.92} phase, occurring from the partial reduction of WO₃.¹⁷ The published

Table 2 BET surface areas, pore volumes and pore sizes of the calcined and non-calcined WO_3/SiO_2 catalysts for different gas pretreatment atmospheres

Catalysts	BET surface area $(m^2 g^{-1})$	Pore volume $(cm^3 g^{-1})$	Pore size (nm)	
W-noncal-fresh	288	1.01	9.51	
W-noncal-N ₂	296	1.02	9.50	
W-noncal-H ₂ /N ₂	303	1.03	9.39	
W-noncal-H ₂	298	1.03	9.45	
W-cal-fresh	285	0.97	9.41	
W-cal-N ₂	286	1.02	9.15	
W-cal- H_2/N_2	288	1.00	9.39	
W-cal-H ₂	287	1.04	9.21	



Fig. 3 XRD patterns of the calcined (colored continuous lines) and non-calcined (dotted lines) WO_3/SiO_2 catalysts with different gas pretreatments and standard data reference from JCPDS (black continuous lines).

literatures reported that the partial reduction or intermediate of tungsten oxide on support affected the metathesis activity. Westhoff et al.²³ proposed that the intermediate between WO₃ and WO_{2.95} was the active phase for metathesis reaction and Choung et al.²² showed some intermediate WO_{3-x} to be the most active for propylene metathesis, while Liu et al.17 indicated that the tetragonal WO₃ and partially reduced WO_{2 92} were the active phases for metathesis. In our results (Fig. 1 and 2), we found that H₂ pretreatment of the non-calcined catalyst exhibited higher activity than the calcined catalysts. Therefore, it could be proposed that WO2.83 crystalline phase of the catalysts played an important role on the active phase in the metathesis reaction of ethylene and 2-butene. When comparing between using mixed H₂/N₂ and pure H₂ pretreatment, the pure H₂ pretreatment exhibited the lower crystallinity than the mixed H₂/N₂ pretreatment. Therefore, the pure H₂ pretreatment offered the better dispersion of W species on the support and that of the non-calcined catalyst showed the best dispersion.

3.2.3 X-ray photoelectron spectroscopy (XPS). XPS measurements were used to determine the surface chemical state of tungsten on the surface of the calcined and noncalcined WO₃/SiO₂ catalysts obtained with various gas pretreatments and the results are shown in Fig. 4. The deconvoluted peaks were based on the full width at half-maximum (FWHM) of 1.4 eV, the binding energy difference between W $4f_{5/2}$ and W $4f_{7/2}$ of 2.1 eV, the peak intensity ratio of W $4f_{5/2}$ and W $4f_{7/2}~({\it I}(f_{7/2}):{\it I}(f_{5/2}))$ of 4:3, and the binding energy difference between W^{5+} $4f_{7/2}$ and W^{6+} $4f_{7/2}$ peak about 0.9-1.1 eV.28,29 The binding energies of 38.8 and 40.9 eV were assigned to W^{6+} $4f_{7/2}$ and W^{6+} $4f_{5/2}$, while the ones of 37.8 and 39.9 eV were assigned to W^{5+} $4f_{7/2}$ and W^{5+} $4f_{5/2}$. The fresh and pure N2 pretreatment of the calcined and non-calcined catalysts exhibited only W⁶⁺ phase, indicating WO₃ on the silica support. While the mixed H₂/N₂ and pure H₂ pretreatment exhibited W⁵⁺ and W^{6+} phases, indicating the WO_{3-x} on the silica support.³⁰ As shown in the figure, the XPS analysis for the mixed H₂/N₂ and



Fig. 4 XPS spectra of the calcined (a) and non-calcined (b) WO_3/SiO_2 catalysts with different gas pretreatments.

pure H_2 pretreatment confirmed that the W^{6^+} was converted to W^{5^+} and that the amount of the W^{5^+} oxidation state increased with increasing hydrogen in the gas pretreatment. Nevertheless, it was found that the mixed H_2/N_2 and pure H_2 pretreatment on the non-calcined catalysts exhibited the W^{5^+} peak higher than the calcined samples (see Table 2). Such results indicated the higher degree of W^{6^+} conversion to W^{5^+} state, which was consistent with the XRD results that showed $WO_{2.83}$ phase for the non-calcined catalyst and $WO_{2.92}$ phase for the calcined catalyst.

The surface compositions of the calcined and non-calcined WO_3/SiO_2 catalysts were determined by XPS and the results are shown in Table 3. All the catalysts showed insignificant changes of oxygen and carbon content on the catalyst surface whereas silica and tungsten compounds were different on the calcined and the non-calcined catalysts. Considering the ratios of W/(Si + W), which indicated the surface dispersion and concentration of tungsten on silica support,³¹ the non-calcined catalysts showed higher ratios of W/(Si + W) than those of the calcined samples. It is suggested that the W surface concentration on the non-calcined catalysts was higher than the calcined catalysts, which was consistent to the XRD results. There was little effect of the gas pretreatment atmosphere on

Table 3 Surface characterization by X-ray photoelectron spectroscopy (XPS) on the calcined and non-calcined WO_3/SiO_2 catalysts with different gas pretreatments

	Elements (at%)				***/			
Catalysts	0	C Si W		W	W/ (Si + W)	$W^{5^{+}}(\%)$	$W^{6^{+}}(\%)$	
W-noncal-fresh	78.1	4.66	10.6	6.57	0.38	0.00	100.0	
W-noncal-N ₂	78.5	4.57	11.1	5.83	0.35	0.00	100.0	
W-noncal-H ₂ /N ₂	78.5	3.48	11.5	6.53	0.36	54.7	45.3	
W-noncal-H ₂	79.0	3.91	11.2	5.89	0.35	56.6	43.4	
W-cal-fresh	79.1	3.62	11.7	5.56	0.32	0.00	100.0	
W-cal-N ₂	78.6	3.24	12.1	6.01	0.33	0.00	100.0	
W-cal-H ₂ /N ₂	79.2	2.46	12.1	6.23	0.34	45.0	55.0	
W-cal-H ₂	78.5	3.55	12.0	5.89	0.33	47.2	52.8	

the dispersion of W species for both inside the pores and on the outer surface of the catalysts.

3.2.4 Transmission electron microscopy (TEM). The particle morphology and lattice spacing of the samples were investigated by TEM and high resolution TEM images as shown in Fig. 5. It was found that the calcined catalysts showed more tungsten agglomerates dispersed on the surface of silica than the non-calcined catalysts, indicating poor tungsten dispersion of the calcined catalysts. Such results were consistent to the XRD and XPS results. Under different gas pretreatment atmospheres, pure H₂ pretreatment on the non-calcined catalyst showed the best dispersion of tungsten on the support. From the high resolution TEM images (inset figure), only one crystal lattice plane was observed. The lattice spacing of all the pretreated catalysts was approximately around 0.38 nm, except the fresh non-calcined catalyst, in which the lattice spacing was not found due to its amorphous structure. From the XRD standard data reference in JCPDS, the lattice spacing of the (020) planes of monoclinic WO₃, (010) planes of WO_{2.92} and (010) planes of WO_{2.83} were about 0.377, 0.382 and 0.379 nm, respectively. Therefore, the lattice spacing obtained from the high resolution TEM images was consistent with the XRD standard data.

3.2.5 Scanning electron microscopy with energy dispersive X-ray spectroscopy (SEM-EDX). The SEM and SEM-EDX were used to investigate the tungsten distribution over the surface of silica (Fig. 6). The SEM results revealed that the topology of catalysts was non-uniform with irregular shape. The non-calcined catalysts with gas pretreatment showed fewer agglomerates compared to the calcined catalysts. In addition, from the measurement of tungsten on the silica support by SEM-EDX, the non-calcined catalysts showed higher amount of

tungsten on the support. Therefore, tungsten dispersion of the non-calcined catalysts was higher than the calcined catalysts, consistent with the XRD, XPS, and TEM results. Under the different gas pretreatment atmospheres, pure H_2 pretreatment of the non-calcined catalyst offered the best tungsten dispersion on the support.

3.2.6 Diffuse reflectance ultraviolet-visible spectra (UV-Vis DRS). Structure of tungsten species produced by different gas pretreatments on the calcined and non-calcined catalysts were analyzed by UV-Vis DRS as shown in Fig. 7. Two absorption bands at 230 and 270 nm were observed in the spectra for all the catalysts, whereas the adsorption band at 400 nm was observed obviously for the fresh calcined catalyst and N2 pretreatment of both calcined and non-calcined catalysts. Nevertheless, the adsorption bands between 400 and 800 nm were observed for pure N_2 , pure H_2 and mixed $1: 1 H_2/N_2$ pretreatment for both calcined and non-calcined catalysts. According to the literature,^{10,32} the absorption bands at 230 nm could be assigned to isolated tetrahedral $[WO_4]^{2-}$ species, while the absorption bands at 270 nm corresponded to octahedral polytungstate species. The band at 400 nm was assigned to WO3 crystallites,10,33 whereas the adsorption bands between 400 and 800 nm could be assigned to W^{4+} and W^{5+} species.³² The adsorption bands at 230 and 270 nm were attributed to W⁶⁺ species.10,32 As shown in Fig. 7, the intensity of adsorption band at 230 nm for all the samples was not much different, except the fresh calcined catalyst in which the band intensity was lower than the others. However, the pure H_2 pretreatment of the noncalcined catalyst exhibited the highest intensity. For the adsorption band at 270 nm, the non-calcined catalysts exhibited the intensities higher than the calcined catalysts and the pure



Fig. 5 TEM images and high-resolution TEM image (inset) of the calcined (top) and non-calcined (bottom) WO_3/SiO_2 catalysts with different gas pretreatments; (a) W-cal-fresh, (b) W-noncal-fresh, (c) W-cal-N₂, (d) W-noncal-N₂, (e) W-cal-H₂/N₂, (f) W-noncal-H₂/N₂, (g) W-cal-H₂ and (h) W-noncal-H₂.



Fig. 6 SEM and SEM-EDX images of the calcined (left) and non-calcined (right) WO_3/SiO_2 catalysts with different gas pretreatments; (a) W-cal-fresh, (b) W-noncal-fresh, (c) W-cal-N₂, (d) W-noncal-N₂, (e) W-cal-H₂/N₂, (f) W-noncal-H₂/N₂, (g) W-cal-H₂ and (h) W-noncal-H₂.

H₂ pretreatment of the non-calcined catalyst showed the highest band intensity. Intensity of the band at 400 nm was obviously observed for the fresh calcined catalyst and N2 pretreatment of the calcined and non-calcined catalysts. The calcined samples showed more obvious peaks than the noncalcined catalysts, indicating a poor dispersion on silica,10 which was consistent with the XRD and XPS results. When pretreating with H_2 (mixed H_2/N_2 and pure H_2), the adsorption band at 400 nm was converted to adsorption bands between 400 and 800 nm. In other words, the crystalline WO₃ was reduced by gas pretreatment, which was consistent with the XRD and XPS results. Comparing the cases of mixed H₂/N₂ and pure H₂ pretreatment for the calcined and non-calcined samples showed that the bands between 400 and 800 nm of the noncalcined catalysts were broader than the calcined catalysts, which were ascribed to ordered mesoporous structure and enlarged oxygen vacancies due to higher W5+ in substoichiometric WO_{3-x} .³⁰

3.2.7 Raman spectroscopy. The Raman spectroscopy results showing the structure of tungsten species present on the

supported catalysts are shown in Fig. 8. The bands at 263-275, 707–720 and 805–808 cm^{-1} were assigned to the deformation mode of W-O-W, bending mode of W-O, and symmetric stretching mode of W-O, respectively.15,31 The Raman band at 325-329 cm⁻¹ assigned to bending mode of O-W-O of surface WOx.8,10 The broad band at 970 cm⁻¹ was assigned to the O=W=O band of isolated surface tetrahedral tungsten oxide species.³¹ Fresh catalyst without calcination (W-noncal-fresh) showed the clear Raman band at 970 cm⁻¹ and a small broad peak at 807 cm⁻¹, indicating the signature bands of distorted WO₆ units.³⁴ While fresh catalyst with calcination (W-cal-fresh) and N₂ pretreatment on both calcined and non-calcined catalysts showed the four strongest peaks (263-275, 325-329, 707-720 and 805–808 cm⁻¹) of crystalline WO₃⁸ and a broad small peaks at 970 cm⁻¹. For the H₂ pretreatment, the Raman bands at 710 and 807 cm^{-1} became broader as the H_2 content increased. It is suggested that there was a gradual degradation of the crystallinity upon hydrogen treatment due to an increasing amount of oxygen vacancies in the form of WO_{3-x} phase.30 Comparing the cases of H2 pretreatment for the



Fig. 7 UV-Vis DRS patterns of the calcined (continuous lines) and non-calcined (dotted lines) WO_3/SiO_2 catalysts with different gas pretreatments; (a) W-cal-fresh, (b) W-noncal-fresh, (c) W-cal-N₂, (d) W-noncal-N₂, (e) W-cal-H₂/N₂, (f) W-noncal-H₂/N₂, (g) W-cal-H₂ and (h) W-noncal-H₂.



Fig. 8 Raman spectra of the calcined (continuous lines) and non-calcined (dotted lines) WO_3/SiO_2 catalysts with different gas pretreatments.

calcined and non-calcined catalysts, the Raman band at 970 cm^{-1} of non-calcined catalysts showed more obvious peaks than those of the calcined samples, indicating more isolated surface tetrahedral tungsten oxide species as also confirmed by the UV-Vis results. The ratios of relative Raman intensities of the peak at 970 to 807 cm^{-1} (I_{970}/I_{807}) are shown in Table 4 as an indicative of the relative amount of isolated surface tetrahedral tungsten oxide species (active site) to WO₃ crystal (non-active site).^{35,36} The pure H₂ pretreatment of the non-calcined catalysts studied. Based on the characterization results described above, we can conclude that the H₂ pretreatment (mixed H₂/N₂ and pure H₂) of the non-calcined catalysts exhibited higher oxygen

Table 4Integral of Raman band area at intensity of 807 and 970 cmand its relative intensities (I_{970}/I_{807}) on the calcined and non-calcinedWO3/SiO2 catalysts with different gas pretreatments

	Peak area of			
Catalysts	807 cm^{-1}	970 ${\rm cm}^{-1}$	I ₉₇₀ /I ₈₀₇ ratio	
W-noncal-fresh	1.73	25.5	14.8	
W-noncal-N ₂	69.2	4.27	0.06	
W-noncal-H ₂ /N ₂	84.1	5.69	0.07	
W-noncal-H ₂	31.5	3.60	0.11	
W-cal-fresh	34.6	0.89	0.03	
W-cal-N ₂	48.2	1.44	0.03	
W-cal-H ₂ /N ₂	49.0	2.40	0.05	
W-cal-H ₂	18.2	1.19	0.07	

vacancies to WO_{3-x} than the calcined ones and the pure H_2 pretreatment of the non-calcined catalyst showed the highest amount of isolated surface tetrahedral tungsten oxide.

3.2.8 Temperature-programmed desorption of ammonia (NH₃-TPD). The NH₃-TPD was performed to characterize the surface acidity of the catalysts. In Fig. 9, the ammonia desorption peaks of the non-calcined WO₃/SiO₂ catalysts occurred at higher temperature than the calcined catalysts, indicating the higher acid strength³¹ as stronger acidity. The amounts of NH₃ desorption decreased with changing gas pretreatment as follows; pure N₂ > mixed H₂/N₂ > pure H₂. In addition, the gas pretreatment caused the ammonia desorption peak to slightly shift to lower temperature, indicating the lower acid strength. This demonstrated that using the gas pretreatment could result in a lower amount of total acid and acid strength. The surface acidity as shown in Fig. 10 also confirmed clearly that gas pretreatment affected to the total acid amount and strength. It



Fig. 9 NH₃-TPD profiles of the calcined (continuous lines) and non-calcined (dotted lines) WO_3/SiO_2 catalysts with different gas pretreatments; (a) W-cal-fresh, (b) W-noncal-fresh, (c) W-cal-N₂, (d) W-noncal-N₂, (e) W-cal-H₂/N₂, (f) W-noncal-H₂/N₂, (g) W-cal-H₂ and (h) W-noncal-H₂.



Fig. 10 The total and strong acidity of the calcined and non-calcined WO_3/SiO_2 catalysts with different gas pretreatments.

appeared that the N_2 pretreatment exhibited both total acid amount and strong acid strength higher than the mixed H_2/N_2 and pure H_2 pretreatment for both calcined and non-calcined catalysts. In other words, H_2 content of gas pretreatment caused only a slight change of acid amount and strength.

3.2.9 Temperature-programmed reduction of hydrogen (H2-TPR). The interaction between W active species and silica support was determined by the H2-TPR technique. The H2-TPR results of the calcined and non-calcined WO₃/SiO₂ catalysts (Fig. 11) showed three peaks at 769-789, 1030-1062 and 1135-1170 K. The low temperature peak was attributed to the reduction of W species in octahedral coordination, and the two high temperature peaks were assigned to the reduction of the surface amorphous WO3 species.10,32 Comparing between the calcined and non-calcined WO₃/SiO₂ catalysts, the reduction peak at low temperature of the non-calcined catalysts appeared at higher temperature than the calcined ones, indicating that interaction of W species in octahedral coordination on silica support of the non-calcined catalysts (789 K) was stronger than the calcined catalysts (769 K). The two reduction peaks at high temperature of the non-calcined catalysts (1052 and 1135 K) appeared at lower temperature than the calcined catalysts (1062 and 1170 K), indicating that reduction of WO₃ crystal of the non-calcined catalysts was weaker than the calcined catalysts, which reflected an improved reducibility of dispersed species.10 Considering the effect of gas pretreatment, the pure H_2 pretreatment led to a boarder low temperature peak while the high temperature peaks of each type (calcined or non-calcined) catalysts were not different. Nevertheless, the H2 content of gas pretreatment was likely to shift the low H₂ consumption peaks to lower temperature. Liu et al.³⁷ mentioned that the strong acidity was partly responsible for the strong interaction between tungsten oxides and support. Therefore, these results were consistent with the NH₃-TPD results.



Fig. 11 $\rm H_2\text{-}TPR$ patterns of the calcined (continuous lines) and non-calcined (dotted lines) WO_3/SiO_2 catalysts with different gas pretreatments.

According to the characterization results, it was concluded that the non-calcined catalysts had better dispersion of tungsten on the silica support (as confirmed by the BET, XRD, XPS, TEM and SEM-EDX results) than the calcined catalysts. Many researchers mentioned that higher dispersion of tungsten on the support exhibited high activity of the metathesis reaction.14,25,35 Additionally, the UV-Vis and Raman results also indicated the higher amount of isolated tetrahedral tungsten oxide and octahedral polytungstate species which were active species for the metathesis reaction³² on the non-calcined catalysts than the calcined catalysts. The NH₃-TPD and H₂-TPR results also showed the higher degrees of metal-support of the non-calcined catalysts due probably to the strong acidity presented on the non-calcined ones.37 For the comparison of gas pretreatment atmospheres, the XRD patterns of H₂ content pretreatment atmosphere of the non-calcined catalysts revealed the formation of a WO_{2.83} phase, while those of the calcined catalysts revealed the WO2.92 phase. The results showed that the pure H₂ pretreatment of the non-calcined catalyst exhibited the highest activity and performance in metathesis of ethylene and 2-butene. Therefore, it could be proposed that WO_{2.83} crystalline phase of the catalysts played an important role on the active in the metathesis reaction of ethylene and 2-butene. Nevertheless, the XPS results of pure H₂ pretreatment of the noncalcined catalysts showed the highest amount of the W5+ content. Huang *et al.*³² proposed that $W^{(6-y)+}$ (0 < y < 1) was the highly active centers for supported tungsten catalysts. Therefore, the improvement of the activity for metathesis reaction of ethylene and 2-butene could be adjusted by the H₂ gas pretreatment atmosphere without the calcination with air. The concept of the summarized results is shown in Scheme 2. The catalytic performance of WO3/SiO2 catalysts could be developed without the calcination of air. The air calcination caused the stronger interaction of crystalline WO₃ phase on the support



Scheme 2 The summarized results of the non-calcined and air-calcined catalysts with ${\rm H_2}$ pretreatment.

and when reduced with H_2 pretreatment, it exhibited the low oxygen vacancies converting crystalline WO₃ to WO_{2.92} phase, which was less active for metathesis reaction. Whilst on the non-calcined catalysts with H_2 pretreatment led to higher oxygen vacancies converting amorphous WO₃ to WO_{2.83} phase. The higher oxygen vacancies could provide more active sites for metathesis reaction.

4. Conclusions

The effect of catalyst pretreatment atmosphere of the calcined and non-calcined WO₃/SiO₂ catalysts for metathesis reaction of ethylene and 2-butene to produce propylene was investigated. The gas pretreatment atmosphere consisted of pure N_2 , pure H_2 and mixed $1:1 H_2/N_2$. The catalytic activity tests were carried out at 2 pressure levels (0.1 and 2.1 MPa). At low pressure of 0.1 MPa, the gas pretreatment atmosphere for the calcined and non-calcined catalysts was not much different, while at high pressure of 2.1 MPa, the effect of pretreatment atmosphere of the non-calcined catalyst became more pronounced. The results showed that the non-calcined catalysts exhibited higher activity than the calcined catalysts. The NH₃-TPD and H₂-TPR results showed a stronger interaction of the catalysts and the support for the non-calcined catalysts than the calcined catalysts. Among different gas pretreatment atmospheres, pure H₂ pretreatment of the non-calcined catalyst exhibited the highest activity and performances. The pure H₂ pretreatment atmosphere of the non-calcined catalyst led to the phase change of tungsten species from WO₃ to WO_{2.83}, while that of the calcined catalyst converted the WO3 to WO2.92 phase, as supported by the XPS, UV-Vis and Raman results. In addition, the XPS, UV-Vis and Raman results showed that the pure H₂ pretreatment atmosphere of the non-calcined catalyst exhibited the high isolated surface tetrahedral tungsten oxide species and W⁵⁺ species. The WO_{2.83} phase of the catalysts played an important role on the high activity of the WO_x/SiO₂ catalyst in metathesis reaction.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors acknowledge the support from the Department of Chemical Engineering, Faculty of Engineering, Chulalongkorn University.

References

- 1 L. G. Wade, *Organic Chemistry*, Pearson Prentice Hall, 6th edn, 2006.
- 2 J. C. Mol, J. Mol. Catal. A: Chem., 2004, 213, 39-45.
- 3 J. Towfighi, A. Niaei, R. Karimzadeh and G. Saedi, *Korean J. Chem. Eng.*, 2006, 23, 8–16.
- 4 M. Stöcker, Microporous Mesoporous Mater., 1999, 29, 3-48.
- 5 F. Cavani, N. Ballarini and A. Cericola, *Catal. Today*, 2007, **127**, 113–131.
- 6 X. Li, W. Zhang, S. Liu, L. Xu, X. Han and X. Bao, J. Phys. Chem. C, 2008, 112, 5955–5960.
- 7 D. P. Debecker, M. Stoyanova, U. Rodemerck and E. M. Gaigneaux, *J. Mol. Catal. A: Chem.*, 2011, **340**, 65–76.
- 8 A. Spamer, T. I. Dube, D. J. Moodley, C. van Schalkwyk and J. M. Botha, *Appl. Catal., A*, 2003, **255**, 153–167.
- 9 P. Jean-Louis Hérisson and Y. Chauvin, *Die Makromolekulare Chemie*, 1971, **141**, 161–176.
- 10 Q. Zhao, S.-L. Chen, J. Gao and C. Xu, *Transition Met. Chem.*, 2009, **34**, 621–627.
- 11 A. G. Basrur, S. R. Patwardhan and S. N. Was, *J. Catal.*, 1991, 127, 86–95.
- 12 S. Chaemchuen, S. Phatanasri, F. Verpoort, N. Sae-ma and K. Suriye, *Kinet. Catal.*, 2012, **53**, 247–252.
- 13 H. Liu, S. Huang, L. Zhang, S. Liu, W. Xin and L. Xu, *Catal. Commun.*, 2009, **10**, 544–548.
- 14 N. Poovarawan, K. Suriye, J. Panpranot, W. Limsangkass, F. J. Santos Cadete Aires and P. Praserthdam, *Catal. Lett.*, 2015, 145, 1868–1875.
- 15 Y. Wang, Q. Chen, W. Yang, Z. Xie, W. Xu and D. Huang, *Appl. Catal.*, *A*, 2003, **250**, 25–37.
- 16 S. K. Gangwal, J. Fathi-kalajahi and G. B. Wills, *Prod. R&D*, 1977, 16, 237–241.
- 17 H. Liu, K. Tao, H. Yu, C. Zhou, Z. Ma, D. Mao and S. Zhou, *C. R. Chim.*, 2015, 18, 644–653.
- 18 A. J. Van Roosmalen and J. C. Mol, J. Catal., 1982, 78, 17-23.
- 19 S. Huang, F. Chen, S. Liu, Q. Zhu, X. Zhu, W. Xin, Z. Feng, C. Li, Q. Wang and L. Xu, *J. Mol. Catal. A: Chem.*, 2007, 267, 224–233.
- 20 K. Ding, A. Gulec, A. M. Johnson, T. L. Drake, W. Wu, Y. Lin,
 E. Weitz, L. D. Marks and P. C. Stair, *ACS Catal.*, 2016, 6, 5740–5746.
- 21 S. Lwin and I. E. Wachs, ACS Catal., 2014, 4, 2505-2520.
- 22 S. J. Choung and S. W. Weller, *Ind. Eng. Chem. Process Des. Dev.*, 1983, **22**, 662–665.
- 23 R. Westhoff and J. A. Moulijn, J. Catal., 1977, 46, 414-416.
- 24 M. I. Zaki, N. E. Fouad, S. A. A. Mansour and A. I. Muftah, *Thermochim. Acta*, 2011, **523**, 90–96.
- 25 S. Maksasithorn, P. Praserthdam, K. Suriye and D. P. Debecker, *Microporous Mesoporous Mater.*, 2015, **213**, 125–133.

- 26 N. Kasempremchit, P. Praserthdam and S. Assabumrungrat, *Korean J. Chem. Eng.*, 2016, **33**, 2842–2848.
- 27 H. Liu, L. Zhang, X. Li, S. Huang, S. Liu, W. Xin, S. Xie and L. Xu, J. Nat. Gas Chem., 2009, 18, 331–336.
- 28 J.-S. Lee, I.-H. Jang and N.-G. Park, J. Phys. Chem. C, 2012, 116, 13480–13487.
- 29 A. P. Shpak, A. M. Korduban, M. M. Medvedskij and V. O. Kandyba, J. Electron Spectrosc. Relat. Phenom., 2007, 156, 172–175.
- 30 L. Wang, Y. Wang, Y. Cheng, Z. Liu, Q. Guo, M. N. Ha and Z. Zhao, J. Mater. Chem. A, 2016, 4, 5314–5322.
- 31 S. Maksasithorn, D. P. Debecker, P. Praserthdam, J. Panpranot, K. Suriye and S. K. N. Ayudhya, *Chin. J. Catal.*, 2014, 35, 232–241.

- 32 S. Huang, S. Liu, W. Xin, J. Bai, S. Xie, Q. Wang and L. Xu, *J. Mol. Catal. A: Chem.*, 2005, **226**, 61–68.
- 33 X.-L. Yang, R. Gao, W.-L. Dai and K. Fan, *J. Phys. Chem. C*, 2008, **112**, 3819–3826.
- 34 C. Yue, X. Zhu, M. Rigutto and E. Hensen, *Appl. Catal., B*, 2015, **163**, 370–381.
- 35 S. Huang, S. Liu, Q. Zhu, X. Zhu, W. Xin, H. Liu, Z. Feng, C. Li, S. Xie, Q. Wang and L. Xu, *Appl. Catal.*, A, 2007, 323, 94–103.
- 36 W. Limsangkass, P. Praserthdam, S. Phatanasri, J. Panpranot, N. Poovarawan, W. Jareewatchara, S. Kunjara Na Ayudhya and K. Suriye, *Catal. Lett.*, 2014, 144, 1524–1529.
- 37 N. Liu, S. Ding, Y. Cui, N. Xue, L. Peng, X. Guo and W. Ding, *Chem. Eng. Res. Des.*, 2013, **91**, 573–580.