


 Cite this: *RSC Adv.*, 2019, **9**, 1602

The modification mechanism and the effect of magnesium chloride on poly(vinyl alcohol) films

 Wenhao Du,^{ab} Li Jiang,^{ab} Mengke Shi,^{ab} Zhaojie Yang^{ab} and Xi Zhang  ^{ab}

The modification mechanism and the effect of $MgCl_2$ on poly(vinyl alcohol) and the effect of water in the system were studied in this paper. The effect of $MgCl_2$ on different fully dried PVA was investigated by Fourier transform infrared spectroscopy, X-ray diffraction, differential scanning calorimeter, thermogravimetric analysis, water content test, dynamic thermomechanical analysis and tensile test, respectively. The results showed that $MgCl_2$ was an effective strengthening agent, which could crosslink with PVA and then effectively decrease the crystallinity of PVA. With the addition of $MgCl_2$, the strength and rigidity of PVA increased and the melting temperature decreased. The effect of $MgCl_2$ on thermal stability of PVA was related to the alcoholysis degree of PVA. The tensile strength of PVA films modified with $MgCl_2$ were all over 120 MPa. Moreover, the effect of $MgCl_2$ on the dynamic thermomechanical properties and tensile properties of PVA with various content of water was studied. Water could interact with $MgCl_2$ to destroy the crosslink between $MgCl_2$ and PVA. In the presence of water, PVA modified with $MgCl_2$ became soft, with lower tensile strength and higher elongation at break.

Received 4th December 2018
 Accepted 31st December 2018

DOI: 10.1039/c8ra09958h
rsc.li/rsc-advances

1 Introduction

Polyvinyl alcohol (PVA) is an environmentally friendly material with excellent gas barrier properties, high strength, tear and flexibility. However, the strong hydrogen bonds among inter- and intra- molecular chains of PVA result in high crystallinity. This makes the pure PVA film brittle and easy to break during preparation and application. The poor mechanical properties have restricted the development of PVA materials. Meanwhile, the high melting point and low decomposition temperature give PVA a narrow thermoplastic processing window resulting in the difficulty of using conventional thermoplastic methods to process. Adding a plasticizer is the most commonly used way to improve the properties of PVA. The most commonly used plasticizer for PVA are water, glycerol, ethylene glycol, poly(ethylene glycol) and caprolactam.^{1,2} These plasticizers can form interaction with the hydroxyl groups of PVA and then destroy the inter- and intra- hydrogen bonding to reach the aim of plasticizing. However, the plasticizing efficiency of them is not high enough to meet the demand of application. Many kinds of inorganic salts have been reported as a new and high efficient plasticizer for PVA.^{3,4} Previous studies have proved that some inorganic salts could decrease the crystallinity of PVA and could be helpful to form new crystals.⁵⁻⁷ Moreover, some inorganic

salts could play a role as heterogeneous nucleating agent of PVA to increase the crystallinity of PVA.⁸ This indicated that with the addition of suitable inorganic salts, it could be expected to prepare PVA with predetermined crystallinity. From then on, the studies of modifying PVA with various kinds of inorganic salts increase gradually.⁹⁻¹² $MgCl_2$ was always considered as a plasticizer of the system in previous studies. However, the effect of water could not be ignored. Thence, the modification mechanism of inorganic salts on PVA remains to further investigation.

Generally, water has a great influence on the properties of PVA films. Water could play a role as plasticizer by forming interaction with the $-OH$ of PVA molecule chains. Lots of researches have been investigating the effect of water on PVA.^{3,4,13,14} However, these studies always focused on the state of water in PVA, the destroying mechanism and the plasticization of water on the crystal of PVA.¹⁵⁻¹⁸ The effect of water on mechanical properties of PVA and the effect of water in the process of modification of PVA with inorganic salts rarely get attention.

The aim of this paper is to study the way of $MgCl_2$ influencing PVA by investigating the effect of $MgCl_2$ on the structure and properties of PVA with different alcoholysis degree and polymerization degree after sufficient drying. In addition, the effect of water in the system was studied in this paper. It could be excepted that the modification mechanism of other inorganic salts could be revealed and PVA with more excellent properties could be prepared based on this study.

^aState Key Laboratory of Polymer Materials Engineering, Chengdu 610065, People's Republic of China. E-mail: zhangxi6352@163.com; Tel: +8613808072562

^bPolymer Research Institute of Sichuan University, Chengdu 610065, People's Republic of China



2 Experimental

Materials

PVA1799 (DP = 1700, degree of hydrolysis 99%), PVA1788 (DP = 1700, degree of hydrolysis 88%), PVA1792 (DP = 1700, degree of hydrolysis 92%), PVA2488 (DP = 2400, degree of hydrolysis 88%) and PVA2499 (DP = 2400, degree of hydrolysis 99%), were provided by Sichuan Vinylon Factory, SINOPEC (China). $MgCl_2 \cdot 6H_2O$ was purchased from Kelong Chemical Co. (Chengdu, China), which was used without any further purification.

Sample preparation

PVA films were prepared by the casting method. First, 5 g PVA and 2 wt%, 4 wt%, 6 wt%, 8 wt%, 10 wt%, 12 wt% and 15 wt% $MgCl_2 \cdot 6H_2O$ were dissolved in distilled water by heating in an oil bath at 90 °C for 3 h, and the aqueous solutions were prepared, which called the film-forming solution. The film-forming solutions were casted onto the Petri-dish and dried at 60 °C for 48 h to eliminate water completely. According to the content of $MgCl_2 \cdot 6H_2O$, the PVA1799 films were called as PVA, PM2, PM4, PM6, PM8, PPM10, PM12 and PM15; the PVA1788 films were called as 880, 884, 886, 888, 8810 and 8815; the PVA1792 films were called as 1792-0, 1792-4, 1792-10 and 1792-15; the PVA2488 films were called as 2488-0, 2488-4, 2488-10, 2488-15.

Fully dried sample preparation: the film-forming solutions were coated on the PTFE sheet and dried at 60 °C for 48 h. All samples were dried at 105 °C for 5 h under vacuum ($P < 0.3$ MPa).

Sample with different water content preparation: PVA, PM4, PM6, PM8 and PM10 were dried at 105 °C for 5 h under vacuum ($P < 0.3$ MPa). Then these films were stored at the environment of high humidity to prepare PVA films with 4% and 12% content water.

Characterizations

Fourier transform infrared (FT-IR) spectroscopy. The infrared spectra were measured using a Fourier transform infrared spectrophotometer (Nicolet 560). The film-forming solutions prepared according to Table 1 was casted on a Petri dish and dried at 60 °C to remove water. The measurements were carried out with a resolution of 4 cm^{-1} .

X-ray diffraction (XRD) measurements. The XRD test was carried out using an X'Pert Pro MPD diffractometer manufactured by Philips Analytical Company of Netherlands, with nickel filter $\text{Cu K}\alpha$ as the radiation source. The acceleration voltage

was 50 kV and the current was 35 mA. The samples were continuously scanned over the 2θ range from 5 to 50°.

Differential scanning calorimetry (DSC). The DSC measurements were performed by a differential scanning calorimeter (NETZSCHDSC204). Samples total weight of 5–7 mg were weighted and were heated from 30 °C to 250 °C at a rate of 10 °C min^{-1} under a flow of nitrogen.

Thermal gravity analysis (TGA). TGA was performed by SDTQ600 TGA thermal analysis instrument (Du Pont). The samples for testing were heated from room temperature to 600 °C at a heating rate of 10 °C min^{-1} .

Dynamic thermomechanical analysis (DMA). The dynamic mechanical measurements were carried out with DMA Q800 (TA, USA). The samples were cut as a dimension of 15.0 mm \times 4.0 mm \times 0.3 mm. The oscillatory frequency was 1 Hz. The temperature was raised from –50 to 150 °C at a constant rate of 3 °C min^{-1} .

Mechanical testing. The mechanical properties (tensile strength (TS), elongation at break (%Eb) and Young's modulus) of the film was determined using a tensile testing equipment (Instron 5567). The crosshead speed was 20 mm min^{-1} . The initial gauge length of the specimen was 20 mm. The width of each tensile sample was 4 mm. The film thickness was measured with a micrometer in triplicate. The samples were placed in an air environment at a relative humidity of 54% for one week before measurement. The required relative humidity was obtained by placing a saturated $Mg(NO_3)_2$ solution in a sealed box at 25 °C. The data were the average of 5–7 specimens.

Water absorption testing. The samples were dried at 105 °C for 5 h and were stored in constant temperature and constant humidity box (SANTN HTC-500) at 25 °C and a relative humidity of 54%. The films were weighed every 12 h and the water content were calculated based on the quality of PVA. The water content (WA) was obtained using the relationship.

$$WA = \frac{W_e - W_d}{W_d} \times 100\%$$

W_e was the weight of the films after storing at the RH of 54% for one week, W_d was the weight of the films after drying sufficiently.

3 Results and discussion

FT-IR analysis

FT-IR was used to characterize the PVA1799 and PVA 1788 films before and after $MgCl_2$ modification, and the results were shown in Fig. 1. In the IR spectrum, the peak at 3000–3500 cm^{-1} corresponds to the stretching vibration of –OH on PVA

Table 1 DSC analysis of thermal characteristic of PVA1799 and PVA1788 with various contents of $MgCl_2 \cdot 6H_2O$

	PVA	PM4	PM6	PM8	PM10	PM12	880	884	886	888	8810
$T_g/^\circ\text{C}$	67.8	76.9	92.1	81.5	80.4	76.8	69.8	69.8	87.8	93.2	97.4
$T_d/^\circ\text{C}$	139	145	143	146	145	149	116	115	141		
$T_m/^\circ\text{C}$	228	226	219	221	214	203	196	193	Double peak	Double peak	151






Fig. 1 The FT-IR spectra of PVA1799 (a) and PVA1788 (b) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.

molecules, the peaks at 2942, 1430 and 1096 cm^{-1} are the characteristic of symmetric stretching vibration of C-H and bending stretching of CH_2 and stretching vibration of C-O, respectively.¹⁹ Due to the lower degree of alcoholysis, there are a large number of ester groups on PVA1788 molecules. Thus, the carbonyl stretching vibration of ester groups at 1733 cm^{-1} could be found in the FT-IR spectra of PVA1788. It could be seen from Fig. 1(a) and (b) that PVA films exhibited a decrease in frequencies after the addition of MgCl_2 . This is because the electron interaction between Mg^{2+} and oxygen atom of $-\text{OH}$ in PVA molecules was stronger than intermolecular and intramolecular hydrogen bonds of PVA. Therefore, MgCl_2 could weak the hydrogen bonds. As a result, the absorption frequency of hydroxyl group of PVA1799 and PVA1788 shifted 10 cm^{-1} and 18 cm^{-1} to a lower wavenumber with the addition of 10 wt% $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$. The difference might arise from the different number of $-\text{OH}$ in PVA1788 and PVA1799. There were less $-\text{OH}$ in PVA1788, so that the percent of $-\text{OH}$ on PVA1788 which could interact with MgCl_2 was higher than that of PVA1799.

Crystalline properties

The X-ray diffraction patterns of PVA1799 and PVA1788 films before and after MgCl_2 modification were displayed in Fig. 2(a) and (b). It could be seen that the diffraction peak of PVA appears at $2\theta = 20^\circ$ ($d = 0.46\text{ nm}$) and the diffraction peaks of PVA film decreased in intensity with the increasing of MgCl_2 content. This phenomenon indicated that MgCl_2 had a damaging effect on the crystals of PVA. This is because that MgCl_2 could form strong interaction with PVA molecules and this interaction could interrupt the hydrogen bonding in the crystalline structure of PVA. The previous work has proved that the area under the diffraction peak or its intensity could be taken as a measurement of the degree of crystallinity. The decrease of the intensity of the diffraction peak indicated that the addition of MgCl_2 could effectively decrease the degree of crystallinity of PVA films. It could also be noticed that the diffraction peaks of MgCl_2 did not appear in the patterns. This also suggests that MgCl_2 was completely dissolved in PVA films and no MgCl_2 crystals or congregates existed.




Fig. 2 The XRD curves of PVA1799 (a) and PVA1788 (b) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.




Fig. 3 The DSC curves of PVA1799 (a) and PVA1788 (b) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.

Thermal properties

The DSC curves of PVA films modified with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ are displayed in Fig. 2, and the corresponding data are shown in Table 1.

With the increasing of MgCl_2 content, both the T_g value of PVA1799 and PVA1788 increased. This is because MgCl_2 could crosslink with PVA as Fig. 4 to some extent. This interaction between MgCl_2 and PVA could weak the activity of PVA chain segments. T_α is the temperature at which chain segments of amorphous region near crystal region in PVA begin to motion. It could be found that the T_α value of PVA1799 increased with the increasing of content of MgCl_2 . This might be due to the influence of MgCl_2 on crystal orientation and crystallinity of PVA.⁸ Moreover, this influence could be reflected by the change of melting peak. It could be seen from Fig. 3(a) that increasing content of MgCl_2 decreased melting point, broadened melting peak and melting range.²⁰ This indicated that the crystal structure of PVA was destroyed and the distribution of the crystal size became wider after the addition of MgCl_2 . In the case of PVA1788, with the addition of over 4 wt% MgCl_2 content, the melting peak of PVA1788 turned from single peak to double peak and moved forward low temperature. While with the

addition of 10 wt% MgCl_2 content, the melting peak became single peak and the melting temperature decreased from 45 °C of pure PVA1788 to 151 °C. This proved that the effect of MgCl_2 on PVA1788 was higher than PVA1799.

In addition, the effect of MgCl_2 on the thermal stability of PVA1799 and PVA1788 were studied. The thermal degradation of PVA could mainly be divided into two steps. Firstly, $-\text{OH}$ and $-\text{OCOCH}_3$ were eliminated to form H_2O and CH_3COOH . In the second step, the main chain of PVA broke and some organic volatiles were produced.^{21,22} It could be seen from Fig. 5, with the addition of 4 wt% $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, the T_i (the initial thermal decomposition temperature) and $T_{\max 1}$ (the temperature of the biggest decomposition rate in the first step) increased from 237 °C, 256 °C of pure PVA1799 to 259 °C and 270 °C, respectively. Meanwhile, with the increasing dosage of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, the T_i and $T_{\max 1}$ increased constantly. This indicated that MgCl_2 could increase the thermal stability of PVA1799. From Fig. 5(c) and (d) it could be seen that the temperature of two steps of pure PVA1788 were nearly the same, which was different with PVA1799. With the addition of 4 wt% $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, the TGA curve was basically in coincidence with that of pure PVA1788. However, when the dosage of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ reached 10 wt%, the first step moved toward the lower temperature. In addition, with the increase of the dosage of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, the thermal stability of PVA1788 decreased constantly. Thus, the effect of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ on the thermal stability of PVA1792, PVA2488 and PVA2499 were studied to figure out the law of MgCl_2 on the thermal stability of PVA.

Thermal stability analysis

The effect of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ on the thermal stability of PVA1792, PVA2488 and PVA2499 were studied and the obtained TGA and DTG curves were shown in Fig. 6. The T_i and $T_{\max 1}$ of PVA with different alcoholysis degree and polymerization degree before and after modifying with MgCl_2 were recorded in Table 2.

For PVA1792, PVA1788 and PVA 2488 with low alcoholysis degree, both the T_i and $T_{\max 1}$ of them were substantially the




Fig. 4 The interaction between MgCl_2 and PVA.






Fig. 5 The TG and DTG curves of PVA1799 (a and b) and PVA1788 (c and d) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.




Fig. 6 The TG (a) and DTG curves of PVA1792 (b), PVA2488 (c) and PVA2499 (d) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.

Table 2 The initial and the first maximum decomposition temperature of different types of PVA

Low alcoholysis		High alcoholysis			
T_i	PVA1792-0	PVA1788-0	PVA2488-0	PVA1799-0	PVA2499-0
T_{max1}	296 °C	295 °C	296 °C	237 °C	265 °C/293 °C
	333 °C	332 °C	332 °C	256 °C	289 °C/352 °C
T_i	PVA1792-10	PVA1788-10	PVA2488-10	PVA1799-10	PVA2499-10
T_{max1}	260 °C	258	258 °C	262 °C	274 °C
	276 °C	275 °C	276 °C	273 °C	289 °C
T_i	PVA1792-15	PVA1788-15	PVA2488-15	PVA1799-15	PVA2499-15
T_{max1}	253 °C	251 °C	252 °C	266 °C	267 °C
	265 °C	263 °C	264 °C	282 °C	280 °C


same. With the addition of 10 wt% $MgCl_2 \cdot 6H_2O$, the T_i and T_{max1} of PVA1792, PVA1788 and PVA 2488 decreased from about 295 °C, 332 °C to 260 °C and 276 °C or so. While with the addition of 15 wt%, the T_i and T_{max1} would decrease to lower values. This indicated that $MgCl_2$ could decrease the thermal stability of PVA with low alcoholysis degree, which was independent of the polymerization degree of PVA. This is probably because there were lots of residual ester groups in PVA with low alcoholysis degree. These ester groups had an effect on the interaction between $MgCl_2$ and the -OH of PVA. As a result, hydroxyl and ester groups would remove at a lower temperature.

However, the effect of $MgCl_2$ on PVA with higher alcoholysis degree was different with above situation. For PVA2499 with higher polymerization degree, there were two decomposition peaks in the first step at 289 °C and 352 °C, respectively. This is maybe because the residual ester groups showed an uneven distribution, thus the alcoholysis degree was higher than 99% in some parts but lower than 99% in other parts of PVA2499. According to the above analysis, it could be seen that the T_{max1} of PVA with lower alcoholysis degree was 332 °C. Thence, the peaks of the first step corresponded to the HA (decomposition of high alcoholysis parts) and LA (decomposition of low alcoholysis parts). With the addition of 4 wt% $MgCl_2 \cdot 6H_2O$, the T_{max1} of HA had no changes, but the T_{max1} of LA decreased from

352 °C of pure PVA2499 to 306 °C. While with the addition of 10 wt% and 15 wt% $MgCl_2 \cdot 6H_2O$, there was only one peak in the first decomposition step at 289 °C and 280 °C, respectively. Oppositely, for PVA1799 with lower polymerization degree, increasing dosage of $MgCl_2$ increased the T_i and T_{max1} . This indicated that the effect of $MgCl_2$ on PVA with high alcoholysis was related to the polymerization degree of PVA: the addition of $MgCl_2$ could increase the thermal stability of PVA with low polymerization degree. In the case of PVA with high polymerization degree, the effect of $MgCl_2$ on the thermal stability of PVA with high polymerization degree was complicated, because the ester groups showed an uneven distribution resulting in various alcoholysis degree on PVA molecules.

Dynamic mechanical properties

DMA was used to study the $\tan \delta$ and storage modulus (G') of PVA1799 and PVA1788. $\tan \delta$ is a damping term defined as the ratio of energy dissipated as heat to the maximum energy stored in the materials. It is an index of the material viscoelasticity. It could be seen from Fig. 7 that the $\tan \delta$ values of PVA increased as the $MgCl_2$ content increased from 4 wt% to 10 wt%. This indicated that with the increasing content of $MgCl_2$, the viscoelasticity of PVA increased. The size of the $\tan \delta$

Fig. 7 Plots of $\tan \delta$ against temperature of PVA1799 (a) and PVA1788 (b) with various contents of $MgCl_2 \cdot 6H_2O$.




Fig. 8 Plots of storage modulus E' against temperature of PVA1799 (a) and PVA1788 (b) with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.

peak is believed to relate to the volume fraction of the material undergoing the transition. It could be found that the peak size of $\tan \delta$ increased with the increasing content of MgCl_2 . This was because the destroy of MgCl_2 on the crystals would increase the amorphous fraction and the relaxation time of chain segments. The peak temperature of the $\tan \delta$ curve is determined as the T_g of the polymer material. It could be found that the T_g of PVA increased with the addition of MgCl_2 . This is probably because that the Mg^{2+} could crosslink with the $-\text{OH}$ of PVA, which limited the chain movement of PVA resulting in the improvement of T_g .

G' is a measurement of the rigidity of the material. Fig. 8 showed the plots of G' versus temperature of PVA1799 and PVA1788. The G' of PVA1799 and PVA1788 decreased as the temperature increased. This was because increasing temperature could destroy the intermolecular and intramolecular hydrogen bonds of PVA and crosslinking between MgCl_2 and PVA resulting in the decrease of chain rigidity. Moreover, it could be seen from Fig. 8(a) that the descending speed of pure PVA1799 was higher than that of PVA1799 modified with MgCl_2 . When the temperature was low, G' of pure PVA was higher than




Fig. 10 The water absorption of PVA and PM10.




Fig. 9 The tensile strength (a) and elongation at break (b) of PVA1799 and PVA1788 with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$.




Fig. 11 Plots of $\tan \delta$ and storage modulus G' against temperature of PVA with 0, 4%, 12% content of water.

that of PM, but it became the opposite as the temperature increased. This might be due to the high alcoholysis degree and high regularity arise from high density hydrogen bonds. PVA1799 had higher crystallinity and thus crystallinity was the main factor to influence G' . However, crystal of PM was destroyed by $MgCl_2$. As the temperature increased, crystal of pure PVA was destroyed, but there was crosslink between Mg^{2+} and PVA in $MgCl_2$ modified PVA1799 resulting in high thermo-mechanical stability. For PVA1788 with low alcoholysis degree and low crystallinity, crystallinity had little influence on G' . Thus, the crosslink between $MgCl_2$ and PVA1788 was the main influence factors on G' . Thence, G' of PVA1788 was greater than or equal to that of pure PVA1788.

Mechanical properties

The influence of $MgCl_2 \cdot 6H_2O$ on the mechanical properties of PVA1799 and PVA1788 was evaluated by tensile testing. Fig. 9

showed the measured values of tensile strength and elongation at break of PVA1799 and PVA1788 before and after modified with various content of $MgCl_2$. After the addition of $MgCl_2$, the tensile strength increased, while the elongation at break decreased. This proved that $MgCl_2$ was an effective strengthening agent, which could improve the strength and rigidity of PVA. The strengthening effect of $MgCl_2$ on PVA could be evaluated by the slope of curves in Fig. 9(a). With the increasing content of $MgCl_2$, the slope of PVA1799 decreased while the slope of PVA1788 increased. This indicated that the strengthening effect of $MgCl_2$ on PVA1788 was higher than that of PVA1799. This is because that the high crystallinity played a major role in increasing the tensile strength of PVA1799. $MgCl_2$ could destroy the crystal but crosslink with PVA. As a result, the strengthening effect of $MgCl_2$ on PVA1799 decreased with the increasing content of $MgCl_2$. While the content of $MgCl_2$ reached 8%wt, the tensile strength did not increase any more. For PVA1788 with low crystallinity, the




Fig. 12 Plots of $\tan \delta$ and storage modulus G' against temperature of PVA with 4% content of water and $MgCl_2 \cdot 6H_2O$, respectively.




Fig. 13 Plots of $\tan \delta$ against temperature of PM with 4% (a) and 12% (b) water.

crosslink between $MgCl_2$ and PVA was the key factor to increase strength. Thus, the slope of PVA1788 increased as the dosage of $MgCl_2$ increased.

Water sorption properties

Due to the lots of $-OH$, PVA is hydrophilic. However, the compact crystal would prevent H_2O from penetrating.⁴ As a result, the water absorption content of PVA depended on the rate of amorphous region. Fig. 10 showed the water absorption rate of PVA 1799 and PM10 at RH of 54%. As shown in Fig. 10, the water content in PM10 was always higher than that of pure PVA, and the difference became larger with the time going. This proved that $MgCl_2$ could destroy the crystal of PVA and increased the amorphous fraction resulting in the high water content in PM10. Meanwhile, the hydrophilicity of $MgCl_2$ could also increase the water content of PM10. As a result, the water sorption of PM was higher than that of PVA.

The effect of water on dynamic mechanical properties of PVA1799 modified with $MgCl_2$

$MgCl_2$ could increase the water sorption of PVA. However, there were few studies on the effect of water on the modification of $MgCl_2$ on PVA. Thence, the role of water in the modification was studied.

Fig. 11 showed the plots of storage modulus (G') and $\tan \delta$ versus temperature of PVA1799 with 0, 4%, 12% content of water. It could be seen from Fig. 11(a) that T_g of PVA decreased with the increasing content of water. While with 12% content of

water, T_g decreased from 82 °C of fully dried PVA to 28 °C. In addition, increasing water content could also decreased G' of PVA. This proved that water was an efficient plasticizer of PVA.

The effect of $MgCl_2 \cdot 6H_2O$ and water on the dynamic mechanical properties of PVA were studied, respectively. As shown in Fig. 12, the T_g of PVA modified with $MgCl_2$ was higher than that of PVA modified with the same content water. Meanwhile, G' of PM was lower than PVA modified with water at low temperature, but it reversed as the temperature increased. This was because that crystallinity was the major factor affecting G' when it was at lower temperature. The addition of $MgCl_2$ would destroy the crystal of PVA. As a result, the storage modulus of PM was lower than PVA modified with water. With




Fig. 14 The way of water damaging the interaction between PVA and $MgCl_2 \cdot 6H_2O$.

Table 3 The difference of T_g values between PVA and PM with various content of water

The difference of T_g	PM4 minus PVA	PM6 minus PVA	PM8 minus PVA	PM10 minus PVA
0%	20.7 °C	25.09 °C	25.07 °C	29.17 °C
4%	10.48 °C	10.77 °C	12.65 °C	15.53 °C
12%	-1.96 °C	-0.81 °C	2.94 °C	3.16 °C




Fig. 15 The tensile strength (a) and elongation (b) at break of PVA with various contents of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ in certain water content (12%).

the increasing temperature, the crystal was destroyed and thus crystallinity had lower difference on the storage modulus. Thence, the crosslink between Mg^{2+} and PVA took an increasing impact on G' . Therefore, G' of PM was higher than PVA modified with water as the temperature increased.

It could be seen from Fig. 13 that increasing dosage of MgCl_2 could increase T_g of PVA in the presence of water. This indicated that MgCl_2 still could crosslink with PVA. Table 3 showed the difference of the T_g between PM and PVA with the same content of water. Increasing water content decreased the difference with any content of MgCl_2 . This indicated that water could destroy the crosslink between MgCl_2 and PVA. Oxygen atom of H_2O could interact with Mg^{2+} , which would hinder the crosslink between Mg^{2+} and PVA resulting in the increase of molecular segmental mobility. The way of water damaging the interaction between PVA and MgCl_2 was shown as Fig. 14. With the 12% content water, both the difference between PM4 and PVA, PM6 and PVA were negative. This proved that the crosslink had been destroyed by water completely. In addition, MgCl_2 existed as hydrated MgCl_2 in the system which had larger size and could increase the free volume of PVA. As a result, both the T_g of PM4 and PM6 were lower than that of pure PVA.

The effect of MgCl_2 on mechanical properties of PVA1799 in the presence of water

The effect of the dosage of MgCl_2 on the tensile strength and elongation at break of PVA in 12% water content was shown in Fig. 15. It could be seen from Fig. 15(a) and 9(a) that the tensile strength of PVA modified with MgCl_2 was 50 MPa or so, but it could be over 120 MPa after sufficient drying. This proved that water played a significant role in decreasing the strength of PVA modified with MgCl_2 . In addition, with the increasing MgCl_2 content, the tensile strength of PVA increased, but the elongation at break decreased. This indicated that MgCl_2 still could crosslink with PVA in the presence of water. However, the mechanical properties in Fig. 15 varied more slightly than that

of PM after sufficient drying. This was might because that water could destroy the crosslink between MgCl_2 and PVA resulting in the decrease of the enhancement of MgCl_2 on PVA.

4 Conclusion

The various PVA films modified with $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ were prepared and the effect of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ on PVA with different alcoholysis degree and polymerization degree were investigated. The modification mechanism of MgCl_2 on PVA and the effect of water in this system were revealed. Basically, MgCl_2 was an effective strengthening agent, which could crosslink with PVA and then effectively destroy the crystals of PVA. With the addition of MgCl_2 , the strength and rigidity of PVA increased significantly and the melting temperature decreased. The tensile strength of PVA films modified with MgCl_2 were all over 120 MPa. The effect of MgCl_2 on the thermal stability of PVA was related to the alcoholysis degree of PVA. MgCl_2 could decrease the thermal stability of PVA with lower alcoholysis degree. In the case of high alcoholysis PVA, the effect was related to the polymerization degree of PVA. MgCl_2 could increase the thermal stability of PVA with low polymerization degree. In addition, water could interact with MgCl_2 to destroy the crosslink between MgCl_2 and PVA resulting in the decrease of the enhancement of MgCl_2 on PVA. Taken together, the above studies revealed that MgCl_2 could interact with PVA to increase the strength and rigidity of PVA and could increase the water sorption properties of PVA; however, the presence of water could decrease the modification effect. The further cognize on the way of MgCl_2 influencing PVA could do help in revealing the modification mechanism of other inorganic salts on PVA and preparing the materials with more excellent properties.

Conflicts of interest

The authors declare no conflict of interest.



Acknowledgements

This research was supported by the National Natural Science Foundation of China (No. 51273129) and Applied Basic Research Project of Sichuan Province (No. 2017JY0247).

References

- 1 R. M. Hodge, T. J. Bastow, G. H. Edward, G. P. Simon and A. J. Hill, *Macromolecules*, 1996, **29**, 8137–8143.
- 2 J. Jang and D. K. Lee, *Polymer*, 2003, **44**, 8139–8146.
- 3 R. Gref, Z. H. Ping, Q. T. Nguyen, *et al.*, *Polymer*, 1995, **36**, 1655–1661.
- 4 G. J. Pritchard, *Poly(vinyl alcohol): basic properties and uses*, Macdonald Technical & Scientific, 1970.
- 5 W. Q. Wu, H. F. Tian and A. Xiang, *J. Polym. Environ.*, 2012, **20**, 63–69.
- 6 H. M. Zidan, *Polym. Test.*, 1999, **18**, 449–461.
- 7 H. M. Zidan, *J. Appl. Polym. Sci.*, 2003, **88**, 516–521.
- 8 Z. Peng and D. Chen, *J. Polym. Sci., Part B: Polym. Phys.*, 2006, **44**, 534–540.
- 9 G. Vijaya Kumar and R. Chandramani, *Appl. Surf. Sci.*, 2009, **255**, 7047–7050.
- 10 R. Singh and S. G. Kulkarni, *Int. J. Polym. Mater. Polym. Biomater.*, 2013, **62**, 351–357.
- 11 J. I. Kubo, N. Rahman, N. Takahashi, T. Kawai, G. Matsuba, K. Nishida, T. Kanaya and M. Yamamoto, *J. Appl. Polym. Sci.*, 2009, **112**, 1647–1652.
- 12 X. C. Jiang, X. F. Zhang, D. Z. Ye, X. Zhang and D. Hua, *Polym. Eng. Sci.*, 2012, **52**, 1565–1570.
- 13 R. M. Hodge, G. H. Edward and G. P. Simon, *Polymer*, 1996, **37**, 1371–1376.
- 14 G. Mann, *Acta Polym.*, 1986, **37**, 744–745.
- 15 R. Iwamoto, M. Miya and S. Mima, *J. Polym. Sci., Part B: Polym. Phys.*, 1979, **17**, 1507–1515.
- 16 R. M. Hodge, T. J. Bastow, G. H. Edward, *et al.*, *Macromolecules*, 1996, **29**, 8137–8143.
- 17 R. Wang, Q. Wang and L. Li, *Polym. Int.*, 2003, **52**, 1820–1826.
- 18 S. J. Peng, S. X. Liu, Y. J. Sun, N. P. Xiang, X. C. Jiang and L. X. Hou, *Eur. Polym. J.*, 2018, **106**, 206–213.
- 19 C. A. Finch, *Polyvinyl alcohol: properties and applications*, Wiley London, 1973.
- 20 P. D. Garrett and D. T. Grubb, *J. Polym. Sci., Part B: Polym. Phys.*, 1988, **26**, 2509–2523.
- 21 Y. Tsuchiya and K. Sumi, *J. Polym. Sci., Part A-1: Polym. Chem.*, 1969, **7**, 3151–3158.
- 22 P. Thomas, J.-P. Guerbois, G. Russell, *et al.*, *J. Therm. Anal. Calorim.*, 2001, **64**, 501–508.

