RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2019, 9, 25064

Received 31st May 2019 Accepted 24th July 2019

DOI: 10.1039/c9ra04141a

rsc.li/rsc-advances

1. Introduction

As a member of perovskite oxides, cobaltites are important agile and multifunctional materials that are very promising for several applications, including high-temperature oxygen separation membranes, cathodes in solid oxide fuel cells (SOFCs), magnetic storage, and magnetic refrigeration.^{1–3} The Co-based sister compounds of manganites have been less intensively studied.^{4–6} It is well-known that the similar Hund's rule exchange energy and crystal-field energy both lead to an additional spin-state degree of freedom in cobaltites, which results in close competition between the multiple ground states. This, in turn, leads to phenomena such as magnetoelectronic phase separation, colossal magnetoresistance, and magnetocaloric effect. The spin state (ST) of cobalt ions is very sensitive to the application of external stimuli such as magnetic and electrical fields, temperature, pressure, or compositional doping.^{7,8} This sensitivity is due to the very small energy difference

^dInstitut NEEL, B. P.166, 38042 Grenoble Cedex 09, France

Magnetic and magnetocaloric properties of La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ and their implementation in critical behaviour study and spontaneous magnetization estimation

F. Saadaoui, 🕑 *^a Muaffaq M. Nofal,^b R. M'nassri, ២ *^a M. Koubaa,^c N. Chniba-Boudjada^d and A. Cheikhrouhou^c

In this work, we present the results of the magnetic, critical, and magnetocaloric properties of the rhombohedral-structured $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ cobaltite. Based on the modified Arrott plot, Kouvel–Fisher, and critical isotherm analyses, we obtained the values of critical exponents (β , γ , and δ) as well as Curie temperature (T_C) for the investigated compound. These components were consistent with their corresponding values and they were validated by the Widom scaling law and scaling theory. The obtained critical exponents were close to the theoretical prediction of the mean-field model values, revealing the characteristic of long-range ferromagnetic interactions. The magnetic entropy, heat capacity, and local exponent $n(T, \mu_0H)$ of the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ compound collapsed to a single universal curve, confirming its universal behaviour. The estimated spontaneous magnetization value extracted through the analysis of the magnetic entropy change was consistent with that deduced through the classical extrapolation of the Arrott curves. Thus, the magnetic entropy change is a valid and useful approach to estimate the spontaneous magnetization of $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$.

between the t_{2g} and e_g levels. Consequently, the state of Co can be presented in a low-spin (LS), intermediate-spin (IS), or high-spin (HS) state.^{4,5,8} This ability of Co to exist in several STs given a principal property distinguishes the cobalt oxides from other transition metals such as manganese and makes the physical phenomena observed in the cobalt oxides very complex, due to which they have not been entirely comprehended so far. The complexity of STs provides promising opportunities for basic science as well as electronic applications, inducing a multifunctional characteristic to cobalt oxides. The latter property derives from the fact that the crystal-field splitting of the 3d energy level of Co ions in cobalt oxides is of the same order of magnitude as the Hund's rule intraatomic exchange energy and 3d orbital bandwidth.⁹

Physical effects such as magnetoresistance and magnetocaloric effects observed in manganites^{10,11} and cobaltites^{3,12-14} have been the subject of several investigations in the last few years. Double exchange (DE), phase separation (PS), Jahn–Teller distortion (JT), and Griffiths phase (GP) have been found to explain the aforementioned effects. Moreover, these compounds are also interesting for applications since they present low costs and longer usage times. This family of materials can be easily elaborated, and grain growth can be achieved to the desired size; moreover, they possess tunable Curie temperature and high chemical stability. La-based cobaltite is one of the perovskite oxides and it shows a wide variety of physical properties with relatively high $T_{\rm C}$ values. Like

^aUnité de Recherche Matériaux Avancés et Nanotechnologies (URMAN), Institut Supérieur des Sciences Appliquées et de Technologie de Kasserine, Kairouan University, BP 471, Kasserine 1200, Tunisia. E-mail: saadaoui.fadhel80@gmail.com; rafik_mnassri@yahoo.fr

^bDepartment of Mathematics and General Sciences, Prince Sultan University, P. O. Box 66833, Riyadh 11586, Saudi Arabia

^cLT2S Lab (LR16 CNRS 01), Digital Research Center of Sfax, Sfax Technopark, Cité El Ons, B.P. 275, 3021, Tunisia

manganese, iron, and copper, cobalt exhibits various possible oxidation states $(Co^{2+}, Co^{3+}, and Co^{4+})$ and several types of coordinations (tetrahedral, pyramidal, and octahedral). Consequently, cobalt oxides offer a wide gamut of opportunities for the creation of many frameworks involving a mixed valence state of cobalt. Similar to manganites, the substitution of La³⁺ by Sr^{2+} in $La_{1-x}Sr_xCoO_3$ converts an adapted number of Co^{3+} to Co⁴⁺, introducing a predominantly ferromagnetic (FM) order due to the DE interactions between Co³⁺ and Co⁴⁺ ions.¹⁵ In addition, the substitution at the A-site of cobaltite oxides induces changes in the chemical internal pressure that locally affects the Co-O-Co networks and easily modifies the ST of cobalt ions due to the fact that crystal-field splitting is very sensitive to changes in the Co-O-Co angle and Co-O distance. Therefore, Co³⁺ adopts three possible STs, namely, LS, IS, and HS, whereas Co⁴⁺ usually exhibits only the LS.

It is believed that doped cobaltites are not a homogeneous ferromagnet. This inhomogeneity might affect the cooperative behavior of the Co sublattice, and therefore, the nature of FMparamagnetic (PM) phase transition and the class of universality of this magnet.¹⁶ Therefore, the analysis of critical exponents (β , γ , and δ) of a magnetic system can yield valuable information about the magnetic phase transitions and can be classified into different universal classes, such as mean field, 3D Ising, and 3D Heisenberg, depending on the exponent values. Recently, the theory of critical phenomena justified the existence of a universal MCE behavior in materials exhibiting second-order magnetic phase transitions.17 Recent studies have revealed the impact of Bi3+ substitution on several properties in La-based manganites.¹⁸⁻²⁰ It is believed that the BiMnO₃ system is a special and promising compound, which exhibits multiferroic properties where phases like ferroelectric, FM, and ferroelastic coexist in this oxide. Earlier reports have suggested that Bi doping in manganite systems exhibit a high charge ordering temperature²¹ and that Bi doping in LaCaMnO₃ exhibits excellent MCE properties with high efficiency.18,20 However, there are relatively few investigations that deal with the investigation of critical and MCE behaviors in Bi-doped Lacobaltite system. In order to understand both these behaviors in rare-Earth cobaltites keeping in mind the abovementioned factors, we have performed a comprehensive investigation of the structural, magnetic, critical, and MCE properties of a small amount (5%) of Bi-doped La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ samples. For a better understanding of the nature of magnetic transition and MCE properties of $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$, we obtained the universal curves of magnetic entropy changes. Further, we have made an effort to estimate the spontaneous magnetization $(M_{\rm SP})$ from magnetic entropy changes and then compared the results with the standard extrapolation of Arrott plots. The present investigation is an attempt to fill this gap to a certain extent and to comprehensively explore the magnetic transition nature of a La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ system.

2. Experimental details

The ceramic with a nominal composition of $La_{0.55}Bi_{0.05}Sr_{0.4}$ -CoO₃ was synthesized by the solid-state reaction method. The

precursors of La₂O₃ (Aldrich 99.9%; USA), Bi₂O₃ (Aldrich 99.9%; USA), SrCO₃ (Aldrich 99.9%; USA), and Co₃O₄ (Aldrich 99.9%; USA) were mixed in an agate mortar with the desired proportions according to the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ system. Then, the obtained powder was heated at 800 °C for 24 h. After cooling to the ambient temperature, the bulk was ground and pressed into pellets and then sintered at 900, 1000, 1100, and 1200 °C for 24 h with intermediate regrinding and repelling to ensure homogenization. Finally, the obtained disk-shaped samples were slowly cooled to room temperature in air. As the sample was exposed to air, it consequently became stoichiometric with respect to oxygen.^{22,23} The X-ray diffraction (XRD) pattern was recorded at room temperature on a PANalytical X'PERT Pro MPD diffractometer using $\theta/2\theta$ Bragg–Brentano geometry with diffracted beam monochromatized CuK α radiation ($\lambda = 1.5406$ Å). The diffraction patterns were collected at steps of 0.017° over the angle range of 20-80°. Rietveld refinement was performed to determine the structural parameters by using the FullProf software. A vibrating-sample magnetometer developed at NEEL Institute was used to investigate the thermomagnetic properties of the sample. The temperature and field dependencies of the magnetization, $M(T, \mu_0 H)$, were recorded in a temperature range around the $T_{\rm C}$. To accurately extract the critical exponents of the sample, the corrected magnetic isotherms were measured in the range of 0-5 T and within a temperature interval of 2 K in the vicinity of $T_{\rm C}$.

3. Scaling analysis

For continuous phase transition, near $T_{\rm C}$, the critical behavior for a second-order magnetic phase transition can be investigated *via* a series of critical exponents (β , γ , and δ). According to the scaling hypothesis, these exponents are expressed as follows:^{24,25}

$$M_{\rm SP} = \lim_{H \to 0} (M) = M_0 (-\varepsilon)^{\beta}, \quad \varepsilon < 0; \ T < T_{\rm C}$$
(1)

$$\chi_0^{-1} = \lim_{H \to 0} (\mu_0 H/M) = (h_0/M_0) \varepsilon^{\gamma}, \quad \varepsilon > T > T_C$$
 (2)

$$M = D(\mu_0 H)^{1/\delta}, \, \varepsilon = 0; \, T = T_{\rm C} \tag{3}$$

where $\varepsilon = (T - T_{\rm C})/T_{\rm C}$ is the reduced temperature. M_0 , h_0 , and D are the critical amplitudes; β (associated with $M_{\rm SP}$), γ (associated with magnetic susceptibility χ_0^{-1}), and δ (associated with the field-dependent magnetization at $T_{\rm C}$) are the critical parameters.

The critical exponents (β , γ , and δ) should obey the scaling equations.^{24,25} A formulation was used in this work, which was based on the scaling equations of state. In the asymptotic critical region and according to the scaling equations, the magnetic equation can be expressed as follows:

$$M(\mu_0 H, \varepsilon) = \varepsilon^{\beta} f_{\pm}(\mu_0 H/\varepsilon^{\beta+\gamma}) \tag{4}$$

where f_{\pm} denote regular analytic functions with f_{-} denoting the FM state for *T* below $T_{\rm C}$ and f_{+} denoting the PM state for *T* above $T_{\rm C}$. Eqn (4) shows that for true scaling relations and for the right

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

choice of β , γ , and δ , $M(\mu_0 H, \varepsilon)\varepsilon^{-\beta}$ vs. $\mu_0 H\varepsilon^{-(\beta+\gamma)}$ yields two universal curves of temperature *T* above and below $T_{\rm C}$.

4. Results and discussions

The XRD θ -2 θ patterns measured at room temperature show that La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ can be refined in the perovskite structure with a rhombohedral structure with the $R\bar{3}c$ space group. This demonstrates that the substitution of La by 5% Bi does not induce the relevant effect on the crystal structure as compared to those in the undoped La_{0.5}Sr_{0.4}CoO₃ compound prepared by the solid-state reaction method²⁶ or sol-gel technique.¹⁴ The structural information of the prepared sample is obtained after fitting the XRD data using the Rietveld refinement technique by means of the FullProf software.^{27,28} During the initial stages of refinement, only the following parameters were changed: scale factor, background coefficients, unit-cell parameters, full-width parameters, sample displacement, and peak asymmetry. First, only the scale factor was refined; then, the remaining parameters were gradually included in the successive least-squares cycles. The background was fit using a third-order polynomial, and the observed peak shapes were approximated by using a pseudo-Voigt profile function, limited to ten full-widths on each side of the peak maximum. Fig. 1 shows the XRD diffractogram for the investigated sample, where the open circle dots represent the measured XRD reflections and the solid lines denote the Rietveld-refined results. Evidently, a marginal difference between the measured spectra and refined ones can be observed. The quality of refinement is evaluated through the goodness of the fit indicator χ^2 , which is equal to 1.98. From Fig. 1, it is clear that a small secondary phase can be observed, which can be attributed to the presence of the CoO impurity. This impurity is identified with the X'Pert HighScore Plus software. It is interesting to note that the most intense peak in the XRD spectra for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ exhibits a double peak, representing the rhombohedral phase.



Fig. 1 Room-temperature XRD pattern for the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample.

The intense peak is shown in the inset of Fig. 1. The lattice parameters are found to be a = b = 5.415(7), c = 13.326(9) Å, and unit cell volume V = 338.51 Å³ for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃. For the undoped compound prepared by using the conventional solid-state reaction method, the lattice parameters can be determined as a = b = 5.436(3), c = 13.226(3) Å, and unit cell volume V = 338.49(1) Å³.²⁶ It is clear that the lattice parameter "*c*" and unit cell volume marginally increase with the addition of 5% Bi content, while parameter "*a*" slightly decreases with the addition of 5% Bi content. This almost-perfect match can be explained considering the similar ionic radii of La³⁺ ions (1.16 Å, 8-coordinate) and Bi³⁺ ions (1.17 Å, 8-coordinate).²⁹

In order to understand the general magnetic behavior and to estimate $T_{\rm C}$, low-field magnetization vs. temperature (M(T)) is obtained in the field-cooled (FC) mode for the La_{0.55}Bi_{0.05}Sr_{0.4}- CoO_3 sample. Fig. 2 shows the M(T) curve under an applied magnetic field of 0.05 T. This curve exhibits a sharp FM-PM phase transition, where $T_{\rm C}$, defined from the inflexion point of the dM/dT vs. T curve (inset, Fig. 2), is found to be 210 K. Here, $T_{\rm C}$ is suppressed by 20 K as compared to undoped La_{0.5}Sr_{0.4}- CoO_3 .¹⁴ It is noteworthy that even a higher value of $T_C = 237$ K was found by T. A. Ho et al.26 for a sample prepared under different conditions. This $T_{\rm C}$ suppression correlates with the competition between the DE interaction and superexchange interactions altered by the incorporation of Bi ion in the Co-O-Co networks. The observed M(T) curve reveals a strong variation in the magnetization around $T_{\rm C}$, which indicates that there is possibly a large magnetic entropy change around the magnetic transition.11,30 When showing the inverse of the magnetic susceptibility $(1/\chi - 1/M)$ curve in the PM state (insets, Fig. 2), a linear behavior with temperature is observed above $T_{\rm C}$, which can be fitted with the Curie-Weiss law:

$$\chi = C/(T - \theta_{\rm P}) \tag{5}$$



Fig. 2 Magnetization measurements as a function of temperature for the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample under 0.05 T. Insets: dM/dT as a function of temperature and temperature dependence of the inverse of magnetic susceptibility. The red line presents a linear fit at higher temperatures.

Paper

where θ_P is the PM T_C and *C* is the Curie constant. The obtained θ_P is determined to be 230 K, which is higher than T_C , where $\Delta T = \theta_P - T_C = 20$ K. This θ_P value is smaller than the one observed in the undoped compound (245 K).²⁶ The decrease in θ_P with 5% Bi doping can be explained by considering the DE mechanism in cobaltites. It is known that Bi³⁺, with the 6s² lone pair, is a highly polarizable ion and it induces local distortions in the Co–O–Co bond angles, resulting in a decrease in the DE interaction strength. For our sample, the positive values of θ_P and ΔT reveal the existence of a FM exchange interaction between the nearest neighbors in the PM region and confirm the presence of a magnetic inhomogeneity.^{31,32} Similar results are observed in several manganites^{33,34} and cobaltite perovskites, such as La_{0.6}Sr_{0.4}CoO₃.^{14,26}

Fig. 3 shows the magnetization vs. applied magnetic field curve up to 8 T, $M(\mu_0 H)$, recorded at 10 K. This curve shows the typical FM nature of La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃. The magnetization sharply increases with the applied magnetic field for $\mu_0 H = 1$ T, but does not saturate even up to a field of 8 T. Such results confirm the existence of FM clusters, which, in cobaltites, are related to the presence of a spin disorder in the system, with indifferent STs of Co^{3+} and Co^{4+} ions.¹⁵ Further, the $M(\mu_0 H, T =$ 10 K) curve can be used for the evaluation of the characteristic magnetization values by means of the procedures described elsewhere.³⁵ Namely, the saturation magnetization (M_{sat}) calculated from the *Mvs.* 1/H plot at $1/H \rightarrow 0$ (inset, Fig. 3). The obtained $M_{\rm sat}$ values reach 1.75 $\mu_{\rm B}$ /Co in the same order as the other perovskite systems.^{33,36,37} At low temperatures, the spontaneous magnetization $M_{sp}(exp)$ determined by the extrapolation of $M(\mu_0 H)$ from the high field to zero field is determined to be 1.37 $\mu_{\rm B}$ /Co (inset, Fig. 3).

Fig. 4 shows the isothermal curves $M(\mu_0 H)$ over a wide range of temperatures and external fields up to 5 T. These curves are used to determine the changes in the magnetic entropy $(-\Delta S_m)$ and critical exponents (β , γ , and δ). From the data, it is clear that

18

1.6

0.8

0.6 L 0

4

 $\mu_0 H(T)$

M(µB/Co)

♦ M at 10 K

75 (µ_R/Co)

 $2 3 (\mu_0 H)^{-1} (T^{-1})$

6

Interpolated

La_{0.55}Bi_{0.05}Sr_{0.4}CoO

= 1.37 (µ_B/Co)

2

Fig. 3 Variation in magnetization as a function of the applied magnetic field for the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample at 10 K. Inset: determination of the saturation magnetization of the sample at 10 K.



Fig. 4 Isothermal magnetization curves at various temperatures for the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample.

the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample shows FM behavior below T_C and PM behavior considerably above $T_{\rm C}$. The $M(\mu_0 H)$ curves of the sample in the temperature range of 100-300 K are shown in the inset of Fig. 4. At lower temperatures, the $M(\mu_0 H)$ curve reveals that the magnetizations rise sharply in weak applied magnetic fields and then progressively increase with the $\mu_0 H$ value. However, a diminution of magnetization with increasing temperature is clearly observed. Further, it is clear that at $T_{\rm C}$, the investigated material transits from the FM state to the PM state. This transition is due to the magnetic disorder established as the temperature increases. In this case, the deflection of magnetic momentum occurs, and hence, the total magnetic moment of the entire system decreases and compound magnetization gets diminished. Therefore, once the temperature reaches $T_{\rm C}$, the thermal motion of the molecules of the material affects the ordered spin at the zero field and the PM behavior is observed instead of the FM behavior.

In order to determine the type of magnetic phase transition in the vicinity of $T_{\rm C}$, Fig. 5a shows the Arrott curves $(M^2 - \mu_0 H/M)$ for the prepared La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ compound. In these curves, it is assumed that the critical exponents follow the mean-field theory (MFT), where $\beta = 0.5$ and $\gamma = 1.^{38}$ Fig. 5a shows that in the low-field region, the nonlinear and curvature characters in $M^2 - \mu_0 H/M$ parts at $T > T_{\rm C}$ and $T < T_{\rm C}$ are driven toward two opposite directions. The latter phenomenon is essentially due to the misaligned magnetic domains, which reveal the FM–PM separation and indicate that the values of $\beta =$ 0.5 and $\gamma = 1$ are inaccurate.

The characteristics of the magnetic phase transition in the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ cobaltite can be determined by assessing the feature of the Arrott plots around T_C . In our case, no inflection or negative slope is observed as a signature of the metamagnetic transition above T_C , indicating the nature of the second-order phase transition (SOPT). This is in agreement with those observed in earlier studies.^{14,39,40} In general, for SOPT, its thermodynamic function can be expressed in the form of a power law with the aforementioned critical exponents,

1.8

1.6

1.4

1.2

1.0

0.8

0.6

0.4

0.2

0.0

0

M(µ_B/Co)



Fig. 5 (a) $M^2 vs. \mu_0 H/M$ isotherms for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃; (b) NS as a function of temperature for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃.

namely, β , γ , and δ . This transition obeys the following asymptotic relations. By using eqn (1) and (2), as well as the socalled Arrott-Noakes equation of state $\left[\frac{\mu_0 H}{M}\right]^{1/\gamma} = a[T - T_{\rm C}]/T + bM^{1/\beta}$ (where *a* and *b* are constant

parameters), we can obtain the values of β and γ ; this approach is known as the modified Arrott plots (MAPs).⁴¹ Therefore, to determine the correct values of β and γ , MAPs should be used. In this context, it is possible to initially use the tri-critical meanfield model ($\beta = 0.25$ and $\gamma = 1$), 3D Ising model ($\beta = 0.325$ and $\gamma = 1.24$), 3D Heisenberg model ($\beta = 0.365$ and $\gamma = 1.386$), and mean-field model ($\beta = 0.5$ and $\gamma = 1$) to construct tentative Arrott plots and then the select the best one to be the initial Arrott plot for fitting the data. The so-called normalized slope (NS) defined as NS = $S(T)/S(T_{\rm C})$ at the critical point can be used for effecting further comparisons. Since the modified Arrott plots are a series of parallel lines, the NS of the most satisfactory model should be close to 1 (unity) regardless of temperature.42 As shown in Fig. 5b, the mean-field model provides an NS value closest to 1 in the temperature range under investigation. The latter model is the best one to determine the critical exponents

as well as to describe the material. The temperature dependencies of $\chi_0^{-1}(T)$ and $M_{\rm SP}(T)$ are shown in Fig. 6a; eqn (1) and (2) are used for fitting these data. These fits yielded the critical parameters as $\beta = 0.486 \pm 0.017$ with $T_{\rm C} = 211.572 \pm 0.1$ K and $\gamma = 1.109 \pm 0.065$ with $T_{\rm C} = 212.024 \pm 0.107$ K. These results are very close to the exponents of the mean-field model ($\beta = 0.5$ and $\gamma = 1$). It is evident that the obtained value of $T_{\rm C}$ agrees well with that obtained from the M(T) curve.

Alternatively, in order to more accurately determine the β , γ , and $T_{\rm C}$ parameters, we can use the Kouvel–Fisher (KF) method^{43,44} expressed as

$$\left[\frac{M_{\rm SP}}{\mathrm{d}M_{\rm SP}/\mathrm{d}T}\right] = \frac{[T-T_{\rm C}]}{\beta}; \quad \left[\frac{\chi_0^{-1}}{\mathrm{d}\chi_0^{-1}/\mathrm{d}T}\right] = \frac{[T-T_{\rm C}]}{\gamma} \qquad (6)$$

According to the above equations, the $1/\beta$ and $1/\gamma$ slopes are obtained by linear fitting and the value of $T_{\rm C}$ is obtained from the intercepts on the temperature axis. The results of the best fits are shown in Fig. 6b, where ($\beta = 0.482 \pm 0.052$, $T_{\rm C} = 212.71 \pm 0.13$ K) and ($\gamma = 0.965 \pm 0.441$, $T_{\rm C} = 212.116 \pm 0.023$ K) for the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ compound. It is worth noting that these new values are also in agreement with those obtained by the MAPs, which indicates that the estimated values are self-consistent and unambiguous.

The third critical exponent, namely, δ , is determined from the Widom scaling relation, *i.e.*, $\delta = 1 + \gamma/\beta$. Here, δ is calculated to be 3.281 \pm 0.084 as obtained by the MAPs and 3.002 \pm 0.493 as obtained by KF. Fig. 6c shows the magnetic isotherm $M(\mu_0 H;$ $T_{\rm C} = 210$ K) and the same plot on the Ln–Ln scale. The Ln(M) vs. $Ln(\mu_0 H)$ curve would be a straight line with a slope of $1/\delta$. The values of δ obtained through the MAP and KF methods are close to that obtained from the fitting of the isotherm at $T = T_{\rm C}$ to eqn (3) ($\delta = 3.125 \pm 0.012$). Moreover, we note that these values of the critical exponents are in good agreement with those obtained from the mean-field model ($\beta = 0.5$, $\gamma = 1$, and $\delta = 3$). When compared with $La_{0.5}Sr_{0.4}CoO_3$, it is evident that the critical exponents of the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ sample are different from those observed for the undoped sample. It has been reported that the critical exponents for La_{0.5}Sr_{0.4}CoO₃ prepared by the sol-gel process are in good agreement with those predicted by the 3D Heisenberg model.¹⁴ However, many inconsistent results have been reported on La_{0.6}Sr_{0.4}CoO₃ made by the solidsolid reaction. For example, T. A. Ho et al. found a complex scenario in the $La_{0.5}Sr_{0.4}CoO_3$ sample.²⁶ The β value of their sample was located between those expected from the mean-field model and 3D Heisenberg model, while the γ value is close to the value obtained from the 3D Ising model. Consequently, it is clear that the replacement of lanthanum by 5% Bi in the La_{0.6}Sr_{0.4}CoO₃ sample induced a long-range magnetic order and modified the class of universality of the sample. In general, these characteristics are related to the differences in the sintering temperatures, preparation routes, particle sizes and shapes, and local geometric structures, resulting in various inhomogeneities and magnetocrystalline anisotropies. In our case, the obvious differences in the class of universalities of La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ and the parent compound are due to the



Fig. 6 (a) Spontaneous magnetization (left axis) and inverse initial susceptibility (right axis) vs. temperature for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃. (b) K-F construction for determining the critical exponents and T_C ; solid lines are the fitted data. (c) Critical isotherm of M vs. $\mu_0 H$ for La_{0.55}Bi_{0.05}-Sr_{0.4}CoO₃. Inset: Ln-Ln scale for M vs. $\mu_0 H$.

influence of the replacement of La^{3+} ion (with zero magnetic moment) by Bi^{3+} ion (with nonzero magnetic moment). Therefore, the insertion of 5% Bi may contribute toward the magnetic interactions along with Co^{3+} and Co^{4+} ions and causes a difference in the critical behavior in the aforementioned samples.

In addition, the scaling equation stipulates that the $M(\mu_0 H, T)$ data in the critical region obeys the scaling relation expressed as⁴⁵

$$M(\mu_0 H, \varepsilon) = \varepsilon^{\beta} f_{\pm}(\mu_0 H/\varepsilon^{\beta+\gamma}) \tag{7}$$

where f_+ and f_- are the analytical functions for $T > T_C$ and $T < T_C$, respectively. Eqn (8) shows that $M(\mu_0 H, \varepsilon)\varepsilon^{-\beta} vs. \mu_0 H\varepsilon^{-(\beta+\gamma)}$ yields two distinct curves: one for $T > T_C$ and the other for $T < T_C$. By using the correct (KF)- β and (KF)- γ values for La_{0.55}Bi_{0.05}-Sr_{0.4}CoO₃, the $M/|\varepsilon|^{\beta} vs. H/|\varepsilon|^{(\beta+\gamma)}$ curves are plotted, as shown in Fig. 7. Evidently, they collapse onto two sides: one above T_C and the other below T_C . The obedience of the scaling equation over the entire range of normalized variables proves that the critical exponents and T_C are reasonably accurate and unambiguous with the scaling theory.

The isothermal magnetic entropy change (ΔS_m) , which results from the spin ordering under the influence of a magnetic field, can be obtained from the $M(\mu_0 H)$ curves at various temperatures according to the classical thermodynamic theory based on Maxwell's relations by using the following expression:⁴⁶

$$\Delta S_{\rm m}(T,\mu_0 H_{\rm max}) = S(T,\mu_0 H_{\rm max}) - S(T,0)$$
$$= \int_0^{\mu_0 H_{\rm max}} \left(\frac{\partial S}{\partial H}\right)_T d\mu_0 H \tag{8}$$



Fig. 7 Scaling plot of $M|\varepsilon|^{-\beta}$ vs. $\mu_0 H|\varepsilon|^{-(\beta+\gamma)}$ for the La_{0.55}Bi_{0.05}Sr_{0.4}-CoO₃ compound at temperature $T < T_C$ and $T > T_C$.

In this work, the magnetization measurements are made under discrete magnetic fields and temperature intervals. Therefore, the magnetic entropy change can be approximately given by

$$\Delta S_{\rm m}(T,\mu_0 H) = \sum \left(\frac{M_i - M_{i+1}}{T_{i+1} - T_i}\right) \Delta \mu_0 H_i \tag{9}$$

In this equation, M_i and M_{i+1} are the experimental values of magnetization measured at temperatures T_i and T_{i+1} , respectively, under the applied magnetic field $\mu_0 H_i$.

Fig. 8a shows the behavior of $\Delta S_{\rm m}$ for the La_{0.55}Bi_{0.05}Sr_{0.4}-CoO₃ sample as a function of temperature. These curves exhibit peaks around $T_{\rm C}$. Immediately below and above $T_{\rm C}$, the $-\Delta S_{\rm m}$ value monotonically increases with an increasing magnetic field, which corresponds to a magnetic FM–PM transition. The dependence of the magnetic entropy changes on the value of $(\partial M/\partial T)_H$ has been clearly indicated in eqn (8). Therefore, a large magnetic entropy change usually occurs near $T_{\rm C}$, where the magnetization changes swiftly with a variation in temperature. Therefore, the negative sign of the magnetic entropy change confirms the FM character of our sample.⁴⁷ The large values of $-\Delta S_{\rm m}$ for the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ system are due to a secondorder magnetic transition.⁴⁸ The magnitude of $\Delta S_{\rm m}$ increases with an increasing strength of $\mu_0 H$. The maximum value of ΔS decreases from 2.66 J kg⁻¹ K⁻¹ for the La_{0.6}Sr_{0.4}CoO₃ sample prepared by the solid–solid reaction⁴⁹ (2.10 J kg⁻¹ K⁻¹ for La_{0.6}Sr_{0.4}CoO₃ made by the sol–gel method¹⁴) to 1.45 J kg⁻¹ K⁻¹ under an applied magnetic field of 5 T. This indicates that Bi substitution leads to a marginal decrease in the MCE properties with a reduced transition temperature. On the other hand, the obtained value of Bi-doped cobaltite is comparable to those obtained in other cobaltites,^{3,14,50,51} indicating that our sample could be used as a refrigerant material in magnetic cooling devices.

In order to determine the magnetic refrigeration efficiency, only the magnitude of the magnetic entropy is insufficient. The relative cooling power (RCP) is another decisive parameter that can be used to select materials for practical applications. RCP can be calculated by the following expression:

$$RCP = |\Delta S_{m}^{max}| \times \delta T_{FWHM}$$
(10)

where $\delta T_{\rm FWHM}$ is the full width at half maximum of $\Delta S_{\rm M}(T)$. For $\mu_0 H = 5$ T, the RCP is ~115.5 J kg⁻¹, which is of the same order of magnitude as those found in other cobaltites, such as La_{0.6}-Sr_{0.4}CoO₃, La_{0.5}Sr_{0.5}CoO₃, and La_{2/3}Sr_{1/3}CoO₃.^{49,50,52} Evidently, substituting La³⁺ by Bi³⁺, $\Delta S_{\rm M}(T)$ shows a considerably broad



Fig. 8 (a) Temperature and field dependence of the magnetic entropy change for $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$. (b) Universal behavior of the scaled entropy change curves under the influence of several magnetic fields. Inset: the dependencies of the two reference temperatures (T_{r1} and T_{r2}) at various magnetic fields. (c) Scaled magnetic entropy change vs. scaled temperature using the critical exponents.

variation with temperature around $T_{\rm C}$ as compared with the parent sample. Such an effect is beneficial for magnetic refrigeration.

Moreover, we can use the obtained $\Delta S_{\rm m}$ curves to accurately distinguish between the order of the PM–FM phase transition according to a phenomenological universal curve of the field dependence of magnetic entropy change.⁵³ Such a method has been successfully applied to FM perovskites, such as cobaltites^{14,54} and manganites.^{55–58} The universal curve could be plotted by means of the normalized entropy change ($\Delta S_{\rm m} / \Delta S_{\rm m}^{\rm peak}$) and rescaling temperature (θ) as follows:⁵³

$$\theta = \begin{cases} -(T - T_{\rm C})/(T_{\rm rl} - T_{\rm C}); & T \le T_{\rm C} \\ (T - T_{\rm C})/(T_{\rm r2} - T_{\rm C}); & T \le T_{\rm C} \end{cases}$$
(11)

where T_{r1} and T_{r2} denote the temperatures of the two reference points that were selected as those corresponding to $\Delta S_{\rm m}^{\rm peak}/2$. If all the universal curves of $\Delta S_{\rm m}(\theta)$ at various magnetic fields collapse onto a single universal curve, the nature of the secondorder transition would be confirmed. As shown in Fig. 8b, it is evident that all the $(\Delta S_{\rm m}/\Delta S_{\rm m}^{\rm peak})$ values fall onto one universal curve, which is consistent with the analysis based on the Arrott plots. The field dependencies of T_{r1} and T_{r2} for the investigated sample are shown in the inset of Fig. 8b.

Based on the relationship between the critical exponents and the scaled equation of state^{59,60} defined as $\frac{\mu_0 H}{M^{\delta}} = f \left[\frac{\varepsilon}{M^{1/\beta}} \right]$, the $\Delta S_{\rm m}$ value can be described in the form of the following scaling relationship:¹⁷

$$-\Delta S(\mu_0 H, T) = (\mu_0 H)^{1-\alpha/4} g \left[\frac{\varepsilon}{(\mu_0 H)^{1/4}} \right]$$
(12)

where α and Δ are the usual critical exponents, which can be obtained by using $\Delta = \beta + \gamma$ and $\alpha + 2\beta + \gamma = 2$.⁶¹ The latter relation has been successfully applied to several manganite systems.^{62,63} This scaling relation is used to confirm the validity of the estimated critical exponents for La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃. Fig. 8c shows that all the $\Delta S_m(T)$ values fall on a universal curve for several applied magnetic fields. The excellent overlap of the experimental data points confirms that the estimated critical exponents and T_C for the investigated compound are in obedience with the scaling theory.

Based on the MCE data, the dependence of the magnetic entropy change on the external magnetic field is analyzed. $\Delta S_{\rm m}$ can be expressed as a power law of the following form:

$$\Delta S_{\max}(T, \,\mu_0 H) = a(T)(\mu_0 H)^{n(T,H)}$$
(13)

where "*a*" depends on the temperature and exponent "*n*" depends, in general, on both the temperature and field. Fig. 9a shows the temperature dependencies of the exponents a (*T*) and *n*(*T*), which were determined by using eqn (13) from the $\Delta S_{\rm m}$ values at several magnetic fields. From Fig. 9a, it is evident that the value of a (*T*) increases with the temperature, reaching the value of ≈ 0.3 at 210 K. This value is very low as compared to those observed in manganite systems.^{63,64} The value of *n* reaches the minimum of n = 0.989 at $T_{\rm C} = 210$ K.



Fig. 9 (a) Temperature dependence of exponent *n*. Inset: parameter a vs. temperature. (b) Local exponent *n* at several magnetic fields for the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ compound. Inset: θ dependence of the local exponent *n*.

Basically, the MFT predicts that for materials with SOPT, the n(T) curve exhibits three regimes: well below $T_{\rm C}$ (n = 1), well above $T_{\rm C}$ (n = 2), and at $T_{\rm C}$ (n = 2/3, which is related to the critical exponents of the transition).⁶⁵ The exponent "*n*" depends on both temperature and field and can be locally estimated using the following formula:⁶⁶

$$n(T,\mu_0 H) = \frac{\mathrm{d}\,\ln(|\Delta S|)}{\mathrm{d}\,\ln(\mu_0 H)} \tag{14}$$

From the curves of $n(T, \mu_0 H)$ shown in Fig. 9b for the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ compound, it is evident that all the curves exhibit the minimum value of n at $T_{\rm C}$, which is different from the MFT value of n = 2/3. In addition, we observed that the n values are unstable under varying temperature T and field $\mu_0 H$. The minima of the curves with changes in $T_{\rm C}$ with the applied magnetic field range within 0.861–1.021. This behavior is related to the magnetic disorder and FM clusters in the vicinity of $T_{\rm C}$.^{14,67,68} A similar behavior has been previously reported in other perovskites.^{36,63,69,70} In order to verify the collapse or

breakdown of $n(T, \mu_0 H)$ curves under the influence of different applied fields, we first arbitrarily selected the reference temperatures (T_r) as those that have $n(T_r) = 1.5$ (ref. 55) and constructed $n(\theta, \mu_0 H)$ as a function of the rescaled temperature θ , which is, in turn, obtained as follows:

$$\theta = (T - T_{\rm C})/(T_{\rm r} - T_{\rm C})$$
 (15)

From the inset of Fig. 9b, it is evident that all the $n(\theta, \mu_0 H)$ values collapse onto a single universal curve, revealing a universal behavior in La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃.

Using the MCE data, we calculated the specific heat (ΔC_P) of La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ by means of the first derivative of ΔS_m with respect to temperature:

$$-\Delta C_{\rm P}(T,\mu_0 H) = T \frac{\partial (\Delta S_{\rm m}(T,\mu_0 H))}{\partial T}$$
(16)

Fig. 10 shows the $\Delta C_{\rm P}$ value of the compound *vs.* temperature under different magnetic fields. Evidently, the $\Delta C_{\rm P}$ curves represent the alternative changes from negative to positive around $T_{\rm C}$ with a negative value below $T_{\rm C}$ and a positive value above $T_{\rm C}$, which can be attributed to the FM–PM transition. This behavior has also been observed in other FM systems.^{56,71–73} The sum of the two parts is the magnetic contribution to the total of $\Delta C_{\rm P}$, which has an impact on the heating or cooling power of the magnetic cooling devices.⁷⁴ $\Delta C_{\rm P}$ has the advantage of delivering values necessary to select a refrigerant material, which can simplify the design of a magnetic refrigerator.

The $\Delta C_{\rm P}$ values induced by the applied magnetic fields can be plotted onto a universal curve by means of the critical exponents. The scaling method is a result of the scaling hypothesis for FM materials near their magnetic transitions. The scaling of $\Delta C_{\rm P}$ changes are plotted in terms of $\frac{-\Delta C_{\rm P}(\mu_0 H, T)}{(\mu_0 H)^{1-\alpha/4}}$ vs. $\frac{\varepsilon}{(\mu_0 H)^{1/4}}$, as shown in the inset of Fig. 10.



Fig. 10 ΔC_p for the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ system. Inset: normalized heat capacity change as a function of the rescaled temperature for all the magnetic fields.

The worthwhile overlap of the data points obviously suggests that the obtained exponents (β and γ) and $T_{\rm C}$ for the La_{0.55}-Bi_{0.05}Sr_{0.4}CoO₃ sample are in agreement with the scaling hypothesis at various magnetic fields.

Moreover, the obtained magnetic entropy change is used to deduce the spontaneous magnetization in the $La_{0.55}Bi_{0.05}Sr_{0.4}$ -CoO₃ sample. According to the MFT and relationship between the magnetic entropy (*S*) and magnetization (*M*), *S*(σ) can be expressed as follows:^{75,76}

$$S(\sigma) = -Nk_{\rm B} \left[\ln(2J+1) - \ln\left(\frac{\sinh\left(\frac{2J+1}{2J}B_{\rm J}^{-1}(\sigma)\right)}{\sinh\left(\frac{1}{2J}B_{\rm J}^{-1}(\sigma)\right)}\right) + B_{\rm J}^{-1}(\sigma)\sigma \right]$$

$$(17)$$

where *M* is the magnetization, *N* is the number of spins, *J* is the electron spin number, $\sigma = M/g\mu_{\rm B}JN$ is the reduced magnetization, $k_{\rm B}$ is the Boltzmann constant, and $B_{\rm J}$ is the Brillouin function. For small *M* values, ΔS is proportional to M^2 :⁷⁵

$$-S(\sigma) = \frac{3}{2} \frac{J}{J+1} N k_{\rm B} \sigma^2 + \mathcal{O}(\sigma^4)$$
(18)

Furthermore, it should be noted that the compound exhibits spontaneous magnetization below $T_{\rm C}$ (FM state), and consequently, the $\sigma = 0$ state is certainly not obtained. By considering only the first term of eqn (18), $\Delta S_{\rm m}$ may be expressed as

$$-S(\sigma) = \frac{3}{2} \frac{J}{J+1} N k_{\rm B} \left(\sigma^2 + \sigma_{\rm Spon}^2\right)$$
(19)

The latter equation indicates that $\Delta S_m vs. M^2$ plots show a linear variation with a constant slope in the FM region. At



Fig. 11 Spontaneous magnetization of La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ determined from the extrapolation of $-\Delta S_m$ vs. M^2 curves and from the mean-field results. Inset: $-\Delta S_m$ vs. M^2 curves. The dashed lines are linear fits to the data.

different temperatures, all the curves exhibit a horizontal drift from the origin corresponding to a value of $M_{\rm spon}^2(T)$. For the PM region, the $\Delta S_{\rm m} vs. M^2$ plots start at a null *M* value.⁷⁷ Fig. 11 shows the $M_{\rm sp}(T)$ data obtained from the $\Delta S_{\rm m} vs. M^2$ curves by the intersection of the linearly extrapolated curve with the M^2 axis (inset, Fig. 11). The linear behavior of $-\Delta S_{\rm m} vs. M^2$ confirmed the validity of the linear expansion of eqn (19). In the same figure, we show a comparison between the estimated $M_{\rm sp}(T)$ values obtained from the isothermal $(-\Delta S_{\rm m}) vs. M^2$ plots and those obtained from the Arrott plots $(\mu_0 H vs. M^2)$. The worthwhile agreement between the aforementioned methods confirms the validity of this process in order to determine the $M_{\rm sp}$ value using a mean-field analysis of $\Delta S_{\rm m}$ in the La_{0.55}-Bi_{0.05}Sr_{0.4}CoO₃ system. The magnetic behavior of our sample is effectively described by the classical MFT.

Finally, the investigation of the scaling hypotheses of the thermomagnetic properties of the $La_{0.55}Bi_{0.05}Sr_{0.4}CoO_3$ sample offer the opportunity of using the universal curve in the investigations of novel FM materials on various applied functionalities. Such methods present a simple screening procedure of the performance of FM compounds, simple way to extrapolate results to magnetic fields or temperatures not available in the laboratories, remake the impact of non-saturating conditions, reduce experimental noise, or eliminate the effects of minority magnetic phases.

5. Conclusion

In summary, we conducted an in-depth investigation on magnetic, critical behavior, and MCE effect on La0.55Bi0.05- $Sr_{0.4}CoO_3$ cobaltite synthesized *via* the solid-state reaction. The XRD analysis shows that the sample exhibits a rhombohedral structure with the $R\bar{3}c$ space group. The magnetic properties reveal that our sample undergoes a FM-PM second-order magnetic transition, which can be confirmed from the Arrott curves and universal curves of magnetic entropy changes. The critical behavior of the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ cobaltite is studied by means of various techniques and validated by using the scaling theory and Widom scaling relation. The obtained critical exponents are close to the theoretical prediction of the mean-field model values, which implies that long-range interactions dominate the critical behavior in La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃. Moreover, the experimental magnetic entropy changes, specific heat capacity changes, and local exponents n obtained for several magnetic fields collapse onto a universal curve, confirming the universal behavior of the MCE properties in this oxide. The estimated spontaneous magnetization value extracted through the analysis of the magnetic entropy change $(-\Delta S_m)$ vs. M^2) is consistent with that extracted through the classical extrapolation of the Arrott plots ($\mu_0 H/M \nu s. M^2$). Consequently, the magnetic entropy change is a valid approach to determine the spontaneous magnetization of the La_{0.55}Bi_{0.05}Sr_{0.4}CoO₃ compound.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This study was supported by the Tunisian Ministry of Higher Education and Scientific Research and the Neel Institute.

References

- 1 E. Vera, B. Alcántar-Vázquez, Y. Duan and H. Pfeiffer, *RSC Adv.*, 2016, **6**(3), 2162–2170.
- 2 W. He, G. Zhang, X. Zhang, J. Ji, G. Li and X. Zhao, *Appl. Energy*, 2015, 143, 1–25.
- 3 I. G. Deac and A. Vladescu, *J. Magn. Magn. Mater.*, 2014, **365**, 1–7.
- 4 V. G. Bhide, D. S. Rajoria, G. R. Rao and C. N. R. Rao, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1972, **6**, 1021–1032.
- 5 P. M. Raccah and J. B. Goodenough, *Phys. Rev.*, 1967, 155, 932-943.
- 6 N. Menyuk, K. Dwight and P. M. Raccah, J. Phys. Chem. Solids, 1967, 28, 549–556.
- 7 K. Asai, O. Yokokura, M. Suzuki, T. Naka, T. Matsumoto, H. Takahashi, N. Môri and K. Kohn, *J. Phys. Soc. Jpn.*, 1997, 66, 967–970.
- 8 J. Mira, J. Rivas, M. Vázquez, J. M. García-Beneytez, J. Arcas,
 R. D. Sánchez and M. A. Señarís-Rodríguez, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **59**, 123–126.
- 9 X. G. Luo, H. Li, X. H. Chen, Y. M. Xiong, G. Wu, G. Y. Wang,
 C. H. Wang, W. J. Miao and X. Li, *Chem. Mater.*, 2006, 18, 1029–1035.
- 10 R. von Helmolt, J. Wecker, B. Holzapfel, L. Schultz and K. Samwer, *Phys. Rev. Lett.*, 1993, 71, 2331–2333.
- 11 M. H. Phan and S. C. Yu, J. Magn. Magn. Mater., 2007, 308, 325-340.
- 12 G. Briceño, H. Chang, X. Sun, P. G. Schultz and X.-D. Xiang, *Science*, 1995, **270**, 273–275.
- V. Golovanov, L. Mihaly and A. R. Moodenbaugh, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, 53, 8207–8210.
- 14 F. Saadaoui, R. M'nassri, H. Omrani, M. Koubaa, N. C. Boudjada and A. Cheikhrouhou, *RSC Adv.*, 2016, 6(56), 50968–50977.
- 15 J. Wu and C. Leighton, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2003, **67**, 174408.
- 16 N. Khan, A. Midya, K. Mydeen, P. Mandal, A. Loid and D. Prabhakaran, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, 82, 064422.
- 17 V. Franco, J. S. Blázquez and A. Conde, *J. Appl. Phys.*, 2008, 103, 07B316.
- 18 H. Gencer, S. Atalay, H. I. Adiguzel and V. S. Kolat, *Phys. B*, 2005, **357**, 326–333.
- 19 R. Li, Z. Qu, J. Fang, X. Yu, L. Zhang and Y. Zhang, *Solid State Commun.*, 2010, **150**, 389–392.
- 20 S. Atalay, V. S. Kolat, H. Gencer and H. I. Adiguzel, J. Magn. Magn. Mater., 2006, 305, 452–456.
- 21 S. Zemni, M. Baazaoui, J. Dhahri, H. Vincent and M. Oumezzine, *Mater. Lett.*, 2009, **63**, 489–491.
- 22 J. H. Kuo, H. U. Anderson and D. M. Sparlin, *J. Solid State Chem.*, 1989, **83**(1), 52–60.

- 23 H. Ben Khlifa, R. M'nassri, W. Cheikhrouhou-Koubaa,
 E. K. Hlil and A. Cheikhrouhou, *Ceram. Int.*, 2017, 43(2), 1853–1861.
- 24 A. K. Pramanik and A. Banerjee, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2009, **79**, 214426.
- 25 M. E. Fisher, Rep. Prog. Phys., 1967, 30, 615-730.
- 26 T. A. Ho, P. T. Long, N. V. Quang, S. L. Cho and S. C. Yu, J. Magn. Magn. Mater., 2019, 477, 396–403.
- 27 H. M. Rietveld, J. Appl. Crystallogr., 1969, 2, 65-71.
- 28 T. Roisnel and J. Rodriguez-Carvajal, *Computer Program FULLPROF*, LLB-LCSIM, May 2003.
- 29 R. D. Shannon and C. T. Prewitt, Acta Crystallogr., Sect. B: Struct. Crystallogr. Cryst. Chem., 1969, 25, 925–946.
- 30 R. M'nassri, J. Supercond. Novel Magn., 2014, 27, 1787-1794.
- 31 R. P. Borges, F. Ott, R. M. Thomas, V. Skumryev, J. M. D. Coey, J. I. Arnaudas and L. Ranno, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1999, **60**, 12847–12851.
- 32 S. Choura-Maatar, R. M'nassri, W. Cheikhrouhou-Koubaa, M. Koubaa, A. Cheikhrouhou and E. K. Hlil, *RSC Adv.*, 2017, 7(79), 50347–50357.
- 33 R. M'nassri, N. C. Boudjada and A. Cheikhrouhou, J. Alloys Compd., 2015, 626, 20–28.
- 34 S. Mahjoub, M. Baazaoui, R. M'nassri, E. K. Hlil and M. Oumezzin, J. Alloys Compd., 2016, 680, 381–387.
- 35 I. Panneer Muthuselvam and R. N. Bhowmik, J. Alloys Compd., 2012, 511, 22–30.
- 36 A. Selmi, R. M'nassri, W. Cheikhrouhou-Koubaa, N. Chniba Boudjada and A. Cheikhrouhou, J. Alloys Compd., 2015, 619, 627–633.
- 37 S. K. Srivastava and S. Ravi, *J. Magn. Magn. Mater.*, 2009, **321**, 4072–4080.
- 38 A. Arrott, Phys. Rev., 1957, 108, 1394-1396.
- 39 S. Mukherjee, P. Raychaudhuri and A. K. Nigam, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2000, **61**, 8651–8653.
- 40 N. Menyuk, P. M. Raccah and K. Dwight, *Phys. Rev.*, 1968, 166, 510–513.
- 41 A. Arrot and J. E. Noakes, Phys. Rev. Lett., 1967, 19, 786–789.
- 42 J. Fan, L. Ling, B. Hong, L. Zhang, L. Pi and Y. Zhang, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, **81**, 144426.
- 43 J. S. Kouvel and M. E. Fisher, *Phys. Rev.*, 1964, **136**, A1626–A1632.
- 44 M. E. Fisher, S. Ma and B. G. Nickel, *Phys. Rev. Lett.*, 1972, **29**, 917–920.
- 45 H. E. Stanley, *Introduction to Phase Transitions and Critical Phenomena*, Oxford University Press, New York, 1971.
- 46 V. K. Pecharsky and K. A. Gschneidner Jr., J. Magn. Magn. Mater., 1999, 200, 44–56.
- 47 M. H. Phan, N. A. Frey, M. Angst, J. de Groot, B. C. Sales,
 D. G. Mandrus and H. Srikanth, *Solid State Commun.*, 2010, 150, 341–345.
- 48 J. Shen, B. Gao, Q.-Y. Dong, Y.-X. Li, F.-X. Hu, J.-R. Sun and B.-G. Shen, J. Phys. D: Appl. Phys., 2008, 41, 245005.
- 49 P. T. Long, T. V. Manh, T. A. Ho, V. Dongquoc, P. Zhang and S. C. Yu, *Ceram. Int.*, 2018, 44, 15542–15549.
- 50 R. Tetean, I. G. Deac, E. Burzo and A. Bezergheanu, *J. Magn. Magn. Mater.*, 2008, **320**, e179–e182.

- 51 T. A. Ho, T. D. Thanh, T. O. Ho, Q. T. Tran, T. L. Phan and S. C. Yu, *IEEE Trans. Magn.*, 2014, **50**(11), 1–4.
- 52 S. Naas, N. Abassi and C. Boudaya, J. Mater. Sci.: Mater. Electron., 2017, 28, 17985–17992.
- 53 C. M. Bonilla, J. Herrero-Albillos, F. Bartolomé, L. M. García, M. Parra-Borderías and V. Franco, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, **81**, 224424.
- 54 F. Saadaoui, R. M'nassri, A. Mleiki, M. Koubaa, N. ChnibaBoudjada and A. Cheikhrouhou, J. Mater. Sci.: Mater. Electron., 2017, 28, 15500–15511.
- 55 R. M'nassri, A. Selmi, N. C. Boudjada and A. Cheikhrouhou, J. Therm. Anal. Calorim., 2017, 129, 53–64.
- 56 R. M'nassri and A. Cheikhrouhou, J. Korean Phys. Soc., 2014, 64, 879–885.
- 57 R. M'nassri and A. Cheikhrouhou, J. Supercond. Novel Magn., 2014, 27, 1463–1468.
- 58 M. Mansouri, H. Omrani, R. M'nassri, W. Cheikhrouhou-Koubaa and A. Cheikhrouhou, J. Mater. Sci.: Mater. Electron., 2018, 29, 14239–14247.
- 59 B. Widom, J. Chem. Phys., 1965, 43, 3898-3905.
- 60 R. B. Griffiths, Phys. Rev., 1967, 158, 176-187.
- 61 A. Hankey and H. E. Stanley, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1972, **6**, 3515–3542.
- 62 S. Tarhouni, R. M'nassri, A. Mleiki, W. Cheikhrouhou-Koubaa, A. Cheikhrouhou and E. K. Hlil, *RSC Adv.*, 2018, 8, 18294–18307.
- 63 R. M'nassri, N. Chniba Boudjada and A. Cheikhrouhou, J. Alloys Compd., 2015, 640, 183–192.
- 64 A. Rostamnejadi, M. Venkatesan, P. Kameli, H. Salamati and J. M. D. Coey, *J. Magn. Magn. Mater.*, 2011, 323, 2214–2218.
- 65 H. Oesterreicher and F. T. Parker, J. Appl. Phys., 1984, 55, 4334–4338.
- 66 V. Franco, J. S. Blazquez, B. Ingale and A. Conde, *Annu. Rev. Mater. Res.*, 2012, **42**, 305–342.
- 67 T.-L. Phan, T. A. Ho, T. V. Manh, N. T. Dang, C. U. Jung,
 B. W. Lee and T. D. Thanh, *J. Appl. Phys.*, 2015, **118**, 143902.
- 68 V. Franco, J. S. Blázquez and A. Conde, *Appl. Phys. Lett.*, 2006, 100, 064307.
- 69 T.-L. Phan, P. Zhang, T. D. Thanh and S. C. Yu, *J. Appl. Phys.*, 2014, **115**, 17A912.
- 70 A. Sakka, R. M'nassri, N. ChnibaBoudjada, M. Ommezzine and A. Cheikhrouhou, *Appl. Phys. A: Mater. Sci. Process.*, 2016, **122**, 603.
- 71 M. Foldeaki, R. Chahine and T. K. Bose, *J. Appl. Phys.*, 1995, 77, 3528–3537.
- 72 H. Yang, Y. H. Zhu, T. Xian and J. L. Jiang, J. Alloys Compd., 2013, 555, 150–155.
- 73 R. M'nassri and A. Cheikhrouhou, *J. Supercond. Novel Magn.*, 2014, 27(4), 1059–1064.
- 74 X. X. Zhang, G. H. Wen, F. W. Wang, W. H. Wang, C. H. Yu and G. H. Wu, *Appl. Phys. Lett.*, 2000, 77, 3072–3074.
- 75 A. M. Tishin and Y. I. Spichin, *The Magnetocaloric Effect and its Applications*, IOP Publishing, London, 2nd edn, 2003.
- 76 J. S. Amaral, N. J. O. Silva and V. S. Amaral, J. Magn. Magn. Mater., 2010, 322, 1569–1571.
- 77 J. C. Debnath, A. M. Strydom, P. Shamba, J. L. Wang and S. X. Dou, *J. Appl. Phys.*, 2013, **113**, 233903.