PCCP



CORRECTION

View Article Online



Cite this: Phys. Chem. Chem. Phys., 2020, 22, 10368

Correction: Micro-spectroscopy of HKUST-1 metal-organic framework crystals loaded with tetracyanoguinodimethane: effects of water on host-guest chemistry and electrical conductivity

Miguel Rivera-Torrente, Matthias Filez, Christian Schneider, Daniel Rivera-Torrente, Matthias Filez, Christian Schneider, Daniel Rivera-Torrente, Matthias Filez, Christian Schneider, Daniel Rivera-Torrente, Matthias Filez, Matthias Filez, Daniel Rivera-Torrente, Matthias Filez, Matthias Filez, Matthias Filez, Matthias Filez, Matthias Filez, Matthias Filez, Matthia Ewout C. van der Feltz, a Konrad Wolkersdörfer, Dereje H. Taffa, C Michael Wark, C Roland A. Fischerb and Bert M. Weckhuysen*a

DOI: 10.1039/d0cp90080j

rsc.li/pccp

Correction for 'Micro-spectroscopy of HKUST-1 metal-organic framework crystals loaded with tetracyanoquinodimethane: effects of water on host-guest chemistry and electrical conductivity' by Miguel Rivera-Torrente et al., Phys. Chem. Chem. Phys., 2019, 21, 25678-25689.

Following the publication of our article it came to our attention that a detail of the experimental procedure was overlooked and should be corrected to support the calculations.

In the original article, in the Experimental section in the left column on page 25680, the text reads:

"The objective has a Numerical Aperture (NA) of 0.4, resulting in an 815.5 \times 815.5 μ m² diameter spot size. All measurements were performed with a total 0.44 mW power output (power density: $1.27 \times 10^{-5} \text{ W cm}^{-2}$) in the 1500-2300 cm⁻¹ range."

However, the corrected text in the Experimental section should read as follows:

"The objective has a Numerical Aperture (NA) of 0.4. The calculated theoretical laser spot size is 1.33 µm diameter. All measurements were performed with a total 0.44 mW power output (max. power density: 1.27×10^5 W cm⁻²) in the 1500-2300 cm⁻¹ range."

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

a Inorganic Chemistry and Catalysis, Debye Institute for Nanomaterials Science, Utrecht University, Universiteitsweg 99, 3584 CG Utrecht, The Netherlands. E-mail: b.m.weckhuysen@uu.nl

^b Department of Chemistry, Technische Universität München, Lichtenbergstraße 4, 85748 Garching, Germany

^c Institute of Chemistry, Chemical Technology 1, Carl von Ossietzky Universität Oldenburg, Carl-von-Ossietzky Straße 9-11, 26129 Oldenburg, Germany