Cite this: *RSC Adv.*, 2020, 10, 1828

DOI: 10.1039/c9ra90099c

rsc.li/rsc-advances

Correction: Visible-light photocatalytic performance, recovery and degradation mechanism of ternary magnetic Fe₃O₄/BiOBr/BiOI composite

Jianhui Li, Fan Yang, Quan Zhou, Lijie Wu, Wenying Li, Ruipeng Ren* and Yongkang Lv *

Correction for 'Visible-light photocatalytic performance, recovery and degradation mechanism of ternary magnetic Fe₃O₄/BiOBr/BiOI composite' by Jianhui Li *et al.*, *RSC Adv.*, 2019, 9, 23545–23553.

The authors regret that incorrect insets were shown in Fig. 9b in the original manuscript. An SEM image of the composite before the reaction was shown in the top inset, whereas an image after the reaction should have been shown. The correct figure is shown below.

Fig. 9 (a) Recycling utilization experiments and magnetism of Fe₃O₄/BiOBr/BiOI (0.4 : 3 : 1) composite before and after recycling (inset); (b) XRD patterns and SEM images (inset) of Fe₃O₄/BiOBr/BiOI (0.4 : 3 : 1) composite before and after recycling.

In addition, on page 23548 in the section on Morphology and composition characterization, the molar ratio of Bi : O : Br : I : Fe in the EDS analysis of the composite was incorrectly shown as 19 : 33 : 15 : 48 : 57. Therefore, the sentence beginning "What is more, the quantitative result presents the atomic..." should be corrected as shown below:

What is more, the quantitative result presents the atomic of Bi : O : Br : I : Fe in the ternary magnetic Fe₃O₄/BiOBr/BiOI (0.4 : 3 : 1) composite is 48 : 57 : 33 : 15 : 19, which is in line with theoretical chemometrics ratio of 20 : 28 : 15 : 5 : 6 for Bi : O : Br : I : Fe in Fe₃O₄/BiOBr/BiOI (0.4 : 3 : 1) in view of instrumental error, implying that the mole ratio of Fe₃O₄, BiOBr and BiOI in the ternary magnetic Fe₃O₄/BiOBr/BiOI (0.4 : 3 : 1) composite is 0.4 : 3 : 1.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.