RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2020, 10, 14670

Received 11th February 2020 Accepted 18th March 2020 DOI: 10.1039/d0ra01307b

rsc.li/rsc-advances

Introduction

The design and growth of peanut-like CuS/BiVO₄ composites for photoelectrochemical sensing[†]

Yang Yang,‡^{ab} Junting Liang,‡^a Wenwen Jin,^c Yingyue Li,^c Menghui Xuan,^c Shijie Wang,^c Xiaoqian Sun,^c Chuanliang Chen*^a and Jianhua Zhang^b*^c

In this study, the CuS/BiVO₄-*X* (where *X* represents the mass percentage of CuS associated with CuS/BiVO₄; X = 2%, 5% and 7%) p-n heterostructures were fabricated using a two-step hydrothermal method. The structural and morphological features were ascertained in great detail using several physical characterization processes. According to the results of the photoelectrochemical (PEC) experimental processes, the PEC properties of CuS/BiVO₄-5% were much more obvious as compared to those of pure BiVO₄, CuS and CuS/BiVO₄-*X*. Moreover, the photoluminescence (PL) and UV-vis diffuse reflection spectra (DRS) affirmed that the CuS/BiVO₄-5% demonstrates an excellent capacity for absorbing visible light and low electron recombination rate as compared with the other composites. Accordingly, PEC sensors with CuS/BiVO₄-5% were fabricated for the detection of dopamine (DA) and bisphenol A (BPA) with outstanding selectivity and stability. For DA, it implied a broad linear range from 0.01–10 μ M and 10–120 μ M, and for BPA, the broad linear range was 0.01–90 μ M. Thus, the PEC sensor has significant potential application when it comes to DA and BPA detection.

optical response should be developed.

Bisphenol A (BPA, 2,2'-bis(4-hydroxyphenyl)propane) is a characteristic environmental incretin-disrupting element that can adversely affect multiple systems in humans and cause Parkinson's disease (PD) by inducing oxidative stress and inflammation.¹⁻³ Moreover, the basic principle of treating this disease is to increase the content of dopamine (DA) in the substantia nigra.⁴ Therefore, it is important to adopt a fast and feasible method to detect the levels of DA and BPA.^{5,6}

Many different approaches have been adopted to detect DA and BPA, such as fluorescence capillary electrophoresis, electrochemical and photoelectrochemical (PEC).⁷⁻⁹ To be specific, PEC analysis, with high sensitivity and ideal signal ratio, has drawn significant attention for its high cost-effectiveness, quick response as well as its excellent stability.¹⁰⁻¹² The PEC method requires semiconductor materials with electrical and optical properties.^{13,14} Thus, for ultra-sensitive PEC approaches,

Open Access Article. Published on 14 April 2020. Downloaded on 8/20/2025 4:44:40 PM.

semiconductor materials with easy fabrication and broad

To date, photocatalysts with a bismuth-system have found application in PEC study, including BiVO₄, Bi₂MoO₆, Bi₂WO₆, BiPO4 and so on.15-18 Bismuth-system oxides, which are composed of 6s Bi orbitals and 2p oxygen orbitals, display outstanding electrical and optical characteristics.¹⁹ Moreover, they enjoy several popular strengths, e.g., abundance, low toxicity, and low cost.20 Among them, bismuth vanadate (BiVO₄), an n-type semiconductor, is regarded to be a photocatalyst that is full of potential due to its narrow band gap (2.4 eV),²¹ together with its wide use in photoelectrocatalytic water splitting,²² PEC sensors²³ and PEC CO₂ reduction.²⁴ However, it is not efficient in energy conversion due to the rate of rapid charge recombination.25 The combination of other semiconductor elements and BiVO4 will help to improve the electron transfer efficiency and facilitate electron-hole pair separation, thus enhancing the energy conversion efficiency.26

In recent years, sulfide-based photocatalysts (MoS_2 , WS_2 , $CdS \ et \ al.$) have become the focus of most exploration as they enjoy a relatively narrow band gap as well as a greater range of light absorption.^{27–29} Copper sulfide (CuS), a promising p-type semiconductor, can absorb and utilize ultraviolet (UV) and visible light due to its small band gap (2.1 eV).^{30,31} The heterojunction formed between a p-type and an n-type semiconductor is capable of enhancing the ability to absorb visible light as well as facilitating the separation process of charge carriers.^{32,33} As such, we designed a complex of BiVO₄ and CuS to improve the PEC performance.

^aClinical Bioinformatics Experimental Center, Henan Provincial People's Hospital, People's Hospital of Zhengzhou University, Zhengzhou, Henan, 450003, China. E-mail: henanccl@163.com

^bDepartment of Neurosurgery, Zhumadian Central Hospital, Zhumadian 463000, China

^cMedical Engineering Technology and Data Mining Institute of Zhengzhou University, Zhengzhou, Henan, 450000, China. E-mail: petermails@zzu.edu.cn

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/d0ra01307b

[‡] Co-first author.

Paper

In this paper, we adopted a two-step hydrothermal method and successfully synthesized $CuS/BiVO_4$ heterojunction composites. The PEC activity was assessed by detecting DA and BPA under visible light irradiation. The results demonstrate that the CuS/BiVO_4 composites developed greater PEC efficiency as compared with CuS and BiVO_4, and showed outstanding selectivity, low detection limits and a wide linear range for detecting DA and BPA. According to the results, the sensors with CuS/BiVO_4 have great potential for applications in the practical detection of DA and BPA.

Experimental

Reagents

All reagents were of analytical grade and were used without further purification. Bismuth nitrate pentahydrate (Bi(NO₃)₃- \cdot 5H₂O), ammonium metavanadate (NH₄VO₃), copper nitrate trihydrate (Cu(NO₃)₂ \cdot 3H₂O), sodium thiosulfate pentahydrate $(Na_2S_2O_3 \cdot 5H_2O)$ and ethylene glycol (EG) were purchased from Sinopharm Chemical Reagent Co. Ltd. (https:// www.sinoreagent.com). Dopamine was purchased from Aladdin Chemical Reagent Co. Ltd. (https://www.aladdine.com). Human serum samples were purchased from the People's Hospital of Zhengzhou University, Clinical Bioinformatics Experimental Center.

Preparation of the CuS/BiVO₄ heterojunction

The CuS/BiVO₄ heterojunction was prepared by a two-step hydrothermal method. To synthesize $BiVO_4$, $Bi(NO_3)_3 \cdot 5H_2O_3$ and NH₄VO₃ were dissolved in a mixture solution of EG and hot water. The solution was transferred into a 100 mL Teflon-lined stainless autoclave and kept at 120 °C for 12 h. The prepared BiVO₄ powder was dispersed in distilled water by ultrasonication for 30 min, and appropriate amounts of $Cu(NO_3)_2$ -·3H₂O and Na₂S₂O₃·5H₂O were added successively. After the addition of 10 mL of ethanol to the above solution under stirring, the mixture was transferred to a 50 mL Teflon-lined stainless autoclave and heated at 200 °C for 12 h. Finally, the product was cleaned and then dried at 60 °C. The CuS/BiVO₄ heterojunction composed of different CuS contents was labeled as CuS/BiVO₄-X, where X represents the mass percentage of CuS associated with the CuS/BiVO₄ heterojunction. For comparison, different CuS/BiVO₄ heterojunctions having different mass ratios of CuS (2 wt%, 5 wt% and 7 wt%) were also prepared.

Electrochemical experiments

All electrochemical experimental processes were conducted using a three-electrode system (CHI 660E). Pt wire and a saturated calomel electrode (SCE) played the roles of the counter electrode and reference electrode, respectively. We performed electrochemical impedance spectroscopy (EIS) in the frequency range of 1 to 1 000 000 Hz in 0.1 M phosphate buffer (pH 7.0) produced by mixing the stock solutions of Na₂HPO₄ and NaH₂PO₄. The indium tin oxide (ITO) glass served as the working electrode, a xenon lamp (PLS-SXE 300, 100 mW⁻cm⁻², $\lambda \ge 420$ nm) was utilized as the light source. The ITO electrodes $(10 \times 15 \text{ mm})$ were cleaned separately with ethanol, acetone and water for 5 min. Next, 3 mg catalyst powders were dispersed in a chitosan and ethanol mixed solution (0.5 mL) for the formation of a homogeneous suspension. Subsequently, 20 µL suspensions were coated on ITO electrodes (0.5 cm²).

Characterization

X-ray diffraction (XRD) patterns were obtained using a Bruker D8 Advance diffractometer with Cu K α radiation. The X-ray photoelectron spectra were achieved with the help of an X-ray photoelectron spectroscope (XPS, ESCALAB 250Xi, Al K α microfocus monochromator with variable spot size (30–400 µm and 5 µm step size)). Diffuse reflection spectra (DRS) were obtained for the materials, which were verified using a UV-vis spectrophotometer, with BaSO₄ as the reference. The morphologies of the samples were characterized by scanning electron microscopy (SEM) and transmission electron microscopy (TEM).

Results and discussion

Choice of materials

The phases of all synthetic materials were studied by XRD (Fig. 1A). For pure CuS, the four typical characteristic peaks around 31.78° , 32.85° and 47.94° correspond to (103), (006) and (110) of CuS (JCPDS 06-0464), while the peaks at 18.98° , 28.82° , 30.54° and 47.30° were attributed to the (110), (121), (040) and (042) lattice planes of BiVO₄ (JCPDS No. 14-0688). For CuS/BiVO₄, the positions of the peaks were the same even for a variety of composites, with both CuS and BiVO₄ peaks being clearly identifiable. More importantly, with the increase in CuS, the (110) peak became more and more prominent. All results indicate that we have successfully synthesized CuS/BiVO₄.

In order to conduct further evaluation of the PEC performances of CuS, BiVO₄ and CuS/BiVO₄-*X*, photocurrent densities of all materials were determined under visible light irradiation in 0.1 M PBS as shown in Fig. 1B. The photocurrent densities of all the materials were of the order CuS/BiVO₄-5% > CuS/BiVO₄-7% > CuS/BiVO₄-2% > BiVO₄ > CuS. These results show that CuS can efficiently improve the absorption of visible light and separate electron-hole pairs; excessive CuS will affect the capability of materials in absorbing visible light, thus reducing the PEC of the materials.³⁴

Electrochemical impedance spectroscopy (EIS) was conducted to evaluate the electron transfer kinetics (Fig. 1C). The EIS was performed in 0.1 M PBS, which consisted of extruded semi-circular portions and linear portions. The electron transfer resistance (R_{ct}) was quantified based on the semicircle diameter, and it was ranked as CuS > BiVO₄ > CuS/BiVO₄-2% > CuS/BiVO₄-7% > CuS/BiVO₄-5%. Double-layer capacitance (C_{dl}), which can be obtained from cyclic voltammetry (CV), is directly related to the electrochemical active surface area (A) and the scanning rate ν in a linear relationship ($C_{dl} \propto \nu \times A$).³⁵ Therefore, the values of C_{dl} can be used to indicate A. As shown in Fig. S1,† the C_{dl} values were ranked CuS (0.29 mF cm⁻²) < BiVO₄ (0.58 mF cm⁻²) < CuS/BiVO₄-2% (0.72 mF cm⁻²) < CuS/BiVO₄-



Fig. 1 XRD spectra (A), photocurrent responses (B), and EIS (C) of the CuS, BiVO₄ and CuS/BiVO₄-X composites in 0.1 M PBS.

7% (1.31 mF cm⁻²) < CuS/BiVO₄-5% (1.49 mF cm⁻²). These results are consistent with EIS. All the results indicate that CuS/ BiVO₄-5% has rapid electron transfer capability, the best electrical conductivity and a large electrochemical active area, which makes it a potential active material. Based on the results shown above, CuS/BiVO₄-5% was selected for further investigation.

Physical characterization

SEM, TEM and HRTEM analysis clearly defined the morphology of the pure $BiVO_4$ and $CuS/BiVO_4$ -5% composite. The results are shown in Fig. 2. Pure $BiVO_4$ particles had the shape of a peanut with a smooth surface (Fig. 2A and C). As compared to the pure $BiVO_4$, the surface of $CuS/BiVO_4$ -5% is rough (Fig. 2B and D). The $CuS/BiVO_4$ -5% composite structure was further verified by HRTEM analysis. As shown in Fig. 2E, the lattice fringes of 0.309 and 0.323 nm correspond to the (121) planes of $BiVO_4$ and the (101) planes of CuS, respectively, which suggests the coexistence of $BiVO_4$ and CuS in the composites. Fig. 2F shows the STEM-EDX mapping images of $CuS/BiVO_4$ -5%, which indicates that the Bi, V, O, Cu and S elements in the composite surface are uniformly distributed. The results further show that $CuS/BiVO_4$ -5% is composed of $BiVO_4$ and CuS, which conforms to the XPS analysis.

We studied the absorption properties of BiVO₄, CuS and CuS/ BiVO₄-5% by UV-vis DRS as shown in Fig. 3A. The pure CuS exhibited strong ultraviolet and visible absorption, while the pure BiVO₄ showed the absorption edge at approximately 550 nm. Furthermore, the visible absorption ability of CuS/ BiVO₄ was significantly higher as compared to BiVO₄. All these can be attributed to the inner absorption of CuS. Based on the fundamental idea of electronegativity,³⁶ the band gap energy was calculated using eqn (1):

$$\alpha h\nu = A(\nu h - E_{\rm g})^{n/2} \tag{1}$$

where *n* is the optical transition type, BiVO₄ is a not direct semiconductor and the value of *n* is 4. A is a constant, ν represents the incident light frequency, *h* is Planck's constant, and α is the absorption coefficient. Fig. S2[†] suggests that the *E*_g energy gap of BiVO₄ is 2.52 eV. CuS refers to a direct

semiconductor, so *n* is $1.^{32}$ Accordingly, the band gap of CuS was nearly 2.26 eV. Next, the ability of synthetic materials for separating holes and electrons was studied based on PL spectra. Fig. 3B suggests that CuS/BiVO₄-5% has the lowest intensity as compared with CuS and BiVO₄, suggesting that CuS/BiVO₄-5% has a low electron recombination rate.¹⁶ According to the discussion above, CuS/BiVO₄-5% displayed terrific PEC performance.

Photoelectrochemical sensor

Fig. 4A and B suggests the photocurrent performance of CuS, BiVO₄ and CuS/BiVO₄-5% at 0 V *vs.* SCE with the addition of 1 μ M DA and BPA under visible light excitation in 0.1 M PBS. The photocurrent of all synthetic materials increased with the addition of DA and BPA. Meanwhile, the photocurrent of CuS/ BiVO₄-5% was larger than that of BiVO₄, since the p–n heterostructure improved the PEC efficiency for DA and BPA to a large extent.

To further evaluate the PEC performance of CuS/BiVO₄-5% for DA and BPA, the photocurrent change was ascertained at many different concentrations of DA and BPA. By the respective addition of DA, the photocurrent response increased significantly as shown in Fig. 4C. A linear relationship was found between the concentration of DA and photocurrent (Fig. 4D), and it displays two linear associations based on the sensor of CuS/BiVO₄-5% for DA. From 0.01–10 μ M, the linear regressing equation is $\Delta I = 0.2807 + 0.5622c$ ($R^2 = 0.9918$), ranging from 10 to 120 μ M; the linear association is $\Delta I = 5.1966 + 0.0712c$ ($R^2 = 0.9942$). The detection limit of the sensor is 3.4 nM (S/N = 3).

Experiments for BPA detection were performed in PBS (Fig. 4E and F). On increasing the BPA concentration in PBS, the photocurrent increased and the as-prepared CuS/BiVO₄-5% photoelectrode detected BPA with a linear range from 0.01 μ M to 90 μ M. The linear regressing equation is $\Delta I = 0.7052 + 0.0574c$ ($R^2 = 0.9911$) with a detection limit (S/N = 3) of 7 nM. In Table 1 a comparison is made of CuS/BiVO₄-5% with other DA and BPA sensors in the literature. It is undeniable that the CuS/BiVO₄-5% sensor outperforms the other DA and BPA sensors in several fields.

By monitoring the photocurrent of the repeated photoexcitation over 600 s, the CuS/BiVO₄-5% stability was also checked



Fig. 2 SEM images of BiVO₄ (A) and CuS/BiVO₄-5% (B). TEM images of BiVO₄ (C) and CuS/BiVO₄-5% (D). (E) HR-TEM images of CuS/BiVO₄-5%. (F) STEM-EDX mapping images of CuS/BiVO₄-5%.

(Fig. S3[†]). The response photocurrent of CuS/BiVO₄-5% remained at 95.3% and 95.8% of its initial value towards 1 μ M DA and 1 μ M BPA within 18 days (Fig. 6A and C). XPS of CuS/

BiVO₄-5% before the stability test was also evaluated, as shown in Fig. 5A. For Bi 4f, O 1s, V 2p, Cu 2p and S 2s, the high resolution is shown in Fig. 5B–F. Fig. 5B shows two core peaks of the

1 µm

 (\mathbf{F})

500 nm Cu

500 nm

0

500 nm

Bi



Fig. 3 UV-vis diffuse reflectance spectra (A), and PL spectra (B) of the CuS, BiVO₄ and CuS/BiVO₄-5% composites.



Fig. 4 Photocurrent responses of the CuS, $BiVO_4$ and $CuS/BiVO_4$ -5% composites with and without 1 μ M DA (A) and 1 μ M BPA (B). (C) Photocurrent responses of $CuS/BiVO_4$ -5% toward DA with increasing concentrations of DA. (D) The relevant calibration plots of the DA concentration. (E) Photocurrent responses of $CuS/BiVO_4$ -5% toward BPA with increasing concentrations of BPA. (F) The relevant calibration plots of the BPA concentration in 0.1 M PBS at 0 V vs. SCE as excited by visible light.

Bi 4f XPS spectra situated at 158.8 eV and 164.2 eV. The peaks at 164.2 eV and 158.8 eV are attributed to Bi $4f_{5/2}$ and Bi $4f_{7/2}$ in normal Bi³⁺.³⁷ The two $2p_{3/2}$ (516.5 eV) and $2p_{1/2}$ (523.9 eV) peaks of biological iodine correspond to V⁵⁺ (Fig. 5C).³⁸ The O 1s peak is shown in Fig. 5D, and the O 1s peak at 530.46 eV is due to the lattice oxygen.³⁹ Cu $3p_{1/2}$ at 951.8 eV and Mo $3p_{3/2}$ at 931.9 eV are matched to Cu²⁺ in Fig. 5E.⁴⁰ In Fig. 2F, the 2s peak at around 226.1 eV was attributed to S 2s, which strongly proved how CuS⁴¹ was formed. Fig. S4[†] shows that the XRD and XPS of CuS/BiVO₄-5% has the best stability. The reproducibility of CuS/BiVO₄-5% was tested by detecting 1 μ M DA and BPA using 5 parallel electrodes (Fig. 6B and D), and the photocurrent did not

exhibit any significant variation, indicating its good reproducibility.

The selectivity of the PEC sensor based on CuS/BiVO₄-5% towards DA and BPA is shown in Fig. S5;† the photocurrent responses of interferences can be ignored, implying that CuS/ BiVO₄-5% can selectively and effectively detect DA and BPA. To verify the practical reliability of the DA and BPA sensor that has been prepared, we used lake water containing BPA, and human blood serum containing DA as convincing samples. As shown in Table 2, for DA, the RSD values are less than 4.21%, and the recoveries are 99.80–101.0%. For BPA, the RSD values are less than 3.19%, and the recoveries are 98.00–100.12%. According to

Analyst Linear range (µM) LOD Ref.	Materials	Method
DA 0.1–100 10 nM 42	MoS_2	Fluorescent
DA 0.2–78.7 0.06 μM 4	CuO/CN	Electrochemical
DA 1-70 0.33 µM 43	RGO-ZnO	Electrochemical
DA 0.01–10 3 nM 7	SnSe NSs	PEC
DA 53-80, 85-155 0.3 μM 44	WO ₃	PEC
DA 0.01–10 3.4 nM This work	CuS/BiVO ₄	PEC
10-120		
/phenyl)valeric acid BPA 0.087–3.5 8.7 nM 45	4,4-Bis(4-hydroxyphenyl)valeric acid	Fluorescence polarization immunoassay
BPA 0.1-28.9 0.047 μM 9	TiO ₂ /Au NTAs	PEC
BPA 0.047–52.1 8.6 nM 46	ZnPc/TiO ₂ NRs	PEC
BPA0.01-907 nMThis work	$CuS/BiVO_4$	PEC
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	KGO-ZhO SnSe NSs WO ₃ CuS/BiVO ₄ 4,4-Bis(4-hydroxyphenyl)valeric acid TiO ₂ /Au NTAs ZnPc/TiO ₂ NRs CuS/BiVO ₄	PEC PEC PEC PEC Fluorescence polarization immunoassay PEC PEC PEC PEC

Table 1 Comparison of different methods for detecting DA and BPA





Fig. 6 Stability and reproducibility tests of the PEC sensor based on CuS/BiVO₄-5% towards DA (A and B) and BPA (C and D).

Table 2 PEC detection of DA and BPA in real samples

Real samples	Added (µM)	Found (µM)	Recovery (%)	RSD (%)
Human blood serum	1.00	1.01	101.00	1.31
(DA)	5.00	4.95	99.90	2.24
	20.00	19.96	99.80	3.11
	50.00	49.92	99.84	3.52
	100.00	99.96	99.96	4.21
Lake water (BPA)	1.00	0.98	98.00	1.01
	5.00	4.98	99.60	1.95
	20.00	20.02	100.10	2.33
	40.00	40.05	100.12	2.71
	80.00	80.09	100.11	3.19

the mentioned results, the sensor based on CuS/BiVO₄-5% is reliable for the detection of DA and BPA in actual samples.

Proposed mechanism of PEC

To explore the mechanism of PEC sensors based on CuS/BiVO₄, the valence band energy ($E_{\rm VB}$) and the conduction band energy ($E_{\rm CB}$) of BiVO₄ and CuS were investigated with the aid of the following equation:⁴⁷

$$E_{\rm VB} = X - E_{\rm e} + 0.5E_{\rm g}$$
 (2)

$$E_{\rm CB} = E_{\rm VB} - E_{\rm g} \tag{3}$$

The value of E_e was almost 4.5 eV, indicating the energy of free the electrons at the scale of hydrogen. *X* represents the semiconductor electronegativity, and *X* was 6.04 eV and 5.29 eV for BiVO₄ and CuS, respectively. The VB edges of BiVO₄ and CuS were +2.8 eV and +1.92 eV, respectively. Besides, we determined the CB edge potentials of BiVO₄ and CuS as +0.28 eV and -0.34 eV, respectively. As shown in Fig. 7, the migrating process of photogenerated electrons occurs from the CB of CuS to the CB of BiVO₄ and the holes are transferred from the VB of BiVO₄ to the VB of CuS due to the dynamic principle, which could help divide the photogenerated electron-hole pairs to effectively utilize the oxidization of holes. By the same token, the holes will be utilized to oxidize DA and BPA.



Fig. 7 PEC mechanism of CuS/BiVO₄ for the detection of DA and BPA.

Conclusion

In summary, we have designed a $CuS/BiVO_4$ composite *via* a two-step hydrothermal method. $CuS/BiVO_4$ -5% exhibited superior PEC properties for DA and BPA as compared with pure BiVO₄, CuS and CuS/BiVO₄-*X*. The CuS content had an impact on the PEC efficiency of CuS/BiVO₄. The PEC efficiency and stability of CuS/BiVO₄ can be attributed to the appropriate CuS content as well as the influential electron-hole pair separation. The study indicates that the sensor based on CuS/BiVO₄-5% is sure to possess great application prospects for DA and BPA PEC detection.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the Natural Science Foundation of Henan Province (Grant No.: 162300410290) and the National Key Research and Development Program of China (Grant No.: 2016YFC1303204).

References

- T. D. P. Allsop, R. Neal, C. Wang, D. A. Nagel, A. V. Hine, P. Culverhouse, J. D. A. Castañón, D. J. Webb, S. Scarano and M. Minunni, *Biosens. Bioelectron.*, 2019, **135**, 102–110.
- 2 M. K. Li, L. Y. Hu, C. G. Niu, D. W. Huang and G. M. Zeng, Sens. Actuators, B, 2018, 266, 805–811.
- 3 A. S. Alnaimat, M. C. B. Alonso and P. B. Barrera, *Microchem. J.*, 2019, **147**, 598–604.
- 4 S. Reddy, B. E. K. Swamy and H. Jayadevappa, *Electrochim. Acta*, 2012, **61**, 78–86.
- 5 M. Annalakshmi, P. Balasubramanian, S. M. Chen, T. W. Chen and P. H. Lin, *Inorg. Chem. Front.*, 2019, 6, 2024–2034.
- 6 L. A. Goulart, S. A. Alves and L. H. Mascaro, *Electroanal. Chem.*, 2019, **839**, 123–133.
- 7 X. Hun, S. S. Wang, S. Y. Mei, H. Q. Qin, H. Zhang and H. L. Luo, *Microchim. Acta*, 2017, **184**, 3333–3338.

- 8 Y. H. Song, J. J. Han, L. J. Xu, L. F. Miao, C. W. Peng and L. Wang, *Sens. Actuators, B*, 2019, **298**, 126949.
- 9 L. S. Hu, C. C. Fong, X. M. Zhang, L. L. Chan, P. K. S. Lam, P. K. Chu, K. Y. Wong and M. S. Yang, *Environ. Sci. Technol.*, 2016, **50**, 4430–4438.
- 10 A. M. Ahmed, F. Mohamed, A. M. Ashraf, M. Shaban, A. A. P. Khan and A. M. Asiri, *Chemosphere*, 2019, 124554.
- 11 Y. Liu, Y. S. Chang, Y. J. Hsu, B. J. Hwang and C. H. Hsueh, Fabrication of WO₃ photoanode decorated with Au nanoplates and its enhanced photoelectrochemical properties, *Electrochim. Acta*, 2019, 134674.
- 12 X. L. Tu, M. Li, Y. J. Su, G. L. Yin, J. Lu and D. N. He, Selftemplated growth of CuInS2 nanosheet arrays for photoelectrochemical water splitting, *J. Alloys Compd.*, 2019, 151794.
- 13 L. F. Wang, W. Q. Zhu, W. B. Lu, L. N. Shi, R. Wang, R. X. Pang, Y. Y. Cao, F. Wang and X. H. Xu, One-step electrodeposition of AuNi nanodendrite arrays as photoelectrochemical biosensors for glucose and hydrogen peroxide detection, *Biosens. Bioelectron.*, 2019, 111577.
- 14 F. G. Cai, X. Chen, L. X. Qiu, L. L. Jiang, S. D. Ma, Q. Y. Zhang and Y. Zhao, Controlled hydrothermal synthesis and photoelectrochemical properties of Bi₂S₃/TiO₂ nanotube arrays heterostructure, *J. Alloys Compd.*, 2019, 151770.
- 15 H. L. Tong, Y. Jiang, Q. Zhang, W. C. Jiang, K. L. Wang, X. X. Luo, Z. Lin and L. X. Xia, Boosting Photoelectrochemical Water Oxidation with Cobalt Phosphide Nanosheets on Porous BiVO₄, ACS Sustainable Chem. Eng., 2019, 7, 769–778.
- 16 W. J. He, Y. J. Sun, G. M. Jiang, Y. H. Li, X. M. Zhang, Y. X. Zhang, Y. Zhou and F. Dong, Defective Bi₄MoO₉/Bi metal core/shell heterostructure: Enhanced visible light photocatalysis and reaction mechanism, *Appl. Catal., B*, 2018, 239, 619–627.
- 17 F. Rong, Q. Y. Wang, Q. F. Lu, L. B. Yao and M. Z. Wei, Rational Fabrication of Hierarchical Z-Scheme WO₃/ Bi₂WO₆ Nanotubes for Superior Photoelectrocatalytic Reaction, *ChemistrySelect*, 2019, 4, 2676–2684.
- 18 J. Qian, Z. T. Yang, C. Q. Wang, K. Wang, Q. Liu, D. Jiang, Y. T. Yan and K. Wang, One-pot synthesis of BiPO4 functionalized reduced graphene oxide with enhanced photoelectrochemical performance for selective and sensitive detection of chlorpyrifos, *J. Mater. Chem. A*, 2015, 3, 13671–13678.
- 19 J. L. Lv, J. F. Zhang, J. Liu, Z. Li, K. Dai and C. H. Liang, Bi SPR-promoted Z-scheme Bi₂MoO₆/CdS-diethylenetriamine composite with effectively enhanced visible light photocatalytic hydrogen evolution activity and stability, *ACS Sustainable Chem. Eng.*, 2017, 6, 696–706.
- 20 F. Yang, X. M. Zhu, J. Z. Fang, D. D. Chen, W. H. Feng and Z. Q. Fang, One step solvothermal synthesis of $Bi/BiPO_4/Bi_2WO_6$ heterostructure with oxygen vacancies for enhanced photocatalytic performance, *Ceram. Int.*, 2018, 44, 6918–6925.
- 21 H. L. Li, Y. J. Chen, W. Zhou, H. Y. Jiang, H. Liu, X. Chen and T. G. Hui, WO₃/BiVO₄/BiOCl porous nanosheet composites

from a biomass template for photocatalytic organic pollutant degradation, *J. Alloys Compd.*, 2019, **802**, 76–85.

- 22 H. D. She, M. Jiang, P. F. Yue, J. W. Huang, L. Wang, J. Z. Lie, G. Q. Zhu and G. Z. Wang, Metal (Ni^{2+}/Co^{2+}) sulfides modified BiVO₄ for effective improvement in photoelectrochemical water splitting, *J. Colloid Interface Sci.*, 2019, **549**, 80–88.
- 23 L. X. Sun, J. H. Sun, N. Han, D. K. Liao, S. L. Bai, X. J. Yang, R. X. Luo, D. Q. Li and A. F. Chen, rGO decorated W doped BiVO₄ novel material for sensing detection of trimethylamine, *Sens. Actuators, B*, 2019, **298**, 126749.
- 24 K. J. Li, J. Han, Y. Yang, T. Wang, Y. Q. Feng, S. Ajmal, Y. Y. Liu, Y. Deng, M. A. Tahir and L. W. Zhang, Simultaneous SO₂ removal and CO₂ reduction in a nano-BiVO₄|Cu-In nanoalloy photoelectrochemical cell, *Chem. Eng. J.*, 2019, 355, 11–21.
- 25 F. Li, W. Zhao and D. Y. C. Leung, Enhanced photoelectrocatalytic hydrogen production *via* Bi/BiVO₄ photoanode under visible light irradiation, *Appl. Catal., B*, 2019, **258**, 117954.
- 26 H. C. He, Y. Zhou, G. L. Ke, X. H. Zhong, M. J. Yang, L. Bian, K. L. Lv and F. Q. Dong, Improved Surface Charge Transfer in MoO₃/BiVO₄ Heterojunction Film for Photoelectrochemical Water Oxidation, *Electrochim. Acta*, 2017, 257, 181–191.
- 27 T. Kosmala, D. Mosconi, G. Giallongo, G. A. Rizzi and G. Granozzi, Highly Efficient MoS₂/Ag₂S/Ag Photoelectrocatalyst Obtained from a Recycled DVD Surface, *ACS Sustainable Chem. Eng.*, 2018, **66**, 7818–7825.
- 28 C. E. Chieh, C. Jian, C. Wan, Z. J. Huei, H. J. Hsien, L. K. Chan, H. B. Cheng and H. Y. Sheng, Microwaveassisted synthesis of TiO₂/WS₂ heterojunctions with enhanced photocatalytic activity, *J. Taiwan Inst. Chem. Eng.*, 2018, **91**, 489–498.
- 29 H. Wang, H. L. Ye, B. H. Zhang, F. Q. Zhao and B. Z. Zeng, Electrostatic Interaction Mechanism Based Synthesis of Z-Scheme BiOI-CdS Photocatalyst for Selective and Sensitive Detection of Cu²⁺, *J. Mater. Chem. A*, 2017, **5**, 10599.
- 30 Y. F. Tang, Y. Chai, X. Q. Liu, L. Li, L. W. Yang, P. P. Liu, Y. M. Zhou, H. X. Ju and Y. Z. Cheng, A photoelectrochemical aptasensor constructed with core-shell CuS-TiO2 heterostructure for detection of microcystin-LR, *Biosens. Bioelectron.*, 2018, **117**, 224–231.
- 31 S. F. Jia, X. Y. Li, B. P. Zhang, J. Yang, S. W. Zhang, S. Li and Z. T. Zhang, TiO₂/CuS heterostructure nanowire array photoanodes toward water oxidation: The role of CuS, *Appl. Surf. Sci.*, 2019, **463**, 829–837.
- 32 C. Lai, M. M. Zhang, B. S. Li, D. L. Huang, G. M. Zeng, L. Qin, X. G. Liu, H. Yi, M. Cheng, L. Li, Z. Chen and L. Chen, Fabrication of CuS/BiVO₄ (040) binary heterojunction photocatalysts with enhanced photocatalytic activity for Ciprofloxacin degradation and mechanism insight, *Chem. Eng. J.*, 2019, **358**, 891–902.
- 33 J. Cao, B. Y. Xu, H. L. Lin and S. F. Chen, Highly improved visible light photocatalytic activity of BiPO₄ through fabricating a novel p–n heterojunction BiOI/BiPO₄ nanocomposite, *Chem. Eng. J.*, 2013, **228**, 482–488.

- 34 P. C. Yan, D. S. Jiang, H. N. Li, M. Cheng, L. Xu, J. C. Qian, J. Bao, J. X. Xia and H. M. Li, Exploitation of a photoelectrochemical sensing platform for catechol quantitative determination using BiPO₄ nanocrystals/BiOI heterojunction, *Anal. Chim. Acta*, 2018, **1042**, 11–19.
- 35 J. D. Benck, Z. Chen, L. Y. Kuritzky, A. J. Forman and T. F. Jaramillo, Amorphous Molybdenum Sulfide Catalysts for Electrochemical Hydrogen Production: Insights into the Origin of Their Catalytic Activity, *ACS Catal.*, 2012, 2, 1916–1923.
- 36 W. S. Kuo and P. H. Ho, Solar photocatalytic decolorization of dyes in solution with TiO2 film, *Dyes Pigm.*, 2006, **71**, 212–217.
- 37 X. Zhang, X. B. Wang, L. M. Wang, W. K. Wang, L. L. Long,
 W. W. Li and H. Q. Yu, Synthesis of a highly efficient
 BiOCl single-crystal nanodisk photocatalyst with exposing
 {001} Facets, ACS Appl. Mater. Interfaces, 2014, 6, 7766–7772.
- 38 Z. H. Wei, Y. F. Wang, Y. Y. Li, L. Zhang, H. C. Yao and Z. J. Li, Enhanced photocatalytic CO_2 reduction activity of Z-scheme CdS/BiVO₄ nanocomposite with thinner BiVO₄ nanosheets, *J. CO2 Util.*, 2018, **28**, 15–25.
- 39 X. L. Luo, Z. Y. Chen, S. Y. Yang and Y. H. Xu, Two-step hydrothermal synthesis of peanut-shaped molybdenum diselenide/bismuth vanadate (MoSe₂/BiVO₄) with enhanced visible-light photocatalytic activity for the degradation of glyphosate, *J. Colloid Interface Sci.*, 2018, **532**, 456–463.
- 40 Y. P. Bhoi and B. G. Mishra, Photocatalytic degradation of alachlor using type-II CuS/BiFeO₃ heterojunctions as novel photocatalyst under visible light irradiation, *Chem. Eng. J.*, 2018, **344**, 391–401.

- 41 Y. P. Bhoi, C. Behera, D. Majhi, S. M. Equeenuddin and B. G. Mishra, Visible light-assisted photocatalytic mineralization of diuron pesticide using novel type II CuS/ Bi₂W₂O₉ heterojunctions with a hierarchical microspherical structure, *New J. Chem.*, 2018, 42, 281–292.
- 42 X. N. Liu, W. T. Zhang, L. J. Huang, N. Hu, W. Liu, Y. N. Liu, S. H. Li, C. Y. Yang, Y. R. Suo and J. L. Wang, Fluorometric determination of dopamine by using molybdenum disulfide quantum dots, *Microchim. Acta*, 2018, **185**, 234.
- 43 X. Zhang, Y. Zhang and L. Ma, One-pot facile fabrication of graphene-zinc oxide composite and its enhanced sensitivity for simultaneous electrochemical detection of ascorbic acid, dopamine and uric acid, *Sens. Actuators, B*, 2016, 227, 488–496.
- 44 S. A. Alves, L. L. Soares, L. A. Goulart and L. H. Mascaro, Solvent effects on the photoelectrochemical properties of WO₃ and its application as dopamine sensor, *J. Solid State Electrochem.*, 2016, **9**, 2461–2470.
- 45 X. L. Wu, L. B. Wang, W. Ma, Y. Y. Zhu, L. G. Xu, H. Kuang and C. L. Xu, A Simple, Sensitive, Rapid and Specific Detection Method for Bisphenol A based on Fluorescence Polarization Immunoassay, *Immunol. Invest.*, 2012, **41**, 38– 50.
- 46 Z. Z. Fan, L. F. Fan, S. M. Shuang and C. Dong, Highly sensitive photoelectrochemical sensing of bisphenol A based on zinc phthalocyanine/TiO₂ nanorod arrays, *Talanta*, 2018, **189**, 16–23.
- 47 M. Y. Li, Y. L. Huang, S. Q. Wang, C. Q. Feng, H. M. Wu and H. Mei, Visible light driven photoelectrochemical sensor for chromium(VI) BiOI microspheres decorated with metallic bismuth, *Microchim. Acta*, 2019, **186**, 345.