


 Cite this: *RSC Adv.*, 2020, 10, 11499

# Phase junction enhanced photocatalytic activity of Ga<sub>2</sub>O<sub>3</sub> nanorod arrays on flexible glass fiber fabric†

 Hanlin Sun,<sup>a</sup> Liying Zhang,<sup>a</sup> Jingyan Yu,<sup>a</sup> Shunli Wang,<sup>\*a</sup> Daoyou Guo,<sup>ID<sup>a</sup></sup> Chaorong Li,<sup>a</sup> Fengmin Wu,<sup>a</sup> Aiping Liu,<sup>a</sup> Peigang Li<sup>b</sup> and Weihua Tang<sup>ID<sup>b</sup></sup>

Ga<sub>2</sub>O<sub>3</sub> nanostructures hold great potential applications in photocatalytic fields due to their stability, high efficiency and environmental friendliness. The construction of phase junction has been proved to be one of the most effective strategies for enhancing Ga<sub>2</sub>O<sub>3</sub> photocatalytic activity. However, the influence of the formation process at the interface of the phase junction on the photocatalytic activity of Ga<sub>2</sub>O<sub>3</sub> nanostructures is far less well understood. In this work, for the first time, large-area Ga<sub>2</sub>O<sub>3</sub> nanorod arrays (NRAs) with controllable  $\alpha/\beta$  phase junction were prepared *in situ* on a flexible glass fiber fabric by a facile and environmentally friendly three-step method. The  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs exhibit an ultra-high photocatalytic degradation rate of 97% during Ultraviolet (UV) irradiation for 60 min, which is attributed to a unique phase junction promoting efficient charge separation. However, the photocatalytic activity of  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs is not evident in the early phase transition, possibly due to the presence of defects acting as charge recombination centers.

Received 15th February 2020

Accepted 10th March 2020

DOI: 10.1039/d0ra01461c

[rsc.li/rsc-advances](http://rsc.li/rsc-advances)

## 1. Introduction

With the continuous development of the social economy, environmental pollution has become an increasingly serious problem, prompting humans to continuously explore new solutions.<sup>1–6</sup> Photocatalytic reaction, as a simple, efficient and cost-effective method, has promising applications in the removal of environmental pollutants and attracted wide attention.<sup>7–13</sup> Recently, various metal oxides with d<sup>10</sup> (In<sup>3+</sup>, Ga<sup>3+</sup>, Ge<sup>4+</sup>, Sn<sup>4+</sup>) configurations have been reported as effective photocatalysts for photodegradation of various organic pollutants.<sup>14,15</sup> Ga<sub>2</sub>O<sub>3</sub> is a typical representative among them.<sup>16</sup>

With a wide bandgap (4.2–4.9 eV) and excellent physical and chemical properties, Ga<sub>2</sub>O<sub>3</sub> is recognized as one of the most promising semiconductors of this century.<sup>17–22</sup> It has extensively been applied to power devices,<sup>23–25</sup> solar-blind ultraviolet (UV) photodetectors,<sup>26–29</sup> gas sensors,<sup>30</sup> solar cells<sup>31</sup> and photocatalysis.<sup>32,33</sup> For photocatalysis applications, related studies claim that Ga<sub>2</sub>O<sub>3</sub> can theoretically exhibit better and more stable photocatalytic activity than commercial TiO<sub>2</sub> and realize the degradation of refractory pollutants.<sup>34,35</sup> This is attributed to the extraordinary redox capability of photogenerated electron–

hole pairs.<sup>1,36,37</sup> Furthermore, Ga<sub>2</sub>O<sub>3</sub> is also widely accepted as an environmentally friendly material with low cost and high chemical stability.<sup>38</sup> Many methods have been investigated to further improve the photocatalytic activity of Ga<sub>2</sub>O<sub>3</sub>, including morphology controlling, doping, surface modification and semiconductor coupling.<sup>39–44</sup> Nitu Syed *et al.* reported a two-step method for the synthesis of porous  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> nanosheets from liquid metal gallium, explaining that the excellent photocatalytic activity of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> originated from the narrowed bandgap caused by trap states.<sup>1</sup> Han *et al.* revealed that the modification of *in situ* Ag nanoparticles can effectively improve the photocatalytic property of Ga<sub>2</sub>O<sub>3</sub> for hydrogen evolution.<sup>39</sup> Zhang *et al.* incorporated solvothermally synthesized Ga<sub>2</sub>O<sub>3</sub> nanoparticles into liquid metal/metal oxide frameworks to form enhanced photocatalytic systems.<sup>41</sup> Xu *et al.* fabricated two-dimensional TiO<sub>2</sub>-Ga<sub>2</sub>O<sub>3</sub> p–n heterostructures, demonstrating the contribution of heterostructures in enhancing photocatalytic activity.<sup>45</sup>

Furthermore, the construction of appropriate phase junction structure in Ga<sub>2</sub>O<sub>3</sub> can also significantly enhance photocatalytic activity.<sup>46–48</sup> Liu *et al.* demonstrated that the mesopores and heterojunction in the mixed-phase Ga<sub>2</sub>O<sub>3</sub> are responsible for enhancing photocatalytic activity.<sup>7</sup> However, the influence of the formation process at the interface of the phase junction on the photocatalytic activity of Ga<sub>2</sub>O<sub>3</sub> nanostructures has not been fully understood. For example, phase transformation is a process from the surface to the bulk, and different thicknesses of phase interface may result in various photocatalytic activities.<sup>49</sup> Therefore, an in-depth understanding of junction-related issues will aid in the design and preparation of efficient Ga<sub>2</sub>O<sub>3</sub>

<sup>a</sup>Key Laboratory of Optical Field Manipulation of Zhejiang Province, Center for Optoelectronics Materials and Devices, Department of Physics, Zhejiang Sci-Tech University Hangzhou, 310018, China. E-mail: shwang@zstu.edu.cn

<sup>b</sup>State Key Laboratory of Information Photonics and Optical Communications, Information Functional Materials and Devices, School of Science, Beijing University of Posts and Telecommunications, Beijing 100876, China

† Electronic supplementary information (ESI) available. See DOI: 10.1039/d0ra01461c



nanostructured photocatalysts. On the other hand, almost all of the reported  $\text{Ga}_2\text{O}_3$  nanostructured photocatalysts are currently applied in suspension systems. The disadvantages of photocatalysts, such as agglomeration, inadequate illumination and difficulty in recovery, restrict their large-scale practical applications. Glass fiber fabric as a support for *in situ* growth of  $\text{Ga}_2\text{O}_3$  nanostructures is expected to effectively overcome this difficulty.<sup>18</sup> To the best of our knowledge, there are no reports of *in situ* preparation of  $\text{Ga}_2\text{O}_3$  nanostructures on glass fiber fabric for the application of photocatalytic degradation.

Herein, for the first time, we reported a facile and environmentally friendly three-step method for *in situ* preparation of large-area  $\text{Ga}_2\text{O}_3$  nanorod arrays (NRAs) with controllable  $\alpha/\beta$  phase junction on a flexible glass fiber fabric. The as-prepared  $\alpha/\beta$ - $\text{Ga}_2\text{O}_3$  phase junction NRAs exhibited excellent photocatalytic activity for the degradation of Rhodamine B (RhB) aqueous solution. In addition, the mechanism of photocatalytic activity enhancement was discussed and compared with related literature.

## 2. Experimental

### 2.1. Materials

Glass fiber fabric, model TS-BXB, specification  $0.06\text{ mm} \times 1.20\text{ m}$ , obtained from Hangzhou Gaojing Fine Chemical Industry Co., Ltd. The glass fiber fabrics were cut into a size of approximately  $20 \times 20\text{ mm}^2$  as the substrate of  $\text{Ga}_2\text{O}_3$  NRAs. Rhodamine B (RhB), gallium nitrate hydrate ( $\text{Ga}(\text{NO}_3)_3 \cdot n\text{H}_2\text{O}$ ) were purchased from Shanghai Saen Chemical Technology Co., Ltd. Fluorine doped tin oxide (FTO) conductive glass ( $14\ \Omega\ \text{cm}^{-2}$ , size:  $10 \times 20 \times 2.2\text{ mm}^3$ ) was made by Japan Nippon Sheet Glass Co., Ltd. Sodium sulphate ( $\text{Na}_2\text{SO}_4$ ) was got from Tianjin Yongda Chemical Regent Co., Ltd. All chemicals are analytical grade.

### 2.2. Sample preparation

The preparation of  $\text{Ga}_2\text{O}_3$  NRAs involves the following three steps. In the first step, a  $\text{SnO}_2$  thin film was fabricated by radio frequency

magnetron sputtering on the surface of the cleaned glass fiber fabric, which was used as a growth seed layer of  $\text{Ga}_2\text{O}_3$ . The growth temperature and Ar gas pressure were fixed at  $550\text{ }^\circ\text{C}$  and  $0.8\text{ Pa}$ , respectively. The second step is to prepare  $\text{GaOOH}$  nanorod precursor by hydrothermal method. Here,  $0.20\text{ g}$  of  $\text{Ga}(\text{NO}_3)_3 \cdot n\text{H}_2\text{O}$  was dissolved in  $30\text{ mL}$  of DI water to prepare a growth solution. Then the substrates glass fiber fabric completed in the first step was placed in the growth solution and transferred separately into a  $50\text{ mL}$  Teflon-lined stainless steel autoclave for hydrothermal treatment at  $150\text{ }^\circ\text{C}$  for  $12\text{ h}$ . After the solution was naturally cooled down to room temperature, the precipitates were filtered and washed with DI water, then dried in air at  $80\text{ }^\circ\text{C}$  for  $2\text{ h}$  to obtain  $\text{GaOOH}$  NRAs precursors. The last step, the as-prepared precursors were annealed at  $400\text{ }^\circ\text{C}$  for  $4\text{ h}$  in air to obtain  $\alpha$ - $\text{Ga}_2\text{O}_3$  NRAs. The detailed synthesis is schematically demonstrated in Fig. 1. Further, other samples were obtained by annealing  $\alpha$ - $\text{Ga}_2\text{O}_3$  NRAs in air at  $700\text{ }^\circ\text{C}$  for different times from  $20\text{ min}$  to  $120\text{ min}$ .

### 2.3. Characterization

The crystal structure of samples was analyzed by a Bruker D8 DISCOVER X-ray diffractometer (XRD). UV-Raman spectra were recorded on a Jobin-Yvon T64000 triple-stage spectrograph with spectral resolution of  $2\text{ cm}^{-1}$ . The thermal behavior of the  $\text{GaOOH}$  nanorod was investigated by thermal gravimetric analyzer (Pyris1 TGA). For the morphological and microstructural analysis, a Hitachi S-4800 field-emission scanning electron microscope (SEM) equipped and a JEOL JEM-2100 transmission electron microscopy (TEM) were utilized. The ultraviolet-visible (UV-vis) absorption spectra were taken using a Hitachi U-3900 UV-vis spectrophotometer. The chemical composition of samples was characterized by a Thermo Scientific K-Alpha X-ray photoelectron spectroscopy (XPS).

### 2.4. Photocatalytic experiments

In this experiment, the glass fiber fabric with  $\text{Ga}_2\text{O}_3$  NRAs were dropped into  $50\text{ mL}$  of RhB aqueous solution ( $2 \times 10^{-5}\text{ M}$ ) and




Fig. 1 Schematic illustration of the preparation process of  $\alpha$ - $\text{Ga}_2\text{O}_3$  NRAs.



placed in the dark for 30 min to ensure adsorption-desorption equilibrium was reached. Then irradiated reaction solution with a 10 W UV light lamp ( $\lambda = 254$  nm). The light intensity of the UV lamp was always maintained at  $1.0 \text{ mW cm}^{-2}$ . During the process, about 3 mL of solution was withdrawn from the reaction system at a given time interval (10 min) for absorbance testing by UV-vis spectrophotometry.

### 2.5. Mott-Schottky measurement

For Mott-Schottky measurements, 5 mg  $\text{Ga}_2\text{O}_3$  NRAs powder was scraped from the glass fiber fabric and dispersed in 2 mL of absolute ethanol, followed by the addition of 20  $\mu\text{L}$  of 0.5% Nafion. After the mixed solution was sonicated for 1 h, 0.5 mL was transferred onto a FTO conductive glass. The resulting electrodes were dried in air and further heated at  $150^\circ\text{C}$  for 1 h under a  $\text{N}_2$  gas flow. The electrochemical measurements were performed in a three-electrode configuration system using a CHI 760E electrochemical workstation (CH Instruments, China), including the as-prepared FTO working electrodes (with an active area of  $1.0 \text{ cm}^2$ ), Pt foil as the counter electrode and saturated calomel electrode (SCE) as the reference electrode. 0.5 M  $\text{Na}_2\text{SO}_4$  aqueous solution was used as the electrolyte.

## 3. Results and discussion

Fig. 2(a) shows the XRD patterns of as-synthesized GaOOH and  $\alpha\text{-Ga}_2\text{O}_3$  NRAs. All the peaks can be indexed to the orthorhombic GaOOH phase (JCPDS no. 06-0180) except the diffraction peak of the  $\text{SnO}_2$  seed layer. After annealing GaOOH at  $400^\circ\text{C}$  for 4 h, the observed diffraction peaks occur at new locations, indicating that the GaOOH is completely converted into  $\alpha\text{-Ga}_2\text{O}_3$  of the corundum structure (JCPDS no. 06-0503).<sup>50</sup> The phase transition of  $\alpha\text{-Ga}_2\text{O}_3$  at  $700^\circ\text{C}$  for various times was also analyzed by XRD, and the corresponding results are shown in Fig. 2(b). With  $\alpha\text{-Ga}_2\text{O}_3$  annealed at  $700^\circ\text{C}$  for 30 min, a diffraction peak corresponding to the (111) plane attributed to monoclinic  $\beta\text{-Ga}_2\text{O}_3$  is detected, and it becomes stronger with the further increase of annealing time.  $\text{Ga}_2\text{O}_3$  with different phase structures can be obtained during annealing for 30–90 min. No diffraction peak assigned to  $\alpha\text{-Ga}_2\text{O}_3$  is observed through annealing for 120 min, suggesting that the  $\alpha\text{-Ga}_2\text{O}_3$  is totally transformed into  $\beta\text{-Ga}_2\text{O}_3$  at this point.

UV Raman spectroscopy was also used to monitor the  $\alpha$  to  $\beta$  phase transformation of  $\text{Ga}_2\text{O}_3$ . As shown in Fig. 2(c), it is worth noting that the typical characteristic Raman bands of  $\beta\text{-Ga}_2\text{O}_3$  at  $198 \text{ cm}^{-1}$  and  $414 \text{ cm}^{-1}$  can be clearly observed after annealing  $\alpha\text{-Ga}_2\text{O}_3$  at  $700^\circ\text{C}$  for 20 min, in addition to the




Fig. 2 (a) XRD patterns of as-synthesized GaOOH and  $\alpha\text{-Ga}_2\text{O}_3$  NRAs. (b) XRD patterns and (c) UV Raman spectra of  $\alpha\text{-Ga}_2\text{O}_3$  NRAs annealed in air at  $700^\circ\text{C}$  for various times. (d) TG/DTG curve of the as-prepared GaOOH NRAs precursor by heating from room temperature to  $800^\circ\text{C}$  in air.






Fig. 3 (a) SEM images of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs. High-magnification SEM images of (b)  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs, (c) Ga<sub>2</sub>O<sub>3</sub>-60 NRAs, (d)  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NRAs. (e) Low and high resolution TEM images of (f).

existing Raman bands of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub>, indicating the formation of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>. However, only Raman bands at 215 cm<sup>-1</sup> and 283 cm<sup>-1</sup> attributed to  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> are detected with annealing time to 60 min, and both disappeared at 90 min. The result is unsynchronized with that revealed by the XRD patterns, which can be attributed to the strong sensitivity of UV Raman spectroscopy to the surface region, and XRD mainly reflects the bulk information of materials.<sup>47</sup> Based on the above results, we suggest that the samples annealed for 20–90 min are  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction. In the following sections, the  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs annealed at 700 °C for various time will be labeled as Ga<sub>2</sub>O<sub>3</sub>-20 (annealed for 20 min), Ga<sub>2</sub>O<sub>3</sub>-30 (annealed for 30 min), Ga<sub>2</sub>O<sub>3</sub>-40 (annealed for 40 min), Ga<sub>2</sub>O<sub>3</sub>-60 (annealed for 60 min), Ga<sub>2</sub>O<sub>3</sub>-90 (annealed for 90 min) and  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NRAs (annealed for 120 min), respectively.

The TG/DTG curve of the as-prepared GaOOH NRAs precursor by heating from room temperature to 800 °C in air atmosphere is shown in Fig. 2(d). A major weight loss of 11.2% can be noticed in the temperature range of approximately 260–480 °C, with the fastest weight loss rate occurring at 438 °C, which is attributed to transformation of GaOOH into  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> by thermal dehydration. A weak weight loss of 2% is also noted at the range of 500–630 °C, indicating the conversion of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> to  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>. With further prolonged heating up to 800 °C, there is no weight loss.

A typical SEM image of as-synthesized  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs, as presented in Fig. 3(a), which reveals the uniform and dense growth of the sample on each fiber rod. High-magnification SEM images of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs and other Ga<sub>2</sub>O<sub>3</sub> NRAs obtained by annealing (Ga<sub>2</sub>O<sub>3</sub>-60 and  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>) are also shown in Fig. 3(b–d), respectively. Further revealing that the diameter of all nanorods ranged from 100 to 400 nm and the tips are all diamond-shaped. The annealing process has not significantly

changed the morphology of Ga<sub>2</sub>O<sub>3</sub> NRAs.<sup>51</sup> Fig. 3(e and f) shows the low and high resolution TEM images of the Ga<sub>2</sub>O<sub>3</sub>-60 NRAs. Different lattice fringes are observed in here. The lattice-spacing value of 0.249 nm matches the (110) planes of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub>, while the lattice-spacing values of 0.242 nm and 0.255 nm are ascribed to the (−310) and (111) planes of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>. This result clearly demonstrates the formation of  $\alpha/\beta$  heterophase junctions in Ga<sub>2</sub>O<sub>3</sub>-60 NRAs, supporting the previous analysis of XRD and UV Raman spectroscopy.

The photocatalytic activities of Ga<sub>2</sub>O<sub>3</sub> NRAs were evaluated by the degradation of RhB aqueous solution under UV light irradiation. A typical UV-vis absorption spectrum of RhB aqueous solution during photocatalytic degradation process in the presence of the Ga<sub>2</sub>O<sub>3</sub> NRAs is shown in Fig. S1.† The decrease of the characteristic peak at 554 nm during illumination suggests RhB decomposition.<sup>1,43</sup> Fig. 4(a) and S2.† reveals the comparison of photocatalytic activities of different Ga<sub>2</sub>O<sub>3</sub> NRAs. Among them, the Ga<sub>2</sub>O<sub>3</sub>-60 NRAs exhibits the best photocatalytic with a degradation rate of 97%, which can be attributed to the  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction promoting the separation of photogenerated electrons and holes.<sup>47</sup> Furthermore, the photocatalytic degradation process of these Ga<sub>2</sub>O<sub>3</sub> NRAs were fitted using the first-order kinetic curve according to the Langmuir–Hinshelwood model.<sup>32,52</sup> As shown in Fig. 4(b), the value of the reaction rate constant (*K*) are estimated to be 0.0232, 0.0301, 0.0265, 0.0245, 0.0589, 0.0546 and 0.0418 min<sup>-1</sup>, corresponding to the  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub>, Ga<sub>2</sub>O<sub>3</sub>-20, Ga<sub>2</sub>O<sub>3</sub>-30, Ga<sub>2</sub>O<sub>3</sub>-40, Ga<sub>2</sub>O<sub>3</sub>-60, Ga<sub>2</sub>O<sub>3</sub>-90 and  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NRAs, respectively.

Generally, a series of photogenerated reactive species, such as h<sup>+</sup>, ·O<sub>2</sub><sup>-</sup> and ·OH, are involved in the photocatalytic process.<sup>4,53</sup> To reveal the main reactive species responsible for the degradation of RhB solution by the Ga<sub>2</sub>O<sub>3</sub>-60 NRAs, radical trapping experiments were performed by adding EDTA






Fig. 4 (a) Photocatalytic degradation of RhB in the presence of different  $\text{Ga}_2\text{O}_3$  NRAs and (b) corresponding kinetic linear simulation curves. (c) Effect of trapping agents on the photocatalytic degradation of RhB over the  $\text{Ga}_2\text{O}_3$ -60 NRAs. (d) Photocatalytic stability test of the  $\text{Ga}_2\text{O}_3$ -60 NRAs in recycling reactions.

(ethylenediamine tetraacetic acid,  $\text{h}^+$  trapping agents), IPA (isopropyl alcohol,  $\cdot\text{OH}$  trapping agents) and BQ (benzoquinone,  $\cdot\text{O}_2^-$  trapping agents), respectively. As shown in Fig. 4(c), the photocatalytic activity of the  $\text{Ga}_2\text{O}_3$ -60 NRAs is affected slightly with the addition of EDTA, indicating that  $\text{h}^+$  is not the main factor in this system. In contrast, the introduction of IPA or BQ greatly suppressed the photocatalytic activity of the  $\text{Ga}_2\text{O}_3$ -60 NRAs, indicating that  $\cdot\text{OH}$  and  $\cdot\text{O}_2^-$  acted as dominating reactive species in the reaction system.

Moreover, the cycling stability of the  $\text{Ga}_2\text{O}_3$ -60 NRAs was evaluated by conducting five consecutive cycle degradation experiments. As shown in Fig. 4(d), the degradation ratio of RhB is not obviously reduced during the repeated experiments, indicating the remarkable stability of the  $\text{Ga}_2\text{O}_3$ -60 NRAs. XRD patterns (Fig. S3<sup>†</sup>) also indicates that no structural difference can be observed between the  $\text{Ga}_2\text{O}_3$ -60 NRAs before and after photocatalytic degradation of RhB solution.

For the proposed photocatalytic degradation mechanism of the system, the band structures of  $\alpha$ - $\text{Ga}_2\text{O}_3$  and  $\beta$ - $\text{Ga}_2\text{O}_3$  were characterized by Mott-Schottky measurements and XPS. As shown in Fig. 5(a and b), the flat band potential of  $\alpha$ - $\text{Ga}_2\text{O}_3$  is calculated to be  $-1.26$  eV (*vs.* SCE), which is more negative than

the  $-0.96$  eV (*vs.* SCE) of  $\beta$ - $\text{Ga}_2\text{O}_3$ , and the valence band potential of  $\beta$ - $\text{Ga}_2\text{O}_3$  is 3.05 eV, which is more positive than the 2.92 eV of  $\alpha$ - $\text{Ga}_2\text{O}_3$ . Further combined with the band gap of  $\text{Ga}_2\text{O}_3$  reported in our previous work,<sup>51</sup> a schematic illustration of photocatalytic reaction process and charge separation transfer of  $\alpha/\beta$ - $\text{Ga}_2\text{O}_3$  phase junction under UV light irradiation is shown in Fig. 5(c). Under UV light irradiation, the internal electric field of the  $\alpha/\beta$ - $\text{Ga}_2\text{O}_3$  phase junction could drive the photogenerated charge transfer, promoting the photogenerated electrons transfer from the  $\alpha$  phase to the  $\beta$  phase, and the photogenerated holes transfer from the  $\beta$  phase to the  $\alpha$  phase. Following that, the photogenerated electrons react with  $\text{O}_2$  to generate  $\cdot\text{O}_2^-$  and the photogenerated holes oxidize  $\text{OH}^-$  to  $\cdot\text{OH}$ , which together involve in RhB degradation. Efficient charge separation inhibits their recombination, resulting in improved photocatalytic degradation performance.<sup>47,49</sup> In addition, it should be mentioned that phase junction can form on both the surface of  $\text{Ga}_2\text{O}_3$  and in the bulk. Although almost no phase junctions were observed on the surface of the  $\text{Ga}_2\text{O}_3$ -60 NRAs, they still function as charge separation centers in the bulk. The separated carriers eventually diffuse to the surface of the sample to participate in the photocatalytic reaction.<sup>4</sup> On the






Fig. 5 (a) Mott–Schottky curves of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs and  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NRAs electrodes measured in 0.5 M Na<sub>2</sub>SO<sub>4</sub> solution. (b) XPS valence band spectra of  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs and  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> NRAs. (c) Schematic illustration of photocatalytic reaction process and charge separation transfer of  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction under UV light irradiation.

other hand, for Ga<sub>2</sub>O<sub>3</sub> as a photocatalytic degradation material, the performance of the  $\beta$  phase is generally better than that of the  $\alpha$  phase,<sup>7,43</sup> which is confirmed in Fig. 4(a) of this research. Therefore, in addition to the efficient charge separation due to the phase junction in the bulk, the excellent photocatalytic activity of the Ga<sub>2</sub>O<sub>3</sub>-60 NRAs is also derived from the inherently high activity of the  $\beta$  surface phase. Interestingly, the Ga<sub>2</sub>O<sub>3</sub>-20,

Ga<sub>2</sub>O<sub>3</sub>-30 and Ga<sub>2</sub>O<sub>3</sub>-40 NRAs did not exhibit excellent photocatalytic activity despite the formation of phase junctions on various surfaces. The phase transformation of Ga<sub>2</sub>O<sub>3</sub> is a surface-preferred process, which is accompanied by the formation of defects.<sup>54</sup> These defects may become the recombination center of photogenerated electron–hole pairs, reducing the number of efficient carriers on the surface.<sup>55</sup> As




Fig. 6 O 1s XPS spectra of (a) Ga<sub>2</sub>O<sub>3</sub>-20 NRAs and (b) Ga<sub>2</sub>O<sub>3</sub>-60 NRAs.



Table 1 Comparison of the photocatalytic activity of a selection of previously reported Ga<sub>2</sub>O<sub>3</sub> related materials and this work

Photocatalyst, concentration (mg L <sup>-1</sup> )	Pollutants, concentration (mol L <sup>-1</sup> )	Light source	Degradation after 60 min	Reference
$\alpha$ -Ga <sub>2</sub> O <sub>3</sub> nanoplates, 90	RhB, $0.45 \times 10^{-5}$	AM 1.5 solar simulator	53%	1
$\alpha$ -Ga <sub>2</sub> O <sub>3</sub> nanoparticles, 400	TC, $5.6 \times 10^{-5}$	30 W UV lamp	85%	5
$\alpha$ -Ga <sub>2</sub> O <sub>3</sub> nanorods, 1000	RhB, $0.84 \times 10^{-5}$	300 W Hg lamp	62%	33
$\beta$ -Ga <sub>2</sub> O <sub>3</sub> nanorods, 1000	RhB, $2 \times 10^{-5}$	150 W xenon lamp	39%	36
$\beta$ -Ga <sub>2</sub> O <sub>3</sub> microspheres, 1000	RhB, $2 \times 10^{-5}$	150 W xenon lamp	60%	37
Ga <sub>2</sub> O <sub>3</sub> sheet, 500	CR, $2.15 \times 10^{-5}$	30 W UV lamp	33%	38
$\beta$ -Ga <sub>2</sub> O <sub>3</sub> nanorods, 1000	RhB, $2 \times 10^{-4}$	1000 W UV lamp	38%	43
TiO <sub>2</sub> -Ga <sub>2</sub> O <sub>3</sub> heterojunctions	MO, $1.8 \times 10^{-5}$	30 W UV lamp	83%	45
$\alpha/\beta$ -Ga <sub>2</sub> O <sub>3</sub> NRAs, 200	RhB, $2 \times 10^{-5}$	10 W UV lamp	97%	This work

a result, the photocatalytic activity of the initially annealed Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs was not satisfactory.

To obtain more insight into the effect of defects on photocatalytic activity, the Ga<sub>2</sub>O<sub>3</sub>-20 NRAs and Ga<sub>2</sub>O<sub>3</sub>-60 NRAs were selected as typical samples for XPS analysis. As shown in Fig. 6, the O 1s spectra could be divided into two peaks: I and II, representing lattice oxygen ions and oxygen ions in the oxygen vacancies region, respectively.<sup>28</sup> The peak ratio (II/I) of the Ga<sub>2</sub>O<sub>3</sub>-20 NRAs is 1/3, which is higher than that of the Ga<sub>2</sub>O<sub>3</sub>-60 NRAs (1/5), indicating the presence of more oxygen vacancies. Obviously, the Ga<sub>2</sub>O<sub>3</sub>-20 NRAs exhibits poor photocatalytic activity due to the existence of abundant oxygen vacancy defects.

The comparison of the photocatalytic degradation activity of  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs in this work and other previously reported Ga<sub>2</sub>O<sub>3</sub> related materials is listed in Table 1. Although the comparison of photocatalytic activity is not absolutely reasonable due to the different light source conditions and pollutants used in each experiment, the photocatalytic activity of  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs in this work is significantly superior to almost all previous reports on Ga<sub>2</sub>O<sub>3</sub> related materials. This method has realized the large-area growth of  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs on the flexible glass fiber fabric and obviously improved its photocatalytic performance, which is of great significance in the future research in the field of photocatalysis.

## 4. Conclusions

In summary, large-area Ga<sub>2</sub>O<sub>3</sub> NRAs with controllable  $\alpha/\beta$  phase junction were firstly prepared *in situ* on a flexible glass fiber fabric by a facile and environmentally friendly three-step method. Photocatalytic degradation experiments showed that the  $\alpha/\beta$ -Ga<sub>2</sub>O<sub>3</sub> phase junction NRAs synthesized by annealing  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> NRAs at 700 °C for 60 min exhibited remarkable performance for RhB, with a degradation rate of 97% in 60 min under UV light. The enhanced photocatalytic activity can be attributed to the unique phase junction promoting efficient charge separation and inhibiting the recombination of photogenerated electron-hole pairs. Additionally, the glass fiber fabric can realize large-area growth of the Ga<sub>2</sub>O<sub>3</sub> NRAs, effectively solve the trouble of difficult recovery and reuse of photocatalysts, as well as the insufficient absorption of light. A facile environmentally

friendly and inexpensive synthesis route will open new avenues for the development of efficient photocatalysts.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was supported by the National Natural Science Foundation of China (No. 61704153, 51572241, 61774019, 51572033), Natural Science Foundation of Zhejiang Province (No. LY20F040005), Zhejiang Public Service Technology Research Program/Analytical Test (LGC19F040001), and Fundamental Research Funds of Zhejiang Sci-Tech University (2019Q061, 2019Q067).

## References

- N. Syed, A. Zavabeti, M. Mohiuddin, B. Zhang, Y. Wang, R. S. Datta, P. Atkin, B. J. Carey, C. Tan, J. van Embden, A. S. R. Chesman, J. Z. Ou, T. Daeneke and K. Kalantar-zadeh, *Adv. Funct. Mater.*, 2017, **27**, 1702295.
- J. Wei, F. Guo, X. Wang, K. Xu, M. Lei, Y. Liang, Y. Zhao and D. Xu, *Adv. Mater.*, 2018, **30**, 1805153.
- W. Zhong, S. Shen, S. Feng, Z. Lin, Z. Wang and B. Fang, *CrystEngComm*, 2018, **20**, 7851–7856.
- Y. Wang, W. Zhang, Z. Wang, Y. Cao, J. Feng, Z. Wang and Y. Ma, *Chin. J. Catal.*, 2018, **39**, 1500–1510.
- J. Liu, W. Lu, Q. Zhong, H. Wu, Y. Li, L. Li and Z. Wang, *J. Colloid Interface Sci.*, 2018, **519**, 255–262.
- X. He, S. Z. Luan, L. Wang, R. Y. Wang, P. Du, Y. Y. Xu, H. J. Yang, Y. G. Wang, K. Huang and M. Lei, *Mater. Lett.*, 2019, **244**, 78–82.
- J. Liu and G. Zhang, *Mater. Res. Bull.*, 2015, **68**, 254–259.
- L. C. Tien, W. T. Chen and C. H. Ho, *J. Am. Ceram. Soc.*, 2011, **94**, 3117–3122.
- Z. Dong, J. Pan, B. Wang, Z. Jiang, C. Zhao, J. Wang, C. Song, Y. Zheng, C. Cui and C. Li, *J. Alloys Compd.*, 2018, **747**, 788–795.
- W. Zhong, Y. Lou, S. Jin, W. Wang and L. Guo, *Sci. Rep.*, 2016, **6**, 23235.



- 11 K. Huang, J. Liu, L. Wang, G. Chang, R. Wang, M. Lei, Y. Wang and Y. He, *Appl. Surf. Sci.*, 2019, **487**, 1145–1151.
- 12 W. Zhong, J. Huang, S. Liang, J. Liu, Y. Li, G. Cai, Y. Jiang and J. Liu, *ACS Energy Lett.*, 2019, **5**, 31–38.
- 13 S. Lin, X. Bai, H. Wang, H. Wang, J. Song, K. Huang, C. Wang, N. Wang, B. Li and M. Lei, *Adv. Mater.*, 2017, **29**, 1703238.
- 14 A. A. Ismail, I. Abdelfattah, M. Faisal and A. Helal, *J. Hazard. Mater.*, 2018, **342**, 519–526.
- 15 W. Zhong, S. Shen, M. He, D. Wang, Z. Wang, Z. Lin, W. Tu and J. Yu, *Appl. Catal., B*, 2019, **258**, 117967.
- 16 Y. Ma, X. Zhao, M. Niu, W. Li, X. Wang, C. Zhai, T. Wang, Y. Tang and X. Dai, *RSC Adv.*, 2017, **7**, 4124–4134.
- 17 A. Kakoria, B. Devi, A. Anand, A. Halder, R. R. Koner and S. Sinha-Ray, *ACS Appl. Nano Mater.*, 2018, **2**, 64–74.
- 18 S. Wang, H. Sun, Z. Wang, X. Zeng, G. Ungar, D. Guo, J. Shen, P. Li, A. Liu, C. Li and W. Tang, *J. Alloys Compd.*, 2019, **787**, 133–139.
- 19 J. Yu, Z. Nie, L. Dong, L. Yuan, D. Li, Y. Huang, L. Zhang, Y. Zhang and R. Jia, *J. Alloys Compd.*, 2019, **798**, 458–466.
- 20 J. Zhang, S. Jiao, Y. Wan, S. Gao, D. Wang and J. Wang, *CrystEngComm*, 2018, **20**, 4329–4335.
- 21 H. Lu, S. Jiao, Y. Nie, S. Liu, S. Gao, D. Wang, J. Wang, L. Li and X. Wang, *J. Alloys Compd.*, 2020, **823**, 153903.
- 22 C. Wu, D. Guo, L. Zhang, P. Li, F. Zhang, C. Tan, S. Wang, A. Liu, F. Wu and W. Tang, *Appl. Phys. Lett.*, 2020, **116**, 072102.
- 23 M. Baldini, Z. Galazka and G. Wagner, *Mater. Sci. Semicond. Process.*, 2018, **78**, 132–146.
- 24 X. Wang, Y. Cui, T. Li, M. Lei, J. Li and Z. Wei, *Adv. Opt. Mater.*, 2018, **7**, 1801274.
- 25 H. Zhang, L. Yuan, R. Jia, X. Tang, J. Hu, Y. Zhang, Y. Zhang and J. Sun, *J. Phys. D: Appl. Phys.*, 2019, **52**, 215104.
- 26 D. Guo, Y. Su, H. Shi, P. Li, N. Zhao, J. Ye, S. Wang, A. Liu, Z. Chen, C. Li and W. Tang, *ACS Nano*, 2018, **12**, 12827–12835.
- 27 L. Dong, J. Yu, R. Jia, J. Hu, Y. Zhang and J. Sun, *Opt. Mater. Express*, 2019, **9**, 1191.
- 28 D. Guo, H. Liu, P. Li, Z. Wu, S. Wang, C. Cui, C. Li and W. Tang, *ACS Appl. Mater. Interfaces*, 2017, **9**, 1619–1628.
- 29 J. Zhang, S. Jiao, D. Wang, S. Ni, S. Gao and J. Wang, *J. Mater. Chem. C*, 2019, **7**, 6867–6871.
- 30 H. J. Lin, H. Gao and P. X. Gao, *Appl. Phys. Lett.*, 2017, **110**, 043101.
- 31 A. Pérez-Tomás, E. Chikoidze, Y. Dumont, M. R. Jennings, S. O. Russell, P. Vales-Castro, G. Catalan, M. Lira-Cantú, C. Ton-That, F. H. Teherani, V. E. Sandana, P. Bove and D. J. Rogers, *Mater. Today Energy*, 2019, **14**, 100350.
- 32 S. Jin, W. Lu, P. C. Stanish and P. V. Radovanovic, *Chem. Phys. Lett.*, 2018, **706**, 509–514.
- 33 D. Li, X. Duan, Q. Qin, H. Fan and W. Zheng, *J. Mater. Chem. A*, 2013, **1**, 12417.
- 34 X. Zhang, H. Huang, Y. Zhang, D. Liu, N. Tong, J. Lin, L. Chen, Z. Zhang and X. Wang, *ACS Omega*, 2018, **3**, 14469–14476.
- 35 H. Liu, Z. Wang, H. Li, X. Zhang, X. Qin, Y. Dai, P. Wang, Y. Liu and B. Huang, *RSC Adv.*, 2018, **8**, 14328–14334.
- 36 K. Girija, S. Thirumalairajan, A. K. Patra, D. Mangalaraj, N. Ponpandian and C. Viswanathan, *Semicond. Sci. Technol.*, 2013, **28**, 035015.
- 37 K. Girija, S. Thirumalairajan, V. R. Mastelaro and D. Mangalaraj, *J. Mater. Chem. A*, 2015, **3**, 2617–2627.
- 38 M. Bagheri and A. R. Mahjoub, *RSC Adv.*, 2016, **6**, 87555–87563.
- 39 C. Han, W. Mao, K. Bao, H. Xie, Z. Jia and L. Ye, *Int. J. Hydrogen Energy*, 2017, **42**, 19913–19919.
- 40 S. Hong, C. K. Rhee and Y. Sohn, *J. Alloys Compd.*, 2019, **774**, 11–17.
- 41 W. Zhang, B. S. Naidu, J. Z. Ou, A. P. O'Mullane, A. F. Chrimes, B. J. Carey, Y. Wang, S. Y. Tang, V. Sivan, A. Mitchell, S. K. Bhargava and K. Kalantar-Zadeh, *ACS Appl. Mater. Interfaces*, 2015, **7**, 1943–1948.
- 42 S. Kikkawa, K. Teramura, H. Asakura, S. Hosokawa and T. Tanaka, *J. Phys. Chem. C*, 2018, **122**, 21132–21139.
- 43 L. S. Reddy, Y. H. Ko and J. S. Yu, *Nanoscale Res. Lett.*, 2015, **10**, 364.
- 44 S. Luan, L. Dong, X. Ma and R. Jia, *J. Alloys Compd.*, 2020, **812**, 152026.
- 45 H. Xu, F. Han, C. Xia, S. Wang, R. K. Ramachandran, C. Detavernier, M. Wei, L. Lin and S. Zhuiykov, *Nanoscale Res. Lett.*, 2019, **14**, 163.
- 46 X. Wang and C. Li, *J. Phys. Chem. C*, 2018, **122**, 21083–21096.
- 47 X. Wang, Q. Xu, M. Li, S. Shen, X. Wang, Y. Wang, Z. Feng, J. Shi, H. Han and C. Li, *Angew. Chem., Int. Ed.*, 2012, **51**, 13089–13092.
- 48 D. Guo, K. Chen, S. Wang, F. Wu, A. Liu, C. Li, P. Li, C. Tan and W. Tang, *Phys. Rev. Appl.*, 2020, **13**, 24051.
- 49 Y. Wang, Q. Wang, X. Zhan, F. Wang, M. Safdar and J. He, *Nanoscale*, 2013, **5**, 8326–8339.
- 50 C. He, D. Guo, K. Chen, S. Wang, J. Shen, N. Zhao, A. Liu, Y. Zheng, P. Li, Z. Wu, C. Li, F. Wu and W. Tang, *ACS Appl. Nano Mater.*, 2019, **2**, 4095–4103.
- 51 K. Chen, S. Wang, C. He, H. Zhu, H. Zhao, D. Guo, Z. Chen, J. Shen, P. Li, A. Liu, C. Li, F. Wu and W. Tang, *ACS Appl. Nano Mater.*, 2019, **2**, 6169–6177.
- 52 B. Das, B. Das, N. S. Das, S. Sarkar and K. K. Chattopadhyay, *Microporous Mesoporous Mater.*, 2019, **288**, 109600.
- 53 S. Wang, D. Li, C. Sun, S. Yang, Y. Guan and H. He, *Appl. Catal., B*, 2014, **144**, 885–892.
- 54 V. Ghodsi, S. Jin, J. C. Byers, Y. Pan and P. V. Radovanovic, *J. Phys. Chem. C*, 2017, **121**, 9433–9441.
- 55 D. Y. Guo, Z. P. Wu, Y. H. An, X. C. Guo, X. L. Chu, C. L. Sun, L. H. Li, P. G. Li and W. H. Tang, *Appl. Phys. Lett.*, 2014, **105**, 023507.

