



Cite this: RSC Adv., 2020, 10, 28100

## Preparation of Ni-IL/SiO<sub>2</sub> and its catalytic performance for one-pot sequential synthesis of 2-propylheptanol from *n*-valeraldehyde

 Hualiang An, Di Wang, Shuang Miao, Qiusheng Yang,\* Xinqiang Zhao \* and Yanji Wang 

A novel silica-immobilized nickel and acid ionic liquid (Ni-IL/SiO<sub>2</sub>) catalyst was prepared by combining a bonding procedure with an impregnation operation and was characterized by means of X-ray diffraction (XRD), Fourier transform infrared (FT-IR) spectra, X-ray photoelectron spectroscopy (XPS) and thermogravimetric analysis (TGA) techniques. Its catalytic performance was evaluated for the one-pot synthesis of 2-propylheptanol (2-PH) via a sequential *n*-valeraldehyde self-condensation and hydrogenation reaction. As a result, Ni-IL/SiO<sub>2</sub> showed an excellent catalytic activity for the one-pot synthesis of 2-PH, affording a 2-PH selectivity of 75.4% at a *n*-valeraldehyde conversion of 100% and the sum of 2-PH and pentanol selectivity reached 98.6% under the suitable reaction conditions.

 Received 28th April 2020  
 Accepted 20th July 2020

DOI: 10.1039/d0ra03800h

[rsc.li/rsc-advances](http://rsc.li/rsc-advances)

### 1. Introduction

2-Propylheptanol (2-PH), an important plasticizer alcohol, can be used for synthesizing a series of plasticizers by esterification with phthalic anhydride, trimellitic anhydride and adipic acid, *etc.* Bis(2-propylheptyl) phthalate (DPHP) is a major 2-PH-derived plasticizer. Compared with dioctyl phthalate (DOP) derived from 2-ethylhexanol, DPHP has the advantages of low toxicity and less volatility and can meet the requirements for health, safety and environmental protection.<sup>1</sup> The industrial production of 2-PH mainly includes three reaction steps: hydroformylation of butene, self-condensation of *n*-valeraldehyde, and hydrogenation of 2-propyl-2-heptenal. One-pot synthesis of 2-PH by sequential aldol condensation and hydrogenation reaction from *n*-valeraldehyde can shorten the process flow, reduce energy consumption, and lower equipment and operating costs. So the one-pot synthesis of 2-PH is of academic and commercial importance.

The one-pot synthesis of 2-PH by sequential aldol condensation and hydrogenation from *n*-valeraldehyde is categorized as a type of reaction integration. At present, the research on the reaction integration of *n*-valeraldehyde self-condensation and 2-propyl-2-heptenal hydrogenation is rarely reported. Instead some researchers including our group have investigated a similar reaction integration of *n*-butyraldehyde self-condensation and successive hydrogenation.<sup>2-8</sup> Liang *et al.*<sup>4</sup>

studied this reaction integration using a bifunctional catalyst of Ni/Ce-Al<sub>2</sub>O<sub>3</sub> and realized one-step synthesis of 2-ethylhexanol from *n*-butyraldehyde, attaining a 2-ethylhexanol selectivity of 66.9% at a *n*-butyraldehyde conversion of 100%. Li *et al.*<sup>5,6</sup> obtained similar 2-ethylhexanol selectivity and *n*-butyraldehyde conversion over Ni/La-Al<sub>2</sub>O<sub>3</sub> catalyst for one-pot sequential synthesis of 2-ethylhexanol. Patankar *et al.*<sup>7</sup> prepared a Cu-Mg-Al catalyst for this reaction integration and obtained a 2-ethylhexanol selectivity of 90% at a 30% of *n*-butyraldehyde conversion. Miao *et al.*<sup>8</sup> obtained a 2-ethylhexanol selectivity of 73.5% at a complete *n*-butyraldehyde conversion using a Cu-Mg-Fe catalyst for one-step synthesis of 2-ethylhexanol from *n*-butyraldehyde. It can be inferred from the above researches that the reaction integration of *n*-butyraldehyde self-condensation and successive hydrogenation needs a multifunctional catalyst with both acid/base active site (for aldol condensation) and metal active site (for hydrogenation). So the reaction integration of *n*-valeraldehyde self-condensation and successive hydrogenation for one-pot synthesis of 2-PH from *n*-valeraldehyde requires a metal-acid/base multifunctional catalyst either.

We once evaluated the catalytic performance of an acid ionic liquid [HSO<sub>3</sub>-*b*-N(Et)<sub>3</sub>]p-TSA in *n*-butyraldehyde self-condensation and the catalytic performance of an acid-base bifunctional ionic liquid [PEmim]Cl-0.5Zn(CH<sub>3</sub>COO)<sub>2</sub> in *n*-valeraldehyde self-condensation. Pretty good results were attained: 2-ethyl-2-hexenal selectivity of 87.8% was achieved at a *n*-butyraldehyde conversion of 89.7% over [HSO<sub>3</sub>-*b*-N(Et)<sub>3</sub>]p-TSA while 2-propyl-2-heptanal selectivity of 86.6% was obtained at a *n*-valeraldehyde conversion of 94.7% over [PEmim]Cl-0.5Zn(CH<sub>3</sub>COO)<sub>2</sub>.<sup>9,10</sup> Moreover, supported Ni-based or Cu-based catalysts show excellent catalytic performance for hydrogenation of 2-propyl-2-heptenal.<sup>11-14</sup> So a combination of an acidic

Hebei Provincial Key Lab of Green Chemical Technology and Efficient Energy Saving, National-Local Joint Engineering Lab for Energy Conservation in Chemical Process Integration and Resources Utilization, School of Chemical Engineering and Technology, Hebei University of Technology, Tianjin 300130, China. E-mail: [yqiuhseng@hebut.edu.cn](mailto:yqiuhseng@hebut.edu.cn); [zhaoxq@hebut.edu.cn](mailto:zhaoxq@hebut.edu.cn)



ionic liquid or an acid-base bifunctional ionic liquid with supported Ni or Cu catalyst will be expected to show a good catalytic performance for the one-pot synthesis of 2-PH from *n*-valeraldehyde. Besides, the immobilization of ionic liquid can reduce the usage of ionic liquid, simplify separation and purification operation, and impose a specially designed environment around the catalytic site, being beneficial to inhibit the side reactions and enhance the product selectivity.<sup>15,16</sup> With such ideas in mind, we prepared a silica-immobilized nickel and acid ionic liquid (Ni-IL/SiO<sub>2</sub>) catalyst and characterized its structure and property by means of FT-IR, TGA, XRD and XPS analysis. To our delight, Ni-IL/SiO<sub>2</sub> showed an excellent catalytic performance for the one-pot synthesis of 2-PH from *n*-valeraldehyde, laying a foundation for establishing a new green technology for 2-PH synthesis.

## 2. Experimental

### 2.1. Preparation of Ni-IL/SiO<sub>2</sub>

The process for preparation of Ni-IL/SiO<sub>2</sub> comprises two steps: firstly an acid ionic liquid was immobilized on silica to form silica-immobilized acid ionic liquid (IL/SiO<sub>2</sub>), and then nickel was introduced in IL/SiO<sub>2</sub> to obtain the target catalyst Ni-IL/SiO<sub>2</sub>.

(1) **Preparation of IL/SiO<sub>2</sub>.** A IL/SiO<sub>2</sub> sample was prepared by a bonding procedure.<sup>17</sup> The mixture of silica, toluene and 3-chloropropyl triethoxysilane was stirred for 6 h under reflux of toluene to obtain a chloropropyl functionalized silica (Intermediate Product-1, IP-1). Then IP-1, potassium iodide and excess imidazole were dispersed in anhydrous toluene and the mixture was refluxed at 110 °C for 16 h to give a 3-(1-imidazole) propyl functionalized silica (IP-2). Next, IP-2 was mixed with a solution of 1,3-propane sultone and toluene and then the mixture was stirred at 100 °C for 6 h to attain a silica-immobilized amphoteric salt (IP-3). After that, CF<sub>3</sub>SO<sub>3</sub>H was added dropwise into a mixture of IP-3 and toluene. The resulting mixture was heated to 80 °C and kept for 5 h to afford an immobilized sulfonic acid functional ionic liquid, IL/SiO<sub>2</sub>. The structure of IL/SiO<sub>2</sub> is presented in Scheme 1.

(2) **Preparation of Ni-IL/SiO<sub>2</sub>.** Ni-IL/SiO<sub>2</sub> catalyst was prepared by impregnating a nickel nitrate aqueous solution into




Fig. 1 XRD patterns of Ni(NO<sub>3</sub>)<sub>2</sub>-IL/SiO<sub>2</sub> and fresh and recovered Ni-IL/SiO<sub>2</sub> (a) Ni(NO<sub>3</sub>)<sub>2</sub>-IL/SiO<sub>2</sub>, (b) fresh Ni-IL/SiO<sub>2</sub>, (c) recovered Ni-IL/SiO<sub>2</sub>.


the IL/SiO<sub>2</sub> sample and then reduction by NaBH<sub>4</sub> under 40 °C for 4 h. The structure of Ni-IL/SiO<sub>2</sub> is shown in Scheme 1 either.

### 2.2. Catalyst characterization

A NICOLET NEXUS 470 infrared spectroscopy (Thermo Electron Corp., USA) was used for the FTIR measurement of samples. The spectra were recorded between 400 and 4000 cm<sup>-1</sup> at a resolution of 4 cm<sup>-1</sup>. The thermal stability of samples was determined using a SDT Q600 simultaneous thermal analyzer (TA Instruments Corp., USA). The test was carried out under a flowing air atmosphere (40 mL min<sup>-1</sup>) with a heating rate of 10 °C min<sup>-1</sup> in the range from room temperature to 700 °C. The binding energy of Ni on the catalyst surface was measured using a Kratos Axis Ultra DLD photoelectron spectrometer (Kratos Analytical, Manchester, England). All the binding energy data were calibrated with C 1s = 284.6 eV as an internal standard. X-ray diffraction (XRD) patterns were recorded with a Rigaku D/max-2550 diffractometer (Rigaku International Corp., Japan) using Cu K $\alpha$  radiation at 100 mA and 40 kV. The scan range covered from 5° to 90° at a rate of 6° min<sup>-1</sup>.

### 2.3. Catalytic performance evaluation

The catalytic performance of Ni-IL/SiO<sub>2</sub> for one-pot synthesis of 2-PH by sequential *n*-valeraldehyde self-condensation and hydrogenation was evaluated in a 100 mL stainless steel autoclave. In a typical procedure, 30 mL (about 24 g) of *n*-valeraldehyde and 4.5 g of Ni-IL/SiO<sub>2</sub> catalyst were added into the autoclave, and the air inside was replaced by nitrogen. The mixture was heated to 200 °C and held for 1.5 h with stirring. Then H<sub>2</sub> was introduced into the reaction system without cooling and separation. The hydrogenation reaction was carried out for 8.0 h under 3.0 MPa of H<sub>2</sub> pressure. After the completion of reaction, the mixture solution was filtered to remove the catalyst and the filtrate was analyzed on a gas chromatograph



Scheme 1 Structure diagrams of IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub>.






Fig. 2 XPS Ni 2p spectra of (a)  $\text{Ni}(\text{NO}_3)_2$ -IL/SiO<sub>2</sub> and (b) Ni-IL/SiO<sub>2</sub>.

equipped with a FID and a KB-1 capillary column and quantified by the internal standard analysis method.

### 3. Results and discussion

#### 3.1. Characterization of Ni-IL/SiO<sub>2</sub> catalyst

The XRD patterns of  $\text{Ni}(\text{NO}_3)_2$ -IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub> are shown in Fig. 1. No characteristic peaks of  $\text{Ni}(\text{NO}_3)_2$  are observed in  $\text{Ni}(\text{NO}_3)_2$ -IL/SiO<sub>2</sub>, indicating that the supported  $\text{Ni}(\text{NO}_3)_2$  has small particle sizes and is homogeneously dispersed on the surface of IL/SiO<sub>2</sub>. For Ni-IL/SiO<sub>2</sub> catalyst, a very weak and broad characteristic peak centered at 2 theta of  $44.5^\circ$  corresponds to amorphous  $\text{Ni}^0$ , indicating that  $\text{Ni}^{2+}$  has been reduced to  $\text{Ni}^0$  successfully in Ni-IL/SiO<sub>2</sub>. After the reaction, some diffraction peaks are observed at around 2 theta of  $44.5^\circ$  and  $52.0^\circ$  (Fig. 1(c)), which attribute to the  $\text{Ni}^0(100)$  and  $\text{Ni}^0(220)$  planes.<sup>18</sup> There are two possible explanations for the change in characteristic peak of  $\text{Ni}^0$ : further reduction under  $\text{H}_2$  atmosphere, or aggregation and growth of Ni grains.

To further analyze the chemical states of nickel, the samples were characterized by XPS analysis. Fig. 2 displays Ni 2p spectra

of the catalyst before and after reduction. It can be seen from Fig. 2(a) that the binding energies of Ni 2p<sub>3/2</sub> and Ni 2p<sub>1/2</sub> in  $\text{Ni}(\text{NO}_3)_2$ -IL/SiO<sub>2</sub> are respectively 857.2 eV and 874.8 eV, which are ascribed to  $\text{Ni}^{2+}$  of  $\text{Ni}(\text{NO}_3)_2$ . There are two valence states of nickel in Ni-IL/SiO<sub>2</sub> (Fig. 2(b)). The binding energies at around 852.7 eV and 870.0 eV for the Ni 2p<sub>3/2</sub> are attributed to  $\text{Ni}^0$  (metallic Ni) whereas the Ni 2p<sub>3/2</sub> and Ni 2p<sub>1/2</sub> peaks at 856.2 eV and 873.9 eV are attributed to  $\text{Ni}^{2+}$  of NiO.<sup>19</sup> An absence of  $\text{Ni}^{2+}$  of  $\text{Ni}(\text{NO}_3)_2$  in Ni-IL/SiO<sub>2</sub> indicates  $\text{Ni}(\text{NO}_3)_2$  has been completely reduced by NaBH<sub>4</sub>. It also demonstrates that the enhancement of XRD diffraction peaks of  $\text{Ni}^0$  in the recovered catalyst is caused by the aggregation and growth of Ni grains. The presence of NiO in Ni-IL/SiO<sub>2</sub> may be due to the reoxidation of metallic nickel by contacting air in the analysis process.<sup>14</sup>

The FT-IR spectra of silica and the prepared IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub> are shown in Fig. 3. The broad band around  $3445\text{ cm}^{-1}$  belongs to asymmetric stretching vibration of -OH on the support surface. The band at  $1625\text{ cm}^{-1}$  is associated with the bending vibration of H-O-H. The bands at  $809\text{ cm}^{-1}$  and  $1099\text{ cm}^{-1}$  are assigned to symmetrical and asymmetric stretching vibration of Si-O-Si while the bending vibration of




Fig. 3 FT-IR spectra of silica, IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub> (a) silica, (b) IL/SiO<sub>2</sub>, (c) Ni-IL/SiO<sub>2</sub>.




Fig. 4 TGA curves of IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub> (a) IL/SiO<sub>2</sub>, (b) Ni-IL/SiO<sub>2</sub>.



**Table 1** Effect of catalyst amount on the catalytic performance of Ni-IL/SiO<sub>2</sub><sup>a</sup>

Catalyst amount/%	X <sub>V</sub> /%	S <sub>PO</sub> /%	S <sub>2-PHEA</sub> /%	S <sub>2-PHA</sub> /%	S <sub>2-PH</sub> /%
5	95.3	20.4	0.7	70.6	3.4
10	100	25.6	0.8	12.8	58.7
15	100	27.4	0.9	2.30	69.0
20	100	24.7	0.9	10.4	63.0

<sup>a</sup> Reaction conditions:  $T = 200\text{ }^{\circ}\text{C}$ ; *n*-valeraldehyde self-condensation:  $t = 1.5\text{ h}$ ; hydrogenation:  $P_{\text{H}_2} = 3\text{ MPa}$ ,  $t = 8\text{ h}$ . V: *n*-valeraldehyde; PO: pentanol; 2-PHEA: 2-propyl-2-heptenal; 2-PHA: 2-propylheptanal; 2-PH: 2-propylheptanol. X: conversion; S: selectivity.

**Table 2** Effect of hydrogen pressure on the catalytic performance of Ni-IL/SiO<sub>2</sub><sup>a</sup>

Reaction pressure/MPa	X <sub>V</sub> /%	S <sub>PO</sub> /%	S <sub>2-PHEA</sub> /%	S <sub>2-PHA</sub> /%	S <sub>2-PH</sub> /%
2	100	28.2	2.3	36.8	28.3
3	100	27.4	0.9	2.3	69.0
4	100	23.2	0.4	0.5	75.4
5	100	24.9	0.2	0.1	70.5

<sup>a</sup> Reaction conditions:  $T = 200\text{ }^{\circ}\text{C}$ , a weight percentage of catalyst = 15%; *n*-valeraldehyde self-condensation:  $t = 1.5\text{ h}$ ; hydrogenation:  $t = 8\text{ h}$ . V: *n*-valeraldehyde; PO: pentanol; 2-PHEA: 2-propyl-2-heptenal; 2-PHA: 2-propylheptanal; 2-PH: 2-propylheptanol. X: conversion; S: selectivity.


Si-OH is observed at  $967\text{ cm}^{-1}$ .<sup>20</sup> Compared with silica support, a new band at  $641\text{ cm}^{-1}$  attributed to the bending vibration of C-F appears in IL/SiO<sub>2</sub> while the bending vibration of Si-OH

amount per unit mass of sample because of the introduction of nickel for Ni-IL/SiO<sub>2</sub>.

### 3.2. Catalytic performance of Ni-IL/SiO<sub>2</sub> for one-pot synthesis of 2-PH

The catalytic performance of Ni-IL/SiO<sub>2</sub> for one-pot synthesis of 2-PH was evaluated at  $200\text{ }^{\circ}\text{C}$  for  $1.5\text{ h}$  first and then  $\text{H}_2$  was introduced for hydrogenation under  $3.0\text{ MPa}$  of  $\text{H}_2$  pressure for  $8.0\text{ h}$ . As a result, the selectivity of 2-PH and pentanol was respectively 58.7% and 25.6% at a *n*-valeraldehyde conversion of 100%. The catalytic performance of Ni-IL/SiO<sub>2</sub> is affected greatly by the reaction conditions. To improve the catalytic performance of Ni-IL/SiO<sub>2</sub>, the effects of reaction conditions such as Ni-IL/SiO<sub>2</sub> dosage, hydrogen pressure, reaction temperature and reaction time were investigated.

**3.2.1 Effect of catalyst dosage.** The results of effect of Ni-IL/SiO<sub>2</sub> dosage are listed in Table 1. With an increase of weight percentage of Ni-IL/SiO<sub>2</sub>, *n*-valeraldehyde conversion increased from 95.3% to 100% while the selectivity of 2-PH increased first, reached its highest point at a weight percentage of Ni-IL/SiO<sub>2</sub> of 15%, and then decreased. The selectivity of 2-propylheptanal changed adversely with 2-PH. The results suggest that the hydrogenation of 2-propyl-2-heptenal to 2-PH proceeds in two steps: C=C bond of 2-propyl-2-heptenal is hydrogenated to 2-propylheptanal first and then C=O bond of 2-propylheptanal is hydrogenated to 2-PH, as shown in eqn (1). The selectivity of 2-propyl-2-heptenal was quite low and changed little, indicating that the hydrogenation of C=C bond is easier than that of C=O bond and thus the hydrogenation of C=O bond is the controlling step.



weakens obviously, indicating the reaction of Si-OH with the coupling agent and the immobilization of ionic liquids on the support. Fortunately, the FT-IR spectrum changes little for the supported nickel catalyst Ni-IL/SiO<sub>2</sub>. Combined with the results of XRD and XPS, it is confirmed that the ionic liquid and nickel has been successfully grafted onto the surface of silica.

Fig. 4 presents the TGA curves of IL/SiO<sub>2</sub> and Ni-IL/SiO<sub>2</sub>. There are two steps of weight loss for the two samples. The first weight loss occurs at about  $70\text{ }^{\circ}\text{C}$ , which is attributed to the physically adsorbed water and residual organic solvents during the process for preparation of catalysts. The second weight loss at higher than  $330\text{ }^{\circ}\text{C}$  is related to the decomposition of the ionic liquids on the surface of supports.<sup>21</sup> The analysis results demonstrate that Ni-IL/SiO<sub>2</sub> shows the same thermal stability as IL/SiO<sub>2</sub> and its weight loss rate is slightly lower than that for IL/SiO<sub>2</sub>. This could be attributed to the decline in ionic liquid

**3.2.2 Effect of hydrogen pressure.** The effect of hydrogen pressure was investigated and the results are listed in Table 2. When the hydrogen pressure was  $2.0\text{ MPa}$ , there was a certain amount of 2-propylheptanal left after the reaction, which demonstrates once again the hydrogenation of C=C bond is easier than that of C=O bond. With increasing hydrogen pressure, the catalytic activity for the hydrogenation of C=O bond was improved: the selectivity of both 2-propyl-2-heptenal and 2-propylheptanal decreased and 2-PH selectivity increased obviously. When the hydrogen pressure was  $4.0\text{ MPa}$ , the highest 2-PH selectivity of 75.4% was reached and the sum of the selectivity of 2-PH and pentanol was 98.6%.

**3.2.3 Effect of reaction time.** The effect of reaction time listed in Table 3 shows that reaction time has a significant influence on the catalytic performance. A low 2-PH selectivity of 47.1% at a reaction time of  $6\text{ h}$  was obtained because 2-



**Table 3** Effect of reaction time on the catalytic performance of Ni-IL/SiO<sub>2</sub><sup>a</sup>

Reaction time/h	X <sub>V</sub> /%	S <sub>PO</sub> /%	S <sub>2-PHEA</sub> /%	S <sub>2-PHA</sub> /%	S <sub>2-PH</sub> /%
6	100	25.7	3.1	23.8	47.1
8	100	23.2	0.4	0.5	75.4
10	100	22.4	0.1	0	72.9

<sup>a</sup> Reaction conditions: a weight percentage of catalyst = 15%, *T* = 200 °C; *n*-valeraldehyde self-condensation: *t* = 1.5 h; hydrogenation: *P*<sub>H<sub>2</sub></sub> = 4 MPa. V: *n*-valeraldehyde; PO: pentanol; 2-PHEA: 2-propyl-2-heptenal; 2-PHA: 2-propylheptanal; 2-PH: 2-propylheptanol. X: conversion; S: selectivity.

**Table 4** Effect of reaction temperature on the catalytic performance of Ni-IL/SiO<sub>2</sub><sup>a</sup>

Reaction temperature/°C	X <sub>V</sub> /%	S <sub>PO</sub> /%	S <sub>2-PHEA</sub> /%	S <sub>2-PHA</sub> /%	S <sub>2-PH</sub> /%
190	99.8	27.1	3.6	24.6	43.8
200	100	23.2	0.4	0.5	75.4
210	100	22.1	0	0.2	65.8

<sup>a</sup> Reaction conditions: a weight percentage of catalyst = 15%; *n*-valeraldehyde self-condensation: *t* = 1.5 h; hydrogenation: *P*<sub>H<sub>2</sub></sub> = 4 MPa, *t* = 8 h. V: *n*-valeraldehyde; PO: pentanol; 2-PHEA: 2-propyl-2-heptenal; 2-PHA: 2-propylheptanal; 2-PH: 2-propylheptanol. X: conversion; S: selectivity.

propylheptanal was not fully hydrogenated. With the prolonging of reaction time, 2-PH selectivity increased while 2-propylheptanal selectivity decreased. When the reaction proceeded for 8 h, 2-propylheptanal was almost completely hydrogenated to 2-PH. With further prolonging reaction time, some side-reactions of 2-PH and *n*-valeraldehyde could be promoted, resulting in the decrease of 2-PH selectivity.<sup>5</sup>

**3.2.4 Effect of reaction temperature.** Table 4 shows the effect of reaction temperature. The highest 2-PH selectivity of 75.4% was obtained with a *n*-valeraldehyde conversion of 100% at 200 °C. A decrease of reaction temperature mainly reduced the hydrogenation rate of C=O bond, resulting an increase of 2-propylheptanal selectivity. However, deep self-condensation of *n*-valeraldehyde could be accelerated at a reaction temperature above 200 °C, affecting the generation of pentanol and 2-PH.

Thus an improved catalytic performance of Ni-IL/SiO<sub>2</sub> was attained by investigating the effect of reaction conditions: a 2-PH selectivity of 75.4% with a *n*-valeraldehyde conversion of 100% under the conditions of 15 wt% of Ni-IL/SiO<sub>2</sub>, a hydrogen pressure of 4 MPa, 200 °C, and 8 h. The Ni/Ce-Al<sub>2</sub>O<sub>3</sub> catalyst reported in our previous work of one-pot synthesis of 2-ethylhexanol<sup>4</sup> was applied in the one-pot synthesis of 2-PH via sequential self-condensation and hydrogenation from *n*-valeraldehyde under the above suitable reaction conditions. A 2-PH selectivity of 69.3% with a complete *n*-valeraldehyde conversion was obtained, indicating that the catalytic performance of Ni-IL/SiO<sub>2</sub> is better than that of Ni/Ce-Al<sub>2</sub>O<sub>3</sub> for one-pot synthesis of 2-PH.

## 4. Conclusions

A novel Ni-IL/SiO<sub>2</sub> catalyst was prepared for one-pot synthesis of 2-PH via sequential self-condensation and hydrogenation from *n*-valeraldehyde. The characterization results demonstrate that Ni(NO<sub>3</sub>)<sub>2</sub> was reduced to Ni completely by NaBH<sub>4</sub>, and Ni-IL/SiO<sub>2</sub> has a good thermal stability below 330 °C. The prepared catalyst shows an excellent catalytic performance in one-pot synthesis of 2-PH: the selectivity of 2-PH attained 75.4% at a *n*-valeraldehyde conversion of 100% and the sum of 2-PH and pentanol selectivity reached 98.6% under the suitable reaction conditions. The hydrogenation of C=O bond of 2-propyl-2-heptenal is more difficult than that of C=C bond, and is the controlling step.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work was financially supported by the National Natural Science Foundation of China (21978066, 21506046), Basic Research Program of Hebei Province for Natural Science Foundation and Key Basic Research Project (18964308D), and Natural Science Foundation of Hebei Province (B2018202220). The authors are gratefully appreciative of their contributions.

## References

- 1 L. Zhao, H. An, X. Zhao and Y. Wang, *Ind. Eng. Chem. Res.*, 2016, **55**, 12326.
- 2 T. Seki, J.-D. Grunwaldt and A. Baiker, *Chem. Commun.*, 2007, **34**, 3562.
- 3 C. A. Hamilton, S. D. Jackson and G. J. Kelly, *Appl. Catal., A*, 2004, **263**, 63.
- 4 N. Liang, X. Zhang, H. An, X. Zhao and Y. Wang, *Green Chem.*, 2015, **17**, 2959.
- 5 Y. Li, X. Liu, H. An, X. Zhao and Y. Wang, *Ind. Eng. Chem. Res.*, 2016, **55**, 6293.
- 6 Y. Li, X. Liu, H. An, X. Zhao and Y. Wang, *J. Chem. Ind. Eng.*, 2017, **68**, 1381.
- 7 S. C. Patankar and G. D. Yadav, *Catal. Today*, 2017, **291**, 223.
- 8 S. Miao, H. An, X. Zhao and Y. Wang, *React. Kinet., Mech. Catal.*, 2019, **128**, 395.
- 9 X. Zhang, H. An, H. Zhang, X. Zhao and Y. Wang, *Ind. Eng. Chem. Res.*, 2014, **53**, 16707.
- 10 H. An, Y. Kong, Q. Yang, X. Zhao and Y. Wang, *J. Chem. Technol. Biotechnol.*, 2020, **95**, 710.
- 11 Z. Sun, *J. Chem. Ind. Eng.*, 2007, **28**, 8.
- 12 Z. Tang, Y. Zhou and Y. Feng, *Appl. Catal., A*, 2004, **273**, 171.
- 13 T. Zhang, J. Shi and S. Zhang, *Petrochem. Technol.*, 2012, **41**, 653.
- 14 L. Zhao, PhD thesis, Hebei University of Technology, 2018.
- 15 A. Dhar, N. S. Kumar, M. Khimani, A. S. Al-Fatesh, A. A. Ibrahim, A. H. Fakieha, H. Patelc and R. L. Vekariya, *RSC Adv.*, 2020, **10**, 15282.
- 16 A. S. Amarasekara, *Chem. Rev.*, 2016, **116**, 6133.



17 H. An, J. Tian, X. Zhao and Y. Wang, *J. Chem. Ind. Eng.*, 2015, **66**, 171.

18 S. K. Sharma and R. V. Jasra, *Indian J. Chem.*, 2015, **54**, 451.

19 C. C. Torres, J. B. Alderete, C. Mella and B. Pawelec, *J. Mol. Catal. A: Chem.*, 2016, **423**, 441.

20 P. Han, H. Zhang, X. Qiu, X. Ji and L. Gao, *J. Mol. Catal. A: Chem.*, 2008, **295**, 57.

21 M. Vafaeenezadeh, Z. B. Dizicheh and M. M. Hashemi, *Catal. Commun.*, 2013, **41**, 96.

