Chemical Science

EDGE ARTICLE

Check for updates

Cite this: Chem. Sci., 2020, 11, 7593

All publication charges for this article have been paid for by the Royal Society of Chemistry

Received 24th January 2020 Accepted 25th February 2020

DOI: 10.1039/d0sc00465k

rsc.li/chemical-science

Introduction

The transformation of CO₂ into value-added products is a promising strategy to mitigate the further increase of CO_2 in the earth's atmosphere that is connected to environmental changes.¹⁻⁴ In that context, the hydrogenation of CO₂ yields CH₃OH that can be used as a base chemical for the production of fuels or as a fuel itself, thus generating a closed carbon-fuelcycle, provided that efficient CO₂ capture and storage, and efficient H₂ production from renewable energy sources are available.5 Major issues associated with the hydrogenation of CO2 into CH3OH are the selectivity of the process and the longterm stability of catalysts. Regarding selectivity, the hydrogenation of CO2 can also yield CO via, for instance, the reverse water gas shift (RWGS) reaction or the decomposition of methyl formate, that can be formed in situ via secondary reactions.6,7 Heterogeneous catalysts that are able to form CH₃OH with good selectivity and activity mainly consist of copper-based catalysts together with zinc oxide (e.g. Cu/ZnO or Cu/ZnO/Al₂O₃), gallium oxide (e.g. Cu/ZnO/Ga₂O₃) or zirconium oxide (Cu/ZrO₂).⁸⁻²³ In the case of ZrO₂, it has been shown that the Lewis acidic surface Zr^{IV} sites stabilize reaction intermediates (CO₂, formates and methoxy) and improve the activity and methanol selectivity. The origin of the promotional effect of zinc or gallium oxide is, however, not fully understood.24-29 For instance, the formation of highly active CuZn surface alloys or interfacial sites between

^bPaul Scherrer Institute, CH-5232 Villigen, Switzerland

Enhanced CH₃OH selectivity in CO₂ hydrogenation using Cu-based catalysts generated *via* SOMC from Ga^{III} single-sites†

Erwin Lam,^a Gina Noh,^a Ka Wing Chan, ^b^a Kim Larmier, ^a Dmitry Lebedev, ^a Keith Searles,^a Patrick Wolf,^a Olga V. Safonova ^b^b and Christophe Copéret ^{*}

Small and narrowly distributed nanoparticles of copper alloyed with gallium supported on silica containing residual Ga^{III} sites can be obtained *via* surface organometallic chemistry in a two-step process: (i) formation of isolated Ga^{III} surface sites on SiO₂ and (ii) subsequent grafting of a Cu¹ precursor, [Cu(O^tBu)]₄, followed by a treatment under H₂ to generate CuGa_x alloys. This material is highly active and selective for CO₂ hydrogenation to CH₃OH. *In situ* X-ray absorption spectroscopy shows that gallium is oxidized under reaction conditions while copper remains as Cu⁰. This CuGa material only stabilizes methoxy surface species while no formate is detected according to *ex situ* infrared and solid-state nuclear magnetic resonance spectroscopy.

Cu and ZnO have both been proposed.²⁴⁻²⁹ The promotional effect of gallium oxide has been far less studied.^{27,30}

Recently, it has been shown that surface organometallic chemistry (SOMC) combined with thermolytic molecular precursors (TMP) constitutes a powerful synthetic strategy to generate supported metal nanoparticles surrounded by welldefined isolated promoter sites that allows investigating the role of interfacial sites via in situ spectroscopic methods.^{31,32} This approach can also yield supported alloyed nanoparticles, depending on the selection of metal and promoters (vide infra). The SOMC/TMP approach can be summarized as follows: in a first step, the support, SiO₂, is dehydroxylated at 700 °C to obtain isolated surface silanol (Si-OH) groups (1 OH, nm⁻²) that are used as anchoring groups to graft the TMP.33 Postthermal treatment at high temperature generates isolated lowcoordinated metal surface sites, that are free of organic ligands, and restores \equiv Si-OH groups (Scheme 1a), onto which a second molecular precursor is grafted. Subsequent post-treatment under reducing conditions (H₂) generates metal nanoparticles interfacing low-coordinated metal surface sites (Scheme 1b). This approach has allowed the generation of highly active and selective CO₂ hydrogenation catalysts by supporting Cu nanoparticles on SiO₂ containing isolated Zr^{IV} and Ti^{IV} sites.^{34,35} These catalysts show high activity and CH₃OH selectivity, but also suffer from the decrease of CH₃OH selectivity at high conversion as observed for other CO₂ hydrogenation catalysts.³⁴ The outstanding activity and CH₃OH selectivity of copper supported on silica containing Ti^{IV} isolated sites is particularly noteworthy, considering that Cu/TiO2 performs very poorly in CH₃OH synthesis by favoring CO formation.^{36–39} This difference of catalyst performance has been ascribed to the site isolation of Ti^{IV} and the use of a non-reducible support, SiO₂, thus allowing



View Article Online

^aDepartment of Chemistry and Applied Biosciences, ETH Zurich, Vladimir Prelog Weg 2, CH-8093 Zurich, Switzerland. E-mail: ccoperet@ethz.ch

[†] Electronic supplementary information (ESI) available. See DOI: 10.1039/d0sc00465k



Scheme 1 (a) General SOMC strategy to generate isolated sites or supported nanoparticles. (b and c) Utilizing isolated metal site supports generated from SOMC for metal and metal–alloy nanoparticle formation.

Ti^{IV} to play exclusively the role of a Lewis acid, that stabilizes reaction intermediates at the interface with Cu particles.³⁵ Using a similar approach, *i.e.*, the treatment under H₂ of a grafted platinum(n) molecular precursor on isolated Ga^{III} sites generates small and narrowly distributed PtGa_x nanoparticles stabilized by remaining Ga^{III} sites that show high activity, selectivity and stability for propane dehydrogenation.⁴⁰

Here, we reasoned that the SOMC/TMP approach would be a useful tool to investigate the behavior of gallium promoters in CO_2 hydrogenation catalysts (Scheme 1c). We thus prepared Cubased nanoparticles by grafting $[Cu(O^tBu)]_4$ on a silica support containing Ga^{III} single-sites, followed by a treatment under H₂. This approach yields nanoparticles consisting of $CuGa_x$ alloys that evolved under CO_2 hydrogenation conditions into Cu^0 and Ga^{III} according to *in situ* X-ray absorption spectroscopy (XAS). Such **Cu-Ga/SiO**₂ catalysts display enhanced activity and selectivity at higher conversions in the hydrogenation of CO_2 into CH_3OH by comparison to other Cu-based catalysts. These improved performances are attributed to Cu^0/Ga^{III} interfaces that only stabilize methoxy and not formate intermediates, according to infrared (IR) and solid state nuclear magnetic resonance (NMR) spectroscopy.

Results and discussion

Catalyst synthesis and characterization

We first prepared well-defined Ga^{III} sites on SiO_2 with *ca.* 1.0 Ga^{III} nm⁻² by grafting and thermolysis of $[Ga(OSi(O^tBu)_3)_3(-THF)]$;^{41,42} $Ga^{III} \otimes SiO_2$ (ref. 42) ($M^x \otimes SiO_2$ denoted as isolated M surface sites in its *x* oxidation state) *via* an SOMC/TMP approach and then grafted $[Cu(O^tBu)]_4$ on residual surface silanols present in $Ga^{III} \otimes SiO_2$. The IR spectra show the consumption of Si-OH groups (3747 cm⁻¹) and the appearance of C-H stretching (2700-3000 cm⁻¹) and bending (1300-1500 cm⁻¹) bands, consistent with grafting of $[Cu(O^tBu)]_4$ *via*

protonolysis of the Si–OH group (Fig. S1†). Next, reduction under H₂ at 500 °C removes all the organics and regenerate the Si–OH groups, as shown by IR spectroscopy, yielding **Cu-Ga**/ **SiO₂** (Fig. 1a). Based on inductively coupled plasma optical emission spectroscopy (ICP-OES), a metal loading of 1.61 wt% gallium and 3.88 wt% copper is obtained for **Cu-Ga/SiO₂** (corresponding to a 5 : 2 Cu : Ga atomic ratio).

A specific surface area of *ca.* 200 $\text{m}^2 \text{g}^{-1}$ – determined by N₂ physisorption isotherms and Brunauer-Emmett-Teller⁴³ (BET) analysis (Table S1[†]) - is obtained, similar to this of the initial material. Transmission electron microscopy (TEM) studies show the formation of small and narrowly distributed nanoparticles on SiO₂ (4.6 \pm 1.4 nm) (Fig. 1b), which corresponds to Cu-Ga alloy nanoparticles (vide infra). These particles are slightly larger than what was found for the corresponding Cu/ SiO₂ (2.9 \pm 1.3 nm) prepared *via* a similar approach.³⁴ Energydispersive X-ray (EDX) mapping of as-prepared Cu-Ga/SiO₂, introduced to the microscope without exposure to air using a vacuum transfer TEM sample holder, shows that gallium is found in the same region as the copper nanoparticles, but it is also dispersed throughout the support (Fig. S2[†]). In addition, the particle size distribution of Cu-Ga/SiO2 from TEM of samples with and without exposure to air does not change, indicating the absence of copper and gallium redispersion under oxidizing conditions (Fig. S3[†]). N₂O titration at 90 °C, that selectively titrates the surface of Cu nanoparticles, was performed, resulting in around 55 μ mol g_{cat}^{-1} surface sites for $Cu-Ga/SiO_2$ (assuming a 1 : 2 stoichiometry between N₂O and the Cu surface site) (Table S1[†]), which is similar for what is obtained for Cu/SiO₂ (50 μ mol g_{cat}⁻¹),³⁴ despite the larger particle sizes for Cu-Ga/SiO₂. It is possible that N₂O reacts with reduced gallium sites leading to a higher N₂O uptake similar to what is observed with zinc in case of Cu/ZnO/Al2O3.24 Chemisorption experiments using H2 at 40 °C indicate around 60 µmol g_{cat}^{-1} surface sites (assuming a 1 : 2 stoichiometry between H₂ and the surface site) for Cu-Ga/SiO2, consistent with the number obtained via N2O titration (Table S1 and Fig. S4⁺). No crystalline phases are observed by powder X-ray diffraction, as expected from the amorphous nature of the SiO₂ support and the presence of small metal nanoparticles (Fig. S5[†]). The presence of residual Lewis acidic gallium sites is supported by pyridine adsorption and IR spectroscopy,44 by the presence of ring vibrational bands of pyridine at 1621 cm⁻¹, characteristic for Lewis acidic surface sites, likely associated with Ga^{III} sites (Fig. S6[†]). Upon adsorption of pyridine, it persists even at 500 °C under high-vacuum (10⁻⁵ mbar) indicating strongly bound pyridine (for details see ESI[†]). IR spectroscopy (Fig. S7[†]) of the catalysts upon adsorption of CO (90 mbar) at room temperature shows stretching bands at 2102 cm⁻¹ for Cu-Ga/SiO₂ corresponding to CO bonded to the metal nanoparticle which are slightly red-shifted with respect to what is observed for pure Cu/ SiO_2 at 2106 cm⁻¹.

Further information regarding the oxidation states and structural environment of copper and gallium in **Cu-Ga/SiO**₂ is obtained by the XAS spectra at the copper and gallium K-edges for the as-prepared catalysts stored under inert conditions (Fig. 1c). The Cu K-edge X-ray absorption near-edge structure



Fig. 1 (a) Schematic procedure for grafting of $[Cu(O^tBu)]_4$ on Ga^{III}@SiO₂ followed by reduction under H₂ at 500 °C. (b) Particle size distribution and TEM images of Cu-Ga/SiO₂. (c) First derivative of the XANES spectra at the Ga K-edge of Cu-Ga/SiO₂ and reference samples.

(XANES) spectrum of Cu-Ga/SiO₂ shows an edge energy at 8979 eV consistent with reduced Cu⁰ but the near edge features of Cu-Ga/SiO2 are different from the Cu/SiO2 or Cu foil spectrum (Fig. S8[†]). Fitting of the extended X-ray absorption fine structure (EXAFS) shows the presence of gallium ($N = 4 \pm 3$ at 2.57 Å) and copper ($N = 7 \pm 2$ at 2.54 Å) scattering paths (Table 1 and Fig. S9 \dagger), suggesting the formation of a CuGa_x alloy phase. The XANES spectrum of Cu-Ga/SiO2 at the gallium K-edge shows an edge energy of 10 368 eV, which is 5 eV lower than the edge energy of Ga^{III}(a)SiO₂ or Ga₂O₃, as reference samples (Fig. 1c and S10[†]). The shift in the edge energy indicates the presence of reduced gallium species, while the feature observed in Ga^{III} (a) SiO₂ or Ga₂O₃ at 10 373 eV is still present, albeit lower in intensity, in Cu-Ga/SiO₂ as shown in the first derivative of the XANES spectrum (Fig. 1c). Further analysis and fitting of the EXAFS (Table 1) at the Ga K-edge reveals the presence of Cu neighbors ($N = 8 \pm 2$ at 2.57 Å) consistent with the EXAFS fitting

Table 1 EXAFS fits parameters of $\mbox{Cu-Ga/SiO}_2$ at the Cu and Ga K-edges

Edge	Neighbor, N ^a	$r [Å]^b$	$\sigma^2 \left[\mathring{\mathrm{A}}^2 ight]^c$
Cu K-edge	Ga, 4 ± 3	2.57 ± 0.01	0.012 ± 0.002
	Cu, 7 ± 2	2.54 ± 0.02	0.0100 ± 0.0009
Ga K-edge	$\mathrm{O,}~2\pm1$	1.81 ± 0.03	0.012 ± 0.009
	Cu, 8 \pm 2	2.57 ± 0.01	0.012 ± 0.002

^{*a*} Number of specified neighbors. ^{*b*} Distance to corresponding neighbor. ^{*c*} Debye–Waller factor. result at the Cu K-edge with part of the gallium forming a metal alloy phase with copper. In addition, there are oxygen neighbors $(N = 2 \pm 1 \text{ at } 1.81 \text{ Å})$, which are attributed to remaining isolated Ga^{III} sites (Fig. S11†), consistent with pyridine adsorption and IR spectroscopy (*vide supra*). Considering the number of oxygen neighbors (N = 4) found in Ga^{III} (SiO₂, ⁴² we estimated that approx. 50% of Ga is in the form of Ga^{III} sites in Cu-Ga/SiO₂. This indicates formation of CuGa_x alloy with $x \approx 0.2$ based on respective copper (3.88 wt%) and gallium (1.61 wt%) loadings and taking into account that *ca*. 50% of gallium sites are present in its reduced form.

Overall, the XAS spectra show that reduction of the samples after Cu grafting (500 °C under H₂) leads to a partial reduction of Ga^{III} with the formation of CuGa_x alloys along with remaining Ga^{III} sites. These finding contrast with what was observed for **Cu-Ti/SiO₂** (ref. 35) and **Cu-Zr/SiO₂** (ref. 34) prepared in a similar fashion from Ti^{IV} and Zr^{IV} single-sites that remained isolated upon Cu nanoparticle formation.

Catalytic performance in CO₂ hydrogenation

The catalytic performance of **Cu-Ga/SiO**₂ in CO₂ hydrogenation was evaluated at 230 °C under a total pressure of 25 bar and 3 : 1 H_2 : CO₂. Following exposure to air, the material is reduced at 300 °C under H_2 in the reactor prior to catalysis. The effect of contact time on the catalytic activity/selectivity by varying the gas flowrate and the intrinsic formation rates extrapolated to zero contact time are evaluated and compared with **Cu/SiO**₂ and **Cu-Zr/SiO**₂ benchmark materials (Fig. S12 and S13†). Catalytic

tests are carried out at conversions below 7%, which are far from thermodynamic equilibrium (15% with a CH₃OH selectivity of 43%)⁶ under the given reaction condition. The intrinsic formation rate for CH₃OH is 1.3 g h^{-1} g_{Cu}⁻¹ for Cu-Ga/SiO₂ that is 4 times higher than Cu/SiO₂ and also slightly higher than Cu-Zr/SiO₂ (Fig. 2a). Note that the product formation rates on the support itself (Ga^{III}@SiO₂) are below detection limits. The intrinsic CO formation rate of Cu-Ga/SiO₂ (0.1 g h⁻¹ g_{Cu}⁻¹) is 3 times lower as compared to Cu/SiO_2 or $Cu-Zr/SiO_2$ (0.3 g h⁻¹ g_{Cu}^{-1}), making Cu-Ga/SiO₂ a better catalysts with an improved selectivity to CH_3OH products of 93% ($CH_3OH/DME = 30$) with only 7% of CO. The formation of DME likely arise from the subsequent dehydration of CH₃OH, indicating a significant Lewis acidity for this support (vide supra).45 Remarkably, Cu-Ga/ SiO₂ shows a higher CH₃OH selectivity than unpromoted Cu/ SiO₂ (48%) or even Cu-Zr/SiO₂ (77%).³⁴ At longer contact times (Fig. S14[†]), both CH₃OH and CO formation rates decrease (with a slightly larger decrease for CH₃OH formation rates (Fig. S14[†])), suggesting product inhibition for both processes for Cu-Ga/SiO₂. The decrease of activity with contact time is a key limiting factor for a high productivity of CH₃OH for the Cu-Ga/SiO₂ catalyst. The product inhibition is likely associated with the blocking of Lewis acidic Ga^{III} sites by H₂O/CH₃OH that in turn reduces CH₃OH and CO formation rates. Note that in case of Cu/SiO2, where no Lewis acidic (interfacial) sites are present to assist the conversion of CO2, CH3OH and CO formation rates remain independent of contact time. Product inhibition was also observed for the related Cu-Ti/SiO2 and Cu-Zr/SiO₂ catalysts. However, the major difference between Cu-Ti/ SiO₂ or Cu-Zr/SiO₂ and Cu-Ga/SiO₂ is that in the former cases, the contact time affects the CH₃OH formation rates more than CO formation rates, leading to a decrease of CH₃OH selectivity. This dramatic decrease of selectivity is not observed for Cu-Ga/ SiO₂, also indicating that CO likely forms via different mechanisms. A high selectivity toward CH₃OH is maintained for Cu-Ga/SiO₂ (>89%; taking into account DME that is initially formed from CH₃OH) at ca. 3% conversions vs. 71% and 60% selectivity for Cu-Ti/SiO₂ and Cu-Zr/SiO₂, respectively at the same conversion (Fig. 2b and S15[†]). After 30 hours of reaction, Cu-Ga/SiO₂ deactivates for both CH₃OH and CO formation by 75% and 80%, respectively. Analysis of the spent catalyst shows a similar particle size distribution by TEM for Cu-Ga/SiO₂ of 4.9 ± 1.6 nm compared to the fresh catalyst (Fig. S16†). The absence of any crystalline phases by powder X-ray diffraction (Fig. S3†) further indicates the absence of significant sintering throughout the catalytic testing. The deactivation of the catalyst could originate from a slightly decreased amount of accessible metal sites as shown by N_2O titration of the fresh/spent catalyst (Table S1†).

In situ X-ray absorption spectroscopy

The role of gallium, especially the effect of metal alloy formation and its consequence in promoting the selective formation of CH₃OH, were further investigated by *in situ* XAS at the copper K-edge and the gallium K-edges for **Cu-Ga/SiO**₂ (Fig. 3). The Xray absorption spectra are first recorded after oxidation of the catalyst in air, followed by reduction at 300 °C under H₂. The reduced catalyst was then cooled down to 230 °C and the reaction gas consisting of CO₂ and H₂ (1 : 3) was introduced at 1 bar and then pressurized to 5 bar.

The XANES spectrum of Cu-Ga/SiO₂ at the gallium K-edge after reduction under H₂ shows a decreased white line intensity and the appearance of a feature at lower energy (10 368 eV) indicative of reduced gallium sites.42 The XANES spectrum has a lower intensity of the feature at that energy (10 368 eV) compared to the as-prepared catalyst, indicating that the gallium sites are more difficult to reduce following exposure to air. The feature toward lower energy associated with reduced gallium sites only appears when copper is present and is not observed for Ga^{III}@SiO₂ treated under H₂ (Fig. S17[†]). Changes in Ga^{III}@SiO₂ during in situ XAS is only due to changes in the oxygen coordination number upon heating at high temperature most likely due to removal of water (due to exposure to air) according to EXAFS fitting (Table S2 and Fig. S18-S20[†]). The absence of reduced gallium sites for the material without copper (Ga^{III}@SiO₂) suggests that copper, most likely in close interaction with gallium, is necessary to reduce Ga^{III} to Ga⁰. Under reaction conditions at 5 bar $(1:3 \text{ ratio of } CO_2:H_2)$, the white line intensity increases and the feature toward lower energy disappears, indicating full oxidation of gallium sites (Fig. 4).

Copper is fully reduced upon reaction with H_2 at 300 °C and under reaction condition according to XAS (Fig. S21†). Furthermore, Lewis acidic surface sites are present in the catalysts after exposure to air followed by reduction as shown by



Fig. 2 (a) Intrinsic formation rates for CO, CH₃OH and DME and (b) overall CH₃OH selectivity vs. conversion for Cu/SiO₂, Cu-Zr/SiO₂ and Cu-Ga/SiO₂.



Fig. 3 In situ XANES spectrum (left) and its first derivative (right) at the gallium K-edge for Cu-Ga/SiO₂ under air at room temperature, reduced at 300 °C under H₂ and under reaction conditions at 5 bar with CO₂ : H₂ : N₂ (1 : 3 : 1) at 230 °C.



Fig. 4 Fraction of gallium sites on Cu-Ga/SiO₂ of the as prepared catalyst and under reaction condition according XAS.

pyridine adsorption and IR spectroscopy (Fig. S22†). This data suggests that the Lewis acidic sites from Ga^{III} would be responsible for the promotion of CH₃OH synthesis, similarly to what is observed for Cu/ZrO₂ or related Cu-Zr/SiO₂.^{17,34}

Ex situ solid state NMR spectroscopy

In order to determine possible intermediates on gallium under reaction conditions, ¹H-¹³C HETCOR spectra of Cu-Ga/SiO₂ (reduced after exposure to air) are recorded after reacting the catalyst with 5 bar of ${}^{1}\text{H}_{2}$: ${}^{13}\text{CO}_{2}$ (3 : 1) for 12 hours at 230 °C followed by evacuating the gas phase under high vacuum (10^{-5}) mbar) at room temperature. The NMR spectra of Cu-Ga/SiO2 shows a cross-peak at around 3/50 ppm (¹H/¹³C), which is indicative of methoxy species (Fig. S23[†]) and the presence of dimethyl ether as evidenced by the additional cross-peak at 3/60 ppm $({}^{1}H/{}^{13}C)$ (Fig. S23[†]), consistent with the observed formation of dimethyl ether during catalysis. Notably, no formate species on Lewis acidic gallium sites (present in the case of Cu/ZrO₂, Cu-Zr/ SiO₂, Cu-Ti/SiO₂ or Cu/Al₂O₃ systems)^{6,17,34,35} are observed, indicating that Ga^{III} Lewis acidic sites possibly favor the subsequent hydrogenation of formate into methoxy species and/or increase the thermodynamic stability of methoxy in comparison to formate species. This is also confirmed by the IR spectra of the ex *situ* Cu-Ga/SiO₂ sample after reacting with ${}^{1}H_{2}/{}^{13}CO_{2}$ (Fig. S24[†]) showing the ¹³C-H stretches at around 2954 and 2855 cm⁻¹

indicating the presence of methoxy, while no band associated with formate species are observed. While formate species are also likely formed as reaction intermediates on $Cu-Ga/SiO_2$ under reaction condition, the lower stability of formate compared to methoxy would be consistent with (and explains) the higher CH_3OH selectivity of this material in contrasts to other systems. Indeed, stable formate species have been shown to be able to generate methyl formate that readily decomposes into $CO.^6$ Further work is needed to investigate the formation (or not) of formate species as key intermediate in this $Cu-Ga/SiO_2$ system.

Conclusions

The use of SOMC was explored in order to understand the promotional effect of gallium in Cu-based CO₂ hydrogenation catalysts, starting from well-defined silica-supported Ga^{III} sites as an initial support. This approach generates small and narrowly distributed silica-supported CuGax nanoparticles along with residual Ga^{III} Lewis acidic sites. This is in contrast to previously studied well-defined isolated Zr^{IV} and Ti^{IV} sites on SiO₂ that yield Cu nanoparticles surrounded with isolated metal interfacial sites.34,35 These materials are readily oxidized to generate the corresponding CuO and Ga^{III} sites upon exposure to air, but can be partially reduced back to $CuGa_x$ alloys under H_2 . These $CuGa_x$ systems display improved catalytic performances in the hydrogenation of CO₂, allowing the increase in the overall CH₃OH $(CH_3OH + DME)$ selectivity (up to *ca.* 90%) at higher conversion (3%) by comparison with the benchmark catalysts, Cu-Zr/SiO₂ and Cu-Ti/SiO2. Under reaction conditions, the silica-supported CuGa_r de-alloys yielding Cu nanoparticles and Ga^{III} sites indicating that the increased activity and selectivity is likely due to an increased interfacial area between Cu⁰ and Ga^{III}O_x that would promote CH₃OH formation. In fact, methoxy surface species are the only observed intermediates according to ex situ solid state NMR or IR. This study overall shows the subtle difference between promoters; it opens new ways to tailor CH₃OH selective catalysts. We are currently exploring other promoters to understand their role and to design improved CO₂ hydrogenation catalysts via a more rational design.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

E. L., G. N., K. L., D. L. and P. W. were supported by the SCCER Heat and Energy Storage program (InnoSuisse). We acknowledge PSI Super-XAS for beamtime (proposal #20180825). Scott R. Docherty (ETH Zürich) and Jan Alfke (ETH Zürich) are acknowledged for helpful discussions and assistance in the processing of the XAS data.

References

- 1 G. A. Olah, A. Goeppert and G. K. Surya Prakash, *Beyond Oil* and Gas: The Methanol Economy, Wiley-VCH, Weinheim, Germany, 2nd edn, 2011.
- 2 A. Goeppert, M. Czaun, J.-P. Jones, G. K. Surya Prakash and G. A. Olah, *Chem. Soc. Rev.*, 2014, **43**, 7995–8048.
- 3 A. Olah George, Angew. Chem., Int. Ed., 2012, 52, 104-107.
- 4 J. Artz, T. E. Müller, K. Thenert, J. Kleinekorte, R. Meys,
 A. Sternberg, A. Bardow and W. Leitner, *Chem. Rev.*, 2018, 118, 434–504.
- 5 A. Álvarez, A. Bansode, A. Urakawa, A. V. Bavykina, T. A. Wezendonk, M. Makkee, J. Gascon and F. Kapteijn, *Chem. Rev.*, 2017, **117**, 9804–9838.
- 6 E. Lam, J. J. Corral-Pérez, K. Larmier, G. Noh, P. Wolf, A. Comas-Vives, A. Urakawa and C. Copéret, *Angew. Chem., Int. Ed.*, 2019, **58**, 13989–13996.
- 7 A. Y. Rozovskii and G. I. Lin, Top. Catal., 2003, 22, 137-150.
- 8 K. T. Jung and A. T. Bell, Catal. Lett., 2002, 80, 63-68.
- 9 A. Baiker, M. Kilo, M. Maciejewski, S. Menzi and A. Wokaun, *Stud. Surf. Sci. Catal.*, 1993, **75**, 1257–1272.
- 10 M. Behrens, F. Studt, I. Kasatkin, S. Kühl, M. Hävecker, F. Abild-Pedersen, S. Zander, F. Girgsdies, P. Kurr, B.-L. Kniep, M. Tovar, R. W. Fischer, J. K. Nørskov and R. Schlögl, *Science*, 2012, **336**, 893–897.
- J. Schumann, T. Lunkenbein, A. Tarasov, N. Thomas, R. Schlögl and M. Behrens, *ChemCatChem*, 2014, 6, 2889– 2897.
- 12 J. D. Grunwaldt, A. M. Molenbroek, N. Y. Topsøe, H. Topsøe and B. S. Clausen, *J. Catal.*, 2000, **194**, 452–460.
- 13 S. Kuld, M. Thorhauge, H. Falsig, C. F. Elkjær, S. Helveg, I. Chorkendorff and J. Schested, *Science*, 2016, 352, 969–974.
- 14 T. Lunkenbein, J. Schumann, M. Behrens, R. Schlögl and M. G. Willinger, *Angew. Chem., Int. Ed.*, 2015, **54**, 4544–4548.
- 15 J. Toyir, P. Ramírez de la Piscina, J. L. G. Fierro and N. s. Homs, *Appl. Catal.*, B, 2001, 34, 255–266.
- 16 J. Toyir, P. Ramírez de la Piscina, J. L. G. Fierro and N. s. Homs, Appl. Catal., B, 2001, 29, 207–215.
- 17 K. Larmier, W. C. Liao, S. Tada, E. Lam, R. Verel, A. Bansode, A. Urakawa, A. Comas-Vives and C. Copéret, *Angew. Chem., Int. Ed.*, 2017, **56**, 2318–2323.
- 18 K. Samson, M. Śliwa, R. P. Socha, K. Góra-Marek, D. Mucha, D. Rutkowska-Zbik, J. F. Paul, M. Ruggiero-Mikołajczyk, R. Grabowski and J. Słoczyński, ACS Catal., 2014, 4, 3730– 3741.
- 19 J. F. Edwards and G. L. Schrader, *J. Phys. Chem.*, 1984, 88, 5620–5624.

- 20 T. Fujitani, I. Nakamura, T. Uchijima and J. Nakamura, *Surf. Sci.*, 1997, **383**, 285–298.
- 21 O. Martin, C. Mondelli, A. Cervellino, D. Ferri, D. Curulla-Ferré and J. Pérez-Ramírez, *Angew. Chem., Int. Ed.*, 2016, 55, 11031–11036.
- 22 F. Arena, G. Italiano, K. Barbera, S. Bordiga, G. Bonura, L. Spadaro and F. Frusteri, *Appl. Catal., A*, 2008, **350**, 16–23.
- 23 E. Lam, K. Larmier, S. Tada, P. Wolf, O. V. Safonova and C. Copéret, *Chin. J. Catal.*, 2019, **40**, 1741–1748.
- 24 S. Kuld, C. Conradsen, P. G. Moses, I. Chorkendorff and J. Sehested, *Angew. Chem., Int. Ed.*, 2014, 53, 5941–5945.
- 25 A. Le Valant, C. Comminges, C. Tisseraud, C. Canaff, L. Pinard and Y. Pouilloux, *J. Catal.*, 2015, **324**, 41–49.
- 26 C. Tisseraud, C. Comminges, T. Belin, H. Ahouari, A. Soualah, Y. Pouilloux and A. Le Valant, *J. Catal.*, 2015, **330**, 533–544.
- 27 J. Nakamura, Y. Choi and T. Fujitani, *Top. Catal.*, 2003, 22, 277–285.
- 28 P. C. K. Vesborg, I. Chorkendorff, I. Knudsen, O. Balmes, J. Nerlov, A. M. Molenbroek, B. S. Clausen and S. Helveg, *J. Catal.*, 2009, 262, 65–72.
- 29 P. L. Hansen, J. B. Wagner, S. Helveg, J. R. Rostrup-Nielsen,
 B. S. Clausen and H. Topsøe, *Science*, 2002, 295, 2053–2055.
- 30 J. C. Medina, M. Figueroa, R. Manrique, J. Rodríguez Pereira, P. D. Srinivasan, J. J. Bravo-Suárez, V. G. Baldovino Medrano, R. Jiménez and A. Karelovic, *Catal. Sci. Technol.*, 2017, 7, 3375–3387.
- 31 C. Copéret, Acc. Chem. Res., 2019, 52, 1697-1708.
- 32 C. Copéret, Nat. Energy, 2019, 4, 1018-1024.
- 33 C. Copéret, A. Comas-Vives, M. P. Conley, D. P. Estes,
 A. Fedorov, V. Mougel, H. Nagae, F. Núñez-Zarur and
 P. A. Zhizhko, *Chem. Rev.*, 2016, **116**, 323–421.
- 34 E. Lam, K. Larmier, P. Wolf, S. Tada, O. V. Safonova and C. Copéret, J. Am. Chem. Soc., 2018, 140, 10530–10535.
- 35 G. Noh, E. Lam, J. L. Alfke, K. Larmier, K. Searles, P. Wolf and C. Copéret, *ChemSusChem*, 2019, **12**, 968–972.
- 36 K. H. Lee and J. S. Lee, *Korean J. Chem. Eng.*, 1995, **12**, 460–465.
- 37 C. Liu, X. Guo, Q. Guo, D. Mao, J. Yu and G. Lu, *J. Mol. Catal.* A: Chem., 2016, 425, 86–93.
- 38 S. Kattel, B. Yan, Y. Yang, J. G. Chen and P. Liu, J. Am. Chem. Soc., 2016, 138, 12440–12450.
- 39 G. Noh, S. R. Docherty, E. Lam, X. Huang, D. Mance, J. L. Alfke and C. Copéret, *J. Phys. Chem. C*, 2019, **123**, 31082–31093.
- 40 K. Searles, K. W. Chan, J. A. Mendes Burak, D. Zemlyanov,
 O. Safonova and C. Copéret, *J. Am. Chem. Soc.*, 2018, 140, 11674–11679.
- 41 J. P. Dombrowski, G. R. Johnson, A. T. Bell and T. D. Tilley, *Dalton Trans.*, 2016, **45**, 11025–11034.
- 42 K. Searles, G. Siddiqi, O. V. Safonova and C. Copéret, *Chem. Sci.*, 2017, **8**, 2661–2666.
- 43 S. Brunauer, P. H. Emmett and E. Teller, *J. Am. Chem. Soc.*, 1938, **60**, 309–319.
- 44 E. P. Parry, J. Catal., 1963, 2, 371-379.
- 45 R. S. Schiffino and R. P. Merrill, *J. Phys. Chem.*, 1993, **97**, 6425–6435.