

CORRECTION

[View Article Online](#)
[View Journal](#) | [View Issue](#)



Cite this: *J. Mater. Chem. A*, 2020, **8**, 1486

DOI: 10.1039/c9ta90299f
rsc.li/materials-a

Correction: Flat-shaped carbon–graphene microcomposites as electrodes for high energy supercapacitors

Gelines Moreno-Fernández,^a Juan L. Gómez-Urbano,^{ab} Marina Enterría,^a Teófilo Rojo^{ab} and Daniel Carriazo  ^{*ac}

Correction for 'Flat-shaped carbon–graphene microcomposites as electrodes for high energy supercapacitors' by Gelines Moreno-Fernández *et al.*, *J. Mater. Chem. A*, 2019, **7**, 14646–14655.

The authors regret a mistake in Table 1 of the published article. The correct version of the Table 1 is shown below.

The authors also wish to amend the following sentences in the original version of the manuscript:

- The sentence "The t-plot method was used to calculate the external surface area (S_{EXT}) in the relative pressure range of 0.07–0.25." included in the physicochemical characterization (page 14648) section should be removed.
- The last sentence of page 14648, where it is written "The increment of S_{EXT} ..." should say "The increment of V_{meso} ..."
- The text on line 7, page 14649 which reads "The isotherm of the activated material also presents a marked micropore contribution but, as evidenced by V_{meso} and S_{EXT} values (Table 1) some narrow mesoporosity is generated during activation." should instead read as follows: "The isotherm of the activated material also presents a marked micropore contribution but, as evidenced by V_{meso} values (Table 1) some narrow mesoporosity is generated during activation".

The authors acknowledge Dr Teresa Centeno, INCAR-CSIC (Spain) for detecting these errors.

Table 1 Total pore volume (V_T), mesopore volume (V_{meso}), micropore volume (V_{DR}), BET specific surface area (S_{BET}), DFT specific surface area (S_{DFT}), total micropore surface area (S_{DR}), narrow micropore volume (V_{DR}), and narrow micropore specific surface area (S_{DR})

	N_2 ^a						CO_2 ^b	
	V_T ($\text{cm}^3 \text{ g}^{-1}$)	V_{meso} ($\text{cm}^3 \text{ g}^{-1}$)	V_{DR} ^c ($\text{cm}^3 \text{ g}^{-1}$)	S_{BET} ($\text{m}^2 \text{ g}^{-1}$)	S_{DFT} ^d ($\text{m}^2 \text{ g}^{-1}$)	S_{DR} ^e ($\text{m}^2 \text{ g}^{-1}$)	V_{DR} ^c ($\text{cm}^3 \text{ g}^{-1}$)	S_{DR} ^e ($\text{m}^2 \text{ g}^{-1}$)
ResFa	0.37	0.13	0.24	598	720	551	0.19	632
ResFaGO	0.50	0.11	0.39	948	1150	880	0.22	840
ResFaGO-A	1.12	0.21	0.91	1961	1991	1373	0.47	1122

^a Data obtained from N_2 adsorption–desorption isotherms at -196°C . ^b Data obtained from CO_2 adsorption isotherms at 0°C . ^c Data obtained from Dubinin–Raduskevich. ^d Data obtained from the 2D-NLDFT. ^e Data obtained from Dubinin–Raduskevich.

The Royal Society of Chemistry apologises for these errors and any consequent inconvenience to authors and readers.

^aCIC EnergigUNE, Parque Tecnológico de Álava, 01510 Miñano, Álava, Spain. E-mail: dcarriazo@cicenergigune.com; Tel: +34 94 529 71 08

^bUniversidad Del País Vasco, UPV/EHU, 48080 Bilbao, Spain

^cIKERBASQUE, Basque Foundation for Science, 48013 Bilbao, Spain