



Cite this: *Nanoscale Adv.*, 2021, **3**, 5016

Tailoring the defects of sub-100 nm multipodal titanium nitride/oxynitride nanotubes for efficient water splitting performance†

Kamel Eid, *^a Mostafa H. Sliem, ^b and Aboubakr M. Abdullah, *^b

Deciphering the photocatalytic-defect relationship of photoanodes can pave the way towards the rational design for high-performance solar energy conversion. Herein, we rationally designed uniform and aligned ultrathin sub-100 nm multipodal titanium nitride/oxynitride nanotubes (TiON_xNTs) ($x = 2, 4$, and 6 h) via the anodic oxidation of Ti-foil in a formamide-based electrolyte followed by annealing under ammonia gas for different durations. XPS, XPS imaging, Auger electron spectra, and positron annihilation spectroscopy disclosed that the high nitridation rate induced the generation of a mixture of Ti-nitride and oxynitride with various vacancy-type defects, including monovacancies, vacancy clusters, and a few voids inside TiO_xNTs . These defects decreased the bandgap energy to 2.4 eV, increased visible-light response, and enhanced the incident photon-to-current collection efficiency (IPCE) and the photocurrent density of TiON_xNTs by nearly 8 times compared with TiO_2NTs , besides a quick carrier diffusion at the nanotube/electrolyte interface. The water-splitting performance of sub-100 nm TiON_6NT multipodal nanotubes was superior to the long compacted TiON_xNTs with different lengths and TiO_2 nanoparticles. Thus, the optimization of the nitridation rate tailors the defect concentration, thereby achieving the highest solar conversion efficiency.

Received 14th April 2021
Accepted 9th July 2021

DOI: 10.1039/d1na00274k
rsc.li/nanoscale-advances

Introduction

Biofuel,^{1,2} gas conversion reactions,^{3–7} anodic and cathodic reactions (*i.e.*, water splitting,^{8,9} methanol¹⁰/ethanol oxidation,¹ and oxygen reduction^{11,12}) driven by porous catalysts are highly promising green and sustainable energy sources. Porous titanium nanostructures, especially nanotubes, have grabbed appreciable attention in photocatalytic water oxidation, owing to their excellent activity, high surface area, low-density, and abundant active sites.^{13,14} However, the wide bandgap and lower visible light-harvesting characteristics are critical, thus making TiO_2 impractical for solar-driven energy conversion devices.^{15,16} As such, various efforts have been devoted to defeating such barriers, which are based on reducing the bandgap and delaying the recombination of the photogenerated electrons and holes.^{17–19} This can be achieved throughout the creation of various defects inside the lattice structure of TiO_2 *via* its doping with non-metal dopants such as H₂, N, S, Cu, and F.^{20–22} These vacancy-type defects act as electron scavengers that retard the

electron–hole pair recombination and enhance the number of charge carriers without diminishing the crystallinity and/or photocurrent density of TiO_2 .^{23,24} This is in addition to significantly decreasing the bandgap energy of TiO_2 , as well as enhancing the UV-visible light responses. To this end, N-doped porous TiO_2 , in the form of titanium oxynitride (TiON), is of great importance in solar-driven water splitting, owing to the excellent visible-light absorption and suitable bandgap.^{25–28} For example, mesoporous TiON films formed through combining sol–gel chemistry, evaporation-induced self-assembly, flash crystallization, and ammonia treatment displayed superior photocatalytic activity as compared to TiO_2 for the degradation of methylene blue and lauric acid.²⁹ Unlike other porous morphologies, nanotubes have higher surface areas, more active sites, quick charge collection efficiencies, greater UV-visible light responses, and enhanced mass transfer. Also, nanotubes provide various active sites that enhance the adsorption of reactants and the desorption of products.^{30,31} However, the fabrication of porous TiON nanotubes has rarely been reported, and they are not sufficiently emphasized for water-splitting as compared with other nanostructures. For instance, TiON-NTs prepared by the annealing of TiO_2NTs under ammonia exhibited a significant enhancement in the photocurrent density and UV-visible light responses of TiO_2NTs .³²

Likewise, TiON-NTs obtained using the anodization of TiN alloy enhanced the incident photon-to-current collection

^aGas Processing Center, College of Engineering, Qatar University, P. O. Box 2713, Doha, Qatar. E-mail: kamel.eid@qu.edu

^bCenter for Advanced Materials, Qatar University, P. O. Box 2713, Doha, Qatar. E-mail: bakr@qu.edu.qa

† Electronic supplementary information (ESI) available. See DOI: 10.1039/d1na00274k

‡ Contributed equally to this work.



efficiency (IPCE) and visible-light responses substantially as compared to TiO_2 .³³ Despite the significant advances in the fabrication of TiON_x NTs, their photocatalytic-defect relationship was not emphasized and is still unknown. Most of the previous reports focused only on the hydrogenated and/or oxygenated TiO_2 nanocrystals to induce the formation of oxygen vacancies and defects inside the TiO_2 nanostructures.^{34–38} Some studies reported that the photocatalytic efficiency of TiO_2 nanocrystals could be enhanced as the concentration of bulk defects to surface defects decreased due to the improved isolation efficiency of the photogenerated electrons–holes.^{37,39,40} The defects can generate trapping centers that accelerate the electron–hole combination besides deteriorating the crystallinity and/or photocurrents of TiO_2 .^{37,39,41} Thus, the photocatalytic-defect relationship of TiO_2 is hitherto ravelled and ambiguous. Consequently, defect engineering in TiON_x NTs and deciphering the defects-photocatalytic relationship can boost their charge carrier collection efficiency while preserving the crystallinity.⁴² This can also pave the way towards integrating TiON_x NTs into cost-effective and efficient, practical solar-driven water-splitting devices.

Herein ultrathin sub-100 nm multipodal TiON_x NTs nanotubes were fabricated using anodic oxidation followed by annealing under ammonia. The nitridation rate was optimized to tailor the concentration and types of the vacancy-type defects inside TiO_2 NTs. The nature and concentration of the vacancy-type defects were confirmed using various characterization techniques like transmission electron microscopy (TEM), X-ray photoelectron spectroscopy (XPS), X-ray diffraction (XRD), and positron annihilation spectroscopy (PALS). In addition, the photoelectrochemical water splitting performance of the ammonia-annealed TiON_x NTs samples was benchmarked relative to the air-annealed TiO_2 NTs to elucidate the relationship between the photocatalytic performance of the ammonia-annealed TiON_x NTs and air-annealed TiO_2 NTs. Unlike previous reports, our newly designed TiON_x NTs possess various inimitable structure and composition merits, including a porous one-dimensional ultrashort sub-100 nm multipodal nanotube structure that provides a short electron pathway and maximizes the charge collection efficiency. The N-doping in TiO_2 NTs forms a mixture of Ti-nitride and oxynitride with various defects such as monovacancies, vacancy clusters, and a few voids that can reduce the valence band edge and enhance the visible light response of TiON_x NTs. Furthermore, our obtained materials were formed as solid nanosheets ornamented with nanotubes that could be directly used as anodes without additional steps for the activation and/or conversion into working electrodes, which are highly essential features for practical applications.

Experimental

Chemicals and materials

Polyvinylpyrrolidone (PVP, 40 000), titanium foil (0.25 mm thick, purity 99.8%), ammonium fluoride (NH_4F), and formamide were purchased from Sigma-Aldrich Chemie GmbH (Munich, Germany).

Synthesis of TiON_x NTs

A Pt sheet was used as the counter electrode during the anodization of Ti foil in an aqueous formamide solution containing 1.2% of NH_4F , 1.3 wt% PVP, and 3 mL H_2O .⁴³ The anodization process was carried out for 2.5 h in an ice bath at 0 °C under 36 V (0.1 V s⁻¹). First, the current was maintained at 25–27 mA under acidic conditions using 0.1 M acetic acid.⁴³ Then, the as-anodized foils were rinsed thoroughly with distilled water and annealed at 450 °C (2 °C min⁻¹) for 1.5 h under air to obtain TiO_2 NTs. Next, the resultant TiO_2 NTs were annealed under ammonia flow (200 sccm) at 600 °C for 2, 4, and 6 h to form TiON_2 NTs, TiON_4 NTs, and TiON_6 NTs, respectively. The heating and cooling rates were 1 °C min⁻¹.

Material characterization

The morphology and composition of typically synthesized nanotubes were characterized by SEM (Hitachi S-4800, Hitachi, Tokyo, Japan) equipped with energy-dispersive X-ray spectroscopy (EDX) and TEM (TecnaiG220, FEI, Hillsboro, OR, USA). The XPS was measured on an Ultra DLD XPS Kratos, Manchester, UK spectrometer equipped with a monochromatic Al $\text{K}\alpha$ radiation source (1486.6 eV) under a UHV environment ($\text{ca. } 5 \times 10^{-9}$ torr). The Auger electron spectra (AES) were measured on an Ultra DLD XPS spectrometer (Kratos, Manchester, UK) using a high-energy Ag $\text{L}\alpha$ monochromatic X-ray source. The XRD patterns were obtained using an X'Pert-Pro MPD diffractometer (PANalytical Co., Netherlands) with a Cu $\text{K}\alpha$ X-ray source ($\lambda = 1.540598$ Å). The ultraviolet-visible (UV-Vis) diffuse reflectance spectra were obtained using a diffuse reflectance accessory of a UV-vis spectrophotometer (UV2550, Shimadzu, Japan). The positron annihilation lifetime spectroscopy (PALS) was recorded using a ^{22}Na (~ 10 µCi) radioactive positron source.


Water-splitting reaction

The photoelectrochemical measurements were carried out on a Gamry electrochemical analyzer (reference 3000, Gamry Co., USA) using a conventional three-electrode photo-glass cell involving a platinum wire as the counter electrode, reversible hydrogen electrode (RHE) (reference electrode), and our prepared samples were used as working electrodes. The sunlight was simulated with a xenon ozone-free lamp (100 W) (Abet Technologies, USA) and AM 1.5G filter at 100 mW cm⁻². All the measured currents were normalized to the geometric area of the working-electrodes, and all potentials were recorded after the *IR*-drop correction.

Results and discussion

TiO_2 NTs were initially synthesized *via* the electrochemical anodization of titanium foils in the formamide-based electrolyte and then were annealed under ammonia gas for different durations (Scheme 1).^{42,43} The formamide, with its remarkable ability to control the electrolyte solution's viscosity and conductivity, prevents the current oscillation due to the “in-pore” local pH variation providing favorable conditions for tailoring the fabrication of ordered, aligned, and oriented thin-





Scheme 1 The formation process of TiO₂NTs and TiON₂NTs, TiON₄NTs, and TiON₆NTs.

walled multipodal nanotubes. The solution pH was adjusted by adding 0.1 M acetic acid, and 1 wt% of PVP was used for structural stability.⁴³ The electrolyte solution should be mixed well under heating at 100 °C before the anodization process to ensure the mixing of the precursors and avoid the precipitation of NH₄F. Fig. 1a reveals the SEM image of the typically synthesized TiO₂NTs. The nanotube arrays were formed in well-ordered, homogeneous, and vertically aligned nanotubes without noticeable debris or distortion. The side view shows that the nanotubes are multipodal with two or more legs, as indicated by the dashed circles (Fig. 1b). The average nanotube length was about 80 ± 2 nm, the pore diameter was 12 ± 1 nm, and the wall thickness was 3–5 nm (Fig. 1b). The as-formed TiO₂NTs were annealed under ammonia gas for 2, 4, and 6 h

to form TiON₂NTs, TiON₄NTs, and TiON₆NTs, respectively (Fig. 1c–e). Interestingly, the ammonia-annealed samples retained their porous nanotube structures without any alteration in the morphology and/or dimensions but with only a slight tight packing at a high nitridation rate (6 h). This confirmed the structural stability of the as-synthesized NTs.

The composition of the as-synthesized materials was investigated by the EDX analysis, which demonstrated the presence of Ti and O in TiO₂NTs with atomic content of 33.9 and 66.1%. The ammonia-annealed samples revealed Ti, O, and an additional N peak. The intensity of the N peak increased with increasing the nitridation time, as indicated by the dashed square (Fig. 1f). From EDX analysis, the estimated N-content in TiON₂NTs, TiON₄NTs, and TiON₆NTs was determined to be 1.7, and 3.2, and 4.9%, respectively. The as-made NTs were immersed in hydrochloric acid to peel off the NTs from the sheets. Fig. 2a shows the TEM image of TiO₂NTs, which demonstrates the porous nanotube morphology. The high-resolution TEM (HR-TEM) image of TiO₂NTs showed the crystalline anatase phase structure. The interplanar distance (*d*-spacing) was determined to be 3.57 Å, assigned to the 101 facets of TiO₂ anatase (Fig. 2b). The selected area electron diffraction (SAED) pattern disclosed the set of the typical rings attributed to the (011), (004), (020), (015), (024), (220), and (125) facets of anatase TiO₂, agreeing with previous reports.⁴⁴ After nitridation, the TiON₂NTs, TiON₄NTs, and TiON₆NTs, preserved their porous nanotube morphology (Fig. 2c, e and g). The HRTEM images of ammonia-annealed samples showed their amorphous crystalline structure. Intriguingly, the determined *d*-spacings were about 0.354, 0.352, 0.350, and 0.346 nm in TiO₂NTs, TiON₂NTs, TiON₄NTs, and TiON₆NTs, respectively, assigned to the facets of anatase (Fig. 2d, f and h).²⁵ The slight




Fig. 1 SEM image of the typically prepared (a and b) TiO₂-NTs, (c) TiON₂NTs, (d) TiON₄NTs, and (e) TiON₆NTs. (f) EDX of the typically synthesized materials.






Fig. 2 (a, c, e and g) TEM images and (b, d, f and h) HRTEM images of TiO_2 NTs, TiON_2 NTs, TiON_4 NTs, and TiON_6 NTs, respectively, and their SAED patterns are shown as insets. The indicated scale bars in the insets of (b, d, f and h) are 5 nm.

decrease in the d -spacing of ammonia-annealed NTs relative to air-annealed NTs plausibly originated from the Ti–N and/or TiON legend effect, which compresses the lattice spacing of TiO_2 . Notably, although the surface-disordered domain was boosted clearly at a high nitridation rate, there was no phase transformation in the lattice structure, suggesting their stability. Simultaneously, the SAED exhibited the typical rings associated with the (110), (111), (020), (015), (022), (220), and (113) facets of a mixture of anatase, TiN, and TiON phases (Fig. 2d, f and h).

The crystalline structures of the as-synthesized TiON_x NTs as compared to TiO_2 NTs were investigated *via* XRD analysis (Fig. 3). The air-annealed TiO_2 NTs showed the main characteristic diffraction peaks attributed to the tetragonal phase matched with (ICSD: 172914) along with some peaks of

tetragonal rutile (ICSD: 33838) (Fig. 3a). After the nitridation, there was a notable change in the XRD patterns in the formed TiO_x NTs. In the TiO_x NTs the diffraction patterns of TiO_2 (011), (020), and (220) were disappeared, whereas the (131) and (222) of TiON (ICSD: 426340) were observed, along with the enhancement in the intensity of (111), (020), (022), and (113) of TiN (ICSD: 236801) (Fig. 3a).

The TiN peaks overlapped with the TiO_2 peaks, which is in line with other reports.^{33,42,45} However, the intensity of the (020) (Fig. 3b) and (220) peaks of TiN (Fig. 3c) and their full width at the half maximum (FWHM) increased significantly with the increasing nitridation time as indicated by the dashed lines, due to the incorporation of N into the TiO_2 lattice structure resulting in the formation of crystal defects. The estimated FWHM of TiON_6 -NTs (0.142°) is larger than that of TiON_4 NTs (0.139°), TiON_2 NTs




Fig. 3 (a) XRD analysis of TiO_2 NTs and TiON_x NTs, (b) magnification of the (020) peak and (c) magnification of A (220). The yellow line represents TiO_2 anatase (ICSD: 172914), green line represents TiN (ICSD: 236801), and the red line represents TiON (ICSD: 426340).



(0.135°) and TiO_2 NTs (0.13°) from (022) peak. That is also obvious in the increment of the lattice parameters of TiON_6 NTs (4.245 Å), TiON_4 NTs (4.223 Å), and TiON_2 NTs (4.173 Å) relative to TiON_2 NTs (4.112 Å), implying the expansion of the crystal lattice with the increased N content, in agreement with previous reports.⁴⁵

The average crystallite size of TiON_6 NTs (12.1 nm) is larger than that of TiON_4 NTs (10.5 nm), TiON_2 NTs (9.1 nm), and TiO_2 NTs (7.2 nm) as determined from the half-peak width of the XRD peak by applying the Scherrer equation ($L = 0.89\lambda/\beta \cos \theta$). The increment of the crystallite size is due to the increase of the annealing time as reported elsewhere.^{43,46}

The valence states, surface composition, and defect-states of the typically fabricated samples were investigated by XPS analysis (Fig. 4). The binding energies of Ti, O, and N and the N-content of the as-synthesized materials are given in (Table S1†). The XPS of TiO_2 NTs revealed the Ti 2p and O 1s core-level, while the ammonia-annealed TiON_x NTs showed the core-level of Ti 2p, O 1s, and N 1s (Fig. 4a). The intensity of the N 1s peak increased with increasing the nitridation time as indicated by the dashed square and the inset in Fig. 4a. The high-resolution Ti 2p spectra of TiO_2 NTs revealed only two peaks assigned to Ti^{2+} (458.4 eV) and Ti^{3+} (464.3 eV) representing a Ti^{4+} oxidation state (Fig. 4b). The high-resolution XPS spectra of Ti 2P in the ammonia-annealed NTs exhibited additional peaks of TiN (455.5 and 461.3 eV) assigned to the Ti^{3+} defect sites, and TiON peaks (457.2 and 462.7 eV) attributed to the Ti^{2+} defect sites, and a small shoulder for TiO_2 (Ti^{2+} at 458.4 and Ti^{3+} at 464.3 eV) (Fig. 4b and Table S1†), indicating that Ti^{3+} and Ti^{2+} are the main phases in TiON_x NTs samples. The intensities of Ti^{3+} and Ti^{2+} defect sites peaks of TiON samples were significantly higher as compared with Ti^{4+} , lower than those of TiN and TiON , and most of the oxide was transformed into oxynitride after ammonia-annealing. Also, the defects of Ti^{3+} were greater as compared with both Ti^{2+} and Ti^{4+} , as indicated by its FWHM. Interestingly, the FWHM of TiN and

TiON peaks in TiON_x NTs increased significantly with increasing the nitridation times, implying the increase in Ti^{3+} and Ti^{2+} defect sites as indicated by the dashed lines in (Fig. 4b). This was attributed to the insertion of N atoms into the lattice structure of TiO_2 , resulting in the replacement of oxygen atoms or the formation of the nitride and oxynitride phase, as was shown by the red-shift in the Ti 2p spectra of ammonia-annealed TiON_x NTs at longer nitridation times. This was due to the N-dopant with less electronegativity being introduced into the crystal lattice of TiO_2 , resulting in the increase in the electron cloud density around Ti and converting Ti^{4+} into Ti^{3+} and Ti^{2+} (Fig. 4b). The O 1s spectra in air-annealed TiO_2 NTs showed three peaks ascribed to the lattice oxygen (Ti-O) at 530.2 eV, the oxygen in the adsorbed hydroxyl (Ti-OH) at 532.1 eV, and O_{ads} at 532.4 eV. The ammonia-annealed TiON_x NTs revealed TiO, O-N, and O_{ads} (Fig. 4c). The disappearance of the Ti-OH peak in TiON_x NTs is due to the neutralization of the oxygen vacancies in TiO_2 , which decreased the concentration of Ti^{4+} and increased the Ti^{3+} and Ti^{2+} defects at a high nitridation rate. This is seen in the lower stoichiometry of ammonia-annealed samples TiON_2 NTs (1.5), TiON_4 NTs (1.42), and TiON_6 NTs (1.4) as compared to the air-annealed TiO_2 NTs (1.8).

The N 1s spectra of TiON_x NTs showed mainly doublet peaks attributed to TiN at 397.3 eV and TiON at 399.0 eV, along with small shoulders around 399 eV, attributed to γ -N, indicating the chemisorption of N_2 , and at 402.0 eV corresponding to β -N states state, indicating the atomic N-doping in the form of the oxynitride TiON shoulder (Fig. 4d and Table S1†). Notably, increasing the annealing time resulted in a significant enhancement in the intensity and FWHM of TiON and TiN peaks, indicating the higher N content. Thus, annealing under ammonia led to the substitution of some O-sites by N, in line with previous reports on N-doped TiO_2 ,^{28,33,42} as shown by the increase in the N content with increasing the nitridation rate. The estimated amounts of N were about 1.9, 3.1, and 4.5% in




Fig. 4 (a) XPS surveys of the as-synthesized materials and their high-resolution XPS spectra of (b) Ti 2p, (c) O 1s, (d) N 1s of TiO_2 NTs and TiON_x NTs before etching.



TiON_2NTs , TiON_4NTs , and TiON_6NTs , respectively, in line with the EDX. To gain further insight into the electronic structure and valence states of the formed materials, XPS was conducted after etching 4 times (Fig. S1 and Table S1†). The XPS surveys showed the same peaks as before etching, including the Ti 2p and O 1s core-level in TiO_2NTs , and Ti 2p, O 1s, and N 1s in TiON_xNTs (Fig. S1a†). The high-resolution Ti 2p spectra of TiO_2NTs revealed two peaks assigned to $\text{Ti} 2p_{3/2}$ and $\text{Ti} 2p_{1/2}$, representing a Ti^{4+} oxidation state (Fig. S1b†). Interestingly, the high-resolution XPS spectra of Ti 2P in TiON_xNTs displayed TiN assigned to Ti^{3+} defect sites and TiON attributed to Ti^{2+} defect sites, and a small shoulder for TiO_2 (Fig. S1b and Table S1†). The TiN and TiON still existed after etching, contributing to the presence of Ti^{3+} and Ti^{2+} defect sites in the bulk, which is important for proving the various active sites, trapping sites, and delaying the electron-hole recombination during water oxidation. The spectra after etching became wider with lower intensities than before etching, which is plausible due to the lower N-content in the bulk. However, the intensity of Ti^{3+} and Ti^{2+} defect sites of TiON_xNTs samples remained significantly higher than that of Ti^{4+} . This is seen in the red-shifted Ti 2p spectra in the ammonia-annealed TiON_xNTs at higher nitridation times. The O 1s spectra in air-annealed TiO_2NTs showed $\text{Ti}-\text{O}$ and O_{ads} , while ammonia-annealed TiON_xNTs revealed TiO , $\text{O}-\text{N}$, and O_{ads} (Fig. S1c†). The N 1s spectra of TiON_xNTs displayed TiN and TiON and adsorbed $\gamma\text{-N}$ (Fig. S1d†). The estimated amount of N was about 1.1, and 1.9, and 2.6% in TiON_2NTs , TiON_4NTs , and TiON_6NTs , respectively, which indicated the homogenous distribution of N in the bulk and surface.

The XPS mapping was used to further investigate the composition of the obtained materials (Fig. 5a–d). The results indicate the good distribution of Ti and O in the air-annealed TiON_xNTs (Fig. 5a), while Ti, O, and N were homogeneously distributed in ammonia-annealed TiON_xNTs (Fig. 5b–d). The N content in TiON_xNTs increased with increasing the annealing time, as shown by the increasing number of red dots in (Fig. 5b–d). These imply the significant effect of ammonia-annealing on the creation of various Ti^{3+} and Ti^{2+} defects. That is also seen in the Auger electron spectroscopy recorded using a 3 kV electron beam with a current of 300 nA (Fig. 5e–g). Fig. 5e shows the AES spectra of TiLMM for air annealed TiO_2NTs and TiON_xNTs , which all displayed the presence of doublet peaks assigned to $\text{TiL}_3\text{M}_{2,3}\text{M}_{4,5}$ at (413 and 418 eV).^{47,48} The intensity of $\text{TiL}_3\text{M}_{2,3}\text{M}_{4,5}$ in the TiON_xNTs increased with increasing the annealing time under ammonia, which was plausibly attributed to the increasing Ti^{3+} and Ti^{2+} defect sites resulting from the integration of N atoms. This is seen in the appearance of a small shoulder at 397 eV, assigned to TiN in the TiON_xNTs .^{49,50} The intensity of the TiN peak increased slightly with increasing the nitridation time as shown in the inset in Fig. 5e. The difference in the intensities of the TiN peak is not high because the N contents in the ammonia-annealed TiON_xNTs are too close. The OKLL spectra revealed $\text{OKL}_1\text{L}_{2,3}(^1\text{p})$ and $\text{OKL}_{2,3}\text{L}_{2,3}$ with a kinetic value of 492 eV and 511 eV, respectively (Fig. 5f). Additionally, two small humps were seen at 479 and 501 eV, assigned to OKL_1L_1 and $\text{OKL}_1\text{L}_{2,3}(^3\text{p})$, respectively, due to the replacement of O with N to form the Ti-ON bond and Ti-Nbond.^{51–53} This is seen in the resolution of the N KVV spectra, including $\text{N KL}_1\text{L}_1$, $\text{KL}_1\text{L}_{2,3}$, and $\text{KL}_{2,3}\text{L}_{2,3}$ at 352, 362, and 384 eV, respectively in the TiON_xNTs , and the intensity of N KVV




Fig. 5 XPS elemental mapping analysis for (a) TiO_2NTs , (b) TiON_2NTs , (c) TiON_4NTs , and (d) TiON_6NTs . The green, blue, and red dots represent Ti, O, and N, respectively. Auger electron spectra (AES) of (e) Ti LMM, (f) O KLL, (g) N KLL.



increased with increasing the nitridation time (Fig. 5g) resulting from the incorporation of N into the TiO_2 lattice to form Ti^{3+} TiN , and Ti^{2+} TiON defect sites.^{28,54,55} Notably, the nitridation for 2, 4, and 6 h are the optimum periods to allow N-doping without affecting the nanotube shape. This is because the nanotubes showed significant debris and distortion when the nitridation time increased to 8 h.

Fig. 6a exhibits the UV-Vis absorption spectra of typically synthesized air-annealed and ammonia-annealed TiON_x NTs. The air-annealed TiO_2 NTs showed an absorption wavelength of around 410 nm. The ammonia-annealed NTs revealed a substantial blue shift in the absorption wavelength from 590 to 520 nm in the visible region. Intriguingly enough, the positive shift in the absorption wavelengths increased remarkably at a high nitridation rate. This is due to the substitution of some oxygen sites by nitrogen, enhancing the visible light absorption efficiency of ammonia-annealed NTs as compared to TiO_2 NTs. This was further observed in the lower bandgap energy of ammonia-annealed NTs as compared with TiO_2 NTs. Regarding this, the bandgap energy of TiO_2 NTs (3.1 eV) was substantially greater than that of TiON_2 NTs (2.8 eV), TiON_4 NTs (2.6 eV), and TiON_6 NTs (2.4 eV) as calculated using Tauc plots (Fig. S2†).

The incident photon to current conversion (IPCE) was measured in a two-electrode cell using air-annealed and ammonia-annealed NTs as working electrodes and a platinum wire as a counter electrode in 0.1 M KOH solution. The IPCE was calculated using the following equation:

$$\text{IPCE} = [1240 \times j_{\text{ph}}/\lambda \times I] \times 100$$

where j_{ph} is the photocurrent density under illumination at a wavelength λ , and I is the light intensity. Fig. 6b demonstrates the IPCE percentage for the as-made NTs as a function of the irradiation wavelengths. The photocurrent responses of ammonia-annealed TiON_x NTs were significantly higher as compared to air-annealed TiO_2 NTs (Fig. 6b). The responses increased at a high N-content, agreeing with the UV-vis absorption results. Indeed, the TiON_2 NTs, TiON_4 NTs, TiON_6 NTs, and TiO_2 NTs achieved IPCEs of 12.18, 20.72, 34.74, and 4.08% at 508, 509, 520, and 488 nm, respectively (Fig. 6b). The ammonia-annealed NTs exhibited a greater IPCE efficiency at earlier wavelengths than that of TiO_2 NTs, indicating the quick

response kinetics and quick charge transfer (Fig. 6c). This indicates the substantial effect of nitridation on enhancing the IPCE efficiency and retarding the electron–hole recombination. The slight drop in the IPCE efficiency at 489 nm on ammonia-annealed TiON_x NTs, owing to their inbuilt defects, implies that the photocurrents originated from the bandgap transition. The obtained IPCE of our newly developed multipodal TiON_6 NTs (80 nm) (34.74) under no applied bias was higher as compared to the previously reported long nanotube (1.3 μm) TiON_x NTs (31%) and N-free (1.3 μm) TiO_2 NTs (5.3%) measured at 0.7 V in KOH,⁴² as well as hydrogen-annealed TiO_2 NTs (70 ± 10 nm) (30%)⁵⁶ and oxygen-annealed TiO_2 NTs (70 ± 10 nm) ($\sim 13\%$) in KOH,⁵⁶ sub-100 nm compacted TiO_2 NTs (15%) under no bias in KOH,⁴³ and TiO_2 /N-doped TiO_2 compacted (850 nm nanotubes) (15%).³³ That is plausibly attributed to the multipodal nanotube shape and high defect concentration of TiON_6 NTs. The photocatalytic water splitting performances of ammonia-annealed NTs were investigated relative to air-annealed TiO_2 NTs. The linear sweep voltammograms (LSVs) were measured in 0.1 M KOH at 10 mV s^{-1} under light irradiation at room temperature.

The ammonia-annealed NTs were significantly superior to air-annealed TiO_2 NTs. In particular, at 1.99 V_{RHE}, TiO_2 NTs produced a photocurrent of 0.57 mA cm^{-2} , whereas the ammonia-annealed TiON_x NTs revealed photocurrents ranging from 1.75 to 4.5 mA cm^{-2} , implying the significant effect of N-doping on the enhancement of the photocatalytic activity (Fig. 7a). It is noteworthy that ammonia-annealed NTs showed a superior activity at earlier potentials than that of TiO_2 NT. Moreover, the ammonia-annealed NTs produced greater photocurrents than TiO_2 NTs under applied potential (Fig. 7b). The measured onset potential (E_{onset}) on TiON_2 NTs (1.45 V), TiON_4 NTs (1.4 V), and TiON_6 NTs (1.2 V) were significantly more negative than that of TiO_2 NTs (1.52 V) (Fig. 7c). This plausibly emanated from the substitution of some O sites by N, which led to introducing a high concentration of vacancy-type defects inside the lattice structure of TiO_2 NTs. These defects provide various electron scavenger sites facilitating the water oxidation kinetics at lower potentials, as further confirmed in the lower Tafel slope of ammonia-annealed NTs (0.44–0.55 V dec^{-1}) relative to TiO_2 NTs (0.8 V dec^{-1}) (Fig. 7d).




Fig. 6 (a) UV-vis transmittance, (b) IPCE spectra of the as-formed material measured in 0.1 M KOH under no applied bias and (c) zooming in on the area between 550 and 750 nm.






Fig. 7 (a and b) LSV of water oxidation on different catalysts measured in an aqueous solution of 0.1 M KOH at a scan rate of 10 mV s⁻¹ at room temperature. (c) Comparisons of photocurrent densities and E_{onset} . (d) Tafel plot of TiO₂NTs and TiON_xNTs. (e) The utilized equivalent circuit (f) electrochemical impedance spectroscopy (EIS) Nyquist plots measured in 0.1 M KOH in a frequency range of 10 mHz to 100 kHz and a perturbation amplitude of 5 mV; (g) double layer, and (h) Mott-Schottky plots of TiO₂NTs and TiON_xNTs. All the tests were performed under light illumination.

Compared with other TiO₂ or TiON nanostructures, the photocurrent obtained on our developed ammonia-annealed multipodal (80 nm) TiON₆NTs (4.5 mA cm⁻²) was superior to that reported for Co-TiON nanowires (80–100 nm) (0.61 mA cm⁻²),⁵⁷ TiON nanowires (4.4 μm) (0.23 mA cm⁻²),⁵⁸ and compacted TiO₂NTs (70 ± 10 nm) (0.45 mA cm⁻²),⁴³ titanium nitride/titanium oxide (TiN/TiO₂) nanocomposite (0.12 mA cm⁻²),⁵⁹ and long TiON nanotubes (1.3 μm) (2.25 mA cm⁻²)⁴² measured under similar conditions in KOH electrolyte under light illumination (a xenon ozone-free lamp 100 or 300 W).

Moreover, we measured the photocatalytic water splitting performances of ammonia-annealed NTs relative to ammonia-annealed TiO₂ nanotubes with different lengths of 1.2 μm (denoted TiONNTs 1.2) and 500 nm (denoted TiONNTs 500), as well as commercial TiO₂ nanoparticles (Fig. S3†). The current densities of ammonia-annealed TiON₆NTs (4.5 mA cm⁻²) were 3.19, 2.14, 11.25, and 20.4 times higher than that of TiONNTs-1.2 (1.41 mA cm⁻²), TiONNTs-500 (2.1 mA cm⁻²), N-free TiO₂-NTs-1.2 (0.4 mA cm⁻²), and TiO₂ nanoparticles (0.225 mA cm⁻²) (Fig. S3†). This is due to the uniformity, multipodal nanotube shape, and high defect concentration of TiON₆NTs, which plausibly enhanced the conductivity and accelerated charge mobility. It is universally accepted that sub-100 nm nanotubes have various unique merits relative to traditional compacted long nanotubes, including but not limited to greater surface area, shorter aspect ratio, and directional/quick charge transfer, as well as a short electron pathway.⁴³ This is in addition to the effective electron-hole separation and better light-harvesting ability that drive the water-splitting at a lower potential relative to traditional long nanotubes. Meanwhile, the multipodal shape provides a graded refractive index, large surface, and easier charge separation at the core-leg interface enabling greater volume ratio and higher scattering.⁶⁰ In contrast, the

long diameter of the compact nanotube (over 170 nm) can act as a sub-wavelength structure that scatters light in Rayleigh fashion as reported before.⁶⁰

That was furthered proved by measuring the electrochemical impedance spectroscopy (EIS) under light for TiO₂NTs and TiON_xNTs. The equivalent circuit (EC) was utilized to fit and analyze the measured data (Fig. 7e). A two-time constant equivalent circuit was employed, which is primarily used for electrodes with coatings or porous oxide layers on top. The EIS parameters, such as the electrolyte resistance (R_s), the charge transfer resistance at the oxide or the oxynitride/solution interface (R_1), the charge transfer resistance at the metal solution interface (R_2), the two constant phase elements (CPE1 and CPE2) associated with the resistances mentioned above, and the deviation parameters (n_1 and n_2), are listed in Table S2.† A constant phase element is used instead of a pure capacitor to express the non-ideal behavior (indicated by the depressed semicircles) of the double-layer capacitance because of the non-uniform (i) thickness of the oxide/nitrided layer, (ii) reaction kinetics on the surface, (iii) current distribution, in addition to (iv) surface roughness.⁶¹ The diameters of the depressed semicircles of TiO_xNTs relative to TiO₂NTs are shown in Fig. 7f. Increasing the N-content leads to decreasing the diameter of the thus-obtained TiO_xNTs, which indicates their quick charge mobility and electrolyte-electrode conductivity relative to air-annealed TiO₂NTs. Fig. 7g depicts the double-layer capacitance (C_{dl}) derived from the variables in Table S2.† using the equation below:

$$C_{\text{dl}} = [(Y_0 \times R_{\text{ct}})^{1/n}] / R_{\text{ct}} \quad (1)$$

It can be noted that the double layer capacitance is inversely proportional to the impedance values (Fig. 7g); the C_{dl} values in



TiON_xNTs were higher than that in TiO_2NTs , indicate the dielectric nature of the TiO_2NTs substrate. This is more obvious in the decreasing R_1 , R_2 , R_s , and n_1 , and n_2 in TiON_xNTs as compared to TiO_2NTs (Table S2†).

Mott-Schottky plots were utilized to elucidate the charge distribution on the as-synthesized interface *versus* the electrolyte by measuring the electrode capacitance C as a function of electrode potential E (Fig. 7h). It is worth mentioning that all samples provided a positive slope, which is characteristic of the n-type TiO_2 semiconductor. Hence, the donor density (N_d) was calculated using the equation below:

$$C^{-2} = (2/e\epsilon\epsilon_0 A N_d) \times (E - E_{FB} - (K_b T/e)) \quad (2)$$

where C , e , ϵ , ϵ_0 , A , E_{FB} , K_b , and T are the space charge capacitance, the electron charge, the dielectric constant, the vacuum permittivity, the tested surface area, the flat band potential, the Boltzmann constant, and the absolute temperature, respectively. Additionally, E_{FB} can be determined from the extrapolation of the linear portion to $1/C^2 = 0$. Generally, it can be noted that the flat band potential shifts negatively with increasing the TiON_xNTs as compared with TiO_2NTs (Fig. 7h). There was a considerable improvement in the electron density in the order of $\text{TiON}_6\text{NTs} > \text{TiON}_4\text{NTs}, (4.15 \times 10^{18} \text{ cm}^{-3})$ as compared with $\text{TiON}_4 (3.93 \times 10^{18} \text{ cm}^{-3})$. This was obvious in the increase of the donor density band potentials obtained from Mott-Schottky plots for TiON_xNTs as compared to TiO_2NTs (Table S3†). Fig. 8 shows the energy level diagram for the typically synthesized materials. In particular, N-doping introduced the N 2p band above the O 2p valence band, resulting in the narrowing of the bandgap of TiO_2 from 3.2 eV to 2.4 eV.⁴² Hence, *via* the visible-light absorption, the electrons migrate from the valence band to the conduction band, which shifts the optical absorption to the visible light region and enhances the visible light responses of TiON_6NTs (Fig. 8a). The proposed photoelectrochemical water splitting mechanism on TiON_6NTs is shown in (Fig. 8b).

Upon light irradiation, the electrons and holes are generated in the conduction band and the valence band, respectively. The electrons and holes are scavenged by the O_2 molecules to produce superoxide radical anions (O_2^\cdot) and hydroxyl radicals (OH^\cdot), which are highly active and act as oxidative species facilitating water oxidation under lower potential (Fig. 8b).

The type and concentration of the defects in the air-annealed TiO_2NTs and ammonia-annealed TiON_xNTs were benchmarked using positron annihilation spectroscopy (PALS). The injected

positrons through TiO_2 are thermalized and annihilated by electrons, which lead to the emission of γ rays and allows the measurement of the lifetime of positrons. The positrons are distributed in the area with low electron density (*i.e.*, vacancy-type defects, vacancy clusters, and microvoids). Thus, the electron-positron annihilation photon allows the measurement of the lifetimes (t_1 , t_2 , and t_3) of positrons and their intensities (I_1 , I_2 , and I_3) as indicators of the defects. The results showed the resolved positron lifetimes, including the shorter lifetime (τ_1), longer positron lifetime (τ_2), and longest lifetime components (τ_3) along with their related intensities I_1 , I_2 , and I_3 (Table 1). The respective τ_1 values attributed to the free annihilation of positrons in the defect-free crystals of TiON_2NTs (178 ps), TiON_4NTs (181 ps), and TiON_6NTs (188 ps) were significantly higher than that of TiO_2NTs (174 ps). The increment in τ_1 is attributed to the higher content of monovacancies and/or shallow positron traps in the ammonia-annealed samples, which decreased the surrounding electron density and subsequently increased the lifetime of τ_1 in TiO_xNTs as compared to in air-annealed TiO_2NTs . Therefore, the prolonged τ_1 of TiON_xNTs validated that a huge number of small neutral Ti^{3+} -N vacancy associates were introduced into the TiO_2 lattice by nitridation.

The lifetime τ_2 is larger than τ_1 , which implies that τ_2 originated from positrons captured by defects of larger size. Thus, the τ_2 of TiON_2NTs (297 ps), TiON_4NTs (301 ps), and TiON_6NTs (311 ps) were greater than that of TiO_2NTs (288 ps), implying the presence of larger-sized vacancy clusters attributed to the interaction among small neutral Ti^{3+} -nitrogen-vacancy associates. The average electron density in larger-sized defects is lower than that in small-sized defects, which decreases the annihilation rate and increases the positron lifetime correspondingly. The longest lifetime (τ_3) is plausibly attributed to the annihilation of orthopositronium atoms formed in the large voids in semiconductors. The τ_3 of ammonia-annealed TiON_2NTs (10.4 ps), TiON_4NTs (12.1 ps), and TiON_6NTs (13.5 ps) are higher than that of air annealed TiO_2NTs (8.3 ps). This demonstrated the higher content of the few voids of N-vacancy associates on the nanoscale in ammonia-annealed samples.

In addition to the lifetimes of the positrons, their relative intensities provide information on the relative concentration of the defects. The relative intensities (I_1) of TiON_2NTs (57.4%), TiON_4NTs (55.2%), and TiON_6NTs (52.9%) were close to that of TiO_2NTs (60.5%). The relative I_2 of TiON_2NTs (35.4%), TiON_4NTs (36.6%), and TiON_6NTs (37.9%) were slightly lower than that of TiO_2NTs (34.5%). The I_1 to I_2 ratios of TiON_2NTs (1.6), TiON_4NTs (1.5), and TiON_6NTs (1.39) were slightly lower than




Fig. 8 Energy level diagrams for (a) TiO_2NTs and (b) TiON_xNTs , as well as the proposed water splitting mechanism.

Table 1 Obtained positron lifetimes (t_1 , t_2 , and t_3) and their intensities (I_1 , I_2 , and I_3) of TiO_2NTs and TiON_xNTs

Samples	t_1 (ps)	I_1 (%)	t_2 (ps)	I_2 (%)	t_3 (ps)	I_3 (%)
TiO_2NTs	174	60.5	288	34.5	8.3	5
TiON_2NTs	178	57.4	297	35.4	10.4	7.2
TiON_4NTs	181	55.2	301	36.6	12.1	8.9
TiON_6NTs	188	52.9	311	37.9	13.5	9.2



that of TiO_2 NTs (1.75). This demonstrates the decrease in the concentration of bulk defects (C_{bd}) to surface defects (C_{sd}) of ammonia-annealed TiON_x NTs relative to air-annealed TiO_2 NTs in addition to a higher concentration of monovacancies than the boundary-like defect. The relative intensities I_3 of TiON_2 NTs (7.2%), TiON_4 NTs (8.9%), and TiON_6 NTs (9.2%) were higher than that of TiO_2 NTs (5%). This indicates the greater concentration of the voids of N-vacancy associates on the nanoscale in ammonia-annealed TiON_x NTs as compared to air-annealed. The slight drop in the I_3 originated from the sharp increase in I_1 and I_2 . The summation of $I_1 + I_2 + I_3$ should be equal to 100. Impressively, it is universally accepted that reducing the C_{bd} to C_{sd} led to the retardation of the electron–hole recombination.^{37,39} As expected, the τ_3 of TiON_2 NTs (10.4 ps), TiON_4 NTs (12.1 ps), and TiON_6 NTs (13.5 ps) were slightly higher than that of TiO_2 NTs (8.3 ps), demonstrating their higher content of the few voids of vacancy associates on the nanoscale. The relative intensities I_3 of ammonia-annealed TiON_x NTs were lower than that of TiO_2 NTs.

These results indicate that annealing under ammonia gas introduced different vacancy-type defects such as monovacancies, vacancy clusters, and a few voids inside the lattice structure of TiO_2 NTs. Such defects led to a significant reduction in the bandgap energy, retarding the electron–hole recombination and enhancing the UV-visible light absorption and photocatalytic water splitting. This is attributed to the substantial effect of the defects/vacancies on boosting the photocurrent in n-type TiO_2 .^{34,37,41} These defects form interbandgap states underneath the conduction band minimum and provide extra charge carriers under UV-light irradiation. Additionally, owing to the great electron trapping ability of defects, the lifetime of the photoelectrons increased significantly, resulting in supreme activity for solar-driven water splitting.

Conclusion

Herein, we rationally synthesized ultrathin, well-aligned, and uniform sub-100 nm multipodal TiO_2 NTs nanotubes (80 ± 2 nm length) *via* the electrochemical anodic oxidation of Ti-foil in formamide-based electrolytes. The as-formed TiO_2 NTs were annealed under ammonia for 2, 4, and 6 h to form TiON_2 NTs, TiON_4 NTs, and TiON_6 NTs, respectively. The N-content was ~ 1.7 , and 3.2, and 4.9%, in TiON_2 NTs, TiON_4 NTs, and TiON_6 NTs, respectively. The HRTEM, XPS, AES, and PALS warranted that a high concentration of vacancy-type defects was introduced inside the TiO_2 NTs lattice structure. The N-content and its subsequent defects inside the TiO_2 NTs lattice increased with the increment of the nitridation time that formed a mixture of Ti-nitride and oxynitride with various defect states. These kinds of defects decreased the bandgap energy to 2.4 eV, enhanced the visible-light response, IPCE, photocurrent density (by 8 times), and accelerated the charge carrier collection efficiency of ammonia-annealed TiON_x NTs as compared to air-annealed TiO_2 NTs. The sub-100 nm nanotubes TiON_6 NTs outperformed the long compacted TiON_x NTs with different lengths and TiO_2 nanoparticles. This

paper could pave the way towards optimizing the defect state of TiO_2 -based photocatalysts for solar-driven water splitting.

Conflicts of interest

There are no conflicts of interest to declare.

Acknowledgements

We greatly appreciate the Gas Processing Center, Qatar University, for supporting this work. Also, the SEM images were captured at the Core Labs of Hamad Bin Khalifa University, Doha, Qatar. This work was supported by the Qatar National Research Fund (QNRF, a member of the Qatar Foundation) through the National Priority Research Program Grant (NPRP) NPRP13S-0117-200095. Also, this publication was supported by Qatar University's internal grant IRCC-2021-015. Statements made herein are solely the responsibility of the authors.

References

- 1 F. Wu, K. Eid, A. M. Abdullah, W. Niu, C. Wang, Y. Lan, A. A. Elzatahry and G. Xu, *ACS Appl. Mater. Interfaces*, 2020, **12**, 31309–31318.
- 2 H. I. Abdu, K. Eid, A. M. Abdullah, Z. Han, M. H. Ibrahim, D. Shan, J. Chen, A. A. Elzatahry and X. Lu, *Renewable Energy*, 2020, **153**, 998–1004.
- 3 K. Eid, M. H. Sliem, H. Al-Kandari, M. A. Sharaf and A. M. Abdullah, *Langmuir*, 2019, **35**, 3421–3431.
- 4 K. Eid, M. H. Sliem and A. M. Abdullah, *Nanoscale*, 2019, **11**, 11755–11764.
- 5 K. Eid, M. H. Sliem, A. S. Eldesoky, H. Al-Kandari and A. M. Abdullah, *Int. J. Hydrogen Energy*, 2019, **44**, 17943–17953.
- 6 Q. Lu, K. Eid, W. Li, A. M. Abdullah, G. Xu and R. S. Varma, *Green Chem.*, 2021, DOI: 10.1039/D1GC01303C.
- 7 K. Eid, M. H. Sliem, K. Jlassi, A. S. Eldesoky, G. G. Abdo, S. Y. Al-Qaradawi, M. A. Sharaf, A. M. Abdullah and A. A. Elzatahry, *Inorg. Chem. Commun.*, 2019, **107**, 107460.
- 8 M. A. Ahsan, T. He, K. Eid, A. M. Abdullah, M. L. Curry, A. Du, A. R. Puente Santiago, L. Echegoyen and J. C. Noveron, *J. Am. Chem. Soc.*, 2021, **143**, 1203–1215.
- 9 A. K. Ipadeola, A. B. Haruna, L. Gaolatthe, A. K. Lebechi, J. Meng, Q. Pang, K. Eid, A. Abdullah and K. I. Ozoemena, *ChemElectroChem*, 2021, DOI: 10.1002/celc.202100574.
- 10 K. Eid, H. Wang, P. He, K. Wang, T. Ahamad, S. M. Alshehri, Y. Yamauchi and L. Wang, *Nanoscale*, 2015, **7**, 16860–16866.
- 11 K. Eid, H. Wang, V. Malgras, Z. A. Alothman, Y. Yamauchi and L. Wang, *J. Phys. Chem. C*, 2015, **119**, 19947–19953.
- 12 H. Wang, S. Yin, K. Eid, Y. Li, Y. Xu, X. Li, H. Xue and L. Wang, *ACS Sustainable Chem. Eng.*, 2018, **6**, 11768–11774.
- 13 A. Pancielejko, P. Mazierski, W. Lisowski, A. Zaleska-Medynska, K. Kosek and J. Łuczak, *ACS Sustainable Chem. Eng.*, 2018, **6**(11), 14510–14522.
- 14 V. Malgras, Y. Shirai, T. Takei and Y. Yamauchi, *J. Am. Chem. Soc.*, 2020, **142**, 15815–15822.



15 C. Zhao, H. Luo, F. Chen, P. Zhang, L. Yi and K. You, *Energy Environ. Sci.*, 2014, **7**, 1700–1707.

16 R. Zazpe, H. Sopha, J. Prikryl, M. Krba, J. Mistrik, F. Dvorak, L. Hromádko and J. Macák, *Nanoscale*, 2018, **10**, 16601–16612.

17 M. Ge, C. Cao, J. Huang, S. Li, Z. Chen, K.-Q. Zhang, S. Al-Deyab and Y. Lai, *J. Mater. Chem. A*, 2016, **4**, 6772–6801.

18 Z. Zhang and P. Wang, *Energy Environ. Sci.*, 2012, **5**, 6506–6512.

19 A. E. R. Mohamed and S. Rohani, *Energy Environ. Sci.*, 2011, **4**, 1065–1086.

20 T. Gakhar and A. Hazra, *Nanoscale*, 2020, **12**, 9082–9093.

21 Y. Alivov, V. Singh, Y. Ding, L. J. Cerkovnik and P. Nagpal, *Nanoscale*, 2014, **6**, 10839–10849.

22 H. Tsuchiya and P. Schmuki, *Nanoscale*, 2020, **12**, 8119–8132.

23 J. A. Seabold, K. Shankar, R. H. Wilke, M. Paulose, O. K. Varghese, C. A. Grimes and K.-S. Choi, *Chem. Mater.*, 2008, **20**, 5266–5273.

24 M. Marszewski, J. Marszevska, S. Pylypenko and M. Jaroniec, *Chem. Mater.*, 2016, **28**, 7878–7888.

25 M. Sluban, P. Umek, Z. Jagličić, J. E. Buh, P. Šmitek, A. Mrzel, C. Bittencourt, P. Guttmann, M.-H. Delville and D. Mihailović, *ACS Nano*, 2015, **9**, 10133–10141.

26 Y.-J. Wei, C.-W. Peng, T.-M. Cheng, H.-K. Lin, Y.-L. Chen, C.-Y. Lee and H.-T. Chiu, *ACS Appl. Mater. Interfaces*, 2011, **3**, 3804–3812.

27 Y. Zhao, X. Qiu and C. Burda, *Chem. Mater.*, 2008, **20**, 2629–2636.

28 R. Asahi, T. Morikawa, H. Irie and T. Ohwaki, *Chem. Rev.*, 2014, **114**, 9824–9852.

29 E. Martínez-Ferrero, Y. Sakatani, C. Boissière, D. Gross, A. Fuertes, J. Fraxedas and C. Sanchez, *Adv. Funct. Mater.*, 2007, **17**, 3348–3354.

30 N. M. Nursam, X. Wang, J. Z. Tan and R. A. Caruso, *ACS Appl. Mater. Interfaces*, 2016, **8**, 17194–17204.

31 D. Spanu, S. Recchia, S. Mohajernia, O. e. Tomanec, S. t. p. n. Kment, R. Zboril, P. Schmuki and M. Altomare, *ACS Catal.*, 2018, **8**, 5298–5305.

32 R. Vitiello, J. Macák, A. Ghicov, H. Tsuchiya, L. Dick and P. Schmuki, *Electrochem. Commun.*, 2006, **8**, 544–548.

33 D. Kim, S. Fujimoto, P. Schmuki and H. Tsuchiya, *Electrochem. Commun.*, 2008, **10**, 910–913.

34 Y. J. Jin, J. Linghu, J. Chai, C. S. Chua, L. M. Wong, Y. P. Feng, M. Yang and S. Wang, *J. Phys. Chem. C*, 2018, **122**, 16600–16606.

35 Y. Liu, Q. Zhu, X. Li, G. Zhang, Y. Liu, S. Tang, E. Sharman, J. Jiang and Y. Luo, *J. Phys. Chem. C*, 2018, **122**, 17221–17227.

36 M. D'Arienzo, N. Siedl, A. Sternig, R. Scotti, F. Morazzoni, J. Bernardi and O. Diwald, *J. Phys. Chem. C*, 2010, **114**, 18067–18072.

37 M. Kong, Y. Li, X. Chen, T. Tian, P. Fang, F. Zheng and X. Zhao, *J. Am. Chem. Soc.*, 2011, **133**, 16414–16417.

38 F. Jin, X. Zhang, M. Wei, T. Chen, H. Ma and Y. Ma, *J. Mater. Chem. A*, 2020, **8**, 20082–20090.

39 X. Jiang, Y. Zhang, J. Jiang, Y. Rong, Y. Wang, Y. Wu and C. Pan, *J. Phys. Chem. C*, 2012, **116**, 22619–22624.

40 A. Das, S. Deshagani, R. Kumar and M. Deepa, *ACS Appl. Mater. Interfaces*, 2018, **10**, 35932–35945.

41 S. Ghosh, G. G. Khan, K. Mandal, A. Samanta and P. Nambissan, *J. Phys. Chem. C*, 2013, **117**, 8458–8467.

42 K. Eid, K. A. Soliman, D. Abdulmalik, D. Mitoraj, M. H. Sleim, M. O. Liedke, H. A. El-Sayed, A. S. AlJaber, I. Y. Al-Qaradawi and O. M. Reyes, *Catal. Sci. Technol.*, 2020, **10**, 801–809.

43 M. Samir, M. Salama and N. K. Allam, *J. Mater. Chem. A*, 2016, **4**, 9375–9380.

44 M. Wang, F. Zhang, X. Zhu, Z. Qi, B. Hong, J. Ding, J. Bao, S. Sun and C. Gao, *Langmuir*, 2015, **31**, 1730–1736.

45 J. H. Han and J. H. Bang, *J. Mater. Chem. A*, 2014, **2**, 10568–10576.

46 J. B. Yoo, H. J. Yoo, H. J. Jung, H. S. Kim, S. Bang, J. Choi, H. Suh, J.-H. Lee, J.-G. Kim and N. H. Hur, *J. Mater. Chem. A*, 2016, **4**, 869–876.

47 J. S. Solomon and W. L. Baun, *Surf. Sci.*, 1975, **51**, 228–236.

48 K. G. Grigorov, G. I. Grigorov, L. Drajeva, D. Bouchier, R. Sporken and R. Caudano, *Vacuum*, 1998, **51**, 153–155.

49 N. Finnegan, T. Y. Lee, R. T. Haasch, J. E. Greene and I. Petrov, *Surf. Sci. Spectra*, 2000, **7**, 213–220.

50 R. T. Haasch, in *Practical Materials Characterization*, ed. M. Sardela, Springer New York, New York, NY, 2014, pp. 93–132, DOI: DOI: 10.1007/978-1-4614-9281-8_3.

51 O. Boese, W. E. S. Unger, E. Kemnitz and S. L. M. Schroeder, *Phys. Chem. Chem. Phys.*, 2002, **4**, 2824–2832.

52 M. Fantauzzi, F. Secci, M. Sanna Angotzi, C. Passiu, C. Cannas and A. Rossi, *RSC Adv.*, 2019, **9**, 19171–19179.

53 I. V. Chernyshova, S. Ponnurangam and P. Somasundaran, *Phys. Chem. Chem. Phys.*, 2010, **12**, 14045–14056.

54 N. Saito and K. Ishizaki, *J. Am. Ceram. Soc.*, 1996, **79**, 1213–1217.

55 R. Pantel, D. Levy and D. Nicolas, *J. Vac. Sci. Technol. A*, 1988, **6**, 2953–2956.

56 M. M. Soliman, M. H. Al Haron, M. Samir, S. A. Tolba, B. S. Shaheen, A. W. Amer, O. F. Mohammed and N. K. Allam, *Phys. Chem. Chem. Phys.*, 2018, **20**, 5975–5982.

57 C. Liu, J. Tang, H. M. Chen, B. Liu and P. Yang, *Nano Lett.*, 2013, **13**, 2989–2992.

58 S. Hoang, S. Guo, N. T. Hahn, A. J. Bard and C. B. Mullins, *Nano Lett.*, 2011, **12**, 26–32.

59 C.-T. Li, S.-R. Li, L.-Y. Chang, C.-P. Lee, P.-Y. Chen, S.-S. Sun, J.-J. Lin, R. Vittal and K.-C. Ho, *J. Mater. Chem. A*, 2015, **3**, 4695–4705.

60 M. M. Omar, S. M. Fawzy, A. B. El-Shabasy and N. K. Allam, *J. Mater. Chem. A*, 2017, **5**, 23600–23611.

61 J. Pan, D. Thierry and C. Leygraf, *Electrochim. Acta*, 1996, **41**, 1143–1153.

