RSC Advances



View Article Online

View Journal | View Issue

PAPER

Check for updates

Cite this: RSC Adv., 2021, 11, 17222

Received 2nd March 2021 Accepted 3rd May 2021

DOI: 10.1039/d1ra01631h

rsc.li/rsc-advances

1 Introduction

The nitrogen molecule has a strong triple bond and high bond energy, and it is difficult to react under environmental conditions.¹ Polynitrogen compounds and polymer nitrogen are favored because of their excellent energy density, energy storage characteristics,² unique chemical character, and thermodynamic stability.³ As is known, there are significant energy differences between the nitrogen–nitrogen single bond (160 kJ mol⁻¹), nitrogen–nitrogen double bond (418 kJ mol⁻¹), and nitrogen–nitrogen triple bond (954 kJ mol⁻¹). When multinitrogen compounds containing single bonds and double bonds are converted into nitrogen molecules, the bonding method between nitrogen and nitrogen changes, which will release a lot of energy.⁴

High energy-density materials (HEDMs) are generally based on the energy density of HMX (5.7 kJ g⁻¹).⁵ High energy-density materials usually refer to high-energy explosives.³ Generally, an ideal HEDM should have the following characteristics: (i) high density, (ii) positive heat of formation, (iii) high detonation

Pressure-induced stability and polymeric nitrogen in alkaline earth metal N-rich nitrides (XN_6 , X = Ca, Sr and Ba): a first-principles study⁺

Zhipeng Liu, Shuli Wei, 🗅 * Yanhui Guo, Haiyang Sun, Hao Sun, Qiang Chang and Yuping Sun 🕩 *

Multi-nitrogen or polynitrogen compounds can be used as potential high energy-density materials, so they have attracted great attention. Nitrogen can exist in alkaline earth metal nitrogen-rich (N-rich) compounds in the form of single or double bonds. In recent years, to explore N-rich compounds which are stable and easy to synthesize has become a new research direction. The N-rich compounds XN₆ (X = Ca, Sr and Ba) have been reported under normal pressure. In order to find other stable crystal structures, we have performed XN₆ (X = Ca, Sr and Ba) exploration under high pressure. We found that SrN₆ has a new $P\bar{1}$ phase at a pressure of 22 GPa and an infinite nitrogen chain structure, and BaN₆ has a new C2/*m* phase at 110 GPa, with an N₆ ring network structure. Further, we observed that the infinite nitrogen chain and the N₆ ring network structure contain typical covalent bonds formed by the hybridization of the sp² and sp³ orbitals of N, respectively. It is found that both SrN₆ and BaN₆ are semiconductor materials and the N-2p orbital plays an important role in the stability of the crystal structure for $P\bar{1}$ -SrN₆ and C2/*m*-BaN₆. Because of the polymerization of nitrogen in the two compounds and their stabilities under high pressure, they can be used as potential high energy-density materials. The research in this paper further promotes the understanding of alkaline earth metal N-rich compounds (XN₆, X = Ca, Sr and Ba).

performance, (iv) low sensitivity towards external stimuli, (v) good thermal stability. In previous studies, for instance, scientists successfully synthesized cubic gauche nitrogen (cg-N)6 containing only single bonds under the condition of (110 GPa, 2000 K),^{7,8} it can be used as a potential high energy-density material. Therefore, N-rich compounds containing a large amount of nitrogen and nitrogen single bond and double bonds may become potential high energy-density materials. Above the stability field of cg-N, a layered polymer (LP)⁹ with a similar Pba2 phase¹⁰ between 120-180 GPa and a hexagonal layered polynitrogen phase10 with a pressure around 250 GPa were also synthesized. In order to stabilize the polynitrogen compounds¹¹ as well as reduce the pressure and conditions for their synthesis, recently, an effective way is to add a small amount of metal atoms to pure nitrogen system through high pressure technology to stabilize the single and double bonds structure to form N-rich compounds.12 Using this research method, scientists have obtained a large number of N-rich metal compounds, for example, alkali metal and alkaline earth metal N-rich compounds.13,14 Metal atoms will cause the redistribution of electrons, leading to changes in chemical bonds, which can reduce the pressure of synthesis and increase energy storage.14

The high pressure compression to form novel compounds has become an valuable method,^{15,16} and the advantage is that it is easy to control and can help obtain more structures of N-rich

School of Physics and Optoelectronic Engineering, Shandong University of Technology, 250049 Zibo, China. E-mail: weishuli@sdut.edu.cn; sunyuping@sdut.edu.cn † Electronic supplementary information (ESI) available. See DOI: 10.1039/d1ra01631h

Paper

nitrides to form stable polynitrogen. High pressure can change the bonding mode, leading to different bond lengths and hybridization modes, forming a rich multi-center covalent polymerization landscape.4 The change in the crystal structure caused by pressure has been proved by predicting the structural diversity of metal nitrides: N₃,¹⁵ N₄,¹⁷ N₅,¹⁸ cyclo-N₆,¹⁷ N₈,¹⁹ N₁₀,²⁰ infinite nitrogen chain²¹ and nitrogen network structure,²² which provide an effective way to obtain N-rich compounds. In recent years, alkaline earth metal N-rich compounds have been theoretically predicted with important research significance as high energy-density materials under high pressure. Compared with alkali metals (Li,23 K,24 Na,25 Rb26 and Cs27), alkaline earth metals (Mg,¹⁷ Be,²⁸ Ca,¹⁹ Sr²⁹ and Ba³⁰) and transition metals (Sc,³¹ Fe,³² Zn,³³ Ag³⁴ and Ir³⁵) has more valence electrons than alkali metals, which are easier to improve the diversity of polymerized nitrogen forms. We have summarized the pressure ranges that exist the stable structures of alkali metals, alkaline earth metals and transition metals, in the Table S1 in ESI.† We also explained the reason for the transition pressure to decrease for the formation of polymeric nitrogen when we move from ionic azide to covalent azide, in the ESI.†

In this paper, we have predicted the stable phase structures of XN₆ (Sr, Ba) alkaline earth metal N-rich compounds, analyzed the phase stability, and further studied their potential applications as high energy-density materials.³ The theoretical prediction found that the new phase of P1-CaN₆ is unstable under high pressure, while the new phase of $P\bar{1}$ -SrN₆ is metastable under pressure, and C2/m-BaN₆ has been reported to be a metastable phase.³⁰ In this paper, the P1-SrN₆ at 22 GPa and C2/m-BaN₆ at 110 GPa were predicted to be stable under the corresponding high pressure conditions. After theoretical prediction and calculation, we found that the infinite nitrogen chain structure in the $P\bar{1}$ -SrN₆ structure is formed by polymerization when the Fddd-SrN₆ structure is under pressure of 22 GPa. And the six-membered annular network structure in the C2/m-BaN₆ structure is formed by polymerization when the Fmmm-BaN₆ structure is under pressure of 110 GPa. We calculated the electronic band structure and projected density of states for SrN₆ and BaN₆, and they are all semiconductor materials. By Zintl-Klemm theory³⁶ and calculating the electronic localization function,37 we know that the bonding manner of nitrogen atoms for P1-SrN₆ in high pressure is nitrogen-nitrogen single bond and double bonds and C2/m-BaN₆ in high pressure the bonding manner of nitrogen atoms is nitrogen-nitrogen single bond. Due to their content of a large number of nitrogen-nitrogen single bond and double bonds, they can be used as a potential high energy-density material. The research in this paper provides new perspective for the exploration of XN₆ system in the future.

2 Computation details

In order to find the stable structures of XN_6 (X = Ca, Sr and Ba) alkaline earth metal N-rich compounds in the pressure range of 0–200 GPa, we used the CALYPSO³⁸ structure prediction method based on swarm intelligence.^{39,40} We selected a point every 10 GPa in the pressure range of 0–200 GPa, and performed high

pressure theoretical predictions and optimization on XN_6 (X = Ca, Sr, Ba) alkaline earth metal N-rich compounds. The CALYPSO structure prediction method has been successfully applied to various systems from elementary solids to binary and ternary compounds.41 The optimization of the structure and the calculation of the electronic structure is performed within the framework of density functional theory (DFT),42 implemented by the VASP (Vienna Ab initio Calculation Simulation Package) code,43 and the (GGA) generalized gradient approximation44 PBE functional is used for calculation. The projector-augmented wave (PAW)⁴⁵ method and the Sr, Ba and N potentials were adopted from the VASP potential library, and $5s^2$, $6s^2$ and $2s^2$ 2p³ were treated as valence electrons for Sr, Ba and N atoms to calculate the electron-ion interaction. A plane-wave basis set cutoff of 800 eV, a Monkhorst-Pack k mesh spacing of $2\pi \times 0.03$ Å⁻¹ in the Brillouin zone⁴⁶ was selected to ensure that all enthalpy calculations converged to less than 1 meV per atom. The relative thermodynamic stability of different XN_6 (X = Ca, Sr and Ba) alkaline earth metal N-rich compounds is calculated as follows:

$$\Delta H (XN_6) = [H (XN_6) - H (X) - 6H (N_2)/2]/(1+6)$$

(X = Ca, Sr and Ba). Select to elemental solid X (X = Ca, Sr and Ba), solid calcium (*fcc*, *bcc*, and β -tin phases), solid strontium (*bcc*, *hcp*, *P*6₃/*mmc*), solid barium (*bcc*, *Im3m*, *hcp*, *P*6₃/*mmc*) and solid nitrogen α , *Pbcn*, *P2/c*, *P*4₁2₁2, *I*2₁3, *Pba*2, and *cg*-N phases were used as reference structures in their corresponding stable pressure ranges. H = U + PV is the enthalpy value of each component, ΔH is the enthalpy of formation of each compound, and the *U*, *P* and *V* are thermodynamic energy, pressure and volume respectively. The crystal structure image is made using VESTA software.⁴⁷ The dynamical stability of the predicted structure is determined by phonon calculations using a supercell approach with the finite displacement method as implemented in the Phonopy code.^{48,49}

3 Results and discussions

In recent studies, we have found that metal nitrides have attracted more and more attention.^{50,51} Because metal nitrides are more stable than pure nitrogen compounds in terms of kinetics, and have the characteristics of low synthesis pressure and superior physical and chemical properties, they can be widely used in the research of high energy-density materials.³

3.1 CaN₆ with $P\overline{1}$ structure

Since the Ca element is adjacent to the K element and can provide one more electron than the K element, this is more conducive to the diversity of nitrogen forms under high pressure. In previous studies, KN_3 has been successfully predicted theoretically and can be used as a potential high energy-density material.⁵² This section mainly studies the structural properties and stability of CaN₆, we found that a new transition phase of CaN₆ occurred, and the *Fddd* structure under normal pressure was changed to the *P* $\bar{1}$ structure at 32 GPa up to 100 GPa, as shown in Fig. 1(a). The infinite nitrogen chain structure in the



Fig. 1 (a) Relative formation enthalpy of P1-CaN₆ structure and Fddd-CaN₆ structure under different pressures. (b) The phonon spectrum of P1-CaN₆ structure. (c) Schematic diagram of the CaN₆ crystal structure under normal pressure. (d) Schematic diagram of the P1-CaN₆ crystal structure under high pressure, the large blue balls represent Ca atoms, and the small balls represent nitrogen atoms.

 $P\bar{1}$ -CaN₆ structure is composed of multiple nitrogen atoms, and its structural feature is an infinite armchair-shaped nitrogen chain,⁵³ as shown in Fig. 1(d). It is polymerized by *Fddd*-CaN₆ structure under 32 GPa, and *Fddd*-CaN₆ structure was shown in Fig. 1(c).

Referring to previous theoretical studies, we generally consider that the length of a single (N–N) bond is 1.45 Å, a double bond (N=N) equals 1.25 Å,¹⁸ and the length of a triple bond (N=N) is 1.10 Å at ambient conditions.³³ The bond length between nitrogen and nitrogen in $P\bar{1}$ -CaN₆ is between 1.23 Å and 1.35 Å, surviving in the alternating range of single and double bonds. In $P\bar{1}$ -CaN₆ structure, the smallest unit formed by six nitrogen atoms can be equivalent to N₆²⁻ anion, this is caused by the calcium atom transfers two valence electrons into the N₆ structure, showing in the form of Ca²⁺(N₆)²⁻. In N₆²⁻ unit, the nitrogen atom satisfies the Zintl–Klemm theory,³⁶ the covalent bonds are formed between the adjacent nitrogen atom, and form nitrogen–nitrogen single bond and nitrogen–nitrogen double bonds coexistence status. In $P\bar{1}$ -CaN₆, the weight ratio of nitrogen is about 67%, due to the presence of single bond and double bonds of nitrogen and nitrogen, when it generates N₂, it will release a lot of energy, which can theoretically be used as a potential high energy-density material. We further analyzed the dynamic stability of the $P\bar{1}$ -CaN₆ structure, and obtained the phonon dispersion curves after calculation, as shown in Fig. 1(b). It can be seen that imaginary frequencies appear in the entire Brillouin zone, indicating the $P\bar{1}$ -CaN₆ structure are not kinetically stable, so the $P\bar{1}$ -CaN₆ does not stable structure. However, our analysis of N₆^{2–} anion has provided valuable information for the study of other metal polynitrides.

3.2 SrN₆ with $P\bar{1}$ structure

This section mainly studies the structural properties and stability of SrN₆, and other forms of strontium nitrogen compounds SrN_n (n = 1-6) have been reported.⁵¹ In previous theoretical prediction, many alkali metal nitrides have been studied and proved to be good energy storage materials, such as RbN₃.²⁶ Because Sr element is adjacent to Rb element, Rb and its compounds have excellent physical and chemical properties such as easy ionization, radiation resistance, energy storage, etc., and are used in various fields.⁵⁴ Because RbN₃ contains nitrogen-nitrogen double bonds and exists stably, it can be used as a potential high energy-density material, that makes strontium nitrogen compound important research significance.55 After theoretical prediction and calculation, we found that the Fddd-SrN₆ structure under ambient pressure can be transformed into a P1-SrN6 structure at 22 GPa, and a new polymerization phase of N occurred, as shown in Fig. 2(a). The Fddd-SrN₆ structure contains an independent unit consisting of every three nitrogen atoms, as shown in Fig. 2(b), and the infinite nitrogen chain structure in the $P\bar{1}$ -SrN₆ structure is formed by polymerization when the Fddd-SrN₆ structure is under pressure of 22 GPa, as shown in Fig. 2(c). The structural parameter information of $P\bar{1}$ -SrN₆ is shown in Table 1.

We further studied the dynamic stability of $P\bar{1}$ -SrN₆ structure, and we obtained the phonon dispersion curves of $P\bar{1}$ -SrN₆



Fig. 2 (a) Relative formation enthalpy of the high-pressure phase P1-SrN₆ structure relative to the normal pressure phase Fddd-SrN₆ structure under different pressures. (b) Schematic diagram of Fddd-SrN₆ structure. (c) Schematic diagram of P1-SrN₆ structure. The large green balls are Sr atoms and the small balls are nitrogen atoms.

 $\label{eq:stable1} \mbox{Table 1} \mbox{ The predicted structural parameters of SrN_6, and BaN_6 under phase change pressure}$

Phase	P (GPa)	Ζ	Space group	Lattice parameters (Å, °)	N−N distance/average (Å)	Atomic coordinates (fractional)
SrN ₆	22	2	ΡĪ	a = 5.28 b = 5.29 c = 5.57 $\alpha = 91.85$	1.32	Sr (0.608, 0.294, 0.780) N (0.179, 0.210, 0.690) (0.735, 0.741, 0.687) (0.130, 0.197, 0.904)
				eta=112.27 $\gamma=62.78$		(0.944, 0.247, 0.479) (0.684, 0.743, 0.900) (0.008, 0.748, 0.736)
BaN ₆	110	2	C2/m	a = 4.43 b = 4.78 c = 6.25 $\alpha = 90.00$ $\beta = 121.04$ $\gamma = 90.00$	1.38	Ba (0.500, -0.500, 0.500) N (1.196, -0.500, 0.774) (1.818, -0.763, 0.917)

structure. It can be seen from the Fig. 3(a) that no virtual frequency appears in the entire Brillouin zone, indicating that $P\bar{1}$ -SrN₆ structure is dynamically stable. The infinite nitrogen chain structure is joined together by covalent bonds, and the valence electrons of Sr atoms are transferred to the N atoms, which plays a very important role in its stability. We calculated the electronic band structure and projected density of states for SrN₆, and found that SrN₆ is a semiconductor material, as shown in Fig. 3(b) and (c). In the projected density of states diagram, we can observe that the 2p state of N occupies a large proportion of the entire energy range, indicating that the valence electron state of N-2p also plays an important role in the stability of the $P\bar{1}$ -SrN₆ crystal structure, as shown in Fig. 3(c). As we all know, the polymerized form of nitrogen plays an important role in high energy-density material. In the infinite nitrogen chain of the P1-SrN₆ structure, every six nitrogen atoms form a unit and combine with one Sr atom. Since the Sr atom loses two electrons to form a Sr²⁺ cation, the nitrogen atoms in each unit get electrons combine with Sr atom. In a unit formed



Fig. 3 (a) The phonon spectrum of P1-SrN₆ structure. (b) Calculated electronic band structure diagram. (c) The calculated projected density of states (PDOS) at 22 GPa. (d) SrN₆ electronic local function graph.

by every six nitrogen atoms, the nitrogen atom satisfies the Zintl–Klemm theory,³⁶ which makes the nitrogen atom produce bond with the surrounding atoms, showing in the form of $\mathrm{Sr}^{2+}(\mathrm{N}_6)^{2-}$, so the nitrogen and the nitrogen form nitrogen-nitrogen single bond and nitrogen–nitrogen double bonds coexistence status. Due to the existence of nitrogen–nitrogen single bond and nitrogen–nitrogen double bonds in the $P\bar{1}$ -SrN₆ structure and the nitrogen and conducive to obtaining high energy-density material.

In order to confirm this conclusion and gain a deeper understanding of the microscopic bonding mechanism of SrN_{6} , we calculated the electronic localization function diagram and found that the nitrogen atoms have strong electronic localization and form typical covalent bonds, as shown in Fig. 3(d). The electronic local function is a three-dimensional spatial function used to characterize the distribution of electronic positioning, and its value is 0 to 1. When ELF = 1, it means the electrons are completely localized, and when ELF = 0, it means the electrons are completely delocalized, and when ELF = 0.5, it means that electrons are free. The ELF can explain the bonding and electronic distribution between the atoms, and can further explain microscopic bonding mechanisms. In Fig. 3(d), the nitrogen atoms form a chained structure, and they participate in bond formation in the form of sp^2 hybridization. The two sp^2 hybrid orbitals of all nitrogen atoms form covalent bond with one sp² hybrid orbital of two adjacent nitrogen atoms. The remaining one sp² hybrid orbitals are filled with isolated electrons. In the $[-N_6^{2}-]$, due to the sp² hybridization of the nitrogen atom, there are nitrogen-nitrogen single bonds and nitrogennitrogen double bonds between nitrogen and nitrogen.33 After calculation, in the infinite nitrogen chain, the distance between nitrogen and nitrogen is between 1.28 Å and 1.38 Å, there is surviving in the alternating range of single and double bonds. It is further proved that the structure of P1-SrN6 contains nitrogen-nitrogen single bond and nitrogen-nitrogen double bonds. In the previously reported article, the N-rich compounds with the infinite nitrogen chain structures have high energy density, in the ESI.† In the above analysis, we can judge that the content of nitrogen-nitrogen single bond and double bonds in $P\bar{1}$ -SrN₆ is relatively high, which a large amount of energy will be released when N₂ is generated, and the synthesis pressure is low, so $P\bar{1}$ -SrN₆ can theoretically be used as a potential high energy-density material.

3.3 BaN₆ with C2/m structure

Recently, the latest research on alkaline earth metal nitrides found that Ba and N can form a variety of compounds under high pressure.³⁰ In this section, we mainly studied the crystal structure properties of the N-rich alkaline earth metal compound BaN₆. In previous theoretical predictions, the alkaline earth metal N-rich compounds formed by alkaline earth metals Be,28 Mg,17 Ca19 and non-metallic N elements can be used as potential high energy-density materials. The chemical properties of Ba element are very active and can react with most nonmetals, such as O2, N2, H2, etc. Ba element has strong reducibility and can form +2 cations, which is easy to combine with the N element under high pressure, so that the Ba element can better promote the diversity of poly-nitrogen forms.⁵⁶ Therefore, exploring the alkaline earth metal N-rich compound BaN₆ as a potential high energy-density material has important research significance.

After theoretical calculations, the relative formation enthalpies of the five structures of BaN_6 are obtained under different pressures, as shown in Fig. 4(a). After theoretical prediction, it is found that there is a $P\overline{1}(I)$ -BaN₆ structure with the lowest enthalpy value in the range of 21–110 GPa. This indicates that the *Fmmm*-BaN₆ structure can be transformed to $P\overline{1}(I)$ -BaN₆ structure at P = 21 GPa. Our prediction of the $P\overline{1}(I)$ -BaN₆ structure is consistent with the previous predictions of Huang *et al.*,³⁰ which also shows that our high-pressure theoretical predictions and calculation results are accurate. Further by theoretically prediction to high-pressure 200 GPa, it is found that a new monoclinic transition phase appears under the

pressure of 110 GPa, the C2/m-BaN₆ structure, as shown in Fig. 4(c). This indicates that the Fmmm-BaN₆ structure can be transformed to C2/m-BaN₆ structure at P = 110 GPa. The nitrogen atoms in the Fmmm-BaN6 structure exists as an independent unit for every two nitrogen atoms, as shown in Fig. 4(b). In the $P\overline{1}(I)$ -BaN₆ structure, under the pressure of 21 GPa, the polymerization form of nitrogen is formed by the polymerization of nitrogen five-rings and one nitrogen atom, as shown in Fig. 4(d). Under the pressure of 110 GPa, the nitrogen atoms polymerize to form the N6 ring network structure²² in C2/ m-BaN₆, as shown in Fig. 4(c). It can be seen from the crystal structure diagram that with the increase of pressure, the degree of polymerization of nitrogen in the three structures gradually increases, indicating that pressure can cause the polymerization of nitrogen to form nitrogen polymers. Here, we mainly calculated and analyzed the performance of C2/m-BaN₆ structure. The structure parameter information of C2/m-BaN₆ is given in Table 1.

We further studied the dynamic stability of C2/m-BaN₆ structure, and obtained the phonon dispersion curves by theoretical calculations, and found that there was no imaginary frequency phenomenon in the entire Brillouin zone, indicating that C2/m-BaN₆ structure it is dynamically stable, as shown in Fig. 5(a). Previous studies have shown that the monoclinic C2/ *m*-BaN₆ structure exists in the form of metastable state.³⁰ In order to analyze the electronic properties of C2/m-BaN₆, so we calculated the electronic band structure and projected density of states for BaN₆ and we found that BaN₆ is a semiconductor material, as shown in Fig. 5(b) and (c). Because Ba element has a higher ionization energy, it is easy to combine with N element, so that valence electrons can be easily transferred to the N6 ring network structure. In Fig. 5(c), it can be seen that the N-2p orbital occupies a large proportion of the entire energy map, which indicates that the N-2p orbital plays an important role in



Fig. 4 (a) The relative enthalpy of formation of BaN_6 with five structures under different pressures. (b) *Fmmm*- BaN_6 crystal structure diagram. (c) C2/m- BaN_6 crystal structure diagram. (d) P1(I)- BaN_6 crystal structure diagram. The large green balls are Ba atoms, and the small balls are nitrogen atom.



Fig. 5 (a) The phonon spectrum of C2/m-BaN₆ structure. (b) Calculated electronic band structure diagram. (c) The calculated projected density of states (PDOS) at 110 GPa. (d) BaN₆ electronic local function graph.

maintaining the entire crystal structure, thereby improving the stability of the overall structure and the energy storage content. We calculated the bond length between nitrogen and nitrogen in the C2/m-BaN₆ structure and found that the bond length between nitrogen and nitrogen in the N6 ring network structure is between 1.37-1.40 Å. Because this values are close to the bond length of the nitrogen-nitrogen single bond,18 which indicates that the N₆ ring network structure contains a large number of nitrogen and nitrogen single bonds. In the C2/m-BaN₆ structure, the N atom in the N₆ ring satisfies the Zintl-Klemm theory³⁶ to achieve charge balance. Since the Ba atom loses two electrons becomes +2 valence cations and combined with the N₆ ring networks, the N atoms in the N6 ring get electrons and combine with Ba showing in the form of $(Ba_x^{2+}-(N_6)_x^{2-})$. In addition, in a $-(N_6)_x^{2-}$, due to the sp³ hybridization of the nitrogen atom, each N atom in the N₆ ring forms two or three σ bonds to connect to the surrounding N atoms, so that nitrogen-nitrogen single bond is formed between N and N. Therefore, we can get that the C2/m-BaN₆ structure contains a large number of nitrogen-nitrogen single bonds.

We have carried out theoretical calculations on the microscopic bonding mechanism of the C2/m-BaN₆ structure, as shown in Fig. 5(d). After theoretical calculations, it is found that in the connected N₆ ring network structures there are strong electronic localization and isolated electrons around N atoms. In Fig. 5(d), a nitrogen six-membered ring network structure is formed among nitrogen atoms, and they participate in bond formation in the form of sp³ hybridization, forming typical covalent bonds. It contains two types of nitrogen atoms, the three sp³ hybrid orbitals of N1 type atoms form three N-N single bonds with the one sp³ hybrid orbital of the adjacent three nitrogen atoms. The remaining one sp³ hybrid orbital is filled with isolated electrons. For every N2 type atom, the two sp^3 hybrid orbitals form two σ bonds with one sp³ hybrid orbital of the surrounding two nitrogen atoms. Particularly, there are two remaining sp³ hybrid orbits are not involved in bonding, the

remaining two sp³ hybrid orbitals are filled with isolated electrons. By analyzing the ELF of C2/m-BaN₆ structure, we can conclude that the degree of N atoms polymerization in C2/m-BaN₆ is relatively higher than other polynitrogen structures, so it has higher energy densities. Therefore, it also can be judged that nitrogen–nitrogen single bond is formed between nitrogen and nitrogen. In the previously reported article, the N-rich compounds with the N₆ ring network structures have high energy density, in the ESI.† Since the N₆ ring network structure contains a large number of nitrogen–nitrogen single bonds, and release a large amount of energy when N₂ is generated. Therefore, the C2/m-BaN₆ structure can theoretically be used as a potential high energy-density material.

4 Conclusions

This paper mainly studied the pressure-induced stability and polymeric nitrogen in alkaline earth metal N-rich nitrides $(XN_6,$ X = Ca, Sr and Ba), and the theoretical calculations were carried out by the first principles and CALYPSO theoretical prediction methods. After theoretical calculation, $P\bar{1}$ -SrN₆ at 22 GPa and C2/ m-BaN₆ at 110 GPa were predicted to be stable under the corresponding high pressure conditions. Further theoretical calculations found that the nitrogen in the $P\bar{1}$ -SrN₆ structure is polymerized in the form of infinite nitrogen chain, and the nitrogen in the monoclinic C2/m-BaN₆ structure is polymerized in the form of an N₆ ring network. Both $P\overline{1}$ -SrN₆ and C2/m-BaN₆ structures are semiconductor materials. And in the $P\bar{1}$ -SrN₆ structure, the nitrogen atom is sp² hybridized, lead to nitrogen and the nitrogen form nitrogen-nitrogen single bond and nitrogennitrogen double bonds coexistence status. In the C2/m-BaN₆ structure, the nitrogen atom is sp³ hybridized, indicating that the nitrogen atom forms two or three σ bonds with the adjacent nitrogen atom. This electronic structure analysis can theoretically indicate that $P\bar{1}$ -SrN₆ and C2/m-BaN₆ may be potential high energydensity materials. The research in this article is helpful to understand the potential properties of alkaline earth metal N-rich compounds under high pressure conditions, and provides a new theoretical basis for obtaining high energy-density materials.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the Natural Science Foundation of Shandong Province (No. ZR2020QA059, ZR2019MA020), Shandong University of Technology Science and Technology PhD Funding.

References

 C. J. M. van der Ham, M. T. M. Koper and D. G. H. Hetterscheid, *Chem. Soc. Rev.*, 2014, 43, 5183–5191.
 J. Uddin, V. Barone and G. E. Scuseria, *Mol. Phys.*, 2006, 104, 745–749.

- 3 T. M. Klapötke, in *High Energy Density Materials*, ed. T. M. Klapötke, Springer Berlin Heidelberg, Berlin, Heidelberg, 2007, pp. 85–121, DOI: 10.1007/430_2007_057.
 4 L. Zhang, Y. Wang, J. Lv and Y. Ma, *Nat. Rev. Mater.*, 2017, 2,
 - 17005. 5 H. Lin, Q. Zhu, C. Huang, D.-D. Yang, N. Lou, S.-G. Zhu and
 - H.-Z. Li, *Struct. Chem.*, 2019, **30**, 2401–2408.
 M. I. Eremets, A. G. Gavriliuk, I. A. Trojan, D. A. Dzivenko and R. Boehler, *Nat. Mater.*, 2004, **3**, 558–563.
 - 7 D. Plašienka and R. Martoňák, J. Chem. Phys., 2015, 142, 094505.
 - 8 M. I. Eremets, R. J. Hemley, H.-k. Mao and E. Gregoryanz, *Nature*, 2001, **411**, 170–174.
 - 9 D. Tomasino, M. Kim, J. Smith and C.-S. Yoo, *Phys. Rev. Lett.*, 2014, **113**, 205502.
 - 10 D. Laniel, G. Geneste, G. Weck, M. Mezouar and P. Loubeyre, *Phys. Rev. Lett.*, 2019, **122**, 066001.
 - 11 F. Zahariev, S. V. Dudiy, J. Hooper, F. Zhang and T. K. Woo, *Phys. Rev. Lett.*, 2006, **97**, 155503.
 - 12 M. Bykov, S. Chariton, E. Bykova, S. Khandarkhaeva, T. Fedotenko, A. V. Ponomareva, J. Tidholm, F. Tasnádi, I. A. Abrikosov, P. Sedmak, V. Prakapenka, M. Hanfland, H.-P. Liermann, M. Mahmood, A. F. Goncharov, N. Dubrovinskaia and L. Dubrovinsky, *Angew. Chem.*, 2020, 59, 10666.
 - 13 R. J. Bruls, H. T. Hintzen and R. Metselaar, *J. Mater. Sci.*, 1999, **34**, 4519–4531.
 - 14 X. Zhang, J. Yang, M. Lu and X. Gong, *RSC Adv.*, 2015, 5, 21823–21830.
 - 15 J. Jiang, P. Zhu, D. Li, Y. Chen, M. Li, X. Wang, B. Liu, Q. Cui and H. Zhu, *J. Phys. Chem. B*, 2016, **120**, 12015–12022.
 - 16 C. Ji, F. Zhang, D. Hou, H. Zhu, J. Wu, M.-C. Chyu, V. I. Levitas and Y. Ma, *J. Phys. Chem. Solids*, 2011, 72, 736– 739.
 - 17 S. Yu, B. Huang, Q. Zeng, A. R. Oganov, L. Zhang and G. Frapper, *J. Phys. Chem. C*, 2017, **121**, 11037–11046.
 - 18 F. Peng, Y. Yao, H. Liu and Y. Ma, *J. Phys. Chem. Lett.*, 2015, 6, 2363–2366.
 - 19 S. Zhu, F. Peng, H. Liu, A. Majumdar, T. Gao and Y. Yao, *Inorg. Chem.*, 2016, 55, 7550–7555.
 - 20 K. Xia, X. Zheng, J. Yuan, C. Liu, H. Gao, Q. Wu and J. Sun, *J. Phys. Chem. C*, 2019, **123**, 10205–10211.
 - 21 J. Zhang, A. R. Oganov, X. Li and H. Niu, *Phys. Rev. B*, 2017, **95**, 020103.
 - 22 X. Wang, Y. Wang, M. Miao, X. Zhong, J. Lv, T. Cui, J. Li,
 L. Chen, C. J. Pickard and Y. Ma, *Phys. Rev. Lett.*, 2012, 109, 175502.
 - 23 K. Ramesh Babu, C. Bheema Lingam, S. P. Tewari and G. Vaitheeswaran, J. Phys. Chem. A, 2011, 115, 4521–4529.
 - 24 K. Ramesh Babu and G. Vaitheeswaran, *Chem. Phys. Lett.*, 2012, **533**, 35–39.
 - 25 M. Zhang, K. Yin, X. Zhang, H. Wang, Q. Li and Z. Wu, *Solid State Commun.*, 2013, **161**, 13–18.
 - 26 X. Wang, J. Li, N. Xu, H. Zhu, Z. Hu and L. Chen, *Sci. Rep.*, 2015, 5, 16677.
 - 27 X. Wang, J. Li, H. Zhu, L. Chen and H. Lin, *J. Chem. Phys.*, 2014, **141**, 044717.

- 28 S. Wei, D. Li, Z. Liu, W. Wang, F. Tian, K. Bao, D. Duan,
 B. Liu and T. Cui, *J. Phys. Chem. C*, 2017, **121**, 9766–9772.
- 29 S. Wei, L. Lian, Y. Liu, D. Li, Z. Liu and T. Cui, *Phys. Chem. Chem. Phys.*, 2020, **22**, 5242–5248.
- 30 B. Huang and G. Frapper, Chem. Mater., 2018, 30, 7623-7636.
- 31 J. Lin, D. Peng, Q. Wang, J. Li, H. Zhu and X. Wang, *Phys. Chem. Chem. Phys.*, 2021, 23, 6863–6870.
- 32 L. Wu, R. Tian, B. Wan, H. Liu, N. Gong, P. Chen, T. Shen, Y. Yao, H. Gou and F. Gao, *Chem. Mater.*, 2018, **30**, 8476– 8485.
- 33 Z. Liu, D. Li, F. Tian, D. Duan, H. Li and T. Cui, *Inorg. Chem.*, 2020, **59**, 8002–8012.
- 34 N. Yedukondalu, G. Vaitheeswaran, P. Modak and A. K. Verma, *Solid State Commun.*, 2019, **297**, 39–44.
- 35 X. Du, Y. Yao, J. Wang, Q. Yang and G. Yang, *J. Chem. Phys.*, 2021, **154**, 054706.
- 36 F. Wang and G. J. Miller, Inorg. Chem., 2011, 50, 7625-7636.
- 37 A. D. Becke and K. E. Edgecombe, *J. Chem. Phys.*, 1990, **92**, 5397–5403.
- 38 Y. Wang, J. Lv, L. Zhu and Y. Ma, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2010, **82**, 094116.
- 39 Y. Wang, J. Lv, L. Zhu and Y. Ma, *Comput. Phys. Commun.*, 2012, **183**, 2063–2070.
- 40 Q. Tong, J. Lv, P. Gao and Y. Wang, *Chin. Phys. B*, 2019, 28, 106105.
- 41 J. Lv, Y. Wang, L. Zhu and Y. Ma, *Phys. Rev. Lett.*, 2011, **106**, 015503.
- 42 B. Delley, J. Phys.: Condens. Matter, 2010, 22, 384208.
- 43 G. Kresse and J. Furthmüller, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1996, **54**, 11169–11186.
- 44 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, 77, 3865–3868.
- 45 X. Blanc, É. Cancès and M.-S. Dupuy, C. R. Math., 2017, 355, 665–670.
- 46 H. J. Monkhorst and J. D. Pack, *Phys. Rev. B: Solid State*, 1976, 13, 5188–5192.
- 47 K. Momma and F. Izumi, *J. Appl. Crystallogr.*, 2011, 44, 1272–1276.
- 48 A. Togo, F. Oba and I. Tanaka, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2008, **78**, 134106.
- 49 S. D. Dabhi and P. K. Jha, Polymer, 2015, 81, 45-49.
- 50 K. Xia, J. Yuan, X. Zheng, C. Liu, H. Gao, Q. Wu and J. Sun, *J. Phys. Chem. Lett.*, 2019, **10**, 6166–6173.
- 51 B. Adivaiah, E. Narsimha Rao and G. Vaitheeswaran, *J. Phys.: Condens. Matter*, 2019, **31**, 475402.
- 52 G. Vaitheeswaran and K. R. Babu, *J. Chem. Sci.*, 2012, **124**, 1391–1398.
- 53 D. Laniel, B. Winkler, E. Koemets, T. Fedotenko, M. Bykov,
 E. Bykova, L. Dubrovinsky and N. Dubrovinskaia, *Nat. Commun.*, 2019, 10, 4515.
- 54 W. C. Butterman and R. G. Reese Jr, *Mineral Commodity Profiles – Rubidium*, Report 2003-45, 2003.
- 55 H. Zhu, X. Han, P. Zhu, X. Wu, Y. Chen, M. Li, X. Li and Q. Cui, *J. Phys. Chem. C*, 2016, **120**, 12423–12428.
- 56 A. A. L. Michalchuk, S. Rudić, C. R. Pulham and C. A. Morrison, *Phys. Chem. Chem. Phys.*, 2018, 20, 29061– 29069.