# **RSC** Advances



View Article Online

View Journal | View Issue

# PAPER

Check for updates

Cite this: RSC Adv., 2021, 11, 39493

# Novel heterostructure Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> coral-like nanoarrays on Ni foam to enhance hydrogen evolution reaction in alkaline media<sup>+</sup>

Yizhi Peng 💿 and Hanwei He\*

Exploring efficient alternatives to precious noble metal catalysts is a challenge. Here, a new type of nonnoble metal  $Cu_2S/Ni_3S_2$  heterostructure nanosheet array is fabricated on 3D Ni foam. This electrocatalyst has excellent activity and durability to Hydrogen Evolution Reaction (HER) under alkaline conditions. The synergistic catalysis produced by the { $\overline{2}10$ } and (034) crystal planes and the increase in charge transfer and the number of active sites caused by lattice defects greatly improve the electrocatalytic activity of Ni<sub>3</sub>S<sub>2</sub>. In the HER process, the  $Cu_2S/Ni_3S_2$  interface increases the formation of S–H bonds, and  $Cu_2S$ promotes the transformation during the HER process into S-doped CuO, optimizing the adsorption capacity of S-doped sites for H. Among electrocatalysts made with different feed ratios,  $Cu_2S/Ni_3S_2/NF-$ 3, for HER, only needs an overpotential of 50 mV to deliver a current density of 10 mA cm<sup>-2</sup>. This work provides a promising non-noble metal electrocatalyst for water splitting under alkaline conditions.

Received 11th October 2021 Accepted 29th November 2021

DOI: 10.1039/d1ra07514d

rsc.li/rsc-advances

### 1. Introduction

 $H_2$ , with its 142 MJ kg<sup>-1</sup> energy density and nonpolluting reproducibility, is a sustainable energy source worthy of research.<sup>1</sup> The application of hydrogen energy urgently requires exploring cleaner, cheaper, and more efficient hydrogen production technology.<sup>2</sup> A viable clean hydrogen production technology is water splitting, but the overpotential requirements of the hydrogen evolution reaction (HER) and the oxygen evolution reaction (OER) limit the wide application. The slow HER kinetic process enormously limits the overall efficiency.<sup>3</sup> Platinum-based electrocatalysts are recognized as the top electrochemical HER catalysts. However, noble metal catalysts cannot be widely used due to practical factors. Commercially available traditional alkaline electrocatalysts are affordable but not sufficiently active,4 such as stainless steel,5 RANEY® nickel,6 and nickel alloys.7 Therefore, exploring catalysts that are effective for HER in abundant non-noble metal elements is urgent.

Owing to these practical problems, research has been carried out for decades to find substitutes for noble metals. Among them, high-performance nickel-based materials with excellent electrochemical performance and intrinsic electrocatalytic activity are expected to become the best candidates.<sup>8-11</sup> Among various nickel sulfides, Ni<sub>3</sub>S<sub>2</sub> with inherent metallic advantages can be a suitable candidate for HER and OER catalysts.<sup>12</sup> As an effective catalyst active ingredient, Ni<sub>3</sub>S<sub>2</sub> is widely used in

electrode materials for supercapacitors and lithium-sulfur batteries.13 Miaomiao Tong14 built special 3D Ni3S2 nanorods@nanosheets, improved their adhesion properties, and exposed more active sites. However, Ni3S2 can still be modified in terms of increasing conductivity, improving catalytic activity, and exposing active sites.15,16 Owing to the inevitable sulfur vacancies in Ni<sub>3</sub>S<sub>2</sub>, the regulation of its surface electronic structure has become a way to improve catalytic activity. Metallic element doping is a feasible solution. It can adjust the adsorption/desorption energy, expand the effective surface area, regulate the electronic structure, and exert a synergistic role between ions.17-19 Relevant literature has reported that Fe,20 Co,<sup>21</sup> Zn,<sup>22</sup> and Mo<sup>23</sup> doping in Ni<sub>3</sub>S<sub>2</sub> improves HER or OER performance. However, Cu-doped high-activity Ni<sub>3</sub>S<sub>2</sub> catalyst with a great HER performance has rarely been reported. Cu, as a doping element, does have a good effect. Several researchers doped Cu as catalytic materials. Zhang et al.24 reported that the charge transfer ability and surface area of Cu-doped Fe-Co oxide have been greatly improved. Co/Cu-modified NiO designed by Guo, ZG et al.25 proved that Cu doping can activate Ni sites at a low overpotential, thereby increasing conductivity and accelerating charge transfer. Until now, studies have focused on the use of doped modified substrate materials. For example, the recent report of Du's group about Cu doped Ni<sub>3</sub>S<sub>2</sub> has an overpotential of 91 mV.26 However, the intrinsic catalytic activity of each substance is different, and it is a novel idea to improve the catalytic activity by constructing a heterostructure. There are few reports on the heterostructure of Cu<sub>2</sub>S and Ni<sub>3</sub>S<sub>2</sub>, which is a direction worth studying. We used the activity of Cu<sub>2</sub>S to construct a heterostructure Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> greatly improved the catalytic activity of Ni<sub>3</sub>S<sub>2</sub> for hydrogen evolution.

Powder Metallurgy Research Institute, Central South University, Changsha, 410083, China. E-mail: hehanwei@csu.edu.cn

<sup>†</sup> Electronic supplementary information (ESI) available. See DOI: 10.1039/d1ra07514d

Based on the above viewpoints, a two-step hydrothermal method was designed to successfully grow Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> with a stable and regular morphology heterostructure on nickel foam. In the first step, the precursor (Cu-Ni layered double hydroxide [LDH]) of the composite structure of nanosheets and nanowires is prepared by changing the feed ratio and reaction conditions. In the second step, a sulfide ion exchange is used to obtain the target sample ( $Cu_2S/Ni_3S_2/NF$ ). The synergistic effect between  $Cu_2S$  and  $Ni_3S_2$  of heterostructure makes the material obtain excellent HER performance. Cu2S/Ni3S2/NF-3 to achieve a current density of 10 mA cm<sup>-2</sup> only needs an overpotential of 50 mV, which is much lower than the reported Cu doped Ni<sub>3</sub>S<sub>2</sub> and Ni-S-Cu systems.<sup>26</sup> The number of active sites calculated by the turnover frequency (TOF) is  $3.568 \times 10^{-4}$  mol. Moreover, the actual surface area of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 is about 2.2 times that of Ni<sub>3</sub>S<sub>2</sub>/NF. The high electrocatalytic performance of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/ NF is mainly manifested in the following aspects: 1. After vulcanization, the surface of the layer structure is "coral-like," exposing abundant active sites and allowing the active ingredients to be in close contact with the electrolyte. 2. The combination of Cu<sub>2</sub>S and Ni<sub>3</sub>S<sub>2</sub>, Cu<sub>2</sub>S is converted into S-doped CuO during the HER process, where CuO introduces a defect level near the Fermi level, accelerates charge transfer and improves intrinsic conductivity.<sup>27</sup> 3. The high conductivity of Ni<sub>3</sub>S<sub>2</sub> provides a fast charge transfer and promotes the electrocatalytic reaction of the catalyst. 4. High-index  $\{\overline{2}10\}$  of Ni<sub>3</sub>S<sub>2</sub> and exposed (034) crystal plane of Cu<sub>2</sub>S improve electrocatalytic performance.

### 2. Experimental section

#### 2.1 Experimental materials preparation

In this experiment, chemicals include ionized water (>18.25 m $\Omega$  cm<sup>-1</sup>, Millipore), and CuCl<sub>2</sub>·2H<sub>2</sub>O, NiCl<sub>2</sub>·6H<sub>2</sub>O, CH<sub>4</sub>N<sub>2</sub>O, NH<sub>4</sub>F, Na<sub>2</sub>S, all purchased from Sinopharm Chemical Reagent Co., Ltd. The nickel foam (NF) used in all experiment were obtained from Kunshan Desco Electronics Co., Ltd. (Suzhou, China) and the density of NF was 350 g m<sup>-2</sup>.

**2.1.1 Fabricating Ni–Cu LDH nanosheet array on NF.** First,  $CuCl_2 \cdot 2H_2O$  and  $NiCl_2 \cdot 6H_2O$  were dissolved in deionized

Table 1         Different feed ratios and corresponding numbers				
$CuCl_2 \cdot 2H_2O$	$NiCl_2 \cdot 6H_2O$	Corresponding Cu–Ni LDH		
2 mmol	2 mmol	Cu–Ni LDH/NF-0		
2 mmol	4 mmol	Cu-Ni LDH/NF-1		
2 mmol	8 mmol	Cu-Ni LDH/NF-2		
2 mmol	18 mmol	Cu-Ni LDH/NF-3		
2 mmol	24 mmol	Cu-Ni LDH/NF-4		

water(70 mL) at different molar ratios (the specific feed ratio and the corresponding serial number are shown in Table 1), 10 mmol  $CH_4N_2O$  and 4 mmol  $NH_4F$  were add in above solution. Then the precursor solution, stirred for 10 minutes, was transferred into a 100 mL Teflon-line stainless autoclave. The prepared clean NF (2 × 5 cm) was immersed in it, then reacted at 120 °C for 6 h. After cooling, the obtained Ni–Cu LDH/NF was washed and then placed at 60 °C to dry overnight in a vacuum oven. Fig. 1 shows the schematic diagram of preparation of  $Cu_2S/Ni_3S_2/NF$ .

**2.1.2** Ni–Cu LDH sulfide to Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>. Prepared 0.2mol  $L^{-1}$  Na<sub>2</sub>S solution and dried NiCu-LDH were put into Teflon-line stainless autoclave. After reacting at 100 °C for 8 h, the black Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF was obtained. After the Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF is washed and dried, the subsequent characterization and performance can be performed.

# 2.2 Preparation for material characterizations and electrochemical measurements

The X-ray diffraction (XRD) of Ni–Cu LDH and  $Cu_2S/Ni_3S_2$  was measured using a PANalytical Empyren equipment at 45 kV and 40 mA with a Cu target. The scanning electron microscopy (SEM) images of Ni–Cu LDH and  $Cu_2S/Ni_3S_2$  were from Zeiss Sigma 500. Energy dispersive spectroscopy (EDS) analyses were recorded by FEI Talos 200s. The valence states of the elements on the electrode surface were obtained by an ESCALAB 250Xi Xray photon spectrometer (XPS). Transmission electron microscopy (TEM), selected area electron diffraction (SAED), highresolution TEM (HRTEM), and scanning TEM were all obtained by using a JEM2100F microscope.

All electrochemical tests use CHI660B electrochemical workstation. A three-electrode system consisting of graphite, saturated calomel electrodes (SCE, KCl saturated) and the sample to be tested was made up in 1 M KOH at 25 °C. The potentials measured in the experiment has been calibrated, and the potential (*vs.* SCE) was converted into a reversible hydrogen electrode (RHE) through the Nernst equation:<sup>28</sup>  $E_{vs.RHE} = E_{vs.SCE}$  + 0.242 V + 0.059 pH. The polarization curves were corrected by the equation:<sup>29</sup>  $E_{corrected} = E_{vs.RHE} - iR$  linear sweep voltammetry (LSV), cyclic voltammetry (CV), electrochemical impedance spectroscopy (EIS) and continuous CV cycles were used to evaluate the electrocatalytic performance of the catalyst.

### 3. Experimental results

#### 3.1 Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> structure analysis

NF with 3D conductive network structure and macropores was used as a base material for electrocatalyst growth. After the twostep hydrothermal reaction mentioned above, the silver white



Fig. 1 Schematic diagram of preparation of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF.

#### Paper

NF changed to brick red (the NiCu LDH precursor) and then black (Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF). The SEM images in Fig. 2(a)-(f) can visually present the microscopic morphology of the sample. Fig. 2(a)-(c) show the SEM images of NiCu LDH. NiCu LDH is uniformly anchored on the NF substrate in a sheet-like manner. After further increasing the magnification, "nano fluff" was evenly distributed on the nanosheets. Compared with NiCu LDH, the SEM images of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF did not change significantly, as shown Fig. 3(d)-(f), indicating that the required LDH layered structure can exist stably. After vulcanization, the "nano fluff" is transformed into a "coral" with a rough surface, exposing more active sites. The SEM picture of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF after 58 h chronopotentiometry test is placed in the support information. As shown in Fig. S1,† some cracks appeared on Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> layer after the test. And the original thin nanosheets are transformed into a stacked coral layer. This transition from

"nano fluff" to "rough coral" increases the specific surface area and helps improve electrocatalytic activity.

Furthermore, Fig. 2(g) shows the XRD pattern of Ni<sub>3</sub>S<sub>2</sub>/NF and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF. Both XRD spectra have the same three strong peaks, based foam nickel (PDF #70-1849). The diffraction peaks of both at  $2\theta = 21.75^{\circ}$ ,  $31.10^{\circ}$ ,  $37.78^{\circ}$ ,  $49.73^{\circ}$ , and  $55.16^{\circ}$ correspond to Ni<sub>3</sub>S<sub>2</sub> (PDF #44-1418) (101), (110), (003), (113), and (122) crystal planes, respectively. Obviously, the characteristic peak of Cu<sub>2</sub>S (PDF #33-0490) appeared in the XRD spectrum (indicated by the orange line) after Cu was added. The XRD spectrum qualitatively showed the existence of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF sample, and their atomic ratio is close to the feed ratio. The Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF after 58 h chronopotentiometry test was characterized by XRD. As shown in the ESI Fig. S2,† after the 58 h stability test, the XRD spectrum of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF showed a CuO



Fig. 2 (a-c) SEM image of NiCu LDH-3, (d-f) SEM image of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3, (g) XRD pattern of Ni<sub>3</sub>S<sub>2</sub>/NF, Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF and NF, (h) EDS image of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF.



Fig. 3 (a) XPS survey spectrum for Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>. XPS spectra of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> in the (b) Ni 2p, (c) Cu 2p and (d) S 2p regions

peak (PDF #89-5899) that had not appeared before the test. The diffraction peaks at  $2\theta = 35.6^{\circ}$ ,  $38.8^{\circ}$ , and  $48.7^{\circ}$  correspond to CuO (-111), (111), and (-202) crystal planes, respectively. The intensity of the Cu<sub>2</sub>S peak weakened, indicating that Cu<sub>2</sub>S was partially converted to CuO.

In addition, the element composition of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 can be obtained by XPS. The overall XPS spectrum of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 is shown in Fig. 3(a), where Ni, Cu, and S are present. Fig. 3(b) shows the XPS spectrum of the Ni 2p region, where the intensities of the Ni  $2p_{1/2}$  and Ni  $2p_{3/2}$  peaks are 855.48 eV and 873.23 eV, respectively, indicating that Ni exists in the form of Ni<sub>3</sub>S<sub>2</sub>.<sup>30</sup> The peaks of 879.2 and 860.8 eV are the concomitant satellites.<sup>31,32</sup> The small peak on the far right (852.8 eV) is a typical metal nickel sulfide or metal nickel peak.<sup>33</sup> In the XPS spectrum of Cu 2p region shown in Fig. 3(c), 932.03 eV is the peak of Cu  $2p_{3/2}$  in Cu<sub>2</sub>S, and 951.93 eV is the peak of Cu  $2p_{1/2}$ .<sup>34</sup> The last picture in Fig. 3(d) is the XPS spectrum of S 2p, where 162.48 and 161.48 eV are attributed to S  $2p_{1/2}$  and  $2p_{3/2}$  in Ni<sub>3</sub>S<sub>2</sub>, respectively.<sup>35</sup> And 162.25 eV is attributed to S 2p<sub>3/2</sub> in Cu<sub>2</sub>S. All XPS spectra fully prove that the synthesized sample is Cu<sub>2</sub>S/ Ni<sub>3</sub>S<sub>2</sub>. After 58 h chronopotentiometry test, the XPS spectra of the electrode is placed in the ESI Fig. S3.<sup>†</sup> In Fig. S3(b)<sup>†</sup> shows that Ni 2p<sub>3/2</sub> and Ni 2p<sub>1/2</sub> of Ni<sub>3</sub>S<sub>2</sub> are the main strong peaks, which can match the conclusion of XRD (Fig. S2<sup>†</sup>). Moreover, in Fig. S3(b).† The Cu 2p spectra (Fig. S3(c)†) shows  $Cu^+$  and  $Cu^{2+}$ peaks. Among them, the Cu  $2p_{3/2}$  and Cu  $2p_{1/2}$  match with the Cu<sub>2</sub>S and the strong Cu<sup>2+</sup> satellite match with the CuO detected by XRD (Fig. S2<sup>†</sup>). Compared with the original XPS spectra, the intensity of S 2p (Fig. S3(d)<sup>†</sup>) is reduced after the chronopotentiometry test. We suspected that the heterostructure Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> catalyst is converted to sulfur-doped CuO in this process. It is reported that the  $\Delta G_{H^*}$  of sulfur-doped CuO is lower than that of pure CuO.<sup>36</sup> The heterostructure between Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> promotes interface electron transfer. The Ni sites at the Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> interface interact with O in water molecules to adsorb water molecules on the surface. After that, the water molecules adsorbed on the Ni site interact with hydrogen bonds or form S-H bonds, which accelerate the adsorption and dissociation of water and increase the speed of the Volmer step.<sup>37-39</sup> It is reported that S optimizes the free energy of H\* ( $\Delta$ EH\*) adsorption of CuO, and the O site of CuO near the S-doped site increased the H adsorption capacity.<sup>40</sup>

Fig. 4(a) clearly shows the TEM image of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF layer structure stacked on top of one another. The SAED pattern of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF in Fig. 4(b) shows typical polycrystalline diffraction rings. These calibrated diffraction rings can correspond well to the peak of the XRD spectrum. Comparing with the PDF card confirmed it to be Ni<sub>3</sub>S<sub>2</sub>. The diffraction ring of the (034) crystal planes of Cu<sub>2</sub>S can also be observed, which corresponds to the strong peak appearing after Cu doping in the XRD spectrum. The exposed (034) crystal planes of Cu<sub>2</sub>S is beneficial for the improvement of the HER performance of the catalyst. The HRTEM lattice fringe image of  $Cu_2S/Ni_3S_2$  is in Fig. 4(c). The crystal planes with interplanar spacings of 0.287, 0.234, and 0.237 nm correspond to the (110), (021), and (003) crystal planes of Ni<sub>3</sub>S<sub>2</sub> (PDF#44-1418), respectively. The exposed crystal surface of the catalyst has an important influence on its catalytic performance. The angle between the two (110) is  $60^{\circ}$ , indicating that the thermodynamically stable {001} crystal planes is exposed. The angle between (003) and (021) is about 70.5°, then

(00)



Fig. 4 (a) TEM image of  $Cu_2S/Ni_3S_2$  layer structure, (b) SAED pattern and (c) HRTEM image of  $Cu_2S/Ni_3S_2$ , (d) mapping of Ni, Cu, S and overlap images of  $Cu_2S/Ni_3S_2$  nanosheet.

high-index  $\{\bar{2}10\}$  is exposed.<sup>41</sup> Research by Liang-Liang Feng *et al.*<sup>41</sup> showed that the synergistic catalysis produced by the nanosheet array and the exposed  $\{\bar{2}10\}$  high-index facets help improve electrocatalytic performance. Numerous disordered defects and the exposed (034) crystal planes of Cu<sub>2</sub>S can also be observed in the HRTEM image, indicating that the exposed active sites and electrical conductivity can be increased.<sup>42</sup> Moreover, the mapping of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> nanosheet in Fig. 4(d) reflects that Ni, S, and Cu are evenly distributed on the nanosheets, which is conducive to the uniform dispersion of active sites.

#### 3.2 Catalyst electrochemical performance analysis

3.2.1 Catalyst HER performance. The LSV of Pt/C,  $Ni_3S_2/NF$ , and  $Cu_2S/Ni_3S_2/NF-x$  (x represents various feed ratios) was

Table 3 Comparison of the electrocatalysts performance of Cu\_2S/  $Ni_3S_2/NF$  and other  $Ni_3S_2$ 

Catalysts	Electrolyte Solution	Overpotential $(\eta_{10})$
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-3	1 М КОН	50 mV
S-v-Ni <sub>3</sub> S <sub>2</sub> $-xP_{x-4}$ (ref. 44)	1 M KOH	89 mV
Mo-doped Ni <sub>3</sub> S <sub>2</sub> (ref. 45)	1 M KOH	90 mV
V-doped Ni <sub>3</sub> S <sub>2</sub> /NiS <sup>46</sup>	1 M KOH	85 mV
CoNi <sub>2</sub> S <sub>4</sub> /Ni <sub>3</sub> S <sub>2</sub> @NF <sup>47</sup>	1 M KOH	171 mV

Table 2	Comparison	of	overpotential	of	different	samples
---------	------------	----	---------------	----	-----------	---------

Catalysts	Current density $(j \text{ mA cm}^{-2})$	Overpotential $\left(\eta/\mathrm{mV}\right)$
Pt/C	10	31
Ni <sub>3</sub> S <sub>2</sub> /NF	10	180
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-0	10	182
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-1	10	159
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-2	10	122
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-3	10	50
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-4	10	134

Table 4 Number of active sites of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-x and Ni<sub>3</sub>S<sub>2</sub>/NF

Catalysts	Number of active sites ( $\times 10^{-4}$ mol)
Ni <sub>3</sub> S <sub>2</sub> /NF	1.625
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-2	2.639
Cu <sub>2</sub> S/Ni <sub>3</sub> S <sub>2</sub> /NF-3	3.568
$Cu_2S/Ni_3S_2/NF-4$	3.533

3



Fig. 5 (a) *iR*-Corrected linear sweep voltammetry curves of Ni<sub>3</sub>S<sub>2</sub>/NF and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-*x* (*x* represents various feed ratios) for HER in 1 M KOH at 5 mV s<sup>-1</sup>, (b) Tafel plots of Ni<sub>3</sub>S<sub>2</sub>/NF, Pt/C and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3, (c) CVs of Ni<sub>3</sub>S<sub>2</sub>/NF and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-*x* at pH = 7 at the scan rate of 50 mV s<sup>-1</sup>, (d) TOF curves of Ni<sub>3</sub>S<sub>2</sub>/NF and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-*x*, (e) polarization curves of Ni<sub>3</sub>S<sub>2</sub>/NF and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-*x* normalized by the ECSA, (f) measured capacitive currents plotted as a function of scan rate.

evaluated in 1 M KOH solution. Comparing the polarization curves clearly shows that Pt/C has the best HER performance ( $\eta_{10} = 31$  mV), whereas Ni<sub>3</sub>S<sub>2</sub>/NF requires 180 mV. The Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 curve, which is closest to Pt/C curve, requires an

overpotential of 50 mV at 10 mA cm<sup>-2</sup>. The overpotentials of five samples are shown in Table 2. Compared with Ni<sub>3</sub>S<sub>2</sub>/NF, the HER performance of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF is indeed improved much. However, experiments have shown that the amount of Cu



Fig. 6 (a) The chronopotentiometry curve of  $Cu_2S/Ni_3S_2/NF$  at constant current density of 10 mA cm<sup>-2</sup>. (b) The polarization curves of  $Cu_2S/Ni_3S_2/NF$  at constant current density of 10 mA cm<sup>-2</sup>. Ni<sub>3</sub>S<sub>2</sub>/NF-3 before and after 2000 CV cycles. (c) Stability test of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 carried out at multiple currents. (d) Impedance Nyquist plots of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-2, Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 and Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-4.

cannot be too much, which is consistent with Byung Keun Kim's report<sup>43</sup> that excessive Cu will increase the internal stress and cause the coating to fall off, thereby reducing catalytic performance. Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF was also compared with the results of other scientific researchers. Detailed data can be found in Table 3.

In alkaline solution, HER follows Volmer-Tafel or Volmer-Heyrovsky mechanism.<sup>48</sup> They all consist of three steps: 1. Discharge ( $H_2O + e^- \rightarrow H^* + OH^-$ , Volmer reaction) 2. Electrochemical desorption ( $H_2O + H^* + e^- \rightarrow H_2 + OH^-$ , Heyrovsky reaction) and 3. Recombination ( $2H^* \rightarrow H_2$ , Tafel reaction). The calculated Tafel slope of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 is 107 mV dec<sup>-1</sup> (lower than 120 mV dec $^{-1}$ ), indicating that hydrogen evolution is mainly limited by the Volmer reaction and follows the Volmer-Heyrovsky mechanism. The Tafel slope of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 is clearly much smaller than that of Ni<sub>3</sub>S<sub>2</sub>/NF, indicating that Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 catalytic reaction kinetics is faster in an alkaline medium, and the catalytic activity of HER is better.<sup>49</sup>

Turnover frequency (TOF) can be used to reflect intrinsic activity.<sup>50</sup> First, CV curves were measured in a ph = 7 phosphate

buffer saline solution at a scan rate of 50 mV s<sup>-1</sup> and a voltage range of -0.2-0.6 V. Then, the number of active sites was calculated from the method reported by Merki.<sup>51</sup> In Table 4, the active sites loaded on the Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 surface is 3.568  $\times$  $10^{-4}$  mol, which is more than Ni<sub>3</sub>S<sub>2</sub>/NF (1.625 × 10<sup>-4</sup> mol). This result may be related to the coral-like surface on the nanosheet shown in the SEM image. This specific morphology can expose more active sites. The calculated TOFs are shown in Fig. 5(d). The overpotentials of Ni<sub>3</sub>S<sub>2</sub>/NF, Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-2~4 at TOF of 0.2 S<sup>-1</sup> are 182, 168, 72, and 119 mV, respectively. In Fig. 6(a), TOFs denote that Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 has a higher catalytic activity.

Electrochemical Active Surface Area (ECSA) test was carried out. First, the CV curves were measured at various scan rate. Then, Half of the values of the positive and negative current density differences  $(\Delta i)$  at the median value of the scanning range are plotted versus the CV scanning rates in Fig. 5(f). The electrochemical double layer charge  $(C_{dl})$  value can be obtained from the fit slope. Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 and Ni<sub>3</sub>S<sub>2</sub>/NF are both cut into 1 cm  $\times$  1 cm rectangles, with the same geometric surface area. The  $C_{dl}$  of  $Cu_2S/Ni_3S_2/NF-3$  (17.95 mF cm<sup>-2</sup>) is approximately 2.2 times that of Ni<sub>3</sub>S<sub>2</sub>/NF (8.23 mF cm<sup>-2</sup>), indicating that the actual surface area of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 is larger. From Fig. S4,† the surface loading of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> is 2.8 mg cm<sup>-2</sup>.

The chronopotentiometry curve was measured to evaluate the mechanical strength and excellent mass transfer performance of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3. In Fig. 6(a), Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF can maintain 95.1% activity stably for at least 58 hours. The fluctuation of the curve in the first 30 minutes is due to the gradual increase in the potential during the activation phase caused by the removal of the hydroxide/oxide on the electrode surface.52 A CV was performed 2000 times continuously from 100 mV to -300 mV. In Fig. 6(b), the HER performance of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 decreased slightly after the CV and need 70 mV to 10 mA  $cm^{-2}$ . Multistep chronopotentiometry (from 10 mA to 100 mA with 10 mA interval) was used to evaluate the mass transfer and stability of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3. The electrode reaction kinetics can be studied by EIS. The Nyquist diagrams of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-2,3,4 were obtained at 200 mV. The equivalent circuit in Fig. 6(d): a constant-phase element (CPE) connected in parallel with a charge transfer resistance  $(R_{ct})$ , then an electrolyte resistance  $(R_s)$  is connected in series. The fitting line represented by the red line is semicircular, which means that the charge transfer controls the entire HER. R<sub>ct</sub> can be determined in the semicircular low-frequency region to reflect the electron transport efficiency.<sup>53</sup> The R<sub>ct</sub> values of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-2,3,4 are 2.44 Ω, 0.79  $\Omega$ , and 1.98  $\Omega$ , respectively. Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 has the smallest  $R_{ct}$ , which means fast electron transfer. The excellent HER performance of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 also echoes this result. By contrast, a small  $R_s$  value indicates that the bonding between the catalyst and the current collector is good.<sup>54</sup> The impedance results of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 are consistent with the previous HER results, which can prove that it can be a candidate with excellent HER kinetics and outstanding electron transport performance.

### 4. Conclusion

Overall, the heterostructure Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> were successfully synthesized by two-step hydrothermal method and exhibited excellent HER activity. Compared with the recently reported system, Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub>/NF-3 has a lower overpotential ( $\eta_{10} = 50$ mV). After vulcanization, the coral-like rough surface exposes more active sites. The heterostructure of Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> exposes specific { $\bar{2}10$ } crystal planes as well as a large number of defects and (034) crystal planes, which helps expose more active sites. The structural characterization is consistent with the electrochemical test results. In HER process, Cu<sub>2</sub>S/Ni<sub>3</sub>S<sub>2</sub> interface increase the formation of S–H bonds, optimizing the adsorption capacity of S-doped sites for H. And Cu<sub>2</sub>S promotes the transformation of the HER process into S-doped CuO. Therefore, the combination of Cu<sub>2</sub>S and Ni<sub>3</sub>S<sub>2</sub> further increases the catalytic activity.

## Conflicts of interest

The authors declare no conflict of interest.

## Acknowledgements

Authors very thanks for the help from the friends and the authoritative opinion and suggestions from the reviewers.

### References

- 1 S. Chu, Y. Cui and N. Liu, The path towards sustainable energy, *Nat. Mater.*, 2017, **16**, 16–22, DOI: 10.1038/nmat4834.
- 2 Z. W. Seh, J. Kibsgaard, C. F. Dickens, I. B. Chorkendorff, J. K. Norskov and T. F. Jaramillo, Combining theory and experiment in electrocatalysis: insights into materials design, *Science*, 2017, **355**, 146, DOI: 10.1126/ science.aad4998.
- 3 L. Peng, J. Shen, X. Zheng, R. Xiang, M. Deng, Z. Mao, Z. Feng, L. Zhang, L. Li and Z. Wei, Rationally design of monometallic NiO-Ni <sub>3</sub> S<sub>2</sub>/NF heteronanosheets as bifunctional electrocatalysts for overall water splitting, *J. Catal.*, 2018, **369**, 345–351, DOI: 10.1016/j.jcat.2018.11.023.
- 4 K. Zeng and D. Zhang, Recent progress in alkaline water electrolysis for hydrogen production and applications, *Prog. Energy Combust. Sci.*, 2010, **36**, 307–326, DOI: 10.1016/ j.pecs.2009.11.002.
- 5 M. Gong and H. Dai, A mini review of NiFe-based materials as highly active oxygen evolution reaction electrocatalysts, *J. Nano Res.*, 2015, **8**, 23–39, DOI: 10.1007/s12274-014-0591-z.
- 6 L. B. Lasia, Studies of the Hydrogen Evolution Reaction on Raney Nickel—Molybdenum Electrodes, *J. Appl. Electrochem.*, 2004, 34, DOI: 10.1023/ B:JACH.0000031161.26544.6a.
- 7 N. Danilovic, R. Subbaraman and D. Strmcnik, Enhancing the Alkaline Hydrogen Evolution Reaction Activity through the Bifunctionality of Ni(OH)<sub>2</sub>/Metal Catalysts, *Angew. Chem.*, 2012, **124**, 12663–12666, DOI: 10.1002/anie.201204842.
- 8 C. Yang, M. Y. Gao, Q. B. Zhang, J. R. Zeng, X. T. Li and A. P. Abbott, *In situ* activation of self-supported 3D hierarchically porous Ni3S2 films grown on nanoporous copper as excellent pH-universal electrocatalysts for hydrogen evolution reaction, *Nano Energy*, 2017, **36**, 85–94, DOI: 10.1016/j.nanoen.2017.04.032.
- 9 X. F. A. B., Y. S. A., J. S. A., L. H. A. and Z. H. B., Superhydrophilic 3D peony flower-like Mo-doped Ni 2 S 3
  (a) NiFe LDH heterostructure electrocatalyst for accelerating water splitting, *Int. J. Hydrogen Energy*, 2021, 46, 5169– 5180, DOI: 10.1016/j.ijhydene.2020.11.018.
- 10 J. J. Duan, Z. Han, R. L. Zhang, J. J. Feng and A. J. Wang, Iron, manganese co-doped Ni<sub>3</sub>S<sub>2</sub> nanoflowers *in situ* assembled by ultrathin nanosheets as a robust electrocatalyst for oxygen evolution reaction, *J. Colloid Interface Sci.*, 2020, **588**, DOI: 10.1016/j.jcis.2020.12.062.
- 11 Q. Ma, C. Hu, K. Liu, S. F. Hung, D. Ou, H. Ming Chen, G. Fu and N. Zheng, Identifying the Electrocatalytic Sites of Nickel Disulfide in Alkaline Hydrogen Evolution Reaction, *Nano Energy*, 2017, **41**, 148–153, DOI: 10.1016/ j.nanoen.2017.09.036.

- 12 Y. J. Liu, C. L. Luan, J. T. Yang, Y. Dong, Y. Wang, C. L. Qin, Z. Dong, S. Q. Wang, X. P. Dai and X. Zhang, In situ fabrication of dynamic self-optimizing  $Ni_3S_2$  nanosheets as an efficient catalyst for the oxygen evolution reaction, *DTr*, 2019, **49**, 70–78, DOI: 10.1039/c9dt03885j.
- 13 M. R. Gao, J. X. Liang, Y. R. Zheng, Y. F. Xu, J. Jiang, Q. Gao, J. Li and S. H. Yu, An efficient molybdenum disulfide/cobalt diselenide hybrid catalyst for electrochemical hydrogen generation, *Nat. Commun.*, 2015, 6, 5982, DOI: 10.1038/ ncomms6982.
- 14 M. Tong, L. Wang, P. Yu, C. Tian, X. Liu, W. Zhou and H. Fu,  $Ni_3S_2$  nanosheets *in situ* epitaxially grown on nanorods as high active and stable homojunction electrocatalyst for hydrogen evolution reaction, *ACS Sustainable Chem. Eng.*, 2017, **6**, 2474–2481, DOI: 10.1021/acssuschemeng.
- 15 X. Luo, P. Ji, P. Wang, R. Cheng and S. Mu, Interface Engineering of Hierarchical Branched Mo-Doped Ni3S2/ NixPy Hollow Heterostructure Nanorods for Efficient Overall Water Splitting, *Adv. Energy Mater.*, 2020, 10, 1–11, DOI: 10.1002/aenm.201903891.
- 16 X. Liang, Y. Li, H. Fan, S. Deng and X. Xia, Bifunctional NiFe layered double hydroxide@Ni<sub>3</sub>S<sub>2</sub> heterostructure as efficient electrocatalyst for overall water splitting, *Nanot*, 2019, 30, 484001, DOI: 10.1088/1361-6528/ab3ce1.
- 17 J. Jian, L. Yuan, H. Qi, X. Sun, L. Zhang, H. Li, H. Yuan and S. Feng, Sn-Ni3S2 Ultrathin Nanosheets as Efficient Bifunctional Water Split-ting Catalyst with Large Current Density and Low Overpotential, ACS Appl. Mater. Interfaces, 2018, 10, DOI: 10.1021/acsami.8b14603.
- 18 Y. Zhang, Y. Liu, M. Ma, X. Ren, Z. Liu, G. Du, A. M. Asiri and X. Sun, A Mn-doped Ni2P nanosheet array: an efficient and durable hydrogen evolution reaction electrocatalyst in alkaline media, *Chem. Commun.*, 2017, 53, 11048–11051, DOI: 10.1039/c7cc06278h.
- 19 G. Zhang, Y. S. Feng, W. T. Lu, D. He, C. Y. Wang, Y. K. Li, X. Y. Wang and F. F. Cao, Enhanced Catalysis of Electrochemical Overall Water Splitting in Alkaline Media by Fe Doping in Ni3S2 Nanosheet Arrays, *ACS Catal.*, 2018, 8, 5431–5441, DOI: 10.1021/acscatal.8b00413.
- 20 N. Xie, D. D. Ma, X. T. Wu and Q. L. Zhu, Facile construction of self-supported Fe-doped Ni3S2 nanoparticle arrays for the ultralow-overpotential oxygen evolution reaction, *Nanoscale*, 2021, **13**, 1807–1812, DOI: 10.1039/d0nr07262a.
- 21 M. Wang, M. Zhang, W. Song, W. Zhong, X. Wang, J. Wang, T. Sun and Y. Tang, A highly stable CoMo2S4/Ni3S2 heterojunction electrocatalyst for efficient hydrogen evolution, *Chem. Commun.*, 2021, 57, 785–788, DOI: 10.1039/d0cc06972h.
- 22 Q. Liu, L. Xie, Z. Liu, G. Du and X. Sun, A Zn-doped Ni3S2 nanosheet array as a high-performance electrochemical water oxidation catalyst in alkaline solution, *Chem. Commun.*, 2017, **53**, 12446–12449, DOI: 10.1039/c7cc06668f.
- 23 P. Phonsuksawang, P. Khajondetchairit, K. Ngamchuea, T. Butburee and T. Siritanon, Enhancing performance of NiCo2S4/Ni3S2 supercapacitor electrode by Mn doping, *Electrochim. Acta*, 2020, **368**, 137634, DOI: 10.1016/ j.electacta.2020.137634.

- 24 Q. Zhang, N. Liu and J. Guan, Accelerative oxygen evolution by Cu-doping into Fe-Co oxides, *Sustainable Energy Fuels*, 2020, 4, 143–148, DOI: 10.1039/c9se00928k.
- 25 Z. Guo, X. Wang, Y. Gao and Z. Liu, Co/Cu-modified NiO film grown on nickel foam as a highly active and stable electrocatalyst for overall water splitting, *DTr*, 2020, **49**, 1776–1784, DOI: 10.1039/c9dt04771a.
- 26 X. Du, Y. Ding and X. Zhang, Cu-doped Ni3S2 interlaced nanosheet arrays as high-efficiency electrocatalyst boosting the alkaline hydrogen evolution, *ChemCatChem*, 2021, 1824–1833, DOI: 10.1002/cctc.202001838.
- 27 S. Chu, W. Chen, G. Chen, J. Huang, R. Zhang, C. Song, X. Wang, C. Li and K. Ostrikov, Holey Ni-Cu phosphide nanosheets as a highly efficient and stable electrocatalyst for hydrogen evolution, *Appl. Catal., B*, 2018, **243**, 537–545, DOI: 10.1016/j.apcatb.2018.10.063.
- 28 Y. Jiao, W. Hong, P. Li, L. Wang and G. Chen, Metal-Organic Framework Derived Ni/NiO Micro-particles with Subtle Lattice Distortions for High-performance Electrocatalyst and Supercapacitor, *Appl. Catal., B*, 2018, **244**, 732–739, DOI: 10.1016/j.apcatb.2018.11.035.
- 29 A. P. Murthy, J. Theerthagiri, K. Premnath, J. Madhavan and K. Murugan, Single-Step Electrodeposited Molybdenum Incorporated Nickel Sulfide Thin Films from Low-Cost Precursors as Highly Efficient Hydrogen Evolution Electrocatalysts in Acid Medium, *J. Phys. Chem. A*, 2017, **121**, 11108–11116, DOI: 10.1021/acs.jpcc.7b02088.
- 30 X. B. Wang, J. J. Hu, W. D. Liu, G. Y. Wang, J. An and J. S. Lian, Ni–Zn binary system hydroxide, oxide and sulfide materials: synthesis and high supercapacitor performance, *J. Mater. Chem. A*, 2015, **3**, 23333–23344, DOI: 10.1039/c5ta07169k.
- 31 Y. Zhu, H. D. Yang, K. Lan, K. Lqbal, Y. Liu, P. Ma, Z. M. Zhao, S. Luo, Y. T. LUO and J. T. Ma, Optimization of iron-doped Ni3S2 nanosheets by disorder engineering for oxygen evolution reaction, *Nanoscale*, 2019, **11**, 2355–2365, DOI: 10.1039/c8nr08469f.
- 32 A. H. Jayatissa and G. Sumanasekera, Surface and gas sensing properties of nanocrystalline nickel oxide thin films, *Appl. Surf. Sci.*, 2013, **276**, 291–297, DOI: 10.1016/ j.apsusc.2013.03.085.
- 33 M. C. Biesinger, B. P. Payne, L. W. M. Lau, A. Gerson and R. S. C. Smart, X-ray photoelectron spectroscopic chemical state quantification of mixed nickel metal, oxide and hydroxide systems, *Surf. Interface Anal.*, 2009, **41**, 324–332, DOI: 10.1002/sia.3026.
- 34 X. Xun, H. Liu, Y. Su, J. Zhang, J. Niu, H. Zhao, G. Zhao, Y. Liu and G. Li, One-pot synthesis Ni-Cu sulfide on Ni foam with novel three-dimensional prisms/spheres hierarchical structure for high-performance supercapacitors, *J. Solid State Chem.*, 2019, 275, 95–102, DOI: 10.1016/j.jssc.2019.04.012.
- 35 Y. Li, L. Cao, L. Qiao, M. Zhou, Y. Yang, P. Xiao and Y. Zhang, Ni–Co sulfide nanowires on nickel foam with ultrahigh capacitance for asymmetric supercapacitors, *J. Mater. Chem. A.*, 2014, 2, 6540–6548, DOI: 10.1039/c3ta15373h.

- 36 Y. G. Lin, Y. K. Hsu, C. J. Chuang, Y. C. Lin and Y. C. Chen, Thermally activated Cu/Cu2S/ZnO nanoarchitectures with surface-plasmon-enhanced Raman scattering, *J. Colloid Interface Sci.*, 2015, 464, 66–72, DOI: 10.1016/ j.jcis.2015.10.043.
- 37 S. Li, C. Xi, Y. Jin, D. Wu and X. W. Du, Ir-O-V Catalytic Group in Ir-Doped NiV(OH)2 for Overall Water Splitting, *ACS Energy Lett.*, 2019, 4, 1823–8195, DOI: 10.1021/ acsenergylett.9b01252.
- 38 Y. Liu, Q. Li, R. Si, G. D. Li, W. Li, D. P. Liu, D. Wang, L. Sun, Y. Zhang and X. Zou, Coupling Sub-Nanometric Copper Clusters with Quasi-Amorphous Cobalt Sulfide Yields Efficient and Robust Electrocatalysts for Water Splitting Reaction, *Adv. Mater.*, 2017, 29, 1606200, DOI: 10.1002/ adma.201606200.
- 39 J. X. Feng, J. Q. Wu, Y. X. Tong and G. R. Li, Correction to Efficient Hydrogen Evolution on Cu Nanodots-Decorated Ni 3 S 2 Nanotubes by Optimizing Atomic Hydrogen Adsorption and Desorption, *J. Am. Chem. Soc.*, 2020, 142, 18997, DOI: 10.1021/jacs.9b06861.
- 40 Z. Zang, X. Wang, X. Li, Q. Zhao and Z. Lu, Co 9 S 8 Nanosheet Coupled Cu 2 S Nanorod Heterostructure as Efficient Catalyst for Overall Water Splitting, ACS Appl. Mater. Interfaces, 2021, 13, DOI: 10.1021/acsami.0c20820.
- 41 L. L. Feng, G. Yu, Y. Wu, G. D. Li, L. Hui, Y. Sun, T. Asefa, W. Chen and X. Zou, High-Index Faceted Ni3S2 Nanosheet Arrays as Highly Active and Ultrastable Electrocatalysts for Water Splitting, *J. Am. Chem. Soc.*, 2015, **137**, 14023–14026, DOI: 10.1021/jacs.5b08186.
- 42 X. Zhang, Y. Zhao, Y. Zhao, R. Shi, G. Waterhouse and T. Zhang, A Simple Synthetic Strategy toward Defect-Rich Porous Monolayer NiFe-Layered Double Hydroxide Nanosheets for Efficient Electrocatalytic Water Oxidation, *Adv. Energy Mater.*, 2019, **9**, 1–7, DOI: 10.1002/ aenm.201900881.
- 43 K. B. Keun, K. Soo-Kil, C. S. Ki and K. J. Jeong, Enhanced Catalytic Activity of Electrodeposited Ni-Cu-P toward Oxygen Evolution Reaction, *Appl. Catal.*, *B*, 2018, 237, 409– 415, DOI: 10.1016/j.apcatb.2018.05.082.
- 44 Y. Yang, H. Mao, R. Ning, X. Zhao and W. Cai, Ar Plasmaassisted P-doped Ni3S2 with S Vacancies for efficient electrocatalytic water splitting, *DTr*, 2021, **50**, 2007–2013, DOI: 10.1039/d0dt03711g.
- 45 H. Xu, Y. Liao, Z. Gao, Y. Qing, Y. Wu and L. Xia, A branchlike Mo-doped Ni3S2 nanoforest as a high-efficiency and

durable catalyst for overall urea electrolysis, *J. Mater. Chem. A*, 2021, **9**, 3418–3426, DOI: 10.1039/d0ta09423d.

- 46 D. Yang, L. Cao, L. Feng, J. Huang and J. Wang, Controlled Synthesis of V-Doped Heterogeneous Ni<sub>3</sub>S<sub>2</sub>/NiS Nanorod Arrays as Efficient Hydrogen Evolution Electrocatalysts, *Langmuir*, 2020, 37, DOI: 10.1021/acs.langmuir.0c02943.
- 47 W. J. Dai, K. Ren, Y. A. Zhu, Y. Pan, J. Yu and T. Lu, Flowerlike CoNi<sub>2</sub>S<sub>4</sub>/Ni<sub>3</sub>S<sub>2</sub> nanosheet clusters on nickel foam as bifunctional electrocatalyst for overall water splitting, *J. Alloys Compd.*, 2020, **844**, 156252, DOI: 10.1016/ j.jallcom.2020.156252.
- 48 Y. Wu and H. He, Electrodeposited nickel-iron-carbonmolybdenum film as efficient bifunctional electrocatalyst for overall water splitting in alkaline solution, *Int. J. Hydrogen Energy*, 2018, **44**, 1336–1344, DOI: 10.1016/ j.ijhydene.2018.11.168.
- 49 T. T. Chen, R. Wang, L. K. Li, Z. J. Li and S. Q. Zang, MOFderived Co958/MoS2 embedded in tri-doped carbon hybrids for efficient electrocatalytic hydrogen evolution, *J. Energy Chem.*, 2019, 44, 90–96, DOI: 10.1016/ j.jechem.2019.09.018.
- 50 R. Nivetha and A. N. Grace, Manganese and zinc ferrite based graphene nanocomposites for electrochemical hydrogen evolution reaction, *J. Alloys Compd.*, 2019, **796**, 185–195, DOI: 10.1016/j.jallcom.2019.05.021.
- 51 Y. S. Park, W.-S. Choi, M. J. Jang, J. H. Lee, S. Park, H. Jin, M. H. Seo, K.-H. Lee, Y. Yin, Y. Kim, J. Yang and S. M. Choi, Three-Dimensional Dendritic Cu-Co-P Electrode by One-Step Electrodeposition on a Hydrogen Bubble Template for Hydrogen Evolution Reaction, ACS Sustainable Chem. Eng., 2019, 7, 10734–10741, DOI: 10.1021/acssuschemeng.9b01426.
- 52 K. Zhang, W. Xiao, J. Li, J. Liu and C. Yan, Two-step Preparation of Porous Nickel-sulfur Electrode for Hydrogen Evolution in Alkaline Water Electrolysis, *Electrochim. Acta*, 2017, 228, 422–427, DOI: 10.1016/j.electacta.2017.01.105.
- 53 Y. Niu, X. Qian, C. Xu, H. Liu, W. Wu and L. Hou, Cu-Ni-CoSex quaternary porous nanocubes as enhanced Pt-free electrocatalysts for highly efficient dye-sensitized solar cells and hydrogen evolution in alkaline medium, *Chem. Eng. J.*, 2019, 357, 11–20, DOI: 10.1016/j.cej.2018.09.116.
- 54 Y. Tian, J. Yu, H. Zhang, C. Wang, M. Zhang, Z. Lin and J. Wang, 3D porous Ni-Co-P nanosheets on carbon fiber cloth for efficient hydrogen evolution reaction, *Electrochim. Acta*, 2019, 300, 217–224, DOI: 10.1016/j.electacta.2019.01.101.